

OUTSIDE-SOURCE REFERENCE MATERIALS

	Page		Page
ACIRS: Australian Coal Industry Reference Samples, Australia	3	IMI: IMI Wolverhampton Metal, UK	37
AR: Alpha Resources Inc., USA	3	IA: Industrial Analytical, South Africa	38
ARCELORMITTAL: ArcelorMittal Maizières Research SA (formerly IRSID), France	4	IPT: Instituto de Pesquisas Tecnológicas, Brazil	39
BAM: Bundesanstalt für Materialforschung und -prüfung, Germany	6	IRMM: Institute for Reference Materials and Measurements (formerly BCR), Belgium	40
BNF: BNF-Fulmer, UK	12	JK: Jernkontoret / Swerea KIMAB, Sweden	41
BS: Brammer Standard Company Inc., USA	16	LUCIDEON: (formerly Ceram Research), UK	44
CANMET: Canada Centre for Mineral and Energy Technology, Canada	20	MBH: MBH Analytical Ltd, UK	45
CTIF: Centre Technique des Industries de la Fonderie, France	24	NILAB: Nordisk Industrielaboratorium AB, Sweden	28
D-LAB: Degerfors Laboratorium AB, Sweden	28	NIST: National Institute of Standards and Technology, USA	48
DL: Dillinger Laboratory, Germany	29	SABS: South African Bureau of Standards, South Africa	54
FLX: FluXana GmbH & Co. KG, Germany	33	SGT: Society of Glass Technology, UK	36
HSL: Health and Safety Laboratory, UK	37	SPL: SPL-LABMAT s.r.o., Czech Republic	56
ICRM: Institute for Certified Reference Materials, Russia	34	SUS: SUS, Germany	57
IGS: Institute of Geological Sciences/British Geological Survey, UK	36	VASKUT: Vasipari Kutato es Fejlesztő Vallalat, Hungary	59

Distributed by

BUREAU OF ANALYSED SAMPLES LTD



CATALOGUE NO. 866

MARCH 2018



PRODUCT INDEX

FERROUS METALS

	Page
(a) Steels	
Alloy Steel CRMs (BAM)	6
Alloy Steel CRMs (ARCELORMITTAL)	4
Alloy Steel CRMs (JK)	41
Alloy Steel CRMs (NILAB)	28
Calcium Treated Steel RMs (BS)	16
C, S, N, H & O in Steel RMs (BS)	16
C, S, N & O in Steel RMs (JK)	42
High Alloyed Steel CRMs (ICRM)	34
High Temperature and Specialty Steel CRMs (NIST) ..	49
High Manganese Steel RMs (BS)	16
Highly Alloyed Steel CRMs (BAM)	7
Highly Alloyed Steel CRM (CTIF)	24
Highly Alloyed Steel CRMs (ARCELORMITTAL)	4
Highly Alloyed Steel CRMs (JK)	41
Highly Alloyed Steel CRMs (VASKUT)	59
H, O & N in Steel RMs (AR)	3
Low Alloy Steel CRMs (NIST)	48
Low Alloy Steel CRMs (VASKUT)	59
Special Alloy CRMs (BAM)	7
Special Alloy CRM (JK)	41
Stainless and High Temperature Steel RMs (BS)	17
Tool Steel CRMs (NIST)	49
Unalloyed Steel CRMs (BAM)	6
Unalloyed Steel CRMs (ARCELORMITTAL)	4
Unalloyed Steel CRM (JK)	41
Unalloyed Steel CRMs (VASKUT)	59
Steel SUS (SUS)	57
(b) Cast Irons	
Austenitic (Ni-resist) Iron RMs (CTIF)	25
Cast Iron CRMs (BAM)	7
Cast Iron CRMs (CTIF)	24
Cast Iron CRMs (IPT)	39
Cast Iron CRMs (SPL)	56
Chromium Iron RMs (CTIF)	25
Cu-Ni-Cr-Mo Iron RMs (CTIF)	25
Electrolytic Iron CRM (NIST)	48
Iron Powder (JK)	42
Iron SUS (SUS)	57
Low Alloy Iron RMs (CTIF)	24
White Cast & Ductile Iron CRMs (NIST)	49
(c) Ferro-Alloys	
Ferro-Alloy CRMs (BAM)	8
Ferro-Alloy CRMs (D-Lab)	28
Ferro-Alloy RMs (DL)	29
Ferro-Alloy CRMs (ICRM)	35
Ferro-Alloy CRMs (ARCELORMITTAL)	5
Ferro-Alloy CRM (JK)	42
Ferro-Alloy CRMs (SABS)	55
Ferro-Alloy Slag RMs (IA)	38
Ferro-Chrome Slag CRM (SABS)	55

NON-FERROUS METALS

Aluminium Alloy CRMs (BAM)	10
Aluminium Alloy RMs (IMI)	37

NON-FERROUS METALS (cont.)

	Page
Aluminium Alloy RMs (MBH)	46
Aluminium and Aluminium Alloy SUS (SUS)	57
Brass RMs (CTIF)	26
Bronze RMs (CTIF)	27
Cobalt Base RMs (BS)	19
Cobalt Alloy RMs (MBH)	47
Cobalt and Cobalt Alloy SUS (SUS)	57
Copper Anode CRMs (CANMET)	23
Copper CRMs (IRMM)	40
Copper Base Alloy RMs (BS)	19
Copper Base RMs (BNF)	12/15
Copper Base CRMs (IPT)	39
Copper and Copper Alloy CRMs (BAM)	9
Copper and Copper Alloy SUS (SUS)	57
Cupro-Beryllium Cobalt RMs (CTIF)	27
Cupro-Nickel RM (CTIF)	27
Gold Alloy CRMs (BAM)	10
H, O & N in Titanium RMs (AR)	3
Lead Alloy CRMs (BAM)	10
Lead Base RM (BNF)	15
Lead Base RMs (MBH)	47
Lead CRMs, (IRMM)	40
Lead and Lead Alloy SUS (SUS)	58
Magnesium Alloy RMs (MBH)	46
Magnesium and Magnesium Alloy SUS (SUS)	58
Nickel Base Alloy RMs (BNF)	14/15
Nickel Base Alloy RMs (BS)	18
Nickel and Nickel Alloy SUS (SUS)	58
Silicon Metal CRMs (IPT)	39
Special Alloy CRMs (CTIF)	24
Tin base RMs (MBH)	46
Tin White Metal RMs (MBH)	47
Zinc-Aluminium Foundry Alloy CRMs (CANMET)	23
Zinc and Zinc Alloy CRMs (IRMM)	40
Zinc and Zinc Alloy RMs (MBH)	45
Zinc and Zinc Alloy SUS (SUS)	58

ORES, ROCKS AND MINERALS

Andalusite CRM (SABS)	55
Coal and Coal Fly Ash RMs (ACIRS)	3
Coal CRMs (SABS)	54
Cover Powder and Rutile RMs (DL)	31
Fluorspar CRMs (JK)	43
Fluorspar CRMs (SABS)	54
Fly Ash CRM (JK)	43
Iron Ore CRMs (JK)	42
Iron Ore RMs (DL)	32
Mineral CRMs (IPT)	39
Mineral RMs (DL)	31
Mineral, Concentrate and Ore CRMs (ARCELORMITTAL)	5
Ore and Concentrate CRMs (NIST)	50
Ore and Concentrate RMs (IGS)	36
Ore Concentrate and Tailing RMs (IA)	38
Ore Concentrate CRMs (Cu, Pb, Zn) (CANMET)	21

ORES, ROCKS AND MINERALS (cont.)

	Page
Ore CRMs (Base Metal) (CANMET)	20
Ore CRMs (Cr, Fe Mn & Zr) (SABS)	54
Ore CRMs (Au & Pt) (SABS)	55
Ore CRMs (Fe & Mn) (BAM)	8
Ore CRMs (Mn) (SABS)	54
Ore CRMs (Noble Metal) (CANMET)	20
Ore CRMs (Sulphide Mill Tailings) (CANMET)	21
Rare Earth Elements with Zr & Nb CRMs (CANMET)	23
Rock and Mineral CRMs (CANMET)	22/23
Rock CRMs (Igneous) (SABS)	54
Rock CRM (Phosphate) (SABS)	54
Rock and Mineral CRMs (NIST)	51
Rock, Mineral and Sediment CRMs (SABS)	55
Siliceous RMs (LUCIDEON)	44
Soil and Till RMs (CANMET)	22
Zircon Bearing and Basic RMs (LUCIDEON)	44

ENVIRONMENTAL MATERIALS

Dust CRMs (Ferrous) (ARCELORMITTAL)	5
Environmental CRMs (NIST)	53
Respirable α -quartz RM (HSL)	37
PGE in Auto Catalyst (BAM)	11
Welding Fume RMs (HSL)	37

REFRACTORIES, SLAGS AND CEMENTS

Basic Slag CRMs (BAM)	8
Blast Furnace and Basic Slag CRMs (ARCELORMITTAL)	5
Blast Furnace and Steelmaking Slag CRMs (JK)	43
Cement CRMs (FluXana)	33
Cement CRMs (NIST)	51
Cement RMs (DL)	32
Ceramic CRMs (BAM)	8
Ceramic (High Oxygen) SUS (JK)	43
Dust and Slag RMs (DL)	30
Glass and Glass Sand CRMs (SGT)	36
Industrial Fly Ash CRMs (JK)	43
Refractory CRMs (IPT)	39
Refractory CRMs (ARCELORMITTAL)	5
Refractory CRMs (NIST)	51
Refractory RMs (DL)	30
Slag, flux and Refractory CRMs (ICRM)	34

BIOLOGICAL MATERIALS

Biological CRMs (NIST)	52
------------------------------	----

OTHERS

Depth Profile SUS (JK)	43
Glass CRM containing hexavalent chromium (BAM)	11
Glass CRMs (FluXana)	33
High Purity Substances (BAM)	11
Silicon Nitride Powder CRM (BAM)	11
Tungsten Metal Powder CRM (BAM)	11
Vanadium Pentoxide CRM (SABS)	55
XRF Monitor Sample (FluXana)	33

INTRODUCTION

For over eighty years Bureau of Analysed Samples Ltd (BAS) has been preparing British Chemical Samples, now known as BCS Certified Reference Materials (CRMs) for the metallurgical industries. Full particulars of all BAS-produced materials are given in a separate catalogue.

When the UK joined the EEC in 1973 BAS was invited to co-operate with BAM in Germany and IRSID in France in the production of CRMs for the iron and steel industry on a European basis and this European Producers Group has been augmented by the inclusion of the Nordic CRM Working Group: this work is now under the auspices of the European Committee for Iron and Steel Standardization (ECISS). These EURONORM Certified Reference Materials (ECRMs) are normally analysed by approximately twenty laboratories from countries in the European Economic Area (EEA) and are issued with a Certificate of Analysis approved by the participating laboratories and the producing organizations. These ECRMs are indicated by an asterisk in this list. Although BAS is no longer a part of the ECRM Producers Group, all ECRMs (prepared by BAM, IRSID (now ARCELORMITTAL), CTIF and Jernkontoret) are available from BAS. Data regarding the BAS-produced ECRMs are given in the BAS Certified Reference Materials Catalogue, whilst the data re BAM, ARCELORMITTAL, CTIF and Jernkontoret - produced ECRMs are given in this catalogue.

Further details of ECRMs, including their method of preparation, certification and supply and the use of the statistical information given on ECRM certificates are given in Technical Reports CEN/TR 10317:2014 (formerly ECISS Information Circular No. 1) and CEN/TR 10350:2013 (formerly ECISS Information Circular No. 5) which are available in the UK from the BSI, 389 Chiswick High Road, London W4 4AL.

In September 1992, the BNF – Fulmer organisation was closed down. BAS purchased their Reference Materials business, including the considerable stock of BNF samples, and is continuing the business as before. Thus, BAS is now the primary source of BNF copper, nickel and lead base Reference Materials. Replacement samples are being produced by BAS in order to maintain continuity of supply of these samples: (see the latest BAS Catalogue for details of such samples already produced by BAS).

In order to assist our customers to obtain complementary Reference Materials from other reputable producers, BAS is now holding a stock, and many of the Reference Materials detailed in this catalogue are immediately available, with delivery of non-stock items usually achieved within two to three weeks.

In this catalogue Reference Materials which are supplied with a Certificate of Analysis giving the information specified in ISO Guide 31 "Contents of Certificates of Reference Materials" are referred to as "Certified Reference Materials" and the remainder as "Reference Materials", in accordance with the definitions given in ISO Guide 30 "Terms and definitions used in connection with Reference Materials". (ISO Guides are available from Case Postale 56, CH-1211 Geneva 20, Switzerland).

The Certificate accompanying each CRM, or Analysis Report/Information Sheet accompanying each RM, should be consulted to obtain the accurate analysis of each sample, since in some cases the figures shown in this catalogue may differ slightly from those given on the Certificate or Analysis Report/Information Sheet.

GENERAL INFORMATION

Our website, at www.basrid.co.uk, is continuously being improved and now includes a database of BAS and "Outside Source" CRMs and RMs, which is simultaneously searchable for up to six constituents.

QUALITY ASSURANCE

Bureau of Analysed Samples Ltd, is very pleased to advise customers that in November 1994 its Quality System was formally approved and recognised by the award of a Certificate of Registration to the Quality Standard BS EN ISO 9002:1994 for the production and supply of CRMs, RMs and SUS. This certificate has now been revalidated to the new standard BS EN ISO 9001:2015. Furthermore, BAS was accredited, in June 2006, to the International Guide, ISO Guide 34 (General Requirements for the Competence of Reference Material Producers) and the accreditation has since been updated to the Standard ISO 17034.

Please note that, whilst BAS is accredited to ISO 17034, only three of the Producers detailed in this catalogue (Brammer Standard Company, Inc., Bundesanstalt für Materialforschung und -prüfung and Community Bureau of Reference / Institute for Reference Materials and Measurements) are so accredited. The CRM/RMs prepared by the other producers in this catalogue will not have been produced under ISO 17034 accreditation.

Australian Coal Industry Reference Samples (ACIRS), Australia

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only

Coal Reference Materials (Finely divided material – unit weights as shown in table)

ACIRS No.	Description	Unit Weight	Ash	Volatile Matter	Total C	H	N	P	C as CO	Cl	F	Hg	Se	Total S	Pyritic S	Sulphate S	Hardgrove Grindability Index	Gross Calorific Value MJ/kg	Relative Density
AD-S1A	Coal	250g	...	...	...	...	...	...	...	...	...	...	...	0.42	...	...	...	...	...
AD-S1C	Coal	250g	...	...	...	...	...	...	...	...	...	...	...	1.46	...	...	...	...	...
G7	Coal	120g	9.71	20.32	80.19	4.45	1.82	0.032	...	0.051	0.0089	0.0000021	(0.00007)	0.591	0.040	0.011	...	32.641	1.371
H6	Coal	4 x 1kg	...	...	...	...	...	...	...	...	...	...	...	...	...	...	32, 44, 61 & 87	...	...
M1	Coal	125g	18.68	32.85	67.40	4.73	1.34	0.098	0.037	(0.014)	0.0149	0.0000120	...	2.392	(0.07)	(0.21)	...	28.356	1.417

Coal Fly Ash Reference Material (Units of 80g)

ACIRS No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	P ₂ O ₅	TiO ₂	Mn ₃ O ₄	BaO	SrO	SO ₃	Co	Cr	Cu	Ni	Pb	V	Zn
A-1	Coal Fly Ash	44.1	28.9	14.6	6.05	1.25	0.43	0.46	1.26	1.56	0.22	0.183	0.16	0.32	(0.0043)	(0.0058)	(0.0099)	(0.0047)	(0.0047)	(0.0176)	(0.0090)

Values are also given for Ash Fusibility Reducing Temperatures:- Deformation 1257°C; Spherical 1287°C; Hemispherical 1309°C; Flow 1367°C
 Ash Fusibility Oxidising Temperatures:- Deformation 1349°C; Spherical 1383°C; Hemispherical 1398°C; Flow 1429°C

ALPHA RESOURCES Inc. (AR), USA

CHEMICAL COMPOSITION (nominal mass content in %)

Oxygen & Nitrogen in Steel Reference Materials (units as shown)

AR No.	Units	Oxygen	Nitrogen
644	100 x 1g pins	0.0003	0.0149
645	"	0.0035	0.0088
646	"	0.0030	0.073
654	100 x 0.5g pins	0.0044	0.0536
655	"	0.0022	0.395
659	"	0.0128	0.0055
661	"	0.0008	0.0091
668	"	0.0010	0.0023
1647	100 x 1g pins	0.0028	0.144
1648	"	0.0099	0.0060
1650	"	0.0146	0.0107
1651	"	0.0030	0.0202
1652	"	0.0039	0.054
1653	"	0.0006	0.0020

Hydrogen in Steel Reference Materials (units as shown)

AR No.	Units	Hydrogen
546	100 x 1g pins	0.000080
555	"	0.00023
556	"	0.00045
558	"	0.00074

Hydrogen, Oxygen & Nitrogen in Titanium Reference Materials (units as shown)

AR No.	Units	Hydrogen	Oxygen	Nitrogen
637	100 x 0.1g pins	0.0013	0.144	0.0092
641	"	0.0041	0.198	0.0304
650	"	0.0071	0.089	0.0099
651	"	0.0026	0.125	0.0060

The above constitutes a selection of Alpha Resource samples. Additional samples are available from both producers, and information on these will be provided on request.

ARCELORMITTAL MAIZIÈRES RESEARCH SA (formerly IRSID), France
CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Unalloyed Steel Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	C	Si	Mn	P	S	Cr	Ni	Al Total	Co	Cu	Pb	Sn
ECRM 012-1	0.082	...	...	0.083	0.255	...	...	...	...	...	...	...
ECRM 021-1	0.243	0.271	1.288	0.0121	0.0087	0.125	0.255	...	...	0.167	...	...
ECRM 022-1	0.115	...	0.797	0.057	0.296	...	...	...	...	...	...	...
ECRM 023-1	0.331	0.264	0.667	0.021	0.0156	...	...	...	...	...	0.280	...
ECRM 024-1	0.104	0.139	0.726	0.0155	0.235	...	...	...	...	...	0.287	...
*ECRM 081-1	0.099	0.105	0.605	0.0129	0.014	...	0.042	0.023	0.017	0.026	...	0.0039

Alloy Steel Certified Reference Materials (Finely divided material – units of 100g; 190-1 also available as 35mm x 35mm x 30mm blocks)

AMMZ/IRSID No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	N	V	W
ECRM 102-1	0.389	0.281	0.367	0.012	0.006	0.261	1.20	4.40	...	...	0.169	...	...	...
ECRM 106-2	0.153	0.238	0.727	...	...	1.030	0.054	1.430	...	...	0.078	...	...	...
ECRM 107-1	0.407	0.286	0.611	...	...	1.443	0.323	0.191	0.345	...	0.108	...	...	...
ECRM 108-1	0.384	0.340	0.690	0.0176	0.017	2.92	0.538	0.215	...	...	0.118	...	...	...
ECRM 112-1	0.348	1.00	0.191	...	...	4.78	1.21	0.234	...	...	0.115	...	0.604	1.78
ECRM 113-1	0.680	0.249	0.586	0.013	0.006	0.816	0.413	1.744	...	...	0.146	...	...	...
*ECRM 188-1	1.094	...	...	...	0.0113	1.538	...	...	...	...	...	...	...	...
*ECRM 190-1	0.395	0.278	1.28	0.0112	0.0044	2.18	0.410	0.934	...	0.034	...	0.0096	...	...

Alloy Steel Certified Reference Materials (continued)

AMMZ/IRSID No.	Bi	Cd	Ga	Hg	Nb	Pb	Sb	Se	Te	Tl	Zn
*ECRM 188-1	<0.00002	<0.00005	0.00251	<0.00001	0.00013	<0.0001	0.00048	<0.0002	<0.0002	<0.00002	<0.0003

Highly Alloyed Steel Certified Reference Materials (Finely divided material – units of 100g; ECRM 269-1 also available as 35mm diameter x 25mm discs)

AMMZ/IRSID No.	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	N	Nb	Sn	Ti	V	W	Ca	Zn
ECRM 201-1	0.291	0.843	0.363	...	...	12.33	0.050	0.202	...	...	0.099	...	...	0.0193	...	0.020	...	0.0018	0.0005
*ECRM 269-1	0.0499	0.441	1.262	0.0313	0.0010	18.150	0.397	8.044	0.0061	0.1116	0.366	0.0460	0.0242	0.0099	0.0006	0.0991	0.0306	...	...
*ECRM 279-2	0.0885	0.5160	0.2584	...	...	15.642	...	1.603	...	...	0.1067	...	...	...	...	...	...	...	...
*ECRM 282-1	0.086	0.734	1.64	0.019	0.0042	16.72	2.19	10.86	...	...	0.109	...	...	...	0.488	0.031	...	...	...

* Denotes Full EURONORM-Certified Reference Material

ARCELORMITTAL MAIZIÈRES RESEARCH SA (formerly IRSID), France

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Ferro-Alloy Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	C	Si	Mn	P	S	Cr	Al	N	Ti
ECRM 503-1	Ferro-Manganese	0.700	0.865	80.8	0.069	<i>0.009</i>	...	...	...	...
ECRM 507-1	Ferro-Chromium	5.43	1.20	0.270	0.018	...	70.27	...	0.050	...
ECRM 509-1	Ferro-Chromium	0.013	0.229	...	0.018	...	72.85	...	0.026	...
ECRM 510-1	Ferro-Titanium	0.058	4.65	...	<i>0.035</i>	...	...	<i>4.9</i>	<i>0.014</i>	26.95

Mineral, Concentrate and Ore Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	V	Cr	Ni	Co	C(T)	Zn	Fe (II)	Others
ECRM 601-1	Iron Ore	36.76	8.95	4.05	1.21	2.33	0.114	0.370	0.590	0.065	...	...	...	...	...	...	...	...	<i>8.8</i>	...
ECRM 603-1	Iron Ore	53.65	1.28	<i>0.91</i>	<i>0.2</i>	4.20	0.137	0.440	0.084	0.097	...	...	...	...	...	...	...	...	<i>0.3</i>	...
ECRM 604-1	Iron Ore	65.69	1.27	0.107	0.049	0.93	0.060	0.092	0.053	0.015	...	...	...	...	...	...	...	...	<i>0.5</i>	...
ECRM 606-1	Iron Ore	59.66	1.04	1.04	0.32	0.34	0.019	2.59	0.026	0.033	...	...	...	...	...	...	...	...	<i>0.1</i>	...
ECRM 607-1	Iron Ore	30.89	3.07	13.74	0.77	2.48	0.123	0.254	0.529	0.050	...	...	...	...	...	...	...	...	<i>5.95</i>	...
ECRM 608-1	Ferriferrous Marl	4.00	28.23	6.22	0.81	5.26	0.428	0.044	0.053	0.455	...	...	...	...	...	...	...	...	<i>1.85</i>	...
ECRM 611-1	Iron Ore Sinter	62.22	2.07	2.85	0.32	0.69	0.035	1.97	0.030	0.008	...	...	...	...	...	...	...	...	<i>13.84</i>	...
ECRM 612-1	Iron Ore Sinter	42.43	5.94	12.06	1.20	3.00	0.151	0.363	0.885	0.053	...	...	...	...	...	...	...	...	<i>9.19</i>	...
*ECRM 677-1	Iron Ore	51.54	11.78	0.038	0.012	0.32	0.013	0.016	0.0170	0.005	0.007	0.008	...	<i>0.002</i>	<i>0.0015</i>	<i>0.0006</i>	...	<i>0.002</i>	...	0.43 H₂O+
*ECRM 685-1	Pre-reduced Iron Ore	91.10	0.795	0.140	0.239	0.320	0.220	0.042	0.017	0.0031	0.077	0.042	0.144	...	0.018	0.013	1.49	...	<i>7.72</i>	80.80 Fe_m
*ECRM 691-1	Iron Ore	64.39	0.556	0.999	2.022	0.475	0.966	0.1734	0.0877	0.0632	0.0164	0.0504	0.0603	0.0095	0.0299	<i>(0.0216)</i>	0.307	0.0195	20.71	{ 0.0768 Cu 0.0008 Pb

Refractory Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	Fe	Si	Ca	Mg	Al	Ti	Cr	Mn	B	N	P	S	C(T)	H ₂ O	LOI
ECRM 702-1	Dolomite	0.440	1.04	21.48	12.37	0.21	0.013	<i><0.002</i>	0.098	...	...	0.024	<i>0.027</i>	<i>12.3</i>	0.5	45.6
*ECRM 778-1	High Carbon Magnesia	0.67	0.489	0.883	48.87	0.297	<i>0.008</i>	0.102	0.011	0.0012	...	<i>0.004</i>	...	14.00	...	15.38
*ECRM 780-1	Silicon Carbide	1.30	63.5	0.84	0.051	1.86	...	...	0.029	...	0.32	...	...	26.38	...	...

Slag and Dust Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	F	V	Cr	Ni	Zn	Cu	As	Pb	C(T)	Cl	Others
ECRM 802-1	Blast Furnace Slag	0.576	15.16	30.62	2.87	8.53	0.366	0.460	0.109	0.714	0.236	0.491	0.243	0.028	0.0053	...	0.0025	...	...	...	...	...	0.0245 B
ECRM 803-1	Blast Furnace Slag	0.613	17.01	30.93	2.44	6.98	0.301	0.552	0.118	0.767	...	...	...	...	...	...	...	...	...	...	...	...	...
ECRM 804-1	Basic Slag	11.92	2.59	36.88	0.88	0.407	0.152	1.48	7.67	0.127	...	...	...	0.460	...	...	...	...	...	...	...	...	...
ECRM 805-1	Basic Slag	14.87	3.10	34.96	1.12	0.326	0.205	1.59	7.07	0.092	...	...	...	0.514	...	...	...	...	...	...	...	...	...
ECRM 806-1	Basic Slag	17.89	5.48	32.97	1.82	0.477	0.302	4.60	0.982	0.110	...	...	...	0.288	...	...	...	...	...	...	...	...	...
*ECRM 876-1	Electric Furnace Dust	24.85	1.72	3.43	1.31	0.34	0.048	2.84	0.128	0.87	1.98	1.63	0.24	...	0.17	0.034	23.29	0.42	0.023	7.82	0.26	3.63	{ 0.13 Cd 0.094 Sn
*ECRM 880-1	Blast Furnace Dust	31.0	3.34	3.15	0.714	1.28	0.081	0.218	0.038	0.425	0.041	0.108	0.034	...	0.027	0.014	0.064	0.005	...	0.017	<i>37.77</i>	0.086	...

* Denotes Full EURONORM Certified Reference Materials

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND -PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Unalloyed Steel Certified Reference Materials (All finely divided materials - units of 100g, except 026-1, 026-2, 027-1, 028-1, and 029-1 which are 10mm dia. x 90mm rods and 098-1 which is in solid disc form 35mm dia. x 25mm: ECRM 035-2 also available as 40mm dia. x 20mm discs and ECRM 083-2 also available as 39mm dia. x 28mm discs)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol.)	Al (Total)	As	Co	Cu	N	Pb	Sn	Ti	V	Others
ECRM 026-1	1969	<i>0.44</i>	...	...	...	...	...	...	...	...	...	...	...	...	0.0053	...	...	...	...	0.0031 O
ECRM 026-2	1973	...	...	...	...	...	...	...	...	...	...	...	...	...	0.0042	...	...	...	...	0.0025 O
ECRM 027-1	1970	<i>0.05</i>	<i>0.003</i>	<i>0.4</i>	<i>0.03</i>	<i>0.03</i>	...	...	...	...	<i>0.001</i>	...	...	...	0.0157	...	...	...	...	0.0084 O
ECRM 028-1	1970	<i>0.1</i>	<i>0.002</i>	<i>0.3</i>	<i>0.06</i>	<i>0.03</i>	...	...	...	...	<i>0.001</i>	...	...	...	0.0029	...	...	...	...	0.0113 O
ECRM 029-1	1970	<i>0.05</i>	<i>0.003</i>	<i>0.3</i>	<i>0.03</i>	<i>0.03</i>	...	...	...	...	<i>0.001</i>	...	...	...	0.0083	...	...	...	...	0.0312 O
ECRM 030-4	1973	0.456	0.318	0.603	0.018	0.021	0.117	...	0.042	...	0.042	0.012	...	0.061	0.0051	...	0.0055	...	...	...
ECRM 031-3	1972	0.055	0.037	0.329	0.014	0.021	...	...	...	...	0.054	0.013	...	0.020	0.0050	...	...	...	...	...
ECRM 032-2	1968	0.271	0.282	0.556	0.0129	0.0254	<i>0.088</i>	...	<i>0.040</i>	...	...	0.020	...	0.085	0.0044	...	...	...	...	...
*ECRM 035-2	1998	1.277	0.216	0.305	0.0038	0.0111	0.0104	0.0056	0.0190	0.0177	0.0193	0.0017	...	0.0085	0.0230	...	...	0.0030	...	...
ECRM 036-1	1968	0.858	0.194	0.327	0.0074	0.0095	<i>0.091</i>	...	<i>0.058</i>	...	<i>0.015</i>	0.0233	...	0.065	0.0100	...	<i>0.006</i>	...	<i>0.019</i>	...
ECRM 042-1	1972	0.108	0.037	0.666	0.0057	0.024	0.016	...	0.029	...	0.010	...	...	0.041	0.0078	...	...	...	...	0.0054 Nb
*ECRM 077-3	2017	0.1650	...	...	...	0.01623	...	...	...	...	...	...	...	...	0.00852	...	...	...	...	...
*ECRM 079-2	1989	0.596	0.247	0.743	0.0234	0.192	0.0382	...	0.022	...	0.021	0.004	...	0.046	0.0074	...	0.0037	...	...	...
*ECRM 082-1	1976	0.415	0.235	0.769	0.013	0.030	0.018	...	0.027	...	0.032	<i>0.029</i>	...	0.025	<i>0.0047</i>	0.149	...	...	...	0.030 Te
*ECRM 083-1	2009	0.0262	...	0.289	0.0076	0.0100	<i>0.013</i>	...	0.014	...	<i>0.004</i>	<i>0.004</i>	...	0.016	0.00189	...	...	...	...	...
*ECRM 083-2	2017	0.0315	0.00747	0.2160	0.0106	0.00561	0.0219	...	0.0116	...	0.0784	0.00177	0.00236	0.0127	0.00157	<i>(0.0002)</i>	...	<i>(0.003)</i>	<i>(0.00053)</i>	0.00439 Zn
*ECRM 098-1	1993	0.00051	0.00008	0.00048	<i>0.00006</i>	0.00031	0.00571	0.00085	...	...	...	...	...	...	0.00024	...	...	...	...	...

Alloy Steel Certified Reference Materials (Finely divided material - units of 100g; 129-3, 179-2, 187-2, 192-1, 193-1, 194-1 and 194-2 also available as 38-39mm dia. x 20-35mm discs)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu	N	Sn	Ti	V	Others
ECRM 126-1	1963	0.841	<i>0.24</i>	1.817	0.009	0.005	0.317	...	<i>0.038</i>	...	...	...	...	<i>0.098</i>	...	...	...	0.143	...
ECRM 128-1	1972	0.085	0.949	0.839	0.007	0.007	0.108	...	0.046	0.286	...	...	...	0.055	<i>0.0024</i>	...	0.890	<i>0.008</i>	...
*ECRM 129-3	2008	0.3684	0.2087	0.371	0.0110	0.0165	1.702	0.206	1.022	1.016	0.0049	<i>0.00014</i>	0.0148	0.0804	0.0046	0.0067	0.030	<i>0.0045</i>	0.00059 Sb
ECRM 130-1	1968	0.546	0.313	1.593	0.0209	0.0158	<i>0.032</i>	...	<i>0.031</i>	0.0037	0.0167	...	...	0.072	0.0093	...	...	<i>0.003</i>	0.0019 Al (Acid Sol.)
*ECRM 179-2	1990	0.598	0.579	0.539	0.0267	<i>0.0006</i>	1.08	0.070	0.078	...	...	...	<i>0.0153</i>	0.111	0.0068	...	<i>0.0014</i>	0.188	{ 1.87 W, <0.00003 Bi, <0.00003 Cd, 0.00129 Ga, 0.00144 Nb, 0.00013 Pb, 0.00175 Sb, <0.0002 Te, 0.00023 Zn }
*ECRM 180-1	1973	0.197	0.362	1.286	0.0174	0.0249	1.250	...	0.096	...	0.030	...	...	0.115	0.0068	...	...	...	...
*ECRM 181-1	1973	0.590	1.054	1.047	0.018	0.035	0.126	...	0.070	0.022	<i>0.026</i>	...	...	0.174	0.0068	<i>0.015</i>	...	...	...
*ECRM 182-1	1993	0.790	0.368	0.389	0.0076	0.011	0.591	...	0.152	0.020	...	...	...	0.141	0.0102	...	...	0.177	0.0039 Pb, 0.0042 Sb, 0.0015 Zn
*ECRM 183-1	1973	0.083	0.421	0.354	0.089	0.031	0.670	...	0.073	0.027	...	...	...	0.445	0.0064	...	...	...	...
*ECRM 187-1	1986	0.195	0.026	1.354	0.014	0.025	1.186	0.035	0.096	0.046	0.018	0.0004	0.014	0.161	0.014	0.011	...	...	...
*ECRM 187-2	2011	0.2038	0.2111	1.257	0.0066	0.0300	1.132	<i>0.0623</i>	0.1755	0.0223	0.0057	0.00048	0.0112	0.1288	0.0105	0.0237	...	0.0122	<i>0.0018 Sb</i>
*ECRM 191-2	2006	0.0043	3.267	0.1334	0.0087	0.0029	0.0314	0.0020	0.0224	0.985	0.0018	...	...	0.0165	0.00105	0.0050	0.0024	...	...
*ECRM 192-1	1995	0.188	0.219	1.377	0.0029	0.0010	0.072	0.482	0.755	0.0308	<i>0.003</i>	<i>0.0002</i>	0.0055	0.045	0.0118	<i>0.003</i>	<i>0.001</i>	<i>0.003</i>	0.029 Al (Acid Sol.)
*ECRM 193-1	1990	0.139	0.404	0.972	0.0063	0.0086	0.182	0.347	1.178	0.0257	0.0062	<i>0.0002</i>	0.0073	0.598	0.0108	...	<i>0.0013</i>	<i>0.0019</i>	0.0232 Nb
*ECRM 194-1	2015	0.1532	0.431	1.188	0.0097	0.00059	0.733	0.2857	0.3417	0.0837	0.0042	0.0020	...	0.0751	0.0115	...	...	0.0243	0.0026 Ca
*ECRM 194-2	2015	0.1694	0.2974	1.282	0.0137	0.00049	0.760	0.402	0.3316	0.0669	0.00208	0.00155	0.00328	0.0313	0.00319	<i>0.0004</i>	0.00322	0.00161	0.0290 Nb, 0.0003 Sb

* Denotes Full EURONORM-Certified Reference Materials

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND -PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Highly Alloyed Steel Certified Reference Materials (Finely divided material – units of 100g; 284-3, 288-1, 289-1, 290-1 and 291-1 also available as 36-38mm dia. x 25-35mm discs; 271-1 as a 37mm dia. x 25mm disc, 294-1 as a 38mm dia. x 20mm disc and both 297-1 and 299-1 as a 38mm dia. x 25mm disc)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Sn	Ti	V	W	Others
ECRM 226-1	1967	0.416	0.514	0.434	0.0207	0.0094	13.67	0.024	0.139	...	0.026	...	0.025	...	0.0362	...	...	0.022	...	...
ECRM 227-1	1994	0.950	0.272	0.236	0.016	0.022	4.25	2.64	0.114	...	...	...	...	0.124	0.040	0.0251	...	2.44	3.03	0.0035 Sb
*ECRM 231-2	2002	0.0140	0.368	1.263	0.0179	0.0250	18.07	0.301	10.105	0.0032	0.0048	0.0020	0.0402	0.0941	0.0444	0.0043	0.0007	0.0708	0.0141	0.00074 Ca 0.0011 Sb
ECRM 235-1	1972	0.912	0.094	12.73	0.045	0.0072	0.354	0.032	...	...	...	...	...	0.073	0.020	...	...	...	...	...
ECRM 237-1	1973	0.068	0.482	1.443	0.032	0.012	17.24	0.306	10.32	...	...	...	0.221	0.123	0.035	...	...	0.057	...	0.660 Nb
*ECRM 271-1	2007	0.3698	0.923	0.437	0.0120	0.00045	5.002	1.247	0.1552	0.0234	0.0057	...	0.0139	0.1371	0.0137	0.0084	0.0020	0.850	0.0054	0.0009 Ca 0.0020 O
*ECRM 278-1	1973	0.903	0.336	0.405	0.0154	0.0052	18.11	1.040	0.236	...	...	...	...	0.077	...	...	...	0.077	...	...
*ECRM 283-1	1985	1.219	0.345	0.217	0.022	0.029	4.15	3.41	...	0.010	...	0.0003	10.27	...	0.033	...	...	3.28	9.66	...
*ECRM 284-2	2000	0.0201	0.537	1.745	0.0258	0.0237	16.811	2.111	10.72	0.0027	0.0063	0.0026	0.0525	0.1831	0.0151	0.0047	0.191	0.0425	...	0.0099 O
*ECRM 284-3	2016	0.0025	0.0442	0.0615	0.0049	0.0066	17.37	2.236	12.09	0.002	0.00131	0.00020	0.0366	0.0105	0.0418	0.00074	0.0050	0.005	0.0039	...
*ECRM 286-1	1985	0.100	...	1.92	0.026	0.280	18.13	0.329	8.54	0.0023	...	0.0003	0.150	...	0.043	0.0084	...	...	...	0.0014 Sb
*ECRM 288-1	1986	2.08	0.260	0.292	0.024	0.0012	12.00	0.103	0.298	0.012	0.006	...	0.018	0.060	0.0151	0.0043	0.020	0.055	0.68	...
*ECRM 289-1	1990	0.0489	0.531	1.016	0.0114	0.0027	14.63	1.102	24.68	0.199	0.006	0.0044	0.065	...	...	0.111	2.01	0.260	...	...
*ECRM 290-1	1990	0.911	0.072	0.244	0.0160	0.0160	4.18	4.83	0.329	...	...	...	5.12	0.081	0.0325	...	...	1.91	6.27	...
*ECRM 291-1	1990	0.903	0.907	0.808	0.0168	0.0087	17.10	2.10	0.563	0.0030	...	...	0.0233	0.0711	0.1142	...	...	0.388	...	...
*ECRM 294-1	2005	0.0657	0.283	18.68	0.0271	0.00031	17.98	0.0861	0.429	0.001	0.0037	<0.0005	0.0288	0.0242	0.566	0.001	<0.002	0.0694	<0.004	...
*ECRM 297-1	2005	0.0223	0.344	0.897	0.0135	0.0101	18.37	0.290	12.33	0.0195	0.0040	1.146	0.0413	0.204	0.0152	...	0.0072	0.535	0.006	...
*ECRM 299-1	2009	0.0154	0.299	0.2678	0.0152	0.00022	22.32	0.0186	0.172	5.33	0.0054	0.0002	0.0187	0.0382	0.0198	0.008	0.1289	0.0329	0.0002	0.1775 Zr

Also available: BAM Steel-H1, highly alloyed steel, with a certified hydrogen content of **0.9725** mg/kg (100 x 1g pins)

Special Alloy Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	N	Nb	V	W	Zr	Ta	Fe
ECRM 326-1	1972	0.092	1.46	0.406	0.0093	0.0028	16.37	0.025	61.16	0.79	0.223	0.027	0.036	...	0.024	...	0.129	...	...
ECRM 327-2	1972	0.152	2.052	1.289	0.0228	0.0046	24.35	0.174	19.72	0.070	0.159	0.060	0.059	...	0.044	...	...	...	...
ECRM 328-1	1973	0.390	0.629	1.395	0.005	0.003	20.54	4.41	20.38	0.070	41.65	0.013	0.027	3.61	...	4.16	...	0.18	2.40

Cast Iron Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Cu	N	Ti	V	Mg
*ECRM 428-2	1998	2.747	1.752	0.750	0.0691	0.1105	0.0366	0.0014	0.0358	...	0.0156	0.0996	...	0.0311	0.0120	...
*ECRM 476-3	1996	3.390	1.813	0.987	0.0908	0.0493	0.0648	...	0.0549	...	0.0145	0.2445	0.0038	0.0222	0.0115	...
*ECRM 478-2	1996	4.003	2.411	0.321	0.202	0.0460	0.251	...	0.151	...	0.0018	0.1276	0.0023	0.0328	0.0113	...
*ECRM 479-1	1978	2.86	2.02	0.136	0.076	0.089	1.00	0.196	1.012	0.014	...	...	...	...	...	...
*ECRM 480-1	1988	3.03	2.41	0.151	0.0021	0.0086	...	...	0.483	0.016	...	...	...	...	...	0.017

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND -PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Ferro-Alloy Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Ni	Al	B	Cu	Pb	N	Ti	V	Ca	Mg	Fe
*ECRM 502-2	2004	6.94	<i>0.10</i>	77.87	0.148	<i>0.002</i>	0.0265	0.0384	...	<i>0.0003</i>	0.0370	0.0179	<i>0.02</i>	0.0034	...	...	...	<i>14.6</i>
ECRM 529-1	1975	0.10	91.11	0.04	0.013	...	...	...	0.86	...	...	...	...	0.09	...	0.46	0.04	6.15
*ECRM 591-1	1996	0.141	0.847	0.307	0.0299	0.0153	...	0.0141	3.19	...	0.0596	...	...	<i>0.044</i>	79.72	...	...	14.59

* Denotes Full EURONORM-Certified Reference Materials

Ore Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	Description	Fe	SiO ₂	Al ₂ O ₃	TiO ₂	CaO	MgO	Mn	P	S	Na ₂ O	K ₂ O	As	Ba	CO ₂	H ₂ O
ECRM 630-1	1969	Bomi-Hill Concentrate	65.63	5.88	0.88	0.066	0.10	0.47	0.060	0.043	0.032	...	...	...	...	...	...
ECRM 631-1	1969	Venezuela Iron Ore	61.09	3.20	1.06	0.109	0.75	0.54	0.044	0.114	0.033	<i>0.04</i>	<i>0.04</i>	...	...	...	...
ECRM 633-1	1967	Manganese Ore	1.64	10.39	1.64	0.079	2.02	0.58	47.85	0.170	0.227	...	...	<i>0.0040</i>	1.13	<i>3.48</i>	<i>7.11</i>

Iron Ore Certified Reference Materials (Finely divided material – units of 100g; 686-1 supplied as 2 x 50g)

BAM No.	Cert. Date	Description	Fe	Si	Al	Ti	Ca	Mg	Mn	P	S	Na	K	Zn	Cl	Co	Cr	Cu	Ni	Others
*ECRM 680-1	1977	Purple Ore	59.98	4.20	0.66	0.045	0.45	0.14	0.025	0.018	0.544	0.128	0.078	0.165	...	0.013	0.005	0.063	0.007	0.317 Pb, 0.057 As
*ECRM 686-1	2002	Iron Oxide	69.44	0.0083	0.0407	0.0014	0.0097	0.0027	0.231	0.0078	...	0.0058	0.0024	0.0004	0.095	0.0019	0.0182	0.0003	0.0004	0.0007 Mo, 0.0002 Sn
*ECRM 687-1	2009	Iron Oxide	69.66	0.0157	0.0356	0.0303	0.0113	0.0018	0.1658	0.0120	...	0.0030	0.0011	0.0051	0.0173	<i>(0.002)</i>	0.0227	0.0030	0.0122	0.0020 Mo, 0.0006 Sn

Ceramic Certified Reference Materials (Finely divided material – units of 100g; 777-1 supplied as 2 x 50g)

BAM No.	Cert. Date	Description	Si	Ca	Mg	Al	Ti	Mn	P	Fe	Na	K	B	Cr
*ECRM 777-1	1984	Silica Brick	44.44	2.02	0.043	0.42	0.27	...	...	0.23	<i>0.02</i>	0.13	...	...
*ECRM 779-1	1991	Magnesite	0.182	1.691	<i>54.6</i>	0.105	0.0081	0.503	0.0267	3.73	<i>0.006</i>	<i>0.002</i>	0.0116	<i>0.003</i>

Slag Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	Description	SiO ₂	CaO	P ₂ O ₅ (Citric Acid Sol.)	P ₂ O ₅ (Total)	Cr	Al	V	K	Na	Mo	Ni	B	Cu	Pb	F
ECRM 826-1	1994	Phosphate Slag	8.96	46.48	10.73	14.65	0.182	0.696	0.503	0.0278	0.375	<i>0.001</i>	<i>0.002</i>	<i>0.003</i>	<i>0.002</i>	<i>0.005</i>	<i>0.37</i>
ECRM 827-1	1991	Thomas Phosphate	6.21	47.38	18.79	20.70	...	...	...	...	...	...	...	...	...	...	...

* Denotes Full EURONORM-Certified Reference Materials

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets are for information only.

Copper and Copper Alloy Certified Reference Materials (223-229 finely divided material – units of 100g; 368 to ERM-EB394a - 40mm dia. x 30mm discs) Mass fraction in %

BAM No.	Cu	Sn	Zn	Pb	Fe	Ni	Al	Mn	Bi	As	Sb	Si	P	S	Cd	Ag	Mg	Others
223	58.74	0.089	38.82	2.13	0.091	0.0214	<0.002	<0.001	0.0018	0.0084	0.0040	<0.003	0.0003	0.0011	...	...	...	<0.0001 Se
224	57.40	0.066	39.40	1.13	0.136	0.038	0.0012	1.70	0.0006	0.0025	0.0026	(0.002)	0.0112	0.0004	...	...	...	...
227	85.57	6.01	3.46	4.12	0.129	0.284	<0.0001	...	0.0088	0.081	0.160	<0.01	0.0002	0.122	...	...	...	0.0028 Se, 0.0012 Te
228	85.34	9.76	3.32	1.24	0.036	0.109	0.0001	<0.001	0.0086	0.024	0.078	...	0.019	0.036	...	...	...	0.0012 Se
229	63.334	0.00485	36.63	0.0192	0.01061	0.01114	...	...	...	0.00217	0.00072	...	0.0011	...	...	...	...	0.0034 Se
368	77.05	0.0147	Bal.	0.0131	0.0193	0.0258	1.972	0.0203	...	0.0246	...	0.013	0.0090	0.0019	...	...	0.0062	0.00129 Ti
369	...	...	0.0022	...	...	...	...	...	0.00097	...	...	...	...	...	...	...	0.00036	0.001042 Co, 0.000921 Cr
370	...	0.00168	...	0.00158	...	...	0.00126	...	...	...	0.00156	0.00187	0.00117	...	...	...	...	...
371	...	...	...	...	0.00183	...	...	...	...	...	...	...	...	0.00121	0.00016	...	...	0.00144 Te
372	...	...	...	...	...	0.00117	...	0.00114	...	0.00103	...	...	...	...	...	0.00090	...	0.00084 Se
ERM-EB374	92.22	7.60	0.00404	0.00083	0.0040	0.00327	<0.0001	0.00043	0.00022	0.00043	0.00063	<0.001	0.1697	0.0013	<0.0001	0.00121	<0.0001	<0.0002 Se, <0.0001 Te
ERM-EB375	58.32	0.209	38.02	2.90	0.207	0.1053	0.0270	0.0222	0.00686	0.0231	0.0122	0.0211	0.00086	...	0.00859	0.0166	...	0.00538 Te
M376a	Bal.	0.0247	0.0217	0.0236	0.0235	0.0209	0.0182	0.0206	0.0200	0.0200	0.0202	...	0.0203	0.0133	0.0186	0.0163	0.0124	0.0210 Se, 0.0215 Te 0.00422 Zr
ERM-EB377	94.04	5.92	0.01006	0.00449	0.01042	0.01074	0.00451	0.00921	0.00422	<0.001	0.0013	<0.0134	<0.001	0.00068	<0.0001	0.00644	<0.0001	0.0055 Se, <0.0001 Te
ERM-EB378	94.13	5.74	0.00073	0.00042	0.00182	0.00183	<0.0001	0.000074	<0.0001	0.00995	0.00861	<0.0010	0.0602	0.00091	0.01007	0.00266	0.00287	<0.0002 Se, 0.00850 Te 0.0089 Co, 0.0311 Cr
ERM-EB387	75.18	0.00301	19.57	0.00108	0.0617	5.020	...	0.0796	...	...	...	...	...	...	...	...	...	...
ERM-EB388	89.27	0.857	4.81	0.000969	0.0303	0.00736	4.972	0.0512	...	...	...	...	...	...	...	...	...	...
ERM-EB389	74.3	0.0262	0.1125	0.0098	0.107	24.7	0.0123	0.415	0.0044	...	0.0046	0.0349	0.0093	0.0308	0.0016	...	0.067	0.0770 Co, 0.0153 Cr 0.0660 Ti, 0.098 Zr
ERM-EB393a	75.8	39.0	(20.8)	0.0104	0.0143	0.00297	0.00021	0.00185	0.000019	0.000134	0.000093	3.35	0.0454	...	0.000061	...	...	0.000047 Se, 0.0000156 Cr
M394	57.70	0.232	...	1.93	0.1191	0.0399	0.00010	0.00141	0.00081	0.01001	0.00238	0.00053	0.00157	...	0.00070	...	...	<0.0002 Cr
M394a	57.64	0.174	...	1.92	0.1323	0.0386	0.00079	0.00125	0.00083	0.00959	0.00241	0.00058	0.00172	...	0.00073	...	...	0.00013 Cr

Also available: 379/1, 379/2 and 379/3 which are certified for oxygen at **38** µg/g, **212** µg/g and **378** µg/g respectively (30mm dia. x 40mm discs).

Pure Copper Certified Reference Materials (M365a finely divided material – units of 100g; all others are 40mm dia. x 30mm discs, except M383a – M384b which are 38mm dia. x 30mm discs)
Mass fraction in µg/g, except where marked

BAM No.	Cu	Sn	Zn	Pb	Fe	Ni	Al	Mn	Bi	As	Sb	Si	P	S	Cd	Co	Cr	Ag	Se	Te	Mg	Ti	Zr
M365a*	99.73%	(29)	30	141	6.1	235	...	...	30.0	40.4	12.1	...	...	...	...	2.13	...	159	179	1.27	...	...	...
M381	Bal.	3.86	5.3	0.59	3.3	0.7	<1	0.22	<0.3	<0.5	<1	<3	...	3.2	<0.4	<0.3	<0.4	<1	<1	<0.3	<0.6	<0.3	<6
M382	Bal.	4.29	6.0	1.0	6.0	1.7	<2.5	0.76	0.53	0.6	0.7	<6	...	3.2	0.90	0.73	0.56	1.8	0.6	0.61	1.4	0.6	<3
M383a	Bal.	1.01	17.1	1.09	3.1	1.13	<1	0.34	2.7	2.5	1.91	<1	<1	3.2	1.16	0.96	<1	11.1	1.34	1.77	<1	<2	<1
M383b	Bal.	0.8	9.3	1.01	3.6	1.43	<1.2	0.18	1.85	2.8	1.69	<2	<1	3.6	0.93	1.02	<1	10.6	1.17	5.7	<1	<1	<1
M383c	Bal.	1.9	2.5	3.0	1.4	4.2	<1.6	1.52	1.01	1.54	2.13	<2.5	<1	4.6	2.06	1.21	<1.5	10.6	2.6	4.6	1.11	2.6	2.9
M384a	Bal.	2.6	5.3	11.7	2.7	6.1	<1.5	0.22	6.16	5.4	5.4	<2.5	<1.5	4.6	4.1	3.64	<0.2	10.7	5.8	9.3	<0.2	<1	0.1
M384b	Bal.	2.1	2.6	1.6	5.1	4.7	2.9	8.1	6.81	6.6	5.8	<2.5	<2	3.8	4.0	10.4	2.3	11.3	2.9	7.2	3.3	2.9	1.3
M385a	Bal.	16.0	9.2	10.8	44.5	10.8	13.3	9.9	5.62	9.3	14.9	7.2	10.0	35.4	2.73	7.5	10.4	24.9	5.2	8.1	(32)	6.7	(18)
ERM-EB386	Bal.	28.3	49.5	23.4	64.7	25.0	36.5	13.3	9.6	24.2	31.2	14.3	7.2	21.9	7.8	5.20	12.4	47.4	11.6	38.3	36.1	...	...
M390	Bal.	<0.01	...	...	0.79	...	...	...	...	...	...	...	1.3	...	...	...	...	...	...	...	...	...	...
M391	Bal.	<0.01	...	...	0.90	...	...	...	...	...	...	...	3.3	...	...	...	...	...	...	...	...	...	...
M392	Bal.	<0.01	...	...	0.80	...	...	...	...	...	...	...	7.0	...	...	...	...	...	...	...	...	...	...

*O=(1712) µg/g

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG (BAM), Germany
CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Aluminium Alloy Certified Reference Materials (201-301 finely divided material – units of 100g; ERM-EB307a, EB312a & 315a – approx. 65mm dia. x 30mm discs; 310, 311 and ERM-EB313 – approx. 60mm dia. x 25mm discs; ERM-EB316 and EB317 – approx. 50mm dia. x 30mm discs)

BAM No.	Si	Mn	Fe	Cu	Ti	Zn	Mg	Pb	Al	Cr	Ni	V	Be	Bi	Ca	Cd	Li	Na	Sn	Zr	Ga
201	13.20	0.38	0.18	0.009	0.011	0.038	0.0024	...	Bal.	...	...	...	...	...	...	...	...	...	...	...	...
300	0.14	0.018	0.203	0.046	0.011	0.128	2.67	0.016	Bal.	0.23	...	...	...	...	...	...	...	...	<0.0005	...	...
301	0.061	0.001	0.054	0.0016	0.005	0.033	0.0008	...	Bal.	...	...	0.0018	...	...	...	...	...	...	<0.0005	...	...
ERM-EB307a	0.152	0.811	0.345	0.0939	0.0595	0.0690	4.80	0.0084	Bal.	0.1536	0.0097	0.0119	0.000537	...	0.00192	0.00326	0.00081	0.00084	0.0075	0.00319	0.0124
310	0.080	0.003	0.070	0.0017	0.003	0.009	0.994	0.0035	Bal.	0.0009	0.002	0.0044	0.00013	...	0.00073	0.0024	0.00037	0.0003	0.0024	0.0014	0.0115
311	0.204	0.694	0.310	4.653	0.056	0.200	1.567	0.0504	Bal.	0.104	0.052	0.0240	0.00052	0.0500	0.00056	0.0013	0.00053	0.0018	0.0127	0.140	0.0159
ERM-EB312a	0.403	0.0488	0.198	0.0509	0.0291	0.0297	0.379	0.00497	Bal.	0.0320	0.00407	0.00673	...	0.00180	0.00169	0.00167	0.00060	0.00040	...	0.00085	0.0129
ERM-EB313	0.363	0.495	0.391	0.0932	0.0947	0.1579	3.40	0.00433	Bal.	0.1224	0.0278	0.0299	0.000547	0.0095	0.00057	0.00074	0.00060	0.00370	0.0197	0.0359	0.0121
ERM-EB315a	9.88	0.311	0.621	2.46	0.142	0.801	0.446	0.077	Bal.	0.0274	0.0955	0.00470	0.000433	0.0036	...	0.00079	...	...	0.0764	0.00310	0.0089
ERM-EB316	11.98	0.204	0.1054	0.2970	0.0790	0.0611	0.045	0.0087	Bal.	0.00593	0.0235	0.0098	0.000295	0.0140	0.00113	0.00208	...	...	0.0106	0.00328	0.0105
ERM-EB317	0.0271	0.0912	0.112	1.77	0.0952	6.93	2.39	0.00481	Bal.	0.141	0.0359	0.0105	0.00101	0.0041	0.00060	...	...	...	0.0237	0.130	0.0183

ERM-EB307a also certified for Co: **0.00051%** and Sb **0.0046%**, ERM-EB312a for Sr: **0.00111%**, ERM-EB315a for Sb: **0.0051%**, ERM-EB316 for Sr: **0.0260%** and ERM-EB317 for Ag: **0.0073%** and In: **0.0162%**

Lead Alloy Certified Reference Materials (Disc samples – dimensions as below)

BAM No.	Description	Disc Dimensions	Ca	Sb	As	Sn	Se	Bi	Ag	Al	Cu	Tl	Ni	Cd	Hg	S	Te	Zn
ERM-EB101a	PbCaSnAl	40mm dia. x 40mm	0.136	<0.00012	<0.0002	0.294	...	0.0165	0.00290	0.0227	0.00243	0.00102	<0.00006	(0.0002)	...	(<0.0003)	<0.0003	0.00010
ERM-EB102a	PbCaSn	40mm dia. x 40mm	0.0635	0.0004	<0.0002	1.01	...	0.00737	0.0170	0.0124	0.00013	0.00302	...	...	...	(<0.0003)	<0.00011	<0.00005
ERM-EB103	PbSb1.6	40mm dia. x 30mm	...	1.64	0.097	0.183	0.0180	0.0158	0.0066	...	0.00097	0.00152	0.000302	0.000020	...	0.00054	0.00019	...
ERM-EB104	PbCaSn	40mm dia. x 40mm	0.0530	...	...	1.27	...	0.0126	0.00293	...	...	...	...	...	...	...	...	...
ERM-EB105	PbCaSn	40mm dia. x 40mm	0.0595	...	...	1.43	...	0.0133	0.00321	...	...	...	...	...	...	...	...	...
ERM-EB106	PbCaSn	40mm dia. x 40mm	0.0782	...	...	1.72	...	(0.0135)	(0.00323)	...	...	...	...	...	...	...	...	...
ERM-EB107	Pure Lead	40mm dia. x 40mm	...	...	...	...	...	...	...	...	...	...	...	0.00261	0.00113	...	...	...
ERM-EB108	Pure Lead	40mm dia. x 40mm	...	...	...	...	...	...	...	...	...	...	...	0.00260	0.00083	...	...	...

Gold Alloy Certified Reference Materials (15.8mm dia. x 0.25mm discs)

BAM No.	Description	Au	Ag	Cu	Ni	Zn
ERM-EB506	Rose Gold	58.56	3.90	35.65	...	1.891
ERM-EB507	White Gold	75.10	3.02	14.69	4.99	2.107
ERM-EB508	Yellow Gold	75.12	24.90	...	...	...

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate.

High Purity Substances Certified Reference Materials (Finely divided material - units of 100g) Mass fraction in µg/g

BAM No.	Description	Cert. Date	CO ₂	H ₂ O	Ag	Al	As	B	Ba	Be	Bi	C	Ca	Cd	Ce	Cl
RS 1	SiO ₂ (>99.99%)	1991	...	...	...	8.7	<0.1	...	...	...	...	...	0.42	<0.05	...	...
RS 2	Al ₂ O ₃ (99.76%)	1994	...	2280	...	...	<0.5	<5	<0.5	<0.2	...	...	3.1	<0.2	<0.1	<10
RS 3	CaCO ₃ (99.79%)	1994	43970	1320	...	<5	...	<1	45.3	...	...	...	...	<0.5	...	...
RS 4	Ni (99.995%)	1996	...	...	<1	<1	<0.5	<2	...	...	<2	9.4	<1	<0.2	...	...
RS 5	NiO (Ni: 79.3%)	1996	...	150	<1	6	<0.2	...	<1	...	<1	14	2.2	<0.2	...	...
RS 6A	MgO (Mg: 60.19%)	1997	...	110	...	46	...	...	<10	...	...	<50	994	...	...	...
RS 6B	MgO (Mg: 60.17%)	1997	...	283	...	49	...	...	<20	...	...	<210	956	...	...	...

BAM No.	Co	Cr	Cu	Fe	Ga	Ge	Hg	In	K	La	Li	Mg	Mn	Mo	N	Na
RS 1 (continued)	...	0.062	<0.1	0.62	...	<1	<0.05	...	0.48	...	0.25	<0.5	<0.2	...	...	<2
RS 2 (continued)	<1	<1.5	<2.5	3.3	<2	...	...	<0.5	<5	<0.3	<1	<3	<1.5	<1	...	<15
RS 3 (continued)	<1	<1	<1	<5	<1.5	...	...	...	<20	<0.5	...	183	3.0	...	...	47.5
RS 4 (continued)	<1	<0.5	<2	4.2	<0.2	...	<1	<0.2	...	...	...	<0.8	<0.5	<0.2	2.5	<1
RS 5 (continued)	<2	10	1.53	27	<0.5	...	...	<1	<2	...	<2	<1	<1	<5	...	<2
RS 6A (continued)	<5	9.2	<6	82	...	...	...	...	...	...	...	601900	5.4	<10	...	...
RS 6B (continued)	<5	8.1	<6	80	...	...	...	...	...	...	...	601700	5.2	<10	...	...

BAM No.	Ni	O	Pb	S	Sb	Se	Si	Sn	Sr	Te	Ti	Tl	V	W	Zn	Zr
RS 1 (continued)	<0.2	...	<0.15	...	...	...	...	...	...	...	1.3	...	...	...	<1.3	<0.1
RS 2 (continued)	<10	...	...	...	...	...	<20	<1	...	...	<2	...	<1	...	<2	3.2
RS 3 (continued)	<3	...	<0.1	...	...	...	<20	<1	173	...	<0.5	...	...	...	<2	<0.2
RS 4 (continued)	999950	29	<1	<2	<0.2	<1	<2	0.3	...	<0.2	...	<0.2	<0.2	<0.1	<4	...
RS 5 (continued)	793000	207000	<2	<4	<0.1	<1	<5	<1	<1	<0.2	<2	<0.5	<1	<1	3.4	<1
RS 6A (continued)	3.9	...	<5	...	...	...	...	...	2.0	...	1.3	...	8.4	...	<6	<20
RS 6B (continued)	3.3	...	<5	...	...	...	...	...	2.1	...	1.2	...	7.8	...	<6	<160

Platinum Group Elements in Used Automobile Catalyst Certified Reference Material (Finely divided material - units of 200g) Mass fraction in µg/g

BAM No.	Pt	Pd	Rh
ERM-EB504a	1414	1596	210.0

Silicon Nitride Powder Certified Reference Material (Finely divided material - units of 50g) Mass fraction in µg/g

BAM No.	Al	Ca	Co	Fe	Mg	Na	W	C	N	O	β-phase
ERM-ED101	469	14.1	43.5	79.5	4.3	7.59	41.3	1620	381000	19100	74300

Tungsten Metal Powder Certified Reference Material (Finely divided material - units of 100g) Mass fraction in µg/g

BAM No.	Al	Ca	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Si	Sn
S002	29.4	46	45	47.0	28.4	53	40.0	38.8	16.7	59	41	29	7.2	106	42

Glass Containing Hexavalent Chromium Certified Reference Material (Finely divided material - units of 50g) Mass fraction in %

BAM No.	SiO ₂	Na ₂ O	CaO	Al ₂ O ₃	BaO	MgO	ZnO	SO ₃	K ₂ O	Cr ₂ O ₃	Fe ₂ O ₃	CuO	Cr Hexavalent	Cr Total
S004	70.9	14.5	9.4	2.15	1.2	0.90	0.33	0.17	0.16	0.07	0.06	0.04	0.0094	0.0471

BNF - FULMER (BNF), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Following the closure of the BNF-Fulmer organization in October 1992, BAS purchased their entire stock of non-ferrous spectroscopic reference materials and will continue to supply these until exhausted. Replacement samples are being produced by BAS in order to maintain continuity of these samples (see BAS Catalogue for details of such samples which are designated as CURMs).

Copper Base Reference Materials (Approx. 50mm dia x 10mm discs)

BNF No.	Description	Cu	Sn	Pb	Zn	Ni	P	Fe	Si	Mn	As	Sb	Bi	Al	Mg	S
C11.01-1	Copper Tin Binary Bronze	Bal.	3.4	0.01	<0.005	0.006	0.009	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C11.02	"	Bal.	5.5	0.02	<0.005	0.006	0.02	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C11.03	"	Bal.	7.4	0.01	<0.005	<0.005	0.04	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C11.04	"	Bal.	9.6	0.01	<0.005	<0.005	0.05	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C30.01-2	Main Elements in Brass	51.48	<0.01	<0.01	Bal.	<0.005	...	<0.005	<0.005	<0.005	<0.005	<0.005	0.005	<0.002	...	...
C30.02-1	"	55.6	<0.01	<0.01	Bal.	<0.005	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	...	...
C30.03-2	"	60.6	<0.01	<0.01	39.3	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	...	...
C30.06-1	"	74.8	<0.01	<0.01	Bal.	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002	...	...
C30.07-1	"	82.0	<0.01	<0.01	Bal.	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002	...	...
C30.10-2	"	93.8	<0.01	<0.01	6.1	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002	...	...
C30.12-2	"	60.85	<0.01	<0.01	Bal.	0.52	...	<0.005	<0.005	0.90	<0.005	<0.005	<0.002	<0.005	...	...
C30.13-1	"	60.6	<0.01	<0.01	Bal.	<0.01	...	<0.005	<0.005	1.9	<0.005	<0.005	<0.002	<0.002	...	...
C30.14-2	"	60.5	<0.005	<0.01	Bal.	1.0	...	<0.01	<0.005	2.4	<0.005	<0.005	<0.005	<0.005	...	...
C30.15-1	"	60.6	<0.01	<0.01	Bal.	<0.01	...	0.55	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002	...	...
C30.16-1	"	61.2	<0.01	<0.01	Bal.	<0.01	...	0.90	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002	...	...
C30.17-2	"	61.6	<0.01	0.01	Bal.	0.01	...	1.4	<0.005	<0.005	<0.005	<0.005	<0.005	<0.005	...	...
C30.18-1	"	64.36	0.65	<0.01	Bal.	<0.005	...	<0.005	0.10	<0.005	<0.005	<0.005	<0.003	2.91	...	...
C30.19-1	"	69.9	1.07	<0.01	Bal.	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.01	<0.002	4.65	...	...
C30.21-1	"	56.0	1.96	<0.005	Bal.	<0.005	...	<0.005	0.18	<0.005	<0.005	<0.01	...	1.44	...	...
C30.22-2	"	58.28	0.009	1.05	Bal.	<0.01	...	0.006	<0.005	<0.005	0.011	<0.012	<0.005	<0.003	...	...
C38.01-1	Impurities in Brass	61	0.20	0.20	Bal.	0.01	...	0.01	<0.0005	0.009	0.03	0.02	<0.0005	0.003	...	...
C38.02-1	"	61	0.10	0.10	Bal.	0.03	...	0.09	0.01	0.14	0.06	0.06	0.005	0.004	...	...
C38.03-1	"	61	0.05	0.06	Bal.	0.13	...	0.05	0.07	0.07	0.08	0.08	0.008	0.07	...	...
C38.04-1	"	61	0.02	0.03	Bal.	0.06	...	0.04	0.12	0.22	0.04	0.12	0.008	0.02	...	...
C38.05-1	"	61	0.01	0.02	Bal.	0.19	...	0.008	0.14	0.02	0.01	0.01	0.01	0.12	...	...
C38.06-1	"	61	<0.005	0.002	Bal.	<0.005	...	<0.005	<0.0005	<0.001	<0.001	<0.002	<0.0005	<0.001	...	...

BNF – FULMER (BNF), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Copper Base Reference Materials (Approx. 50mm dia x 10mm discs)

BNF No.	Description	Cu	Sn	Pb	Zn	Ni	P	Fe	Si	Mn	As	Sb	Bi	Al	Mg	Co	S	Cr	Ag	Cd
C42.21-1	Admiralty and Naval Brass	66.1	0.54	0.23	Bal.	0.096	0.081	0.06	0.081	<0.005	<0.005	0.19	0.012	0.005	...	...	0.007	...	...	...
C42.25	"	58.5	2.2	<0.01	Bal.	<0.005	0.06	<0.005	<0.002	0.13	0.10	<0.005	<0.002	0.02	...	...	0.001	...	...	...
C43.03-1	Aluminium Brass	80.0	<0.01	0.11	Bal.	<0.003	...	0.044	<0.005	<0.002	<0.005	<0.01	<0.005	1.41	...	...	...	...	...	...
C48.03-1	Cartridge Brass	70.45	0.047	0.054	Bal.	0.030	<0.001	<0.001	<0.002	0.040	0.079	0.097	0.029	0.007	0.001	...	0.004	0.0005	...	0.013
C48.06	"	71.6	0.03	0.02	Bal.	0.11	0.002	0.02	0.006	0.006	0.008	0.006	0.004	0.002	0.001	...	0.006	0.0006	...	0.008
C51.12-2	Aluminium Bronze	Bal.	0.18	0.25	0.42	0.11	<0.005	2.90	<0.01	1.25	0.11	...	...	6.06	...	...	...	...	...	...
C51.13-2	"	Bal.	0.19	0.12	0.30	0.053	0.021	2.05	0.16	0.77	0.21	...	...	6.93	...	...	...	...	...	...
C52.51-3	Aluminium Bronze	Bal.	<0.01	<0.01	0.02	5.1	...	4.3	<0.01	<0.01	...	...	...	10.0	<0.01	...	...	<0.01	...	...
C52.55-3	"	Bal.	0.03	0.14	0.10	4.6	...	4.9	0.03	1.1	...	...	...	9.3	0.13	...	...	0.05	...	...
C52.56-3	"	Bal.	0.11	0.17	0.28	5.6	...	4.6	0.15	0.74	...	...	...	8.9	0.09	...	...	0.14	...	...
C54.01-3	Phosphor Bronze	Bal.	3.2	0.29	0.31	0.26	0.05	0.01	0.006	0.13	0.04	0.08	...	0.009	<0.001	...	0.03	...	...	...
C62.11-2	Cupro-Nickel	Bal.	0.04	<0.005	0.097	29.8	...	0.60	0.36	0.52	...	...	...	...	0.03	<0.005	<0.005	...	...	...
C62.14-2	"	Bal.	0.12	0.01	0.12	20.2	...	1.49	0.022	0.24	...	...	...	...	0.002	0.03	0.083	...	...	...
C62.15-2	"	Bal.	0.03	0.016	0.04	25.9	...	2.36	0.014	0.23	...	...	...	...	0.004	0.042	0.023	...	...	...
C65.27-1	Nickel Silver	57.0	0.01	0.04	28.7	13.9	0.02	0.26	<0.002	0.13	...	...	...	...	<0.01	...	0.03	...	...	...
C65.28-1	"	56.9	0.15	0.06	26.7	15.3	0.07	0.13	0.01	0.57	...	...	...	...	0.01	...	0.03	...	...	...
C65.29-1	"	58.9	0.08	0.11	23.4	16.8	0.07	0.39	0.02	0.17	...	...	...	...	0.01	...	0.07	...	...	...
C71.34-3	Gunmetal	Bal.	8.20	2.47	1.55	<0.01	0.020	0.29	0.04	0.05	0.18	0.071	0.029	0.007	...	...	0.16	0.03	0.025	...

BNF - FULMER (BNF), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Nickel Base Alloy Reference Materials (Approx. 28.6mm dia. x 25mm discs)

BNF No.	Description	C	Si	Cu	Fe	Mn	Cr	Ti	Al	Co	Mo	Mg	Ni
B6998	MONEL Alloy 400	0.09	0.04	31.3*	2.30	0.29	0.02	0.11	0.008	0.025	...	0.079	Bal.
B7000	"	0.05	0.11	31.5*	0.64	0.87	0.035	0.03	0.028	0.50	...	0.026	Bal.
B7001	"	0.01	0.28	31.4*	0.32	1.66	0.05	0.025	0.040	0.25	...	0.010	Bal.
B7002	"	0.015	0.15	31.7*	0.13	2.65	0.10	0.015	0.060	0.10	...	0.007	Bal.
E3918	NIMONIC Alloy 75	0.05	1.14	0.005	1.57	0.85	19.4*	0.72	0.25	0.22	0.49	0.058	Bal.
E3919	"	0.07	0.89	0.055	2.62	0.47	19.6*	0.40	0.15	1.00	0.25	0.040	Bal.
E3920	"	0.07	0.57	0.11	3.02	0.28	19.2*	0.35	0.13	2.02	0.095	0.020	Bal.
E3921	"	0.11	0.34	0.27	3.50	0.14	19.4*	0.20	0.045	0.53	0.05	...	Bal.
E3922	"	0.14	0.16	0.50	3.98	0.10	19.2*	0.08	0.035	0.115	0.03	0.014	Bal.
B7004	NIMONIC Alloy 80A	0.01	0.17	0.14	0.97	0.08	19.6*	2.63	1.64	0.06	0.06	0.002	Bal.
B7005	"	0.035	0.23	0.045	0.32	0.16	19.6*	2.52	1.55	1.04	0.10	0.005	Bal.
B7006	"	0.08	1.03	0.075	0.61	0.25	19.6*	2.14	1.19	0.35	0.20	0.008	Bal.
B7007	"	0.14	0.66	0.22	0.22	0.53	19.4*	2.31	1.36	0.15	0.39	0.019	Bal.
B7008	"	0.21	0.36	0.025	0.19	0.02	19.3*	2.33	1.46	2.00	<0.01	0.030	Bal.
B7010	NIMONIC Alloy 90	0.05	0.22	0.04	0.62	0.24	19.7*	2.48	1.61	16.9*	0.10	0.004	Bal.
B7011	"	0.095	1.02	0.065	0.34	0.16	19.7*	2.05	1.20	17.0*	0.20	0.010	Bal.
B7012	"	0.16	0.39	0.11	0.25	0.53	19.6*	2.28	1.25	17.0*	0.39	0.018	Bal.
B7013	"	0.22	0.65	0.20	0.22	0.06	19.6*	2.39	1.46	17.0*	<0.01	0.030	Bal.

* These values are not designed for calibration purposes and are quoted for reference only (MONEL, NIMONIC and INCOLOY are all trade marks of Special Metals Corporation)

BNF - FULMER (BNF), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Nickel Base Alloy Reference Materials (Approx. 28.6mm dia. x 25mm discs)

BNF No.	Description	C	Si	Cu	Fe	Mn	Cr	Ti	Al	Co	Mg	Mo	Nb	Ni
E3923	NIMONIC Alloy 800	0.01	0.17	0.54	Bal.	1.00	20.6*	0.29	0.57	0.06	...	0.51	...	32.0*
E3924	"	0.03	0.30	0.29	Bal.	0.85	20.6*	0.30	0.28	0.13	...	0.26	...	32.3*
E3925	"	0.08	0.41	0.14	Bal.	0.68	20.8*	0.28	0.24	0.28	...	0.10	...	32.2*
E3926	"	0.06	0.60	0.085	Bal.	0.50	20.2*	0.39	0.08	0.54	...	0.05	...	32.0*
E3927	"	0.08	0.75	0.055	Bal.	0.40	20.4*	0.58	0.10	1.02	...	0.025	...	32.1*
E3928	INCOLOY Alloy DS	0.10	1.77	0.05	Bal.	1.44	18.2*	0.24	0.115	1.01	...	0.025	...	36.5*
E3929	"	0.085	1.80	0.085	Bal.	1.30	17.9*	0.14	0.07	0.52	...	0.055	...	36.3*
E3930	"	0.08	2.09	0.135	Bal.	1.18	18.6*	0.065	0.03	0.26	...	0.105	...	36.2*
E3931	"	0.05	2.32	0.28	Bal.	1.06	18.5*	0.035	0.015	0.12	...	0.25	...	36.4*
E3932	"	0.04	2.50	0.55	Bal.	0.93	18.5*	0.025	0.01	0.07	...	0.49	...	36.4*
B5789	INCONEL Alloy 600	...	0.61	0.24	6.10	0.39	16.5*	0.52	0.09	0.60	0.017	...	...	Bal.
B5871	"	...	0.88	0.02	6.34	0.57	16.0*	0.27	0.18	1.09	0.013	...	...	Bal.
B5967	"	...	0.45	0.41	7.18	0.23	16.0*	0.28	0.09	0.31	0.038	...	...	Bal.
B5968	"	...	0.22	0.80	8.05	0.12	16.0*	0.11	0.03	0.18	0.059	...	...	Bal.
B7047	INCONEL Alloy X-750	0.035	0.17	0.49	5.51	1.29	15.0*	2.71	0.49	...	...	0.58	1.36†	Bal.
B7048	"	0.075	0.23	0.30	6.09	1.00	15.1*	2.52	0.71	...	...	0.30	1.18†	Bal.
B7049	"	0.09	0.33	0.155	7.08	0.81	15.0*	2.30	0.91	...	...	0.20	0.97†	Bal.
B7050	"	0.125	0.44	0.075	8.09	0.61	15.0*	2.27	1.01	...	...	0.10	0.77†	Bal.

(INCONEL is a trade mark of Special Metals Corporation)

† Samples contain less than 0.01% Ta

* The Cr and Ni values are not designed for calibration purposes and are quoted for reference only

Lead Base Alloy Reference Material (Approx. 50mm square x 20mm blocks)

BNF No.	Description	Cu	Sn	Pb	Zn	Ni	Cd	Sb	Bi	Ca	Ag
L21.02-1	Battery Alloy	0.0013	0.27	Bal.	0.0016	≤0.0002	≤0.0002	0.0003	0.01	0.03	0.008

BRAMMER STANDARD COMPANY, Inc. (BS), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

C, S, N, H & O in Steel Reference Materials (CSN 2-1 and CSN 2-2 are 500 x 1g pins; CSN 2C and CSN A are 100g of finely divided material; HON T is 100 x 1g pins)

BRAMMER No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Cu	H	V	O	Ca	Sn	Ti	Co	N
BS CSN 2-1	0.476	(0.03)	(0.4)	(0.004)	0.034	(16.8)	(0.5)	(0.2)	...	...	...	...	...	...	...	...	...	0.064
BS CSN 2-2	0.548	(0.03)	(0.4)	(0.004)	0.028	(16.8)	(0.5)	(0.2)	...	...	...	...	...	...	...	...	...	0.076
BS CSN 2C	0.469	0.17	0.60	0.012	0.0305	0.072	(0.006)	0.071	0.046	0.073	...	0.004	...	0.0033	(0.006)	0.002	(0.006)	0.0173
BS CSN A	0.068	(0.05)	(1.0)	(0.14)	0.305	(0.06)	...	(0.05)	...	(0.06)	...	...	...	...	...	...	...	0.0081
BS HON T	0.050	(0.6)	(1.7)	(0.03)	0.0040	(18.4)	(0.4)	(9.2)	...	...	0.00027	...	0.0044	...	...	...	...	0.0365

Calcium Treated Carbon Steel Reference Materials (38-41mm dia. x 19-30mm discs)

BRAMMER No.	C	Si	Mn	P	S	Cr	Ni	Mo	Al	As	B	Ca	Co	Cu
BS 56H	0.457	0.210	0.772	0.0096	0.0234	0.098	0.154	0.0419	0.0009	0.0056	0.0002	0.0012	0.0078	0.299
BS 1018	0.195	0.237	0.79	0.012	0.024	0.177	0.104	0.044	0.029	0.0041	(0.0002)	(0.0004)	0.0058	0.130
BS 3941	0.407	0.257	0.802	0.016	0.023	0.069	0.018	0.0061	0.0019	0.0036	(0.0001)	0.0011	0.0042	0.053
BS 9325A	0.203	0.612	0.969	0.0079	0.0045	1.50	3.29	0.358	0.0056	0.0024	(0.0001)	0.0039	0.0093	0.163
BS HiCal-1	0.271	1.29	1.00	(0.007)	0.0007	1.55	3.28	0.379	0.070	0.0022	(0.0001)	0.0140	0.0024	0.152

BRAMMER No.	Fe	Mg	Nb	N	O	Pb	Sb	Sn	Ta	Ti	V	W	Zr
BS 56H (continued)	(97.8) #	0.0002	0.0009	0.0106	0.0025	0.0004	0.0025	0.0124	0.0011	0.0009	0.0295	0.0007	0.0007
BS 1018 (continued)	98.2	(0.0003)	(0.0006)	0.0079	0.0014	(0.0006)	(0.001)	0.0099	...	0.0009	0.0009	0.0014	(0.001)
BS 3941 (continued)	(98.3) #	(0.0002)	0.033	0.0069	0.0055	0.0010	0.0005	0.0019	(0.0004)	0.0017	0.0025	(0.0004)	(0.0003)
BS 9325A (continued)	92.8	(0.0002)	0.0017	0.0076	...	(0.0003)	...	(0.0003)	(0.010)	0.0030	0.0024	0.024	(0.001)
BS HiCal-1 (continued)	91.9	(0.0003)	(0.002)	...	...	(0.0005)	...	(0.0002)	...	0.0037	0.0027	(0.0009)	(0.0008)

Calculated by difference

High Manganese Steel Reference Materials (32mm dia. x 17mm discs)

BRAMMER No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	N	Nb	Sn	Ti	V
BS 17A	0.588	0.22	19.38	0.043	0.005	1.37	0.52	0.060	0.052	(0.0001)	0.013	0.135	0.038	0.06	0.012	(0.002)	0.016
BS 19A	1.57	1.46	8.76	0.092	0.009	3.75	1.97	1.48	0.057	(0.0005)	0.014	0.51	0.039	0.040	0.037	(0.007)	0.10

BRAMMER STANDARD COMPANY, Inc. (BS), USA
CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Stainless and High Temperature Steel Reference Materials (37-44mm dia. x 10-19mm discs)

BRAMMER No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Ca	Co	Cu	N	O	Nb	Sn	Ti	V	W	Others
BS 17-4PHA	0.018	0.40	0.85	0.023	0.022	15.40	0.34	4.69	0.004	0.0016	0.0009	0.072	3.30	0.022	0.006	0.204	0.007	(0.002)	0.043	0.04	(0.002) Ta
BS 17-4PHB	0.042	0.42	0.56	0.021	0.024	15.60	0.11	4.53	0.035	0.0036	(0.0003)	0.040	3.35	0.046	(0.0021)	0.31	0.012	0.005	0.059	(0.01)	(0.002) Ta
BS 82E	0.062	0.58	1.61	0.027	0.001	22.38	0.31	12.49	0.006	0.0024	0.0014	0.12	0.26	0.072	...	0.062	0.006	0.003	0.064	0.041	...
BS 83G	0.073	0.56	1.66	0.024	0.004	24.50	0.085	19.15	(0.004)	(0.0001)	...	0.153	0.114	0.026	0.0064	0.061	0.003	(0.003)	0.077	0.007	...
BS 85D	0.049	0.55	1.69	0.025	0.024	17.09	0.59	10.03	0.13	0.0006	0.0004	0.97	0.45	0.016	0.0014	0.065	(0.006)	0.48	0.134	0.06	{ 0.006 As 0.001 Sb
BS 86F	0.054	1.22	1.30	0.021	0.0011	18.74	0.24	34.99	(0.007)	0.0026	(0.001)	0.098	0.23	0.035	...	0.19	0.004	(0.006)	0.061	(0.03)	{ (0.003) As (0.001) Pb
BS 87F	0.055	0.67	1.64	0.024	0.025	17.30	0.29	10.12	0.004	(0.0006)	0.0007	0.17	0.28	0.037	0.005	0.57	0.004	0.004	0.13	0.050	0.005 As
BS 90F	0.085	0.58	0.53	0.023	0.328	13.01	0.14	0.30	(0.006)	...	...	0.021	0.12	0.037	0.011	0.011	0.005	(0.002)	0.076	0.032	...
BS 94C	0.057	0.62	0.45	0.024	0.002	25.90	0.20	0.43	0.004	(0.0005)	0.0008	0.042	0.056	0.065	0.0061	0.032	0.006	...	0.12	(0.03)	...
BS 180A	0.018	0.32	5.05	0.012	0.001	21.09	2.04	13.19	0.012	(0.0023)	...	0.039	0.067	0.334	0.003	0.20	(0.002)	(0.002)	0.20	0.02	(0.002) As
BS 181B	0.070	3.94	8.07	0.021	0.0009	16.17	0.173	8.18	0.0119	(0.0008)	(0.001)	0.044	0.206	0.158	0.0010	0.026	(0.004)	0.0051	0.044	0.016	62.8 Fe
BS 183A	0.172	0.37	0.35	0.016	0.0040	12.14	0.12	1.85	0.002	(<0.0005)	0.0020	0.036	0.093	0.0256	0.0065	0.006	0.003	0.002	0.090	2.60	(0.002) As
BS 184A	0.035	0.080	0.06	0.007	0.001	12.66	2.20	8.34	1.00	(0.0004)	(0.0003)	0.036	0.041	0.0045	(0.0003)	(0.006)	(0.002)	0.051	0.014	0.032	(0.002) Ta
BS 185A	0.033	0.38	0.49	0.022	0.002	14.46	0.30	4.43	0.002	0.0017	(0.0002)	0.026	3.41	0.027	(0.0021)	0.32	0.007	(0.001)	0.048	(0.014)	(0.002) Ta
BS 186A	0.040	0.19	0.72	0.008	0.0053	0.16	0.0032	35.86	(0.001)	...	...	0.028	0.016	0.0026	...	(<0.002)	(0.002)	(<0.003)	0.0012	(0.01)	0.229 Se
BS 187D	0.0337	0.669	0.938	0.0155	0.0021	19.91	2.17	32.3	0.0164	0.0026	0.0063	0.089	3.52	0.046	0.0026	0.621	0.0085	0.0027	0.073	0.086	{ 0.0019 Pb 0.0008 Ta
BS 188B	0.046	0.266	0.247	0.016	(0.0007)	14.32	1.30	24.81	0.168	0.0047	(0.00003)	0.274	0.120	0.0021	0.0006	0.099	0.0051	2.20	0.264	0.043	{ 0.0045 As 55.8 Fe
BS 189A	0.0147	0.30	0.639	0.019	(0.001)	20.4	6.04	23.8	0.0129	(0.0002)	(0.0004)	0.100	0.184	0.198	0.0024	0.13	0.0035	0.0065	0.054	0.037	{ 0.0039 As (0.001) Zr
BS 316E	0.0183	0.268	1.413	0.0295	0.0214	16.70	2.06	10.43	0.0027	0.0036	(0.0006)	0.287	0.408	0.042	0.0039	0.0282	0.0082	(0.002)	0.074	0.067	{ 0.003 As 68.1 Fe
BS 430	0.061	0.37	0.71	0.024	0.002	16.5	0.052	0.22	<0.05	<0.005	<0.005	<0.5	0.12	0.06	(0.006)	0.01	0.009	<0.05	0.057	<0.05	{ 0.0045 As 81.7 Fe
BS 2205	0.0199	0.564	1.029	0.0227	0.0005	22.92	3.26	5.27	0.0080	0.0016	0.0014	0.041	0.196	0.169	0.0034	0.0052	0.0050	0.0019	0.0560	0.0309	{ 0.0059 As 0.0010 Sb
BS 9841	0.067	0.54	1.69	0.024	0.024	24.30	0.57	19.55	(<0.006)	0.0026	(0.0002)	0.116	0.356	0.064	(0.011)	0.070	0.006	(0.002)	0.070	0.06	(0.006) Sb
BS 9842	0.059	0.99	1.50	0.025	0.0016	24.19	0.111	20.02	0.014	0.0025	0.0010	0.237	0.147	0.037	(0.0044)	0.026	0.005	0.003	0.075	0.011	(0.002) As
BS 9941	0.021	0.33	1.78	0.027	0.024	18.48	3.24	13.68	0.004	0.0025	(0.0003)	0.178	0.424	0.036	(0.0058)	0.015	0.007	(0.002)	0.062	0.068	(0.010) As
BS 9942	0.021	0.49	1.84	0.025	0.006	18.21	3.30	13.55	0.004	0.0014	0.0014	0.086	0.305	0.071	(0.0023)	0.005	0.006	(0.002)	0.072	0.032	(0.004) As
BS SS 3951	0.014	0.61	1.56	0.023	0.031	18.71	0.303	9.18	0.002	(0.0006)	0.0005	0.16	0.22	0.077	0.0074	0.085	0.007	(0.002)	0.067	0.040	(0.003) As

BRAMMER STANDARD COMPANY, Inc. (BS), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Nickel Base Alloy Reference Materials (Disc samples – dimensions as below)

Brammer No.	Description	Disc Dimensions mm	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	Pb	Sn	Ti	V	W	Fe	Mg	Others
BS 200A	Nickel 200	38 dia. x 19	0.078	0.0051	0.151	0.0007	0.0037	0.0006	0.0004	99.54	0.0281	0.0044	0.0564	0.0038	0.0004	(0.00005)	(0.00002)	0.0427	0.0006	0.0005	0.074	0.0131	0.0013 O
BS 200-1	"	38 dia. x 15	0.0413	0.037	0.111	0.0009	0.0011	0.0011	0.0004	99.60	0.0048	0.0033	0.089	0.0077	0.0004	0.0010	(0.0001)	0.0209	0.0008	0.00016	0.046	0.0307	0.0015 O
BS 200-2	"	"	0.050	0.060	0.244	0.0020	0.0068	0.0094	0.0005	99.31	0.0041	0.0031	0.104	0.053	0.0009	0.0006	(0.0002)	0.0197	0.0014	(0.0003)	0.115	0.0368	0.0025 O
BS 200-3	"	"	0.0145	0.0110	0.157	0.0015	0.0032	0.0091	0.0004	99.4	0.0068	0.0037	0.103	0.108	0.0004	0.0008	0.0003	0.0235	0.0009	(0.0004)	0.138	0.0240	0.0026 O
BS 200-4	"	"	0.107	0.101	0.310	0.0023	0.0076	0.132	0.0013	98.9	0.0057	0.0037	0.0911	0.0482	0.0010	0.00087	0.00020	0.0191	0.0024	0.00095	0.297	0.0312	0.0015 O
BS 600-2	Nickel 600 Alloy	38 dia. x 20	0.071	0.23	0.31	0.006	0.004	16.36	0.007	75.34	0.16	0.0098	0.10	0.089	(0.02)	(<0.002)	(0.002)	0.37	0.028	...	6.80	0.012	0.030 N
BS 600-3	"	"	0.020	0.19	0.28	0.008	0.005	14.77	0.007	75.05	0.09	0.0082	0.10	0.24	(0.02)	(0.001)	(0.002)	0.20	0.020	...	8.88	0.012	0.0081 N
BS 600-4	"	"	0.034	0.22	0.20	0.007	0.004	14.72	(0.002)	75.88	0.06	0.0060	0.09	0.08	(0.015)	(<0.001)	(0.002)	0.20	0.023	...	8.40	0.020	0.021 N
BS 600-5	"	38 dia. x 19	0.047	0.26	0.21	0.005	<0.002	15.59	0.049	74.83	0.19	0.0018	0.029	0.10	(0.03)	(<0.001)	(<0.003)	0.23	0.054	...	8.36	0.004	0.011 N
BS 600-6	"	"	0.083	0.31	0.21	0.007	0.001	14.86	0.12	76.00	0.278	0.0028	0.066	0.24	0.14	(<0.001)	(<0.003)	0.24	0.030	...	7.33	0.022	0.0078 N 0.0012 O
BS 625D	Inconel 625	"	0.048	0.072	0.069	0.0039	0.0004	22.33	8.74	60.9	0.21	0.0019	0.041	0.019	3.54	...	(0.0006)	0.276	0.018	0.014	3.81	...	0.0007 As 0.0067 N 0.0012 O
BS 625E	"	35 dia. x 19	0.049	0.065	0.050	0.004	0.0005	22.44	8.77	60.7	0.214	0.0022	0.031	0.024	3.56	(0.00005)	(0.0006)	0.27	0.020	0.016	3.81	0.0021	(0.003) As 0.0074 N 0.0015 O
BS 800A	Cr/Fe Nickel Alloy	45 dia. x 19	0.075	0.361	0.883	0.013	(0.0007)	21.09	0.117	33.3	0.362	0.0018	0.069	0.244	0.021	(0.001)	0.0041	0.526	0.058	(0.030)	42.7	0.0022	0.0126 N 0.0014 O
BS 197A	Ra 333 Alloy	38 dia. x 19	0.050	0.96	1.56	0.021	(<0.001)	25.11	2.99	44.44	0.185	0.0019	3.06	0.119	0.20	(0.0002)	...	0.017	0.051	2.80	18.07	(0.0030)	(0.052) N
BS 718D	In 718 Alloy	"	0.037	0.072	0.100	0.0083	0.0004	18.32	3.00	52.5	0.631	0.0041	0.368	0.071	5.16	(0.00006)	0.0020	0.93	0.038	0.049	18.51	0.0038	0.0011 As 0.0084 N 0.0015 O
BS 825F	Nickel Alloy 825	"	0.012	0.59	0.521	0.018	(0.005)	23.2	3.19	38.9	0.081	0.0023	0.064	1.78	(0.02)	(0.0008)	0.0036	0.91	0.086	0.015	30.7	0.0013	<0.0085 N <0.0009 O
BS 400D	Monel Alloy	"	0.130	0.146	0.993	(0.0010)	0.0006	0.0057	0.0024	63.4	0.0231	0.0009	0.032	33.0	(0.0001)	0.0004	0.00012	0.064	(0.0002)	0.0004	2.00	0.0217	0.00017 N 0.0008 O 0.0003 Zr
BS 400-1	"	38 dia. x 18	0.109	0.16	1.07	0.022	0.008	0.033	0.001	66.0	0.004	(0.0005)	0.37	30.97	0.0003	0.0020	0.0010	0.007	(0.001)	...	1.27	0.048	0.004 As
BS 400-2	"	"	0.170	0.17	1.17	0.027	0.008	0.091	0.0012	65.9	0.006	(0.0006)	0.46	30.75	0.0004	(0.001)	0.0012	0.011	(0.003)	...	1.42	0.033	0.004 As
BS 400-3	"	"	0.153	0.063	0.85	0.026	0.006	0.21	0.003	65.4	0.001	(0.0002)	0.46	31.25	(0.0004)	(0.0015)	0.0014	0.004	0.003	...	1.60	0.012	0.004 As
BS 500E	"	38 dia. x 19	0.134	0.148	0.605	0.0022	0.0006	0.0174	0.0044	64.7	2.94	0.0017	0.017	29.9	(0.002)	(0.0008)	(0.0008)	0.607	(0.001)	(0.002)	0.722	0.0058	0.0005 O 0.0133 Zr
BS H1C	Hastelloy (B-2)	"	0.0022	(0.01)	0.51	0.0049	(0.0004)	0.70	27.2	69.8	0.15	(0.001)	(0.01)	(0.002)	(0.009)	(0.00002)	(0.002)	(0.008)	(0.02)	(0.009)	1.29	(0.0012)	(0.001) As (0.009) Ta
BS H2D	" (C-276)	32 dia. x 19	0.0025	0.030	0.414	0.0081	0.00034	16.08	15.34	58.4	0.129	0.0013	0.180	0.117	0.029	(0.00009)	0.0010	0.0129	0.022	3.25	6.01	0.0065	0.0126 N
BS H3C	" (x)	38 dia. x 19	0.087	0.36	0.492	0.0150	(0.0003)	21.50	8.82	46.6	0.149	0.0020	1.37	0.106	0.095	...	0.0019	(0.0064)	0.047	0.623	19.54	0.0020	0.0266 N 0.0013 O
BS H6B	" (C-22)	"	(0.008)	(0.035)	0.226	0.0054	0.0005	22.3	14.05	55.9	0.23	0.0016	0.079	0.035	(0.1)	...	(0.0007)	0.050	0.0063	3.20	3.45	0.0010	0.0118 N 0.0007 O

BS 200A to 200-4 also certified for As and Ca, plus some for N, Sb and Ta

BRAMMER STANDARD COMPANY, Inc. (BS), USA
CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Copper Base Alloy Reference Materials (38-41mm dia. x 12-19mm discs)

BRAMMER No.	Cu	Pb	Sn	Zn	Mn	Al	Fe	Ni	P	As	Si	Sb	C	S	Others
BS 172 Be-1 (Wrought)	97.68	(0.002)	0.033	0.007	0.001	(0.02)	0.052	0.039	...	...	0.055	...	...	...	1.89 Be , 0.21 Co
BS 464A (Wrought)	60.6	0.056	0.62	38.73	0.0002	(0.001)	0.013	0.004	0.012	<0.002	<0.01	(0.001)	(0.0006)	(0.001)	...
BS 482A (Wrought)	60.0	0.50	0.65	38.8	<0.002	(0.003)	0.020	(0.007)	<0.003	<0.002	(0.002)	0.0012	(0.0015)	<0.002	...
BS 510B (Wrought)	95.0	0.0112	4.6	0.251	0.0004	(0.006)	0.009	0.0211	0.074	0.0010	(0.003)	(0.002)	0.0010	0.007	(0.0001) N , 0.0009 O
BS 544B (Wrought)	88.2	3.9	4.06	3.51	(0.0009)	(0.0009)	0.087	0.068	0.0258	0.0043	0.0042	0.0244	0.0031	0.0249	0.0173 Ag , 0.0005 O
BS 623A (Wrought)	88.13	0.001	0.002	0.008	0.273	9.12	2.19	0.146	<0.002	(0.006)	0.014	<0.002	(0.002)	(<0.0005)	...
BS 630C (Wrought)	80.7	0.0093	0.0152	0.234	0.325	9.90	3.82	4.82	0.0043	0.0007	0.064	0.0003	0.0060	(<0.0005)	0.0019 Co , 0.0030 Cr 0.0011 Mg
BS 655A (Wrought)	95.74	0.008	0.07	0.02	0.91	(0.002)	0.075	0.008	(0.004)	<0.002	3.14	<0.002	(0.0006)	(0.0003)	...
BS 675A (Wrought)	58.5	0.074	0.80	39.1	0.32	<0.002	1.12	0.019	0.010	0.003	(0.005)	0.0011	(0.0007)	(0.0005)	...
BS 706B (Wrought)	87.00	0.006	0.006	0.054	0.61	<0.003	1.56	10.9	0.009	<0.0005	<0.002	<0.002	(0.004)	0.009	0.005 Co
BS 715A (Wrought)	68.0	(0.007)	0.008	0.10	0.82	(0.01)	0.61	30.22	0.006	(0.0014)	0.10	(0.003)	0.03	0.001	...
BS 836A-4 (Cast)	84.7	5.31	4.58	4.64	(0.001)	0.0013	0.026	0.46	0.086	0.008	0.0019	0.068	(0.002)	0.041	0.023 Ag
BS 857B-1 (Cast)	61.3	1.22	1.14	34.91	0.003	0.35	0.30	0.61	0.004	(0.001)	0.004	(0.002)	...	...	(0.002) Ag
BS 903E (Cast)	87.0	0.100	8.63	4.11	...	(0.001)	0.0072	0.293	0.056	(0.002)	(0.0018)	0.010	(0.002)	0.0092	(0.007) O
BS 905A-1 (Cast)	87.3	0.030	10.25	2.27	(<0.0003)	(<0.003)	0.015	0.018	0.055	(0.001)	(<0.004)	0.004	...	...	(0.002) Ag
BS 932F (Cast)	82.1	7.32	6.30	3.39	(0.0002)	(0.0008)	0.057	0.388	0.0105	0.0091	0.0011	0.199	(0.0053)	0.0368	(0.0003) N , 0.0025 O
BS 938-1 (Cast)	77.1	14.8	7.16	0.26	(0.001)	(<0.002)	(0.015)	0.49	(0.059)	(0.004)	(<0.004)	0.033	...	0.009	0.0048 Ag
BS 954B (Cast)	83.9	0.047	0.07	0.10	0.27	10.20	3.90	1.38	0.012	(0.005)	0.07	(0.001)	(0.005)	(<0.0005)	0.003 Ag
BS 955C (Cast)	80.6	0.003	0.003	0.15	0.06	10.68	4.04	4.31	0.012	(<0.002)	0.025	(<0.002)	...	...	0.014 Ag

Cobalt Base Reference Materials (38mm dia. X 19mm discs)

BRAMMER No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	V	W	Fe	La
BS 171B	Stellite 4605	0.087	0.29	1.90	0.008	<0.001	20.5	0.65	10.68	0.08	(0.0025)	Bal.	0.035	0.046	(0.02)	15.1	1.82	...
BS 172A	Stellite 188	0.098	0.37	0.77	(0.011)	(<0.0005)	21.85	0.30	23.7	0.08	(0.003)	Bal.	0.027	0.09	0.007	14.0	1.76	0.045

CANADA CENTRE FOR MINERAL AND ENERGY TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Base Metal Ore Certified Reference Materials (Finely divided material – units of 200g)

CANMET No.	Description	Si	Al	S	Fe	K	Na	Ca	As	Mg	C	Cd	Pb	Cu	Ti	W
BH-1	Tungsten Ore	38.0	3.5	0.8	3.2	0.7	0.1	0.5	...	0.4	0.1	...	...	...	0.4	0.422
CD-1	Antimony Ore	32.9	5.5	3.1	2.8	1.8	0.1	1.4	0.66	0.6	0.21	...	0.02	<0.01	...	...
CT-1	Tungsten Ore	17.2	2.9	8.2	17.5	0.7	0.2	12.2	...	2.0	1.7	...	...	...	0.2	1.04
HV-2a	Copper-Molybdenum Ore	31.34	7.96	0.344	2.044	2.31	2.335	1.891	0.00121	0.329	(0.4)	(0.2)	0.00069	0.3808	0.0000128	0.000789
MP-1b	Zinc-Tin-Copper-Lead Ore	16.79	3.46	13.79	8.19	(0.2)	...	2.47	2.30	0.024	(0.028)	0.0527	2.091	3.069	0.075	(0.11)
MP-2a	Tungsten-Molybdenum Ore	31.2	5.99	0.716	5.00	1.226	(0.03)	3.22	0.558	0.0923	...	0.00145	0.277	0.0459	0.0268	0.338
OKA-1	Niobium Ore	2.4	0.9	0.6	2.8	0.3	0.2	31.3	...	1.3	...	...	...	...	...	...
SCH-1	Iron Ore	3.78	0.509	0.007	60.73	0.026	0.019	0.029	...	0.020	...	...	...	...	0.031	...
TAN-1	Tantalum Ore	33.42	8.2	...	0.2	1.5	4.6	0.5	...	0.02	...	...	...	...	...	...
TLG-1	Tungsten Ore	21.5	3.0	...	8.6	0.4	0.2	16.6	...	2.7	1.4	...	...	...	0.1	0.083

(Continued from above)

CANMET No.	Bi	Cr	Mn	Mo	P	Zn	Zr	Sr	In	Nb	Ta	Sn	Sb	Ag	H ₂ O (105°C)	LOI
BH-1 (continued)	...	...	0.2	0.02	...	...	...	...	...	...	...	...	...	...	...	...
CD-1 (continued)	...	...	...	...	...	...	...	...	...	...	...	...	3.57	...	0.2	4.0
CT-1 (continued)	...	...	0.7	0.03	...	...	...	...	...	...	...	...	...	...	...	...
HV-2a (continued)	0.000158	0.0100	0.0545	0.01254	0.0427	0.00565	0.00658	0.00123	...	(0.0002)	(0.00002)	(0.00012)	0.000689	0.0001448	(0.3)	3.01
MP-1b (continued)	0.0954	...	(0.048)	0.0285	(0.02)	16.67	...	...	0.056	...	...	1.61	0.0054	0.00470	...	...
MP-2a (continued)	0.0989	0.0150	0.1018	0.1586	...	0.566	0.0134	0.00123	0.001209	0.0097	0.0016	0.0537	0.00078	0.000482	...	(4)
OKA-1 (continued)	...	...	1.1	...	1.1	0.05	...	1.0	...	0.37	...	...	...	...	...	31.9
SCH-1 (continued)	...	...	0.777	...	0.054	...	...	...	...	...	...	...	...	...	...	...
TAN-1 (continued)	...	...	0.02	...	...	...	...	...	...	0.02	0.236	0.01	...	...	...	...
TLG-1 (continued)	...	...	1.3	<0.01	...	...	...	...	...	...	...	...	...	...	1.6	...

HV-2a also certified for Ba: **869** µg/g, Ce: **19.1** µg/g, Co: **3.40** µg/g, Cs: **2.70** µg/g, Dy: **1.126** µg/g, Er: **0.646** µg/g, Gd: **1.40** µg/g, La: **9.1** µg/g, Nd: **8.77** µg/g, Ni: **6.47** µg/g, Rb: **48.3** µg/g, Sm: **1.69** µg/g, Th: **1.28** µg/g, U: **1.08** µg/g.

MP-2a also certified for Ba: **12.3** µg/g, Ce: **357** µg/g, Co: **5.50** µg/g, Cs: **5.78** µg/g, Dy: **32.5** µg/g, Gd: **24.8** µg/g, Hf: **9.40** µg/g, La: **157** µg/g, Li: **81** µg/g, Lu: **4.36** µg/g, Nd: **117.9** µg/g, Rb: **229** µg/g, Sc: **4.87** µg/g, Sm: **26.7** µg/g, Tb: **4.82** µg/g, Th: **61.3** µg/g, Tm: **4.10** µg/g, U: **37** µg/g, Yb: **28.8** µg/g.

Noble Metal Ore, Concentrate and Matte Certified Reference Materials (Finely divided material – CH-4, MA-1b, MA-3a, PTC-1b and SU-1b in units of 200g, GTS-2a in units of 350g, DS-1, MA-2c, PTA-1, PTM-1a and UMT-1 in units of 400g)

CANMET No.	Description	Si	SiO ₂	Fe	Al	Ca	K	Na	S	Mg	Ni	Cu	Co	Pb	Ag	As	Pd	Pt	Au	Rh	C	Zn	H ₂ O	LOI
CH-4	Gold Ore	...	62.75	5.32	7.73	1.96	1.80	3.18	0.65	1.40	0.0051	0.20	0.0026	(0.0014)	0.00021	0.00082	...	...	0.000088	...	0.12	0.020	...	(0.9)
DS-1	Gold Ore	25.68	...	(3.0)	4.48	6.248	1.1	...	2.85	2.76	0.00487	0.00271	0.00095	0.00138	0.000047	0.6960	...	...	0.003259	...	...	0.0206	...	13
GTS-2a	Gold Ore Mill Tailings	23.65	...	7.56	6.96	4.01	2.021	0.617	0.348	2.412	0.00771	0.00886	0.00221	0.00179	(0.000064)	0.0124	(0.002)	...	0.0000272	...	2.011	0.0208	...	9.87
MA-1b	Gold Ore	24.5	...	4.62	6.11	4.6	4.45	1.49	1.17	2.6	...	...	...	...	0.0004	...	...	...	0.00170	...	2.44	...	0.1	7.9
MA-2c	Gold Ore	24.40	...	5.39	6.70	4.76	3.20	2.23	0.23	2.91	0.0064	0.0095	0.0029	0.0029	0.000051	0.0009	...	...	0.000302	...	1.78	0.0093	...	7.55
MA-3a	Gold Ore	21	...	5	6	5.5	4	1.5	1	3	0.007	0.01	0.003	0.002	0.00024	0.0008	...	...	0.000856	...	2.5	0.008	...	10
PTA-1	Platiniferous Black Sand	...	3.6	63.0	2.9	1.2	...	...	...	0.6	...	...	...	...	...	...	...	0.000305	...	...	...	...	...	...
PTC-1b	Nickel-Copper Sulphide	2.468	...	36.78	0.752	0.571	0.15	(0.17)	29.95	0.441	11.256	7.919	0.3253	0.0795	0.00531	0.0222	0.000946	0.000647	0.000199	(0.00005)	...	0.2083	0.81	13.44
PTM-1a	Nickel-Copper Matte	...	...	1.48	...	...	...	...	22.4	...	47.44	24.96	1.97	0.029	0.0135	0.22	0.001001	0.000731	0.00033	0.00007	...	...	...	...
SU-1b	Nickel Copper Cobalt Ore	15.23	...	25.54	4.30	2.21	(0.6)	(1.6)	14.14	1.790	1.953	1.185	0.0672	0.0058	0.00639	0.000249	0.0000791	0.0000491	(0.00002)	...	0.04	0.0235	(0.6)	(8)
UMT-1	Ultramafic Ore Tailings	...	...	...	...	...	...	...	...	...	0.1396	0.0743	0.0077	...	...	...	0.0000106	0.0000129	0.0000048	0.0000001	...	...	...	...

DS-1 also certified for Ba: **0.0221**%, Hg: **0.0082**%, Mn: **0.0437**%, P: **0.034**% and Ti: **0.0020**%.

GTS-2a also certified for Ba: **0.0186**%, Mn: **0.1510**%, P: **0.0892**%, Sr: **98.2** µg/g and Th: **1.244** µg/g. SU-1b is also certified for Mn: **0.0703**%.

PTM-1a and UMT-1 also have provisional constituent values for Ir and Ru. SU-1b has provisional constituent values for Bi, Se and V.

CANADA CENTRE FOR MINERAL AND ENERGY TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Ore Concentrate Certified Reference Materials (Finely divided material – units of 200g)

CANMET No.	Description	SiO ₂	Al	Mg	Ca	Cu	Zn	Pb	Ag	Hg	Au	S	Fe	Sb
CCU-1e	Copper Concentrate	3.134	0.1385	0.706	0.129	23.07	3.02	0.703	0.02052	0.00104	0.002027	35.28	30.7	0.0104
CPB-2	Lead Concentrate	<i>0.652</i>	0.074	0.0683	<i>0.0776</i>	0.1213	6.04	63.52	<i>0.03573</i>	<i>0.001003</i>	<i>(0.000002)</i>	<i>17.82</i>	7.065	<i>0.423</i>
CZN-4	Zinc Concentrate	0.295 Si	0.0715	<i>0.0352</i>	<i>0.0419</i>	0.403	55.24	0.1861	0.00514	0.000454	<i>(0.000004)</i>	33.07	<i>9.086</i>	<i>(0.001)</i>

CANMET No.	As	Bi	C	Cd	Co	Mn	Mo	Se	Te	Tl	H ₂ O	LOI
CCU-1e (continued)	0.101	<i>(0.0003)</i>	0.100	0.00742	0.0301	0.0096	0.00181	0.0244	0.00618	0.000269	<i>0.150</i>	<i>17.14</i>
CPB-2 (continued)	<i>(0.04)</i>	<i>0.02112</i>	...	0.0167	<i>(0.0004)</i>	<i>0.0395</i>	<i>(0.0009)</i>	<i>(0.0010)</i>	...	<i>(0.0340)</i>	...	...
CZN-4 (continued)	0.0356	<i>(0.0010)</i>	<i>(0.09)</i>	0.2604	0.00935	<i>(0.009)</i>	...	0.00867	...	...	<i>0.149</i>	...

Sulphide Ore Mill Tailings and Concentrate/Tailings Certified Reference Materials (Finely divided material – RTS-3a and RTS-5 in units of 100g, TPO-1 in units of 25g)

CANMET No.	Description	Al	As	Ca	Co	Cu	Fe	Mg	Ni	Pb	Si	SiO ₂	S (Sulphate)	S (Total)	Zn
RTS-3a	Sulphide Ore Mill Tailings	5.12	0.00182	2.14	0.0143	0.2353	20.49	2.483	0.00613	0.0209	18.28	...	<i>(1.1)</i>	9.59	0.2890
RTS-5	Nickel-Copper-Gold Tailings	6.25	0.1286	3.86	0.00769	0.0647	11.9	3.59	0.1104	0.00663	19.20	...	<i>1.23</i>	1.924	0.0105
TPO-1	Iron Sulphide Conc./Tailings	<i>3.51</i>	...	<i>2.17</i>	0.021	0.118	34.85	<i>1.66</i>	0.617	...	...	25.52	...	18.03	<i>0.02</i>

CANMET No.	Ag	Au	Ba	Bi	C	Cd	CO ₂	Cr	H ₂ O	K	Mn
RTS-3a (continued)	0.00111	<i>0.0000561</i>	0.0106	0.00313	<i>(0.04)</i>	0.00092	<i>(0.04)</i>	<i>0.0176</i>	...	0.460	0.1585
RTS-5 (continued)	0.000150	0.0000408	0.0252	<i>0.000205</i>	<i>1.617</i>	...	...	0.0261	<i>(1.4)</i>	0.850	0.1092
TPO-1 (continued)	...	...	...	...	...	...	...	<i>0.03</i>	...	<i>0.56</i>	<i>0.08</i>

CANMET No.	Na	Pd	Pt	P	Se	Sr	S (Elemental)	S (Sulphide)	Ti	Zr	LOI
RTS-3a (continued)	0.684	<i>(0.0000004)</i>	...	<i>0.0446</i>	<i>0.00448</i>	0.00447	<i>(1.2)</i>	<i>(8)</i>	<i>0.351</i>	<i>0.0078</i>	<i>(10.6)</i>
RTS-5 (continued)	1.285	<i>(0.000014)</i>	<i>(0.00002)</i>	0.0369	<i>0.000803</i>	0.01306	<i>(0.3)</i>	...	0.3132	<i>(0.0075)</i>	<i>9.90</i>
TPO-1 (continued)	<i>0.85</i>	<i>0.02</i>	...	<i>0.03</i>	...	...	...	...	<i>0.35</i>	...	...

CANADA CENTRE FOR ENERGY AND MINERAL TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content) - Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Geochemical Soil and Till Reference Materials (Finely divided material – units of 100g)

CANMET No.	Description	Mass content	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	P ₂ O ₅	S	LOI (500°C)	LOI (1000°C)
TILL-1	Soil	%	<i>60.9</i>	<i>13.7</i>	<i>6.82</i>	<i>2.15</i>	<i>2.72</i>	<i>2.71</i>	<i>2.22</i>	<i>0.18</i>	<i>0.98</i>	<i>0.22</i>	<i><0.05</i>	<i>6.3</i>	<i>7.3</i>
TILL-2	Till	%	<i>60.8</i>	<i>16.0</i>	<i>5.39</i>	<i>1.83</i>	<i>1.27</i>	<i>2.19</i>	<i>3.07</i>	<i>0.10</i>	<i>0.88</i>	<i>0.17</i>	<i><0.05</i>	<i>6.8</i>	<i>8.1</i>
TILL-3	Soil	%	<i>69.1</i>	<i>12.2</i>	<i>3.92</i>	<i>1.71</i>	<i>2.63</i>	<i>2.64</i>	<i>2.42</i>	<i>0.06</i>	<i>0.49</i>	<i>0.11</i>	<i><0.05</i>	<i>3.6</i>	<i>4.6</i>

CANMET No.	Mass content	As	Au	Ba	Be	Bi	Br	Ce	Co	Cr	Cs	Cu	Eu	Er	Hf	La	Li	Lu	Mn	Mo	Nb
TILL-1 (continued)	µg/g	<i>18</i>	<i>0.013</i>	<i>702</i>	<i>2.4</i>	<i><5</i>	<i>6.4</i>	<i>71</i>	<i>18</i>	<i>65</i>	<i>1.0</i>	<i>47</i>	<i>1.3</i>	<i>3.6</i>	<i>13</i>	<i>28</i>	<i>15</i>	<i>0.6</i>	<i>1420</i>	<i>2</i>	<i>10</i>
TILL-2 (continued)	µg/g	<i>26</i>	<i>0.002</i>	<i>540</i>	<i>4.0</i>	<i><5</i>	<i>12.2</i>	<i>98</i>	<i>15</i>	<i>74</i>	<i>12</i>	<i>150</i>	<i>1.0</i>	<i>3.7</i>	<i>11</i>	<i>44</i>	<i>47</i>	<i>0.6</i>	<i>780</i>	<i>14</i>	<i>20</i>
TILL-3 (continued)	µg/g	<i>87</i>	<i>0.006</i>	<i>489</i>	<i>2.0</i>	<i><5</i>	<i>4.5</i>	<i>42</i>	<i>15</i>	<i>123</i>	<i>1.7</i>	<i>22</i>	<i><1</i>	<i>1.4</i>	<i>8</i>	<i>21</i>	<i>21</i>	<i>0.2</i>	<i>520</i>	<i>2</i>	<i>7</i>

CANMET No.	Mass content	Nd	Ni	P	Pb	Rb	Sb	Sc	Sm	Sr	Ta	Tb	Th	Ti	U	V	W	Y	Yb	Zn	Zr
TILL-1 (continued)	µg/g	<i>26</i>	<i>24</i>	<i>930</i>	<i>22</i>	<i>44</i>	<i>7.8</i>	<i>13</i>	<i>5.9</i>	<i>291</i>	<i>0.7</i>	<i>1.1</i>	<i>5.6</i>	<i>5990</i>	<i>2.2</i>	<i>99</i>	<i><1</i>	<i>38</i>	<i>3.9</i>	<i>98</i>	<i>502</i>
TILL-2 (continued)	µg/g	<i>36</i>	<i>32</i>	<i>750</i>	<i>31</i>	<i>143</i>	<i>0.8</i>	<i>12</i>	<i>7.4</i>	<i>144</i>	<i>1.9</i>	<i>1.2</i>	<i>18.4</i>	<i>5300</i>	<i>5.7</i>	<i>77</i>	<i>5</i>	<i>40</i>	<i>3.7</i>	<i>130</i>	<i>390</i>
TILL-3 (continued)	µg/g	<i>16</i>	<i>39</i>	<i>490</i>	<i>26</i>	<i>55</i>	<i>0.9</i>	<i>10</i>	<i>3.3</i>	<i>300</i>	<i><0.5</i>	<i><0.5</i>	<i>4.6</i>	<i>2910</i>	<i>2.1</i>	<i>62</i>	<i><1</i>	<i>17</i>	<i>1.5</i>	<i>56</i>	<i>230</i>

Information is also given on the certificate of analysis re several partial extraction elements using HNO₃/HCl.

Rock and Mineral Certified Reference Materials (Finely divided material – units of 400g, except WMG-1a - 350g and WMS-1a - 200g) Nominal mass content in %

CANMET No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	Fe	TiO ₂	CaO	MgO	K ₂ O	Na ₂ O	MnO	P ₂ O ₅	Cu	Cr _(total)	Ni	S	LOI
TDB-1	Diabase Rock	<i>50.2</i>	<i>13.6</i>	<i>14.4</i>	10.4	<i>2.3</i>	<i>9.6</i>	<i>5.9</i>	<i>0.89</i>	<i>2.2</i>	<i>0.20</i>	<i>0.23</i>	0.0323	0.0251	0.0092	<i>0.03</i>	<i>0.3</i>
WGB-1	Gabbro Rock	<i>49.1</i>	<i>11.15</i>	6.71	...	<i>0.84</i>	<i>15.78</i>	9.40	0.94	<i>2.15</i>	<i>0.143</i>	<i>0.099</i>	<i>0.0106</i>	0.0291	<i>0.0076</i>	<i>0.02</i>	<i>4</i>
WMG-1a	Mineralized Gabbro	18.27 Si	4.75 Al	...	12.71	0.419 Ti	10.06 Ca	7.41 Mg	0.1021 K	0.1119 Na	<i>0.1141 Mn</i>	0.0731 P	0.7120	0.0804	0.2480	3.43	<i>4.31</i>
WMS-1a	Massive Sulphide	<i>(4.7) Si</i>	1.350 Al	...	45.4	<i>0.084 Ti</i>	3.09 Ca	<i>0.331 Mg</i>	<i>0.0991 K</i>	0.0329 Na	<i>0.060 Mn</i>	<i>(0.018) P</i>	1.396	<i>0.0068</i>	3.02	28.17	...
WPR-1a	Altered Peridotite	17.62 Si	2.621 Al	...	11.34	0.3527 Ti	2.528 Ca	<i>15.22 Mg</i>	0.156 K	<i>0.050 Na</i>	0.138 Mn	0.0303 P	0.299	<i>0.322</i>	0.439	1.764	<i>8.42</i>

Nominal mass content in ng/g

CANMET No.	As	Au	Pt	Pd	Rh	Ru	Ir	Os	Ba	Ce	Ag	Co	Sb	Th	V	Zn
TDB-1 (continued)	...	6.3	5.8	22.4	<i>0.7</i>	<i>0.3</i>	<i>0.15</i>	...	241000	41000	<i>(500)</i>	<i>47000</i>	<i>1000</i>	2700	<i>471000</i>	155000
WGB-1 (continued)	...	2.9	6.1	13.9	<i>0.32</i>	<i>0.3</i>	<i>0.33</i>	...	<i>851000</i>	<i>(<20000)</i>	<i>(<1000)</i>	<i>29800</i>	<i>2000</i>	<i>(<1600)</i>	<i>222000</i>	<i>31500</i>
WMG-1a (continued)	5990	<i>617</i>	899	484	<i>(15)</i>	<i>(20)</i>	<i>(27)</i>	...	216	<i>17180</i>	3030	191	<i>1550</i>	1070	158000	112
WMS-1a (continued)	30900	300	1910	1450	222	<i>145</i>	<i>322</i>	<i>(150)</i>	<i>(70000)</i>	<i>(7900)</i>	<i>3700</i>	<i>1450000</i>	<i>6920</i>	<i>(1200)</i>	<i>140000</i>	<i>130000</i>
WPR-1a (continued)	9300	<i>50</i>	452	614	...	...	<i>20</i>	...	70600	9690	1020	213000	3130	<i>640</i>	135000	160000

WPR-1a also certified for Bi, Cd, Cs, Dy, Er, Eu, Ga, Gd, Hf, Ho, La, Li, Lu, Nd, Pb, Pd, Rb, Sc, Sm, Sr, Tb, Tm, Y and Yb.

CANADA CENTRE FOR ENERGY AND MINERAL TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Rock Certified Reference Material (Finely divided material – units of 100g)

CANMET No.	Description	SiO ₂	TiO ₂	Al ₂ O ₃	FeO	Fe ₂ O ₃	MnO	MgO	CaO	Na ₂ O	K ₂ O	CO ₂	P ₂ O ₅	Sr	LOI
SY-4	Diorite Gneiss	49.9	0.29	20.69	2.86	6.21	0.108	0.54	8.05	7.10	1.66	3.5	0.131	0.1191	4.56

Also shows values for trace levels of many elements, including Ba, Be, Ce, Co, Cr, Cs, Cu, Dy, Er, Eu, Ga, Gd, Hf, Ho, La, Li, Lu, Nb, Nd, Ni, Pb, Pr, Rb, Sc, Sm, Ta, Tb, Th, Tm, V, Y, Yb, Zn, Zr.

Rare Earth Elements with Zirconium and Niobium Certified Reference Materials (Finely divided material – units of 100g)

CANMET No.	Description	Al	As	Ba	Ca	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Fe	Gd	Hf
REE-1	Rare Earth Elements	3.59	0.0124	0.01001	2.30	0.3960	0.000158	0.0277	0.000107	0.00797	0.0847	0.0701	0.00235	<i>4.16</i>	0.0433	0.0479
REE-2	Rare Earth Elements	0.761	...	5.02	13.68	0.9610	0.000771	<i>0.00327</i>	<i>(0.000009)</i>	0.000555	0.00692	0.00140	0.00966	12.14	<i>0.0219</i>	<i>0.000095</i>

CANMET No.	Ho	K	La	La(Total)	Li	Mg(Total)	Mn(Total)	Na	Nb	Nd	Ni	P	Pb	Pr	Rb	S(Total)	Sc
REE-1 (continued)	0.0208	3.09	0.1661	...	<i>0.0205</i>	<i>0.895</i>	<i>0.155</i>	1.445	0.4050	0.1456	0.00247	0.0261	0.1137	0.0435	0.1047	<i>(0.03)</i>	<i>(0.0008)</i>
REE-2 (continued)	0.000787	<i>0.0172</i>	<i>(0.46)</i>	0.5130	0.000961	6.26	1.316	<i>0.120</i>	<i>0.1060</i>	0.3660	<i>0.000899</i>	0.461	<i>0.00408</i>	0.1075	0.000122	1.745	0.00575

CANMET No.	Si	Si(Total)	Sm	Sn	Sr	Ta	Tb	Th	Ti	Tm	U	W	Y	Yb	Zr	L.O.I
REE-1 (continued)	31.36	...	0.0381	0.0498	0.0129	<i>0.0231</i>	0.01062	0.0719	<i>0.384</i>	0.01060	0.0137	<i>(0.001)</i>	0.548	0.0678	1.91	<i>(2)</i>
REE-2 (continued)	...	1.377	0.0410	0.00241	0.2300	0.000117	0.00203	0.0737	0.1969	0.0001383	0.000373	0.00099	0.0176	...	<i>0.00322</i>	31.38

Copper Anode Certified Reference Materials (finely divided material – units of 425g)

CANMET No.	Description	Ag	As	Au	Bi	Cu	Fe	Ni	Pb	Sb	Se	Sn	Te	Zn
CUAR-1	Copper Anode	0.0294	0.0145	0.00023	<i>0.0083</i>	<i>(98.6)</i>	0.0076	<i>0.4109</i>	0.0864	<i>0.0798</i>	<i>0.0026</i>	0.0113	0.0033	<i>(0.0032)</i>
CUPD-1	Copper Anode	0.0216	0.0306	0.00039	0.0062	<i>(99.5)</i>	0.0040	0.0147	0.0069	0.0147	0.0237	0.0005	<i>0.0056</i>	<i>(0.0011)</i>

Zinc-Aluminium Foundry Alloy Certified Reference Materials (50mm dia. x 12mm discs; also as finely divided material – units of 80g)

CANMET No.	Description	Al	Cu	Mg	Fe	Sn	Pb	Cd
NZA-1	Zinc-Aluminium Foundry Alloy	28.70	1.51	0.020	0.046	0.0069	0.0030	0.00098
NZA-2	Zinc-Aluminium Foundry Alloy	23.81	3.00	0.029	0.021	0.0045	0.0076	0.0047
NZA-3	Zinc-Aluminium Foundry Alloy	25.99	2.00	0.0049	0.066	0.0034	0.0045	0.0064
NZA-4	Zinc-Aluminium Foundry Alloy	26.65	2.45	0.0106	0.027	0.0087	0.0101	0.0029
NZA-5	Zinc-Aluminium Foundry Alloy	10.85	1.04	0.021	0.016	0.0017	0.0012	0.0095
NZA-6	Zinc-Aluminium Foundry Alloy	7.54	3.17	0.00037	0.0105	0.0051	0.0809	0.0147
NZA-7	Zinc-Aluminium Foundry Alloy	13.17	0.212	0.052	0.016	0.0116	0.0136	0.00020

CENTRE TECHNIQUE DES INDUSTRIES DE LA FONDERIE (CTIF), France

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Highly Alloyed Steel Certified Reference Material (Finely divided material units of 100g or a 40mm dia x 20mm disc)

CTIF No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	N	Nb	Sn	V	Al _{sol.}	Al _{tot.}	Ga
*ECRM 273-1	Highly Alloyed Steel	0.0336	0.378	0.785	0.0131	0.00037	14.747	0.246	4.852	0.0030	0.0391	3.047	0.0444	0.221	0.0021	0.0512	<i>0.0032</i>	<i>0.0062</i>	<i>0.0023</i>

Special Alloy Certified Reference Materials (40mm dia. x 20mm discs: ECRM 378-1 is also available in the finely divided form in units of 100g.)

CTIF No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	Ti	W	Fe
*ECRM 377-1	Nickel Alloy IN 625	0.0202	0.077	0.0225	0.0036	0.0006	21.72	8.94	61.45	0.216	<i>0.0006</i>	0.0348	0.0110	3.50	0.255	...	3.77
*ECRM 377-2	Nickel Alloy IN 625	0.0202	0.077	0.0225	0.0036	0.0006	21.72	8.94	61.45	0.232	<i>0.0006</i>	0.0348	0.0104	3.50	0.264	...	3.77
*ECRM 378-1	Cobalt Alloy, Stellite grade 6	1.181	1.172	0.0579	<i>0.0023</i>	0.0055	28.22	0.0503	0.617	...	...	63.52	...	...	...	4.43	0.606

Cast Iron Certified Reference Materials (Finely divided material units of 100g)

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Co	Cu	N	Sn	Te	Ti	V	Zn
*ECRM 485-3	3.514	...	...	...	0.1488	...	...	...	...	...	...	...	0.0081	...	...	...	...	...
*ECRM 487-2	3.573	0.0899	0.0491	0.0066	0.0031	0.0249	0.0034	0.0219	0.079	0.0064	0.0151	0.0136	0.0044	0.0045	0.0064	0.0021	0.0117	0.0012
*ECRM 488-2	3.956	0.374	0.201	0.0111	0.1173	0.303	<i>0.0008</i>	0.1247	...	...	...	0.0256	0.0052	0.0013	<i>0.0089</i>	0.0636	0.0545	<i>0.0006</i>
*ECRM 490-1	4.813	<i>0.03</i>	10.83	0.0267	0.0040	0.0183	...	<i>0.02</i>	...	...	...	0.0088	0.0030	...	...	0.0035	0.0152	...
*ECRM 491-1	3.616	...	...	...	0.0866	...	...	...	...	...	...	...	...	...	...	...	...	...
*ECRM 492-1	3.258	...	...	...	0.0854	...	...	...	...	...	...	...	0.0048	...	...	...	...	...

* Denotes Full EURONORM Certified Reference Materials

Low Alloy Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material.

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Co	Cu	Sn	Ti	V	Others
FL 1-1	<i>2.1</i>	<i>3.2</i>	<i>0.80</i>	<i>0.118</i>	<i>0.0765</i>	<i>0.06</i>	<i>0.038</i>	<i>0.245</i>	...	<i>0.0195</i>	<i>0.305</i>	<i>0.020</i>	<i>0.015</i>	...
FL 3-1	<i>2.3</i>	<i>2.1</i>	<i>0.27</i>	<i>0.729</i>	<i>(0.013)</i>	<i>0.107</i>	<i>0.106</i>	<i>0.553</i>	<i>(0.022)</i>	<i>0.102</i>	<i>0.111</i>	<i>0.054</i>	<i>0.049</i>	<i>0.008 N</i>
FL 7-1	<i>3.1</i>	<i>2.55</i>	<i>0.1</i>	<i>1.34</i>	<i>0.048</i>	<i>0.043</i>	<i>0.335</i>	<i>0.232</i>	...	<i>0.351</i>	<i>0.0291</i>	<i>0.05</i>	<i>0.0796</i>	<i>0.0266 As, 0.004 N</i>
FO 4-3	<i>2.81</i>	<i>1.51</i>	<i>0.64</i>	<i>0.58</i>	<i>0.009</i>	<i>0.17</i>	<i>0.095</i>	<i>0.32</i>	...	<i>0.32</i>	<i>0.013</i>	<i>0.075</i>	<i>0.049</i>	...
FO 5-4	<i>3.2</i>	<i>0.7</i>	<i>0.2</i>	<i>1.30</i>	<i>0.027</i>	<i>0.23</i>	<i>0.41</i>	<i>0.172</i>	<i>(0.019)</i>	<i>0.12</i>	<i>0.109</i>	<i>0.04</i>	<i>0.14</i>	<i>(0.003) As</i>
FO 6-4	<i>3.5</i>	<i>0.55</i>	<i>0.7</i>	<i>0.87</i>	<i>0.106</i>	<i>0.45</i>	<i>0.202</i>	<i>0.128</i>	...	<i>0.12</i>	<i>0.039</i>	<i>0.09</i>	<i>0.11</i>	...
FO 7-2	<i>2.45</i>	<i>0.675</i>	<i>0.70</i>	<i>0.84</i>	<i>0.085</i>	<i>0.455</i>	<i>0.26</i>	<i>0.15</i>	...	<i>0.125</i>	...	<i>0.065</i>	<i>0.13</i>	<i>0.0113 N</i>
FO 8-2	<i>3.6</i>	<i>1.04</i>	<i>0.37</i>	<i>0.107</i>	<i>0.019</i>	<i>0.30</i>	<i>0.0086</i>	<i>0.30</i>	...	<i>0.215</i>	<i>0.051</i>	<i>0.05</i>	<i>0.010</i>	<i>0.0095 As, 0.0067 N</i>
FO 9-2	<i>2.7</i>	<i>1.5</i>	<i>0.7</i>	<i>0.02</i>	<i>0.015</i>	<i>0.18</i>	<i>0.13</i>	<i>0.355</i>	...	<i>0.31</i>	<i>0.144</i>	<i>0.017</i>	<i>0.022</i>	...
FO 10-3	<i>3.5</i>	<i>0.65</i>	<i>1.05</i>	<i>0.196</i>	<i>0.101</i>	<i>0.379</i>	<i>0.202</i>	<i>0.117</i>	<i>0.0275</i>	<i>0.116</i>	<i>(0.002)</i>	<i>0.1</i>	<i>0.085</i>	<i>0.0012 As</i>
FO 12-1	<i>3.7</i>	<i>1.86</i>	<i>0.44</i>	<i>0.038</i>	<i>0.004</i>	...	...	...	...	<i>0.77</i>	<i>0.011</i>	...	...	...
FO 17-1	<i>3.0</i>	<i>2.48</i>	<i>0.47</i>	<i>0.470</i>	<i>0.168</i>	<i>(0.016)</i>	...	<i>0.021</i>	<i>0.032</i>	<i>(0.006)</i>	<i>0.024</i>	<i>0.032</i>	<i>0.018</i>	...
FO 18-2	<i>3.4</i>	<i>1.2</i>	<i>0.60</i>	<i>1.34</i>	<i>0.136</i>	<i>0.170</i>	<i>0.179</i>	<i>0.140</i>	...	<i>0.049</i>	<i>0.046</i>	<i>0.055</i>	<i>0.102</i>	<i>0.004 N</i>
FO 19-2	<i>4.04</i>	<i>1.05</i>	<i>1.05</i>	<i>0.030</i>	<i>0.057</i>	<i>0.0420</i>	...	<i>(0.075)</i>	<i>0.0392</i>	<i>0.0298</i>	<i>0.0012</i>	<i>0.029</i>	<i>0.0419</i>	<i>0.0005 Te, 0.0070 N</i>
FPA-1-3	<i>3.10</i>	<i>0.029</i>	<i>0.105</i>	<i>0.002</i>	<i>0.0009</i>	<i>0.073</i>	<i>0.0109</i>	<i>0.045</i>	<i>0.0097</i>	<i>0.062</i>	...	<i>0.0010</i>	<i>0.0010</i>	<i>0.0109 As, 0.012 N</i>
FT 1-3	<i>2.9</i>	<i>2.25</i>	<i>0.7</i>	<i>0.118</i>	<i>(0.006)</i>	<i>0.07</i>	...	<i>0.134</i>	...	<i>0.018</i>	...	<i>0.04</i>	<i>0.7</i>	...
FT 2-1	<i>3.4</i>	<i>1.4</i>	<i>0.78</i>	<i>0.045</i>	<i>0.095</i>	<i>0.03</i>	...	<i>0.07</i>	...	<i>0.01</i>	...	<i>0.10</i>	<i>0.405</i>	...
FT 3-1	<i>3.2</i>	<i>1.55</i>	<i>0.345</i>	<i>0.063</i>	<i>0.051</i>	<i>0.685</i>	...	<i>0.092</i>	...	<i>0.015</i>	...	<i>0.2</i>	<i>0.016</i>	...

CENTRE TECHNIQUE DES INDUSTRIES DE LA FONDERIE (CTIF), France

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Cu, Ni, Cr, Mo Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Cu
NH 1-2	3.00	1.35	0.90	0.060	0.105	0.83	1.45	1.38	1.99
NH 2-3	2.45	1.80	1.05	0.043	0.065	1.26	1.00	1.82	1.00
NH 3-2	3.45	0.85	0.175	0.36	0.024	1.76	0.73	2.53	0.031
NH 4-2	2.85	0.49	0.28	0.12	0.022	2.46	0.30	3.60	0.09
NH 5-2	2.30	0.31	0.24	0.115	0.04	2.85	0.017	4.90	0.035
NH 6-1	2.70	2.28	0.355	0.066	0.036	6.60	0.11	7.06	0.115
NH 7-1	3.43	0.95	0.63	0.035	0.022	9.02	...	5.53	0.105
NH 7-2	3.20	1.20	0.91	0.034	0.0120	8.87	...	5.53	0.108
NH 8-1	3.00	0.80	0.57	0.052	0.076	5.03	0.125	8.16	0.065
NH 9-1	3.15	1.24	0.65	0.087	0.029	11.70	0.059	4.11	0.203

Austenitic (Ni-resist) Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material

CTIF No.	C	Si	Mn	P	S	Cr	Ni	Cu	N	Nb	Mg
NR CU 1-1B	3.1	1.0	1.465	0.172	0.09	0.994	18.02	4.95	...	...	...
NR CU 2	2.52	2.07	1.07	0.115	0.049	2.05	15.9	6.50	...	...	...
NR CU 3	1.94	3.12	0.597	0.047	0.017	3.49	13.30	8.07	(0.008)	...	...
NR 1-2L	2.50	2.99	1.34	0.125	0.10	1.74	25.87	0.49	...	...	...
NR 3-2L	2.99	3.04	0.72	0.088	0.052	2.97	21.58	0.26	...	...	...
NR 5-2L	1.77	2.99	1.207	0.037	0.083	0.27	33.89	0.48	...	...	...
NR 6-2L	1.76	2.07	0.70	0.031	0.063	3.49	30.37	0.020	...	...	...
NR 8-2L	2.89	1.74	5.19	0.054	0.025	0.165	13.33	0.075	...	...	...
NR 1-2S	2.58	3.02	1.54	0.19	...	2.00	20.60	0.11	...	...	^ variable between 0.003% and 0.25% v
NR 2-2S	2.32	1.43	0.53	0.062	...	0.51	36.3	0.21	...	...	
NR 3-2S	2.92	2.91	0.77	0.024	...	3.05	24.63	0.33	...	...	
NR 4-2S	2.47	4.87	1.71	0.145	...	1.50	18.30	0.63	...	...	
NR 6-2S	1.815	2.44	0.99	0.019	...	1.06	30.75	0.03	...	...	
NR 8-2S	3.05	1.41	4.39	0.124	...	0.191	14.20	0.071	...	...	
NR2-1G	2.2	1.5	0.4	0.05	<0.01	0.40	36.3	0.23	...	0.25	

Chromium Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N
FCR 1-3	2.46	0.48	0.63	0.019	0.007	18.71	1.41	1.30	0.031	...
FCR 2-4	2.8	1.07	0.74	0.137	0.055	11.8	3.88	1.87	0.135	...
FCR 3-1	2.03	0.255	0.99	0.034	0.035	14.85	0.91	0.652	0.0490	...
FCR 4-1	2.45	1.40	2.05	0.097	0.066	24.2	2.16	0.57	1.32	...
FCR 5-1	3.43	0.30	0.55	0.052	0.0175	28.5	3.27	2.69	1.02	...
FCR 6-1	1.3	0.75	1.4	0.201	0.086	30.84	0.455	0.188	0.480	...
FCR 7-1	3.3	1.07	0.365	0.099	0.0427	33.65	2.62	0.947	0.704	...
FCR NI 1	1.27	1.63	0.71	0.41	0.06	26.20	...	16.50	0.02	...
FCR NI 2	2.0	1.51	0.60	0.185	0.024	29.07	...	13.11	...	0.1
FCR NI 3	2.74	0.67	0.46	0.036	0.011	31.65	...	11.05	...	...

CENTRE TECHNIQUE DES INDUSTRIES DE LA FONDERIE (CTIF), France

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Brass Reference Materials (60mm dia. x 5-6 mm mushrooms)

CTIF No.	Cu	Sn	Pb	Zn	Fe	Ni	Mn	Al	Si	Sb	P	Others
L 1-1	58.7	0.046	0.06	39.7	0.017	0.106	...	0.01	0.36	...	0.08	...
L 2	61.55	0.48	0.408	35.55	0.216	0.71	0.350	0.485	0.202	...	...	...
L 3-1	58.5	1.62	1.32	35.5	0.357	0.993	0.214	1.22	0.0256	0.032	0.0306	0.073 As
L 4-1	61.70	0.693	2.017	34.60	0.466	0.227	0.109	0.104	0.12	...	...	...
L 5-1	61.0	0.88	2.99	31.5	(1.0)	0.494	0.50	0.64	(0.50)	0.174	(0.15)	0.13 As
L 6	65.95	0.193	0.159	30.70	0.108	1.30	0.029	0.130	1.28	0.060	0.040	0.102 As
L 7	55.60	0.038	0.71	42.45	0.031	0.020	0.62	0.308	0.13	...	...	...
L 20-1	85.2	0.49	0.274	13.3	0.039	0.223	0.130	(0.06)	0.106	...	0.026	0.099 As
L 21	82.50	1.50	0.209	15.40	0.086	0.156	0.004	...	0.036	...	...	0.103 As
L 22	83.0	1.05	0.123	15.0	0.15	0.105	<0.001	...	0.05	0.088	0.06	<0.05 Mg
L 23	81.20	0.20	0.058	17.90	0.246	0.033	...	...	0.280	...	...	0.051 As
LH 1-1	64.9	(0.007)	0.022	16.9	4.48	0.0944	5.18	7.99	0.205	0.081	0.079	...
LH 2-1	61.2	0.051	0.103	22.4	3.15	3.27	3.19	6.50	0.057	...	...	...
LH 5-1	66.0	0.141	0.110	25.72	1.26	1.57	1.37	3.65	0.114	...	...	...
LH 6-1	63.18	0.257	0.25	19.04	3.13	3.19	4.54	6.09	0.20	...	...	...
LH 7-1A	63.40	0.227	0.327	(26.85)	(2.35)	0.70	2.96	3.16	0.055	...	...	...
LH 10	59.05	0.203	1.76	28.90	(1.0)	1.49	3.57	2.66	1.30	...	...	...
LH 11	66.80	0.44	1.26	26.20	0.36	2.91	0.71	0.46	0.88	...	...	...
LH 12	62.75	0.83	0.21	33.15	(1.2)	0.505	0.125	1.13	(0.06)	...	...	...
LH 13	55.75	1.19	0.67	31.8	(2.00)	3.22	3.14	2.00	0.21	...	...	...
LS 1	77.7	0.243	0.213	16.3	0.448	0.55	0.039	(0.02)	4.35	...	0.128	...
LS 3	76.05	0.154	0.576	18.95	0.101	0.113	0.151	0.426	3.32	0.107	0.0110	...
UZ 52-3	81.18	1.06	0.11	16.90	0.32	0.084	0.002	...	0.12	0.08	0.068	0.040 Mg , 0.014 Be
UZ 53	82.60	0.205	0.025	16.67	0.255	0.025	≤0.001	...	0.145	...	0.055	0.01 As

CENTRE TECHNIQUE DES INDUSTRIES DE LA FONDERIE (CTIF), France

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Bronze Reference Materials (60mm dia. x 6 mm mushrooms)

CTIF No.	Cu	Sn	Pb	Zn	Fe	Ni	Mn	Si	S	P	Al	Sb	As
B1	83.0	15.10	0.202	0.88	0.085	0.063	...	0.053	0.030	0.034	0.061	0.444	...
B2	85.90	13.55	0.02	0.11	0.051	(0.004)	...	0.17	0.048	0.17	(0.003)	(≤0.002)	...
B3	80.2	12.8	1.6	2.2	0.2	1.5	0.20	0.07	0.04	0.45	0.1	0.2	...
B4	83.75	11.10	2.53	1.34	0.021	0.57	...	0.015	0.019	0.52	...	0.10	...
B5	85.95	9.90	0.48	0.42	0.18	2.28	0.082	0.049	0.067	0.041	0.039	0.47	...
B10	83.90	6.60	4.03	2.55	0.17	0.97	<0.01	<0.01	0.05	0.015	0.17	1.09	0.009
B11-1	84.5	8.3	2.0	2.0	0.2	2.06	0.02	0.2	0.098	0.07	...	0.73	...
B12	85.65	9.57	0.201	0.6	0.162	2.63	0.235	0.050	0.013	0.520	0.120	0.117	0.111
B13	86.35	10.05	0.99	1.09	0.250	0.50	0.046	0.085	0.070	0.210	0.016	0.243	0.065
B14	87.00	10.75	0.50	0.15	0.11	0.30	0.02	0.075	0.02	0.64	<0.01	0.08	0.04
B20-1	83.35	6.35	5.10	3.77	0.165	0.51	...	0.055	0.115	0.072	0.040	0.520	...
B21	83.0	5.13	3.79	6.22	0.285	1.21	...	0.135	0.047	(0.004)	...	0.18	...
B22-1	83.0	3.5	6.0	4.0	<0.10	2.5	...	<0.1	0.03	...	...	0.05	...
B23-1	83.45	7.18	7.20	1.46	(0.040)	0.086	...	0.025	0.019	0.070	0.020	0.384	...
B30-1	76.5	11.1	9.6	1.0	0.07	1.19	0.1	(<0.06)	0.075	0.05	(<0.05)	0.214	0.0088
B31	78.65	7.65	11.79	0.79	(0.015)	0.489	...	(0.047)	0.028	...	(0.031)	0.475	...
B32	74.65	5.96	16.10	1.21	0.11	1.49	...	0.075	0.027	0.041	0.085	0.13	0.0056

Cupro-Beryllium Cobalt and Cupro-Nickel Reference Materials (60mm dia. x 6mm mushrooms)

CTIF No.	Cu	Sn	Pb	Zn	Fe	Ni	Mn	Si	S	Al	Be	Co	Ag	C	Nb	Others
4583	96.35	0.25	0.084	0.094	(0.15)	2.02	0.064	0.08	...	0.029	0.84	(0.002)	...	...	...	...
4584	97.05	0.022	(0.002)	0.022	0.120	0.015	(0.002)	0.166	...	0.033	2.53	0.04	...	...	...	...
4766	96.83	0.100	0.053	0.070	0.160	0.203	0.008	0.110	...	0.027	1.58	0.64	...	...	...	(0.2) Cr
4872	97.00	0.044	0.019	0.119	0.104	0.103	<0.008	0.16	...	0.059	1.93	0.400	...	...	...	(0.04) Cr
4873	98.40	(0.007)	(0.003)	(0.003)	0.078	0.049	(0.002)	0.088	...	0.094	0.17	0.98	...	...	...	0.105 Cr
CuBeCo6	93.09	0.0135	0.0397	0.0330	0.12	(1.45)	0.0173	0.26	...	0.135	1.5	(1.90)	1.37	...	...	0.0576 Cr
CN1	85.0	(0.005)	0.085	0.2	1.1	12.3	0.8	(0.05)	0.046	(0.003)	...	...	...	(0.002)	(0.1)	...
CN2	88.5	(0.005)	0.055	0.5	1.6	7.8	1.1	0.24	0.028	(0.005)	...	...	...	(0.005)	(0.005)	...
CN4	84.0	0.058	0.006	0.07	1.8	11.2	1.5	(0.01)	(0.001)	(0.02)	...	...	...	(0.001)	0.7	...
CN33	67.1	(0.003)	0.053	0.37	1.6	29.75	0.45	0.47	0.013	(0.01)	...	...	...	0.02	0.06	0.02 P , 0.0212 Bi 0.006 Cd , <0.06 Mg 0.0224 Te
UN 3S	92.65	0.215	0.20	1.62	0.30	3.45	0.07	1.24	...	0.11	...	...	...	...	...	...

DEGERFORS LABORATORIUM AB (D-LAB), Sweden

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Ferro-Alloy Certified Reference Materials from Degerfors Laboratorium AB (D-LAB), Sweden (Finely divided material – units of 50g)

D-LAB No.	Description	C	Si	P	S	Cr	N	O	H
DFS 1	Ferro-chromium - Low Carbon	0.0549	<i>0.87</i>	<i>0.027</i>	<i>0.0017</i>	69.8	0.0973	<i>0.56</i>	<i>0.0024</i>
DFS 2	Ferro-chromium - High Carbon	9.03	<i>0.2</i>	<i>0.021</i>	<i>0.0174</i>	69.6	<i>0.0178</i>	<i>0.2</i>	...
DFS 3	Ferro-chromium - High Nitrogen	<i>0.068</i>	<i>0.54</i>	<i>0.023</i>	<i>0.016</i>	64.2	9.71	<i>3</i>	...

Nordisk Industrilaboratorium AB (NILAB), Sweden

CHEMICAL COMPOSITION (nominal mass content in %)

Alloy Steel Certified Reference Materials (500 HA and 501 HA available in finely divided form and all available in disc form – see table)

NILAB No.	Description	Unit sizes	C	Si	Mn	P	S	Cr	Mo	Ni
100 LA	Bearing Steel	34mm dia. x 20mm disc	1.002	0.283	0.333	0.012	0.018	1.517	0.012	0.027
500 HA	Stainless Steel	150g powder 38mm dia. x 20mm disc	0.041	0.720	1.541	0.024	0.012	16.93	2.73	11.00
501 HA	Highly Alloyed Steel	150g powder 38mm dia. x 20mm disc	0.014	0.676	0.858	0.020	0.003	19.79	6.14	17.69

Alloy Steel Certified Reference Materials (cont.)

NILAB No.	Al	As	Co	Cu	N	Nb	Ti	V
100 LA (cont.)	0.005	0.004	0.007	0.019	0.0046	...	0.0007	0.004
500 HA (cont.)	...	...	0.139	0.182	0.1154	0.023	...	0.074
501 HA (cont.)	0.003	...	0.159	0.761	0.223	0.007	...	0.044

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Ferro-Alloy, Calcium-Silicon, Silico-Chromium, Silico-Manganese and Electrolytic Manganese Reference Materials (Finely divided material - units of 50g)

Dillinger No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	N
DL SL01-07	Silico – Manganese	1.65	17.36	77.82	0.135	...	...	...	0.021	...	...	0.030	...
DL SL04-06	Calcium – Silicon	0.61	60.79	0.056	0.031	0.022	<0.009	<0.021	<0.007	0.333	...	...	...
DL SL12-07	Ferro – Manganese	1.630	1.113	88.00	0.081	...	0.060	...	0.022	...	...	0.039	...
DL SL17-05	Ferro – Boron	0.62	1.011	0.416	0.061	...	0.925	0.023	0.097	0.085	20.23	0.025	...
DL SL20-10	Ferro – Molybdenum	0.026	0.161	0.010	0.015	0.092	0.035	78.09	0.112	0.008	...	0.020	...
DL SL23-10	Ferro – Silicon	0.11	75.94	0.139	0.021	...	0.019	...	0.006	2.041	...	...	...
DL SL25-10	Ferro – Vanadium	0.120	0.894	1.154	0.051	0.016	0.201	0.029	0.009	0.783	...	0.008	...
DL SL28-15	Ferro – Niobium	0.043	1.580	0.842	0.065	0.056	0.028	0.020	0.019	4.82	...	...	...
DL SL29-02	Fe-Si-Ti	0.284	59.25	1.64	0.010	0.005	0.059	0.126	0.043	0.613	...	...	...
DL SL30-01	Fe-Si-Zr	0.338	51.14	0.210	0.033	0.002	0.004	...	0.013	0.852	...	...	0.027
DL SL54-03	Silico – Chromium	0.034	40.46	0.41	0.022	...	36.93	...	0.190	0.579	...	...	...
DL SL77-01	Electrolytic Manganese	0.120	1.09	95.85	0.056	0.016	0.411	...	0.0068	0.0015	...	0.0012	...

Dillinger No.	Cu	Nb	Pb	Ti	V	W	Zr	Ba	Ca	Mg	Ta	Zn	Fe
DL SL01-07 (cont.)	0.012	...	...	0.122	0.015	...	...	...	...	...	...	...	2.64
DL SL04-06 (cont.)	<0.010	...	...	0.055	...	...	...	...	30.48	0.010	...	...	5.17
DL SL12-07 (cont.)	0.016	...	...	...	0.026	...	...	...	...	...	...	0.009	8.78
DL SL17-05 (cont.)	0.072	...	...	0.025	0.006	0.127	...	...	...	...	...	...	75.71
DL SL20-10 (cont.)	0.464	...	...	...	...	...	...	...	...	...	...	...	20.66
DL SL23-10 (cont.)	0.011	...	...	0.093	...	...	...	0.042	1.019	0.029	...	...	19.42
DL SL25-10 (cont.)	0.038	0.013	...	0.071	80.85	0.025	...	...	...	0.010	...	...	14.25
DL SL28-15 (cont.)	0.209	60.15	0.140	0.185	0.013	...	0.105	...	...	...	0.856	...	28.77
DL SL29-02 (cont.)	0.022	...	...	11.21	0.154	...	0.046	...	0.220	0.234	...	...	24.80
DL SL30-01 (cont.)	...	...	...	0.073	...	...	36.06	...	0.157	...	...	...	8.87
DL SL54-03 (cont.)	0.020	...	...	0.124	0.074	...	...	...	...	...	...	...	20.93
DL SL77-01 (cont.)	0.007	...	...	...	...	...	...	...	...	...	...	0.0011	2.07

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Dust and Slag Reference Materials (Finely divided material - all units of 100g except DL SX62-05 - units of 20g)

Dillinger No.	Description	CaO	SiO ₂	Fe	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	S	SO ₃	CuO	Al ₂ O ₃	MgO	NiO	Cr ₂ O ₃
DL SX62-05	Cupola Dust	4.91	34.52	...	9.49	2.57	0.147	...	2.70	0.163	1.30	1.85	0.005	0.041
DL SX66-04	Tundish Slag	1.609	24.75	...	4.62	0.098	0.084	...	0.026	...	1.884	64.65	0.165	0.255
DL SX74-02	Zinc Slag	0.405	11.01	0.207	...	0.113	14.03	0.114	...	7.02	5.99	0.118	...	0.086

Dillinger No.	SnO ₂	V ₂ O ₅	MoO ₃	TiO ₂	PbO	SnO ₂	ZnO	Cl	F	Na ₂ O	K ₂ O	CO ₂	C(tot)	H ₂ O (900°C)
DL SX62-05 (cont.)	0.018	0.019	0.030	0.060	2.43	...	21.01	2.88	0.096	2.26	3.68	3.84	6.80	0.107
DL SX66-04 (cont.)	...	...	...	0.141	...	...	...	...	...	0.516	0.089	0.35	0.471	1.02
DL SX74-02 (cont.)	...	...	...	0.274	...	0.386	45.16	...	...	0.13	0.164	...	11.92	0.077

Dunite, Refractory, Magnesite and Uncover Compound Reference Materials (Finely divided material - units of 100g)

Dillinger No.	Description	CaO	SiO ₂	Fe	FeO	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	SO ₃	Al ₂ O ₃
DL SX10-02	Dunite	4.36	41.87	5.40	0.623	...	0.061	0.922	...	8.87
DL SX26-12	Refractory	1.80	40.80	...	...	3.10	0.135	0.279	...	36.45
DL SX42-03	Magnesite	2.06	15.94	...	...	2.75	0.090	0.059	0.070	1.27
DL SX59-03	Uncover Compound	61.81	21.41	...	...	1.36	0.046	0.151	...	3.70

Dillinger No.	MgO	NiO	TiO ₂	Cr ₂ O ₃	V ₂ O ₅	ZrO ₂	Na ₂ O	K ₂ O	C (tot)	CO ₂	H ₂ O (900°C)
DL SX10-02 (cont.)	23.79	0.023	0.929	0.037	...	...	0.068	4.80	0.332	0.767	5.95
DL SX26-12 (cont.)	13.3	0.032	1.25	0.385	0.027	0.163	0.242	0.759	0.437	0.54	0.75
DL SX42-03 (cont.)	76.81	...	0.054	...	...	...	0.375	0.019	0.396	0.104	1.01
DL SX59-03 (cont.)	10.07	...	0.183	...	...	...	0.174	0.599	...	0.016	0.023

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Fluorspar, Continuous Casting Powder, Limestone and Gravel Reference Materials (Finely divided material - all units of 100g)

Dillinger No.	Description	Ca	CaO	SiO ₂	Fe	Fe ₂ O ₃	MnO	Mn ₃ O ₄	P ₂ O ₅
DL SX27-12	Fluorspar	44.18	...	8.91	...	0.373	0.237	...	...
DL SX30-13	Continuous Casting Powder	30.73	...	37.70	...	0.437	0.045	...	0.047
DL SX35-15	Limestone	...	48.91	8.75	1.293	1.293	0.028	...	0.036
DL SX36-09	Gravel	...	0.047	96.35	0.706	0.706	...	0.20	0.019

Dillinger No.	S	SO ₄	Al ₂ O ₃	MgO	TiO ₂	Na ₂ O	K ₂ O	V ₂ O ₅	Cr ₂ O ₃	F
DL SX27-12 (cont.)	...	0.103	1.01	0.739	0.069	...	0.125	...	0.106	40.6
DL SX30-13 (cont.)	0.077	...	5.95	1.93	0.064	6.43	0.288	...	...	5.72
DL SX35-15 (cont.)	0.025	...	0.787	0.379	0.048	0.032	0.187	...	...	...
DL SX36-09 (cont.)	...	...	1.46	0.104	0.086	0.045	0.334	<0.006	0.029	...

Dillinger No.	BaO	Co ₃ O ₄	NiO	CuO	ZnO	SnO ₂	PbO	SrO	CO ₂	H ₂ O (900°C)
DL SX27-12 (cont.)	...	...	0.153	0.199	0.103	0.054	0.102	...	2.11	0.370
DL SX30-13 (cont.)	0.121	...	...	...	...	...	...	0.034	...	...
DL SX35-15 (cont.)	...	...	...	...	...	...	...	0.050	...	...
DL SX36-09 (cont.)	...	0.005	...	...	...	...	...	...	<0.025	0.043

Cover Powder and Rutile Reference Materials (Finely divided material - DL SX57-04 - units of 20g, DL SX58-05 - units of 100g)

Dillinger No.	Description	CaO	SiO ₂	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	S	Al ₂ O ₃	MgO
DL SX57-04	Cover Powder	0.302	92.49	0.090	0.067	0.273	0.071	0.198	0.362
DL SX58-05	Rutile	0.035	0.297	3.53	0.124	0.147	0.027	0.500	0.032

Dillinger No.	Cr ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	V ₂ O ₅	Nb ₂ O ₅	ZrO ₂	C	CO ₂	H ₂ O (900°C)
DL SX57-04 (cont.)	...	...	0.070	0.97	...	...	...	3.60	0.008	1.38
DL SX58-05 (cont.)	0.117	93.35	...	...	0.243	0.532	0.198	0.23	...	...

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Iron Ore Reference Materials (Finely divided material – units of 100g)

Dillinger No.	CaO	SiO ₂	Fe	FeO	Mn	P ₂ O ₅	S	Al ₂ O ₃	MgO	Cr ₂ O ₃	V ₂ O ₅	TiO ₂	Na ₂ O	K ₂ O	C(tot)	CO ₂	H ₂ O (900°C)
DL SX11-13	0.030	1.80	66.33	0.04	0.432	0.084	0.002	1.11	0.040	0.010	0.007	0.046	<0.003	0.010	0.035	...	1.244
DL SX11-14	0.421	7.47	65.55	27.20	0.029	0.028	0.019	0.271	0.565	0.006	0.002	0.060	0.078	0.061	0.125	...	...
DL SX11-15	0.494	5.79	63.17	...	0.074	0.101	...	2.68	0.244	0.005	0.010	0.128	0.020	0.008	...	...	...
DL SX11-16	1.149	4.67	64.69	...	0.198	0.058	...	0.722	0.400	0.038	0.009	0.078	0.016	0.023	0.016	0.026	0.059
DL SX11-18	0.052	1.56	64.72	...	0.713	0.141	0.009	1.785	0.057	...	0.017	0.075	0.014	0.020	0.085	0.033	2.51
DL SX11-23	0.034	2.67	64.80	0.133	0.049	0.123	0.011	1.619	0.037	...	0.005	0.047	0.006	0.008	0.058	...	...
DL SX11-25	2.53	2.52	64.05	0.193	0.068	0.087	0.010	1.20	0.421	0.002	0.008	0.045	0.016	0.033	0.671	0.929	...
DL SX11-35	0.011	0.696	64.69	0.06	1.520	0.140	0.006	1.49	0.033	...	...	0.052	...	0.016	0.069	0.007	2.31
DL SX11-36	0.370	3.35	65.74	...	1.21	0.017	0.002	0.345	0.083	0.025	0.006	0.023	0.025	0.033	0.016	0.030	0.057
DL SX11-37	1.930	2.365	66.15	0.32	0.038	0.113	0.003	0.442	0.164	0.017	...	0.032	0.020	0.011	0.101	0.089	0.080

Some additional information is also given regarding the following oxides and trace element in these iron ore samples:- CuO, NiO, ZnO, Co₃O₄ and U.

Cement Reference Materials (Finely divided material – units of 100g)

Dillinger No.	Ca	CaO	SiO ₂	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	S	Al ₂ O ₃	MgO	TiO ₂	SrO	K ₂ O	Na ₂ O	BaO	V ₂ O ₅
DL SX02-09	48.78	...	21.95	0.204	0.025	0.043	1.19	4.63	0.717	0.095	0.051	1.01	0.078	0.028	...
DL SX02-10	33.39	46.72	30.30	1.66	0.327	0.066	1.77	9.99	4.96	0.421	0.077	0.541	0.236	0.071	0.011
DL SX02-11	40.63	...	25.04	2.98	0.172	0.137	1.48	6.86	2.79	0.319	0.083	0.524	0.156	0.041	0.014
DL SX02-12	46.48	...	21.16	3.94	0.062	0.191	1.18	4.41	0.945	0.242	0.086	0.495	0.084	...	...

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

FLUXANA GMBH & CO. KG REFERENCE MATERIALS (FLX), GERMANY

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Cement Reference Materials (Finely divided material – unit weights as shown)

FLX No.	Unit Weight	Al ₂ O ₃	CaO	Cl	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	Mn ₂ O ₃	Na ₂ O	P ₂ O ₅	S	SiO ₂	SO ₃	SO ₄ as SO ₃	SrO	TiO ₂	ZnO	LOI
FLX-CRM 100	50g	5.54	64.51	(0.09)	0.009	2.62	0.82	1.47	0.066	0.23	0.166	(0.06)	20.89	2.97	...	0.286	0.283	0.051	2.37
FLX-CRM 101	50g	8.81	48.24	(0.05)	0.01	3.52	2.1	1.7	0.118	0.68	0.191	(0.06)	30.31	3.16	...	0.248	0.469	0.044	3.84
FLX-CRM 103	50g	7.75	54.9	...	0.007	1.78	0.77	4.44	0.17	0.33	0.09	...	26.95	2.73	...	0.07	0.372	0.014	...
FLX-CRM 105	30g	4.27	65.24	0.049	0.008	2.5	1.24	1.57	0.04	0.21	0.0053	...	20.84	3.37	...	0.146	0.179	0.054	(2.61)
FLX-CRM 106	30g	5.7	66.05	0.055	0.008	1.98	0.86	0.96	0.161	0.12	0.111	...	20.29	3.01	...	0.206	0.271	0.012	(2.06)
FLX-CRM 107	30g	4.23	67.19	0.043	0.006	1.29	0.7	0.7	0.04	0.18	0.16	...	21.81	3.13	...	0.151	0.194	0.013	(6.59)
FLX-CRM 108	30g	4.66	65.15	0.042	0.007	2.97	0.74	2.15	0.219	0.09	0.169	...	20.06	3.31	...	0.083	0.186	0.036	(2.68)
FLX-CRM 109	30g	4.25	66.45	0.049	0.008	2.32	1.06	1.59	0.051	0.18	0.052	...	20.39	3.11	...	0.144	0.0203	0.042	(5.96)
FLX-CRM 110	30g	4.7	68.13	0.008	0.004	0.18	0.94	0.65	0.029	0.05	0.037	...	22.01	2.88	...	0.041	0.17	0.003	(3.46)
FLX-CRM 130	30g	11.62	56.6	...	0.021	2.88	0.682	1.84	0.062	0.277	0.067	...	14.35	10.91	(10.18)	0.052	0.563	0.018	(5.12)
FLX-CRM 131	30g	23.1	42.89	...	0.038	3.24	0.287	1.62	0.029	0.466	0.06	...	8.73	18.19	(17.85)	0.067	1.15	0.006	(2.03)

Glass Reference Materials (Discs - dimensions as shown)

FLX No.	Description	Dimensions	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	MnO	CaO	MgO	Na ₂ O	K ₂ O	SO ₃	BaO	Cr ₂ O ₃	PbO	ZnO	ZrO ₂
FLX-DGG1	Soda-lime Glass	40mm dia. x 10mm	71.72	1.23	0.137	0.191	...	6.73	4.18	14.95	0.338	0.436	...	...	...	...	...
FLX-DGG2	Float Glass	40mm dia. x 5mm	72.26	0.1	0.033	0.021	...	10.05	3.4	13.78	...	0.27	...	...	...	...	...
FLX-Q0	Quartz Glass	40mm dia. x ~5mm	...	<0.1	0.0103	0.0103	<0.0002	<0.0002	<0.1	<0.1	<0.0003	<0.01	<0.025	<0.0002	<0.0007	<0.0003	<0.02

FLX No.	As ₂ O ₃	CdO	CeO ₂	Co ₃ O ₄	CuO	Gd ₂ O ₃	La ₂ O ₃	NiO	Sb ₂ O ₃	SeO ₂	SnO ₂	SrO	TeO ₂	Y ₂ O ₃
FLX-Q0 (continued)	<0.016	<0.0009	<0.05	<0.0002	<0.000	<0.3	<0.0005	<0.0003	<0.0014	<0.0004	<0.0013	<0.8	<0.0018	<0.3

XRF Monitor Glass (40mm dia. x approx. 3mm disc)

FLX No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	MnO	CaO	MgO	Na ₂ O	K ₂ O	SO ₃	P ₂ O ₅	B ₂ O ₃	SrO	Cl	F
FLX-Z1	XRF Monitor Glass	14.01	0.62	0.09	0.09	0.04	30.22	0.44	5.80	0.09	2.97	0.23	bal.	0.01	0.84	3.23

INSTITUTE OF CERTIFIED REFERENCE MATERIALS (ICRM), RUSSIA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified and figures in brackets are for information only.

High Alloy Steel Certified Reference Materials (LG57-LG64 31-42mm dia. x 25-35mm discs; LG65-LG68 38-40mm dia. x 15-23mm discs; LG73-LG78 40-50mm dia. x 25-32mm discs)

ICRM No.	Description	C	Si	Mn	Cr	P	S	Mo	Ni	Al	Co	Cu	N	Ti	Nb	V	W
LG57	High Alloy Steel	0.016	0.56	0.52	13.70	0.011	0.0023	0.401	25.2	0.151	...	0.080	...	1.81	(0.008)	0.65	4.24
LG58	Stainless Steel	0.48	0.292	0.99	23.4	0.0135	0.0280	2.41	4.26	(0.006)	...	0.388	...	0.039	0.214	0.264	0.21
LG59	High Alloy Steel	0.073	0.63	1.15	15.81	0.011	0.0083	0.094	35.1	0.079	...	0.083	...	1.12	0.106	0.273	3.08
LG60	High Alloy Steel	0.020	0.289	2.31	21.8	0.028	0.0205	3.62	19.86	0.040	...	0.027	...	0.265	0.83	0.229	0.115
LG61	Stainless Steel	0.307	0.83	1.51	18.8	0.0133	0.0107	1.05	9.18	0.033	...	0.065	...	0.40	0.47	0.197	1.11
LG63	High Alloy Steel	0.068	0.285	0.356	10.13	0.010	0.0050	1.65	22.15	0.45	...	0.024	...	2.98	0.113	0.086	0.43
LG64	High Alloy Steel	0.049	0.76	0.75	24.7	0.017	0.0032	2.89	28.3	0.189	...	2.88	...	0.64	0.048	0.094	0.013
LG65	High Mn Steel	1.19	0.49	12.2	0.19	0.080	0.0033	...	0.11	0.006	...	0.119	...	...	...	...	...
LG66	High Mn Steel	0.44	0.41	16.1	0.30	0.031	0.010	...	0.059	2.6	...	0.104	...	...	...	...	...
LG67	High Mn Steel	0.39	0.31	20.9	0.19	0.020	0.007	...	0.11	2.88	...	0.090	...	...	...	1.09	...
LG68	High Mn Steel	0.89	...	28.8	0.13	(0.02)	0.003	0.46	0.20	8.6	...	0.11	...	...	0.46	...	...
LG73	Stainless Steel	0.098	0.570	1.26	22.60	0.019	0.0073	0.061	17.74	...	0.247	0.140	0.0319	0.0022	...	...	0.018
LG74	Stainless Steel	0.373	2.49	0.962	18.30	0.024	0.0049	0.104	23.66	0.035	0.031	0.093	0.030	0.030	...	...	0.052
LG75	Stainless Steel	0.027	0.298	0.728	14.80	0.0046	0.0026	0.052	24.5	0.113	0.019	0.029	0.0044	1.76	...	...	4.14
LG76	Stainless Steel	0.445	0.455	0.342	13.77	0.021	0.0076	0.263	13.39	0.034	...	0.098	0.031	0.020	...	0.041	2.38
LG78	Stainless Steel	0.074	0.58	1.60	14.71	0.017	0.0017	0.061	35.4	0.15	...	0.053	0.0062	1.31	0.004	0.020	3.16

Slag, Flux and Refractory Certified Reference Materials (Finely divided material – unit weights as shown)

ICRM No.	Description	Unit Weight	Fe	Fe ₂ O ₃	SiO ₂	CaO	MgO	Al ₂ O ₃	MnO	P	S	TiO ₂	K ₂ O	Na ₂ O	CaF ₂	C	FeO	V ₂ O ₅	Cr ₂ O ₃	CaCO ₃
SH4/4	Steel-smelting Slag	100g	23.2	...	16.7	25.5	18.3	3.62	4.17	0.259	0.037	1.02	...	...	...	...	25.5	...	...	...
SH6/2	Flux	125g	...	1.30	39.2	12.72	1.60	3.00	38.5	0.069	0.0092	...	...	...	7.71	...	...	...	...	...
SH7/3	Flux	100g	...	...	23.4	24.0	11.4	29.8	0.40	0.011	0.031	...	0.94	1.41	28.5	...	0.56	...	...	...
SH8/4	Flux	100g	0.147	...	1.77	(52.7)	...	26.5	...	0.013	0.013	...	...	...	68.6	0.039	...	...	...	...
SH9/3	Vanadium Slag	150g	28.9	...	16.63	1.61	3.53	1.76	9.73	0.015	0.015	7.39	...	...	...	...	...	22.2	3.32	...
SH12/3	Alumina, Semi-conc.	75g	0.66	...	0.76	18.8	2.15	73.6	...	...	...	...	...	...	...	...	...	...	0.46	...
SH13	Fluorite Concentrate	100g	0.353	...	...	...	...	...	...	0.012	0.103	...	...	...	84.7	...	...	...	...	0.51
K10/3	Corundum	125g	...	1.82	(0.2)	(0.03)	...	97.0	...	...	...	0.35	(0.03)	(0.5)	...	(0.05)	...	...	...	...
K11	Clay, Bentonitic	50g	...	(6.3)	62.2	1.61	2.01	16.8	0.064	...	0.050	0.98	...	...	...	...	...	...	...	...

INSTITUTE OF CERTIFIED REFERENCE MATERIALS (ICRM), RUSSIA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified and figures in brackets are for information only.

Ferro-Alloy Certified Reference Materials (Finely divided material – units of 100g)

ICRM No.	Description	C	Si	Mn	Cr	S	P	Al	Cu	Ti	Fe	V	Zn	N	As	Sn	Pb	Mo	Others
F5/3	Manganese, Metallic	0.079	1.25	95.9	...	0.0095	0.062	...	0.0055	...	2.73	...	...	...	...	...	...	...	...
F7/4	Ferro-Manganese	6.80	0.269	79.8	...	0.0037	0.372	...	...	...	12.75	...	...	...	...	...	...	...	...
F8/2	Chromium Metal	0.029	0.250	...	99.2	0.013	0.0035	0.17	0.0014	...	0.26	...	0.0030	0.025	0.00027	0.00030	0.00033	...	...
F17/4	Ferro-Molybdenum	0.081	0.54	...	...	0.066	0.032	...	0.52	...	...	...	0.0064	...	0.0111	0.0023	0.0029	59.2	0.022 W, 0.0039 Sb, 0.00056 Bi
F18/2	Ferro-Tungsten	0.075	0.35	0.095	...	0.071	0.042	...	0.105	...	...	...	(<i><0.0001</i>)	...	0.028	0.038	0.00014	0.56	74.7 W, 0.0069 Sb, (<i><0.0001</i>) Bi
F19/3	Ferro-Vanadium	0.418	1.47	3.30	1.21	0.0102	0.059	(<i>0.005</i>)	0.204	...	...	42.6	...	...	0.0009	...	...	...	...
F20/3	Ferro-Niobium	0.136	0.67	...	...	0.0091	0.039	0.35	...	0.292	33.3	...	...	0.067	...	0.0014	...	...	63.5 Nb+Ta, 0.0056 Co
F21/2	Ferro-Boron	0.047	0.73	...	...	...	0.0119	1.546	0.0120	...	...	...	0.0055	...	...	...	...	...	20.91 B
F22/3	Ferro-Boron	0.161	7.82	...	...	0.018	0.021	7.78	3.43	...	...	...	...	...	...	...	...	...	8.95 B
F24/2	Ferrosilicochromium	0.019	49.9	...	29.18	0.0015	0.027	0.87	...	...	...	...	...	...	...	...	...	...	...
F25/3	Ferro-Calcium	...	51.5	...	...	0.0056	0.011	0.67	...	...	23.06	...	...	...	...	...	...	...	21.3 Ca
F26/2	Ferro-Calcium	...	59.5	...	...	0.030	0.024	1.52	...	0.156	6.29	...	...	...	(<i><0.001</i>)	...	...	...	29.9 Ca
F27/2	Ferrosilicozirconium	0.111	26.1	...	...	(<i>0.001</i>)	0.044	7.48	1.47	0.215	(<i>12</i>)	...	...	...	...	...	...	...	51.5 Zr
F28/2	Ferro-Phosphorus	...	1.11	1.20	...	0.021	16.05	...	...	...	...	...	...	...	...	...	...	...	...
F29/3	Manganese, Metallic	0.146	...	87.5	...	0.031	0.055	...	...	...	2.26	...	...	4.63	...	...	...	...	...
F30/4	Ferro-Titanium	0.154	0.163	0.189	0.154	0.0054	0.0030	3.83	0.065	70.3	21.51	2.29	...	0.38	...	0.077	...	0.60	0.053 Ni, 0.231 Zr
F32/3	Ferro-Vanadium, Nitrated	(<i>0.4</i>)	(<i>1.2</i>)	3.14	...	(<i>0.008</i>)	(<i>0.05</i>)	(<i><0.05</i>)	(<i>0.2</i>)	...	...	40.2	...	7.51	(<i><0.001</i>)	...	...	...	...
F35/2	Ferro-Chromium	0.79	0.181	...	68.9	0.0022	0.027	...	...	...	28.16	...	...	0.185	...	...	...	...	...
F40	Ferro-Vanadium	0.096	1.31	1.49	0.185	0.014	0.022	2.12	0.081	...	...	80.1	...	...	...	...	...	...	...
F41	Ferro-Nickel - low Fe	0.0124	...	...	...	0.132	...	...	0.47	...	5.68	...	...	...	0.058	...	...	...	91.4 Ni, 2.04 Co
F42	Ferro-Titanium	0.55	6.74	1.10	2.22	0.023	0.050	11.41	1.32	27.15	...	0.249	0.129	(<i>0.15</i>)	...	0.033	...	0.106	(<i>0.44</i>) Zr
F43	Ferro-Titanium	0.098	2.50	1.22	0.354	0.0058	0.038	11.11	0.336	31.9	...	0.152	0.032	0.085	...	0.013	...	0.0036	0.059 Zr
F44	Silico-calcium with Mg	0.166	49.7	...	...	0.0066	0.014	1.68	...	...	19.91	(<i>2.5</i>)	...	...	...	...	...	...	12.6 Ca, 9.6 Mg
F45	Ferro-Chromium	0.071	1.10	...	69.0	0.0024	0.027	0.041	...	...	...	...	...	0.082	...	...	...	...	...
F46	Ferro-Chromium	5.47	1.05	...	68.8	0.015	0.030	...	...	...	...	...	...	0.055	...	...	...	...	...
F47	Ferro-Chromium	8.80	0.103	...	69.8	0.036	0.025	...	...	...	...	...	...	0.020	...	...	...	...	...
F48	Ferro-Tungsten	0.074	0.47	0.695	...	0.211	0.035	0.64	0.096	...	...	...	...	...	0.037	0.031	0.0048	0.047	71.0 W, 0.014 Sb
F50	Ferro-Chromium	0.079	1.29	...	64.3	0.0058	0.0048	0.168	...	...	...	...	...	11.2	...	...	...	...	...

INSTITUTE OF GEOLOGICAL SCIENCES/BRITISH GEOLOGICAL SURVEY (IGS), U.K.

CHEMICAL COMPOSITION (nominal mass content in %)

Ore and Concentrate Reference Materials (Finely divided material - approximate unit weights as shown)

IGS No.	Description	Unit Weight	Ba	Cu	F	Fe	MnO ₂	Nb	Sr	Ti	W	SiO ₂	Others
27	Molybdenum-Tungsten Ore	65g	...	2.11	...	1.76	...	...	...	...	0.036	...	0.276 Mo
29	Pyrolusite	40g	0.59	0.185	...	...	93.38	...	...	...	...	2.21	...
30	Chromite	55g	...	...	...	11.20	...	...	...	0.14	...	2.76	23.95 Cr, 16.63 MgO 29.12 Al ₂ O ₃
32	Rutile	45g	...	...	...	...	...	0.26	...	57.19	...	...	...
35	Zircon	50g	...	...	...	...	...	...	...	0.16	...	...	1.20 Hf, 48.96 Zr
39	Fluorite	55g	0.44	...	46.85	...	...	...	0.014	...	...	...	...

SOCIETY OF GLASS TECHNOLOGY (SGT), U.K.

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Glass Certified Reference Materials (Broken pieces - units of 25g) (G4, G7, G10 and G11 are also available as 40mm dia. glass discs)

SGT No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	BaO	Na ₂ O	K ₂ O	PbO	As ₂ O ₃	B ₂ O ₃	TiO ₂	Cr ₂ O ₃	ZnO	ZrO ₂	Mn ₃ O ₄	F	SO ₃	LOI (550°C)
G4	Fluoride Opal Glass	69.49	3.02	0.099	4.24	<0.05	...	15.45	0.57	...	...	0.19	0.041	...	3.28	...	...	4.96	<0.05*	0.22
G6	Soda-Lime-Silica Glass	73.06	1.70	0.034*	9.97	<0.1	...	14.65	<0.1	...	...	...	0.02	...	...	...	...	...	0.20*	...
G7	Soda-Lime-Silica Glass	72.64	1.50	0.044*	11.03	0.14	...	13.90	0.43	...	...	...	0.042	...	...	...	...	...	0.19*	0.07
G8	Lead Oxide-Potassium Oxide-Silica Glass	56.34	0.05	0.010*	<0.02	<0.02	...	0.23	11.85	30.59	0.32*	0.36	0.02	...	...	...	...	...	...	0.21
G10	Amber Soda-Lime-Silica Container Glass	72.7	1.62	0.325	10.7	1.81	0.02	12.2	0.35	...	...	...	0.097	0.020	...	(0.024)	(0.038)	...	0.05	...
G11	Green Soda-Lime-Silica Container Glass	70.7	1.83	0.342	10.3	2.14	0.03	13.6	0.69	...	...	...	0.068	0.205	...	(0.015)	(0.034)	...	0.06	...

* Total iron as iron (III) oxide Fe₂O₃

* Total arsenic as As₂O₃

* Total sulphur as SO₃

HEALTH AND SAFETY LABORATORY (HSL), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Welding Fume Reference Materials (Finely divided material – units of 1g)

HSL No.	Description	Fe	Mn	Ni	Cr	Zn
MSWF-1	Elements in Mild Steel Welding Fume	<i>42.8</i>	<i>1.48</i>	<i>...</i>	<i>...</i>	<i>21.7</i>
SSWF-1	Elements in Stainless Steel Welding Fume	<i>29.8</i>	<i>22.9</i>	<i>3.7</i>	<i>8.4</i>	<i>...</i>

Respirable α -Quartz Reference Material (Finely divided material – units of 5g)

HSL No.	Description	% Crystallinity
A9950	Respirable α -Quartz Powder	89.3

IMI WOLVERHAMPTON METAL (IMI), U.K.
CHEMICAL COMPOSITION (nominal mass content in %)

Aluminium Alloy Reference Materials (Mushroom samples, approx. 58mm diameter x 7mm thick)

IMI Ref No.	Description	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr
IMI 2WM1	BS 1490: LM 2	<i>1.69</i>	<i>0.005</i>	<i>8.90</i>	<i>0.26</i>	<i>0.60</i>	<i>0.39</i>	<i>2.42</i>	<i>0.21</i>	<i>0.20</i>	<i>0.20</i>	<i><0.005</i>
IMI 2WM3		<i>0.41</i>	<i>0.19</i>	<i>8.33</i>	<i>1.19</i>	<i>0.35</i>	<i>0.21</i>	<i>0.70</i>	<i>0.10</i>	<i>0.10</i>	<i>0.11</i>	<i>0.09</i>
IMI 4P1	BS 1490: LM 4	<i>1.80</i>	<i>0.25</i>	<i>5.92</i>	<i>0.25</i>	<i>0.63</i>	<i>0.40</i>	<i>0.01</i>	<i>0.19</i>	<i>0.19</i>	<i>0.21</i>	<i><0.005</i>
IMI 4P2		<i>2.35</i>	<i>0.19</i>	<i>5.50</i>	<i>0.40</i>	<i>0.54</i>	<i>0.31</i>	<i>0.16</i>	<i>0.14</i>	<i>0.15</i>	<i>0.15</i>	<i>0.05</i>
IMI 4P4		<i>3.69</i>	<i>0.045</i>	<i>4.55</i>	<i>0.84</i>	<i>0.30</i>	<i>0.11</i>	<i>0.46</i>	<i>0.05</i>	<i>0.055</i>	<i>0.05</i>	<i>0.15</i>
IMI 4P5		<i>4.25</i>	<i><0.005</i>	<i>3.94</i>	<i>1.03</i>	<i>0.14</i>	<i><0.005</i>	<i>0.61</i>	<i><0.005</i>	<i><0.005</i>	<i><0.005</i>	<i>0.19</i>
IMI 620WM5	BS 1490: LM 6/9/20	<i><0.005</i>	<i>0.005</i>	<i>12.85</i>	<i>0.15</i>	<i>0.84</i>	<i><0.005</i>	<i>0.005</i>	<i><0.005</i>	<i><0.005</i>	<i>0.005</i>	<i>0.14</i>
IMI 231P2	BS 1490: LM 20	<i>0.41</i>	<i>0.22</i>	<i>12.64</i>	<i>0.46</i>	<i>0.48</i>	<i>0.10</i>	<i>0.16</i>	<i>0.055</i>	<i>0.055</i>	<i>0.16</i>	<i>0.14</i>
IMI 24WM6	BS 1490: LM 24	<i>1.85</i>	<i>0.20</i>	<i>6.55</i>	<i>1.02</i>	<i>0.63</i>	<i>0.45</i>	<i>0.56</i>	<i>0.26</i>	<i>0.10</i>	<i>0.23</i>	<i>0.19</i>
IMI 25WM1	BS 1490: LM 25	<i><0.005</i>	<i>0.87</i>	<i>5.92</i>	<i>0.59</i>	<i>0.24</i>	<i>0.19</i>	<i>0.20</i>	<i><0.005</i>	<i>0.12</i>	<i>0.19</i>	<i><0.005</i>
IMI 25WM5		<i>0.075</i>	<i>0.19</i>	<i>8.36</i>	<i>0.42</i>	<i>0.15</i>	<i><0.005</i>	<i>0.015</i>	<i>0.07</i>	<i><0.005</i>	<i><0.005</i>	<i>0.10</i>
IMI 27WM2	BS 1490: LM 27	<i>1.52</i>	<i>0.12</i>	<i>7.79</i>	<i>0.35</i>	<i>0.57</i>	<i>0.30</i>	<i>0.63</i>	<i>0.14</i>	<i>0.045</i>	<i>0.16</i>	<i>0.12</i>
IMI 27WM3		<i>1.98</i>	<i>0.18</i>	<i>7.50</i>	<i>0.55</i>	<i>0.40</i>	<i>0.20</i>	<i>0.80</i>	<i>0.10</i>	<i>0.085</i>	<i>0.11</i>	<i>0.075</i>
IMI 27WM5		<i>2.79</i>	<i>0.36</i>	<i>5.60</i>	<i>0.91</i>	<i>0.10</i>	<i>0.005</i>	<i>1.13</i>	<i><0.005</i>	<i>0.15</i>	<i>0.005</i>	<i><0.005</i>

Note that all the IMI RMs have a dimple, approx 15mm diameter, in the surface and hence are unsuitable for XRF analysis.

INDUSTRIAL ANALYTICAL (PTY) LTD. (IA), SOUTH AFRICA
CHEMICAL COMPOSITION (nominal mass content) – Figures in brackets are for information only.

Concentrate/Tailing Reference Materials (Finely divided material – unit of 120g) (nominal mass content in %)

IA No.	Description	SiO ₂	Al ₂ O ₃	CaO	MgO	Pb	Cu	Zn	Fe	C	S	Mn	As	Sn	Cd	Ni	Ag
RPZ-PC	Lead Concentrate	1.26	0.22	4.06	2.30	52.13	0.66	7.05	5.03	3.45	16.76	0.39	0.059	0.012	0.015	0.00052	0.0660
RPZ-PF	Lead Feed Stock	14.32	1.66	14.12	8.48	3.85	0.29	12.85	5.16	5.77	1.57	1.35	0.023	0.018	0.026	0.00071	0.0070
RPZ-ZC	Zinc Concentrate	0.53	0.14	1.80	0.89	3.53	0.65	55.26	4.02	0.89	31.75	0.77	0.023	0.012	0.11	0.00032	0.0310

Concentrate/Tailing Reference Materials (Finely divided material – units of 120g) (nominal mass content in µg/g)

IA No.	Description	Co	Cu	Ni	Au	Pt	Pd	Rh	Ru	Ir	Ag
HGC	High Grade Sulphide Concentrate	1600	69500	61500	9.7	81.5	47.5	4.79	4.44	2.42	(14.7)
HGT	High Grade Tail	97	230	78	0.13	0.40	0.32	0.05	0.051	0.016	(0.27)
LGC	Low Grade Sulphide Concentrate	1000	29100	34900	5.39	38.5	27.0	2.89	2.74	1.44	(0.98)
LGT	Low Grade Tail	97	220	700	0.097	0.37	0.28	0.05	0.053	0.023	(0.18)
MGC-A	Medium Grade Sulphide Concentrate A	1030	31900	35700	5.56	40.4	29.1	3.28	3.02	1.55	(1.17)
MIM C2	PGM bearing Pyroxenite Concentrate	1230	33100	42800	4.90	44.5	33.4	4.01	3.76	2.18	(5.5)
MIM T2	PGM bearing Pyroxenite Tailing	70	180	840	0.13	0.358	0.384	0.048	0.055	(<0.5)	(0.15)

Nickel Ore/Concentrate/Tailing Reference Materials (Finely divided material – unit of 130g) (nominal mass content in %)

IA No.	Description	Ni	Co	Cu	Si	Fe	Ca	Mg	Al	S	Ti
TN-O 01	Tati Nickel Ore	0.40	0.014	0.31	22.52	7.07	6.41	5.48	9.32	1.94	...
TN-T 01	Tati Nickel Tailing	0.083	0.0047	0.047	...	...	...	...	...	0.22	0.20

Nickel Ore/Concentrate/Tailing RMs (continued) (nominal mass content in µg/g)

IA No.	Au	Pt	Pd	Rh	Ag	Sn	Se	Te	Zn	Pb	Cd	Cr	As	Mn	Bi	V
TN-O 01 (cont.)	0.04	0.15	0.65	(<0.01)	0.60	0.73	11.50	0.82	46.5	10.80	22.10	547	12.0	771	0.75	101
TN-T 01 (cont.)	...	...	...	...	...	...	...	...	...	...	...	490	...	860	...	...

Ferro-Alloy Slag Reference Materials (Finely divided material – units of 120g) (nominal mass content in %)

IA No.	Description	SiO ₂	Al ₂ O ₃	FeO	Fe ₂ O ₃	MnO	MgO	CaO	B ₂ O ₃	Cr ₂ O ₃
XS-FCS	Ferro-Chrome Slag	24.34	23.72	10.82	...	...	15.39	3.91	...	22.45
SAM-FMS1	Ferro-Manganese Slag	30.21	4.95	...	0.065	...	7.38	30.26	0.59	...
SAM-SMS1	Silico-Manganese Slag	43.28	8.96	...	0.178	16.81	5.16	19.47	0.26	...

INSTITUTO DE PESQUISAS TECNOLOGICAS (IPT), BRAZIL

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified and figures in italic type only approximate.

Cast Iron Certified Reference Materials (Finely divided material – units of 80g)

IPT No.	Description	C (Total)	C (Graphitic)	Si	Mn	P	S	Cr	Mo	Ni	Cu	Ti	V
49	White Iron	2.11	...	0.78	0.272	0.012	0.019	0.020	...	0.021	0.040	...	...
69	Cast Iron	3.34	2.50	2.07	0.715	0.267	0.018	0.353	0.004	0.272	0.473	0.019	...
75A	Ni-Cr-Mo-Cu Iron	3.4	2.7	1.98	0.722	0.250	0.033	0.487	0.439	0.425	0.433	0.022	0.030

Copper Base Alloy Certified Reference Materials (Finely divided material – unit weights as shown)

IPT No.	Description	Unit Weight	Cu	Sn	Pb	Zn	Ni	P	Fe	As	Sb	Bi	Al	S	Ag	Cd	Se	Te
10B	Bronze	80g	85.2	4.61	4.74	4.73	0.33	0.003	0.211	0.019	0.114	...	...	0.068	...	...	...	...
40	Brass	100g	58.10	0.18	2.45	39.1	0.001	...	0.007	...	0.023	...	0.010	...	0.0015	0.049	...	...
64	Pure Copper	50g	99.98	<0.0005	0.00006	0.001	0.00018	...	0.00045	0.0002	0.0002	<0.0001	<0.0006	...	0.0010	...	<0.0002	<0.0001
74	Bronze	60g	80.41	2.84	6.24	9.88	0.15	0.002	0.315	0.002	0.016	...	...	0.056	...	0.013	...	...

Silicon Metal Certified Reference Materials (Finely divided material – units of 60g)

IPT No.	Fe	Ca	Al	C	S	Mn	Ti	Mg	P	Cu	Cr	Ni	V	Pb
134	0.29	0.102	0.085	0.025	0.002	0.0113	0.0097	0.0048	0.0033	0.0014	0.0011	0.0006	0.0004	0.0002
135	0.125	0.011	0.045	0.018	0.002	0.0070	0.0113	0.0012	0.0027	0.0008	0.0006	0.0005	0.0003	0.0002

Clay, Refractory, Feldspar, Glass Sand, Limestone and Bauxite Certified Reference Materials (Finely divided material – unit weights as shown)

IPT No.	Description	Unit Weight	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	ZrO ₂	SrO	CaO	MgO	MnO	Li ₂ O	Na ₂ O	K ₂ O	P ₂ O ₅	LOI
32	Plastic Clay	50g	51.8	28.5	3.46	1.49	...	...	0.17	0.39	...	...	0.16	0.80	0.13	12.6
42	Clay	50g	51.9	32.2	1.09	0.96	...	...	0.05	0.19	...	...	0.02	0.47	0.07	12.9
51	Burnt Refractory	80g	55.0	40.3	1.19	2.19	0.070	...	0.06	0.20	...	0.018	0.09	0.69	0.09	0.16
53	Potash Feldspar	80g	65.8	18.3	0.13	0.013	...	...	0.27	0.05	...	...	2.5	12.1	0.072	0.51
57	Burnt Refractory	80g	24.3	71.5	1.25	1.19	0.20	0.009	0.05	0.13	...	0.008	0.35	0.83	0.054	0.20
63	Silica Refractory	80g	96.28	0.48	0.52	0.030	0.002	...	2.21	0.18	0.008	0.0005	0.013	0.043	0.013	0.17
72	Soda Feldspar	80g	66.2	20.26	0.09	0.005	...	...	0.18	0.022	...	...	10.0	1.47	1.03	0.66
122	Dolomitic Limestone	80g	4.3	1.24	0.65	0.06	...	0.018	32.0	17.5	0.042	...	0.019	0.43	0.048	43.3
131	Bauxite	70g	0.78	54.1	11.5	1.77	0.35	...	...	...	0.31	...	...	0.022	0.15	30.0

INSTITUTE FOR REFERENCE MATERIALS AND MEASUREMENTS (formerly BCR) (IRMM), Belgium

CHEMICAL COMPOSITION (nominal mass content as shown in tables) - Figures in bold type certified and figures in small italic type only approximate.

Copper Certified Reference Materials (nominal mass content in µg/g)

IRRM/BCR No.	Description	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	O	P	Pb	S	Sb	Se	Sn	Te	Zn
017	Phosphorus Deoxidised Copper	...	...	...	...	...	...	...	...	...	...	6.9	...	10.4	...	...	...	...	...
022	Electrolytic Copper	...	...	...	...	...	...	...	...	...	138	...	...	...	...	...	...	...	...
054R	Low Oxygen in Copper	...	...	...	...	...	...	...	...	...	0.47	...	...	...	...	...	...	...	...
058	Continuous Cast Copper	...	...	...	...	...	...	...	...	...	390	...	...	...	...	...	...	...	...
074	Electrolytic Copper (OFHC)	12.8	0.78	<i>0.10</i>	<0.02	<0.05	<0.1	1.14	1.27	1.04	...	...	0.97	...	0.58	0.37	<0.07	<i>0.21</i>	0.46

These copper CRMs are available in the following forms:

017B	50g of chips	054R	7mm dia. x 50mm rods
022A	26mm dia. x 9mm discs	058	7mm dia. x 50mm rods
022B	9mm dia. x 50mm rods	074A	40mm dia. x 30mm discs

Lead Certified Reference Materials (All available as finely divided material units of 160g, as 286B, 287B and 288B; also 286A and 287A available as 60 x 60 x 12mm blocks) nominal mass content in µg/g

IRRM/BCR No.	Description	Ag	As	Bi	Cd	Cu	Ni	Pb	Sb	Se	Sn	Te	Tl	Zn
286A / 286B	Electrorefined Lead	0.015	<i><0.002</i>	21.5	0.125	1.49	0.041	Bal.	0.10	<i><0.05</i>	<i><0.05</i>	<i><0.1</i>	2.5	<i><0.1</i>
287A / 287B	Thermally Refined Lead	15.20	<i>0.003</i>	67.3	0.356	0.98	<i>0.024</i>	Bal.	0.040	<i>0.050</i>	<i><0.05</i>	<i>0.200</i>	0.73	<i><0.1</i>
288B	Lead with added impurities	<i>30.5</i>	55.7	215.8	33.3	19.3	<i>4.57</i>	Bal.	<i>32.5</i>	<i><0.2</i>	<i>30.6</i>	32.8	2.26	8.2

Zinc and Zinc Alloy Certified Reference Materials (80mm dia x 20mm discs)

IRRM/BCR No.	Description	Al	Cd	Cu	Fe	In	Mg	Ni	Pb	Sn	Tl
321	Unalloyed Zinc µg/g	<0.7	<i>0.22</i>	<i>0.95</i>	<i>2.3</i>	<0.2	...	...	4.7	<0.5	0.8
EB322	" "	...	15.08	5.89	19.1	...	...	...	15.0	5.6	5.28
EB323	" "	...	6.51	18.9	11.3	...	...	...	48.6	18.7	10.8
EB324	" "	...	48.6	9.87	58.5	...	...	...	26.1	9.8	19.9
EB325	" "	...	94.7	47.5	56.1	...	...	...	142	46.1	36.8
326	" "	<i><0.7</i>	204	105	265	...	...	...	307	...	...
327	" "	...	302	<i>0.56</i>	144	...	...	...	408	...	...
351	Zamak 3	43500	<i>0.2</i>	12.1	...	<0.2	130	<i>1.9</i>	4.5	<1	0.7
352	" "	41500	2.9	31.2	...	3.0	282	6.8	<i>6.5</i>	3.0	3.2
353	" "	39500	10.5	100	...	2.6	452	...	24.7	5.5	4.0
354	" "	37300	30	311	...	9.8	604	83.5	31.0	14.0	11.0
355	" "	34400	58	1034	...	24.6	786	267	57	29.4	23
356	Zamak 5	44300	0.73	3940	31.4	<0.2	133	3.4	10	0.3	0.8
357	" "	42300	2.8	5850	25.5	3.3	273	9.8	14	3.5	2.8
360	" "	34200	60	12320	...	30	707	267	75	33.3	26.0
361	" "	<i>40700</i>	<i>0.80</i>	798	10.4	<i><0.2</i>	...	...	5.3	46.8	37.2

These tables represent only a small selection from the IRMM range, which includes samples under the headings:

Biological	Gases in Metals	Coal	Organic Compounds	Biomedical
Environmental	Non Ferrous Metals	PCBs	Flash Point	Thermal Conductivity
Particle Size Distribution	Ores	Lead Crystal Glass	Limiting Viscosity Number	Gas Mixtures
Sulphur in Fuel	Coke	Fertilizers	Cosmetic Preservatives	Polycyclic Aromatic Compounds

JERNKONTORET / SWEREA KIMAB (JK), Sweden

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Alloy Steel and Special Alloy Certified Reference Materials (Finely divided – units of 100g; also available as discs of 38mm diameter x 25mm depth)

JK No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Pb
ECRM 196-2	Silicon Steel	0.0060	1.808	0.364	0.00369	0.00065	0.0282	0.0142	0.0401	0.2167	0.00033	0.00014	0.0138	0.0057	0.00178	...
ECRM 197-1	Low alloy Steel	0.219	0.275	0.792	0.0073	0.0232	0.451	0.402	0.148	0.0313	0.0083	...	0.0135	0.152	0.0114	<i>0.0003</i>
ECRM 270-1	Stainless Steel	0.0742	1.517	0.540	0.0196	0.0007	20.88	0.2099	10.86	<i>0.0023</i>	<i>0.0034</i>	...	0.0685	0.1076	0.1417	...
ECRM 274-1	Vanadium Steel	1.563	1.057	0.397	0.0148	0.0096	8.036	1.4551	0.077	<i>0.0025</i>	<i>0.0013</i>	<i>0.0005</i>	0.023	0.0281	0.0769	<i>0.000064</i>
ECRM 298-1	Duplex Steel	0.0146	0.262	0.398	0.0198	0.0006	24.72	3.799	7.056	0.0285	<i>0.003</i>	0.0021	0.055	0.201	0.263	0.00008
ECRM 379-1	Stainless Steel	0.0121	0.393	1.804	0.0166	0.0006	26.79	3.290	30.83	<i>0.0246</i>	<i>0.0028</i>	0.00190	0.0390	0.984	0.0550	<i>0.000038</i>

Alloy Steel and Special Alloy Certified Reference Materials (cont.)

JK No.	Sn	Ti	V	W	Bi	Ca	Ce	Ga	Ir	La	Mg	Nb	Pr	Sb	Zn	Fe	O
ECRM 196-2 (cont.)	0.00047	0.00253	0.00368	...	...	0.00071	...	...	...	...	0.00075	...	...	...	0.00019	...	...
ECRM 197-1 (cont.)	0.0097	0.0005	<i>0.005</i>	...	...	...	...	...	...	...	...	...	...	<i>0.002</i>	...	...	...
ECRM 270-1 (cont.)	<i>0.0035</i>	<i>0.0019</i>	0.0256	<i>0.0244</i>	...	...	0.0487	<i>0.0021</i>	<i>0.0002</i>	0.0154	<i>0.0009</i>	...	<i>0.00295</i>	<i>0.0007</i>	<i>0.00074</i>	...	...
ECRM 274-1 (cont.)	<i>0.001</i>	<i>0.0011</i>	4.010	0.0087	...	...	...	...	...	...	...	...	...	<i>0.0002</i>	...	...	<i>0.0026</i>
ECRM 298-1 (cont.)	<i>0.004</i>	0.0014	0.0607	<i>0.02</i>	<i>0.000006</i>	<i>0.002</i>	<i>0.00004</i>	<i>0.0023</i>	<i>0.00002</i>	...	<i>0.0008</i>	<i>0.004</i>	...	<i>0.0007</i>	...	63.38	<i>0.0036</i>
ECRM 379-1 (cont.)	0.0021	<i>0.0014</i>	0.0663	<i>0.0091</i>	<i>0.00001</i>	0.0033	<i>0.00001</i>	<i>0.0023</i>	<i>0.00001</i>	...	<i>0.0006</i>	<i>0.0028</i>	<i>0.00002</i>	0.00057	...	<i>35.6</i>	<i>0.0027</i>

Alloy Steel and Special Alloy Certified Reference Materials (Finely divided or disc material – as shown in table)

JK No.	Description	Unit	C	Si	Mn	P	S	Cr	Mo	Ni	Al _{Tot}	Co	Cu	N	Pb	Sn	V	W	Ce
JK 3B	Unalloyed Steel	150g	0.742	0.251	0.803	0.0101	0.0071	0.0529	0.0051	0.0591	0.0036	0.0048	0.0175	0.0054	<i>0.0002</i>	0.0044	<i>0.002</i>	...	...
JK 7B	Low Alloy Steel	150g	0.342	0.267	0.697	0.0057	0.0064	1.34	0.182	1.34	0.014	...	0.021	0.0050	...	...	0.004	...	...
JK 12A	Tool Steel	150g	0.886	0.30	0.312	0.020	0.023	4.04	4.85	0.191	...	0.189	0.062	0.0259	0.0004	0.007	1.94	6.42	...
JK 20A	Tool Steel	150g	1.263	...	...	...	0.0094	...	...	...	...	...	...	0.0027	0.160	...	0.161	1.75	...
JK 21	Low Alloy Steel	150g	0.1741	0.36	1.46	0.0148	0.011	0.024	0.004	0.035	...	0.008	0.045	0.008	<i>0.0010</i>	0.006	0.002	<i>0.0006</i>	...
JK 25	Stainless Steel	150g	...	...	<i>1.7</i>	...	...	<i>22.3</i>	<i>0.1</i>	<i>11.3</i>	...	...	...	...	...	...	...	...	0.096
JK 27B	Austenitic Stainless Steel	150g/disc	0.0089	0.401	1.510	0.0298	0.0207	17.36	2.510	12.56	<i>0.0021</i>	0.142	0.265	0.0630	<i>0.000097</i>	0.0068	0.057	0.031	...
JK 49	High Alloy Steel	disc	<i>1</i>	<i>0.5</i>	<i>0.4</i>	<i>0.02</i>	<i>0.01</i>	<i>5</i>	<i>3</i>	<i>0.2</i>	...	<i>0.3</i>	<i>0.1</i>	1.89	...	...	<i>9</i>	<i>4</i>	...

Alloy Steel and Special Alloy Certified Reference Materials (cont.)

JK No.	Al Acid Sol.	Al Non-Acid	As	B	Nb	Sb	Ta	Ti	Zr	Ca	O	Mg	Ag	Bi	Zn	Cd
JK 3B (cont.)	...	...	<i>0.002</i>	...	...	<i>0.0007</i>	...	<i>0.0020</i>	...	<i>0.0005</i>	<i>0.018</i>	<i>0.0001</i>	<i>0.00002</i>	<i>0.0001</i>	...	...
JK 21 (cont.)	0.032	0.005	<i>0.0100</i>	...	0.0175	<i>0.0010</i>	<i>0.0010</i>	0.0008	<i>0.0010</i>	...	...	...	...	...	<i>0.0007</i>	<i>0.0001</i>
JK 27B (cont.)	...	...	<i>(0.006)</i>	0.00072	...	<i>(0.0014)</i>	...	<i>0.0002</i>	...	0.0022	<i>0.008</i>	...	...	...	<i>0.00017</i>	...

JERNKONTORET / SWEREA KIMAB (JK), Sweden

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

C, S, N & O in Steel Certified Reference Materials (Finely divided or rod material – as shown in table)

JK No.	Description	Unit	C	Si	Mn	S	Cr	Ni	Al Tot.	Al Sol.	N	O
JK 31	Alloy Steel	8mm dia. x 500mm rod	<i>1.03</i>	<i>0.32</i>	<i>0.36</i>	...	...	...	<i>0.021</i>	<i>0.020</i>	...	0.0015
JK 32	Alloy Steel	10mm dia. x 500mm rod	<i>1.02</i>	<i>0.32</i>	<i>0.30</i>	...	<i>1.38</i>	...	<i>0.011</i>	<i>0.008</i>	...	0.0028
JK 34	Alloy Steel	8mm dia. x 500mm rod	<i>0.13</i>	<i>0.31</i>	<i>1.40</i>	...	...	...	<i>0.051</i>	<i>0.047</i>	...	0.0068
JK 35	High Alloy Steel	10mm dia. x 500mm rod	<i>0.04</i>	<i>0.31</i>	<i>1.51</i>	...	<i>17.3</i>	<i>9.9</i>	<i>0.002</i>	<i>0.001</i>	...	0.0198
JK 36	Stainless Steel	150g	0.0125	...	...	0.0126	...	...	...	...	0.0337	...

Iron Powder Certified Reference Material (Finely divided material – unit weight of 35g)

JK No.	Description	O	N	C	S
JK 47A	Iron Powder	0.69	0.0062	0.370	<i>0.0090</i>

Ferro-Alloy Certified Reference Material (Finely divided material – unit weight of 50g)

JK No.	Description	C	Si	Mn	P	Cr	Ni	Al	Ca	Co	Cu	Fe	Ti	V
JK 39	Ferro-Silicon	0.105	75.9	0.165	0.018	<i>0.01</i>	<i>0.008</i>	1.45	0.24	<i>0.002</i>	0.013	21.6	0.116	<i>0.007</i>

Iron Ore Certified Reference Material (Finely divided material – ECRMs 688-1 and 689-1 in units of 100g, JK 28 in units of 150g, JK 29A and JK 42A in units of 100g)

JK No.	Description	Fe ₂ O ₃	FeO	Fe	SiO ₂	CaO	MgO	Al ₂ O ₃	TiO ₂	MnO	P ₂ O ₅	P	S
ECRM 688-1	Iron Ore	...	...	61.38	3.383 Si	1.449 Ca	1.061 Mg	0.679 Al	0.408 Ti	0.0457 Mn	...	0.337	<i>0.047</i>
ECRM 689-1	Iron Ore	...	...	57.05	<i>5.4 Si</i>	1.183 Ca	0.980 Mg	1.185 Al	0.3264 Ti	0.1196 Mn	...	0.0706	<i>0.058</i>
JK 28	Iron Ore	91.5	2.4	65.86	4.20	0.30	0.30	0.60	0.20	0.059	0.102	0.045	0.004
JK 29A	Magnetite	...	...	71.36	0.33	0.082	0.223	0.232	0.292	0.0632	...	0.0059	0.0059
JK 42A	Magnetite	...	...	70.66	0.800	0.199	0.382	0.278	0.385	0.0506	...	0.0247	0.0082

Alloy Steel and Special Alloy Certified Reference Materials (cont.)

JK No.	Na ₂ O	K ₂ O	V ₂ O ₅	Cr	Ni	Co	Cu	Sn	Pb	Zn
ECRM 688-1 (cont.)	0.333 Na	0.180 K	0.135 V	<i>0.002</i>	0.0136	0.0096	0.0023	<i>0.0003</i>	0.00025	0.0015
ECRM 689-1 (cont.)	0.638 Na	0.462 K	0.1020 V	<i><0.002</i>	0.0195	0.0103	0.0068	<i><0.0004</i>	<i>(0.0005)</i>	0.0042
JK 28 (cont.)	0.11	0.12	0.21	...	...	...	0.002	...	...	...
JK 29A (cont.)	0.015	0.0087	0.266	0.0057	0.0167	0.0106	0.0007	<i>0.0002</i>	<i><0.001</i>	0.0016
JK 42A (cont.)	0.043	0.0157	0.251	0.0010	0.0129	0.0105	0.0007	<i>0.0003</i>	<i><0.001</i>	0.0015

JERNKONTORET / SWEREA KIMAB (JK), Sweden

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Slag and Fluorspar Reference Materials (Finely divided material – unit weights as shown in table)

JK No.	Description	Unit	SiO ₂	Al ₂ O ₃	TiO ₂	FeO	Fe ₂ O ₃	Ca	CaO	CaF ₂	MgO	MnO	P	S	C	F	P ₂ O ₅	V ₂ O ₅	Cr ₂ O ₃	Pb	BaO
JK S10	Electro Slag Refining	100g	7.8	0.54	0.05	0.10	...	50.8	20.3	70.7	0.30	0.03	0.002	...	0.022	34.4	...	<i><0.01</i>	...	...	...
JK S11	AOD Slag	100g	26.8	2.85	0.95	0.2	...	...	60.0	...	4.7	0.12	...	0.30	...	7.9	<i><0.005</i>	<i><0.01</i>	0.17	...	...
JK C	Fluorspar	100g	8.2	0.66	...	...	0.70	...	...	76.91	...	...	0.025	1.75	...	37.43	...	...	...	0.070	8.2
JK D	Fluorspar	100g	<i>1.5</i>	0.04	...	...	0.20	...	...	97.07	...	...	0.035	0.004	...	47.24	...	...	...	<i><0.001</i>	...

Blast Furnace Slag Certified Reference Material (Finely divided material – unit of 100g)

JK No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	V	Cr	Ni	Mo	Ba	Sr	Zr
ECRM 883-1	Blast Furnace Slag	0.9820	16.67	21.32	8.86	6.55	1.3331	0.546	0.0033	1.0885	0.316	0.393	0.122	0.0130	0.00053	≤0.001	0.0436	0.0380	0.0276

Industrial Fly Ash Certified Reference Materials (Finely divided material – unit weights as shown in table)

JK No.	Description	Unit	Fe	Ca	Al	Na	K	Zn	Pb	Cd	Cr	Ni	Cu	V	As	Bi	Sb	Hg	Sn
ECRM 882-1	Industrial Fly Ash	100g	22.20	10.11	0.375	0.697	0.960	28.49	1.324	0.0183	0.490	0.0263	0.218	0.0090	0.0054	0.0026	0.0116	0.000075	<i>0.021</i>
JK 43	Industrial Fly Ash	15g	<i>20</i>	<i>12</i>	<i>0.2</i>	<i>0.5</i>	<i>0.3</i>	4.96	0.21	0.0023	<i>8</i>	<i>2</i>	<i>0.2</i>	<i>0.02</i>	...	...	...	0.00039	...
JK 44	Industrial Fly Ash	25g	<i>27</i>	<i>5</i>	<i>0.2</i>	<i>1</i>	<i>1.3</i>	27.3	2.74	0.0469	<i>0.2</i>	<i>0.02</i>	<i>0.2</i>	<i>0.02</i>	...	...	...	0.00028	...
JK 45	Industrial Fly Ash	15g	<i>40</i>	<i>7</i>	<i>0.1</i>	<i>7</i>	<i>0.4</i>	1.53	0.11	0.0047	<i>0.3</i>	<i>0.05</i>	<i>0.01</i>	<i>0.1</i>	...	...	...	0.000025	...

Ceramic (high oxygen) Setting-up Sample (disc – 25mm dia. x 8mm)

JK No.	Description	O	Al	C _{Total}	Ti	Fe	W
CE 650A	Ceramic (high oxygen)	<i>30</i>	<i>34</i>	<i>6</i>	<i>21</i>	<i>2.1</i>	<i>0.8</i>

Depth Profile Setting-up Sample

JK No.	Description	P	Al	Ni	Layer thickness
JK SUS NiP-1	Steel plate with a layer of electroless nickel (NiP alloy)	<i>5.8 ± 0.02</i>	<i>0.26 ± 0.02</i>	<i>bal.</i>	<i>8.7 ± 0.5 μm</i>

LUCIDEON (formerly CERAM Research) (LUCIDEON), UK
CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Siliceous, Zircon Bearing and Basic Reference Materials (Finely divided material – units of 100g)

LUCIDEON No.	Description	SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	K ₂ O	Na ₂ O	Li ₂ O	P ₂ O ₅	Cr ₂ O ₃	Mn ₃ O ₄	B ₂ O ₃	BaO	CuO	PbO	ZnO	SrO	ZrO ₂	HfO ₂	LOI
AN25	Alumina	<0.01	<0.01	99.39	0.03	0.03	<0.01	0.01	0.53	...	<0.01	...	...	...	...	...	...	...	...	...	...	# (0.34)
AN26	Alumina	0.12	<0.01	99.76	0.03	0.03	<0.01	<0.01	0.02	...	...	...	...	...	...	...	...	...	...	...	...	# (0.08)
AN27	Alumina	0.08	<0.01	99.76	0.02	0.03	<0.01	<0.01	0.08	...	...	...	...	...	...	...	...	...	...	...	...	#
AN28	Lead Bisilicate Frit	32.76	<0.01	2.46	0.018	0.05	<0.01	0.05	0.05	...	...	...	...	...	...	...	64.33	...	...	...	...	0.15
AN36	Magnesite	0.48	0.01	0.42	4.66	0.94	93.30	<0.01	<0.05	...	0.008	0.004	0.11	0.09	...	...	...	...	...	...	...	...
AN37	Magnesite	1.39	0.03	1.06	1.80	1.46	94.00	<0.01	<0.05	...	0.02	0.005	0.12	0.09	...	...	...	...	...	...	...	...
AN41	China Clay	48.5	0.03	36.4	0.62	0.09	0.35	1.59	0.10	...	0.14	...	0.01	...	0.02	...	...	0.01	0.01	...	...	12.3
AN46	Zircon Batt	45.46	0.48	30.52	0.85	0.20	5.34	1.03	0.15	0.02	...	...	...	...	...	...	...	...	...	15.41	0.32	0.08
AN100	Chrome Ore	11.1	0.21	24.7	12.88	1.16	22.38	0.01	0.04	...	...	26.60	0.13	...	...	0.02	...	0.04	...	...	...	# (5.03)
2CAS12	Sillimanite	33.9	1.31	63.8	0.31	0.25	0.12	0.13	0.15	...	...	...	...	...	...	...	...	...	...	...	...	0.13
2CAS14	Steatite	62.7	0.005	0.149	0.314	0.249	31.28	0.002	0.008	...	...	...	...	...	...	...	...	...	...	...	...	5.10
2CAS15	Zircon	33.9	0.20	0.38	0.07	0.28	0.07	0.01	0.02	...	...	...	...	...	...	...	...	...	...	63.6	1.28	0.23
CCB1*	Calcined Bone	1.28	<0.01	0.05	0.04	53.4	1.14	0.011	0.52	...	40.5	...	...	...	0.031	...	...	...	0.049	...	...	2.60
CEB1	Earthenware Body	74.0	0.34	16.2	0.48	0.52	0.16	1.75	0.71	...	0.14	...	...	...	0.05	...	...	...	0.02	...	...	5.60

* **CCB1** has the following additional constituent values: F 0.13%, SiO₂ as quartz (0.5%), SO₃ (0.114%) and H₂O (0.12%). Hydroxyapatite is the major constituent, estimated as 99.5% (by difference).

Results calculated on the ignited 1025°C basis (otherwise calculated on the dried basis at 110°C)

Please note that LUCIDEON (formerly CERAM Research) also provides a series of RMs for physical properties of ceramic materials. These include two thermal expansion RMs, one of alumina and the other of cordierite. Further details of how these RMs are supplied, as special cut bars or pieces, will gladly be provided on request.

LUCIDEON (formerly CERAM Research) also supplies a Dental Frit Particle Size Distribution CRM, with D50% 3.2 µm, Median diameter 3.2 µm, with 90% between 0.6 and 10.0 µm. This is available in units of 75g.

Please ask us for further details of these Alumina and Cordierite Thermal Expansion CRMs and Dental Frit Particle Size Distribution CRM.

MBH ANALYTICAL LTD. (MBH), U.K.

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Pure Zinc (Cast) Reference Materials (Approx. 50mm dia. x 20mm discs)

MBH No.	Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Ti	In	Tl	Bi	Sb	Si	Hg
41X Z1(Q)	0.00276	(0.00010)	(0.00011)	0.00120	0.00282	0.00051	0.00116	0.00014	0.00047	...	0.00026	0.00028	0.00030	(0.00024)	...	0.00034
41X Z2(P)	0.00400	(0.00033)	0.00015	0.00214	0.00331	0.00197	0.00201	0.00111	0.00341	...	0.00111	0.00112	0.00116	0.00020	...	0.00150
41X Z3(M)	0.00502	(0.00034)	0.00158	0.00327	0.00605	0.00297	0.00345	0.00209	0.00524	...	0.00233	0.00210	0.00315	0.00167	...	0.00289
41X Z4(L)	0.0058	0.0033	0.0065	0.00437	0.0148	0.00221	0.00326	0.00320	0.00286	<0.0005	0.00300	0.00277	0.00310	0.00340	(0.0014)	0.0025
41X Z5(N)	0.0286	0.0107	0.0243	0.0165	0.0262	0.00632	0.0109	0.00514	0.00494	...	0.00573	0.0068	0.0056	0.0054	...	0.0050
41X Z6(A)	0.031	<0.0005	0.0096	0.0093	(0.002)	0.0038	0.0088	0.0002	0.0002	...	0.0228	0.0004	0.0122	...	...	...
41X Z11(A)	0.0077	...	0.0261	0.0155	0.0019	0.0072	0.0116	...	...	...	0.0345	(0.0010)	0.0189	0.0026	...	(0.0009)

Low Alloy Zinc (Cast) Reference Materials (50mm dia. x 20mm discs)

MBH No.	Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Cr	Ti
41X 2951Zn1(A)	0.0042	0.0029	0.029	0.0005	0.011	(0.0007)	0.79	0.0038	0.0013	0.083	0.278
41X 2951Zn2(A)	0.0040	0.0123	0.032	0.0037	0.019	(0.0015)	1.37	0.0027	0.0011	0.142	0.209
41X 2951Zn3(A)	0.0065	0.0164	0.078	0.0062	0.029	(0.006)	1.89	0.0010	0.0018	0.184	0.133

Zinc/Aluminium (Cast) Reference Materials (Approx. 50mm dia. x 20mm discs)

MBH No.	Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Cr	In	Ti	Tl	Si	Sb	Ce	La
42X Z1(J)	0.0017	0.0009	4.66	0.0014	0.013	0.0007	0.0050	0.0014	0.0038	0.0004	...	...	...	(0.0018)	0.0011	0.0011	(0.0008)
42X Z2(K)	0.0029	0.0146	3.79	0.0017	0.0055	0.0011	0.0300	0.00155	0.0274	(0.0001)	...	...	...	0.0011	0.0010	0.0055	0.0026
42X Z3(J)	0.0068	0.0503	3.84	0.0065	0.0145	0.0048	0.135	0.0071	0.0090	...	...	...	...	(0.0018)	0.0006	0.0032	0.0013
42X Z4(J)	0.0133	0.0663	3.52	0.0065	0.019	0.0052	0.0752	0.0170	0.0083	(0.0002)	0.0025	...	...	0.006	...	0.0361	0.0183
42X Z5(M)	0.0030	0.0508	4.33	0.0013	(0.05)	0.0012	0.111	0.041	0.0049	(0.0002)	0.0047	...	0.0017	...	...	0.0328	0.0150
42X Z6(B)	0.0093	0.177	3.67	0.0039	0.008	0.0057	0.238	0.00030	0.0157	0.0034	0.00191	...	0.0021	(0.010)	0.0169	(0.012)	(0.011)
42X Z7(C)	0.0097	0.0095	4.39	0.030	0.027	0.012	0.0249	0.0067	0.0045	(0.0001)	...	(0.0001)	...	0.006	...	0.09	0.08
42X Z8(A)	0.0025	0.0033	7.03	0.0003	0.013	(0.0023)	0.0215	0.0019	0.0014	(0.0002)	...	(0.0001)	...	0.013	...	0.0081	0.0079
42X Z9(A)	0.0021	0.0464	5.58	0.0054	0.032	(0.00035)	0.0070	(0.0003)	0.0006	...	...	0.020	...	(0.004)	0.011 Zr	0.0047	0.0044
42X Z11(A)	0.0058	0.0329	3.19	0.0020	(0.036)	0.0017	0.093	0.0241	0.0196	0.0016	0.0037	...	0.0047	...	0.0047	0.0014	(0.0009)
42X Z12(A)	0.0079	0.0488	4.72	0.0028	0.046	0.0022	0.156	0.0413	0.0483	0.00063	0.0068	...	0.0076	...	0.0070	0.0116	0.0084

Zinc/Aluminium/Copper (Cast) Reference Materials (50mm dia. x 20mm discs)

MBH No.	Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Cr	Ti	Sb	Bi	Si	Be
43X Z1(K)	0.0038	0.0256	4.50	0.0014	0.0070	0.0019	0.717	0.0010	0.0014	0.0007	...	0.0007	0.0015	...	...
43X Z2(P)*	0.0055	0.062	4.05	0.0033	0.0015	0.0035	1.03	0.010	0.016	...	0.011 Ag	0.0013	0.004	...	...
43X Z3(M)	0.0077	0.114	3.40	0.0109	(0.042)	0.0058	1.499	0.0062	0.0013	0.0046	...	0.0029	0.0092	...	...
43X Z4(C)	0.0062	0.0480	4.79	0.0033	0.0017	0.0030	2.69	0.0258	0.0153	...	...	(0.0023)	0.0113	(0.0012)	...
43X Z5(B)	0.0029	0.0144	3.164	0.0030	0.10	(0.0004)	5.92	0.0056	0.0061	...	0.0254 Ag	0.065	0.0148	(0.0005) As	(0.0013) Sr
43X Z6(B)	0.004	0.0238	4.51	0.0031	0.024	0.0052	2.85	0.0027	0.0022	0.0005	...	0.0044	0.0054	...	...
43X Z7(A)	0.0058	0.062	3.68	0.00092	0.029	0.0031	3.14	0.0005	0.0025	0.0003	0.067	0.0016	(0.0009)	...	0.0194
43X Z8(A)	0.0027	0.00155	2.51	0.00090	(0.0017)	(0.0005)	0.481	0.00033	0.00021	0.00024	...	...	...	...	...
43X Z9(A)	0.0078	0.0472	3.17	0.0034	0.073	0.0020	4.82	0.0027	0.0108	0.0034	0.0012	0.0033	0.0033	...	0.0010
43X Z10(A)	0.0046	0.0403	3.99	0.0014	0.007	0.0012	2.97	0.0036	0.0050	0.00027	...	...	...	0.009	...
43X Z11(F)	0.0202	0.0357	11.12	0.0175	0.015	0.0145	0.335	0.0014	0.0032	(0.0003)	...	0.0009	0.0046	0.0013	...
43X Z12(E)	0.0041	0.0287	10.38	0.0045	0.037	0.0017	0.791	0.0033	0.0026	0.0008	0.0050	0.0032	0.0021	(0.002)	...
43X Z13(E)	0.0086	0.0198	9.01	0.0072	0.0045	0.056	1.113	0.0036	0.0025	0.0004	...	0.0020	0.0014	(0.0012)	...
43X Z14(F)	0.0019	0.0123	7.98	0.00567	0.0025	0.0005	1.238	0.0058	(0.0003)	0.0037	(0.0001)	0.0105	0.0106	(<0.001)	...
43X Z15(C)	0.0054	0.0024	7.36	0.0030	0.009	0.004	1.53	0.0019	0.0020	0.0025	0.0020	0.005	0.005	(0.011)	...

* Supplied with a provisional certificate.

MBH ANALYTICAL LTD. (MBH), U.K.

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Aluminium/Silicon/Copper (Cast) Reference Materials (All approx. 50mm dia. x 13-15mm discs, except 55X G02D8(M) approx. 65mm dia. x 30mm discs)

MBH No.	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Sb	Cd	Be
55X G02D5(A)	0.406	0.331	10.03	0.557	0.391	0.0652	0.131	0.067	0.051	0.0180	0.760	0.0752	0.0129	0.031	0.0182	0.0037
55X G02D6(K)	0.510	0.376	11.55	0.528	0.300	0.0511	0.577	0.0580	0.0355	0.055	0.366	0.0195	0.0182	0.0150	0.0115	0.0026
55X G02D7(P) #	1.5	0.34	10.2	1.0	0.49	0.21	0.88	0.35	0.17	0.21	0.055	0.038	0.024	<0.001	<0.001	0.007 Ca
55X G02D8(M)	2.481	0.1517	9.24	0.776	0.256	0.406	1.415	0.201	0.201	0.1535	0.0756	0.0107	0.0536	0.0112	0.0029	0.0008
55X G02D9(K)	3.51	0.093	8.49	0.423	0.269	0.494	2.48	0.10	0.187	0.096	0.185	0.0074	0.0223	0.049	0.0012	0.0035
55X G02D10(L)	4.59	0.0206	7.33	0.975	0.0524	0.645	2.77	0.022	0.138	0.0302	0.128	0.0544	0.0341	0.0086	0.0012	0.0389

Supplied with a provisional certificate.

Magnesium/Aluminium/Zinc (Cast) Reference Materials (40-50mm dia. x 15-20mm discs)

MBH No.	Al	Zn	Mn	Cu	Si	Fe	Ni	Ca	Sn	Pb	Ag	Be	Cd	Ce	La	Sr	Ti	Zr
65X MgA1(J)*	5.45	1.26	0.060	0.221	0.20	0.021	0.021	0.029	0.072	0.012	0.012	0.006	0.013	0.009	0.007	...	(0.005)	(0.0015)
65X MgA5(A)	8.00	0.411	0.401	0.0195	0.110	0.006	0.0201	(0.014)	0.0124	0.042	0.0050	0.0013	0.0035	...	...	0.0004	(0.001)	...
65X MgA11(A)	3.63	1.59	0.044	0.0496	0.022	0.0048	0.0134	0.102	0.093	0.0190	(0.0002)	0.0021	0.0014	(0.0005)	(0.0005)	0.006 Hg	...	...
65X MgA12(A)	5.68	3.18	0.198	0.266	0.0142	0.0053	0.0148	0.037	0.0021	0.010	0.0128	(0.0036)	0.0121	0.0009	0.0007	(0.016) Hg	...	...
65X MgA13(A)	7.45	0.925	0.092	0.125	0.022	(0.008)	0.0039	0.0064	0.043	0.0085	0.0074	(0.010)	0.0055	0.0024	0.0021	(0.033) Hg	...	...
65X MgA14(B) #	9.35	0.75	0.24	0.017	0.21	0.021	0.01	...	0.01	0.01	0.005	0.002	0.0014	0.015	0.007	0.035 Hg	...	...
65X MgA15(A)	10.67	0.348	0.067	0.0273	0.034	0.010	0.0026	(0.0014)	0.0021	0.0051	0.030	0.0062	0.0034	0.0069	0.0048	0.011 Hg	...	...
65X MgA16(A)	6.78	4.03	0.271	0.099	0.023	0.0073	0.0057	0.0024	0.028	0.050	0.0035	0.0011	0.0066	0.0017	0.0012	0.005 Hg	...	...
65X MgA17(A)	4.20	0.128	0.203	0.0215	0.33	0.0069	0.0141	0.021	0.0050	0.009	0.0064	...	0.0049	...	...	...	...	...
65X MgB2(C)	2.67	0.95	0.333	0.113	0.069	0.010	0.0028	0.011	0.0047	0.0036	0.0099	0.0008	0.0115	0.0009	0.0007	...	0.0003	<0.001
65X MgB3(C)	3.38	0.711	0.277	0.0222	0.042	0.0028	0.0027	(0.003)	0.0017	0.0023	0.0028	0.0019	0.0025	...	...	...	...	...
65X MgB4(C)	3.86	0.333	0.031	0.0183	0.037	(0.009)	0.0003	0.0010	0.0050	0.0037	0.0046	0.0033	0.00016	0.0003	(0.0001)	...	(0.0008)	<0.001

* Unsuitable for use with glow-discharge systems

Supplied with a provisional certificate

Tin with Impurities (Cast) Reference Materials (Approx. 40mm dia. x 15mm discs)

MBH No.	Sb	As	Bi	Pb	Cu	Fe	Co	Ni	Al	Ag	Cr	P	Tl	Cd	Zn	In	Au	Te	Se	Ga	Hg	Ge
71X SR0(C)	0.0055	0.0005	0.0029	0.046	0.0073	0.0040	(0.0004)	0.0025	0.041	0.0024	...	(0.0004)	...	0.0024	0.0053	0.0088	0.0012	0.0021	0.0006	0.0054	0.0099	(0.002)
71X SR1(F) #	0.018	0.003	0.010	0.026	0.002	0.007	...	0.007	...	0.012	...	...	...	0.011	0.020	0.010	0.002	0.001	0.005	...	0.018	0.011
71X SR2(F)	0.074	0.0070	0.0403	0.151	0.116	0.0133	0.0064	0.0183	0.0022	0.0212	0.0031	(0.007)	0.005	0.0351	0.0058	0.0597	0.0077	0.0246	...	...	0.140	0.009
71X SR3(F)	0.128	0.097	0.123	0.306	0.121	0.0203	...	0.0371	(0.0014)	0.050	...	...	...	0.100	0.054	0.104	0.0145	0.070	0.0031	0.0339	0.115	...

Supplied with a provisional certificate.

MBH ANALYTICAL LTD. (MBH), U.K.

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Tin White Metal (Pewter, Babbitt) Reference Materials (Approx. 40mm dia. x 12-15mm discs)

MBH No.	As	Bi	Sb	Pb	Cu	Fe	Cd	Zn	Ni	Al	Ag	Co	In	S	P
73X SC1(A)	0.008	0.084	1.48	0.067	2.02	0.0025	0.006	0.003	0.0041	0.0025	0.010	<0.001	0.008	<0.002	...
73X SC2(B)	0.0355	0.602	3.05	0.0457	1.028	0.0037	0.0282	(0.0007)	0.0156	...	0.0318	0.0217	0.0099	...	...
73X SC3(A)	0.029	0.020	4.60	0.0400	0.222	0.017	0.024	0.0014	0.0136	0.001	0.013	0.006	0.031	(0.002)	...
73X SC4(B)	0.0268	0.153	5.94	0.429	2.63	0.0014	0.0085	(0.001)	0.0130	(0.0015)	0.0525	0.0020	0.0143	...	0.005
73X SC5(A)	0.013	0.43	7.03	0.136	0.57	0.004	0.008	0.001	0.0058	0.003	0.063	0.011	0.036	(0.001)	...
73X SC6(A)	0.204	0.115	0.092	0.100	5.17	0.007	0.0125	0.01	0.013	(0.003)	0.08	0.005	0.058	(0.004)	...
73X SC7(B)	0.059	0.013	13.86	0.32	5.71	(0.043)	0.0019	0.0033	0.016	(0.001)	0.0059	0.0143	0.0194	(0.0007)	...
73X SC8(B)	0.11	0.0531	5.52	0.110	3.78	0.055	0.098	0.004	0.0351	(0.0007)	0.0253	0.0267	0.0325	0.004	...
73X SC9(B)	0.117	0.0825	8.31	0.305	8.03	0.053	0.0506	...	0.0084	(0.0010)	0.0055	0.0051	0.0059	...	...
73X SC11(C)	0.248	0.554	12.98	0.0630	11.51	0.0052	1.72	0.005	0.110	...	(0.056)	...	...	...	0.025
73X SC12(B)	(0.034)	0.0301	7.50	0.091	6.03	0.024	0.758	0.0212	0.115	0.0015	0.842	0.0210	...	...	...
73X SC13(A)	0.054	0.0188	4.21	0.259	4.19	0.053	0.0021	0.0126	...	(0.01)	...	...	...	...	(0.02)

Lead with Impurities Reference Materials (Approx. 40mm dia. x 15mm discs)

MBH No.	Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Ni	Te	Se	Au	Tl	Na	Hg	Pt	S
83X PR1(K)	0.016	0.0100	0.0508	0.0465	0.0338	0.1029	...	(0.002)	0.074	0.0080	(0.0004)	0.0058	0.0008	0.0019	...	...	...	...	...
83X PR2(G)	0.0948	0.0499	0.0404	0.0309	0.0233	0.055	...	0.0005	0.0020	0.0010	0.0006	0.0100	0.0005	0.0005	(0.0017)	0.0013	0.003	...	...
83X PR4(H)	...	0.0050	0.0150	0.0454	0.0003	0.0114	...	...	0.0081	...	0.0029	0.0229	(0.004)	0.0021	0.0021	...	0.019	...	...
83X PR5(G)	0.0010	0.0006	0.0086	0.00058	0.0004	0.00110	...	(0.00016)	0.00029	0.0002	(0.00017)	0.0003	0.0004	...	(0.0001)	...	(0.0001)	...	...
83X PR7(B)	0.189	0.795	0.479	0.176	0.051	0.290	(0.0008)	(0.0006)	0.455	0.653	(0.0015)	0.0097	0.0052	...	...	...	...	0.0047	...
83X PR8(D)	0.604	0.257	1.18	0.0448	0.134	0.497	...	0.0004	0.199	0.293	0.0008	0.0014	(0.0003)	0.0106	...	...	0.086	...	...
83X PR11(A)	0.119	0.497	0.0117	0.0551	0.0095	0.0030	(0.0003)	...	0.0008	...	0.0011	...	(0.0001)	...	0.0042	...	...	...	0.009
83X PR12(A)	0.0005	0.0011	0.0119	0.0353	(0.0003)	0.0030	(0.0003)	...	0.0011	...	0.0009	...	(0.0002)	...	0.0051	...	...	...	(0.0002)

Lead with Impurities Reference Materials (Approx. 40mm dia. x 13mm discs)

MBH No.	Sn	Ag	Zn	Cd	Al	Li	Na	Mg	Ca	Ba
83X PR9-1(A)	0.054	0.003	0.0007	0.0004	0.0001	0.004	0.015	0.006	0.096	0.033
83X PR9-2(A)	0.015	0.003	0.0002	0.0004	0.0001	0.002	0.007	0.002	0.046	0.015

Cobalt Alloy (Cast) Reference Material (Approx. 40mm dia. x 15mm discs)

MBH No.	C	Si	S	Mn	Ni	Cr	W	Mo	Fe	Al	Cu	Nb	P	Ta	B	N
112X 14943(H)	0.190	0.201	0.0197	1.008	0.151	31.00	0.051	7.96	0.763	(0.13)	0.203	0.099	0.0043	(0.014)	0.0045	0.0284

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Electrolytic Iron and Low Alloy Steel Certified Reference Materials

(SRMs 361 and 363 finely divided material, units of 150g; SRMs 1264a and 1265a 31mm dia x 19mm discs and 1761a-1768 31-34mm dia. x 19mm discs)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu
SRM 361	AISI 4340	2016	0.383	0.222	0.66	0.014	0.0143	0.694	0.19	2.00	0.021	0.017	0.000478	0.032	0.042
SRM 363	Cr-V (Mod)	2012	0.62	0.74	1.50	0.029	0.0068	1.31	0.028	0.30	0.24	0.010	0.00131	0.048	0.10
SRM 1264a	High Carbon (Mod)	2006	0.87	0.067	0.258	0.010	0.025	0.066	0.49	0.142	<i>0.008</i>	0.052	<i>0.011</i>	0.15	0.250
SRM 1265a	Electrolytic Iron	1989	0.0067	0.0080	0.0057	0.0011	0.0055	0.0072	0.0050	0.041	<i>0.0007</i>	<i>0.0002</i>	0.00013	0.0070	0.0058
SRM 1761a	Low Alloy Steel	2008	<i>1.05</i>	<i>0.182</i>	0.679	0.042	0.037	0.222	0.103	1.981	0.055	<i>0.011</i>	0.0023	<i>0.027</i>	0.298
SRM 1762a	Low Alloy Steel	2015	0.341	0.351	1.912	0.0346	0.0295	0.923	0.353	1.156	0.0706	0.0173	0.0042	0.0616	0.1186
SRM 1763a	Low Alloy Steel	2010	0.202	0.663	1.584	0.0123	0.022	0.498	0.490	0.513	0.0435	0.055	0.0054	0.093	0.42
SRM 1764a	Low Alloy Steel	2009	0.592	0.0595	1.193	0.0210	0.0118	1.468	0.2007	0.2006	0.0098	0.0100	<i>0.0010</i>	<i>0.012</i>	0.5178
SRM 1765	Low Alloy Steel	1993	0.006	<i>0.004</i>	0.144	0.0052	0.0038	0.051	0.005	0.154	<i>0.006</i>	0.0010	0.0009	0.0012	0.0013
SRM 1766	Low Alloy Steel	1993	0.015	0.010	0.067	0.002	0.0024	0.024	0.0035	0.021	0.012	0.0035	0.00012	0.0020	0.015
SRM 1767	Low Alloy Steel	1993	0.052	0.026	0.022	0.0031	0.0090	0.0015	0.020	0.002	0.004	0.0005	0.001	0.0050	0.0014
SRM 1768	High Purity Iron	2011	0.0010	<i>(<0.001)</i>	0.0014	0.0013	0.0003	<i>(<0.0002)</i>	<i>(<0.0003)</i>	0.0014	0.0024	<i>(<0.0001)</i>	<i>(<0.0002)</i>	0.0025	0.0006

Electrolytic Iron and Low Alloy Steel CRMs (continued)

NIST No.	N	Nb	Pb	Sn	Ta	Ti	V	W	Zr	Ag	Bi	Ca	Ce
SRM 361	<i>0.0037</i>	0.022	0.000025	0.010	0.020	0.020	0.011	0.017	0.009	0.0004	<i>0.0004</i>	0.00010	0.0040
SRM 363	<i>0.0041</i>	0.049	0.00186	0.104	<i>0.053</i>	0.050	0.31	0.046	0.049	0.0037	<i>0.0008</i>	0.00022	0.0030
SRM 1264a	<i>0.0032</i>	0.157	0.024	<i>0.008</i>	0.11	0.24	0.106	0.102	0.069	<i>0.00002</i>	<i>0.0009</i>	0.00004	0.00022
SRM 1265a	<i>0.0011</i>	...	0.000015	<i>0.0002</i>	<i><0.0005</i>	<i>0.0001</i>	0.0006	<i>0.00004</i>	<i><0.00001</i>	<i>0.000002</i>	<i><0.00001</i>	<i><0.00001</i>	<i><0.000005</i>
SRM 1761a	<i>0.0042</i>	0.021	...	<i>0.050</i>	<i>0.050</i>	0.173	0.054	...	0.012	...	...	...	...
SRM 1762a	<i>(0.002)</i>	0.0692	...	0.0479	0.0203	0.0952	0.2010	...	0.0285	...	...	...	...
SRM 1763a	<i>0.0045</i>	0.100	...	<i>0.011</i>	<i>0.012</i>	0.308	0.307	<i>(0.002)</i>	0.044	...	...	...	...
SRM 1764a	<i>0.0023</i>	0.0416	...	<i>0.024</i>	0.0297	0.0286	0.1063	<i>(0.0016)</i>	<i>0.0012</i>	...	...	...	...
SRM 1765	0.0010	0.0004	0.0003	0.002	<i>0.004</i>	0.0055	0.0040	...	<i>0.0002</i>	0.0002	<i><0.0001</i>	...	...
SRM 1766	0.0033	0.005	0.003	0.0010	<i>0.006</i>	0.0005	0.009	<i>0.001</i>	<i>0.0004</i>	0.0005	<i><0.0001</i>	...	<i>0.002</i>
SRM 1767	0.0008	0.010	<i>0.0001</i>	0.006	<i>0.002</i>	0.011	0.033	...	<i>0.004</i>	0.0008	<i><0.0001</i>	<i>0.0003</i>	...
SRM 1768	0.002	<i>(<0.0005)</i>	<i>(<0.0001)</i>	<i>(<0.0001)</i>	<i>(<0.0001)</i>	<i>(<0.001)</i>	<i>(<0.0001)</i>	<i>(<0.0002)</i>	<i>(<0.0001)</i>	...	<i>(<0.0004)</i>	<i>(<0.0001)</i>	...

Electrolytic Iron and Low Alloy Steel CRMs (continued)

NIST No.	Fe	Au	Ge	H	Hf	La	Mg	Nd	O	Pr	Sb	Te	Zn
SRM 361	<i>95.6</i>	<i><0.00005</i>	<i>0.006</i>	<i><0.0005</i>	<i>0.0002</i>	<i>0.001</i>	0.00026	0.00029	<i>0.0009</i>	<i>0.0003</i>	0.0042	<i>0.0006</i>	<i>0.0001</i>
SRM 363	<i>94.4</i>	0.0005	<i>0.010</i>	<i><0.0005</i>	<i>0.0005</i>	<i>0.002</i>	0.00062	0.0012	<i>0.00066</i>	<i>0.0004</i>	0.002	<i>0.0009</i>	<i>0.0004</i>
SRM 1264a	<i>96.7</i>	0.0001	<i>0.003</i>	<i><0.0005</i>	<i>0.0013</i>	0.00007	0.00015	0.00007	<i>0.0010</i>	<i>0.00003</i>	0.034	0.00018	<i>0.001</i>
SRM 1265a	<i>99.9</i>	<i><0.000002</i>	<i>0.0014</i>	<i>0.0001</i>	<i><0.00002</i>	<i><0.000005</i>	<i><0.00002</i>	<i><0.000005</i>	<i>0.0063</i>	<i><0.000005</i>	<i><0.00001</i>	<i><0.00001</i>	<i><0.0001</i>
SRM 1761a	<i>95.0</i>	...	...	...	...	...	...	...	...	...	<i>0.0052</i>	...	...
SRM 1762a	<i>(94.2)</i>	...	...	...	...	...	...	...	...	...	...	...	...
SRM 1763a	<i>(95.3)</i>	...	...	...	...	...	...	...	...	...	<i>0.011</i>	...	...
SRM 1764a	<i>(95.1)</i>	...	...	...	...	...	...	...	...	...	...	...	...
SRM 1768	<i>99.9</i>	...	...	...	...	...	<i>(<0.0006)</i>	...	0.036	...	<i>(<0.0001)</i>	<i>(<0.0001)</i>	<i>(<0.0001)</i>

Information on NIST samples not included in this list will be provided on request.

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

High Temperature Alloy and Specialty Steel Certified Reference Materials (Approx. 32-35mm dia x 19mm discs except SRM 126c, SRM 867 & SRM 868 which are finely divided material, units of 150g, 100g and 150g respectively)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Cu	N	Nb
SRM 1158 (SRM 126c)	High Nickel Steel (36% Ni)	2009	0.02540	0.1936	0.4684	<i>0.00350</i>	<i>0.0050</i>	<i>0.0625</i>	<i>0.0110</i>	36.054	...	...	<i>0.0396</i>	...	...
SRM 1230	High Temperature Alloy A286	2016	0.0428	0.411	0.652	0.0239	0.00095	14.65	1.15	24.08	0.249	<i>(<0.005)</i>	0.137	<i>(0.003)</i>	<i>0.067</i>
SRM 1247 (SRM 867)	Ni-Fe-Cr Alloy UNS N08825	2015	0.0212	0.3234	0.3806	0.0203	<i>0.0017</i>	23.375	2.723	43.47	0.0630	0.00257	1.767	<i>0.0170</i>	0.458
SRM 1250 (SRM 868)	High Temperature Alloy Fe-Ni-Co	1993	0.022	0.097	0.052	<i>(<0.003)</i>	0.0025	0.077	0.014	37.78	0.99	...	0.022	...	2.99
SRM C2400	Fe-Cr-Ni Alloy UNS J92180	2016	0.036	0.61	0.71	0.013	0.003	17.06	0.23	4.07	<i>(<0.01)</i>	...	2.63	...	0.15

High Temperature Alloy and Specialty Steel CRMs (continued)

NIST No.	Pb	Sn	Ta	Ti	Tl	V	W	Zr	Ag	B	Bi	Co	Fe	Ga	O
SRM 1158 (SRM 126c)	...	...	...	...	...	<i>(0.001)</i>	...	...	...	...	...	<i>0.0080</i>	...	...	...
SRM 1230	<i>(<0.0003)</i>	<i>(<0.033)</i>	<i>(<0.001)</i>	2.18	...	0.229	<i>0.0695</i>	<i>(<0.018)</i>	<i>(0.000025)</i>	0.00519	<i>(<0.0001)</i>	0.151	55.6	...	...
SRM 1247 (SRM 867)	0.0000340	<i>(0.0030)</i>	<i>(<0.0010)</i>	0.755	0.000000223	0.0478	<i>0.0056</i>	...	<i>0.000025</i>	0.00198	<i>(<0.00005)</i>	0.092	26.564	<i>0.0112</i>	<i>0.0050</i>
SRM 1250 (SRM 868)	...	...	0.003	1.48	...	0.077	...	...	...	0.0078	...	16.1	40.5	...	...
SRM C2400	...	...	...	<i>(<0.01)</i>	...	0.092	<i>(0.1)</i>	<i>(<0.01)</i>	...	<i>(0.0004)</i>	...	0.10	...	...	...

Tool Steel Certified Reference Materials (SRM 1772 approx. 34mm dia x 19mm discs, SRM 50c & SRM 2172 are both finely divided materials, units of 150g)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	As	Cu	N	V	W	Pb	Sn	B	Ca	Co
SRM 50c	W-Cr-V Steel	2011	<i>0.7193</i>	0.3102	0.3417	0.0222	0.006367	4.128	0.0821	0.0686	0.0225	0.0792	0.0117	1.158	18.445	...	0.0183	...	...	<i>(0.035)</i>
SRM 1772	Tool Steel (S-7)	1995	0.477	0.264	0.61	0.008	0.0031	3.10	1.39	0.105	...	0.083	...	0.236	<i>0.002</i>	<i><0.001</i>	<i>0.008</i>	<i><0.001</i>	<i>0.001</i>	<i>0.007</i>
SRM 2172	Tool Steel (S-7)	1996	0.480	0.263	0.61	0.008	0.0031	3.11	1.37	0.104	...	0.083	...	0.234	<i>0.002</i>	<i><0.001</i>	<i>0.008</i>	<i><0.001</i>	<i>0.001</i>	<i>0.007</i>

White Cast and Ductile Iron Certified Reference Materials (Approx. 32mm dia x 19mm discs except SRM 892 which is finely divided material, units of 150g)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	Ti	V
SRM 892	White Cast Iron (Ni-Hard Type IV)	1982	3.33	1.83	0.76	0.054	0.015	10.18	0.20	5.53	0.270	<i>(0.02)</i>	0.041
SRM C1145a	White Cast Iron	1988	2.92	0.271	0.187	0.215	0.191	0.63	0.48	0.62	0.46	0.012	0.112
SRM C1290	White Cast Iron (HC-250+V)	1985	3.04	0.971	0.66	0.030	0.013	30.5	<i>(0.041)</i>	0.917	0.065	...	0.442
SRM C1291	White Cast Iron (Ni-Hard Type I)	1985	2.67	1.34	1.14	0.028	0.032	2.78	0.32	4.34	0.26	...	0.031
SRM C1292	White Cast Iron (Ni-Hard Type IV)	1985	3.47	0.59	0.55	0.049	0.016	11.4	0.25	5.04	0.36	...	0.041
SRM C2424	Ductile Iron	1985	2.68	3.37	0.268	0.041	0.024	0.13	0.019	0.061	...	0.050	0.083

White Cast and Ductile Iron CRMs (continued)

NIST No.	Mg	Pb	Sb	Sn	Zr	Al	As	B	Bi	Ce	Co	La	Fe
SRM 892	...	...	<i>(0.0012)</i>	<i>(0.02)</i>	<i>(<0.001)</i>	<i>(0.009)</i>	<i>(0.006)</i>	<i>(0.0020)</i>	...	...	0.31	...	<i>(77.4)</i>
SRM C1145a	...	0.0012	<i>(0.04)</i>	<i>(0.10)</i>	<i>(0.002)</i>	<i>(0.04)</i>	<i>(0.03)</i>	<i>(0.02)</i>	<i>(<0.01)</i>	...	0.058	...	...
SRM C2424	0.006	...	...	...	...	<i>(<0.01)</i>	...	<i>(0.002)</i>	...	0.0046	<i>(0.05)</i>	0.0011	...

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Ore and Concentrate Certified Reference Materials (Finely divided material – unit weights as shown in table)

NIST No.	Description	Cert. Date	Unit Weight	Fe ₂ O ₃	SiO ₂	Al ₂ O ₃	TiO ₂	CaO	MgO	MnO	P ₂ O ₅	SO ₃	K ₂ O
SRM 25d	Manganese Ore	2010	60g	<i>3.91</i>	2.54	<i>5.33</i>	<i>0.136</i>	<i>(0.052)</i>	...	51.78 Mn	0.251	...	<i>0.928</i>
SRM 69b	Bauxite, Arkansas	1991	60g	7.14	13.43	48.8	1.90	0.13	0.085	0.110	0.118	0.63	0.068
SRM 277	Tungsten Concentrate	2013	100g	<i>7.47 Fe</i>	<i>0.842 Si</i>	...	<i>2.20 Ti</i>	<i>0.38 Ca</i>	...	<i>10.2 Mn</i>	<i>0.034 P</i>	<i>0.267 S</i>	...
SRM 600	Bauxite, Australian	1991	90g	17.0	20.3	40.0	1.31	0.22	0.05	0.013	0.039	0.19	0.23
SRM 670	Rutile Ore	1993	90g	0.86	0.51	...	96.16	...	...	...	...	...	...
SRM 690	Iron Ore, Canada	1992	100g	66.85 Fe	3.71	0.18	0.022	0.20	0.18	0.23	0.011 P	0.003 S	0.0030
SRM 691	Iron Oxide, Reduced	1991	100g	90.8 Fe	3.7	1.22	0.27	0.63	0.52	0.043	0.006 P	0.008 S	...
SRM 692	Iron Ore, Labrador	1992	100g	59.58 Fe	10.14	1.41	0.045	0.023	0.035	0.46	0.039 P	0.005 S	0.039
SRM 693	Iron Ore, Nimba	1990	100g	65.11 Fe	3.87	1.02	0.035	0.016	0.013	0.091	0.056 P	0.005 S	0.0028
SRM 694	Phosphate Rock (Western)	1993	90g	0.79	11.2	1.8	0.11	43.6	0.33	0.0116	30.2	...	0.51
SRM 696	Bauxite, Surinam	1991	60g	8.70	3.79	54.5	2.64	0.018	0.012	0.004	0.050	0.21	0.009
SRM 697	Bauxite, Dominican	1991	60g	20.0	6.81	45.8	2.52	0.71	0.18	0.41	0.97	0.0769	0.062
SRM 698	Bauxite, Jamaican	1991	60g	19.6	0.69	48.2	2.38	0.62	0.058	0.38	0.37	0.22	0.010
SRM 699	Alumina (Reduction grade)	2006	60g	0.013	0.0120	...	...	0.036	0.0006	0.0005	0.0002	...	...
SRM 1835	Borate Ore	1987	60g	1.141	18.408	3.47	0.133	21.622	3.411	0.0333	...	1.477	1.261
SRM 2430	Scheelite Ore	2016	100g	<i>1.13 Fe</i>	1.74 Si	<i>(0.4) Al</i>	...	19.44	<i>(0.5) Mg</i>	0.1178 Mn	<i>(0.02) P</i>	<i>0.25 S</i>	0.179 K

Ore and Concentrate CRMs (continued)

NIST No.	Na ₂ O	Cr ₂ O ₃	Ga ₂ O ₃	Li ₂ O	V ₂ O ₅	WO ₃	ZnO	ZrO ₂	Bi	Cu	F	Mo	Pb	Others	LOI
SRM 25d (continued)	...	...	...	...	...	...	...	...	...	...	...	...	...	<i>(1) H₂O</i>	...
SRM 69b (continued)	<i>0.025</i>	0.011	...	...	0.028	...	0.0035	0.29	...	...	...	...	...	...	25.72
SRM 277 (continued)	...	...	...	...	...	67.50	...	<i>(<0.8) Zr</i>	<i>(<0.01)</i>	<i>(0.014)</i>	...	<i>0.060</i>	<i>0.068</i>	<i>(22.0) O₂</i>	...
SRM 600 (continued)	0.022	0.024	...	...	0.060	...	0.003	0.060	...	...	...	...	...	...	...
SRM 670 (continued)	...	0.23	...	...	0.66	...	...	0.84	...	...	...	...	...	...	...
SRM 690 (continued)	0.003	...	...	...	...	...	...	...	...	...	...	...	...	...	...
SRM 691 (continued)	0.186	...	...	...	...	...	...	...	...	0.032	...	...	...	0.030 Co	...
SRM 692 (continued)	0.008	...	...	...	...	...	...	...	...	...	...	...	...	...	...
SRM 693 (continued)	0.0028	...	...	...	...	...	...	...	...	...	...	...	...	...	...
SRM 694 (continued)	0.86	<i>0.10</i>	...	...	0.31	...	<i>0.19</i>	...	...	...	3.2	...	...	0.0141 U	...
SRM 696 (continued)	<i>0.007</i>	0.047	...	...	0.072	...	0.0014	0.14	...	...	...	...	...	...	29.9
SRM 697 (continued)	<i>0.036</i>	0.100	...	...	0.063	...	0.037	0.065	...	...	...	...	...	<i>0.0013 Co</i>	22.1
SRM 698 (continued)	<i>0.015</i>	0.080	...	...	0.064	...	0.029	0.061	...	...	...	...	...	...	27.3
SRM 699 (continued)	0.59	0.0002	0.010	0.002	0.0005	...	0.013	...	...	...	...	...	...	0.000281 Be	0.69
SRM 1835 (continued)	3.484	...	...	...	...	...	...	...	...	...	0.348	...	...	...	...
SRM 2430 (continued)	<i>0.018 Na</i>	...	...	...	...	70.30	...	...	<i>0.080</i>	<i>0.0086</i>	<i>(1.3)</i>	<i>0.22</i>	...	<i>0.0022 As</i>	...

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified and figures in italic type only approximate.

Rock, Mineral and Refractory Certified Reference Materials (Finely divided material – unit weights as shown in table)

NIST No.	Description	Cert. Date	Unit Weight	SiO ₂	Al ₂ O ₃	TiO ₂	FeO	Fe ₂ O ₃	Cr ₂ O ₃	MnO	CaO	MgO	BaO	Na ₂ O	K ₂ O	Li ₂ O	P ₂ O ₅	SrO	ZrO ₂	LOI
SRM 1d	Limestone, Argillaceous	2005	70g	4.080	0.526	0.07	...	0.3191	<i>0.0012</i>	...	52.85	0.301	<i>0.0033</i>	0.0109	0.1358	...	0.0413	0.0303	...	39.9
SRM 76a	Burnt Refractory (Al ₂ O ₃ -40%)	1992	75g	54.9	38.7	2.03	...	1.60	...	...	0.22	0.52	...	0.07	1.33	0.042	0.120	0.037	...	<i>0.34</i>
SRM 77a	Burnt Refractory (Al ₂ O ₃ -60%)	1992	75g	35.0	60.2	2.66	...	1.00	...	...	0.05	0.38	...	0.037	0.090	0.025	0.092	0.009	...	<i>0.22</i>
SRM 78a	Burnt Refractory (Al ₂ O ₃ -70%)	1992	75g	19.4	71.7	3.22	...	1.2	...	...	0.11	0.70	...	0.078	1.22	0.12	1.3	0.25	...	<i>0.42</i>
SRM 81a	Glass Sand	1978	75g	...	0.66	0.12	...	0.082	0.0046	...	...	...	...	...	...	...	...	...	0.034	...
SRM 88b	Limestone, Dolomitic	1994	75g	1.13	0.34	0.016	...	0.28	...	0.016	30.12	21.03	...	0.029	0.10	...	0.004	0.008	...	<i>47.0</i>
SRM 165a	Glass Sand (low iron)	1992	75g	...	0.059	0.011	...	0.012	0.00011	...	...	...	...	...	...	...	...	...	0.006	...
SRM 198	Silica Brick	1960	45g	...	0.16	0.02	...	0.66	...	0.008	2.71	0.07	...	0.012	0.017	0.001	0.022	...	<0.01	0.21
SRM 199	Silica Brick	1991	45g	...	0.48	0.06	...	0.74	...	0.007	2.41	0.13	...	0.015	0.094	0.002	0.015	...	0.01	0.17
SRM 278	Obsidian Rock	1992	35g	73.05	14.15	0.245	...	2.04	...	0.052	0.983	...	...	4.84	4.16	...	0.036	...	...	...
SRM 688	Basalt Rock	1981	60g	48.4	17.36	1.17	7.64	10.35	...	0.167	...	...	...	2.15	0.187	...	0.134	...	...	...
SRM 1413	Glass Sand (high alumina)	1985	75g	82.77	9.90	0.11	...	0.24	ZnO	Mn₂O₃	0.74	0.06	0.12	1.75	3.94	...	...	...	...	...
SRM 2696	Silica Fume	2013	70g	95.61	0.2080	0.11	...	<i>0.055</i>	0.051	0.032	0.426	0.235	...	<i>0.129</i>	0.652	...	<i>0.0863</i>	...	...	<i>2.11</i>

Cement Certified Reference Materials (Finely divided material – units of 4 x 5g sealed vials, except SRM 634a units of 100g, SRM SRM 1884b units of 5 x 4.5g sealed vials, SRM 1885b and 1886b units of 5 x 5g vials, SRM 1887b units of 5 x 4g vials and SRM 114q units of 20 x 5g vials)

NIST No.	Cert. Date	CaO	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	SO ₃	Na ₂ O	K ₂ O	TiO ₂	SrO	Mn ₂ O ₃	P ₂ O ₅	Cl	F	ZnO	Cr ₂ O ₃	LOI
SRM 634a	2015	65.07	20.493	5.015	3.362	1.0057	2.780	0.0842	0.3572	0.2463	0.0735	0.0229	0.1767	...	...	0.0222	0.0114	1.683
SRM 1880b	2010	64.16	20.42	5.183	3.681	1.176	2.710	0.0914	0.646	0.236	0.0272	0.1981	0.2443	0.01830	0.0539	0.01054	0.01927	1.666
SRM 1882a	1999	39.29	4.01	39.14	14.67	0.51	...	0.021	0.051	1.786	0.024	0.060	0.070	...	...	0.004	0.113	0.20
SRM 1883a	1999	29.52	0.24	70.04	0.078	0.19	...	0.30	0.014	0.02	0.019	0.003	0.003	...	...	...	0.006	0.35
SRM 1884b	2009	61.31	19.30	4.851	2.937	4.74	4.034	0.278	0.957	0.2651	0.0258	0.0750	0.0965	0.0065	0.0394	0.0042	0.00791	0.597
SRM 1885b	2013	61.87	20.05	4.70	3.044	3.86	2.832	0.293	0.497	0.2361	0.0795	0.1282	0.0737	0.0021	0.0524	0.0354	0.02709	2.310
SRM 1886a	2016	67.87	22.38	3.875	0.152	1.932	2.086	0.021	0.093	0.084	0.018	0.0073	0.022	0.0042	0.02	0.001	0.0024	1.56
SRM 1886b	2016	67.05	22.08	3.903	0.297	1.526	2.757	0.01682	0.0164	0.2054	0.0886	0.02639	0.0413	0.00399	0.0118	0.00058	0.00404	3.344
SRM 1887b	2013	61.15	19.59	4.911	2.471	3.624	4.599	0.288	0.961	0.2034	0.2625	0.0957	0.1540	0.01001	0.101	0.01560	0.01551	2.121
SRM 1888b	2010	63.13	20.42	4.277	3.062	3.562	2.634	0.1364	0.658	0.2316	0.1009	0.0652	0.07307	0.0143	0.048	0.01253	0.01021	2.039
SRM 1889a	2016	65.34	20.66	3.89	1.937	0.814	2.69	0.195	0.605	0.227	0.110	0.2588	0.110	0.0019	0.05	0.0048	0.0072	3.28
SRM 114q	2016	Specific Surface Area by ASTM C204-96a, 3818 cm ² /g: Specific Surface Area by ASTM C115-96a, 2183 cm ² /g: Sieve Residue on 45µm sieve by ASTM C430-96, 0.79%																

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Biological Certified Reference Materials (Finely divided material – unit weights as shown in table) nominal mass content in %

NIST No.	Description	Cert. Date	Unit Weight	Ca	Cl	Mg	N	P	K	Na	S
SRM 1515	Apple Leaves	2017	50g	1.525	0.0582	0.271	2.299	0.1593	1.608	0.00244	(0.18)
SRM 1547	Peach Leaves	2017	50g	1.559	0.0361	0.432	2.965	0.1371	2.433	0.00238	(0.20)
SRM 1566b	Oyster Tissue	2017	25g	0.0838	0.514	0.1085	7.6	...	0.652	0.3297	0.687
SRM 1567b	Wheat Flour	2014	50g	0.01914	0.05653	0.0398	...	0.1333	0.1325	0.000671	0.1645
SRM 1568b	Rice Flour	2013	50g	0.01184	0.03011	0.0559	...	0.1530	0.1282	0.000674	0.1200
SRM 1570a	Spinach Leaves	2014	60g	1.526	...	(0.9)	6.06	0.5187	2.900	1.821	(0.5)
SRM 1573a	Tomato Leaves	1995	50g	5.05	0.66	(1.2)	3.03	0.216	2.70	0.0136	(0.96)
SRM 1575a	Pine Needles	2017	50g	0.25	0.0421	0.106	...	0.107	0.417	0.0063	...

SRM 1568b also certified for Arsenic Species.

Biological CRMs (continued) nominal mass content in µg/g

NIST No.	Al	As	B	Ba	Cr	Cu	Fe	Mn	Rb	Sr	Zn
SRM 1515 (continued)	284.5	...	27.6	48.8	(0.3)	5.69	82.7	54.1	10.2	25.1	12.45
SRM 1547 (continued)	248.9	...	28.73	123.7	(1)	3.75	219.8	97.8	19.65	53.0	17.97
SRM 1566b (continued)	197.2	7.65	4.5	8.6	...	71.6	205.8	18.5	3.26	6.8	1424
SRM 1567b (continued)	4.4	0.0048	6.45	...	...	2.03	14.11	9.00	0.671	...	11.61
SRM 1568b (continued)	4.21	0.285	...	...	...	2.35	7.42	19.2	6.198	...	19.42
SRM 1570a (continued)	310	0.068	37.7	...	...	12.22	...	76.0	12.7	55.54	82.3
SRM 1573a (continued)	598	0.112	33.3	(63)	1.99	4.70	368	246	14.89	(85)	30.9
SRM 1575a (continued)	580	0.039	9.6	6.0	<0.5	2.8	46	488	16.5	...	38

Biological CRMs (continued) nominal mass content in ng/g

NIST No.	Cd	Co	I	Pb	Hg	Mo	Ni	Se	Ag	Th	U	V
SRM 1515 (continued)	13.2	(90)	(300)	470	43.2	95	936	...	...	(30)	(6)	254
SRM 1547 (continued)	26.1	(70)	(300)	869	31.7	60.3	689	...	...	(50)	(15)	367
SRM 1566b (continued)	2480	371	...	308	37.1	...	1040	2060	666	36.7	255.0	577
SRM 1567b (continued)	25.4	...	...	10.4	(0.5)	464	...	1140	...	...	...	(10)
SRM 1568b (continued)	22.4	17.7	...	5	5.91	1451	...	365	...	...	...	...
SRM 1570a (continued)	2876	393	...	(200)	29.7	...	2142	115.2	...	48.0	155	568
SRM 1573a (continued)	1520	570	(850)	...	34	(460)	1590	54	...	(120)	(35)	835
SRM 1575a (continued)	233	61	...	167	39.9	...	1470	99	...	...	...	...

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Environmental Certified Reference Materials (Finely divided materials – unit weights as shown in table) nominal mass content in %

NIST No.	Description	Cert. Date	Unit Weight	Al	Ca	Cl	C	Fe	H	K	Mg	Na	P	Pb	S	Si	Ti	Ash content	Calorific Value (Btu/lb)
SRM 1632d	Trace Elements in Coal (Bituminous)	2014	50g	<i>0.912</i>	<i>0.144</i>	0.1142	<i>76.98</i>	0.749	5.10	0.1094	<i>0.0390</i>	0.02969	...	3.845	1.642	<i>1.65</i>	0.0477	<i>(7.078)</i>	<i>(13821)</i>
SRM 1633c	Trace Elements in Coal Fly Ash	2011	75g	13.28	1.365	...	...	10.49	...	1.773	0.498	0.1707	<i>0.192</i>	0.00952	<i>0.110</i>	<i>21.30</i>	0.724	...	...
SRM 1635a	Trace Elements in Coal (Subbituminous)	2012	50g	<i>0.5437</i>	<i>1.087</i>	...	<i>(77.90)</i>	0.2472	<i>3.92</i>	...	<i>0.2303</i>	0.1031	<i>0.01874</i>	0.000285	<i>(0.294)</i>	...	<i>0.0524</i>	<i>(6.29)</i>	<i>(11664)</i>
SRM 1646a	Estuarine Sediment	2004	70g	2.297	0.519	...	...	2.008	...	0.864	0.388	0.741	0.027	0.00117	0.352	40.00	0.456	...	...
SRM 1648a	Urban Particulate	2015	2g	3.43	5.84	0.4543	<i>(12.7)</i>	3.92	...	1.056	0.813	0.4240	...	0.655	5.51	<i>12.8</i>	0.4021	...	...
SRM 2689	Fly Ash, Low Lime	2015	Set (3)	12.94	2.18	...	...	9.32	...	2.20	0.61	0.25	0.10	<i>(0.0052)</i>	...	24.06	0.75	<i>(12)</i>	<i>(12000)</i>
SRM 2690	Fly Ash, Medium Lime	2015	Set (3)	12.35	5.71	...	...	3.57	...	1.04	1.53	0.24	0.52	<i>(0.0039)</i>	0.15	25.85	0.52	<i>(5.3)</i>	<i>(9700)</i>
SRM 2691	Fly Ash, High Lime	2015	Set (3)	9.81	18.45	...	...	4.42	...	0.34	3.12	1.09	0.51	<i>(0.0029)</i>	0.83	16.83	0.90	<i>(4.8)</i>	<i>(8800)</i>
SRM 2709a	San Joaquin Soil	2009	50g	7.37	1.91	...	...	3.36	...	2.11	1.46	1.22	0.0688	0.00173	...	30.3	0.336	...	...
SRM 2710a	Montana I Soil	2009	50g	5.95	0.964	...	...	4.32	...	2.17	0.734	0.894	0.105	0.552	...	31.1	0.311	...	...
SRM 2711a	Montana II Soil	2009	50g	6.72	0.00541	...	...	2.82	...	2.53	1.07	1.20	0.0842	0.140	...	31.4	0.317	...	...

SRM 1648a also certified for PAH and PCB Congeners;

Environmental CRMs (continued) nominal mass content in µg/g

NIST No.	Ag	As	Ba	Br	Cd	Ce	Co	Cr	Cu	Hg	Mn	Ni	Rb	Sb	Se	Sr	Th	Tl	U	V	Zn
SRM 1632d (continued)	...	<i>6.1</i>	40.42	...	0.08	...	3.424	<i>13.7</i>	5.83	0.0928	<i>13.1</i>	<i>(10)</i>	7.36	0.445	<i>1.29</i>	63.5	1.428	...	0.517	23.74	<i>12.9</i>
SRM 1633c (continued)	...	186.2	1126	...	0.758	...	42.9	<i>258</i>	173.7	1.005	240.2	132	117.42	<i>8.56</i>	<i>13.9</i>	901	<i>23.0</i>	...	<i>9.25</i>	286.2	<i>235</i>
SRM 1635a (continued)	...	0.860	3578	...	<i>0.282</i>	...	2.004	3.56	11.42	0.0836	6.69	5.37	1.226	0.251	0.662	160	1.299	...	0.4792	13.34	<i>7.3</i>
SRM 1646a (continued)	<i><0.3</i>	6.23	<i>210</i>	...	0.148	<i>(64)</i>	<i>5</i>	40.9	10.01	<i>0.04</i>	234.5	22.5	<i>38</i>	<i>0.3</i>	0.193	<i>68</i>	<i>5.8</i>	...	<i>2.0</i>	44.84	48.9
SRM 1648a (continued)	<i>6.0</i>	115.5	...	502	73.7	54.6	17.93	402	610	1.323	790	81.1	51.0	45.4	<i>28.4</i>	215	...	...	...	127	4800
SRM 2689 (continued)	...	<i>(200)</i>	<i>(800)</i>	...	...	...	<i>(48)</i>	<i>(170)</i>	...	<i>(0.018)</i>	<i>(300)</i>	<i>(122)</i>	...	<i>(9)</i>	<i>(7)</i>	<i>(700)</i>	<i>(25)</i>	...	...	...	<i>(240)</i>
SRM 2690 (continued)	...	<i>(26)</i>	<i>(5800)</i>	...	...	...	<i>(19)</i>	<i>(67)</i>	...	<i>(0.0005)</i>	<i>(300)</i>	<i>(46)</i>	...	<i>(6)</i>	<i>(0.8)</i>	<i>(2000)</i>	<i>(25)</i>	...	...	...	<i>(120)</i>
SRM 2691 (continued)	...	<i>(30)</i>	<i>(5900)</i>	...	...	...	<i>(26)</i>	<i>(68)</i>	...	0.0578	<i>(200)</i>	<i>(53)</i>	...	<i>(3)</i>	<i>(17)</i>	<i>(2700)</i>	<i>(26)</i>	...	...	...	<i>(120)</i>
SRM 2709a (continued)	...	<i>10.5</i>	979	...	0.371	<i>42</i>	12.8	130	<i>33.9</i>	<i>0.9</i>	529	<i>85</i>	<i>99</i>	1.55	<i>(1.5)</i>	239	<i>10.9</i>	<i>0.58</i>	<i>3.15</i>	110	<i>103</i>
SRM 2710a (continued)	<i>(40)</i>	1540	792	...	12.3	<i>(60)</i>	5.99	<i>6</i>	3420	9.88	2149	<i>8</i>	<i>117</i>	52.5	<i>(1)</i>	255	<i>18.1</i>	<i>1.52</i>	9.11	<i>82</i>	4180
SRM 2711a (continued)	<i>(6)</i>	107	730	...	54.1	<i>(70)</i>	9.89	52.3	140	7.42	675	21.7	<i>120</i>	23.8	<i>(2)</i>	242	<i>15</i>	<i>(3)</i>	3.01	80.7	414

Please note that other categories of NIST SRMs (Standard Reference Materials) are available from BAS if required.

SOUTH AFRICAN BUREAU OF STANDARDS (SABS), South Africa

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified and figures in small italic type only approximate.

Igneous Rock Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	SiO ₂	Al ₂ O ₃	Total Fe as Fe ₂ O ₃	Fe ₂ O ₃	FeO	MgO	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	Cr ₂ O ₃	P ₂ O ₅	BaO	H ₂ O ⁺	CO ₂
SARM 4	NIM-N Norite	52.64	16.50	8.97	<i>0.8</i>	7.47	7.50	11.50	2.46	0.25	0.18	0.20	...	...	...	0.33	<i>0.1</i>
SARM 5	NIM-P Pyroxenite	51.10	4.18	12.70	0.87	10.59	25.33	2.66	0.37	0.09	0.22	0.20	3.50	...	...	0.26	<i>0.08</i>
SARM 6	NIM-D Dunite	38.96	<i>0.3</i>	17.00	0.71	14.63	43.51	0.28	<i>0.04</i>	<i>0.01</i>	0.22	...	...	0.26	0.42	0.30	0.40

Values are also given for the following minor and trace elements:- Ba, Ce, Co, Cr, Cu, Dy, Eu, F, Ga, Gd, La, Li, Lu, Mn, Nb, Ni, P, Pb, Rb, S, Sm, Sr, Tb, Th, Ti, Tm, U, V, Y, Yb, Zn, and Zr.

Chromium Ore Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	Al ₂ O ₃	CaO	Cr ₂ O ₃	FeO	Fe ₂ O ₃	MgO	MnO	SiO ₂	TiO ₂	V ₂ O ₅
SARM 131	Chromium Ore	14.60	<i>0.24</i>	41.83	...	30.7	9.15	0.243	3.13	0.944	0.414
SARM 146	Chromium Ore	14.54	0.10	46.91	25.58	...	10.62	0.22	0.616	0.57	0.32

Magnetite Iron Ore Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Fe	Al	K	Si	As	Ca	Cd	Co	Cr	Cu	Mg	Mn	Na	Ni	P	Pb	S	Ti	Zn	V
SARM 12	Magnetite Ore	66.63	0.41	0.0108	0.16	<i>0.0002</i>	0.78	<i>0.0005</i>	0.0223	0.0021	0.0502	1.69	0.17	0.0091	0.0281	0.0477	0.0025	0.0695	0.43	0.0142	0.0520

Hematite Iron Ore Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Fe	SiO ₂	Al ₂ O ₃	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	P
SARM 132	Hematite Iron Ore	62.2	7.82	1.84	<i>0.09</i>	<i>0.03</i>	0.22	<i>0.020</i>	<i>0.09</i>	0.054

Zirconium Concentrate Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	ZrO ₂	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	P ₂ O ₅	HfO ₂	CaO	MgO	Cr
SARM 13	Zirconium Concentrate	64.01	32.45	0.61	0.187	0.295	0.23	1.29	<i>0.14</i>	<i>0.044</i>	<i>0.0023</i>

Fluorspar Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	CaF ₂	CaCO ₃	MgCO ₃	P ₂ O ₅	Mn	SiO ₂	Fe ₂ O ₃
SARM 14	Acid Grade, Buffalo	97.32	<i>0.3</i>	<i>0.03</i>	<i>0.18</i>	...	<i>0.57</i>	<i>0.06</i>
SARM 15	Acid Grade, Zeerust	97.84	0.95	0.55	0.017	0.0213	<i>0.26</i>	<i>0.23</i>

Manganese Ore Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	Mn	Fe	SiO ₂	CaO	MgO	Al ₂ O ₃	P	Na ₂ O	K ₂ O	BaO	S	CO ₂	Zn
SARM 16	Manganese Ore (Wessels)	49.17	11.48	5.04	4.70	0.76	<i>0.3</i>	0.033	<i>0.03</i>	0.02	0.60	0.17	<i>1.3</i>	0.0364
SARM 17	Manganese Ore (Mamatwan)	38.81	4.27	4.69	<i>14.4</i>	3.03	0.24	0.018	0.09	0.09	<i>0.08</i>	<i>0.01</i>	15.40	0.0043
SARM 149	Manganese Ore (Kalahari)	38.0	5.39	5.89	14.2	2.08	0.221	0.021	0.147	0.132	0.050	...	...	...

The mineral content of SARM 149 is Braunitz: 57.4%, Calcite: 24.6% and Ankerite: 18.0% (Quartz, Hematite and Iron Sulphate were also observed).

Coal Certified Reference Materials (Finely divided material – units of 120g)

SABS No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	CaO	MgO	Na ₂ O	K ₂ O	P ₂ O ₅	S	LOI
SARM 18	Witbank Coal	6.20	2.57	0.29	0.114	0.18	0.11	...	0.145	...	0.56	90.11
SARM 19	OFS Coal	15.00	8.01	1.75	0.341	1.39	0.20	0.29	0.24	...	1.49	71.28
SARM 20	Sasolburg Coal	17.66	11.27	1.17	0.63	1.87	0.43	0.27	0.14	0.14	0.51	64.66

Values are also given for the following minor and trace elements:- As, Ba, Be, Ce, Co, Cr, Cs, Cu, Ga, Ge, Hf, Hg, La, Mn, Ni, P, Pb, Rb, Sc, Se, Sm, Sr, Ta, Th, U, V, Y, Zn and Zr.

Phosphate Rock Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	P ₂ O ₅	CaO	F	CO ₂	MgO	SrO	Fe ₂ O ₃
SARM 32	Phosphate rock	39.96	54.44	2.49	1.61	0.50	0.52	0.14

SOUTH AFRICAN BUREAU OF STANDARDS (SABS), South Africa

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets are for information only.

Andalusite Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Al ₂ O ₃	SiO ₂	Fe (as Fe ₂ O ₃)	TiO ₂	K ₂ O	Na ₂ O	MgO	CaO	LOI
SARM 34	Andalusite	59.15	39.04	0.75	0.168	0.238	0.093	0.131	<i>0.13</i>	0.622

Vanadium Pentoxide Certified Material (Finely divided material – units of 100g)

SABS No.	Description	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	As	S	V (Total)
SARM 38	Vanadium Pentoxide	0.14	<i>0.019</i>	0.119	0.060	0.0037	0.22	<i>0.008</i>	0.11	<i>0.001</i>	<i>0.0045</i>	55.84

Rock, Mineral and Sediment Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	Mass content	SiO ₂	Al ₂ O ₃	Fe as Fe ₂ O ₃	FeO	MgO	ZrO ₂	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	P ₂ O ₅	Cr ₂ O ₃	HfO ₂	U ₃ O ₈	ThO ₂	S
SARM 41	Carbonaceous Shale	%	56.67	13.50	4.23	<i>0.3</i>	8.10	...	1.50	0.93	1.39	0.06	0.55	0.05	...	...	...	...	<i>0.15</i>
SARM 42	Soil	%	74.09	10.03	4.68	<i>4.0</i>	1.92	...	0.89	<i>0.15</i>	0.45	0.10	0.36	<i>0.04</i>	0.63	...	...	...	<i>0.02</i>
SARM 43	Magnesite	%	5.99	<i>0.06</i>	0.26	<i>0.1</i>	44.11	...	0.75	<i>0.05</i>	<i>0.04</i>	<i>0.01</i>	<i>0.01</i>	<i>0.02</i>	...	...	...	...	<i>0.04</i>
SARM 44	Sillimanite Schist	%	38.84	58.80	2.60	<i>1.0</i>	<i>0.1</i>	...	0.14	<i>0.05</i>	0.18	0.03	1.83	0.10	...	...	...	...	<i>0.03</i>
SARM 47	Serpentinite	%	36.30	1.09	4.14	<i>0.4</i>	42.09	...	<i>0.10</i>	<i>0.05</i>	<i>0.02</i>	0.06	0.01	<i>0.02</i>	0.29	...	...	...	<i>0.02</i>
SARM 48	Fluorspar Granite	%	67.11	11.24	0.58	<i>0.2</i>	0.18	...	8.90	3.22	4.26	0.02	0.10	<i>0.09</i>	...	...	...	...	...
SARM 50	Dolerite	%	51.56	15.28	11.00	8.49	7.57	...	10.80	2.30	0.61	0.17	0.86	0.15	...	...	...	...	<i>0.03</i>
SARM 52	Stream Sediment	%	57.81	9.38	19.71	<i>4.0</i>	0.60	...	0.37	<i>0.1</i>	0.25	0.27	1.30	0.09	0.19	...	...	...	<i>0.02</i>
SARM 62	Zircon (RBM)	%	32.8	0.88	0.07	...	0.04	64.2	0.11	...	...	...	0.13	0.12	...	1.31	0.0354	0.0158	...

Rock, Mineral and Sediment Certified Reference Materials (continued)

SABS No.	Mass content	Ba	Ce	Co	Cr	Cu	Ga	Mo	Nb	Ni	Pb	Rb	Sr	Th	V	Y	Zn	Zr
SARM 41 (continued)	µg/g	820	<i>60</i>	<i>15</i>	123	53	<i>20</i>	<i>5</i>	8	122	<i>30</i>	59	54	<i>12</i>	139	17	76	146
SARM 42 (continued)	µg/g	<i>250</i>	<i>30</i>	35	...	17	<i>12</i>	<i>5</i>	8	125	<i>10</i>	22	37	<i>5</i>	94	11	44	192
SARM 43 (continued)	µg/g	<i>25</i>	<i>20</i>	4	<i>195</i>	<i>15</i>	...	...	...	252	...	...	8	...	...	...	<i>10</i>	...
SARM 44 (continued)	µg/g	<i>50</i>	<i>220</i>	<i>8</i>	384	<i>10</i>	<i>55</i>	<i>15</i>	96	<i>15</i>	<i>30</i>	13	5	50	395	84	271	405
SARM 47 (continued)	µg/g	<i>75</i>	<i>20</i>	79	...	<i>5</i>	<i>5</i>	...	...	2221	<i>60</i>	...	<i>3</i>	...	<i>16</i>	<i>5</i>	45	...
SARM 48 (continued)	µg/g	<i>290</i>	<i>850</i>	...	23	<i>10</i>	...	<i>5</i>	202	...	135	291	<i>5</i>	113	<i>8</i>	436	53	300
SARM 50 (continued)	µg/g	220	<i>30</i>	40	357	84	...	...	<i>10</i>	<i>85</i>	<i>25</i>	14	195	<i>6</i>	216	23	81	86
SARM 52 (continued)	µg/g	<i>410</i>	<i>210</i>	81	...	219	<i>15</i>	...	11	182	1200	20	25	<i>11</i>	346	20	264	250

PGM and Gold Ore Certified Reference Materials (Finely divided material – units of 3kg) nominal mass content in µg/g

SABS No	Description	Pt	Pd	Au	Rh	Ru	Ir	Ni
SARM 75	Sheba Sulphide Zone	0.32	0.61	0.053	...	...	...	2300
SARM 81	Gold Ore	2.50	1.48	<i>0.034</i>	0.490	<i>0.76</i>	<i>0.18</i>	...
SARM 107	PGM Ore	1.99	0.926	0.046	0.320	0.626	<i>0.14</i>	...

Ferro-Alloy Certified Reference Materials (Finely divided material – units of 100g) nominal mass content in %

SABS No.	Description	C	Si	Mn	P	S	Cr	Ni	Al	Co	Mg	Ti	V	Fe
SARM 33	Ferro-silicon	1.01	15.60	0.75	0.043	...	0.43	0.28	...	...	...	...	...	80.2
SARM 144	Ferro-chromium	6.64	5.30	0.32	<i>0.02</i>	<i>0.04</i>	49.02	0.20	<i>0.06</i>	<i>0.06</i>	<i>(0.04)</i>	0.67	0.36	36.87

Ferro-Chrome Slag Certified Reference Material (Finely divided material – units of 100g) nominal mass content in %

SABS No.	Description	Cr ₂ O ₃	SiO ₂	Al ₂ O ₃	Fe _{Total}	CaO	MgO	S
SARM 77	Ferro-Chrome Slag	12.5	26.8	27.5	5.31	3.64	22.99	<i>0.32</i>

SPL-LABMAT (SPL), Czech Republic

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified and figures in small italic type only approximate.

Cast Iron Certified Reference Materials (Approx. 40mm diameter x 18mm depth discs)

SPL No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co
CZ02033-1G	3.22	2.53	0.701	0.036	0.007	0.044	0.185	0.357	0.062	0.0034	0.010
CZ02033-2G	3.78	1.10	0.096	0.125	0.009	0.027	0.002	0.650	0.019	0.0023	0.012
CZ02033-3D	3.24	2.12	0.317	0.008	0.006	0.236	0.453	0.025	0.055	0.0071	0.014
CZ02033-4E	4.45	0.090	0.034	0.023	0.006	0.030	0.002	0.049	0.003	...	0.033
CZ02033-5C	2.30	1.40	0.704	0.027	0.091	0.085	0.104	0.188	0.103	0.0078	0.013
CZ02033-6C	3.11	3.25	1.25	0.097	0.019	1.33	0.006	0.021	0.024	0.0024	0.005
CZ02033-7C	3.55	1.73	0.389	0.028	0.026	0.542	0.966	1.26	0.040	0.0008	0.048
CZ02033-8C	3.41	1.93	0.408	0.168	0.058	0.125	0.041	0.102	0.004	...	0.030

SPL No.	Cu	Pb	Sn	Ti	V	W	Bi	Ce	Mg	Sb	Zn
CZ02033-1G (cont.)	0.027	0.016	0.028	0.054	0.019	0.015	0.005	0.023	0.050	...	0.003
CZ02033-2G (cont.)	0.88	0.008	0.015	0.029	0.017	0.004	0.006	0.013	0.036	0.029	0.020
CZ02033-3D (cont.)	0.396	0.005	0.009	0.016	0.072	...	0.002	0.006	0.016	0.007	...
CZ02033-4E (cont.)	0.005	0.002	0.001	0.011	0.015	...	0.002	...	...	...	...
CZ02033-5C (cont.)	0.013	...	0.002	0.008	0.054	...	0.007	...	...	0.002	...
CZ02033-6C (cont.)	0.273	0.003	0.131	0.107	0.192	0.007	...	...	...	0.044	...
CZ02033-7C (cont.)	0.016	...	0.004	0.026	0.067	0.037	0.002	...	...	...	...
CZ02033-8C (cont.)	0.158	0.008	0.067	0.022	0.015	...	0.009	...	...	0.014	...

Cast Iron Certified Reference Materials (Approx. 40mm diameter x 18mm depth discs)

SPL No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Zr
CZ20034-11B	2.44	3.67	0.382	0.271	0.140	1.178	1.144	0.082	0.067	0.0032	0.007	0.007
CZ20034-12B	2.92	2.96	1.047	0.484	0.077	0.638	0.117	0.174	0.077	0.047	0.002	0.002
CZ20034-13C	3.15	2.23	0.704	0.0261	0.0044	0.124	0.360	1.299	0.022	...	0.02	0.02
CZ20034-14C	3.14	2.49	0.275	0.0162	0.0081	0.045	0.646	0.030	0.007	0.0123	0.013	0.013
CZ20034-15C	3.47	1.68	0.060	0.054	0.0028	0.078	0.002	0.728	0.010	0.0057	...	...
CZ20034-16C	3.87	0.95	1.311	0.173	0.0243	0.332	0.195	0.375	0.004	0.00	0.002	0.002
CZ20034-17C	4.08	0.150	0.503	0.104	0.0033	0.178	0.030	2.32	0.002	0.0006	...	...

SPL No.	Cu	Pb	Sn	Ti	V	W	Bi	Ce	Mg	Sb	As	Zn
CZ20034-11B (cont.)	0.130	0.007	0.074	0.041	0.182	0.005	0.007	...	...	0.011	0.005	...
CZ20034-12B (cont.)	0.223	0.009	0.042	0.071	0.326	0.002	0.006	...	...	0.046	0.024	0.004
CZ20034-13C (cont.)	0.089	...	0.014	0.015	0.043	0.003	...	0.011	0.064	0.002	0.002	...
CZ20034-14C (cont.)	0.585	...	0.025	0.018	0.013	0.003	...	0.019	0.017	0.020	0.035	0.010
CZ20034-15C (cont.)	1.123	...	0.006	0.036	0.019	0.004	0.008	0.030	0.040	0.056	0.003	...
CZ20034-16C (cont.)	0.345	0.015	0.125	0.057	0.027	0.015	...	...	...	0.010	0.003	0.017
CZ20034-17C (cont.)	0.037	0.002	0.002	0.015	0.076	0.004	0.002	0.003	0.007	...	0.005	...

Some other SPL samples are available, and information on these will be provided on request.

SUS (SUS), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – figures in small italic type only approximate and and figures in brackets are for information only.

Aluminium and Aluminium Alloy Setting-up Samples (Approx. 55mm dia. x 50mm discs)

SUS No.	Al	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ag	B	Be	Bi	Ca	Cd	Co	Ga	Li	P	Pb	Sn	Sr	V	Zr	Na	Sb	In
SUS-RA10	<i>99.99</i>	<i>0.0010</i>	<i>0.0005</i>	<i>0.0002</i>	<i><0.0001</i>	<i><0.0001</i>	<i><0.0001</i>	<i><0.0002</i>	<i><0.0003</i>	<i><0.0001</i>	<i><0.0001</i>	<i><0.0002</i>	<i><0.0001</i>	<i><0.0003</i>	<i><0.00001</i>	...	<i><0.0001</i>	<i><0.0001</i>	<i><0.00002</i>	...	<i><0.0003</i>	<i><0.0003</i>	<i><0.00003</i>	<i><0.0002</i>	<i><0.0001</i>	<i><0.00001</i>	<i><0.0003</i>	...
SUS-RA18	<i>75</i>	<i>15</i>	<i>0.2</i>	<i>7.5</i>	<i>0.3</i>	<i>0.2</i>	<i>0.0003</i>	<i>3</i>	<i>0.3</i>	<i>0.001</i>	<i>0.01</i>	<i>0.0035</i>	<i><0.0001</i>	<i>0.001</i>	<i>0.004</i>	<i>0.0005</i>	<i><0.001</i>	<i>0.008</i>	<i><0.001</i>	<i>0.015</i>	<i>0.37</i>	<i>0.37</i>	<i>0.05</i>	<i>0.001</i>	<i>0.005</i>	<i>0.005</i>	<i>0.45</i>	...
SUS-RA19	<i>78</i>	<i>1.7</i>	<i>1.3</i>	<i>0.8</i>	<i>1.3</i>	<i>8</i>	<i>0.2</i>	<i>0.6</i>	<i>7</i>	<i>0.2</i>	<i>0.3</i>	<i>0.001</i>	<i>0.005</i>	<i>0.2</i>	<i>0.008</i>	<i>0.04</i>	<i>0.3</i>	<i>0.06</i>	<i>0.009</i>	<i>0.0009</i>	<i>0.01</i>	<i>0.02</i>	<i>0.009</i>	<i>0.1</i>	<i>0.2</i>	<i>0.001</i>	<i>0.007</i>	<i>0.01</i>
SUS-RA20	<i>75.8</i>	<i>13.5</i>	<i>0.7</i>	<i>5.2</i>	<i>0.3</i>	<i>1</i>	<i>0.09</i>	<i>2.7</i>	<i>0.2</i>	<i>0.05</i>	...	...	...	...	<i>0.005</i>	...	...	...	...	<i>0.02</i>	<i>0.1</i>	<i>0.06</i>	...	<i>0.1</i>	<i>0.09</i>	<i>0.008</i>	...	...

Cobalt and Cobalt Alloy Setting-up Samples (Approx. 40mm dia. x 20mm discs)

SUS No.	Co	C	Si	Mn	P	S	Cr	Cu	Ni	Mo	Nb	Ti	V	W	Zr	Fe	Ta	Al
SUS-RC011	<i>99.9</i>	...	<i>0.01</i>	<i><0.005</i>	<i><0.003</i>	<i>0.0005</i>	<i><0.005</i>	<i><0.01</i>	<i>0.003</i>	<i><0.0005</i>	<i><0.0005</i>	<i><0.3</i>	<i>0.001</i>	<i>0.01</i>	<i><0.003</i>	<i><0.02</i>	...	...
SUS-RC014	<i>52</i>	<i>0.2</i>	<i>1</i>	<i>0.5</i>	<i>(0.005)</i>	<i>(0.005)</i>	<i>30</i>	...	<i>10</i>	...	...	...	...	<i>7</i>	...	<i>(0.7)</i>	...	...
SUS-RC015	...	<i>1</i>	<i>0.2</i>	...	<i>0.02</i>	<i>0.02</i>	...	<i>1</i>	...	<i>6</i>	<i>2</i>	<i>0.1</i>	<i>0.1</i>	...	...	<i>24</i>	<i>0.5</i>	<i>0.1</i>
SUS-RC016	...	<i>0.2</i>	<i>0.4</i>	...	...	...	...	<i>3</i>	...	<i>3</i>	<i>2</i>	<i>0.1</i>	<i>1</i>	...	...	<i>25</i>	<i>0.2</i>	<i>0.1</i>

Copper and Copper Alloy Setting-up Samples (Approx. 40mm dia. x 40mm discs)

SUS No.	Cu	Zn	Pb	Sn	Mn	Fe	Ni	Si	Sb	Al	C	S
SUS-RC11	<i>99.99</i>	<i>0.0002</i>	<i>0.0002</i>	<i>0.0004</i>	<i>0.0001</i>	<i>0.0005</i>	<i>0.0005</i>	<i>0.0001</i>	<i>0.0001</i>	<i>0.0001</i>	...	<i>0.0010</i>
SUS-RC32	<i>60</i>	<i>35</i>	<i>(0.6)</i>	<i>(0.2)</i>	<i>(0.5)</i>	<i>(0.3)</i>	<i>(1.5)</i>	<i>0.5</i>	...	<i>1.5</i>	...	...
SUS-RC33	<i>80</i>	<i>(0.02)</i>	<i>(0.01)</i>	...	<i>(0.4)</i>	<i>4.5</i>	<i>4</i>	...	...	<i>10</i>	...	...
SUS-RC36	<i>80</i>	<i>(0.4)</i>	<i>12</i>	<i>7</i>	...	<i>(0.01)</i>	<i>(1.7)</i>	...	<i>(0.3)</i>	...	...	...
SUS-RC38	<i>65</i>	<i>(0.02)</i>	<i>(0.01)</i>	...	<i>0.75</i>	<i>0.5</i>	<i>30</i>	...	...	...	<i>(0.05)</i>	<i>(0.015)</i>
SUS-RC40	<i>82</i>	<i>(0.01)</i>	<i>(0.02)</i>	...	<i>5</i>	<i>1.5</i>	<i>2</i>	...	...	<i>9</i>	...	...

Iron and Steel Setting-up Samples (Disc samples – approx. dimensions as below)

SUS No.	Disc Dimensions	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	Nb	Pb	Sn	Ti	V	W
SUS-RE12	40mm dia. x 40mm	<i><0.005</i>	<i>0.003</i>	<i><0.01</i>	<i><0.005</i>	<i><0.002</i>	<i><0.01</i>	<i><0.005</i>	<i><0.01</i>	<i><0.005</i>	<i><0.001</i>	<i><0.0001</i>	<i>0.002</i>	<i><0.01</i>	<i>0.002</i>	<i><0.002</i>	<i>0.001</i>	<i>0.0003</i>	<i><0.001</i>	<i><0.01</i>
SUS-RG13	40mm dia. x 20mm	<i>3</i>	<i>2</i>	<i>1</i>	<i>0.3</i>	<i>0.05</i>	<i>1</i>	<i>0.3</i>	<i>0.6</i>	<i>0.02</i>	...	...	...	<i>0.05</i>	...	...	<i>0.2</i>	<i>0.04</i>	<i>0.3</i>	...
SUS-RG14	"	<i>3</i>	<i>2</i>	<i>0.2</i>	<i>0.02</i>	<i>0.005</i>	<i>1</i>	...	...	<i>0.02</i>	...	...	...	<i>0.05</i>	...	...	<i>0.2</i>	...	<i>0.1</i>	...
SUS-RH12	40mm dia. x 40mm	<i>0.5</i>	<i>0.6</i>	<i>17</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>4</i>	...	...	...	...	...	...	...	...	...	...	...	...	...
SUS-RH18	"	<i>1.3</i>	<i>(0.04)</i>	<i>(0.3)</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>4</i>	<i>3.5</i>	...	...	...	...	...	<i>10</i>	...	...	...	...	<i>3</i>	<i>10</i>
SUS-RH31	"	<i>0.03</i>	<i>0.3</i>	<i>1.2</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>17</i>	<i>2</i>	<i>20</i>	...	...	...	...	<i>2</i>	<i>0.3</i>	<i>2</i>	...	...	...	...
SUS-RN13	40mm dia. x 40mm	<i>1</i>	<i>(0.05)</i>	<i>1.8</i>	<i>(0.005)</i>	<i>(0.005)</i>	<i>(0.05)</i>	<i>(0.01)</i>	<i>3</i>	<i>0.4</i>	<i>(0.002)</i>	<i>(0.0005)</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>(0.005)</i>	<i>(0.001)</i>	<i>0.05</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>(0.01)</i>
SUS-RN14	"	<i>(0.05)</i>	<i>1.8</i>	<i>(0.07)</i>	<i>0.08</i>	<i>0.08</i>	<i>3</i>	<i>0.5</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>0.05</i>	<i>0.006</i>	<i>0.4</i>	<i>0.4</i>	<i>0.5</i>	<i>0.03</i>	<i>(0.0005)</i>	<i>0.1</i>	<i>0.5</i>	<i>0.4</i>
SUS-RN19	"	<i>1</i>	<i>1</i>	<i>1.5</i>	<i>0.08</i>	<i>0.07</i>	<i>3</i>	<i>1</i>	<i>1</i>	<i>0.5</i>	<i>0.05</i>	<i>0.006</i>	<i>0.8</i>	<i>0.5</i>	<i>0.5</i>	<i>(0.03)</i>	<i>0.1</i>	<i>0.1</i>	<i>0.5</i>	<i>0.5</i>
SUS-CFE3	40mm dia. x 30mm	<i>0.04</i>	<i>0.4</i>	<i>1.7</i>	<i>0.3</i>	<i>0.002</i>	<i>16.7</i>	<i>2.0</i>	<i>11</i>	<i>0.007</i>	...	<i>0.005</i>	<i>0.21</i>	<i>0.09</i>	<i>0.77</i>	...	...	<i>0.005</i>	<i>0.07</i>	<i>0.03</i>
SUS-CFE4	"	<i>1.7</i>	<i>0.4</i>	<i>0.4</i>	<i>0.01</i>	<i>0.01</i>	<i>11</i>	<i>0.8</i>	<i>0.3</i>	<i>0.008</i>	<i>0.008</i>	<i>0.002</i>	<i>0.03</i>	<i>0.06</i>	<i>0.04</i>	<i>0.005</i>	<i>0.005</i>	<i>0.003</i>	<i>1</i>	<i>0.03</i>
SUS-CFE5	40mm dia. x 20mm	<i>4</i>	<i>0.3</i>	<i>0.3</i>	<i>0.1</i>	<i>0.03</i>	<i>0.1</i>	<i>0.1</i>	<i>0.1</i>	<i>0.1</i>	...	...	...	<i>0.1</i>	...	...	<i>0.04</i>	...	<i>0.1</i>	...

The above figures are target levels and may vary between batches. Bracketed figures may vary more significantly.

SUS (SUS), Germany

CHEMICAL COMPOSITION (nominal mass content in %) - figures in small italic type only approximate and figures in brackets for information only.

Lead and Lead Alloy Setting-up Samples (Approx. 40mm dia. x 40mm discs)

SUS No.	Pb	Zn	Sn	Cd	As	Cu	Bi	Fe	Ti	Ni	Ag	Sb	Te	Se	S	Al	In	Ca	Cr	Co	Ge	Ba	Mn	Pt	Na	Au	Mg	Pd
SUS-RPB11	<i>99.99</i>	<i>0.0005</i>	<i>0.0005</i>	<i>0.0005</i>	<i>0.0005</i>	<i>0.0002</i>	<i>0.0030</i>	<i>0.0002</i>	<i>0.0003</i>	<i>0.0002</i>	<i>0.0006</i>	<i>0.0003</i>	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
SUS-RPB14	<i>88</i>	<i><0.003</i>	<i>0.015</i>	<i>0.002</i>	<i>1.2</i>	<i>0.06</i>	<i>0.005</i>	...	<i>0.01</i>	<i>0.001</i>	<i>0.005</i>	<i>10</i>	<i>0.01</i>	<i>0.01</i>	<i>0.01</i>	...	...	...	...	...	...	...	...	...	...	...	...	...
SUS-RPB15	<i>64</i>	<i>0.1</i>	<i>30</i>	<i>0.01</i>	<i>0.02</i>	<i>1.5</i>	<i>0.1</i>	<i>0.005</i>	<i>0.01</i>	<i>0.003</i>	<i>3</i>	<i>2</i>	<i>0.01</i>	<i>0.01</i>	...	...	...	...	...	...	...	...	...	...	...	...	...	...
SUS-RPB16	<i>97</i>	<i>0.001</i>	<i>0.18</i>	...	...	...	...	...	...	...	<i>0.003</i>	...	...	...	...	<i>0.02</i>	...	<i>0.3</i>	...	...	<i>0.01</i>	<i>0.02</i>	...	...	<i>0.01</i>	...	<i>0.0015</i>	...
SUS-RPB17	<i>83</i>	<i>0.001</i>	<i>3.6</i>	...	<i>0.3</i>	<i>1.5</i>	<i>0.1</i>	<i>0.007</i>	<i>0.002</i>	<i>0.001</i>	<i>0.3</i>	<i>9.9</i>	<i>0.003</i>	...	...	...	...	<i>0.01</i>	<i>0.0009</i>	<i>0.001</i>	<i>0.001</i>	...	<i>0.0002</i>	<i>0.001</i>	...	<i>0.001</i>	...	<i>0.0003</i>
SUS-RPB18	<i>90</i>	...	<i>0.03</i>	<i>0.03</i>	<i>7.6</i>	<i>0.06</i>	<i>0.3</i>	...	<i>0.02</i>	...	<i>0.09</i>	<i>1.2</i>	<i>0.03</i>	<i>0.02</i>	...	...	<i>0.01</i>	...	...	...	...	...	...	...	...	...	...	...

Magnesium and Magnesium Alloy Setting-up Samples (Approx. 50mm dia. x 50mm discs)

SUS No.	Mg	Si	Fe	Cu	Mn	Ni	Al	Zn	Pb	Sn	Zr	Cd	Na	Ce	La	Y	Nd	Pr
SUS-RMG11	<i>99.9</i>	<i><0.01</i>	<i><0.03</i>	<i><0.002</i>	<i>0.01</i>	<i><0.001</i>	<i>0.01</i>	<i>0.01</i>	<i>0.001</i>	<i>0.001</i>	<i>0.001</i>	...	...	...	...	...	...	...
SUS-RMG13	<i>93</i>	<i>0.01</i>	<i>0.001</i>	<i>0.006</i>	<i>0.2</i>	<i>0.001</i>	<i>5.7</i>	<i>0.8</i>	<i>0.001</i>	<i>0.001</i>	<i>0.004</i>	<i>0.0001</i>	<i>0.001</i>	...	...	...	...	...
SUS-RMG14	<i>88</i>	<i>0.8</i>	<i>0.003</i>	<i>0.3</i>	<i>0.4</i>	<i>0.04</i>	<i>7.9</i>	<i>1</i>	<i>0.02</i>	<i>0.08</i>	<i>0.08</i>	<i><0.01</i>	<i><0.01</i>	...	...	...	...	...
SUS-RMG16	...	...	<i>0.001</i>	...	...	...	...	...	...	...	<i>0.06</i>	...	...	<i>2.2</i>	<i>1</i>	<i>2.2</i>	<i>1.6</i>	<i>0.26</i>

Nickel and Nickel Alloy Setting-up Samples (Approx. 40mm dia. x 40mm discs)

SUS No.	Ni	C	Si	Mn	P	S	Cr	Fe	Mo	V	Cu	Nb	Co	W	B	Ti	Al	Pb	Zn	Ag
SUS-RNI10	<i>99.99</i>	<i><0.0008</i>	<i><0.0010</i>	...	...	<i><0.0002</i>	...	<i><0.0005</i>	...	...	<i><0.0001</i>	...	<i><0.0003</i>	...	...	...	<i><0.0004</i>	<i>0.00008</i>	<i>0.0002</i>	<i>0.00003</i>
SUS-RNI11	<i>99.6</i>	<i>(0.03)</i>	<i>(0.1)</i>	<i>(0.25)</i>	...	<i>(0.25)</i>	...	<i>(0.25)</i>	...	...	<i>(0.03)</i>	...	...	...	...	<i>(0.03)</i>	...	...	...	...
SUS-RNI12	<i>65</i>	<i>(0.1)</i>	<i>(0.1)</i>	<i>(0.6)</i>	...	<i>(0.6)</i>	...	<i>(0.6)</i>	...	...	<i>30</i>	...	...	...	...	<i>0.5</i>	<i>2.5</i>	...	...	...
SUS-RNI13	<i>57</i>	<i>(0.02)</i>	<i>(0.05)</i>	<i>(0.5)</i>	<i>(0.01)</i>	<i>(0.5)</i>	<i>16</i>	<i>(0.5)</i>	<i>16</i>	<i>(0.2)</i>	<i>(0.1)</i>	...	<i>(1.5)</i>	<i>3.5</i>	...	...	...	...	...	...
SUS-RNI14	<i>50</i>	<i>0.05</i>	<i>(0.2)</i>	<i>(0.2)</i>	...	<i>(0.2)</i>	<i>20</i>	<i>(0.2)</i>	<i>6</i>	...	<i>(0.03)</i>	...	<i>20</i>	...	<i>(0.0005)</i>	<i>2</i>	<i>0.5</i>	...	...	...
SUS-RNI15	<i>51</i>	<i>0.05</i>	<i>(0.1)</i>	<i>(0.1)</i>	<i>(0.005)</i>	<i>(0.1)</i>	<i>18</i>	<i>(0.1)</i>	<i>3</i>	...	<i>(0.03)</i>	<i>5</i>	<i>(0.5)</i>	...	<i>0.005</i>	<i>1</i>	<i>0.6</i>	...	...	...

Zinc and Zinc Alloy Setting-up Samples (Approx. 40mm dia. x 30mm discs)

SUS No.	Zn	Pb	Sn	Cd	Cu	Fe	Al	Mg	Ti	Ni	Mn	Ag	In	Sb	Tl
SUS-RZN11	<i>99.99</i>	<i>0.0008</i>	<i><0.0001</i>	<i><0.0001</i>	<i>0.0003</i>	<i>0.0005</i>	<i><0.0001</i>	<i><0.0001</i>	<i><0.0001</i>	<i>0.0001</i>	<i><0.0001</i>	...	...	...	...
SUS-RZN13	<i>99</i>	<i>0.6</i>	<i>0.3</i>	<i>0.3</i>	<i>0.3</i>	<i>0.02</i>	<i>0.3</i>	<i><0.001</i>	<i><0.001</i>	<i>0.05</i>	<i><0.001</i>	<i>0.05</i>	<i>0.3</i>	<i>0.2</i>	<i>0.03</i>
SUS-RZN14	<i>85.7</i>	<i>0.03</i>	<i>0.02</i>	<i>0.02</i>	<i>4</i>	<i>0.05</i>	<i>10</i>	<i>0.08</i>	<i>0.1</i>	<i>0.004</i>	<i>0.015</i>	<i>0.007</i>	<i><0.01</i>	<i><0.01</i>	...

The above figures are target levels and may vary between batches. Bracketed figures may vary more significantly.

VASIPARI KUTATO ES FEJLESZTO VALLALAT (VASKUT), Hungary

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Unalloyed and Low Alloy Steel Certified Reference Materials (32-35mm dia. x 19mm discs)

VASKUT No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	Nb	Sn	Ti	V	Sb
A11/1	0.043	(1.46)	0.21	0.011	0.0137	0.02	1.20	0.04	0.02	...	...	...	0.047	0.16	0.002	0.17	0.46	<0.001
A12	0.031	1.19	0.31	0.014	0.082	1.25	0.47	2.43	0.18	0.007	...	0.012	0.18	(0.03)	...	0.05	0.042	0.013
A13	0.104	0.81	0.49	0.053	0.073	0.14	0.91	1.93	0.042	0.070	(0.002)	0.013	0.166	...	0.060	0.11	0.23	0.024
A14	0.12	0.73	0.75	0.041	0.052	0.59	0.25	1.32	(0.01)	0.13	0.004	0.070	0.20	0.044	0.10	0.12	0.67	0.047
A18	1.16	0.15	(1.99)	0.014	0.007	0.90	...	0.125	(0.02)	0.003	(0.011)	...	0.066	0.035	0.016	0.011	0.10	0.005

Unalloyed and Low Alloy Steel Certified Reference Materials (All 32-35mm dia. x 19mm discs, except K3-K9 which are 32-25mm dia. x 40mm discs)

VASKUT No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	Nb	Ti	V	W	Zr
B2/1	0.067	0.34	1.34	0.047	0.046	...	1.09	1.49	0.082	...	0.24	...	0.22	0.91	...	...
B3	0.20	0.53	0.14	(0.012)	0.025	5.94	...	...	...	...	0.25	...	...	1.16	1.19	...
B4	0.55	1.72	1.07	0.047	0.043	...	...	...	...	...	0.49	...	...	...	...	0.09
B15	0.98	0.80	0.69	0.030	0.031	3.70	1.20	0.15	0.13	0.21	0.14	...	0.32	0.33	...	...
B16	0.16	1.95	2.05	0.068	0.051	0.26	0.11	3.74	(0.037)	...	0.09	0.11	0.075	0.53	...	...
K3	1.03	0.32	0.46	(0.02)	0.010	1.63	...	0.18	...	...	0.09	...	...	...	...	...
K4	0.52	0.46	0.84	(0.02)	0.025	1.24	...	(0.1)	...	...	0.28	...	...	0.20	...	...
K6	0.51	0.30	0.79	(0.02)	0.026	0.96	0.37	1.72	...	...	0.26	...	...	...	...	...
K9	0.096	0.59	1.53	(0.01)	0.018	0.64	0.56	0.97	(0.01)	...	0.73	(0.04)	0.11	0.27	...	...

Austenitic Stainless Steel Certified Reference Materials (All 32-35mm dia. x 19mm discs, except K7-K10/C which are 32-25mm dia. x 40mm discs)

VASKUT No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Cu	Nb	Ti	Fe
K7	0.063	0.89	1.44	0.026	0.012	17.5	...	10.45	...	0.20	...	0.27	...
K8	0.061	1.38	1.10	0.026	0.017	23.5	...	...	1.53	(0.18)	...	...	...
K10/C	0.13	0.88	1.77	0.022	0.020	17.5	2.98	11.2	...	0.16	0.98	...	...
S15	0.043	0.26	0.38	(0.02)	0.013	16.7	2.46	3.90	...	1.54	0.64	...	(74.0)
S19	0.26	2.32	0.32	0.012	0.021	7.00	0.11	12.8	...	0.19	0.81	0.048	(76.1)
S20	0.097	1.80	1.50	0.011	0.025	2.06	3.15	18.2	...	0.44	1.22	(0.01)	(71.5)
S21	0.37	1.26	0.19	0.017	0.021	3.99	4.12	22.3	...	0.11	...	0.50	(67.1)
S22	0.014	0.61	0.34	0.009	0.008	1.00	0.82	28.2	...	(0.02)	...	0.13	(68.8)
S25	0.067	1.49	1.90	0.045	0.015	15.6	1.77	13.8	...	0.07	0.07	0.46	(64.7)
S26	0.076	0.67	0.99	0.027	0.026	18.9	2.59	3.31	...	0.14	0.07	0.11	(73.1)

PURCHASE PROCEDURE

ORDERING PROCEDURE

Please give the quantity, unit size or weight, reference number, description and producer of the samples required, and ensure we have your full delivery and invoice address. In the case of EU customers, please also provide your VAT number.

PRICES

For prices see separate price list. Prices are stated in £ Sterling (GBP) and are subject to revision without notice. They exclude packing, despatch and VAT where applicable.

TERMS

The following terms apply:-

- (i) **United Kingdom.** Net monthly account (subject to approved bank and trade references.) Insurance and freight are charged extra, and Value Added Tax at the standard rate is charged on the net invoice value.
- (ii) **Overseas.** Packing, documentation, insurance and carriage are charged extra at cost. We shall be pleased to forward a quotation detailing these costs upon request. Prepayment is required on all orders.

PAYMENT

To enable us to meet customer requirements with the minimum of delay, new and occasional customers are asked to make payment in advance using one of the following options:-

By BACS or inter-bank transfer to Barclays Bank PLC, Middlesbrough, Sort Code 20-56-74, SWIFT BARC GB22

In **Sterling** to account No 90217506, IBAN GB 07 BARC 20567490217506.

In **Euros** to account No 85465422, IBAN GB 10 BARC 20567485465422.

We accept Barclays charges in the UK but not your own bank's charges.

By credit/debit card.

Customers who indicate that they wish to purchase by this method will receive a secure link for Worldpay by email. The link will only be sent at our request and is not available from our web site. For additional security we do not require you to send us any card details to our address.

Please send all orders, enquiries and correspondence to:

**BUREAU OF ANALYSED SAMPLES LTD.,
NEWHAM HALL, NEWBY,
MIDDLESBROUGH, ENGLAND TS8 9EA**

Telephone: National: Middlesbrough (01642) 300500
International: + 44 1642 300500
Fax: National: Middlesbrough (01642) 315209
International: + 44 1642 315209
Website: www.basrid.co.uk
Email: enquiries@basrid.co.uk

BAS

MIDDLESBROUGH

UK