

INDEX

- A
- ACID EXTRACTION [64](#), [74](#)
 ALBITE [71](#)
 ALPHA ALUMINA [2](#)
 ALUMINA [2](#)
 ALUMINUM ELECTROLYTE [2](#)
 ALUMINUM FLUORITE [2](#)
 AMPHIBOLITE [28](#)
 ANDALUSITE [2](#)
 ANDESITE [3](#), [92](#)
 ANHYDRITE [3](#)
 ANORTHOSITE [4](#), [91](#)
 ANTIMONY ORE [4](#)
 AQUA REGIA METHOD [41](#), [73](#)
 ARAGONITE [4](#)
 ASCHARITE ORE [4](#)
- B
- BARITE ORE [4](#)
 BASALT [5](#), [91](#), [92](#)
 BAUXITE [2](#), [6](#)
 BERYLLIUM ORE [7](#)
 BORATE ORE [7](#)
 BRUCITE [7](#)
- C
- CALCEROUS OOZE [56](#)
 CALCINED BONE [7](#)
 CALCITE [4](#)
 CARBONATITE [7](#)
 CHERT [7](#)
 CHROME MAGNESITE [8](#)
 CHROMITE [8](#)
 CHROMIUM ORE [8](#)
 CLAY [9](#), [71](#)
 CONTAMINATED RIVER SEDIMENT [68](#)
 CONTAMINATED SOIL [79](#), [80](#)
 COPPER ORE [10](#), [11](#), [12](#), [13](#)
 CORUNDUM [13](#)
 CRYOLITE [14](#)
 CYANIDE [79](#)
- D
- DACITE [91](#)
 DIABASE [14](#)
 DIORITE [14](#), [24](#), [26](#)
 DOLERITE [15](#)
 DOLOMITE [16](#), [41](#), [42](#), [43](#), [44](#)
 DOLOMITE SUBSTITUTE [16](#)
 DUNITE [17](#)
- E
- ESTUARY SEDIMENT [65](#)
 EXTRACTION [64](#), [74](#)
- F
- FELDSPAR [18](#), [71](#)
 FIRECLAY [9](#)
 FLAGSTONE [92](#)
 FLUORITE [19](#)
 FLUORSPAR [19](#)
- G
- GABBRO [20](#), [92](#)
 GAIROME CLAY [71](#)
 GOLD ASSAY PILLS [21](#)
 GOLD ORE [22](#), [23](#), [24](#), [54](#), [91](#)
- GRANITE [25](#)
 GRANODIORITE [24](#), [26](#), [92](#)
 GRAPHITE [26](#), [27](#)
 GREISEN [27](#)
 GYPSUM [27](#), [28](#)
- H
- HEXAVALENT CHROMIUM [79](#)
 HORNBLENDITE [28](#)
- I
- ILMENITE [85](#)
 IRON ORE [30](#), [31](#), [32](#), [33](#), [34](#), [35](#), [36](#), [37](#), [38](#)
 IRON ORE SINTER [39](#)
 IRON PELLETS [29](#)
 IRON SULPHIDE [29](#)
- K
- KAOLIN [39](#), [71](#)
 KIMBERLITE [40](#)
 KOMATIITE [87](#)
- L
- LAKE SEDIMENT [64](#)
 LATERITE [40](#)
 LEAD BASILICATE [41](#)
 LEAD ORE [41](#), [51](#)
 LIMESTONE [16](#), [41](#), [42](#), [43](#), [44](#)
 LITHIUM ORE [45](#)
 LUJAVRITE [46](#)
- M
- MAGNESITE [46](#)
 MAGNETITE ORE [46](#)
 MANGANESE NODULE [48](#)
 MANGANESE ORE [47](#)
 MARINE SEDIMENT [65](#)
 MARIPOLITE [49](#)
 MERCURY IN SOIL [73](#)
 MERCURY ORE [49](#), [73](#)
 MOLOCHITE [50](#)
 MOLYBDENUM ORE [50](#)
 MULLITE [2](#), [9](#)
 MULTI-METAL ORE [52](#), [53](#), [81](#)
- N
- NEPHELINE SYENITE [83](#)
 NICKEL ORE [40](#), [53](#), [54](#)
 NIOBIUM ORE [54](#)
 NOBLE METAL ORE [54](#), [55](#)
 NORITE [91](#)
- O
- OBSIDIAN [56](#)
 OLIVINE [5](#), [56](#)
 OOZE [56](#)
 OPHIOLITE [92](#)
- P
- PEGMATITE [57](#)
 PERIDOTITE [57](#)
 PHOSPHATE ROCK [58](#)
 PLAGIOGNEISS [58](#)
 POTASSIUM FELDSPAR [71](#)
 POTTERY STONE [71](#)
 PROPHILITE [58](#)
 PROPHYLITE [71](#)
- Q
- QUARTZ [59](#)
 QUARTZITE [59](#)
- R
- RARE EARTH ORE [59](#), [60](#), [61](#), [91](#)
 RHYOLITE [62](#)
 RIVER SEDIMENT [66](#), [68](#)
 RUTILE [62](#)
- S
- SANDSTONE [63](#)
 SCHIST [63](#), [71](#)
 SEDIMENT [64](#), [65](#), [66](#), [67](#), [68](#), [69](#)
 SEQUENTIAL EXTRACTION [64](#)
 SERPENTINITE [69](#)
 SHALE [70](#)
 SILICA ROCK [71](#)
 SILICEOUS MINERALS [71](#)
 SILICEOUS OOZE [56](#)
 SILLIMANITE [2](#), [71](#)
 SILLIMANITE SCHIST [71](#)
 SILT [71](#)
 SILTSTONE [92](#)
 SILVER ORE [22](#), [23](#), [24](#), [54](#), [72](#)
 SLATE [72](#)
 SOIL [73](#), [74](#), [75](#), [76](#), [77](#), [78](#), [79](#), [80](#), [93](#),
[94](#), [95](#), [96](#), [97](#), [98](#)
 STEATITE [80](#)
 STONE [71](#)
 STREAM SEDIMENT [66](#), [67](#)
 SULPHIDE ORE [51](#)
 SULPHUR ORE [81](#), [82](#)
 SYENITE [83](#)
- T
- TALC [84](#)
 TANTALUM ORE [84](#)
 TIBET SEDIMENT [69](#)
 TILL [74](#)
 TIN ORE [51](#), [84](#)
 TITANIUM ORE [85](#)
 TUNGSTEN ORE [84](#), [86](#)
- U
- ULTRAMAFIC ROCK [87](#)
 URANIUM ORE [87](#)
 URTITE [87](#)
- V
- VANADIUM ORE [87](#)
 VOLCANIC TUFF [87](#)
- W
- WOLLASTONITE [88](#)
- Z
- ZEOLITE [88](#)
 ZINC ORE [51](#), [89](#), [90](#)
 ZIRCONIUM MATERIALS [90](#)
 ZIRCONIUM ORE [90](#)

CRM ALPHA ALUMINA

analysis listed in mass %		many other trace elements on certificate										100 g units	
Number	Alpha-Alumina	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI
IIMS-135A	99.02	(99.96)	<0.01	<0.01	(0.002)	<0.01	<0.01	<0.01	<0.001	<0.001	<0.01	<0.01	(0.15)

ALUMINA

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg T = Total

#	Number	Al ₂ O ₃	Be*	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO*	Na ₂ O	P*	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Units
2	CERAM AN26	99.76	.	0.03	.	0.03	<0.01	<0.01	.	0.02	.	.	0.12	<0.01	(0.08)	25 or 100 g
2	CERAM AN25	99.39	.	0.03	.	0.03	0.01	<0.01	.	0.53	.	<0.01	<0.01	<0.01	(0.34)	25 or 100 g
1	VS SH12/3	73.6	.	18.8	0.46	0.66T	.	2.15	0.76	.	.	100 g
1	NCS DC62107b	67.64	.	0.60	.	2.48	0.11	0.21	.	0.03	SO ₃ :0.03	.	10.85	3.14	14.50	20 g

CRM ALUMINA SET

SET/3 ONLY for R034, others set or individually

trace informational Cl, NiO, SO₃ 50 g

Number	B ₂ O ₃	CaO	CuO	Fe ₂ O ₃	Ga ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	SrO	TiO ₂	ZnO	ZrO ₂	LOI
JCRM R034	(<0.0006)	0.0002	(<0.0003)	(0.0003)	0.0021	0.0020	(<0.0001)	0.0018	0.0045	(<0.0001)	(<0.0004)	(<0.0002)	(<0.0002)	0.188
JCRM R035	(<0.0006)	0.0188	0.0018	0.0151	0.0074	0.0005	0.0013	0.222	0.0116	0.0007	0.0029	0.0012	0.0009	0.156
JCRM R036	0.0533	0.0242	(<0.0003)	0.0139	0.0076	(0.0002)	0.0006	0.0316	0.0569	0.0002	0.0032	0.0007	0.0004	0.072

CRM ALUMINOUS SET

available in SET/3 only

100 g units

Number	Type	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	ZrO ₂ +HfO ₂	LOI
JCRM R303	Bauxite	88.49	0.012	1.51	.	0.006	.	0.064	5.55	2.93	0.110	.
JCRM R304	Sillimanite	55.94	0.427	0.585	0.329	0.451	0.273	.	35.90	1.33	0.105	4.26
JCRM R041	Mullite	70.18	0.059	0.598	0.174	0.190	0.197	0.136	28.11	0.185	0.058	.

CRM ALUMINUM ELECTROLYTE SET

available only in set/7

powder 100 g

Number	Al	Al ₂ O ₃	Ca	F	Fe ₂ O ₃	K	Li	Mg	SiO ₂
NCS DC91030-1	14.16	4.63	2.06	49.94	0.242	2.37	0.491	0.406	0.134
NCS DC91030-2	15.55	6.96	2.41	50.05	0.113	1.06	0.625	0.302	0.120
NCS DC91030-3	14.58	3.41	3.36	52.88	0.024	1.63	0.235	0.339	(0.024)
NCS DC91030-4	12.24	3.43	5.52	51.41	0.022	1.21	0.148	0.249	0.023
NCS DC91030-5	12.74	1.97	5.14	52.72	0.017	1.40	0.171	0.284	0.026
NCS DC91030-6	14.84	2.86	2.79	53.73	0.018	1.41	0.223	0.296	(0.021)
NCS DC91030-7	12.59	2.19	1.15	52.66	0.017	0.084	0.028	0.952	(0.017)

CRM ALUMINUM FLUORITE

analysis listed in mass %

100 g units

Number	F	Al	Fe ₂ O ₃	Na	P ₂ O ₅	SiO ₂	SO ₄	LOI
NCS DC91016	64.97	31.92	0.025	0.028	0.0275	0.196	0.076	1.25
NCS DC91008	61.79	30.70	0.132	0.097	0.0253	0.104	0.585	(4.61)
NCS DC91011	61.51	32.28	0.021	0.121	0.1317	0.429	0.627	0.754
NCS DC91010	60.96	30.52	0.126	0.125	0.0265	0.251	0.748	(5.48)
NCS DC91013	60.88	33.12	0.020	0.315	0.0013	0.017	0.098	0.467
NCS DC91007	60.76	30.27	0.156	0.104	0.0295	0.146	0.654	(6.00)
NCS DC91015	59.99	30.70	0.107	0.111	0.0247	0.301	0.702	(5.61)
NCS DC91012	59.74	33.93	0.037	0.126	0.0027	0.016	0.136	0.547
NCS DC91009	57.79	34.68	0.028	0.113	0.0008	0.015	0.093	0.662
NCS DC91014	57.72	34.76	0.015	0.113	0.0007	0.014	0.104	0.640

CRM ANDALUSITE

100 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	TiO ₂	LOI
SARM 34	59.15	(0.13)	0.75	0.23	0.13	0.093	39.04	0.16	0.62

CRM ANDESITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	Si	SiO ₂	Al	Al ₂ O ₃	CO ₂	CaO	Fe	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	
JA-1	29.90	63.97	8.06	15.22	.	5.70	4.95	3.98	2.59	7.07	+0.72	-0.30	0.77	1.57	0.157	3.84	0.165	0.85	.
JA-1a	.	63.66	.	15.40	.	5.74	.	3.67	.	7.17	.	.	0.78	1.55	0.157	3.90	0.165	0.87	.
GBW 07110	.	63.06	.	16.1	1.03	2.47	.	0.19	4.51	.	+1.79	.	5.17	0.84	0.089	3.06	0.36	0.80	.
JA-3	29.11	62.27	8.23	15.56	.	6.24	4.62	4.83	1.15	6.60	+0.20	-0.11	1.41	3.72	0.104	3.19	0.116	0.70	.
GBW 07104	.	60.62	.	16.17	3.47	5.20	.	2.39	.	4.90	+1.5)	.	1.89	1.72	.	3.86	.	.	4.44
US AGV-2a	27.7	59.3	8.95	16.91	.	5.20	4.68	.	.	6.69	.	.	2.88	1.79	.	4.19	0.48	1.05	.
USZ 48-2009	.	59.20	.	16.72	.	5.58	.	(1.66)	.	5.43	.	.	2.42	3.52	0.081	4.46	0.264	0.71	1.39
CGL 019	.	58.64	.	16.0	.	3.85	.	.	.	5.91	.	(0.58)	4.85	1.74	0.0469	4.41	1.002	1.395	(1.33)
JA-2	26.37	56.42	8.16	15.41	.	6.29	4.34	3.69	2.16	6.21	+1.12	-1.25	1.81	7.60	0.108	3.11	0.146	0.66	.

continued analysis listed in mg/kg except * which is ppb and % which is mass %

Number	Ag	As	Au*	B	Ba	Be	Bi	Ca%	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	
JA-1	.	2.78	0.16	21.0	311	0.50	.	4.07	0.11	13.3	43.0	12.3	7.83	0.62	43.0	4.55	3.04	1.20	
JA-1a	(322)	(12.9)	(4.1)	.	(41.8)
GBW 07110	0.17	5.96	.	10.8	1053	3.64	0.09	.	0.61	117	160	7.9	7.7	7.16	9.1	5.32	2.93	1.96	
JA-3	0.084	.	.	24.8	323	0.80	.	4.46	.	22.8	.	21.1	66.2	2.08	43.4	3.01	1.57	0.82	
GBW 07104	0.071	2.1	(0.95)	4.7	1020	1.1	0.081	.	0.061	40	(46)	13.2	32	2.3	55	1.85	0.85	1.02	
US AGV-2a	.	.	.	1140	2.3	.	.	3.72	.	68	.	16	17	(1.16)	53	3.6	(1.79)	(1.54)	
USZ 48-2009	(0.08)	(3.64)	.	.	672	(2.01)	(0.12)	.	(0.06)	55.2	.	19.2	95.9	1.09	41.2	(2.55)	(1.18)	1.44	
CGL 019	.	6.5	.	.	2828	2.22	(0.10)	.	.	219	.	13.4	35	11.7	21.6	4.03	1.62	3.36	
JA-2	.	.	0.26	20.7	321	2.05	.	4.50	.	32.7	.	29.5	436	4.63	29.7	2.80	1.48	0.93	

Number	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	K%	La	Li	Lu	Mg%	Mn%	Mo	Na%	Nb
JA-1	161	16.7	4.36	1.33	2.42	.	0.95	.	.	0.64	5.24	10.8	0.47	0.95	0.122	1.59	2.85	1.85
JA-1a	(11.6)	.	.	.	(1.2)	.	.
GBW 07110	1120	19.8	6.54	1.11	7.5	0.014	1.10	0.07	0.11	.	62.5	17.5	0.49	.	0.95	.	20.8	
JA-3	.	16.3	2.96	.	3.42	.	0.51	.	.	1.17	9.33	14.5	0.32	2.24	0.081	1.89	2.37	3.41
GBW 07104	280	18.1	2.7	0.93	2.9	0.012	0.34	(0.14)	0.037	.	22	18.3	0.12	0.3	0.0604	0.54	.	6.8
US AGV-2a	(440)	20	(4.69)	.	(5.08)	.	(0.71)	.	.	2.39	38	(11)	(0.25)	1.08	0.0770	.	3.11	15
USZ 48-2009	.	21.1	(3.93)	.	3.80	(0.004)	(0.46)	.	.	.	26.2	(13.2)	(0.15)	.	.	(0.60)	.	3.23
CGL 019	.	21.7	(7.8)	.	8.3	.	0.658	.	.	112	22.7	0.179	.	.	(1.74)	.	14.8	
JA-2	.	16.9	3.06	.	2.86	.	0.50	.	.	1.50	15.8	27.3	0.27	4.58	0.084	0.60	2.31	9.47

Number	Nd	Ni	P%	Pb	Pr	Rb	S	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Ti%
JA-1	10.9	.	0.072	6.55	1.71	12.3	21.6	0.22	28.5	.	3.52	.	263	0.13	0.75	.	0.82	0.51
JA-1a	.	(2.3)	(268)
GBW 07110	47.2	12.6	.	97.7	13.2	183	230	1.34	7.52	0.03	8.63	3.12	318	1.42	0.99	(0.007)	16.7	.
JA-3	12.3	32.2	0.051	7.70	2.40	36.7	.	.	22.0	.	3.05	.	287	0.27	0.52	.	3.25	0.42
GBW 07104	19	17	0.1030	11.3	4.9	38	192	0.12	9.5	(0.04)	3.4	0.79	790	0.40	0.41	0.017	2.6	0.3090
US AGV-2a	30	19	0.21	13	8.3	68.6	.	(0.6)	13	.	(5.7)	(2.3)	658	(0.89)	(0.64)	.	6.1	0.63
USZ 48-2009	27.2	61.2	.	18.7	(6.77)	49.7	.	(0.27)	11.8	.	5.16	(0.86)	1116	(0.25)	0.49	.	6.46	.
CGL 019	90.7	27	.	34.1	25.3	104	.	8.5	8.6	.	13.2	1.8	2692	0.74	0.871	.	11.4	.
JA-2	13.9	130	0.064	19.2	3.84	72.9	.	.	19.6	.	3.11	1.68	248	0.80	0.44	.	5.03	0.40

Number	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
JA-1	.	0.47	0.34	105	.	30.6	3.03	90.9	88.3	20 g last of stock
JA-1a	.	.	.	(107)	.	.	.	(91)	(94.9)	100 g
GBW 07110	1.02	0.50	3.04	64.3	1.62	28.0	3.15	164	335	50 g
JA-3	.	.	1.18	169	.	21.2	2.16	67.7	118	20 g
GBW 07104	0.16	0.15	0.90	94	(0.45)	9.3	0.89	71	99	70 g
US AGV-2a	(0.27)	(0.26)	1.88	120	.	20	1.6	86	230	25 g
USZ 48-2009	(0.22)	(0.17)	1.96	123	(1.70)	11.8	1.00	71.5	141	100 g
CGL 019	(0.45)	0.207	1.72	102	(0.93)	17.7	1.231	89	368	100 g
JA-2	0.32	0.28	2.21	126	.	18.3	1.62	64.7	116	20 g

CRM ANHYDRITE

analysis listed in mass %

50 g units

Number	Al ₂ O ₃	CO ₂	CaO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	SO ₃	SiO ₂	Sr	TiO ₂
GUV AN	(0.023)	0.65	40.7	0.014	(0.5)	0.013	0.34	(0.002)	0.032	57.6	(0.22)	0.14	(0.003)

continued analysis listed in mg/kg

Number	B	Ba	Cl	Cr	Cs	Cu	Ga	Li	Mo	Rb	Sb	Ta	Th	V	Zn	Zr
GUV AN	100	14.8	0.033	0.90	0.037	4	4.3	9	1.2	4.7	0.044	0.007	0.048	18	7.9	13

CRM ANORTHOSITE

analysis listed in mass %

40 g units

Number	SiO ₂	Al ₂ O ₃	Ba	CaO	CO ₂	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	H ₂ O+	T.H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂
VS MO11	53.46	27.42	0.0319	10.95	0.0	1.09	0.53	1.74	0.088	0.33	0.42	0.65	0.49	0.037	4.39	0.041	0.0100	0.10
VS 2120-81	51.77	22.78	0.051	10.06	0.36	4.66	6.26	.	0.40	.	.	0.76	2.10	0.076	4.04	0.140	0.069	1.87
VS MO10	51.65	23.91	0.0294	10.18	0.14	4.40	1.45	6.34	0.095	0.26	0.36	0.50	2.24	0.073	3.99	0.13	0.0460	0.83

continued

analysis listed in mg/kg except % which is mass %

Number	B	Be	Co	Cr	Cs	Cu	F	Ga	La	Li	Mo	Nb	Ni	Pb	Rb	Sc	Sn	Sr	V%	Y	Yb	Zn	Zr
VS MO11	4.5	0.8	9.6	12	0.73	26	420	21	20	7.5	1.2	2.6	14	6.8	2.7	5	5.1	802	0.0024	8	1.1	50	42
VS 2120-81	.	0.9	23	36	.	31	.	17	10	7	.	23	.	.	0.013	.	.	83	72
VS MO10	8.7	1.1	27	23	0.55	44	380	26	24	7.1	2.0	3.9	32	8.0	5.5	11	5.0	477	0.0109	17	2.0	96	58

CRM ANTIMONY ORE

analysis listed in mass %

200 g units

Number	Al	As	C	Ca	Cu	Fe	H ₂ O	K	Mg	Na	Pb	S	Sb	Si	LOI
CAN CD-1	(5.5)	0.66	(0.2)	(1.4)	(<0.01)	(2.8)	(0.2)	(1.8)	(0.6)	(0.1)	(0.02)	(3.1)	3.57	(32.9)	(4.0)

CRM ANTIMONY ORE

analysis listed in mass %

analysis in mg/kg * Sb calculated from certified results for 4ACID, ICP, and XRF

Number	Sb	Pb	S	Se	Zn	Ag	As	Au	Bi	Cd	Co	Cu	Ga	Li	Nb	Ni	Sn	Units
GSb-3 *	53.69	10 g
GSb-2	31.0838	23.64	10 g
GSb-11 *	21.10	10 g
GSb-10 *	11.66	10 g
GSb-6 *	9.88	10 g
GSb-9 *	6.50	10 g
GSb-4 *	3.43	10 g
NCS DC70013	1.81	0.012	1.02	0.018	0.037	7.3	25.3	.	(0.24)	2.6	2.2	51.3	9.1	22.8	5.4	3.2	3.0	50 g
GSb-7 *	1.75	10 g
GSb-8 *	1.63	10 g
GSb-5 *	0.18	10 g
GSb-1	0.1636	10 g

CRM ARAGONITE/CALCITE

100 g units

Number	Al ₂ O ₃	CO ₂	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	S	SiO ₂	SrO	LOI
UNS AK	0.11	43.0	54.9	0.20	0.130	0.037	0.110	0.047	0.029	0.046	0.64	0.28	43.27

CRM ASCHARITE ORE

Number	B ₂ O ₃	CaO	T.Fe	FeO	MgO	P	S	SiO ₂	Ins.Res.	Units
NCS DC16005	5.65	0.15	52.98	26.13	11.64	0.016	1.242	4.51	4.72	100 g

CRM BARITE ORE

70 g units

Number	BaO	BaSO ₄	CaF ₂	Cu	T.Fe ₂ O ₃	Pb	Salt	SO ₃	Sr	Zn
NCS DC86002	65.40	98.47	.	(0.00029)	.	.	(0.11)	34.37	0.10	(0.00060)
NCS DC86004	57.36	86.14	.	0.00421	.	.	(0.13)	31.44	1.22	(0.00056)
NCS DC86005	44.80	66.93	.	0.0129	.	.	(0.21)	24.50	1.12	0.00269
NCS DC86003	28.36	41.46	14.03	0.00067	.	.	(0.37)	14.99	0.054	0.00124
NCS DC86001	28.34	42.41	.	0.0109	49.37	.	(0.28)	15.94	0.39	0.00223
NCS DC86007	27.01	40.54	.	0.00102	.	.	(0.21)	13.95	0.059	0.00364
NCS DC86006	13.00	18.87	.	0.14	20.96	0.41	0.93	51.33	0.058	3.76

CRM BASALT WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	H ₂ O+	T.H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂
US BER-2	54.1	13.5	.	7.12	.	.	13.8	.	.	.	1.79	3.59	.	3.16	0.35	2.26
JB-2	53.25	14.64	.	9.82	9.98	3.33	14.25	0.13-	0.25	.	0.42	4.62	0.218	2.04	0.101	1.19
JB-2a	53.22	14.67	.	9.79	9.83	.	14.18	.	.	.	0.41	4.58	0.214	2.03	0.095	1.18
USZ 46-2008	51.85	14.50	.	5.41	6.15	9.85	3.99	6.33	0.13	4.40	0.85	2.11
JB-1b	51.11	14.38	.	9.6	5.16	3.29	9.02	1.06-	1.53	.	1.32	8.14	0.147	2.63	0.256	1.26
JB-3	50.96	17.20	.	9.79	7.85	3.20	11.82	0.07-	0.18	.	0.78	5.19	0.177	2.73	0.294	1.44
JB-3a	50.87	17.16	.	9.75	7.71	.	11.83	.	.	.	0.78	5.17	0.179	2.74	0.291	1.44
US BHVO-2	49.9	13.5	.	11.4	.	.	12.3	.	.	.	0.52	7.23	.	2.22	0.27	2.73
VS MO15	49.55	16.93	0.20	8.30	4.60	4.96	10.07	0.32-	1.34	1.66	1.51	5.23	0.059	4.35	0.39	1.68
GUV BM	49.51	16.25	1.35	6.47	7.28	9.67	.	3.62	.	.	0.20	7.47	0.140	4.65	0.106	1.14
VS 2116-81	49.15	16.53 (0.13)	.	18.87	7.71	1.07	.	1.34	.	.	0.98	6.56	0.164	3.74	0.40	1.65
SRM 688	48.4	17.36	.	(12.17)	7.64	10.35	0.187 (8.4)	.	.	2.15	0.134	1.17
CGL 014	48.34	13.03	.	8.88 (7.91)	.	.	12.66	(0.13)	(0.37)	.	1.72	8.03	0.15	3.63	0.70	2.68
US BIR-1a	47.96	15.5	.	13.3	8.34	2.06	11.3	.	.	.	0.030	9.70	0.175	1.82	0.021	0.96
VS MO14	46.85	17.06	0.0	9.60	6.83	3.26	10.85	0.81	1.73	2.54 (0.46)	8.05	0.15	3.00	0.37	1.62	Olivine

continued analysis listed in mg/kg except % which is mass % and * which is ppb

Number	Ag	Al*	As	Au*	B	Ba	Be	Bi	C	Ca%	Cd	Ce	Cl	Co	Cr	Cs	Cu
US BER-2	.	7.14	.	.	.	683	.	.	.	5.09	.	53	.	37	18	(1.1)	(19)
JB-2	(0.072)	7.75	2.87	5.64	30.2	222	(0.26)	(0.033)	(0.0218)	7.02	0.14	6.76	281	38	28.1	0.85	225
JB-2a	(222)	(39)	(28)	.	(272)
USZ 46-2008	772	2.81	103	.	36.3	222	1.15	32.21
JB-1b	.	1.24	1.3	.	419	40.3	439	1.21	55.5
JB-3	0.075	9.10	1.84	1.99	18.0	245	0.81	.	(120)	7.00	0.081	21.5	(259)	34.3	58.1	0.94	194
JB-3a	(244)	(0.69)	(35.5)	(57)	.	(195)
US BHVO-2	.	7.16	.	.	.	130	.	.	.	8.17	.	38	.	45	280	.	127
VS MO15	.	.	.	9.9	225	2.2	34	136	1.4	28
GUV BM	(0.8)	.	13	.	(12)	250	1.3	36	121	2.0	43
VS 2116-81	300	2.3	37	99	.	61
SRM 688	332	.	.
CGL 014	474	67.51	.	46.50	188	(0.6)	64.00
US BIR-1a	.	(0.44)	.	(0.33)	(6)	(0.58)	1.9	(26)	52	370	.	125	
VS MO14	.	.	.	8.7	172	1.9	50	152	1.5	66	

Number	Dy	Er	Eu	F*	Fe	Ga	Gd	Ge	Hf	Hg	Ho	In	K%	La	Li	Lu	Mg%
US BER-2	.	.	2.0	(0.0440)	9.65	23	6.8	.	(4.8)	.	(1.33)	.	1.49	25	(9)	(0.51)	2.16
JB-2	3.73	2.6	0.86	0.00985	9.97	17	3.28	1.35	1.49	0.00478	0.75	0.094	0.35	2.35	7.78	0.4	2.79
JB-2a	(7.9)	.	.
USZ 46-2008	4.67	1.84	2.62	.	.	22.63	7.17	1.29	6.63	.	0.78	.	.	55.99	11.08	0.19	.
JB-1b	10.8	.	.
JB-3	4.54	2.49	1.32	0.0253	8.27	19.8	4.67	1.12	2.67	(0.0024)	0.80	.	0.65	8.81	7.21	0.39	3.13
JB-3a	(7.3)	.	.	.
US BHVO-2	.	.	.	(0.0370)	8.63	21.7	(6.3)	.	4.1	.	(1.04)	.	0.43	15	(5)	(0.28)	4.36
VS MO15	.	.	.	0.1600	.	20	69	16	.	.
GUV BM	(4.6)	(2.7)	1.12	0.028	.	16	(5.8)	(1.3)	3.0	.	(1.4)	.	.	9	72	0.41	.
VS 2116-81	.	.	.	0.0480	.	22	.	1.1	4.0	9.3	.	.
SRM 688
CGL 014	(5.23)	(2.21)	(2.48)	(0.08)	.	21.20	(7.3)	.	(5.25)	.	(0.91)	.	.	35.11	(9.33)	(0.22)	.
US BIR-1a	4	.	0.55	(0.0044)	.	(16)	2	.	0.6	0.63	3.6	(0.3)	.
VS MO14	.	.	.	0.0470	.	15	34	7.5	.	.

Number	Mn%	Mo	Na%	Nb	Nd	Ni	P%	Pb	Pr	Rb	S	Sb	Sc	Se	Si%	Sm	Sn
US BER-2	0.1520	248	2.34	.	28	.	0.15	(11)	(6.8)	48	.	.	33	.	25.3	(6.7)	.
JB-2	0.169	1.08	1.51	(1.58)	6.63	16.6	0.044	5.36	1.01	7.37	0.00179	0.25	53.5	(0.19)	24.89	2.31	0.95
JB-2a	(15.5)	.	.	.	(7.2)
USZ 46-2008	.	5.20	.	52.21	46.62	162	.	8.70	11.90	63.05	.	0.28	10.10	.	.	8.72	2.66
JB-1b	148	.	6.8	.	39.1	10	0.2
JB-3	0.137	1.09	2.03	2.47	15.6	36.2	0.128	5.58	3.11	15.1	9.86	0.12	33.8	(0.069)	23.82	4.27	0.94
JB-3a	(39)	.	(5.7)	.	(15.1)
US BHVO-2	0.1290	.	1.64	(18)	25.0	119	0.12	.	.	9.8	.	.	32	.	23.3	(6.2)	(1.9)
VS MO15	.	3.4	.	13	.	90	.	8.8	.	50	160	.	29	.	.	.	4.2
GUV BM	.	(0.8)	.	.	15	57	.	13	(3.0)	10	.	2.3	34	.	.	3.6	.
VS 2116-81	.	1.8	.	.	.	86	.	12	.	14	(90)	.	22	.	.	.	7.0
SRM 688	0.167	1.91
CGL 014	.	(2.92)	.	56.50	36.33	163	.	5.66	(8.19)	28.60	SO3: (0.10)	19.33	.	.	.	(7.74)	.
US BIR-1a	.	.	.	(0.6)	2.5	170	.	(3)	.	.	.	(0.58)	44	.	.	(1.1)	.
VS MO14	.	2.5	.	11	.	111	.	8.6	.	4.0	60	.	25	.	.	.	2.4

Number	Sr	Ta	Tb	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	LOI	Units
US BER-2	346	.	(1.07)	6.2	1.35	.	(0.54)	1.69	416	.	37	3.5	127	188	.	50 g
JB-2	178	0.13	0.6	0.35	0.71	(0.042)	0.41	0.18	575	(0.26)	24.9	2.62	108	51.2	.	20 g last of stock
JB-2a	(179)	(574)	.	(25.4)	.	(108)	(61.8)	.	100 g
USZ 46-2008	927	3.20	0.95	6.95	.	0.12	0.23	1.64	105	1.15	20.48	1.34	114	287	.	100 g
JB-1b	439	214	80	.	.	100 g
JB-3	403	0.15	0.73	1.27	0.86	0.048	0.42	0.48	372	(1.06)	26.9	2.55	100	97.8	.	20 or 100 g
JB-3a	(405)	(377)	.	(27.7)	.	(102)	(100)	.	100 g
US BHVO-2	389	(1.4)	(0.9)	(1.2)	1.63	.	.	.	317	.	26	(20)	103	172	.	50 g
VS MO15	554	234	.	39	2.6	33	152	.	40 g
GUV BM	220	(0.3)	0.9	(3.0)	.	.	.	(1.1)	190	0.9	27	3.0	120	100	.	50 g
VS 2116-81	500	150	.	29	2.6	82	190	.	40 g
SRM 688	169.2	60 g
CGL 014	741	(3.24)	(1.02)	(4.76)	.	.	(0.27)	(0.93)	197	(3.41)	23.60	(1.69)	133	201	(0.17)	100 g
US BIR-1a	110	310	.	16	1.7	70	18	.	25 g
VS MO14	468	181	.	39	3.0	108	162	.	40 g

BAUXITE

= class, 1=CRM and 2=RM

17034

#	Number	Al ₂ O ₃	A.Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	F ₂ O ₅	SiO ₂	R.SiO ₂	TiO ₂	V ₂ O ₅	ZrO ₂	LOI
1	BCS 394/1	88.88	.	0.0173	.	.	1.372	.	0.0047	.	0.0574	6.47	.	2.969	.	.	.
1	NCS HC28815	88.55	.	0.15	.	.	1.75	0.11	0.073	0.017	0.23	4.88	.	3.69	.	.	.
1	NCS DC14223	88.34	.	0.29	.	.	1.24	0.078	0.4	0.28	0.11	6.97	.	1.57	.	.	0.66
1	NCS DC14222	87.5	.	0.58	.	.	1.61	0.087	0.12	0.15	0.13	6.01	.	3.14	.	.	0.61
1	JCRM R301	87.5	.	0.03	.	.	1.40	0.04	0.02	0.03	0.07	7.24	.	2.90	.	0.13*	0.35
1	NCS DC61105	85.07	.	0.24	.	.	1.18	0.44	0.21	0.080	.	8.17	.	3.76	.	.	0.29
1	NCS DC14221	83.61	.	0.45	.	.	1.71	0.2	0.18	0.036	0.22	10.07	.	3.27	.	.	0.098
1	NCS HC28814	83.07	.	0.22	.	.	2.71	0.17	0.088	0.022	0.18	9.69	.	3.64	.	.	0.15
1	NCS DC91017	71.14	.	0.75	.	.	2.01	0.477	0.090	0.022	0.221	3.16	.	3.04	.	.	.
1	NCS HC28813	70.28	.	0.37	.	.	6.64	0.20	0.18	0.051	0.25	14.20	.	2.85	.	.	4.57
1	NCS DC91018	64.53	.	0.26	.	.	6.06	0.22	0.246	0.030	0.185	8.02	.	2.59	.	.	.
1	NCS DC14220	63.53	.	0.98	.	.	1.97	0.35	1.93	0.21	0.26	26.56	.	2.59	.	.	1.39
1	NCS HC28812	60.41	.	0.51	.	.	9.69	0.22	0.26	0.070	0.30	17.82	.	2.22	.	.	7.96
1	DSZU 123.62-13	57.4	.	0.12	0.035	.	0.88	.	0.075	.	0.073	8.73	.	2.51	0.044	.	.
1	NCS DC91019	57.15	.	0.089	.	.	16.11	1.00	0.235	0.31	0.077	6.31	.	2.65	.	.	.
1	SRM 696	54.5	.	0.018	0.047	.	8.70	0.009	0.012	(0.007)	0.050	3.79	.	2.64	0.072	0.14	29.9
1	IPT 131	54.1	11.5	0.022	.	.	0.15	0.78	.	1.77	0.042	0.35	30.0
1	BCS 395	52.4	.	0.05	(0.07)	.	16.3	(0.02)	0.02	(0.02)	.	1.24	.	1.93	.	.	27.8
1	SRM 69b	48.8	.	0.13	0.011	.	7.14	0.068	0.085	(0.025)	0.118	13.43	.	1.90	0.028	0.29	27.2
1	SRM 698	48.2	.	0.62	0.080	.	19.6	0.010	0.058	.	0.37	0.69	.	2.38	0.064	0.061	27.3
1	IMS-469	47.19	.	(0.013)	0.098	.	23.20	0.022	0.025	0.017	0.091	2.26	.	2.56	0.129	0.088	24.33
1	IMS PBS-75	46.76	.	0.022	0.045	.	19.15	0.024	0.070	0.027	0.070	15.90	.	2.53	0.060	0.122	15.22
1	NCS HC28811	46.52	.	0.69	.	.	14.01	0.25	0.37	0.10	0.35	22.96	.	1.36	.	.	12.75
1	IMS-470	46.32	.	(0.010)	0.099	.	23.90	0.023	0.026	0.018	0.093	2.32	.	2.52	0.132	0.087	24.53
1	SRM 697	45.8	.	0.71	0.100	.	20.0	0.062	0.18	.	0.97	6.81	.	2.52	0.063	0.065	22.1
1	IMS-471	44.24	.	(0.010)	0.091	.	26.87	0.037	0.029	0.019	0.108	2.82	.	2.40	0.142	0.092	23.15
1	DSZU 123.61-13	42.8	.	0.13	0.22	.	27.2	.	0.046	.	0.086	3.36	.	2.15	0.071	.	.
1	IMS PBS-74	42.53	.	0.016	0.041	.	19.73	0.019	0.050	0.025	0.043	18.41	.	1.86	0.064	0.072	17.2
1	IMS PBS-62	40.39	.	0.038	0.068	.	27.44	0.039	0.066	0.034	0.051	9.59	.	3.77	0.118	0.099	18.33
1	GBAP-17	40.01	.	0.041	.	.	18.42	0.184	.	0.030	0.080	16.02	.	1.62	0.042	.	19.79
1	SRM 600	40.0	.	0.22	0.024	.	17.0	0.23	0.05	0.022	0.039	20.3	.	1.31	0.060	0.060	20.5
1	GBAP-18	39.77	.	0.010	.	.	18.44	0.256	.	0.015	0.049	19.00	.	1.35	0.059	.	20.8

#	Number	Al ₂ O ₃	A.Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	F ₂ O ₅	SiO ₂	R.SiO ₂	TiO ₂	V ₂ O ₅	ZrO ₂	LOI
---	--------	--------------------------------	----------------------------------	-----	--------------------------------	----	--------------------------------	------------------	-----	-------------------	-------------------------------	------------------	--------------------	------------------	-------------------------------	------------------	-----

A.Al₂O₃: Available Alumina R.SiO₂: Reactive Silica * Includes H₂O

Number	BaO	C	Ga ₂ O ₃	MnO	S	SO ₃	ZnO	Units
BCS 394/1	100 g
NCS HC28815	.	0.018	50 g
NCS DC14223	50 g
NCS DC14222	50 g
JCRM R301	100 g
NCS DC61105	50 g
NCS DC14221	50 g
NCS HC28814	.	0.050	.	0.011	.	.	.	50 g
NCS DC91017	.	.	0.0114	0.036	0.031	.	0.0018	50 g
NCS HC28813	.	0.099	.	0.053	.	.	.	50 g
NCS DC91018	.	.	0.0106	0.012	0.040	.	0.0040	50 g
NCS DC14220	50 g
NCS HC28812	.	0.014	.	0.082	.	.	.	50 g
DSZU 123.62-13	.	0.10	0.013	0.009	0.030	.	CO ₂ :0.09	100 g
NCS DC91019	.	.	0.008	0.021	0.033	.	0.0036	50 g
SRM 696	.	.	.	0.004	.	0.150	0.0014	60 g
IPT 131	.	.	.	0.31	.	.	0.013	70 g
BCS 395	100 g
SRM 69b	.	.	.	0.110	.	0.551	0.0035	60 g
SRM 698	.	.	.	0.38	.	0.143	0.029	60 g
IMS-469	(0.007)	0.16	OrgC:0.11	0.015	.	0.060	.	10 g
IMS PBS-75	(0.013)	.	.	0.042	.	0.061	.	250 g
NCS HC28811	.	0.20	.	0.13	.	.	.	50 g
IMS-470	(0.007)	0.16	OrgC:0.11	0.015	.	0.061	.	10 g
SRM 697	.	.	.	0.41	.	0.0770	0.037	60 g
IMS-471	(0.007)	0.17	OrgC:0.12	0.014	.	0.073	.	10 g
DSZU 123.61-13	.	0.22	0.009	0.023	S:0.045	.	CO ₂ :0.19	100 g
IMS PBS-74	(0.009)	.	.	0.010	.	0.034	.	250 g
IMS PBS-62	.	.	.	0.020	.	0.074	.	250 g
GBAP-17	.	.	0.009	.	.	1.20	.	10 g
SRM 600	.	.	.	0.013	.	0.155	0.003	90 g
GBAP-18	.	.	0.009	.	.	0.21	.	10 g

Number	BaO	C	Ga ₂ O ₃	MnO	S	SO ₃	ZnO	Units
--------	-----	---	--------------------------------	-----	---	-----------------	-----	-------

RM	BAUXITE																	
	Al ₂ O ₃ : Available Alumina										C.Org: Organic Carbon			BXT-04, BXT-06 500 g units			others 100 g	
Number	Al ₂ O ₃	C.Org	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	F ₂ O ₅	SO ₃	SiO ₂	TiO ₂	V ₂ O ₅	ZnO	ZrO ₂	A.Al ₂ O ₃	LOI
ALC-BXT-10	54	(0.08)	(<0.01)	(0.03)	12.4	(<0.01)	.	(0.01)	.	(0.05)	.	2.7	2.01	(0.06)	.	(0.07)	.	28.6
ALC-BXT-09	53.4	(0.2)	(0.01)	0.037	14.5	(0.01)	(0.03)	(0.04)	(0.01)	(0.07)	(0.06)	7.57	2.98	(0.06)	(0.002)	(0.12)	.	20.8
ALC-BXT-13	53.4	0.051	(0.02)	0.016	11.44	(0.01)	(0.01)	(0.01)	(0.01)	(0.02)	(0.09)	4.82	1.54	(0.04)	(0.002)	(0.08)	53.3	28.52
ALC-BXT-08	51.5	(0.082)	(0.02)	(0.049)	9.6	(0.018)	(0.03)	(0.021)	(0.02)	(0.26)	.	3.2	9.5	(0.17)	(0.006)	(0.089)	.	25.6
ALC-BXT-14	51.2	0.162	(0.01)	(0.01)	13.17	(0.01)	(0.01)	(0.02)	(0.01)	(0.062)	(0.11)	5.86	1.11	(0.01)	(0.005)	0.131	50.4	28.35

CRM BERYLLIUM ORE

analysis listed in mass %

Number	BeO	Al ₂ O ₃	CaO	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Units
NCS DC86313	3.02	15.55	0.52	0.0088 (F-)	0.15	0.47	(0.63)	3.28	0.083	0.020	3.63	(0.018)	71.97	0.010	0.86	50 g
NGS DC86302	0.365	14.86	0.584	0.041	(0.18)	0.593	0.59	3.89	0.069	0.036	4.67	0.013	73.99	0.016	0.73	50 g
NGS DC86301	0.060	14.86	0.582	0.019	(0.18)	0.513	0.60	4.10	0.071	0.030	4.79	(0.012)	73.97	0.015	0.68	50 g

continued analysis listed in mg/kg

Number	CeO ₂	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Lu ₂ O ₃	Mo	Nd ₂ O ₃	Pr ₆ O ₁₁	RExOy*	Sc ₂ O ₃	Sm ₂ O ₃	Tb ₄ O ₇	Tm ₂ O ₃	W	Y ₂ O ₃	Yb ₂ O ₃
NCS DC86313	13.1	3.62	1.95	0.11	2.83	0.67	6.08	0.25	3.37	5.96	1.58	63.6	1.91	1.99	0.57	0.29	.	23.0	1.88
NGS DC86302	14.8	4.6	2.2	0.15	3.8	0.87	7.7	0.36	1.2	7.6	2.0	78.6	3.1	2.7	0.80	0.36	5.5	28.9	2.5
NGS DC86301	14.3	4.5	2.1	0.14	3.6	0.82	7.0	0.31	0.41	6.6	1.7	75.6	1.7	2.5	0.80	0.32	1.3	29.2	2.2

* RE_xO_y: Rare Earth Oxide

BORATE ORE

= class, 1=CRM and 2=RM

analysis listed in mass %

BCS: 100 g units

SRM: 60 g units

#	Number	B ₂ O ₃	Al ₂ O ₃	BaO	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	SO ₃	SiO ₂	SrO	TiO ₂	LOI+H ₂ O
1	SRM 1835	18.739	3.474	0.0497	21.622	0.348	1.141	1.261	3.411	0.0333	3.484	1.477	18.408	0.9418	0.1332	25.724
2	BCS 205a	18.46	5.38	.	12.58	.	0.15	1.04	0.62	.	8.53	.	52.0	.	0.04	.

CRM BRUCITE

T = total

50 g units

Number	Al ₂ O ₃	CaO	CO ₂	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂
NCS DC60129	0.053	2.51	8.08	0.49	(25.24)	0.0041	61.43	0.036	0.0066	0.12	2.69
NCS DC60130	0.067	6.18	9.95	0.40	(23.22)	0.0066	56.21	0.033	0.013	0.12	4.47

RM CALCINED BONE

100 g

Number	Al ₂ O ₃	BaO	CaO	F	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	SO ₃	SrO	TiO ₂	LOI
CERAM CCB1	0.05	0.031	53.4	0.13	0.04	(0.12)	0.011	1.14	0.52	40.5	1.28	0.114	0.049	<0.01	2.60 last

CRM CARBONATITE

analysis listed in mass %

FOR ALTERNATES SEE LIMESTONE IN THIS CATALOG

Number	Al ₂ O ₃	CaO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	Ba	Ce	La	Nb	Sr
US EQQ 1	0.37	48.3	2.94	0.16	1.25	0.43	0.04	2.6	3.47	0.15	0.1000	0.1700	0.0750	0.3900	1.2000

CRM CHERT

analysis listed in mass %

20 g units

Number	Al ₂ O ₃	C	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂
JCh-1	0.734	(0.0037)	(0.055)	0.0449	0.0867	0.272	0.356	0.152	0.356	0.221	0.0754	0.0173	0.0305	0.0167	(0.0004)	97.81	0.0316

continued analysis listed in mg/kg

Number	Ag	As	Au	Ba	Be	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu
JCh-1	(0.0041)	0.567	(0.00017)	302	(0.373)	(0.006)	5.21	(14)	15.5	7.04	0.243	15.3	(0.378)	(0.233)	0.0594

Number	F	Gd	Hf	Hg	Ho	La	Li	Lu	Nb	Nd	Ni	Pb	Pd	Pr	Rb	Sc
JCh-1	(134)	(1.7)	0.195	(0.00413)	(0.112)	1.52	(6.48)	0.0344	(1.7)	2.05	8.76	2	(0.0004)	(4.25)	8.61	0.979

Number	Sm	Sr	Ta	Tb	Th	U	V	W	Y	Yb	Zn	Zr
JCh-1	0.359	4.2	(0.182)	(0.0385)	0.735	0.736	10.4	(92.3)	1.81	0.182	7.93	11.5

CRM CHROME MAGNESITE

analysis listed in mass %

BCS, NCS DC25x: 100 g

GCR: 10 g

NCS DC28x: 50 g

NH: 75 g

VS: 125 g

Number	MgO	Cr ₂ O ₃	Al ₂ O ₃	B ₂ O ₃	CaO	Fe	Fe ₂ O ₃	K ₂ O	Li ₂ O	MnO	Na ₂ O	F ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI
BCS 396	64.6	15.6	5.73	0.09	1.12	.	10.9	(0.03)	(0.05)	0.17	(0.06)	.	.	1.37	0.26	.
NH 95	63.93	18.30	3.50	.	1.23	.	6.77	4.05	.	.
BCS 370	61.8	13.4	12.3	.	1.54	.	7.23	0.03	0.03	0.11	0.06	.	.	3.01	0.13	.
BCS 369	53.5	17.2	14.7	.	1.17	.	10.3	0.03	0.03	0.11	0.05	.	.	2.59	0.14	.
VS K5/2	54.8	22.6	4.28	.	1.15	.	8.47	8.64	.	.
NH 96	46.98	22.37	12.92	.	1.59	.	11.90	2.71	.	.
GCR-04	36.29	0.701	0.42	.	0.039	.	12.288	(0.02)	.	0.0422	.	0.0182	0.093	39.22	0.115	10.666
NH 97	21.26	40.00	16.12	.	0.52	.	14.73	5.94	.	.
NCS DC25002	20.59	36.31	10.97	.	0.82	9.71	F: (0.0072)S: (0.017)	.	11.71	.	100g
GCR-01	14.59	44.95	11.31	.	0.052	.	19.63	0.448	.	0.4448	.	(0.0098)	0.048	6.63	0.311	1.286
GCR-05	13.21	38.04	11.53	.	0.039	.	25.49	(0.015)	.	0.811	.	(0.0089)	0.018	7.53	0.258	2.848
GCR-02	12.84	43.97	6.87	.	0.107	.	27.13	(0.03)	.	0.716	.	(0.0071)	0.019	5.83	0.317	1.883
GCR-06	9.01	47.92	8.72	.	0.087	.	28.8	0.0198	.	0.716	.	(0.0096)	0.033	3.21	0.343	0.795

CRM CHROMITE

Number	Origin	Cr	Fe	MgO	Ti	Units
FGS 30	Philippines	23.95	11.21	(16.62)	0.14	55 g

CHROMIUM ORE

= class, where 1 = CRM and 2 = RM

analysis listed in mass % except * which is mg/kg

#	Number	Cr ₂ O ₃	Al ₂ O ₃	CaO	MgO	Fe	FeO	Fe ₂ O ₃	Mn	MnO	Mn ₃ O ₄	P	F ₂ O ₅	S	SO ₃	SiO ₂	Ti	TiO ₂
1	NCS HC26617	96.19	0.054	0.002	.	0.26	.	.
1	NCS DC73013	57.80	10.53	(0.13)	16.45	.	(8.3)	13.70T	0.097	.	.	(0.0012)	.	(0.005)	.	1.10	0.122	.
1	USZ 36-2002	54.37	8.24	0.24	16.09	.	.	14.73T	.	0.15	.	.	0.02	.	0.07	4.73	.	0.11
1	NM 181	52.52	10.64	0.11	12.13	.	14.90	.	.	0.32	.	0.005	.	0.004	.	4.43	.	0.16
1	VS R27/1	50.8	8.08	0.131	19.7	9.45	11.2	0.0019	.	0.019	.	7.10	.	.
1	VS R14/5	47.0	7.2	0.13	21.6	9.32	10.8	0.0017	.	0.037	.	8.79	.	.
1	SARM 146	46.91	14.54	0.10	10.62	.	25.58	.	.	0.22	0.616	.	0.57
1	NCS DC28130	46.74	14.53	0.053	9.79	20.34	.	0.156	.	.	0.0027	.	0.003	.	.	0.79	0.373	.
1	NCS DC73012	46.56	11.60	0.46	17.92	.	(12.0)	15.34T	0.135	.	.	(0.0013)	.	0.076	.	5.06	0.070	.
1	NM 182	46.06	10.34	0.10	9.74	.	19.33	.	.	0.38	.	0.004	.	0.004	.	7.47	.	0.22
1	BCS 308/1	44.91	15.10	0.65	9.15	.	26.58	.	.	0.230	1.194	.	0.74
1	NCS DC28131	45.10	13.70	0.18	10.37	19.66	.	.	0.150	.	.	0.0033	.	0.0029	.	2.93	0.344	.
1	SARM 131	41.83	14.60	(0.24)	9.15	.	.	30.7	.	0.243	3.13	.	0.944
1	NCS DC28133	40.20	15.97	0.46	13.41	16.74	.	.	0.142	.	.	0.0037	.	0.017	.	4.73	0.294	.
1	NCS DC28132	36.50	16.22	0.69	15.32	14.83	.	.	0.133	.	.	0.0028	.	0.022	.	7.70	0.244	.
1	NCS DC73011	34.44	11.37	0.32	23.32	.	(8.5)	11.84T	0.090	.	.	0.0020	.	0.024	.	12.24	0.100	.
1	NCS DC28129	33.00	13.94	1.00	17.27	12.90	.	.	0.180	.	.	0.0030	.	0.021	.	12.19	0.136	.
1	NM 183	32.69	12.14	0.16	7.66	.	22.43	.	.	0.76	.	0.005	.	0.004	.	13.33	.	0.31
1	NM 184	28.54	7.12	0.16	5.91	.	22.21	.	.	0.33	.	0.005	.	0.004	.	27.28	.	0.17
1	NCS DC28128	27.55	18.94	1.27	20.48	9.76	.	.	0.114	.	.	0.0029	.	0.035	.	12.55	0.145	.
2	CERAM AN100	26.60	24.7	1.16	22.38	.	.	12.88	.	.	0.13	11.1	.	0.21
1	NCS DC73010	17.59	11.86	0.44	28.12	.	(8.68)	10.51T	0.088	.	.	0.0031	.	0.037	.	20.30	0.085	.
1	FLX CRM111	11.48	4.66	2.07	70.20	.	.	9.54	.	.	0.370	.	0.088	.	(0.13)	1.40	.	0.160

continued

Number	Au*	C	CO ₂	Co	H ₂ O-	H ₂ O+	HfO ₂	K ₂ O	Na ₂ O	Ni	NiO	V	WO ₃	Zn	ZrO ₂	LOI	Units
NCS HC26617	.	0.006	soluble Cr: 1.34%	20 g
NCS DC73013	.	.	(0.14) 0.016	.	(0.59)	.	.	(0.004)	(0.016)	0.16	.	0.048	50 g
USZ 36-2002	0.03	.	0.47 0.01	0.11	0.09	.	0.04	.	0.023	.	1.07	200 g
NM 181	0.17	.	V ₂ O ₅ :0.10	.	.	.	2.60	100 g
VS R27/1	100 g
VS R14/5	.	(0.113)	0.044	100 g
SARM 146	V ₂ O ₅ :0.32	100 g
NCS DC28130	.	.	0.025	.	.	.	0.014	.	0.092	.	.	0.215	.	0.071	.	.	50 g
NCS DC73012	.	.	(1.2) 0.016	2.5	.	.	(0.010)	0.018	0.134	.	.	0.064	50 g
NM 182	0.25	.	.	V ₂ O ₅ :0.10	.	.	.	4.45	100 g
BCS 308/1	100 g
NCS DC28131	.	.	0.025	.	.	.	0.015	.	0.094	.	.	0.207	.	0.065	.	.	50 g
SARM 131	V ₂ O ₅ :0.414	100 g
NCS DC28133	.	.	0.022	.	.	.	0.023	.	0.121	.	.	0.162	.	0.065	.	.	50 g
NCS DC28132	.	.	0.022	.	.	.	0.033	.	0.134	.	.	0.143	.	0.058	.	.	50 g
NCS DC73011	.	.	(0.46) 0.014	.	(6.4)	.	0.026	0.073	0.175	.	.	0.044	50 g
NCS DC28129	.	.	0.027	.	.	.	0.035	.	0.162	.	.	0.089	.	0.102	.	.	50 g
NM 183	0.32	.	.	V ₂ O ₅ :0.10	.	.	.	6.14	100 g
NM 184	0.37	.	.	V ₂ O ₅ :0.08	.	.	.	4.63	100 g
NCS DC28128	.	.	0.016	.	.	.	0.043	.	0.169	.	.	0.077	.	0.049	.	.	50 g
CERAM AN100	.	.	CuO:0.02	.	.	.	0.01	0.04	ZnO:0.04	.	(5.03)	.	25 or 100 g
NCS DC73010	.	.	(0.6) 0.0124	.	(10.7)	.	0.046	(0.13)	0.188	.	.	0.043	50 g
FLX CRM111	.	.	Co3O4: 0.012	.	.	<0.01	0.010	<0.1	.	0.031	.	.	<0.02	.	0.057	(0.58)	80 g

CRM CLAY

analysis listed in mass %

Number	Al	B	Ba	Ca	Ce	Co	Cr	Fe	K	Li	Mg	Mn	Na	P	Si	Sr
SRM 97b	20.76	.	(0.018)	0.0249	.	(0.00038)	0.0227	0.831	0.513	0.0550	0.113	0.0047	0.0492	(0.02)	19.81	0.0084
SRM 98b	14.30	.	(0.07)	0.0759	.	(0.00163)	0.0119	1.18	2.81	0.0215	0.358	0.0116	0.1496	(0.03)	26.65	0.0189
SRM 679	11.01	.	0.0432	0.1628	(0.0105)	(0.0026)	0.01097	9.05	2.433	0.00717	0.7552	(0.1730)	0.1304	(0.075)	24.34	0.00734

continued analysis listed in mass %

analysis listed in mg/kg

Number	Ti	Zn	Zr	LOI	Cs	Eu	Hf	Rb	Sb	Sc	Th	Units
SRM 97b	1.43	(0.0087)	(0.05)	(13.3)	(3.4)	(0.84)	(13)	(33)	(2.2)	(22)	(36)	60 g powder
SRM 98b	0.809	(0.0110)	(0.022)	(7.5)	(16.5)	(1.3)	(7.2)	(180)	(1.6)	(22)	(21)	60 g powder
SRM 679	0.577	(0.0150)	.	.	(9.6)	(1.9)	(4.6)	(190)	.	(22.5)	(14)	75 g powder

CLAYS and FIRECLAYS

= class, where 1 = CRM and 2 = RM

analysis listed in mass %

#	Number	SiO ₂	Al ₂ O ₃	CaO	Cl-	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	TiO ₂	LOI	Units	Other
1	NCS DC72006	72.73	14.24	0.89	.	1.97	0.60	2.57	0.00	1.90	0.026	0.29	0.13	4.65	1 kg	
1	NH 138	68.90	26.01	0.23	.	1.47	0.98	0.22	.	0.10	.	.	0.92	.	75 g	last
1	NCS DC62108d	68.59	14.12	1.21	.	5.29	2.33	1.58	.	1.24	.	0.03	0.76	4.22	20 g	
1	NCS DC72005	67.63	17.06	0.99	.	3.36	1.37	1.99	0.023	2.40	0.036	0.024	0.24	4.72	1 kg	
1	GBW 03103	66.64	13.28	3.23	0.011	4.64	2.50	1.84	0.088	1.81	0.106	0.027	.	5.10	50 g	CO ₂ : 1.66
1	VS K11	62.2	16.8	1.2	.	(6.3)	.	2.01	0.064	.	.	S:0.05	0.98	.	50 g	
1	NH 137	61.46	32.43	0.28	.	1.63	1.31	0.28	.	0.126	.	.	1.13	.	75 g	
1	NCS DC72008	60.02	8.86	1.27	.	4.48	0.87	11.55	0.068	0.071	0.49	.	0.60	11.59	1 kg	CO ₂ : 0.68
1	NCS DC72003	59.71	18.11	4.34	.	2.64	0.60	3.51	0.12	0.37	0.11	0.060	0.34	10.08	1 kg	
1	NCS DC72007	56.29	10.20	6.00	.	4.41	1.16	7.11	0.31	0.16	0.16	.	0.62	13.32	1 kg	CO ₂ : 5.17
1	NCS DC72004	56.21	23.35	0.95	.	4.60	0.31	3.04	0.035	0.11	0.054	0.025	1.00	10.25	1 kg	
1	GBW 03115	55.90	28.57	0.70	.	0.87	1.54	0.30	.	1.74	.	.	1.21	8.72	50 g	
1	GBW 03102a	53.67	31.32	1.80	0.0029	0.33	1.15	0.083	0.020	2.55	0.053	0.023	0.030	8.81	50 g	CO ₂ : (0.051)
2	IAG DBC-1	51.98	31.82	(0.20)	.	0.94T	2.64	0.36	.	(0.39)	0.071	.	1.123	(10.1)	35 g	more data on certificate
1	IPT 42	51.9	32.2	0.05	.	1.09	0.47	0.19	.	0.02	0.07	.	0.96	12.9	50 g	
1	IPT 32	51.8	28.5	0.17	.	3.46	0.80	0.39	.	0.16	0.13	.	1.49	12.6	50 g	
1	BCS 348	51.13	31.59	0.173	.	1.04	2.23	0.305	.	0.344	0.071	.	1.08	11.75	100 g	
1	GBW 03101a	49.98	26.27	0.13	0.0041	10.55	0.79	0.46	0.052	0.060	0.14	0.49	0.70	10.62	50 g	CO ₂ : (0.041)
2	FLX 134	F: 0.0678	Fluorine in Ball Clay, single element												30 g	

CRM CLAY - SYNTHETIC MULLITE

80 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P	SiO ₂	TiO ₂
NCS HC14809	72.39	0.19	0.93	0.24	0.42	0.16	0.043	21.81	3.64
NCS HC14808	57.47	0.15	0.46	1.69	0.14	0.46	0.022	37.41	1.45
NCS HC14807	43.62	0.23	1.14	1.62	0.21	0.46	0.062	51.43	0.65

CRM COPPER ORE WITH EXTENSIVE ANALYSIS - CONTINUED ON THE NEXT PAGE

analysis listed in mass % except * which is mg/kg # = provisional analysis

Number	Cu	Ag*	Au*	C	F	Fe	Fe ₂ O ₃	Mo	Ni	Pb	Pd*	Pt*	S	Zn	LOI
VS 2891-84	40.4	707.7	.	.	.	(5.78)	.	.	.	2.25	.	.	(15.98)	2.89	.
CGL 203	31.80	(66)	.	.	.	(21.0)	.	0.1399	.	0.01366	.	.	(33.94)	0.1526	.
CAN CCU-1F	23.33	157.0	19.08	(0.06)	(0.0080)	29.50	.	(0.00116)	(0.00192)	0.2095	.	.	34.82	4.085	(19.15)
CGL 210	22.24	47.50	19.92	.	0.0451	28.05	.	0.2219	.	0.0744	.	.	32.77	0.2815	.
Jcu-1 #	3.73	.	.	(3.06T)	.	.	17.5T	.	(0.0425)	(0.0004)	.	.	(7.00)	0.0679	(15.37)
GBW 07233	1.15	3.9	.	.	0.079	.	55.58	0.00014	0.00096	0.00091	.	.	0.72	0.059	.
CETEM CBPA-1	0.98	.	(0.17)	(0.16 org)	(0.0708)	.	16.5	(0.0010)	0.0276	(0.0033)	.	.	(0.16)	0.0126	(3.8)
SRM 330a	0.845	(1.06)	.	(0.00045)	0.002895	(0.0027)	.	.	.	0.00949	.
CGL 103	0.8080	2.05	.	.	.	2.75	.	0.0160	(0.000950)	(0.00727)	.	.	2.12	0.0096	(4.27)
OREAS 503e	0.531	1.52	0.709	(0.115)	.	4.11	(5.98)	0.0343	0.00476	0.0078	.	.	0.875	0.0261	(1.70)
CAN HV-2a	0.3808	1.448	.	(0.4)	.	2.044	.	0.01254	0.000647	0.00069	.	.	0.344	0.00565	(3.01)
GBW 07234	0.19	0.7	.	.	0.080	.	12.25	0.00024	0.00056	0.00130	.	.	0.14	0.013	.
USZ 4-85	0.115	(1.1)	3.9T	0.007	(0.00165)	(0.00510)	.	.	2.03	(0.00680)	(4.26)

continued analysis listed in mass %

Number	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	SiO ₂	Ti	TiO ₂
VS 2891-84	(21.74)	.	.
CGL 203	(6)	.	.
CAN CCU-1F	0.1203	.	0.140	.	(0.0161)	.	0.383	.	0.00829	.	(0.02)	.	(0.0013)	.	2.015	(0.00528)	.
CGL 210	1.143	.	(0.16)	.	.	(0.25)	.	(0.02)	(0.01)	.	(6.77)	(0.0700)	.
Jcu-1 #	.	0.29	.	23.5	.	0.015	.	2.13	.	0.59	.	0.052	.	(<0.005)	(28.68)	.	0.013
GBW 07233	.	1.73	.	9.61	.	0.071	.	3.91	.	0.60	.	0.044	.	.	9.27	.	0.079
CETEM CBPA-1	.	10.1	.	2.97	.	1.85	.	3.29	0.058	.	.	1.42	.	1.00	(56.4)	(0.35)	.
SRM 330a	7.053	.	0.323	.	5.47	.	0.868	.	.	.	0.657	.	(0.0326)	Si: 33.4	33.4	(0.1223)	.
CGL 103	.	16.19	.	0.285	.	3.71	.	0.69	.	(0.0160)	.	1.48	.	0.139	67.07	.	0.463
OREAS 503e	7.55	(14.46)	1.95	(2.71)	2.95	(3.54)	0.917	(1.60)	0.043	(0.055)	2.01	(2.79)	0.088	(0.200)	(65.22)	0.351	(0.600)
CAN HV-2a	7.96	.	1.891	.	2.31	.	0.329	.	0.0545	.	2.335	.	0.0427	.	Si: 31.34	.	0.128
GBW 07234	.	15.18	.	4.95	.	2.71	.	1.30	.	0.12	.	3.21	.	.	53.36	.	0.50
USZ 4-85	(3.38)	(1.74)	.	(0.15)	.	.	.

continued analysis listed in mg/kg

Number	As	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf
VS 2891-84	290
CGL 203	(9.31)	.	(86.87)	(42.97)
CAN CCU-1F	821	(7)	.	(0.649)	110.2	(0.80)	304.2	(7)	(3.39)	.	(0.8)	.
CGL 210	1197	(55.5)	.	.	(16.9)	.	(50.5)	(35.1)	.	.	(0.47)	(0.39)
Jcu-1 #	(173)	(3.5)	.	.	(3.6)	.	(324)	(10)
GBW 07233	4.2	.	.	1.5	0.42	13.2	.	(7)	.	1.1	0.78	0.28	22.6	1.1	0.89	.
CETEM CBPA-1	(9)	(478)	.	.	(3)	(427)	78	26	(22.2)	.	.	.
SRM 330a	.	1560	.	.	3.391	22.32	4.542	77.0	17.4	.	.	.
CGL 103	167	958	(1.04)	.	(0.57)	(40.35)	12	(18)	(2.27)	.	.	.	(18.92)	.	.	.
OREAS 503e	28.8	926	2.34	1.86	0.75	67	16.3	45.9	9.33	3.50	1.44	1.29	19.4	5.50	0.18	1.83
CAN HV-2a	12.1	869	(1.02)	(1.58)	(0.2)	19.1	3.40	100	2.70	1.126	0.646	(0.502)	19.56	1.40	.	(2)
GBW 07234	1.5	(800)	.	0.43	0.14	72.6	.	(10)	(10)	2.4	1.3	1.3	22.6	3.6	0.93	.
USZ 4-85	(47)	.	(4.5)	(21.7)	.	.	(12)	(22)

Number	Hg	Ho	In	La	Li	Lu	Nb	Nd	Pr	Rb	Re	Sb	Sc	Se	Sm	Sn
VS 2891-84	28.2
CGL 203	(400)	.	(77)	.	.
CAN CCU-1F	12.19	.	(5.71)	.	(0.4)	(0.3)	(0.005)	85.5	(0.5)	(211)	.	(9)
CGL 210	.	(0.19)	.	(5.11)	(128)	.	.	(1.19)	.
Jcu-1 #	(2.9)	(1.9)	.	(3.8)
GBW 07233	.	0.26	1.4	7.5	(9)	0.16	.	4.7	1.4	.	.	0.36	1.8	5.1	1	11.1
CETEM CBPA-1	.	.	.	(267)	.	(10)	(143)	.	.	(101)	.	.	(16)	.	(20)	(7)
SRM 330a	22.19	.	(5.7)	5.693	.	.	.
CGL 103	.	.	.	(19.38)	(83.76)	.	23
OREAS 503e	.	0.58	0.38	33.3	46.3	0.19	11.0	31.0	7.83	146	0.016	236	9.66	6.03	6.21	4.51
CAN HV-2a	.	(0.2)	.	9.1	(11)	(0.109)	(2)	8.77	(2.32)	48.3	(0.1)	0.689	(3)	(0.7)	1.69	(1.2)
GBW 07234	.	0.48	0.25	40.3	(15)	0.2	.	29.4	8.1	(94)	.	0.23	5.4	0.89	5.1	3.8
USZ 4-85	(80)	.	.	.	(5.4)	.	.

CRM COPPER ORE WITH EXTENSIVE ANALYSIS - CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mg/kg		# = provisional analysis											OREAS samples list multiple methods, more information upon request			
Number	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zr	Units	Other	
VS 2891-84	50 g		
CGL 203	100 or 250 g		
CAN CCU-1F	(2)	49.9	.	.	.	1.51	.	(0.4)	(3)	(1.12)	(0.8)	.	.	200 g	H ₂ O%:(0.96)	
CGL 210	(0.29)	200 g		
JCu-1 #	(75)	(9)	100 g	H ₂ O%:(0.54-, 1.00+)	
GBW 07233	.	.	0.21	0.62	0.9	0.06	0.11	.	.	4.1	7.3	0.28	.	50 g		
CETEM CBPA-1	(67)	(5)	.	.	(25)	.	.	(41)	(168)	.	(69)	.	(149)	135 g		
SRM 330a	218.1	.	.	.	(7.6)	.	.	.	(43)	.	20.01	.	.	80.5	90 g	
CGL 103	181	(0.96)	(59.43)	(13.55)	.	.	.	(102.76)	100 g	
OREAS 503e	229	0.97	0.69	0.85	12.3	0.82	0.20	3.47	79	10.6	14.9	1.18	57	10g 60g or 1kg	SO ₃ :(2.18)	
CAN HV-2a	472	(0.2)	(0.19)	.	1.28	(0.1)	(0.10)	1.08	(52.2)	(7.89)	(5.96)	(0.680)	(65.8)	200 g	H ₂ O%:(0.3)	
GBW 07234	.	.	0.48	0.13	8.8	0.36	0.18	.	3.9	11.8	1.2	.	.	50 g		
USZ 4-85	.	.	.	(6.8)	(16)	.	.	(149)	100 g		

CRM COPPER ORE

analysis listed in mass %		F = Sodium Peroxide Fusion ICP											A = Four Fcid Digestion ICP-OES/MS values		10 g
Number	Cu	Ag	Al ₂ O ₃	As	CaO	Cd	Co	Fe	MgO	Pb	S	Sb	SiO ₂	Zn	
OREAS 113 4	13.5	0.00226	.	0.0234	.	0.00155	0.0766	28.2	.	0.0230	.	0.0008	.	0.4178	
OREAS 113 F	13.3	(0.0025)	.	0.0238	.	(0.0016)	0.0754	28.0	.	0.0248	.	0.00076	.	0.4158	
OREAS 166 4	8.82	0.00108	1.38	.	0.98	.	0.1970	11.38	1.67	0.0140	11.6	.	.	0.0037	
OREAS 166 F	8.75	0.0012	1.34	.	0.98	.	0.2077	11.45	1.67	0.0128	11.29	.	61.4	0.0037	
OREAS 112 F	5.13	0.0017	.	0.0240	.	0.0015	0.0547	33.3	.	0.0349	.	0.0017	.	0.4302	
OREAS 112 4	5.10	0.00132	.	0.0222	.	0.00146	0.0551	34.1	.	0.0360	.	0.0016	.	0.4351	
OREAS 165 F	3.21	0.00031	2.61	.	0.11	.	0.2485	8.86	3.48	0.0434	8.28	.	72.0	0.0044	
OREAS 165 4	3.20	0.000302	2.59	.	0.081	.	0.2445	8.86	3.53	0.0443	8.5	.	.	0.0037	
OREAS 111b 4	2.47	0.00101	.	0.0220	.	0.00143	0.0490	36.1	.	0.0393	.	0.0021	.	0.4334	last
OREAS 111b F	2.44	<0.0020	.	0.0212	.	0.00148	0.0488	35.5	.	0.0397	.	0.0019	.	0.4370	last
OREAS 164 4	2.25	0.000294	2.07	.	0.393	.	0.0168	6.80	3.07	0.0214	6.2	.	.	0.0045	
OREAS 164 F	2.22	<0.0005	2.05	.	0.401	.	0.0167	6.88	3.07	0.0199	5.98	.	77.9	0.0047	
OREAS 163 4	1.76	0.00043	3.24	.	0.860	.	0.0230	11.07	5.42	0.0492	10.4	.	.	0.0108	
OREAS 163 F	1.71	0.0005	3.16	.	0.92	.	0.0230	11.1	5.34	0.0461	9.98	.	.	0.0102	
OREAS 162 4	0.772	0.00035	1.70	.	13.2	.	0.0631	8.57	9.17	0.0340	4.38	.	.	0.0026	
OREAS 162 F	0.761	0.000358	1.64	.	13.1	.	0.0660	8.63	9.04	0.0320	4.40	.	.	0.002755	
Number	Cu	Ag	Al ₂ O ₃	As	CaO	Cd	Co	Fe	MgO	Pb	S	Sb	SiO ₂	Zn	

CRM COPPER ORE

analysis listed in mass % except * which is mg/kg		50 g units											
Number	Cu	Al ₂ O ₃	As	CaO	F	Fe	Pb	S	SiO ₂	Sn	Zn	Ag	Au*
NCS DC28188	31.05	0.72	0.024	4.54	0.012	22.19	0.15	24.52	8.17	.	0.075	0.0330	9
NCS DC11058	26.96	0.170	0.71	0.073	0.050	27.72	1.53	33.29	0.55	1.02	5.77	0.144	0.65
NCS DC28192	24.40	0.71	0.013	2.1	0.012	28.46	0.097	31.22	5.28	.	0.20	0.0181	12
NCS DC11059	23.92	1.12	1.56	0.37	0.36	25.84	1.35	30.09	6.28	0.90	5.05	0.126	0.61
NCS DC28187	22.50	0.27	0.007	0.56	0.012	31.37	0.011	33.81	3.72	.	0.45	0.0021	15
NCS DC11060	20.67	2.06	2.36	0.63	0.63	23.82	1.21	26.54	11.27	0.78	4.40	0.111	0.58
NCS DC28191	20.12	0.49	0.007	1.41	0.028	26.02	0.012	24.62	12.53	.	0.50	0.0017	10
NCS DC11061	18.63	2.61	2.79	0.81	0.80	22.65	1.04	24.23	14.60	0.69	3.89	0.095	0.51
NCS DC28190	16.92	1.32	0.011	0.38	0.012	34.12	0.13	38.00	3.73	.	0.034	0.0186	10
NCS DC11062	14.37	3.90	3.89	1.20	1.17	20.63	0.83	20.73	22.03	0.56	3.17	0.076	0.49
NCS DC11063	12.16	4.43	4.43	1.36	1.36	19.23	0.70	18.30	25.58	0.47	2.73	0.064	0.43
NCS DC28189	9.88	5.11	0.018	1.93	0.044	25.18	0.26	24.91	14.03	.	0.069	0.0141	9
NCS DC11064	9.59	5.40	5.55	1.66	1.57	18.65	0.57	16.44	30.35	0.37	2.24	0.051	0.42

continued analysis

Number	Bi	Cd	Co	Ge*	Hg*	K ₂ O	MgO	Mn	Na ₂ O	Ni	Sb	Se
NCS DC28188	0.11	0.001	0.012	.	(1.4)	0.081	1.04	0.027	0.054	0.008	0.003	.
NCS DC11058	0.072	0.033	0.0006	(1)	(0.6)	0.045	0.031	0.0099	0.011	.	0.12	0.0014
NCS DC28192	0.052	0.0005	0.096	.	(1.3)	0.13	1.27	0.032	0.036	0.074	0.0015	.
NCS DC11059	0.072	0.029	0.00162	(1)	(0.4)	0.42	0.187	0.0137	0.068	.	0.108	0.0012
NCS DC28187	0.0004	0.0003	0.24	.	(0.3)	0.015	2.05	0.013	0.008	0.19	0.0006	.
NCS DC11060	0.056	0.025	0.0024	(1)	(0.4)	0.76	0.327	0.0179	0.13	.	0.096	0.0012
NCS DC28191	0.0003	0.0002	0.14	.	(0.3)	0.037	6.40	0.023	0.025	0.13	(0.0003)	.
NCS DC11061	0.049	0.023	0.0030	(0.8)	0.32	0.95	0.427	0.021	0.16	.	0.084	0.0011
NCS DC28190	0.061	0.0002	0.013	.	(0.1)	0.38	0.46	0.068	0.045	0.009	0.0005	.
NCS DC11062	0.041	0.018	0.0042	(0.8)	(0.3)	1.43	0.64	0.027	0.24	.	0.070	0.0010
NCS DC11063	0.037	0.016	0.0050	(0.9)	(0.3)	1.62	0.73	0.029	0.27	.	0.061	(0.0007)
NCS DC28189	0.038	0.0005	0.008	.	(0.2)	1.44	0.77	0.14	0.19	0.006	0.003	.
NCS DC11064	0.030	0.014	0.0063	(1.0)	(0.4)	1.97	0.88	0.035	0.34	.	0.049	(0.0007)

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

CRM COPPER ORE - EXTENSIVE ANALYSIS NOT SHOWN

analysis listed in mass % except * which is mg/kg

10g, 60g, or 1 kg

Number	Cu	Ag*	Au*	Bi	Co	Ni	Pb	Rb	Se	Sn	Zn	Zr
OREAS 98 4	14.8	45.1	.	0.00972	0.0121	(0.00353)	0.0345	(0.00817)	0.0158	0.0206	0.1355	(0.00667)
OREAS 98 A	14.7	42.8	.	0.00928	0.0111	.	0.0343	.	0.0143	0.0171	0.1302	.
OREAS 935 I	12.43	43.73	.	0.0679	0.0085	(0.0156)	0.0233	(0.0089)	0.0105	0.0119	0.0721	(0.0074)
OREAS 935 4	12.55	43.87	(<0.1)	0.0709	0.0077	0.00297	0.0225	(0.0080)	0.0088	0.0108	0.0692	0.00474
OREAS 935 A	12.48	43.67	(0.04)	0.0680	0.0077	0.00262	0.0222	(0.00136)	0.0086	0.0096	0.0666	(0.00133)
OREAS 935 F	12.54	.	.	.	<0.0100	(0.00158)	(0.0255)	.	.	(0.0138)	0.0688	(0.0050)
OREAS 934 I	9.50	34.67	.	0.0517	0.0075	(0.00320)	0.0262	(0.0106)	0.0096	0.0095	0.0744	(0.0093)
OREAS 934 4	9.59	36.46	(<0.1)	0.0527	0.0071	0.00282	0.0240	(0.0097)	0.0085	0.0083	0.0724	0.0058
OREAS 934 A	9.58	34.40	(0.022)	0.0515	0.0067	0.00257	0.0242	(0.00145)	0.0080	0.0076	0.0692	(0.00162)
OREAS 934 F	9.51	.	.	.	<0.0100	(0.000917)	0.0242	.	.	(0.0116)	0.0718	(0.0073)
OREAS 933 I	8.34	29.32	.	0.0466	0.0063	(0.0108)	0.0197	(0.0103)	0.0079	0.0086	0.0617	(0.0101)
OREAS 933 4	8.37	31.05	(<0.1)	0.0451	0.0060	0.00281	0.0189	(0.0095)	0.0068	0.0073	0.0602	0.0063
OREAS 933 A	8.27	29.62	(0.027)	0.0449	0.0061	0.00281	0.0187	(0.00126)	0.0066	0.0066	0.0596	(0.00164)
OREAS 933 F	8.38	.	.	.	<0.0100	(0.000800)	0.0210	.	.	(0.0106)	0.0606	(0.0090)
OREAS 97 4	6.31	19.6	.	0.00401	0.00629	(0.00370)	0.0147	(0.0126)	0.00714	0.00957	0.0646	(0.00965)
OREAS 97 A	6.28	19.5	.	0.00403	0.00625	.	0.0142	.	0.00673	0.00838	0.0635	.
OREAS 932 I	6.17	23.00	.	0.0337	0.0062	(0.00303)	0.0195	(0.0122)	0.0073	0.0067	0.0590	(0.0114)
OREAS 932 4	6.13	22.41	(<0.1)	0.0324	0.0060	0.00274	0.0184	(0.0112)	0.0067	0.0058	0.0591	0.0073
OREAS 932 A	6.11	21.96	(0.012)	0.0322	0.0061	0.00282	0.0182	(0.00162)	0.0063	0.0051	0.0579	(0.00191)
OREAS 932 F	6.19	.	.	.	<0.0100	(0.00133)	0.0200	.	.	(0.0092)	0.0599	(0.0093)
OREAS 96 4	3.93	11.5	.	0.00263	0.00499	(0.00393)	0.0101	(0.0141)	0.00407	0.00656	0.0457	(0.0109) last
OREAS 96 A	3.91	11.5	.	0.00279	0.00492	.	0.0100	.	0.00410	0.00528	0.0448	.
OREAS 931 I	3.83	13.62	.	0.0205	0.00466	(0.00362)	0.0155	(0.0134)	0.0050	<0.0060	0.0490	(0.0132)
OREAS 931 4	3.82	14.04	(<0.1)	0.0204	0.00469	0.00288	0.0147	(0.0128)	0.00435	0.00421	0.0480	(0.0085)
OREAS 931 A	3.81	14.18	(0.006)	0.0206	0.00453	0.00287	0.0146	(0.00153)	0.00422	0.00330	0.0472	(0.00199)
OREAS 931 F	3.82	.	.	.	<0.0050	(0.0010)	(0.0159)	.	.	(0.0064)	0.0495	(0.0097)
OREAS 930 I	2.51	8.63	.	0.0138	0.00391	(<0.0050)	<0.0150	(0.0150)	0.00336	0.00351	0.0499	(0.0147)
OREAS 930 4	2.52	9.00	(<0.1)	0.0136	0.00374	0.00311	0.0141	(0.0136)	0.00301	0.00311	0.0492	0.0089
OREAS 930 A	2.51	9.13	(0.004)	0.0139	0.00364	0.00306	0.0142	(0.00181)	0.00286	0.00234	0.0488	(0.00220)
OREAS 930 F	2.51	.	.	.	<0.0100	(0.00217)	<0.0160	.	.	(0.0059)	0.0504	(0.0112)
OREAS 929 I	2.00	<8	.	0.0114	0.00362	(<0.0020)	0.0116	(0.0141)	0.00243	0.00311	0.0492	(0.0141)
OREAS 929 4	2.00	7.18	(<0.1)	0.0111	0.00336	0.00307	0.0130	(0.0129)	0.00241	0.00291	0.0477	0.0088
OREAS 929 A	2.02	7.03	(0.004)	0.0114	0.00336	0.00297	0.0131	(0.00175)	0.00240	0.00201	0.0468	(0.00211)
OREAS 929 F	2.02	.	.	.	<0.0100	(0.00275)	0.0143	.	.	(0.00458)	0.0486	(0.0127)
Number	Cu	Ag*	Au*	Bi	Co	Ni	Pb	Rb	Se	Sn	Zn	Zr
OREAS 928 I	1.52	<8	.	0.0083	0.00335	(0.00376)	0.0112	(0.0127)	<0.0020	0.00278	0.0432	(0.0141)
OREAS 928 4	1.53	5.39	(<0.100)	0.0079	0.00313	0.00296	0.0122	(0.0116)	0.00188	0.00262	0.0436	(0.0094)
OREAS 928 A	1.52	5.11	(0.006)	0.0080	0.00306	0.00281	0.0122	(0.00148)	0.00179	0.00157	0.0429	(0.00199)
OREAS 928 F	1.52	.	.	.	<0.0050	(0.00208)	(0.0133)	.	.	(0.00300)	0.0435	(0.0108)
OREAS 504b 4	1.11	3.07	1.61	0.000492	0.00209	0.00345	0.00262	0.0106	0.00124	0.00114	0.0108	0.0060
OREAS 504b A	1.10	2.98	1.56	0.000513	0.00187	0.00300	0.00201	0.0051	0.00116	0.00104	0.0096	0.0042
OREAS 927 I	1.09	.	.	0.0062	0.00310	0.00302	0.0214	0.0122	.	0.00238	0.0750	.
OREAS 927 4	1.08	4.08	.	0.0057	0.00287	0.00297	0.0209	0.0119	0.00157	0.00207	0.0716	0.0097
OREAS 927 A	1.06	3.90	<0.010	0.0059	0.00286	0.00280	0.0203	0.00147	0.00153	0.00122	0.0717	0.00201
OREAS 903 4 **	0.652	0.432	(<0.050)	0.00089	0.0131	0.0054	0.00113	0.0137	0.000606	0.000263	0.00243	0.0152
OREAS 903 A	0.671	0.349	(<0.005)	0.00088	0.0131	0.00487	0.000895	0.00126	0.000534	(0.00004)	0.00213	0.00182
OREAS 925 I	0.621	.	.	0.00336	0.00254	0.00355	0.0115	0.0166	.	0.00179	0.0459	.
OREAS 925 4	0.615	2.36	.	0.00313	0.00246	0.00348	0.0110	0.0163	0.000907	0.00149	0.0446	0.0106
OREAS 925 A	0.629	2.41	<0.005	0.00324	0.00238	0.00317	0.0111	0.00189	0.000891	0.000777	0.0437	0.00218
OREAS 503b	0.531	1.54	0.695	0.000261	0.00171	0.00387	0.00243	0.0163	0.000661	0.000752	0.0092	0.0071 last
OREAS 924 I	0.520	.	.	0.00293	0.00244	0.00385	0.0096	0.0173	.	0.00167	0.0389	.
OREAS 924 4	0.512	1.99	.	0.00273	0.00234	0.00360	0.0092	0.0172	0.000786	0.00136	0.0380	0.0109
OREAS 924 A	0.516	1.92	<0.005	0.00257	0.00227	0.00326	0.0092	0.00203	0.000732	0.000672	0.0370	0.00222
OREAS 923 I	0.4328	.	.	0.00212	0.00239	0.00407	0.0086	0.0169	.	0.00161	0.0358	.
OREAS 923 4	0.4230	1.60	.	0.00214	0.00231	0.00358	0.0083	0.0166	0.000654	0.00133	0.0345	0.0116
OREAS 923 A	0.4248	1.62	<0.005	0.00218	0.00222	0.00327	0.0081	0.00196	0.000599	0.000599	0.0335	0.00225
OREAS 501c	0.276	0.461	0.221	0.000069	0.00151	0.0060	0.00215	0.0196	0.000207	0.000338	0.0081	0.0081
OREAS 922 I	0.2215	.	.	0.00108	0.00209	0.00434	0.0064	0.0167	.	0.00100	0.0277	.
OREAS 922 4	0.2122	0.888	.	0.00101	0.00204	0.00379	0.0059	0.0164	0.000376	0.000995	0.0267	0.0127
OREAS 922 A	0.2176	0.851	<0.005	0.00103	0.00194	0.00343	0.0060	0.00227	0.000344	0.000383	0.0256	0.00223
OREAS 921 I	0.0293	.	.	<0.0002	0.00173	0.00419	0.00271	0.0178	.	<0.0010	0.0139	.
OREAS 921 4	0.0274	0.152	.	0.000120	0.00165	0.00411	0.00280	0.0176	<0.0002	0.000582	0.0132	0.0147
OREAS 921 A	0.0278	0.164	<0.005	0.000125	0.00155	0.00380	0.00260	0.00242	0.000104	0.000145	0.0124	0.00214
OREAS 501b 4	0.260	0.778	0.248	0.000154	0.00158	0.00415	0.00230	0.0184	(0.000363)	0.000558	0.0089	0.0077
OREAS 501b A	0.258	0.721	0.243	0.000160	0.00149	0.00375	0.000942	0.0126	0.000278	0.000465	0.0080	0.00109
Number	Cu	Ag*	Au*	Bi	Co	Ni	Pb	Rb	Se	Sn	Zn	Zr

** OREAS 903 also certifies Cu at 0.434% using acid leach

These samples also detail up to 74 additional elements, certificates available upon request.
 Each sample is certified for a variety of methods: 4 = 4 ACID DIGESTION, A = AQUA REGIA, F = FUSION, I = ICP

COPPER ORE

= class, where 1=CRM and 2=RM; analysis in mass % except * = mg/kg; GBM: 10 or 250g NCS: 50g VS: 100g

#	Number	Cu	Ag*	As	Ni	Pb	Tot.S	Zn	Au*	Bi*	Co*	Cd*	Fe	Hg*	Mo*	Sb*	SiO ₂
1	IMN Ko-P2	26.10	458.7	0.138	1.16	250 g units
1	GBM922-16	24.6093	326.3	.	0.0805	0.7508	26.31	1.2224
1	GBM313-16	24.2702	109.3	.	0.0153	0.0035	3.64	0.0043
1	GBM316-12	23.8210	86.0	.	0.0009	0.0236	25.43	0.0480
1	IMN W5	22.95	392	0.117	.	1.38	.	C:10.71	Org.C:7.91	100 g units
1	GBM913-14	22.7577	200.3	.	0.0053	0.0029	6.22	0.0107
1	GBM314-15	21.2876	176.2	.	0.0037	0.0145	6.54	0.02
1	ORFAS 991	20.66	48.14	(0.0170)	(0.00320)	(0.0123)	(30.77)	.	47.04	(<50)	(122)	.	(26.92)	.	(490)	.	50 g units
1	GBM319-12	19.5549	112.9	.	0.2069	0.2128	13.42	0.8434
1	GBM319-11	18.0603	108.0	.	0.0914	1.1393	22.96	1.5795
1	VS R34/1	17.21	81	0.35	.	0.17	38.6	2.45	4.7	60	.	32.9	.	97	680	1.92	.
1	GBM905-14	17.3667	.	.	0.0531	0.0334	.	0.0074
1	GBM908-11	17.7033	11.4	.	.	0.0547	29.78	2.3604	last
1	GBM314-16	16.0964	89.4	.	0.0661	0.0884	22.79	0.2898
1	GBM323-16	15.7320	220.6	.	0.3131	0.4159	23.85	3.4195
1	GBM913-13	12.1059	74.1	.	0.0084	0.0125	2.43	0.0386
1	GBM317-13	10.3409	19.0	.	3.9436	0.7361	15.52	2.4779
1	NCS DC29110	8.53	120	0.020	.	0.027	(15.42)	0.19	.	.	.	13.5	(0.039)	.	35.3	.	.
1	GBM319-16	6.9993	8.8	.	0.0055	0.0012	0.04	0.0023
1	GBM319-8	6.9613	8.8	0.0115	0.0057	0.0005	0.0023	0.0023	.	.	53
1	GBM321-16	6.9389	22.0	.	0.0065	0.0677	7.47	0.1007
1	GBM319-7	4.3368	51.8	0.1241	0.0008	0.0061	.	0.0669	.	.	45
1	GBM319-15	4.3324	51.3	.	0.0009	0.0069	0.07	0.0681	.	.	.	5.68	(0.043)	.	71	.	.
1	NCS DC29109	3.84	59.9	0.046	.	0.024	(8.58)	0.083
1	GBM916-14	3.6746	26.8	.	0.0023	0.0515	23.66	0.7103
1	GBM905-11	3.1758	.	.	0.0038	0.0042	.	0.0084
1	GBM319-14	2.9546	36.4	.	0.0299	0.7331	4.92	2.2491
1	GBM903-13	2.9077	23.9	.	2.4567	2.1559	2.42	0.9340
1	GBM922-14	2.8311	8.9	.	0.0041	0.0165	3.51	0.0949
1	GBM916-12	2.6105	17.0	.	0.0023	0.0566	19.10	0.5018
1	GBM318-4	2.4208	20.5	0.0545	0.0077	0.0023	.	0.0407	.	.	40
1	GBM322-12	2.4118	19.8	.	0.0077	0.0024	0.03	0.0413
1	GBM316-11	2.2288	21.7	.	0.0021	0.1065	18.11	1.0133
1	GBM905-12	2.1853	.	.	0.0062	0.0033	.	0.0100
1	GBM323-11	2.2045	42.2	.	0.0055	0.0799	2.65	0.0909
1	GBM920-10	2.1707	41.9	0.0083	0.0057	0.0779	.	0.0890	.	.	94
1	GBM921-11	2.1510	15.6	.	0.0019	0.1469	1.22	0.2519
1	GBM916-13	2.0136	12.5	.	0.0023	0.0390	17.60	0.3795
1	GBM319-13	1.5964	7.4	.	0.0075	0.0066	2.18	0.0454
1	GBM319-1	1.5759	7.2	0.0052	0.0080	0.0061	.	0.0450	.	.	73
1	GBM920-12	1.5542	5.3	.	0.0269	0.0053	21.84	0.0107
1	GBM920-2	1.5495	5.4	0.1607	0.0270	0.0038	.	0.0104	.	.	567
1	GBM920-13	1.5481	5.4	.	0.0284	0.0046	23.50	0.0110
1	GBM920-3	1.5471	5.3	0.1688	0.0283	0.0038	.	0.0103	.	.	594
1	GBM915-4	1.1835	25.7	0.0663	0.0118	0.4921	.	1.0035	.	.	69
1	VS R35	1.65	17.4	0.067	.	0.036	26.7	0.74	1.23	35.2
2	IMN MR2	1.61	29	0.013	.	0.085	.	0.025	.	.	.	0.88	200 g units
1	GBM322-13	1.3016	4.1	.	0.0210	0.0098	6.32	0.0613
2	IMN MR1	1.23	58	0.028	.	0.15	.	0.040	.	.	.	1.41	.	.	.	last	200 g units
1	GBM321-12	1.1883	26.0	.	0.0113	0.4967	2.06	1.0128
1	GBM910-6	1.0084	3.6	0.0117	0.0044	0.0173	.	0.0907	.	.	131
1	GBM922-13	1.0050	3.5	.	0.0052	0.0176	1.52	0.0931
1	NCS DC29108	0.90	14.9	0.00766	.	0.0080	(1.65)	0.020	(0.028)	.	11.7	.	.
1	NCS DC29107	0.29	6.1	0.00414	.	0.00345	(0.68)	0.010	(0.15)	.	23.4	.	.
1	IMN W2	0.285	6.2	0.00123	.	0.0412	.	C:7.59	Org.C:(0.361)	100 g units
1	IMN W7	0.00424	100 g units

#	Number	Cu	Ag*	As	Ni	Pb	Tot.S	Zn	Au*	Bi*	Co*	Cd*	Fe	Hg*	Mo*	Sb*	SiO ₂
---	--------	----	-----	----	----	----	-------	----	-----	-----	-----	-----	----	-----	-----	-----	------------------

CRM COPPER ORE analysis listed in mass % except * which is mg/kg

Number	Cu	As	Bi	Cd	F	Fe	MgO	Mn	Ni	Pb	S	Sb	Zn	Ag*	Au*	Units
NCS DC28058	20.56	0.012	.	<0.001	0.056	24.70	7.63	0.013	0.093	0.015	22.87	.	0.194	17.1	4.68	20 g
NCS DC28055	12.79	4.68	0.023	0.0067	0.028	3.22	0.18	0.110	0.017	0.037	1.54	0.25	0.64	85.9	0.04	50 g
NCS DC28057	10.71	0.034	.	<0.001	0.036	29.34	4.01	0.084	0.072	0.019	25.05	.	0.052	12.0	6.16	20 g
NCS DC28056	8.46	2.14	0.19	0.0064	0.53	10.44	7.04	0.169	0.011	0.087	0.86	0.22	0.503	109.9	0.05	50 g
NCS DC28054	6.78	0.209	0.283	0.0021	1.15	15.39	12.51	0.124	<0.005	0.106	0.082	.	0.456	126.1	0.05	50 g

CRM COPPER ORE analysis listed in mass % except * which is mg/kg

20 g units

Number	Cu	Ag*	Au*	Al ₂ O ₃	As	Bi	CaO	Cd*	Co	F	Fe	MgO	Mn	Ni	Pb	S	SiO ₂	Zn
NCS DC28059a	18.04	157.0	2.48	2.89	0.104	0.897	14.71	64	0.026	0.162	19.80	1.12	0.085	0.045	0.031	9.53	6.22	0.59

CRM CORUNDUM analysis listed in listed in mass 50 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI
NCS DC14225	99.04	0.029	0.043	0.002	0.012	0.45	0.016	0.061	0.024	0.29
NCS DC14226	99.02	0.028	0.040	0.003	0.013	0.43	0.013	0.061	0.020	0.34
NCS DC14224	96.00	0.31	0.21	0.048	0.28	0.014	0.024	0.68	2.28	(0.04)

CRM	CRYOLITE										analysis listed in mass %
Number	Al	CaO	F	Fe ₂ O ₃	Na	P ₂ O ₅	SO ₄ ²⁻	SiO ₂	LOI	Units	
NCS DC91001	17.34	(0.606)	55.45	0.053	21.75	0.0034	0.233	0.087	4.53	100 g	
NCS DC91002	15.18	(0.597)	54.66	0.032	26.32	0.025	0.199	0.211	2.97	100 g	
NCS DC91003	13.65	(0.719)	53.89	0.036	29.29	0.013	0.205	0.363	2.25	100 g	
NCS DC91004	13.16	(0.508)	53.2	0.033	30.26	0.037	0.293	0.389	2.12	100 g	
NCS DC91005	12.69	(0.0062)	52.14	0.0098	32.01	0.065	0.45	0.485	1.4	100 g	
NCS DC91006	11.75	0.112	51.21	0.04	33.24	0.051	0.683	0.238	1.6	100 g	

CRM DIABASE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

US: 25 g units

NCS: 70 g units

Number	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SO ₃	SiO ₂	TiO ₂	LOI
US W-2b	15.45	.	10.86	(0.0205)	8.34	1.53	10.83	.	0.626	6.37	0.167	2.20	0.14	(0.0079)	.	52.68	1.06	.
NCS DC71311	13.21	(0.11)	7.83	(0.07)	7.24	.	(13.40)	(2.44)	1.49	5.88	.	3.17	0.55	.	0.44	49.88	2.94	2.30

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd
US W-2b	.	(1.2)	(12)	170	(1.3)	.	.	23	(0.0190)	43	92	(0.99)	110	3.6	(2.5)	(1.0)	17	.
NCS DC71311	0.33	5.1	17.0	614	1.5	0.39	0.39	78.1	(0.04)	37.5	111	1.7	82.6	5.5	(2.6)	3.5	21.2	7.2

Number	Ge	Hf	Hg	Ho	La	Li	Lu	Mn%	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm
US W-2b	.	2.6	.	(0.76)	10	9.6	(0.33)	.	.	(7.9)	13	70	(9.3)	.	21	(0.79)	36	.	3.3
NCS DC71311	1.5	9.2	0.017	1.2	38.1	20.8	0.34	(0.16)	1.4	25.3	42.8	56.8	33.0	10.6	47.4	2.3	27.1	(0.19)	8.6

Number	Sn	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb	Zn	Zr
US W-2b	.	190	(0.5)	(0.63)	2.4	(0.38)	(0.53)	260	.	23	2.1	80	100
NCS DC71311	2.0	470	1.8	1.1	4.9	0.36	1.2	268	1.4	24.5	2.2	(160)	359

DIORITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

T = Total

IAG: RM, ~35 g units

all others: CRM, 100 g units

Number	Al ₂ O ₃	CaO	CO ₂	Fe	FeO	Fe ₂ O ₃	H ₂ O+	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Type
CAN SY-4	20.69	8.05	3.5	4.2	2.86	6.21	(1.0)	(0.15)	1.66	0.54	0.108	7.10	0.131	49.9	0.287	4.56	Diorite Gneiss
VS 6103-91	16.56	4.84	(0.18)	.	3.79	5.55	(1.6)	(0.14)	2.98	3.05	0.086	3.57	0.17	60.45	0.86	1.59	Quartz
USZ 50-2009	15.97	6.99	.	.	4.82	8.10T	0.35	(0.11)	1.55	3.81	0.12	3.33	(0.39)	57.75	1.34	0.51	Diorite
IAG OU-4	14.83	4.48	.	.	4.52	5.82T	.	.	2.70	2.30	0.14	3.61	0.173	63.34	0.77	1.72	Microdiorite

continued analysis listed in mg/kg

Number	B	Ba	Be	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd	Hf	Ho
CAN SY-4	.	340	2.6	122	2.8	12	1.5	7	10.2	14.2	2.00	.	335	14.0	10.6	4.3
VS 6103-91	46	720	2.4	46	17	58	2.9	39	.	.	1.3	710	18	.	.	.
USZ 50-2009	.	425	.	50.8	84.9	100	(5.24)	100	(4.29)	(2.29)	(1.41)	.	419.58	(5.21)	(3.69)	(0.85)
IAG OU-4	.	360.8	1.79	55.7	13.5	54.7	2.07	27.3	7.81	4.83	1.64	.	17.4	7.39	5.54	1.63

Number	La	Li	Lu	Mn	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Sm	Sn	Sr
CAN SY-4	58	37	2.1	819	13	57	9	10	15.0	55	.	1.1	12.7	.	1191
VS 6103-91	27	30	0.30	.	12	24	33	24	.	83	.	15	4.8	.	410
USZ 50-2009	24.40	(13.9)	(0.30)	.	6.92	30.48	40.94	8.97	(6.45)	48.5	.	20.46	(5.61)	.	454
IAG OU-4	24.96	35.0	0.71	.	12.8	27.9	21.0	14.1	6.85	98.5	0.30	19.1	6.94	2.42	99.9

Number	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
CAN SY-4	0.9	2.6	1.4	.	2.3	0.8	8	.	119	14.8	93	517
VS 6103-91	.	.	6.8	.	.	.	96	21	2.1	71	173	.
USZ 50-2009	(0.48)	(0.76)	3.88	.	(0.32)	(1.09)	213	266	23.62	2.05	92.77	191
IAG OU-4	1.00	1.25	8.42	0.46	0.72	2.19	82.7	.	47.1	4.70	69.5	195.1

DOLERITE WITH EXTENSIVE ANALYSIS

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	SiO ₂	Al ₂ O ₃	CaO	F	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI	Units
1	SARM 50	51.56	15.28	10.80	.	8.49	11.0	.	.	0.61	7.57	0.17	2.30	0.15	.	0.86	.	100 g
2	IAG OU-2	51.095	13.801	8.994	.	8.404	.	13.253	.	0.990	5.585	0.170	2.480	0.300	.	2.425	.	~35 g
2	IAG OU-5	49.10	13.62	6.63	.	8.74	14.60	.	.	0.826	5.17	0.310	4.29	0.440	.	2.718	2.08	~35 g
1	VS 8671-2005	47.99	14.63	10.42	(0.021)	10.33	.	14.62	(0.88)	0.46	7.51	0.21	2.32	0.17	(0.026)	1.59	(0.42)	100 g
1	US DNC 1a	47.15	18.34	11.49	(0.0066)	7.32	1.79	9.97	.	0.234	10.13	0.15	1.89	0.07	.	0.48	.	25 g

continued analysis listed in mg/kg

Number	Ag	As	Au	B	Ba	Be	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu
SARM 50	220	.	.	(30)	.	40	357	.	84	.	.	.
IAG OU-2	341.1	1.11	.	60.2	.	44.8	97.0	0.495	63.0	6.09	3.06	2.23
IAG OU-5	.	(2.45)	.	.	309.2	1.31	(0.20)	44.17	.	38.60	38.40	0.555	27.32	9.04	5.49	2.35
VS 8671-2005	(0.05)	.	(0.0026)	(3.8)	227	0.8	.	22	.	52	213	(0.45)	180	5.1	2.9	1.4
US DNC 1a	.	(0.12)	.	(0.9)	118	(1)	.	.	(60)	57	270	.	100	(3)	.	0.59

Number	Ga	Gd	Ge	Hf	Ho	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb
SARM 50	(10)	.	(85)	25	.	14
IAG OU-2	23.05	7.26	.	5.29	1.21	27.71	12.79	0.372	3.05	17.25	33.35	51.77	13.12	7.92	25.44
IAG OU-5	21.2	8.64	(2.03)	5.59	1.92	18.10	21.74	0.767	.	9.58	28.47	15.00	4.66	6.29	19.29
VS 8671-2005	17	4.5	1.5	2.7	(1)	8	8.6	0.44	0.98	6	13.2	126	(3)	2.6	11
US DNC 1a	(15)	(2)	.	.	(0.62)	3.6	5.2	.	.	(3)	5.2	247	(6.3)	.	(4.5)

Number	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
SARM 50	195	.	.	(6)	216	.	23	81	86
IAG OU-2	.	28.21	8.70	17.73	403.7	1.20	1.11	3.02	.	0.427	0.63	339.3	.	30.93	2.52	113.0	200.5
IAG OU-5	0.42	42.4	7.64	2.00	226.8	(0.546)	1.46	2.25	(0.125)	0.789	0.500	447.8	(0.865)	51.8	5.10	133.6	219.9
VS 8671-2005	.	41	4	2.64	197	0.35	0.8	1.0	.	0.44	0.45	315	(0.4)	29	3.3	112	125
US DNC 1a	0.96	31	.	.	144	148	.	18	2	70	38

CRM		DOLOMITE WITH EXTENSIVE ANALYSIS														analysis listed in mass %				
Number	CaO	MgO	Al ₂ O ₃	CO ₂	Cl	F	FeO	Fe ₂ O ₃	H ₂ O	K ₂ O	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Units			
UL DWA1	30.84	21.40	(0.05)	0.27	.	0.010	(0.06)	0.042	(0.023)	(0.06)	(0.010)	47.29	50 g			
GBW 07114	30.02	21.8	0.10	46.77	0.012	0.014	0.15	0.04	(0.34)	0.038	0.010	(0.03)	0.006	0.62	0.015	.	50 g			
continued		analysis listed in mg/kg except % which is mass %																		
Number	Ag	As	B	Ba	Be	Bi	Br	Tot.C%	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	
UL DWA1	.	(1.3)	.	24	2.2	(0.2)	(4)	.	(4)	0.82	0.50	0.16	.	0.81
GBW 07114	0.04	0.23	20.5	44.3	(0.22)	0.03	0.84	(12.88)	0.07	3.58	3.88	2.6	0.07	30.2	0.19	0.09	0.05	(0.21)	0.18	
Number	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	S%	Sb		
UL DWA1	.	(0.03)	.	0.18	.	.	3.6	.	0.05	.	.	3	.	(35)	0.67	
GBW 07114	0.15	(0.10)	(0.004)	0.04	0.23	(0.066)	1.34	2.30	0.019	(0.24)	(2.77)	1.39	241	(4.44)	(0.44)	(1.42)	0.011	0.04		
Number	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr		
UL DWA1	0.24	.	0.62	.	284	.	0.12	.	0.08	.	0.06	1.4	6.9	.	9.4	0.39	83	.		
GBW 07114	0.098	0.08	0.25	0.53	49	(0.18)	0.05	(0.012)	0.11	(0.070)	(0.040)	0.16	2.10	0.11	(1.40)	0.09	11.7	3.0		

DOLOMITE

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	CaO	MgO	SiO ₂	Al ₂ O ₃	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MnO	Na ₂ O	P	P ₂ O ₅	PbO
1	NCS DC28009a	45.90	6.65	2.56	0.47	.	0.235	0.272	0.0049	0.012	0.0033	.	.
1	NCS DC28206	41.66	11.31	4.64	0.16	.	0.112	.	0.0050	.	0.0032	.	.
1	NCS DC14020b	35.73	15.28	4.21	0.92	.	0.533	0.017	0.022	0.015	0.0032	.	.
1	NCS DC14021b	34.82	17.34	1.30	0.18	.	0.447	0.027	0.0072	0.019	0.0057	.	.
1	NCS DC28203	34.74	17.16	1.45	0.286	.	0.404	.	0.012	.	0.016	.	.
1	NCS DC28015a	33.60	15.50	4.89	1.40	.	0.641	0.35	0.0085	0.019	0.011	.	.
1	NCS DC14018b	31.96	19.92	0.77	0.23	.	0.269	0.030	0.031	0.033	0.0023	.	.
1	NCS DC11003a	31.49	21.06	0.098	0.083	.	0.024	0.0030	0.0061	0.017	0.0016	.	.
1	NCS DC28014a	31.46	18.60	2.97	0.81	.	0.472	0.29	0.012	0.021	0.0061	.	.
1	NCS DC28013a	31.12	19.10	2.65	0.73	.	0.504	0.13	0.011	0.034	0.0034	.	.
1	NCS DC28012a	30.94	20.92	1.48	0.23	.	0.26	0.085	0.011	0.012	0.014	.	.
1	NCS DC28208	30.80	20.79	0.99	0.23	.	0.32	.	0.019	.	0.0013	.	.
1	NCS DC28202	30.79	20.73	2.12	0.203	.	0.275	.	0.026	.	0.0013	.	.
1	NCS DC28201	30.62	20.53	6.75	0.048	.	0.085	.	0.0072	.	0.0012	.	.
1	BCS 512	30.61	21.59	0.379	0.055	(<0.001)	0.030	(<0.02)	0.0036	.	(0.02)	(0.001)	.
1	CGL 021	30.59	21.40	0.267	0.200	.	0.228	0.062	0.047	(0.040)	.	0.044	.
2	DH 0915	30.59	21.21	0.035	0.019	.	0.191	0.007	0.050	0.026	.	0.008	.
1	ECRM 782-1	30.34	21.29	0.266	0.104	0.0009	0.450	0.0260	0.081	.	.	0.0128	0.0029
1	NCS DC28207	30.33	20.88	1.26	0.27	.	0.44	.	0.013	.	0.018	.	.
2	FLX 135	30.00	21.24	0.969	0.276	.	0.162	0.063	Mn ₂ O ₃ : 0.052

Number	S	Sr	SrO	Ti	TiO ₂	ZnO	LOI	Units
NCS DC28009a	0.021	.	0.020	.	0.024	.	43.48	50 g
NCS DC28206	0.0093	.	0.015	.	0.0056	.	41.70	50 g
NCS DC14020b	0.030	0.026	.	0.025	.	.	42.69	70 g
NCS DC14021b	0.009	0.021	.	0.085	.	.	45.37	50 g
NCS DC28203	0.028	45.58	50 g
NCS DC28015a	0.013	.	0.0060	.	0.074	.	43.24	50 g
NCS DC14018b	0.010	0.0081	.	0.011	.	.	46.24	70 g
NCS DC11003a	0.011	0.021	.	0.0043	.	.	46.71	70 g
NCS DC28014a	0.019	.	0.0058	.	0.041	.	44.94	50 g
NCS DC28013a	0.007	.	0.0064	.	0.034	.	45.49	50 g
NCS DC28012a	0.003	.	0.0070	.	0.0080	.	45.58	50 g
NCS DC28208	0.022	46.20	50 g
NCS DC28202	0.016	45.22	50 or 100 g
NCS DC28201	0.0019	41.00	50 g
BCS 512	.	.	0.024	.	0.0020	(<0.01)	46.80	100 g
CGL 021	.	(0.0057)	.	.	(0.013)	.	(46.63)	50 g C: (12.925)
DH 0915	100 g
ECRM 782-1	0.0042	0.0082	47.25	100 g
NCS DC28207	0.033	46.11	50 g
FLX 135	30 g

RM DOLOMITE SUBSTITUTE

typical analysis in mass % * DH 0710 also contains 0.015 CuO ** DH 0712 also contains 0.167 Na₂O and 0.012 Nb₂O₅ 100 g units

Number	CaO	MgO	Al ₂ O ₃	Cr ₂ O ₃	Fe	K ₂ O	Mn ₃ O ₄	NiO	P ₂ O ₅	PbO	S	SiO ₂	SrO	TiO ₂	V ₂ O ₅	ZnO	ZrO ₂
DH 0710 *	35.36	35.30	0.28	0.591	5.14	0.077	1.079	0.013	0.107	0.011	0.265	10.23	0.028	0.301	0.032	0.159	0.051
DH 0711	32.46	28.57	9.49	0.84	8.81	0.092	1.745	0.020	0.262	0.015	0.314	12.07	0.029	0.370	0.056	0.183	0.068
DH 0709	23.45	63.07	5.62	0.071	1.96	0.053	0.444	0.010	0.133	0.029	0.097	3.69	0.011	0.131	0.021	0.014	0.057
DH 0712 **	20.16	32.62	20.79	0.560	6.72	0.146	0.906	0.050	0.141	0.008	0.129	13.30	0.016	0.671	0.039	0.052	0.383

DUNITE

= class, where 1 = CRM and 2 = RM analysis listed in mass % DH, SARM: 100 g US: 25 g VS 2112: 40 g VS 4233: 100 g

#	Number	MgO	SiO ₂	Si	Al ₂ O ₃	Al	CO ₂	Tot.C	CaO	Ca	Co	Cr	Cr ₂ O ₃	T.Fe	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃
1	US DTS-2B	49.4	39.4	18.4	0.45	0.24	.	.	0.12	0.09	0.0120	1.5500	.	5.43	(4.27 FeII)	.	7.76
1	SARM 6	43.51	38.96	.	(0.3)	.	.	.	0.28	.	.	.	0.42	.	14.63	0.71	.
1	VS 2112-81	42.40	35.07	.	.	.	0.46	.	.	.	0.0129	10.06
1	VS 4233-88	41.86	39.58	.	0.97	.	(1.61)	.	1.52	.	0.012	0.41	.	.	(5.54)	.	8.91

continued analysis listed in mass %

Number	H ₂ O	K ₂ O	Mg	MnO	Na	Na ₂ O	Ni	F ₂ O ₅	S	TiO ₂	V	LOI @ 900 °C
US DTS-2B	.	.	29.8	.	(0.02)	.	0.3780	.	.	.	0.0022	.
SARM 6	.	(0.01)	.	0.22	.	(0.04)	.	.	.	(0.02)	.	.
VS 2112-81	11.35	.	.	0.176	.	.	0.133	.	.	.	0.00069	.
VS 4233-88	(+4.82 -0.4)	0.010	.	0.13	.	0.035	0.22	(0.01)	(0.041)	0.018	0.0033	6.31

continued analysis listed in mg/kg except % which is mass %

Number	Ba	Cu	Ge	Li	Mn	Mo	Pb	Rb	Sb	Sc	Sn	Sr	Zn
US DTS-2B	(16)	(3)	(0.7)	.	830	.	(4)	(2)	(0.6)	(3)	.	.	45
SARM 6
VS 2112-81	.	27	.	.	1.4	2.2	.	.	82
VS 4233-88	.	33	1.1	2.0	9	.	18	30

H₂O+: (4.82)

FELDSPAR

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	SiO ₂	Al ₂ O ₃	BaO	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	PbO	Rb ₂ O	SrO	TiO ₂	LOI	Units
1	BCS 532	77.07	13.46	.	0.212	.	0.181	3.80	0.159	4.35	0.56	100 g
1	FLX CRM129	69.84	16.44	0.130	0.374	.	(0.104)	10.78	.	2.11	0.068	.	.	(0.014)	(0.036)	(0.428)	40 g
1	BCS 375/1	69.24	17.88	.	0.78	.	0.291	1.47	0.180	8.89	0.226	.	.	.	0.312	0.72	100 g
1	FLX CRM128	67.88	19.95	(0.007)	1.08	.	(0.021)	0.206	.	10.74	(0.008)	.	.	(0.049)	(0.017)	(0.171)	40 g
2	DH X1602	66.93	17.16	0.323	0.032	0.047	.	14.19	0.001	.	0.087	0.012	.	0.036	0.038	.	100 g
1	GBW 03116	66.26	18.63	.	0.76	.	0.19	9.60	0.054	3.69	0.048	0.86	50 g
1	IPT 72	66.2	20.26	.	0.18	.	0.09	1.47	(0.022)	10.0	1.03	.	.	.	0.005	0.66	80 g
1	IPT 53	65.8	18.3	.	0.27	.	0.13	12.1	0.05	2.5	0.072	.	.	.	0.013	0.51	80 g
1	BCS 376/1	65.77	18.63	0.0210	0.421	.	0.085	11.59	(0.03)	3.00	(0.02)	0.0090	.	.	(<0.01)	0.203	100 g
1	BCS 529	56.24	26.84	.	9.58	.	0.273	0.421	0.045	5.58	0.550	100 g
	Number	Si	Al	Ba	Ca		Fe	K		Na	P	Pb	Rb	Sr			
1	SRM 99b	(32.07)	10.36	0.1409	(1.18)	.	0.02787	3.09	.	5.25	(0.0044)	0.00712	0.00726	0.0444	.	.	40 g

CRM FELDSPAR WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	Li ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Rb ₂ O	TiO ₂	LOI	Units
GUV FK	88.2	6.18	.	0.110	.	0.261	.	.	4.23	.	0.15	0.0037	0.25	0.077	.	0.058	.	50 g
UNS ZK	74.38	14.19	.	0.43	0.73	0.88	.	.	4.06	0.06	0.067	0.025	4.50	.	0.094	0.039	0.54	100 g
JF-1	66.69	18.08	.	0.93	.	0.06	0.08	+0.23 -0.13	9.99	.	0.006	0.001	3.37	0.01	.	0.005	.	100 g
JF-2	65.30	18.52	.	0.09	.	0.06	0.06	+0.24 -0.18	12.94	.	0.001	0.001	2.39	.	.	0.005	.	100 g
VS 811-89	60.67	18.20	0.20	0.51	4.8	7.20	.	4.0	3.43	.	2.22	0.042	2.31	0.19	.	0.94	.	100 g
SRM 70b	40 g

analysis listed in mg/kg except % indicating mass %, * indicating ppb, and ! indicating scientific notation

Number	Al%	As	B%	Ba%	Be	Ca%	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F%	Fe%	Ga	Ge
GUV FK	.	.	.	0.0700	2.6	11	6	.	.
UNS ZK	.	4.8	5.7	7.0	38.7	12.2	33.3	.	.
JF-1	9.57	.	.	0.1750	.	0.66	4.19	0.12	5.48	2.09	0.82	0.39	0.31	0.87	.	0.06	17.4	.
JF-2	9.80	.	.	0.0298	.	0.06	0.84	0.68	1.06	0.78	.	.	0.59	0.04	0.04	17.9	.	.
VS 811-89	.	.	0.008	0.09	3.0	.	0.007*	21	96	6.3	41	.	.	0.06	.	22	1.7	.
SRM 70b	7.98	.	.	0.00282	.	0.1770	(0.13)	.	.	.

Number	Hf	Ho	K%	La	Li%	Mg%	Mn%	Mo	Na%	Nb	Nd	Ni	P%	Pb	Pr	Ra!	Rb%	S%
GUV FK	0.0008	0.004	18	.	.	0.0132	.
UNS ZK	1.4	21.0	.	33.5	.	29.4
JF-1	1.18	0.11	8.29	2.80	0.000981	0.004	0.001	2.50	0.74	1.46	.	.	33.4	0.48	.	0.0266	.	
JF-2	0.19	.	10.74	0.63	0.000219	.	0.001	1.77	0.70	.	.	.	48.7	.	.	0.0218	.	
VS 811-89	.	.	6.33	.	0.006	.	(0.0298)	0.00630	2.36	14	59	.	0.0790	20	3e-10	0.012	0.087	
SRM 70b	(57)	.	.	(0.0495)	.

Number	Sc	Si%	Sm	Sr%	Ta	Tb	Th	Ti%	Tl	U	V	Y	Yb	Zn%	Zr%
GUV FK	.	.	.	0.0072	0.0014	.
UNS ZK	3.6	.	16.8	.	19.4	.	4.7	8.4	.	0.00194	.
JF-1	0.23	31.17	0.41	0.0172	0.079	0.076	1.17	0.003	1.18	0.33	5.43	2.84	0.35	0.000441	0.00386
JF-2	0.089	30.52	0.11	0.0200	.	.	0.31	0.003	1.10	.	4.86	2.67	.	0.000140	0.000673
VS 811-89	19	.	3.2	0.017	1.3	.	11	.	.	2.5	0.016%	32	3.4	0.012	0.021
SRM 70b	.	(34.4)	.	(0.0027)	.	.	.	(0.0032)	.	.	(0.93)	.	.	(0.00077)	.

CRM TRACE ELEMENTS IN FELDSPAR

analysis listed in mg/kg

Number	Rb	Uncertainty	Sr	Uncertainty	⁸⁷ Sr/ ⁸⁶ Sr	⁸⁶ Sr/ ⁸⁸ Sr	Units
SRM 607	523.90	1.01	65.485	0.320	1.20039	0.1194	5 g

CRM FLUORSPAR (FLUORITE)

analysis listed in mass % NCS DC62003a: 20g NCS DC14046-8,NCS DC282x, RH0₃: 50g other NCS, CMSI, GBW: 65g SRM: 120g all others: 100g

Number	CaF ₂	F	Al ₂ O ₃	BaO	CaCO ₃	CaO	Fe	Fe ₂ O ₃	K ₂ O	Na ₂ O	P	S	SiO ₂	Others
NCS DC14026b	98.90	.	BaSO ₄ : (0.03)	.	0.31	.	.	0.039	.	.	0.0083	0.010	0.70	As: (0.00009) Pb: (0.0002)
SRM 180	98.80
SARM 15	97.84	.	.	.	0.95	.	.	(0.23)	.	.	0.007	.	(0.26)	MgCO ₃ : 0.55 Mn: 0.0213
SARM 14	97.32	.	.	.	(0.3)	.	.	(0.06)	.	.	(0.079)	.	(0.57)	.
BCS 392	97.2	.	.	0.37	.	0.52	0.12	0.67	CO ₂ : 0.48 Pb: 0.18
JK D	97.07	47.24	0.04	0.20	.	.	0.035	0.004	(1.5)	.
NCS DC28088	96.87	.	0.14	.	0.14	.	.	0.173	0.036	0.019	0.015	0.092	1.76	MgO: 0.015 Mn: 0.040
NCS DC28228	94.81	.	.	.	0.99	.	0.26	.	.	.	0.076	0.107	2.76	Mn: 0.010
NCS DC14022a	93.68	.	.	.	0.30	.	0.166	.	0.026	0.006	0.014	0.35	3.06	.
GBW 07252	92.57	.	.	.	(0.02)	.	.	0.124	0.029	0.006	0.0024	0.043	6.84	last of stock
VS 3383-86	91.84	.	0.53	.	.	.	0.612	.	.	.	0.063	0.095	5.03	.
GBW 07251	90.87	.	.	.	(0.02)	.	.	0.124	0.026	0.005	0.0031	0.090	8.35	.
NCS DC28230	90.72	.	.	.	0.87	.	0.25	.	.	.	0.063	0.084	7.68	Mn: 0.012
CGL 132	88.65	.	.	.	(0.78)	(0.012)	(0.019)	10.15	.
NCS DC28229	85.56	.	.	.	0.58	.	0.28	.	.	.	0.045	0.079	10.62	Mn: 0.013
IPT 95	85.4	0.36	8.3	.
GBW 07253	85.21	.	.	.	(0.02)	.	.	0.209	0.044	0.005	0.0013	0.045	14.15	.
VS SH13	84.7	.	.	.	0.51	.	0.353	.	.	.	0.012	0.103	13.0	.
NCS DC28087	83.12	.	0.69	.	1.06	.	.	0.36	0.28	0.031	0.018	0.050	13.74	MgO: 0.14 Mn: 0.0099
NCS DC28227	78.75	.	.	.	0.33	.	0.28	0.028	19.36	Mn: 0.012
NCS DC28226	77.33	.	.	.	0.20	.	0.31	0.068	18.04	Mn: 0.014
NCS DC28086	73.73	.	1.07	.	2.06	.	.	0.87	0.38	0.054	0.023	0.28	19.27	MgO: 0.73 Mn: 0.027
NCS DC62003a	60.98	.	3.69	.	.	1.17	.	2.35	1.44	0.52	.	SO ₃ : 0.12	26.20	MgO: 0.18 TiO ₂ : 0.15 LOI: 1.38
NCS DC28085	60.16	.	1.29	.	3.73	.	.	1.32	0.41	0.067	0.021	0.52	27.17	MgO: 1.99 Mn: 0.034
NCS DC28084	46.59	.	0.99	.	9.08	.	.	0.52	0.34	0.061	0.0071	0.071	28.89	MgO: 5.51 Mn: 0.051
CGL 135	35.60	.	.	.	(0.68)	0.037	0.41	47.67	.
VS 4182-87	32.75	.	.	.	1.70	0.114	0.038	47.52	.
VS 5132-89	32.69	.	.	.	11.75	(27.68)	.
VS 5133-89	4.17	.	.	.	1.10

Number	CaF ₂	F	Al ₂ O ₃	BaO	CaCO ₃	CaO	Fe	Fe ₂ O ₃	K ₂ O	Na ₂ O	P	S	SiO ₂	Others
--------	------------------	---	--------------------------------	-----	-------------------	-----	----	--------------------------------	------------------	-------------------	---	---	------------------	--------

FLUORSPAR (FLUORITE)

= class where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg IGS: 55 g all others: 100 g

#	Number	Ca	F	Al ₂ O ₃	BaO	CO ₂	CuO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	SiO ₂	SO ₄	TiO ₂	ZnO	LOI 900°C
1	IGS 39	.	46.69
2	DH 2712	44.18	40.6	1.01	.	2.11	0.199	0.373	0.125	0.739	0.237	.	8.91	0.103	0.069	0.103	0.370
2	DH 2709	39.98	38.10	0.310	.	0.027	0.052	15.72	0.029	0.017	0.077	0.030	3.93	0.027	.	0.004	0.929
1	USZ HJ	37.32	34.92	2.35	.	.	0.34	0.99	23.01	.	0.047	.	.
1	UNS FM **	35.89	34.03	(0.329)	3.89	(0.13)	.	0.496	0.097	(0.036)	.	(0.087)	22.59	.	0.018	.	.

Number	Bi*	Ce*	Cr*	Cr ₂ O ₃ %	Cu*	Eu*	La*	Mo*	Pb*	S	Sb*	Sc*	Sm*	Sr%	Y*
IGS 39	(0.014)	.
DH 2712	.	.	.	0.106	.	.	NiO:0.153	.	PbO:0.102	.	.	.	SnO ₂ :0.054	.	.
DH 2709	.	.	.	0.004
USZ HJ
UNS FM **	(58.8)	28.3	272	.	60.7	1.16	14.1	44.6	72.2	0.91	2.1	0.67	5.6	(0.0580)	154

** UNS FM also contains Co: 2.6*, Cs: 0.81*, Mn: 64*, U: 2.9*, Yb: 3* and trace informational values for 19 other elements

CRM GABBRO

analysis listed in mass %

40 g units

Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	H ₂ O+	T.H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂
VS M08	51.98	16.39	0.43	9.02	0.0390	9.61	0.85	11.55	0.088	0.22	0.31	0.46	6.39	0.16	3.27	0.21	0.1700	1.15
VS M07	40.79	17.60	0.03	14.62	0.1300	7.76	3.73	12.35	0.12	0.70	0.82	0.75	6.46	0.15	2.05	1.08	0.1800	3.39

continued

analysis listed in mg/kg except % which is mass %

VS M08: Gabbro

VS M07: Orthoclase Gabbro

Number	B	Ba	Be	Co	Cr	Cs	Cu	Ga	La	Li	Mo	Nb	Ni	Pb	Rb	Sc	Sn	Sr	V	Y	Yb	Zn	Zr
VS M08	7.5	272	0.8	48	126	1.1	40	18	26	5.5	3.2	3.7	18	7.3	4.0	31	2.7	477	199	18	2.0	84	48
VS M07	4.5	7480	(1.2)	49	76	1.1	59	(18)	37	5.4	(2.4)	12	45	7.6	12	(25)	(3.8)	1745	270	.	.	65	53

GABBRO WITH EXTENSIVE ANALYSIS

= class, where 1 = CRM and 2 = RM

analysis listed in mass % except * which is mg/kg

#	Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI
2	IAG OU-7	51.15	17.02	.	9.27	.	(5.8)	.	10.45	.	1.16	5.10	0.150	3.23	0.201	1.329	(0.75)
1	USZ 51-2009	48.00	26.26	.	13.61	(0.085)	2.00	.	4.22	(+0.61 -0.13)	0.31	2.85	0.080	2.42	0.078	0.37	1.40
1	VS 8670-2005	46.63	14.93	.	10.68	0.13	6.23	.	11.33	(+0.93)	3.09	6.81	0.167	2.72	1.03	1.72	(0.77)
1	JGb-2	46.47	23.48	.	14.10	.	5.41	0.62	6.69	-0.14	0.059	6.18	0.13	0.92	0.017	0.56	.
1	JGb-1	43.66	17.49	.	11.90	0.0133	9.43	4.79	15.06	+1.28 -0.13	0.24	7.85	0.189	1.20	0.056	1.60	.
1	CGL 013	43.15	22.57	.	14.99	(0.099)	4.57	.	10.99	(+0.46 -0.21)	0.11	4.51	0.10	1.41	(0.038)	0.94	(1.03)
1	VS 2117-81	37.62	13.67	(0.16)	15.75	0.0720	9.05	18.54	.	(0.12)	0.204	8.66	0.222	0.72	2.15	1.46	.
1	GBW 07112	35.69	14.14	0.12	9.86	0.006	13.36	9.90	.	1.09	0.15	5.25	0.193	2.11	0.028	7.69	.
	Number	Si	Al	.	Ca	.	Fe	.	.	.	K	Mg	Mn	Na	P	Ti	
1	CAN WMG-1A	18.27	4.75	.	10.06	.	12.71	.	.	.	0.1021	7.41	(0.1141)	0.1119	0.0731	0.419*	(4.31)

continued

analysis listed in mg/kg except % which is mass %

Number	Ag	As	B	Ba%	Be	Bi	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd
IAG OU-7	(0.10)	.	.	0.0405	0.96	.	(0.13)	37.8	.	35.6	176	0.35	98.2	4.52	2.61	1.52	20.1	4.83
USZ 51-2009	.	.	.	0.0119	.	.	.	7.90	.	14.93	69.97	.	45.32	.	.	.	18.87	.
VS 8670-2005	(0.09)	.	(15)	0.152	1.9	.	.	163	.	40	58	3.3	58	6.2	2.8	3.9	17	11.5
JGb-2	.	.	.	0.00365	.	.	.	3.0	.	25.8	125	0.51	11.4	.	.	0.59	15.9	.
JGb-1	.	1.09	4.03	0.00643	.	.	0.087	8.17	.	60.1	57.8	0.26	85.7	1.56	1.04	0.62	17.9	1.61
CGL 013	.	.	.	0.004994	.	.	.	(3.43)	.	35.21	35.72	.	608	(0.79)	(0.44)	(0.37)	17.94	(0.8)
VS 2117-81	.	.	.	0.0110	.	.	.	65	.	14	.	3600	21	.
GBW 07112	0.05	.	1.84	0.00862	.	0.04	0.09	4.2	0.006	93.0	14.5	.	28.3	1.11	0.47	0.74	23.7	1.31
CAN WMG-1A	3.03	5.99	.	0.0216	.	(0.251)	(0.818)	(17.18)	.	191	804	.	7120	2.291	(1.34)	(0.733)	(12.4)	(2.351)

Number	Ge	Hf	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pd	Pb	Pr	Pt	Rb	S%
IAG OU-7	(1.2)	(3.2)	0.92	Hg:(0.012)	17.4	7.56	0.35	0.52	6.35	20.7	63.6	.	.	6.25	4.84	.	27.6	.
USZ 51-2009	12.33	0.1196	23.94	6.00	.	.	6.58	.
VS 8670-2005	1.3	5.3	1.1	.	.	82	12	0.3	1.4	8.4	89	47	15	20.7	.	.	80	(0.015)
JGb-2	.	0.25	.	.	.	1.5	.	0.062	0.42	1.9	1.8	13.6	.	1.5	.	.	2.9	.
JGb-1	1.01	0.88	0.33	.	.	3.60	4.59	0.15	0.59	3.34	5.47	25.4	.	1.92	1.13	.	6.87	0.1910
CGL 013	.	(0.32)	(0.16)	.	.	(1.31)	(4.89)	(0.06)	(0.5)	(0.36)	(2.33)	23.34	.	4.68	(0.5)	.	(1.96)	.
VS 2117-81	2.1	3.3	.	2.0	.	.	.	28	.	6	.	.	.	0.1240
GBW 07112	1.06	0.65	0.20	0.08	0.12	1.71	1.94	0.06	.	9.3	4.10	69	.	0.84	.	.	0.37	.
CAN WMG-1A	8.47	(44.7)	(0.196)	2.49	(5.26)	9.41	2480	0.484	(9.2)	(2.220)	0.899	(2.53)	3.43

Number	Sc	Se	Sm	Sn	Sr%	Ta	Tb	Te	Th	Tl	Tm	U	V	Y	Yb	Zn	Zr	Units
IAG OU-7	29.5	.	4.66	1.2	0.0367	0.38	0.76	.	1.82	0.15	0.37	0.41	262	24.5	2.33	76.6	(134)	35 g
USZ 51-2009	12.33	.	.	.	0.1196	85.28	5.14	.	59.87	(33.49)	100 g
VS 8670-2005	26	.	17	3.2	0.224	0.5	1.5	.	8	.	(0.35)	1.8	250	30	2.5	120	219	100 g
JGb-2	27	.	0.51	.	0.0438	0.29	0.15	.	0.19	.	.	.	174	4.5	0.39	48.5	11.6	100 g
JGb-1	35.8	.	1.49	0.48	0.0327	0.18	0.29	.	0.48	.	0.16	0.13	635	10.4	1.06	109	32.8	20 g
CGL 013	39.66	.	(0.72)	.	0.0778	.	(0.13)	.	.	.	(0.05)	.	420	4.30	(0.39)	98.00	(12)	100 or 250 g
VS 2117-81	37	.	.	6.5	0.1040	960	.	2.6	136	.	100 g
GBW 07112	22.5	0.26	1.22	0.89	0.0612	.	0.20	0.010	0.07	0.09	.	.	768	4.9	0.36	118	29	50 g
CAN WMG-1A	21.33	14.1	2.211	(1.91)	0.00390	(0.355)	.	(1.19)	1.07	.	(0.192)	(0.65)	158	12.67	(1.220)	112	35.7	350 g

CRM GOLD ORE

ng/g (ppb) 10g or 1kg

Number	Au
GLG919-2	635.73
GLG321-2	329.99
GLG322-1	327.84
GLG320-1	322.15
GLG321-5	315.63
GLG920-3	276.79
GLG318-1	259.04
GLG319-3	238.19
GLG922-2	231.81
GLG313-3	227.70
GLG912-5	224.34
GLG917-3	222.13
GLG318-3	214.41
GLG911-5	209.21
GLG904-4	204.08
GLG322-2	202.03
GLG322-3	199.16
GLG315-5	194.82
GLG317-2	189.96
GLG313-4	183.83
GLG921-4	160.65
GLG922-1	158.89
GLG317-1	151.88
GLG316-2	150.84
GLG920-2	138.05
GLG921-3	127.92
GLG304-4	121.43
GLG919-1	120.71
GLG314-3	103.11
GLG314-5	95.23
GLG319-4	93.13
GLG317-3	94.60
GLG323-3	84.99
GLG922-3	83.98
GLG922-4	83.56
GLG313-5	83.36
GLG310-5	79.83
GLG919-3	76.60
GLG320-2	66.38
GLG323-5	59.61
GLG305-3	55.48
GLG320-3	52.09
GLG319-5	44.93
GLG919-5	34.78
GLG910-3	32.02
GLG322-5	30.91
GLG920-1	28.01
GLG319-1	25.63
GLG321-1	24.31
GLG913-2	22.75
GLG921-5	21.48
GLG312-1	20.65
GLG323-4	19.69
GLG321-4	19.52
GLG920-5	18.99
GLG920-4	16.60
GLG922-5	14.95
GLG915-1	14.01
GLG919-4	11.32
GLG322-4	10.96
GLG901-2	9.92
GLG912-1	6.86
GLG910-4	6.36
GLG916-1	5.06
GLG911-4	4.65
GLG910-1	4.89
GLG921-1	4.65
GLG921-2	4.37
GLG321-3	4.28
GLG907-1	4.18
GLG912-3	3.98
GLG904-1	3.82
GLG911-3	3.74
GLG914-2	3.68
GLG314-1	3.63
GLG316-5	3.50
GLG916-2	3.48
GLG916-3	3.45
GLG323-2	3.43
GLG916-4	3.27
GLG302-4	3.23
GLG913-4	3.10
GLG318-2	3.03
GLG314-2	2.98
GLG323-1	2.88
GLG913-3	2.81
GLG312-2	2.78
GLG320-4	2.76
GLG316-3	2.75
GLG910-5	2.58
GLG912-2	2.54
GLG319-2	2.50

CRM GOLD ASSAY PILLS

25 x 1g pressed powder

Number	Au mg/kg (ppm)
GAP-06	2.2202
GAP-03	1.0000
GAP-05	0.5249
GAP-01	0.3237
GAP-04	0.2117
GAP-02	0.1025
GAP-07	0.0304

RM GOLD ORE

g/t = mg/kg = ppm 1 kg, last

Number	Au	Pd*	Pt*
CDN GS-50	50.5	.	.
CDN GS-20A	21.12	.	.

CRM 17034 GOLD ORE

Number	Au (mg/kg)	Units
IMS-261	7.03	Powder 1 kg
IMS-247	4.24	Powder 1 kg
IMS-231	3.43	Powder 1 kg
IMS-230	2.19	Powder 1 kg
IMS-237	2.06	Coarse Material 500 g
IMS-267	2.00	Powder 1 kg
IMS-266	1.03	Powder 1 kg
IMS-255	0.89	Powder 1 kg
IMS-227	0.82	Powder 1 kg
IMS-236	0.72	Coarse Material 500 g
IMS-226	0.61	Powder 1 kg
IMS-265	0.31	Powder 1 kg
IMS-235	0.23	Coarse Material 500 g
IMS-225	0.21	Powder 1 kg

CRM GOLD ORE

mg/kg (ppm) 10g or 1kg

Number	Au Fire Assay
G915-10	48.68
G310-10	48.53 last 1kg
G306-6	48.53
G914-8	33.30
G915-8	24.72
G917-2	24.36
G916-5	19.92
G917-8	17.12
G315-8	9.93
G310-8	7.97
G307-7	7.87
G313-7	6.93
G316-8	6.11
G316-7	5.85
G312-9	5.84
G314-5	5.29
G917-4	5.10
G310-1	4.94
G316-10	4.65
G915-1	4.56
G916-7	4.51
G306-7	4.50
G398-10	4.07
G910-3	4.02
G397-6	3.95
G905-7	3.92
G900-4	3.76
G913-5	3.70
G911-8	3.65
G307-1	3.37
G917-10	3.33
G310-9	3.29 last 1kg
G900-5	3.21
G305-8	3.14
G910-6	3.09
G998-10	3.05
G916-10	2.81
G914-1	2.57
G912-2	2.51
G914-2	2.48
G308-8	2.45
G314-7	2.45
G305-5	2.43
G313-8	2.43
G322-4	2.43
G322-4	2.43
G312-6	2.42
G913-2	2.40
G913-7	2.31
G913-6	2.19
G912-3	2.09
G313-2	2.04
G313-4	2.00
G300-10	1.99
G307-8	1.99
G916-2	1.98
G999-9	1.98

CRM GOLD ORE

mg/kg (ppm) 10g or 1kg

Number	Au Fire Assay
G316-9	1.75
G916-1	1.72
G312-5	1.60
G311-8	1.57
G300-9	1.53
G314-9	1.52
G910-9	1.51
G307-4	1.40
G316-6	1.40
G911-3	1.37
G913-4	1.37
G311-5	1.32
G911-10	1.30
G308-6	1.28
G914-3	1.24
G316-2	1.04
G314-8	1.03
G315-9	1.02
G310-5	1.01
G315-2	0.98
G910-10	0.97
G910-2	0.90
G399-5	0.87
G917-6	0.76
G911-7	0.72
G310-6	0.65
G322-2	0.65
G910-8	0.63
G912-8	0.53
G916-4	0.51
G322-1	0.34
G322-3	0.33
G311-3	0.27
G316-4	0.24
G311-6	0.22
G316-3	0.21
G911-5	0.20
G911-6	0.17
G315-5	0.10
G310-3	0.07

Number Au Fire Assay

CRM GOLD ORE

analysis listed in mg/kg (ppm) except % which is mass 10g or 200g units

Number	Au	Fire	Au Aqua	Ag	As	Co	Cu	Ni	Pb	S%	Zn
GBMS623-4	17.95	17.29	49.9	1263	106	22728	196	9476	3.88	19340	
GBMS623-3	5.85	5.46	3.7	570	332	10792	77	322	5.16	35	
GBMS304-4	5.67	5.29	3.4	535	.	9786	732	271	6.27	149	
GBMS623-2	3.13	2.93	6.9	450	55	3422	265	241	1.18	583	
GBMS911-2	2.88	2.82	1.24	62	78	1417	34	47	1.30	122	
GBMS304-3	2.68	2.51	1.5	263	137	3637	376	159	2.35	143	
GBMS304-5	1.62	1.59	0.8	99	68	2293	21	65	1.04	13	
GBMS911-3	1.33	1.31	0.17	13	31	7652	27	37	0.99	196	
GBMS911-1	1.04	1.04	1.19	335	31	10028	23	5844	1.40	1221	

Fire = Fire Assay, Aqua = Aqua Regia

CRM GOLD ORE

analysis listed in mass % except * which is mg/kg for U, M = /ICP and X = XRF D = Demotu/Specific Gravity

Number	Au*	Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SiO ₂	TiO ₂	U M	LOI	D	Units
AMIS 0429	22.93	.	0.48	(0.11)	4.97	0.54	.	(0.04)	.	1.57	87.70	.	0.0722	(1.87)	.	100 g
AMIS 0430	2.68	2.80	0.19	0.12	2.03	0.32	(0.11)	0.030	(0.06)	0.33	92.3	(0.14)	0.0113	(1.66)	2.71	100 g

CRM GOLD AND SILVER ORE

analysis listed in mg/kg (ppm) * and mass percent %

Number	Ag*	Au*	As%	S%	Sb%	Units
NCS DC28104	62.2	63.4	.	.	.	250 g
CGL 205	21.48	10.72	.	.	.	250 g
USZ 29-2000	6.05	42.26	.	.	.	100 or 200 g
VS 5938-91	6.5	36	8.45	28.73	0.021	100 g
VS 5937-91	6.4	33	7.78	25.83	0.019	100 g
VS 2739-83	5.7	34	8.0	26.0	0.020	100 g
NCS DC28107	20.4	20.0	.	.	.	250 g
NCS DC29103	18.0	20.0	.	.	.	500 g
CAN MA-1b	(4)	17.0	.	.	.	200 g
VS 5936-91	3.5	20	4.72	15.26	0.012	100 g
VS 5935-91	23	13	.	15.10	0.044	100 g
NCS DC28106	11.0	11.0	.	.	.	500 g
USZ 39-2005	49.33	10.92	.	.	.	250 g
VS 5934-91	1.8	8.9	2.11	6.77	0.0057	200 g
CAN MA-3a	(2.4)	8.56	.	.	.	200 g
USZ 40-2005	27.06	7.38	.	.	.	100 or 250 g
USZ 30-2000	1.18	5.92	.	.	.	250 g
NCS DC28105	5.8	5.0	.	.	.	500 g
VS 5933-91	1.1	4.6	1.08	3.35	0.0039	100 g
NCS DC29102	37.4	4.30	.	.	.	500 g
VS 8815-2006	0.75	4.25	1.000	3.27	0.00260	100 g
USZ 31-2000	1.07	3.28	.	.	.	250 g
CAN MA-2c	(0.51)	3.02	.	.	.	400 g
VS 5932-91	0.9	3.0	0.54	1.77	0.0021	100 g
NCS DC28102b	7.4	2.5	.	.	.	500 g
VS 8816-2006	0.360	2.13	0.500	1.64	0.00135	100 g
NCS DC28103	3.1	1.8	.	.	.	500 g
NCS DC28101	4.2	1.7	.	.	.	500 g
USZ 21-98	.	1.06	.	.	.	250 g
VS 2740-83	0.31	0.9	0.17	0.38	0.0019	100 g last
NCS DC29101	.	0.64	.	.	.	500 g
VS 5940-91	0.9	0.55	0.063	0.34	0.0075	100 g
VS 5939-91	0.7	0.37	.	0.24	0.0025	100 g
SRM 886	.	8.25	.	1.466	.	200 g
KZ 63-86	.	0.023	.	.	.	100 g
NCS DC90006	732	50 g
NCS DC90005	559	50 g
NCS DC90004	446	50 g
NCS DC90003	298	50 g
NCS DC29106	199	50 g
NCS DC29105	138.1	50 g
NCS DC90002	112	50 g
NCS DC29104	50.3	50 g
NCS DC90001	46.9	50 g

Number Ag* Au* As% S% Sb% Units

CRM GOLD AND SILVER ORE

minesite carbon material

data listed in mg/kg (ppm) 10 g units

Number	Au	Ag	
GLC302-3	7467	1248	
GLC323-2	4998	2410	last of stock
GLC323-1	4293	1825	
GLC922-1	3239	1581	
GLC323-3	3175	415	
GLC920-2	3161	473	
GLC921-1	2448	171	
GLC314-1	2031	947	last of stock
GLC922-3	1984	993	
GLC922-2	1102	558	
GBC319-4	808	225	
GBC323-2	789	225	
GBC917-2	770	219	
GBC323-1	713	208	
GBC321-2	713	207	
GBC917-3	628	195	
GBC922-3	546	225	
GBC323-3	475	67	
GBC911-3	470	596	last of stock
GBC902-3	285	83	last of stock
GBC314-1	51	38	last of stock
GBC922-2	19	34	

Number Au Ag

RM GOLD AND SILVER ORE

data in mg/kg (ppm) 100 g, last

Number	Au	Ag
CDN GS-1Q	1.24	40.7

RM GOLD AND SILVER ORE

analysis listed in mg/kg (ppm) 1 kg, last

Number	Ag	Au	Au
CDN GS-8C	.	8.59 FA/Inst	8.62 FA/Grav

CRM 17034 GOLD ORE

analysis in mg/kg 60 g units

Number	Au	Pd	Pt
IMS-328	16.80	.	.
IMS-330	7.75	.	.
IMS-333	2.99	.	.
IMS-334	1.45	.	.
IMS-348	1.00	0.41	0.42
IMS-336	0.61	0.094	0.094
IMS-349	0.0082	0.0026	0.0025
IMS-401	0.0002	<0.0002	<0.0005

CRM GOLD AND SILVER ORE - CONTINUED ON THE NEXT PAGES

analysis listed in mass % except * which is mg/kg

OREAS samples list multiple methods, more information upon request

Number	Au*	Ag*	As	Ba	Cu	Fe	Fe ₂ O ₃	Pb	S	SO ₃	Sb	Zn	LOI
CAN DS-1	32.59	0.47	0.6960	0.0221	0.00271	(3.0)	.	0.00138	(2.609)	.	(0.0107)	0.0206	(13)
USZ 38-2005	31.28	.	.	0.02	0.43	.	14.71	0.006529	2.59
USZ 20-98	10.05	3.05	1.92	0.95
KZ 3597-86	8.8	.	3.96
UNS AuM	2.5	.	0.08765	BaO:0.066	0.00359	.	5.55
USZ 41-2006	0.91	.	.	0.0249	0.75	.	.	0.0027	.	3.87	.	0.0136	5.43
CAN CH-4	0.88	2.1	0.00088	(0.0425)	0.20	5.42	.	.	0.63	.	0.77	0.020	(0.9)
USZ 34-2002	0.79	1.7	0.12	.	0.001484	2.18T	.	0.002	.	.	0.14	0.0025	2.84
US DGPM-1	0.73	.	0.0180	.	.	.	1.92	.	.	.	0.0014	.	.
USZ 35-2002	0.57	1.25
KZ 6585-93	0.28	11.6	0.075	.	0.064	.	.	0.12	.	.	.	0.60	.
CAN GTS-2a	0.272	(0.64)	0.0124	0.0186	0.00886	7.56	.	.	0.348	.	(0.000133)	0.0208	(9.87)
OREAS 24b	<0.003	.	(0.00100)	BaO:0.0819	.	.	6.35	.	0.190	.	.	(0.0113)	2.46
OREAS 24b 4	.	(0.127)	(0.000835)	0.0716	0.00380	4.39	.	0.00231	0.198	.	0.000100	0.0105	.
OREAS 24b A	(0.002)	(0.058)	0.000796	0.0146	0.00364	3.93	.	0.000923	0.200	.	(0.000048)	0.0093	.
OREAS 24b F	.	(2.17)	(0.000974)	0.0739	(0.00351)	4.45	.	(0.00229)	0.203	.	(0.000133)	(0.0103)	.
OREAS 22d	<0.001	<0.1	<0.0001	0.000617	0.000923	0.468	.	0.000072	(<0.01)	.	0.000021	0.000670	.

Number	Al	Al ₂ O ₃	C	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	Si	SiO ₂	Ti	TiO ₂
CAN DS-1	4.48	.	(3.126)	(6.248)	.	(1.1)	.	2.76	.	0.0437	.	.	.	0.0340	.	(25.68)	.	.	.
USZ 38-2005	.	2.03	.	.	0.56	.	0.64	.	1.01	.	0.03	.	0.17	.	0.05	.	77.37	.	0.15
USZ 20-98	.	1.70	.	.	0.77	.	0.37	.	.	.	0.025	.	0.07	.	0.037	.	92.57	.	0.08
KZ 3597-86
UNS AuM	.	14.06	.	.	4.09	.	1.92	.	1.81	.	0.082	.	3.08	.	.	.	66.15	.	0.39
USZ 41-2006	.	14.58	.	.	3.14	.	2.81	.	5.52	.	0.12	.	2.36	.	0.27	.	52.09	.	0.93
CAN CH-4	7.73	.	0.12	1.96	.	1.81	.	1.43	.	0.043	.	3.26	.	0.061	.	.	63.10	0.31	.
USZ 34-2002	.	4.79	.	.	2.53	.	1.48	.	0.37	.	0.017	.	0.055	.	0.125	.	84.70	.	0.17
US DGPM-1	.	9.56	.	.	(0.22)	.	2.74	.	(0.56)	79.82	.	.
USZ 35-2002
KZ 6585-93
CAN GTS-2a	6.96	.	2.011	4.01	.	2.021	.	2.412	.	0.1510	.	0.617	.	0.0892	.	23.65	.	(0.5*)	.
OREAS 24b	.	15.15	0.189	.	1.47	.	3.39	.	2.75	.	0.059	.	1.15	.	0.161	.	66.0	.	0.798
OREAS 24b 4	8.02	.	.	1.08	.	2.81	.	1.65	.	0.044	.	0.846	.	0.069	.	.	.	0.468	.
OREAS 24b A	3.15	.	.	0.461	.	1.17	.	1.36	.	0.035	.	0.108	.	(0.062)	.	.	.	0.198	.
OREAS 24b F	7.81	.	.	1.06	.	2.74	.	1.62	.	0.046	.	0.824	.	(0.073)	.	31.12	.	0.481	.
OREAS 22d	0.132	.	.	(0.010)	.	(0.008)	.	(0.009)	.	0.011	.	(0.009)	.	(0.001)	.	.	.	0.021	.

Number	B	Be	Bi	Cd	Ce	Co	Cr	Cr ₂ O ₃	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf	Hg
CAN DS-1	.	(0.819)	(0.1)	(0.98)	(40)	9.5	(59)	.	(7)	.	.	(1)	(10)	.	.	(4)	82
USZ 38-2005
USZ 20-98
KZ 3597-86	1.08%	0.17%
UNS AuM	47	12.9
USZ 41-2006	24.3	99.3
CAN CH-4	.	.	.	1.14	.	26	114
USZ 34-2002
US DGPM-1
USZ 35-2002
KZ 6585-93	.	.	.	96
CAN GTS-2a	.	.	.	(0.58)	.	22.1	(270)
OREAS 24b	(28.3)	.	201
OREAS 24b 4	.	2.92	0.68	(0.049)	84	16.9	118	.	10.7	(4.47)	(2.54)	(1.36)	20.1	(6.02)	(0.83)	3.90	
OREAS 24b A	(6.23)	(1.65)	0.73	(0.046)	(61)	15.7	106	.	9.15	(2.65)	(1.21)	(0.66)	10.8	(3.96)	(0.26)	(0.52)	
OREAS 24b F	(69)	2.95	(1.03)	.	86	16.9	142	.	10.5	5.83	3.41	1.39	20.2	6.27	(1.64)	6.15	
OREAS 22d	.	(0.066)	<0.1	<0.1	(2.43)	0.85	(11.9)	.	(0.10)	(0.15)	(<0.1)	(<0.05)	(0.26)	(0.20)	(0.065)	0.22	

Number	B	Be	Bi	Cd	Ce	Co	Cr	Cr ₂ O ₃	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf	Hg
--------	---	----	----	----	----	----	----	--------------------------------	----	----	----	----	----	----	----	----	----

CRM GOLD AND SILVER ORE - CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mg/kg except % which is mass %

OREAS samples list multiple methods, more information upon request

Number	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pd	Pr	Pt	Rb	Re	Sc	Se	Sm
CAN DS-1	.	(0.5)	(20)	(20)	48.7
USZ 38-2005	0.11%	.	.	28.27
USZ 20-98
KZ 3597-86
UNS AuM
USZ 41-2006	51.8	.	.	25.4
CAN CH-4	51	2.1	.
USZ 34-2002
US DGPM-1
USZ 35-2002
KZ 6585-93
CAN GTS-2a	77.1
OREAS 24b	(59)	<0.001	.	<0.001
OREAS 24b 4	(0.80)	(0.077)	42.4	52	(0.32)	4.03	14.6	(36.2)	60	.	(9.86)	.	164	(0.002)	15.3	(0.66)	(7.06)
OREAS 24b A	(0.46)	(0.048)	(29.2)	45.6	(0.20)	3.86	(0.31)	(24.6)	57	(<0.01)	(6.87)	(0.001)	114	(<0.001)	9.51	(0.42)	(4.68)
OREAS 24b F	1.17	.	44.0	52	0.49	(4.91)	16.0	38.7	61	.	10.2	.	161	(<0.1)	14.1	.	7.17
OREAS 22d	(<0.05)	(<0.005)	(1.20)	14.2	(0.013)	2.36	0.88	(1.03)	4.38	(<0.005)	(0.32)	(<0.005)	0.54	(<0.002)	(0.20)	(<1)	(0.22)

Number	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	W	Y	Yb	Zr	Units	Other
CAN DS-1	20	400 g	
USZ 38-2005	.	88.71	0.01%	.	.	.	250 g	
USZ 20-98	250 g	last of stock
KZ 3597-86	100 g	last of stock
UNS AuM	.	187.7	14.2	.	81	200 g	
USZ 41-2006	.	259	78.3	100 g	
CAN CH-4	.	(209)	200 g	
USZ 34-2002	250 g	
US DGPM-1	(76)	200 g	H ₂ O: 0.10- last of stock
USZ 35-2002	250 g	
KZ 6585-93	100 g	
CAN GTS-2a	.	92.8	.	.	.	1.244	350 g	
OREAS 24b	.	(134)	60 g	last of stock Cl: (<10ppm)
OREAS 24b 4	4.25	124	1.23	(0.87)	.	16.4	0.86	(0.31)	3.06	3.64	19.9	(2.17)	134	" 4 acid digestion, GRANODIORITE	
OREAS 24b A	2.26	(29.0)	.	(0.54)	.	14.3	0.66	(0.17)	1.74	(1.19)	12.3	(1.15)	24.5	" aqua regia	
OREAS 24b F	4.65	125	1.32	0.98	.	16.5	0.91	0.50	3.31	4.13	32.5	3.24	213	" fusion ICP-OES/MS	
OREAS 22d	0.61	(1.14)	(0.036)	(<0.05)	(<0.05)	0.67	(<0.02)	(<0.05)	0.18	0.21	0.69	(<0.1)	7.02	10 g	V: 2.63 last then 22e

GRANITE WITH EXTENSIVE ANALYSIS

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI
1	JG-2	76.83	12.47	.	0.70	(0.0972)	0.57	0.33	0.97	+0.33 -0.12	4.71	0.037	0.016	3.54	0.002	0.044	.
1	SARM 1	75.70	12.08	(0.10)	0.78	0.42	1.30	(0.6)	2.00	0.49	4.99	(0.06)	.	3.36	.	(0.09)	.
1	VS 3333-85	74.76	10.64	(0.1)	0.32	0.062	1.61	4.50	.	(0.30)	4.64	0.10	0.120	4.24	0.024	0.26	.
2	IAG OU-3	74.09	11.10	1.913	0.2	0.1100	3.255	.	3.8341	.	4.55	.	0.090	3.678	.	0.224	1.815
1	IAG GMN-1	73.50	13.47	C: (0.0862)	1.00	.	.	.	1.96	.	4.80	(0.37)	0.050	3.83	0.060	0.210	.
1	GUV GM	73.42	13.55	0.28	1.07	0.067	1.13	2.01	.	0.35	4.76	0.37	0.043	3.78	0.062	2.12	.
1	USZ 47-2008	72.37	14.07	.	1.15	.	1.81	2.44	.	.	4.68	0.38	0.06	3.63	0.13	0.30	0.64
1	USZ 28-99	71.61	16.13	.	0.39	1.25	0.29	.	0.51	-(0.05)	3.52	(0.29)	0.13	5.25	0.028	(0.03)	1.14
1	MBH-GNH-P	71.3	14.2	.	1.56	.	.	1.82	.	.	4.3	0.75	.	3.66	.	0.278	1.05
1	SARM 48	67.11	11.24	.	8.90	.	(0.2)	0.58	.	.	4.26	0.18	0.02	3.22	(0.09)	0.10	.
1	NCS DC73376	66.27	16.33	0.35	2.66	0.0670	(1.6)	.	3.12	(1.0)	2.60	1.63	.	5.3	.	.	1.28

continued analysis listed in mg/kg except % which is mass % and * which is ng/g

Number	Ag	Al%	As	B	Ba	Be	Bi	Ca%	Cd	Ce	Cl	Co	Cr	Cs	Cs ₂ O%	Cu	Dy
JG-2	(0.019)	6.60	(0.68)	(1.78)	81.0	3.26	(0.64)	0.50	(0.004)	48.3	.	3.62	6.37	6.79	.	0.49	10.5
SARM 1	(120)	195	.	.	12	.	.	12	(17)
VS 3333-85	(0.06)	.	(4)	11	90	5	.	.	.	90	.	1.3	3.1	4.5	.	12	(10)
IAG OU-3	.	.	3.3793	.	28	10.94	.	.	0.38	196.3	.	.	18.61	0.66	.	3.3	18.87
IAG GMN-1	.	.	(2.12)	.	344	5.00	0.160	.	(0.026)	70.0	.	2.11	(545)	8.07	.	(2.49)	4.75
GUV GM	(0.09)	.	4.1	11	340	(4.8)	.	.	.	65	.	3.7	11	8.1	.	13	(5.4)
USZ 47-2008	.	.	2.28	.	350	8.63	1.03	.	.	64.38	.	2.71	182	17.02	.	7.36	4.42
USZ 28-99	.	.	(3)	(25)	.	.	(130)	.	0.012	8	.
MBH-GNH-P	(0.03)	.	(0.8)	.	852	4.5	(0.04)	.	(0.02)	43	.	3.6	(22)	5.0	.	8	1.82
SARM 48	(290)	(850)	.	.	23	.	.	(10)	.
NCS DC73376	0.03	.	(0.25)	15	1140	1.7	0.096	.	(0.06)	48	(120)	7.8	24	2.6	.	(3.1)	1.52

Number	Er	Eu	Fe%	Ga	Gd	Ge	Hf	Hg	Ho	In	K%	La	Li	Li ₂ O%	Lu	Mg%	Mn%
JG-2	6.04	0.10	0.68	18.6	8.01	(1.70)	4.73	(0.0033)	1.67	.	3.91	19.9	42.2	.	1.22	0.02	0.012
SARM 1	.	0.35	.	27	(14)	109	(12)	.	(2)	.	0.0160
VS 3333-85	(6)	0.4	.	27	.	2.2	12	45	52	.	0.9	.	.
IAG OU-3	11.44	1.152	.	32.1	18.073	1.5	22.631	.	4.011	.	.	94.64	1.41	.	1.628	.	.
IAG GMN-1	2.98	0.60	.	17.6	4.51	(1.67)	5.26	.	0.97	(0.033)	.	36.2	.	.	0.476	.	.
GUV GM	(2.2)	0.60	.	15	(5.2)	(1.6)	5.1	(0.0033)	(1.0)	.	.	41	50	.	0.40	.	.
USZ 47-2008	2.37	0.58	.	22.80	4.95	1.50	4.75	.	0.85	.	.	29.59	124	.	0.35	.	.
USZ 28-99	(15)	.	0.37	.	.	.
MBH-GNH-P	0.79	0.84	.	21.9	2.9	(0.6)	2.5	.	0.31	(0.04)	.	21.1	94	.	0.10	.	0.0284
SARM 48
NCS DC73376	0.76	1.0	.	18.2	2.4	0.93	3.3	0.0035	0.27	(0.03)	.	25	24.7	.	0.11	.	0.0430

Number	Mo	Na%	Nb	Nd	Ni	P%	Pb	Pr	Rb	Rb ₂ O%	S	Sb	Sc	Se	Si%	Sm	Sn	Sr
JG-2	0.37	2.63	14.7	26.4	(4.35)	0.001	31.5	6.20	301	.	(7.0)	(0.057)	2.42	.	35.91	7.78	3.00	17.9
SARM 1	.	.	53	72	(8)	.	40	.	325	15.8	.	10
VS 3333-85	1.7	.	17	50	6	.	10	.	140	.	(160)	(0.5)	4.6	.	10	5	8	
IAG OU-3	1.975	.	80.2	87	.	.	36	22.7	171	.	.	0.3	.	.	18.71	11.45	11.2	
IAG GMN-1	1.64	.	(22.6)	26.6	8.93	.	31.9	7.80	255	.	.	0.095	4.99	.	.	5.24	5.62	136
GUV GM	1.1	.	18	30	6.8	.	30	(7.2)	260	.	.	(0.51)	4.8	.	.	4.9	4.4	133
USZ 47-2008	3.06	.	15.22	27.10	5.76	.	24.81	7.27	275	.	.	0.19	4.36	.	.	5.54	13.30	111
USZ 28-99	.	.	71	.	10	.	64	.	.	0.24	.	.	(7)
MBH-GNH-P	(0.3)	.	6.6	18.6	(10)	0.0347	45	4.8	164	.	143	(0.1)	4.1	(0.1)	.	3.8	2.9	318
SARM 48	(5)	.	202	.	.	.	135	29
NCS DC73376	(0.27)	.	4.5	21	13	0.0570	7.6	5.8	57	.	(50)	0.063	5.0	0.019	.	3.3	0.8	690

Number	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
JG-2	2.76	1.62	.	1.62	0.026	1.55	1.16	11.3	3.78	23.0	86.5	6.85	13.6	97.6	20 g
SARM 1	.	3.0	.	51	0.0540	.	(2)	(15)	(2)	.	143	14.2	50	300	100 g
VS 3333-85	1.1	0.4	.	80	.	.	1.8	6	(1.1)	.	60	7	140	470	100 g
IAG OU-3	5.748	3.081	.	22.845	.	0.735	1.731	5.5396	.	.	113.1	11.3	149.22	942	~35 g
IAG GMN-1	1.80	0.737	.	35.1	.	1.52	0.450	12.4	13.2	3.90	29.7	3.04	31.8	142	35 g
GUV GM	1.7	0.7	.	36	.	.	6.4	11	1.6	26	7	3.1	34	149	50 g
USZ 47-2008	2.56	0.79	.	19.35	.	1.72	0.37	5.44	14.03	0.56	25.19	2.36	54.59	169	100 g
USZ 28-99	54	0.086%	46	100 g
MBH-GNH-P	(1.0)	0.38	.	7.8	.	0.95	0.105	5.4	30	(0.3)	8.7	0.66	49	88	85 g
SARM 48	.	.	.	113	.	.	.	(8)	.	.	436	.	53	300	100 g
NCS DC73376	(0.34)	0.29	.	1.9	0.1800	(0.20)	0.11	(0.4)	45	0.38	7.3	0.69	47	(100)	70 g

CRM GRANODIORITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	Al	CO ₂	CaO	Fe	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Si	TiO ₂	
JG-1a	72.30	14.30	7.57	.	2.13	1.40	1.36	0.51	2.00	+0.59	-0.12	3.96	0.69	0.057	3.39	0.083	33.80	0.25
JG-1	72.30	14.24	7.54	.	2.20	1.52	1.61	0.38	2.18	+0.54	-0.07	3.98	0.74	0.063	3.38	0.099	33.80	0.26
JG-3	67.29	15.48	8.19	.	3.69	2.58	1.83	1.62	3.69	+0.67	-0.17	2.64	1.79	0.071	3.96	0.122	31.45	0.48
US GSP-2	66.6	14.9	7.88	.	2.10	3.43	.	.	4.90	.	.	5.38	0.96	.	2.78	0.29	31.1	0.66
VS 2125-81	64.08	15.35	.	0.14	3.93	.	2.87	5.23	.	.	.	3.98	1.87	0.160	3.25	0.228	.	0.517
GBW 07111	59.68	16.56	.	0.15	4.72	.	3.08	2.64	.	0.88	.	3.50	2.81	0.094	4.05	0.34	.	0.77

continued analysis listed in mg/kg except % which is mass % and * which is ppb

Number	Ag	As	Au*	B	Ba%	Be	Bi	Br	C%	Ca%	Cd	Ce	Cl%	Co	Cr	Cs	Cu
JG-1a	(0.023)	(0.43)	0.21	3.95	0.0470	3.16	(0.43)	.	(0.0295)	1.52	(0.026)	45.0	(0.0065)	5.90	17.6	10.6	1.67
JG-1	0.034	0.33	0.11	6.87	0.0466	3.15	0.50	(0.068)	(0.0216)	1.57	0.040	45.8	0.00581	4.06	53.2	10.1	2.52
JG-3	(0.029)	(0.37)	0.17	(2.15)	0.0466	(1.60)	(0.05)	.	(0.0120)	2.64	(0.054)	40.3	(0.0156)	11.7	22.4	1.78	6.81
US GSP-2	0.1340	(1.5)	.	.	.	1.50	.	410	.	7.3	20	(1.2)	43
VS 2125-81	.	.	.	27	0.14	3.7	13	37	.	57
GBW 07111	0.066	0.4	.	3.92	0.1900	2.11	0.05	(0.34)	(0.057 Org)	.	0.08	112	0.023	15.6	37.6	0.97	8.8

Number	Dy	Er	Eu	F%	Ga	Gd	Ge	Hf	Hg*	Ho	I*	In	Ir*	K%	La	Li	Lu
JG-1a	4.44	2.57	0.70	0.0439	16.5	4.08	(1.5)	3.59	(4.1)	0.82	.	(0.025)	.	3.29	21.3	79.5	0.44
JG-1	4.14	2.16	0.73	0.0498	17.8	4.28	1.44	3.56	16.5	0.81	(0.012)	(0.044)	.	3.30	22.4	86.6	0.39
JG-3	2.59	1.52	0.90	(0.0317)	17.1	2.92	(1.06)	4.29	(2.4)	0.38	.	.	(0.0016)	2.19	20.6	20.9	0.26
US GSP-2	(6.1)	(2.2)	2.3	(0.3000)	22	(12)	.	(14)	.	(1.0)	.	.	.	4.48	180	(36)	(0.23)
VS 2125-81	22	.	1.8	20	.	.
GBW 07111	3.20	1.57	1.91	0.084	20.8	5.09	1.00	5.2	35	0.60	(78)	0.08	.	60.5	16.2	0.24	

Number	Mg%	Mn%	Mo	Na%	Nb	Nd	Ni	P%	Pb%	Pd*	Pr	Rb%	S%	Sb	Sc	Se	Sm
JG-1a	0.42	0.044	0.45	2.51	11.4	20.4	6.91	0.036	0.00264	(<0.2)	5.63	0.0178	(0.0011)	(0.048)	6.21	.	4.53
JG-1	0.45	0.049	1.75	2.51	12.4	19.3	7.47	0.043	0.00254	(<0.2)	4.83	0.0182	0.00109	0.13	6.53	0.0030	4.62
JG-3	1.08	0.055	0.45	2.94	5.88	17.2	14.3	0.053	0.00117	(<0.2)	4.70	0.00673	(0.0055)	(0.08)	8.76	.	3.39
US GSP-2	0.58	0.0320	(2.1)	2.06	27	200	17	0.13	0.0042	.	(51)	0.0245	.	.	6.3	.	27
VS 2125-81	.	.	3.22	.	8.8	.	15	.	0.016	.	.	0.016	0.019	.	13	.	.
GBW 07111	.	.	0.47	.	10.6	48.1	24.4	.	0.00198	.	13.2	0.00701	0.011	0.06	10.3	0.03	7.74

Number	Sn	Sr%	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn%	Zr%	Units
JG-1a	4.47	0.0187	1.90	0.81	.	12.8	0.15	0.98	0.38	4.69	22.7	12.4	32.1	2.70	0.00365	0.0118	20 or 100 g
JG-1	3.60	0.0184	1.79	0.78	.	13.2	0.16	1.03	0.41	3.47	25.2	(1.58)	30.6	2.47	0.00411	0.0111	20 g
JG-3	1.40	0.0379	0.70	0.46	.	8.28	0.29	(0.40)	0.24	2.21	70.1	(14.1)	17.3	1.77	0.00465	0.0144	100 g
US GSP-2	.	0.0240	.	.	.	105	0.40	(1.1)	(0.29)	2.40	52	.	28	1.6	0.0120	0.0550	50 g
VS 2125-81	8.0	0.048	0.016	.	90	.	0.012	.	0.021	40 g	
GBW 07111	1.44	0.1198	0.62	0.68	0.011	10.9	.	0.39	0.26	1.40	104	0.19	15.5	1.56	0.00854	0.0224	50 g

GRAPHITE

analysis listed in mass % Graph = Graphitic, T = Total CDN: RM, all others: CRM CDN: 10 g GGC: 10 g NCS: 50 g USZ: 100 g

Number	Al ₂ O ₃	C.Graph	T.C	CO ₂	CaO	Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	Ni	P ₂ O ₅	Rb	S	SiO ₂	TiO ₂	Zn	Zr	LOI
NCS DC60121	5.60	76.50	.	0.28	0.74	1.48T	1.98	0.99	0.50	0.022	0.23	.	0.16	.	0.14	10.34	0.55	Volatile:2.72	Ash:20.78	
GGC-15	.	26.66	28.19	1.14
GGC-16	.	25.85	27.52	1.52
GGC-17	.	23.86	24.84	1.01
GGC-18	.	18.22	18.96	0.97
GGC-19	.	15.29	15.69	0.62
GGC-20	.	12.75	13.13	0.44
USZ 32-2000	9.33	(12.0)	14.43	4.10	7.05	3.48	.	2.54	1.94	0.03	0.47	0.007	.	0.014	.	52.20	0.57	0.018	0.012	22.21
USZ 33-2000	8.46	(11.34)	13.38	2.45	.	3.61	.	2.09	.	0.07	0.51	52.84	0.49	.	.	17.0
NCS DC60120	13.03	9.91	.	0.67	5.34	6.99T	2.80	2.17	5.35	0.054	1.56	.	0.14	.	2.59	49.34	0.64	.	.	.
GGC-21	.	9.79	10.40	0.50
GGC-22	.	7.10	7.48	0.24
GGC-23	.	5.53	5.79	0.23
GGC-24	.	3.56	3.72	0.17
GGC-25	.	3.94	3.12	0.14
CDN GR-1	(8.6)	3.12	.	.	(6.3)	(4.2)	.	(3.0)	(2.4)	(<0.1)	(0.3)	.	.	.	(1.0)	(65.3)	(0.4)	.	last	(6.8)
NCS DC60119	12.93	2.91	.	3.60	9.37	6.73T	2.60	2.54	6.10	0.084	1.60	.	0.13	.	1.18	49.84	0.57	.	.	.
GGC-26	.	1.71	1.85	0.10
GGC-27	.	1.19	1.32	0.09
GGC-08	.	0.39	1.03	1.57
GGC-07	.	0.13	0.56	0.51

CRM	GRAPHITE ORE												analysis listed in mass %		50 g units	
Number	Al ₂ O ₃	Ash	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	Volatile			
NCS DC28120	10.93	95.62	11.81	5.34	2.39	8.79	0.048	1.50	0.083	1.06	52.73	0.39	2.22			
NCS DC28121	10.72	90.65	11.12	5.00	2.32	8.43	0.047	1.38	0.083	0.99	50.28	0.36	2.48			
NCS DC28119	8.13	29.00	0.23	2.09	1.33	0.55	0.032	0.28	0.087	0.02	15.66	0.44	2.88			
NCS DC28118	1.92	11.45	0.91	1.98	0.19	1.00	0.021	0.088	0.007	0.49	5.00	0.085	1.87			
NCS DC28117	0.63	3.47	0.19	0.46	0.17	0.18	0.005	0.009	0.004	0.17	1.76	0.014	1.33			

CRM	GRAPHITE - SYNTHETIC															analysis listed in mg/kg		50 g units	
available as a set or individually																			
Number	Al	As	Ca	Cl	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	NO ₃	Na	Ni	Pb			
CIBA KD-2	35	(0.05)	98	(4.1)	(0.10)	1.3	1.0	180	(41)	(21)	23	(0.22)	(0.5)	(20)	3.9	(1.6)			
CIBA LD-4	33	(0.06)	126	(3.3)	(0.11)	3.4	1.3	149	(25)	(7.5)	3.5	(0.62)	(0.5)	(13)	5.5	(1.1)			
CIBA KD-3	15	(0.04)	62	(4.4)	(0.07)	0.69	0.81	111	(39)	(22)	13	(0.44)	(0.5)	(17)	4.2	(0.90)			
CIBA KD-6	8.4	(0.04)	79	(3.3)	(0.03)	0.44	0.62	37	(17)	.	4.3	(0.39)	(0.5)	(7)	2.0	(1.2)			
CIBA PD-7	5.5	(0.03)	22	(6.4)	(0.03)	2.2	0.51	59	(17)	.	1.1	(0.25)	(0.5)	(2)	1.1	(1.0)			

continued

Number	S	SO ₄	Sb	Si	Sn	Sr	Ta	Ti	V	W	Zn	Zr
CIBA KD-2	(44)	(88)	(0.05)	(145)	(<0.2)	(2.8)	(0.005)	(46)	(3.6)	(<0.08)	(4.4)	(3.7)
CIBA LD-4	(68)	(98)	(0.03)	(404)	.	(2.7)	(0.011)	(49)	(4.3)	(<0.06)	(2.9)	(8.6)
CIBA KD-3	(43)	(85)	(0.02)	(147)	.	(1.9)	(0.006)	(38)	(3.8)	(<0.08)	(1.2)	(4.5)
CIBA KD-6	(44)	(73)	(0.03)	(66)	.	(1.9)	(0.006)	(51)	(4.9)	(0.03)	(1.7)	(6.0)
CIBA PD-7	(23)	(25)	(0.02)	(50)	.	(1.3)	(0.005)	(29)	(2.0)	(0.03)	(0.9)	(4.5)

CRM	GREISEN													analysis listed in mass%		T = Total		CGL: 17025, 100 g units		GUW: 50 g units	
Number	SiO ₂	Al ₂ O ₃	CaO	F	Fe ₂ O ₃	FeO	K ₂ O	MgO	MnO	Na ₂ O	Li	P ₂ O ₅	Rb	Sn	TiO ₂	Zn	Zr	LOI			
CGL 022	80.93	10.26	0.836	(1.48)	3.25T	.	(1.47)	0.044	0.102	(0.038)	.	0.018	(0.0463)	0.1884	0.086	0.0273	0.0148	1.46			
GUW GNA	71.47	14.7	0.62	3.32	5.92	3.81	2.63	0.168	0.034	0.08	0.49	.	0.202	0.19	0.022	0.0078	0.0070	.			

continued analysis listed in mg/kg

Number	As	Ba	Bi	Cr	Cs	Cu	Dy	Ga	Mo	Nb	Sr	Ta	Th	U
CGL 022	63.6	(25.6)	(29.6)	271	(29.7)	563	(14.1)	26.1	.	28.4	16.6	(4.01)	32.9	(6.12)
GUW GNA	7	51	220	.	45	.	3	.	100	.	.	29	.	22

also 19 more informational elements

CRM	GYPSUM ROCK													analysis listed in mass %		100 g units	
Number	SO ₃	CaO	Al ₂ O ₃	CO ₂	Fe ₂ O ₃ *	H ₂ O	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	SrO	L.O.I.**				
DOMTAR GYP A	46.2	32.9	0.10	0.47	0.05	19.4	0.021	0.18	0.009	0.011	0.45	0.11	20.06				

* Total iron calculated as Fe2O3

** Loss on ignition at 1000°C

continued analysis listed in mg/kg

Number	As	Ba	Br	Cd	Ce	Cl	Co	Cr	Cs	Eu	Hf	La
DOMTAR GYP A	0.19	(28)	(0.5)	0.51	(0.7)	12	(0.2)	(2)	(0.15)	0.06	0.26	0.24

continued

Number	Lu	Mn	Rb	Sb	Sc	Sm	Th	Ti	U	Yb	Zn	Zr
DOMTAR GYP A	(0.006)	19	(0.8)	0.04	0.09	0.041	(0.1)	(78)	0.1	0.02	7	(9)

CRM GYPSUM ROCK

analysis listed in mass %

Number	SO ₃	CaO	Al ₂ O ₃	CO ₂	Cl	F	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	SrO	TiO ₂	LOI	Units
GBW 03109a	51.91	39.24	0.34	(4.02)	0.033	.	0.16	0.39	0.094	1.74	0.065	.	1.68	(0.27)	0.016	4.55	50 g
NCS DC62008a	43.12	31.60	0.77	.	0.067	(0.09)	0.35	.	0.15	0.45	0.09	(0.05)	2.29	.	0.05	21.00	20 g
NCS DC62106d	43.91	32.21	0.25	.	.	.	0.20	.	0.08	0.72	0.11	.	0.99	.	0.01	21.52	20 g
GBW 03111a	40.72	32.30	0.14	(5.44)	0.0032	.	0.11	17.95	0.026	2.47	0.014	.	0.63	(0.096)	0.010	23.60	50 g
NCS DC62009	39.01	27.94	0.42	.	0.002	(0.09)	0.12	.	0.11	0.02	0.06	0.99	13.30	.	0.10	18.69	20 g
GBW 03111	37.64	30.28	1.14	(5.80)	0.013	.	0.38	16.62	0.23	3.19	0.014	.	4.16	(0.077)	0.058	(22.88)	50 g

RM GYPSUM BYPRODUCT

analysis listed in mass % based on a dry (40°C) sample

100 g units

Number	SO ₃	CaO	Al ₂ O ₃	CO ₂	Cr ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	SrO	TiO ₂	V ₂ O ₅	%Total	LOI*
DOMTAR FGD-1	46.4	32.7	0.023	0.02	0.0002	0.014	20.70	0.007	0.007	0.005	0.03	0.13	0.012	.	0.0003	100.05	21.04
DOMTAR FGD-2	45.6	32.8	0.033	0.62	0.0015	0.043	20.38	0.01	0.019	0.02	0.05	0.21	0.024	.	0.0009	98.81	21.33
DOMTAR TIG-1	43.4	32.3	0.57	1.41	0.036	0.26	20.3	0.008	0.12	0.036	0.04	0.11	0.42	0.82	0.10	99.93	22.03

H₂O+ combined water at 250°C * Loss on ignition at 1000°C (1 hr)

continued

analysis listed in mg/kg

Number	As	Ce	Cl	Co	Cr	Dy	Eu	F	Hf	La	Mn	Sb
DOMTAR FGD-1	0.10	0.5	(100)	0.02	1.2	.	0.02	95	.	0.35	2.0	0.03
DOMTAR FGD-2	0.48	1.7	(115)	0.07	10.2	0.48	0.09	320	0.06	2.18	2.5	0.024
DOMTAR TIG-1	0.22	6	400	0.26	246	0.42	0.08	230	3.0	2.7	36	0.05

Number	Sc	Se	Sm	Ta	Tb	Th	Ti	U	V	Yb	Zn	Zr
DOMTAR FGD-1	0.023	0.8	0.07	.	.	0.03	75	.	1.5	.	1.7	.
DOMTAR FGD-2	0.166	3.0	0.52	.	0.07	0.38	75	1.10	5.1	0.27	2.3	(10)
DOMTAR TIG-1	17.1	.	0.65	3.1	(2)	2.14	6154	2.5	560	0.31	(32)	(80)

CRM HORNBLENDITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	Al ₂ O ₃	CO ₂	CaO	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	Mn	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	Ti	TiO ₂	LOI
VS 2113-81	14.24	.	11.04	9.72	18.26	.	0.382	12.70	.	0.144	2.14	.	.	37.95	.	1.91	.
NCS DC73377	13.76	(0.16)	9.6	10.8	14.8	(1.7)	0.48	7.2	0.1600	.	2.07	.	(0.0060)	49.62	0.5510	.	1.06
JH-1	5.66	.	15.02	(8.09)	10.27	.	0.53	16.73	.	0.19	0.71	0.099	.	48.18	.	0.67	.

continued analysis listed in mg/kg except * which is ng/g

Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Cl	Co	Cr	Cs	Cu%	Dy	Er	Eu	F	Ga	Gd
VS 2113-81	.	.	.	99	.	.	.	74	15	.	0.074	25	.
NCS DC73377	(0.05)	26	12	62	0.34	(0.06)	(0.14)	7.7	(116)	52	137	1.8	0.0084	3.5	2.3	0.91	200	17.2	2.8
JH-1	.	.	.	106	.	.	.	17.6	.	51.5	616	0.87	0.00086	2.5	1.2	0.86	.	7.9	.

Number	Ge	Hf	Hg*	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	Sb	Sc
VS 2113-81	1.3	.	.	57	.	4.9	.	.	.	58
NCS DC73377	1.46	1.5	3.3	0.85	(0.06)	2.9	11.2	0.39	0.15	2.7	6.5	117	360	(8)	1.25	29	0.63	43
JH-1	.	1.4	.	0.53	.	7.9	.	0.17	0.77	4.2	11.6	58.2	.	2.6	.	14.4	.	77.6

Number	Se	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
VS 2113-81	.	.	2.9	39	1.5	1370	21	40 g
NCS DC73377	0.083	2.1	(0.8)	142	(0.18)	0.57	(0.4)	(0.11)	0.37	(0.14)	296	0.34	20	2.4	100	(57)	70 g
JH-1	.	3.1	.	153	0.23	0.52	1.4	.	.	0.58	228	.	13.7	1.2	61.8	48.3	100 g

AMPHIBOLITE

IRON PELLETS (supplied in homogeneous powder form)

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	Fe (met)	FeO	Al	Al ₂ O ₃	Ca	CaO	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
1	VS R10/4	90.9	87.3	.	.	0.29	.	1.65	.	0.30	.	.	.	0.094	0.0104	0.0062	.	4.11	.	.
1	SRM 691	90.5	.	.	.	1.21	.	0.64	.	0.51	.	0.042	.	0.177	0.005	(0.009)	.	3.6	.	0.27
1	NCS DC28240a	66.18	.	0.78	.	0.43	.	0.51	.	0.79	.	0.040	.	.	0.010	0.0066	.	3.81	.	0.048
1	VS R29	64.95	.	0.48	.	0.38	.	0.45	.	0.149	0.0123	0.0118	.	6.13	.	.
1	NCS DC28239b	63.78	.	0.77	.	0.98	.	0.85	.	1.59	.	0.065	.	.	0.016	0.0086	.	5.29	.	0.18
1	NCS DC28020a	63.07	.	(0.04)	.	1.47	.	1.34	.	0.96	.	0.303	.	0.103	0.028	0.0084	.	5.22	.	0.258
1	VS R28	63.01	.	1.16	.	0.37	.	4.09	.	0.194	0.0121	0.087	.	5.11	.	.
1	NCS DC28020b	61.81	.	(0.18)	.	1.48	.	1.30	.	1.00	.	0.310	.	0.099	0.032	0.0055	.	6.88	.	0.251
1	NCS DC11025	61.37	.	(1.92)	.	1.35	.	1.04	.	0.80	.	0.120	.	0.105	0.093	0.021	.	6.59	.	1.61
1	NCS DC28020c	60.46	.	0.33	.	0.76	.	0.75	.	5.15	.	0.130	.	0.036	0.013	0.029	.	6.12	.	0.154
1	VS R3/2	58.72	.	2.53	.	2.50	.	4.47	.	2.48	.	0.232	.	.	0.0027	0.005	.	3.74	.	2.49
1	VS R23/1	58.7	4.45	3.75	.	.
1	NCS DC28021a	57.88	.	6.53	.	2.54	.	3.15	.	3.11	.	0.126	.	0.105	0.016	0.115	.	7.92	.	0.207

Number	As*	C	Cd*	Co	Cr	Cu	K	K ₂ O	Mo*	N*	Ni	Pb*	Sn	V	V ₂ O ₅	Zn	Units
VS R10/4	.	1.72	.	.	.	0.0019	.	0.055	.	.	.	1.8	.	.	.	0.0018	100 g
SRM 691	(14)	(0.12T)	(<5)	0.031	0.025	0.030	0.065	.	(<20)	(50)	(0.269)	(<20)	(<0.001)	0.015	.	(0.004)	100 g
NCS DC28240a	50 g
VS R29	100 g
NCS DC28239b	50 g
NCS DC28020a	0.0089	.	0.078	0.012	50 g
VS R28	100 g
NCS DC28020b	0.0089	.	0.066	0.155	.	0.012	50 g
NCS DC11025	0.111	0.012	70 g
NCS DC28020c	0.010	.	0.081	0.012	50 g
VS R3/2	.	.	.	0.020	0.56	.	100 g
VS R23/1	150 g
NCS DC28021a	12	0.018	.	0.265	.	.	.	47	.	.	.	0.039	50 g

CRM IRON SULPHIDE CONCENTRATE

analysis listed in mass %

25 g units

Number	Al	Ca	Co	Cr	Cu	Fe	K	Mg	Mn	Na	Ni	P	Pb	S	SiO ₂	Ti	Zn
CAN TPO-1	(3.51)	(2.17)	0.021	(0.03)	0.118	34.85	(0.56)	(1.66)	(0.08)	(0.85)	0.617	(0.03)	(0.02)	18.03	25.52	(0.35)	(0.02)

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

CRM IRON ORE, chart 1 of 9 # = class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂
1	VS R21/2	99.0	0.3	.	.	.	0.01	.	0.02	0.06	.	.	.
1	VS R16/3	98.2	0.380	.	.	0.0110	.	.	0.0198	0.073	.	.	.
1	FLX 2001	Fe2O3:96.47	.	.	1.40	.	0.026	Mn ₂ O ₃ :0.134	.	.	.	0.202	.	.	.	1.67	.	0.134
1	FLX 2003	Fe2O3:96.11	.	.	0.274	.	0.332	.	(0.018)	.	1.279	Mn ₃ O ₄ :0.057	.	.	(0.022)	.	(0.014)	.	.	1.489	.	0.278
1	JK 55	92.47	.	.	(0.21)	.	(1.2)	.	(0.032)	.	(0.86)	Mn ₃ O ₄ :0.084	.	.	.	(0.036)	.	.	.	(1.0)	.	(0.17)
1	MP CFe09001	91.11	.	.	3.05	0.016	0.20	.	.	2.57	.	0.22
2	VS R40	90.95	.	.	0.82	0.90	.	.	0.05129	.	0.299	.	.	.	0.084	0.0094	.	0.0057	.	4.13	.	.
1	MP CFe09002	76.89	.	.	6.91	0.16	.	.	7.66	.	0.22
1	NCS DC28039	72.02	28.78	.	0.095	.	0.026	.	0.0064	.	0.043	0.043	.	0.0008	0.0016	.	.	0.0030	.	0.14	0.029	.
1	NCS DC28029	72.01	28.63	.	0.095	.	0.025	.	0.0068	.	0.042	0.043	.	0.0008	0.0013	.	.	0.0028	.	0.158	0.028	.
1	JK 29A	71.36	.	.	0.232	.	0.082	.	0.0087	.	0.223	.	0.0632	.	0.015	0.0059	.	0.0059	.	0.33	.	0.292
1	MP CFe09003	70.97	.	.	11.07	0.14	.	.	8.70	.	0.66
1	NCS DC11032	70.69	27.98	.	0.32	.	0.066	.	0.012	.	0.045	.	0.28	.	0.010	0.012	.	0.0032	.	0.293	.	0.535
1	JK 42A	70.66	.	.	0.278	.	0.199	.	0.0157	.	0.382	.	0.0506	.	0.043	0.0247	.	0.0082	.	0.800	.	0.385
1	IMZ 350	70.20	30.06	.	0.077	.	0.084	.	0.015	.	0.19	0.030	.	.	0.033	0.007	.	0.0097	.	2.51	.	0.021
1	ECRM 687-1	69.66	.	0.0356	.	0.0113	.	0.0011	.	0.0018	.	0.1658	.	0.0030	.	0.0120	.	.	0.0157	.	0.0303	.
1	GIOP-117	69.631	.	.	0.06	.	(0.01)	.	(0.0026)	.	(0.013)	0.008	.	0.011	.	0.00325	.	0.0026	.	0.203	.	0.0902
1	NCS DC28220	69.05	23.8	.	0.50	.	0.20	.	0.17	.	0.17	0.079	.	.	0.010	.	0.011	.	2.45	.	0.313	.
1	NCS DC13019c	68.96	28.98	.	0.174	.	0.196	.	0.0068	.	0.268	0.049	.	.	0.0060	0.010	.	0.0277	.	3.98	.	0.0174
2	IMZ 324	68.93	28.27	.	0.11	.	0.107	.	0.026	.	0.24	0.026	.	.	(0.04)	0.014	.	0.044	.	3.96	.	0.028
1	NCS DC28219	68.55	23.0	.	0.54	.	0.21	.	.	0.20	.	0.052	.	.	0.0054	.	0.027	.	3.21	.	0.116	.
1	VS R38	68.55	.	.	0.212	.	0.118	.	0.087	.	0.131	.	0.035	.	0.036	0.0122	.	0.334	.	4.56	.	0.022
1	NCS DC28005c	68.38	28.80	.	0.58	.	0.78	.	0.050	.	1.15	0.086	.	.	0.026	0.0035	.	0.034	.	2.25	.	0.057
2	IMZ 323	68.35	27.65	.	0.23	.	0.109	.	0.027	.	0.28	0.043	.	.	0.035	0.018	.	0.052	.	4.31	.	0.017
1	NCS DC28115	68.29	28.25	.	0.43	.	0.70	.	0.060	.	1.25	0.061	.	.	0.021	0.0047	.	0.041	.	2.08	0.034	0.057
1	NCS DC28032	68.29	0.24	.	0.74	.	0.074	.	0.0063	.	0.025	0.096	.	.	0.015	0.028	.	0.0028	.	0.85	0.050	.
1	NCS DC93024	68.02	30.50	.	0.34	.	0.35	.	0.018	.	0.19	0.017	.	.	0.012	0.017	.	0.301	.	4.58	.	0.056
1	IMZ 352	67.84	29.09	.	0.206	.	0.295	.	0.020	.	0.55	0.032	.	.	0.030	0.018	.	0.061	.	4.56	.	0.015
1	NCS DC28005b	67.84	29.72	.	0.45	.	0.155	.	0.055	.	0.202	.	0.030	.	0.018	0.0025	.	0.106	.	5.32	.	0.097
1	NCS DC28221	67.84	28.8	.	0.60	.	0.63	.	.	1.40	.	0.070	.	.	.	0.0046	.	0.041	.	2.34	.	0.061
2	IMZ 320	67.76	27.37	.	0.12	.	0.13	.	0.049	.	0.30	0.029	.	.	0.037	0.022	.	0.012	.	5.30	.	0.016
2	IMZ 325	67.73	28.03	.	0.20	.	0.17	.	0.027	.	0.27	0.031	.	.	(0.03)	0.016	.	0.077	.	5.01	.	0.018
1	IMZ 351	67.55	28.52	.	0.132	.	0.095	.	0.019	.	0.25	0.0121	.	.	0.037	0.008	.	0.023	.	5.71	.	0.010
2	IMZ 261/1	67.54	.	.	0.59	.	0.30	.	.	1.37	.	0.16	.	.	.	(0.019)	.	0.080	.	3.16	.	.
1	VS R25/1	67.3	0.14	.	.	0.25	3.37	.	.
1	VS R22/2	67.0	.	.	0.3	.	0.1	.	.	0.2	0.008	.	.	.	3.3	.	.
1	NCS DC73009	66.87	23.14	.	0.99	.	0.14	.	0.030	.	0.22	0.071	.	.	0.012	(0.011)	.	0.0055	.	5.05	0.059	.
1	SRM 690	66.8	.	.	0.17	.	0.20	.	0.0030	.	0.177	.	0.230	.	0.0027	0.009	.	(0.004)	.	3.70	.	0.021
1	OREAS 40	66.72	1.76	.	0.130	.	0.015	.	0.018	.	0.017	.	0.020	.	.	0.004	.	0.008	.	4.64	.	0.050
1	ECRM 690-1	66.70	.	0.198	.	0.269	.	0.0158	.	0.815	.	0.0337	.	0.0312	.	0.0085	.	.	0.881	.	0.229	.
1	NCS DC28222	66.64	27.9	.	0.76	.	0.86	.	.	1.62	.	0.091	.	.	.	0.0051	.	0.096	.	2.96	.	0.070
1	NCS DC14028c	66.56	26.01	.	0.28	.	0.11	.	0.009	.	0.11	0.135	.	.	(0.006)	0.015	.	0.0045	.	6.09	0.283	.
1	NCS DC14208	66.56	26.01	.	0.28	.	0.11	.	0.009	.	0.11	0.135	.	.	(0.006)	0.015	.	0.0045	.	6.09	0.283	.
1	NCS DC28037	66.54	0.21	.	1.43	.	0.031	.	0.012	.	0.054	0.482	.	.	0.015	0.034	.	0.0071	.	0.962	0.051	.
1	NCS DC28109	66.52	27.91	.	0.62	.	1.10	.	0.091	.	1.96	0.070	.	.	0.032	0.0062	.	0.064	.	3.26	0.037	0.061

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂
	Number	As	Ba	C	Cl	Co	Cr	Cr₂O₃	Cu	Ni	Pb	V	V₂O₅	Zn	LOI	Units	Other					
	VS R21/2	.	.	0.02	100 g	O: 0.3					
	VS R16/3	.	.	0.108	.	Insoluble Residue: 0.155	100 g	O: 1.15					
	FLX 2001	35 g	17034					
	FLX 2003	Co ₃ O ₄ : (0.016)	Cr ₂ O ₃ : (0.015)	NiO:0.031	SO ₃ : (0.013)	.	.	.	0.223	(-2.90)	30 g	FeII: (22.34)	17034				
	JK 55	Metallic Iron: 84.15%	(0.27)	100 g	.					
	MP CFe09001	2.61	100 g					
	VS R40	.	.	1.393	.	Metallic Iron: 85.7%	100 g						
	MP CFe09002	7.73	100 g					
	NCS DC28039	70 g						
	NCS DC28029	0.00012	.	.	.	0.0008	0.0062	.	0.0007	0.0022	0.0002	.	.	.	0.0026	50 g						
	JK 29A	0.0106	0.0057	.	0.0007	0.0167	.	.	.	0.266	0.0016	100 g						
	MP CFe09003	7.69	100 g					
	NCS DC11032	0.258	0.030	70 g						
	JK 42A	0.0105	0.0010	.	0.0007	0.0129	.	.	.	0.251	0.0015	100 g						
	IMZ 350	.	(0.0019)	0.024	.	(0.0024)	0.0031	.	(0.0006)	.	.	0.0020	.	(0.0017)	.	100 g						
	ECRM 687-1	.	Mo: 0.0020	0.0173	.	0.0227	.	0.0030	0.0122	.	Sn: 0.0006	0.0051	.	.	100 g							
	GIOP-117	(0.0038)	(0.0038)	0.012	(0.001)	(0.0031)	.	(0.0037)	(0.0026)	(0.0048)	(0.0013)	.	(0.0014)	0.085	10 g							
	NCS DC28220	50 g							
	NCS DC13019c	0.0052	.	.	.	0.0030	50 g							
	IMZ 324	.	0.0024	0.052	.	0.003	0.0025	.	0.0014	0.0013	0.0002	.	.	(0.003)	2.91	100 g						
	NCS DC2																					

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

CRM		IRON ORE, chart 2 of 9																		# = class, where 1 = CRM and 2 = RM		analysis listed in mass % except * which is mg/kg										
#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂										
1	NCS DC28028	66.47	0.58	.	1.36	.	0.028	.	0.014	.	0.091	0.137	.	.	0.005	0.055	.	0.0066	.	1.79	0.046	.										
1	IMZ 353	66.42	1.41	.	0.40	.	0.098	.	0.011	.	0.054	0.051	.	.	0.012	0.018	.	0.0049	.	4.07	.	0.28										
1	SARM 145	66.42	.	.	0.58	.	0.15	.	0.09	.	0.02	.	0.02	.	0.02	.	0.12	(0.014)	.	3.56	.	0.03										
1	NCS DC28027	66.34	0.07	.	1.42	.	0.02	.	0.013	.	0.063	0.48	.	.	0.0055	0.034	.	0.0071	.	1.02	0.057	.										
1	NCS DC28223	66.31	24.4	.	1.04	.	0.64	.	.	.	0.26	.	0.085	.	0.039	.	.	0.011	.	4.17	.	0.709										
1	BCS 517	66.30	.	0.508	.	0.033	.	0.0105	.	0.0311	.	0.679	.	0.0097	.	0.0408	.	0.0090	0.519	.	0.0332	.										
1	JSS 805-2	66.22	.	0.565	.	0.0071	.	0.012	.	0.0221	.	0.596	.	0.0026	.	0.047	.	0.0077	0.552	.	0.0409	.										
1	GIOP-116	66.214	.	.	0.909	.	0.0898	.	0.0088	.	0.0559	0.04	.	0.035	.	0.01331	.	0.00428	.	3.577	.	0.1249										
1	NCS DC28005a	66.18	27.01	.	0.54	.	0.74	.	0.054	.	2.64	.	0.103	.	0.031	0.0067	.	0.059	.	2.90	.	0.077										
1	NCS DC28033	66.17	26.04	.	0.260	.	0.21	.	0.014	.	0.18	0.043	.	.	0.0015	0.012	.	0.044	.	7.21	0.024	.										
2	DH 1137	66.15	0.32	.	0.442	.	1.930	.	0.011	.	0.164	0.038	.	.	0.020	.	0.113	0.003	.	2.365	.	0.032										
1	ECRM 602-2	66.12	.	0.325	0.0133	.	.	0.0311	.	.	.	0.0529	.	0.0140	0.833	.	0.0441	.										
1	IMZ 358	66.08	0.84	.	0.214	.	2.61	.	0.029	.	0.23	0.027	.	.	0.032	0.0066	.	0.0103	.	2.60	.	0.022										
1	VS R1/4	66.0	26.1	.	0.28	.	0.17	.	.	.	0.38	0.0157	.	0.029	.	7.38	.	.										
1	NCS DC28214	65.97	27.0	.	0.70	.	0.43	.	.	.	0.45	.	0.094	.	.	0.013	.	0.291	.	5.02	.	0.541										
2	BS 105	65.9	.	0.098	.	0.50	.	0.013	.	0.188	.	0.087	.	0.016	.	0.0077	.	(0.002)	2.17	.	0.0074	.										
1	JK 28	65.86	2.4	0.35	.	0.21	.	0.99	.	0.18	.	0.045	.	0.078	.	0.045	.	0.004	1.96	.	0.11	.										
1	IMZ 362	65.81	0.4	.	0.123	.	1.69	.	0.118	.	0.18	0.0087	.	.	0.058	0.0091	.	0.0021	.	3.79	.	0.008										
1	VS R37	65.81	.	.	0.264	.	0.050	.	.	.	0.029	.	0.015	.	.	0.0110	.	1.29	.	3.06	.	0.013										
1	IMS-PBS-204	65.75	.	.	0.98	.	(0.010)	.	0.003	.	0.040	0.019	.	.	0.010	0.124	.	0.014	.	1.14	.	0.060										
2	DH 1136	65.74	.	.	0.345	.	0.370	.	0.033	.	0.083	1.21	.	.	0.025	.	0.017	0.002	.	3.35	.	0.023										
1	NCS DC28114	65.71	27.14	.	0.83	.	0.72	.	0.048	.	3.33	0.127	.	.	0.015	0.013	.	0.158	.	2.07	0.418	0.697										
1	ECRM 604-1	65.69	.	0.93	.	0.107	.	.	0.049	.	0.092	0.053	.	0.015	1.27	.	0.060	.										
1	JSS 850-4	65.67	(0.30)	.	0.40	.	0.41	.	0.075	.	0.79	0.019	.	.	0.129	0.013	.	0.006	.	4.12	.	0.056										
1	NCS DC28035	65.66	0.54	.	1.64	.	0.056	.	0.018	.	0.102	0.135	.	.	0.007	0.060	.	0.022	.	1.92	0.048	.										
1	BAM 630-1	65.63	.	.	0.88	.	0.10	.	.	.	0.47	0.060	.	.	.	0.043	.	0.032	.	5.88	.	0.066										
1	CAN IOC-1	65.62	20.76	.	(0.184)	.	0.975	.	(0.004)	.	1.043	.	0.472	.	.	0.0120	.	(0.00657)	.	2.633	.	0.0429										
1	VS R29/1	65.6	1.44	.	0.34	.	0.47	.	.	.	0.187	0.0129	.	0.0061	.	5.53	.	.										
2	DH 1114	65.55	27.20	.	0.271	.	0.421	.	0.061	.	0.565	0.029	.	0.078	.	0.028	0.019	.	0.019	.	7.47	0.060										
2	IMZ 322	65.50	26.82	.	0.095	.	0.26	.	0.058	.	0.46	0.026	.	.	0.069	0.015	.	0.047	.	7.56	.	0.012										
1	JSS 805-3	65.43	.	0.595	.	0.0087	.	0.0141	.	0.0222	0.194	.	.	0.00431	.	0.057	.	0.0089	0.866	.	0.052	.										
2	IMZ 310	65.25	1.61	.	1.02	.	0.30	.	0.022	.	0.25	0.058	.	.	0.054	0.034	.	0.011	.	6.58	.	0.035										
1	SRM 693	65.08	.	.	1.043	.	0.0158	.	0.00283	.	0.0143	.	0.0900	.	0.0023	0.0563	.	(0.005)	.	3.860	.	0.0345										
1	JSS 804-3	64.91	.	0.473	.	0.109	.	.	.	0.0119	.	0.0199	.	.	.	0.056	.	0.0073	2.47	.	0.026	.										
1	IMZ 363	64.90	0.57	.	0.30	.	0.372	.	0.040	.	0.375	0.0301	.	.	0.112	0.0086	.	0.004	.	6.08	.	0.032										
1	NCS DC28217	64.82	24.5	.	1.30	.	0.85	.	.	.	0.31	.	0.088	.	.	0.053	.	0.011	.	4.91	.	0.949										
1	NCS DC28218	64.81	25.4	.	0.80	.	0.65	.	.	.	1.78	.	0.084	.	.	0.026	.	0.035	.	5.04	.	0.477										
2	DH 1123	64.80	0.133	.	1.619	.	0.634	.	0.008	.	0.037	0.049	.	.	0.006	.	0.123	0.011	.	2.67	.	0.047										
2	DH 1118	64.72	.	.	1.785	.	0.052	.	0.020	.	0.057	0.713	.	.	0.014	.	0.141	0.009	.	1.56	.	0.075										
2	DH 1135	64.69	0.06	.	1.49	.	0.011	.	0.016	.	0.033	1.520	0.140	0.006	.	0.696	.	0.052										
2	DH 1116	64.69	.	.	0.722	.	1.149	.	0.023	.	0.400	0.198	.	.	0.016	.	0.058	.	.	4.67	.	0.078										
1	NCS DC28052	64.53	0.28	.	0.77	.	0.30	.	0.038	.	0.32	0.075	.	.	0.054	0.025	.	0.0053	.	5.65	0.122	.										

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂	
	Number	As	Ba	C	CO ₂	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	NiO	Pb	V	V ₂ O ₅	Zn	ZnO	LOI	Units	Other			
	NCS DC28028	0.0012	0.0008	0.003	.	0.0014	0.0019	.	0.0013	.	.	0.0044	.	.	.	50 g			
	IMZ 353	(0.0007)	.	0.011	.	(0.0039)	(0.0018)	0.0045	.	0.0008	(0.0017)	.	(0.0011)	0.005	.	(0.0010)	.	(0.086)	.	100 g			
	SARM 145	BaO: (0.046)	0.36	.	100 g		
	NCS DC28027	0.0004	0.0009	0.0015	.	0.0085	0.0008	.	0.0013	.	.	0.0032	.	.	.	50 g			
	NCS DC28223	50 g		
	BCS 517	.	.	0.061	.	0.00075	.	.	.	0.0088	.	.	0.0028	0.0040	.	0.0047	.	1.898	.	100 g			
	JSS 805-2	0.0094	0.0039	.	0.0047	.	1.72	.	100 g			
	GIOP-116	0.0346	0.404	.	10 g		Zr: 0.0104	
	NCS DC28005a	0.0050	0.0070	.	.	.	50 g			
	NCS DC28033	70 g			
	DH 1137	.	.	0.101	0.017	0.080	.	100 g		CO ₂ : 0.089
	ECRM 602-2	0.0005	.	.	.	0.0004	0.0015	100 g			
	IMZ 358	(0.0008)	.	0.030	.	(0.0016)	.	0.0034	.	0.0008	(0.0016)	.	(0.0011)	0.0015	.	(0.0013)	.	0.051	.	100 g			
	VS R1/4	100 g			
	NCS DC28214	50 g			
	BS 105	(0.001)	.	.	.	(0.0005)	.	0.012	.	(0.001)	0.0036	.	(0.002)	0.0024	.	(0.001)	.	.	.	100 g		Sn: (0.002)	
	JK 28	last	.	150 g		Fe ₂ O ₃ : 91.5
	IMZ 362	.	(0.003)	(0.016)	.	(0.0005)	.	0.0020	.	0.0011	0.0010	.	0.0017	.	.	0.0010	.	0.13	.	100 g			
	VS R37	100 g		
	IMS-PBS-204	0.001	(0.004)	.	.	(0.002)	(0.002)	(0.002)	.	(0.003)	(0.002)	.	(0.004)	(0.003)	(0.002)	0.002	.						

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

IRON ORE, chart 3 of 9

= class, where 1 = CRM and 2 = RM

analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂
1	GIOP-127	64.499	.	.	2.815	.	0.1522	.	0.0195	.	0.0644	0.0633	.	0.0184	.	0.0457	.	0.0133	.	2.578	.	0.0581
1	NCS DC14001b	64.48	0.34	.	1.26	.	0.15	.	0.096	.	0.041	0.087	.	.	0.013	0.049	.	0.018	.	3.40	.	0.057
1	NCS DC28113	64.42	27.00	.	0.90	.	1.06	.	0.099	.	3.28	0.109	.	.	0.034	0.011	.	0.381	.	3.56	0.315	0.522
1	IMZ 356	64.41	(0.47)	.	1.63	.	0.035	.	0.021	.	0.057	0.765	.	.	0.011	0.040	.	0.0084	.	2.85	.	0.101
1	BCRM 691-1	64.39	.	0.475	.	0.999	.	0.0504	.	2.022	.	0.1734	.	0.0164	.	0.0877	.	0.0632	0.556	.	0.966	.
1	NCS DC14028d	64.37	20.96	.	1.10	.	1.17	.	0.036	.	1.30	0.147	.	.	0.017	0.013	.	0.371	.	2.95	0.294	.
1	NCS DC93025	64.17	31.34	.	0.29	.	0.56	.	0.012	.	0.49	0.032	.	.	0.011	0.033	.	0.624	.	9.43	.	0.049
1	NM 613C	64.03	.	.	3.11	.	0.24	.	.	.	0.35	0.025	.	.	.	0.023	.	0.013	3.63	.	.	.
1	VS R15/2	64.0	28.0	.	.	.	0.9	2.3	.	.
1	NCS DC28215	63.93	26.9	.	1.09	.	2.06	.	.	.	0.79	.	0.136	.	.	0.017	.	0.282	.	5.90	0.444	.
1	NCS DC14049	63.86	0.25	.	2.04	.	0.084	.	0.33	.	0.056	0.170	.	.	0.027	0.037	.	0.020	.	4.62	.	0.12
1	NCS DC28051	63.56	0.35	.	0.926	.	1.12	.	0.13	.	1.48	0.134	.	.	0.070	0.018	.	0.015	.	4.57	0.071	.
1	ASCRM 032	63.53	.	0.97	.	0.040	.	0.006	.	0.039	.	0.071	.	0.0085	.	0.074	.	0.011	1.81	.	0.043	.
1	NCS DC11005a	63.34	(0.07)	.	0.52	.	0.12	.	0.070	.	0.146	.	0.84	.	0.020	0.016	.	0.107	.	3.36	.	0.034
1	IMZ 360	63.36	25.3	.	0.356	.	2.77	.	0.039	.	0.63	0.098	.	.	0.027	0.019	.	0.074	.	5.4	.	0.023
1	NCS DC11017	63.33	1.76	.	1.13	.	1.05	.	0.115	.	1.30	.	0.086	.	0.070	0.011	.	0.0030	.	5.56	.	0.151
1	GIOP-141	63.226	.	.	1.8	.	0.036	.	0.0189	.	0.1003	0.0691	.	0.024	.	0.0665	.	0.0281	.	3.548	.	0.0574
1	NCS DC28224	63.20	1.4	.	1.02	.	0.86	.	.	.	0.50	.	0.083	.	.	0.020	.	0.015	.	6.55	0.319	.
2	DH 1115	63.17	.	.	2.68	.	0.494	.	0.008	.	0.244	0.074	.	.	0.020	.	0.101	.	.	5.79	.	0.128
2	IMZ 330	63.09	1.19	.	0.13	.	1.04	.	0.18	.	0.23	0.012	.	.	0.073	0.013	.	0.003	.	8.26	.	0.01
1	NCS DC28003b	63.07	23.93	.	0.64	.	0.71	.	0.025	.	4.82	.	1.08	.	0.016	0.016	.	0.024	.	3.38	.	0.224
2	IMZ 331	63.05	1.55	.	0.24	.	3.78	.	0.092	.	0.21	0.028	.	.	0.037	0.015	.	0.107	.	5.11	.	0.017
1	GIOP-143	62.97	.	.	1.49	.	0.0348	.	0.00942	.	0.0475	0.1353	.	0.0121	.	0.064	.	0.01731	.	3.086	.	0.0531
1	NM 161.6A	62.83	.	.	2.93	0.065	.	0.009	.	2.66	.	0.093
1	IMZ 357	62.79	0.95	.	1.07	.	0.060	.	0.012	.	0.047	0.173	.	.	0.0098	0.058	.	0.0064	.	7.08	.	0.081
1	JSS 806-1	62.77	.	0.96	.	0.0197	.	0.0091	.	0.034	.	0.125	.	0.0115	.	0.083	.	0.019	1.55	.	0.044	.
1	IMZ 354	62.76	1.41	.	1.48	.	1.31	.	0.15	.	0.49	0.390	.	.	0.096	0.028	.	0.0149	.	4.78	.	0.68
1	GIOP-44	62.75	.	.	2.216	.	0.0255	.	0.0127	.	0.0571	0.0709	.	(0.02)	.	0.06267	.	0.0199	.	4.55	.	0.1064
1	VS 5403-90	62.74	25.74	.	0.73	.	0.89	.	.	.	0.65	0.162	3.89	.	7.14	.	0.055
1	NCS DC28003a	62.65	24.53	.	0.39	.	0.71	.	0.040	.	4.73	.	0.113	.	0.013	0.011	.	0.114	.	4.20	.	0.117
1	NCS DC28110	62.63	23.21	.	1.19	.	1.09	.	0.068	.	5.21	0.170	.	.	0.028	0.017	.	0.255	.	3.15	0.096	0.160
1	ASCRM 031	62.53	.	0.80	.	0.011	.	0.005	.	0.035	.	0.110	.	0.0010	.	0.062	.	0.025	1.29	.	0.032	.
1	GIOP-37	62.53	.	.	2.037	.	0.0341	.	0.0146	.	0.0446	0.0959	.	0.015	.	0.1097	.	0.0159	.	3.877	.	0.0615
1	NCS DC73007	62.51	21.54	.	1.02	.	0.18	.	0.037	.	0.28	0.061	.	.	0.016	0.11	.	0.0058	.	10.93	0.059	.
1	JSS 803-8	62.47	.	0.797	.	0.0277	.	0.00561	.	0.029	0.090	0.00633	.	.	.	0.089	.	0.0153	1.52	.	0.037	.

Number	As	Ba	C	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other
GIOP-127	0.0066	0.0072	.	.	0.0066 (0.0034)	0.007	.	0.0024	0.0042	0.0065	0.01274	.	0.0023	(0.0028)	1.834	10 g	Sr: 0.0036
NCS DC14001b	50 g	.
NCS DC28113	0.013	0.047	0.0096	.	.	70 g	.
IMZ 356	.	0.028	0.043	(0.0087) (0.0023)	0.0028	.	.	0.0109	.	0.0015	0.0052	.	0.0066	.	2.37	100 g	.
BCRM 691-1	Fe II: 20.71	0.307	.	.	.	0.0095	.	0.0768	0.0299	0.0008	0.0603	.	0.0195	.	.	100 g	.
NCS DC14028d	50 g	.
NCS DC93025	100 g	.
NM 613C	100 g	.
VS R15/2	0.6	100 g	.
NCS DC28215	50 g	.
NCS DC14049	65 g	.
NCS DC28051	70 g	.
ASCRM 032	0.0018	0.0037	.	.	0.0080	0.0008	0.0022	0.0009	0.0011	0.0008	0.0022	.	0.0022	0.0019	2.90	10x10 g	Sn: 0.0013 Sr: 0.0008
NCS DC11005a	0.0044	(0.62 BaO)	0.119	.	0.0031	.	.	0.034	.	0.035	.	.	0.026	.	.	50 g	.
IMZ 360	.	0.0033	0.69	.	(0.0011)	0.0077	.	0.007	0.0041	0.011	(0.0013)	.	0.28	.	(-0.30)	100 g	.
NCS DC11017	(0.0006)	0.0045	.	(0.0006)	.	.	0.0058	.	.	70 g	.
GIOP-141	0.00195	(0.004)	.	0.0103	0.00159	0.0154	.	0.0043	0.0055	(0.0034)	0.0022	.	0.00282	0.0027	3.687	10 g	Sr: 0.0027
NCS DC28224	50 g	.
DH 1115	0.005	0.010	.	.	100 g	.
IMZ 330	.	(0.003)	0.016	.	.	0.003	.	0.0017	(0.002)	0.0016	.	.	0.002	.	-0.04	100 g	.
NCS DC28003b	0.055	.	.	50 g	.
IMZ 331	(0.0004)	0.0025	.	.	0.001	0.0051	.	0.0016	0.002	0.002	0.003	.	0.003	.	0.22	100 g	Sn: 11*
GIOP-143	(0.0016)	(0.0059)	.	0.009	0.00187	(0.0016)	.	(0.0021)	(0.0028)	(0.004)	0.0016	.	0.00168	(0.0018)	4.898	10 g	Sr: 0.0029
NM 161.6A	100 g	.
IMZ 357	(0.0006)	(0.0064)	0.054	.	.	0.0039	.	0.0014	(0.0019)	(0.0014)	0.0047	.	0.0019	.	2.14	100 g	.
JSS 806-1	0.0033	.	0.0012	0.0013	.	0.0018	.	0.0020	.	4.4	150 g	FeII: 0.15
IMZ 354	.	(0.0042)	0.251	(0.0046) (0.0023)	0.0064	0.0064	.	0.0016	(0.0017)	(0.0009)	0.013	.	0.0017	.	0.97	100 g	.
GIOP-44	.	.	.	0.0082	.	0.0033	.	0.0026	2.929	10 g	.
VS 5403-90	0.32	0.029	.	.	50 g	Ag: 5.9* CO ₂ : 0.39
NCS DC28003a	0.0071	0.0085	.	.	50 g	.
NCS DC28110	0.018	0.010	.	.	70 g	.
ASCRM 031	0.0011	0.0029	.	0.0106	0.0012	0.0026	.	0.0011	0.0013	0.0006	0.0013	.	0.0018	0.0014	5.80	10x10 g	Sn: 0.0013 Sr: 0.0001
GIOP-37	.	.	.	0.0109	4.021	10 g	.
NCS DC73007	(0.0015)	50 g	.
JSS 803-8	0.0029	.	0.00068	0.0012	.	0.0018	.	0.0023	.	(5.06)	100 g	FeII: 0.183%

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

CRM		IRON ORE, chart 4 of 9																# = class, where 1 = CRM and 2 = RM																analysis listed in mass % except * which is mg/kg															
#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂																											
1	GIOP-56	62.41	.	.	1.969	.	0.0369	.	0.0184	.	0.0513	0.2196	.	0.0174	.	0.0902	.	0.0164	.	3.594	.	0.06																											
1	GIOP-43	62.39	.	.	2.368	.	0.028	.	0.0134	.	0.0623	0.0821	.	(0.012)	.	0.0587	.	0.024	.	4.707	.	0.1213																											
1	IMS FBS-72	62.38	.	.	2.14	.	0.053	.	0.041	.	(0.081)	0.404	.	.	(0.023)	0.064	.	(0.020)	.	3.65	.	0.105																											
1	NCS DC15605	62.36	0.48	.	2.56	.	0.050	.	0.015	.	0.062	0.112	.	.	0.015	0.073	.	0.022	.	4.69	.	0.113																											
1	ASCRM 035	62.35	.	0.72	.	0.117	.	0.022	.	0.150	.	0.152	.	0.0565	.	0.078	.	0.057	1.99	.	0.046	.																											
1	NCS DC28026	62.27	0.59	.	2.39	.	0.144	.	0.023	.	0.156	0.17	.	.	0.024	0.078	.	0.02	.	4.2	0.055	.																											
1	IRSID 611-1	62.22	.	0.69	.	2.85	.	.	.	0.32	.	1.97	.	.	0.030	.	(0.008)	2.07	.	0.033	.	.																											
1	USZ 27-99	62.2	21.06	.	1.37	.	0.56	.	0.07	.	2.78	.	.	(0.04)	.	(0.016)	.	.	.	3.37	.	0.101																											
1	SARM 132	62.2	.	.	1.84	.	(0.086)	.	0.219	.	.	0.105	.	(0.0200)	(0.031)	0.054	.	.	.	7.82	.	(0.094)																											
1	GIOP-38	62.15	.	.	2.008	.	0.0407	.	0.023	.	0.07	0.5627	.	0.0195	.	0.0515	.	0.0256	.	3.101	.	0.0687																											
1	NCS DC28025	62.11	0.58	.	2.06	.	0.021	.	0.023	.	0.101	0.65	.	.	0.013	0.067	.	0.013	.	2.92	0.051	.																											
2	IMZ 332	62.10	1.61	.	0.32	.	0.39	.	0.117	.	0.71	0.026	.	.	0.050	0.010	.	0.003	.	9.63	.	0.027																											
1	NCS DC28216	62.01	26.9	.	1.46	.	3.65	.	.	1.10	.	0.176	.	.	0.020	.	0.258	.	6.74	0.388	.	.																											
1	DSZU RG36	62.01	0.67	.	0.84	.	0.051	.	0.017	.	0.48	.	0.026	.	0.079	0.015	.	0.0068	.	9.43	.	0.037																											
1	NCS DC11009a	61.96	15.13	.	0.914	.	0.375	.	0.093	.	0.364	.	0.947	.	0.024	0.027	.	0.212	.	4.92	.	0.447																											
1	GIOP-47	61.9	.	.	1.88	.	0.0151	.	0.0064	.	0.041	0.0782	.	(0.015)	.	0.0688	.	0.0199	.	2.809	.	0.0614																											
2	IMZ 333	61.87	1.65	.	0.33	.	0.34	.	0.11	.	0.73	0.034	.	.	0.057	0.008	.	0.001	.	10.07	.	0.026																											
1	GIOP-41	61.85	.	.	1.978	.	0.0368	.	0.0113	.	0.053	0.1078	.	0.018	.	0.1109	.	0.0335	.	3.043	.	0.0762																											
1	NCS DC28031	61.82	0.55	.	2.26	.	0.024	.	0.024	.	0.085	0.61	.	.	0.012	0.073	.	0.012	.	2.94	0.054	.																											
1	NCS DC18011	61.80	0.30	.	3.05	.	0.051	.	0.102	.	0.102	.	0.170	.	0.076	.	0.022	.	4.52	.	0.134	.																											
1	IMZ 359	61.74	3.17	.	0.25	.	2.93	.	0.061	.	0.86	0.028	.	.	0.079	0.0078	.	0.017	.	7.75	.	0.021																											
1	NCS DC14633	61.73	1.51	.	0.48	.	0.11	.	0.056	.	0.055	0.027	.	.	0.0056	0.024	.	0.036	.	9.82	0.041	.																											
1	GIOP-42	61.7	.	.	1.896	.	0.0172	.	(0.0049)	.	0.045	0.0541	.	0.018	.	0.0618	.	0.0137	.	2.743	.	0.0674																											
1	GIOP-46	61.699	.	.	1.854	.	0.0159	.	(0.0056)	.	0.045	0.0685	.	(0.012)	.	0.0684	.	0.0152	.	3.064	.	0.0656																											
1	NCS DC28053	61.68	0.24	.	0.84	.	0.33	.	0.071	.	0.38	0.042	.	.	0.046	0.017	.	0.020	.	10.32	0.063	.																											
1	GIOP-121	61.609	.	.	2.174	.	0.0207	.	0.0093	.	0.049	0.1915	.	0.011	.	0.0629	.	0.0168	.	2.986	.	0.0588																											
1	ASCRM 034	61.59	.	1.19	.	0.029	.	0.012	.	0.040	.	0.141	.	0.0117	.	0.082	.	0.024	2.00	.	0.054	.																											
1	GIOP-82	61.58	.	.	1.255	.	0.02	.	0.0097	.	0.04	0.2102	.	0.0172	.	0.0524	.	0.0155	.	3.079	.	0.697																											
1	NCS DC28024	61.53	0.24	.	2.12	.	0.118	.	0.026	.	0.109	0.276	.	.	0.034	0.068	.	0.038	.	3.43	0.052	.																											
1	GIOP-25	61.5	.	.	3.58	.	(<0.05)	.	0.028	.	0.055	0.023	.	.	0.023	.	0.017	.	5.28	.	0.135	.																											
1	NCS DC73006	61.46	(0.35)	.	1.68	.	0.52	.	0.098	.	0.77	0.072	.	.	0.080	0.019	.	(0.0067)	.	6.65	1.12	.																											
2	IMZ 340	61.45	3.40	.	2.37	.	1.22	.	(0.020)	.	2.40	0.15	.	.	0.066	(0.002)	.	.	.	4.20	.	2.45																											
1	OREAS 406	61.44	.	.	1.14	.	0.157	.	0.019	.	(0.037)	.	0.039	.	(0.017)	0.085	.	(0.006)	.	7.96	.	0.047																											
1	ECRM 688-1	61.38	.	0.679	.	1.449	.	0.180	.	1.061	.	0.0457	.	0.333	.	0.337	.	(0.0468)	3.383	.	0.408	.																											
1	NCS DC93023	61.34	29.68	.	0.45	.	0.64	.	0.018	.	(0.60)	0.056	.	.	0.012	0.036	.	0.494	.	12.36	.	0.064																											
1	GIOP-62	61.3	.	.	2.254	.	0.0628	.	0.0476	.	0.085	0.308	.	0.0209	.	0.0537	.	0.0348	.	4.282	.	0.1592																											
1	GIOP-115	61.28	.	.	1.748	.	0.2298	.	0.0205	.	0.1622	0.0166	.	0.0595	.	0.00882	.	0.0073	.	9.046	.	0.199																											
1	IMZ 361	61.16	3.4	.	2.60	.	0.074	.	0.0059	.	0.027	0.054	.	0.005	.	0.082	.	0.015	.	5.6	.	0.072																											
1	GIOP-51	61.126	.	.	2.096	.	0.0287	.	0.0114	.	0.049	0.274	.	0.0134	.	0.0665	.	0.0196	.	3.133	.	0.063																											
1	BAM 631-1	61.09	.	.	1.06	.	0.75	.	(0.04)	.	0.54	0.044	.	.	(0.04)	0.114	.	0.033	.	3.20	.	0.109																											
1	GIOP-124	61.051	.	.	2.529	.	0.0148	.	0.012	.	0.0679	0.0769	.	0.0193	.	0.0667	.	0.0178	.	3.535	.	0.0735																											
1	NCS DC28030	60.82	0.21	.	2.27	.	0.035	.	0.022	.	0.112	0.298	.	.	0.026	0.073	.	0.041	.	3.45	0.056	.																											
1	IMS FBS-203	60.67	.	.	1.62	.	0.067	.	0.215	.	0.096	4.29	.	.	0.056	0.041	.	0.017	.	2.20	.	0.101																											
1	GIOP-18	60.64	.	.	2.4	0.056	.	.	.	4.74	.	0.04																											

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂
		As	Ba	C	CO ₂	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other			
	GIOP-56	0.014	0.007	0.0038	0.00237	.	4.076	10 g				
	GIOP-43	0.0088	.	0.0038	.	0.0027	3.167	10 g				
	IMS FBS-72	(0.002)	(0.011)	.	(0.013)	(0.001)	(0.005)	(0.002)	(0.003)	(0.002)	(0.002)	0.020	.	.	(0.005)	(0.003)	3.89	250 g	Sr: 0.059			
	NCS DC15605	0.0019	100 g			
	ASCRM 035	0.0079	0.0017	.	.	0.0398	0.0018	0.0048	.	0.0087	0.0033	0.0005	0.0024	.	0.0029	0.0023	4.02	10x10 g	Sn: 0.0011	Sr: 0.0009		
	NCS DC28026	0.0013	0.001	0.0027	.	0.0015	0.0024	0.0004	.	.	0.0026	.	.	.	50 g			
	IRSID 611-1	100 g			
	USZ 27-99	0.013	.	.	0.030	0.008	.	.	.	(0.013)	.	(1.46)	10 g				
	SARM 132	100 g			
	GIOP-38	.	.	.	0.0124	.	.	0.0078	4.87	10 g			
	NCS DC28025	0.0011	0.0015	0.0038	.	0.0018	0.0033	0.0008	.	.	0.0026	.	.	50 g				
	IMZ 332	.	0.0036	0.012	.	.	.	0.005	.	0.0021	0.002	0.0016	(0.001)	.	0.0023	.	0.11	100 g				
	NCS DC28216	50 g			
	DSZU RG36	(1.1)	150 g	Insoluble Residue: 10.0%			
	NCS DC11009a	0.011	.	0.128	.	.	0.0061	.	.	0.063	.	0.042	.	.	0.054	.	.	50 g	BaO: (0.71)			
	GIOP-47	0.00263	6.309	10 g			
	IMZ 333	.	0.003	0.011	.	.	.	0.006	.	0.002	0.002	0.0015	0.001	.	0.0014	.	0.13	100				

CRM **IRON ORE, chart 6 of 9** # = class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
1	VS R36	57.47	0.73	.	0.71	.	0.037	.	0.015	.	0.39	.	0.024	.	0.076	0.0138	0.0064	.	16.28	.	0.031
1	NCS DC28081	57.41	1.89	.	5.11	.	0.34	.	0.150	.	0.142	.	0.228	.	0.045	0.054	0.018	.	7.31	.	0.230
1	GIOP-86	57.26	.	.	2.657	.	0.1514	.	0.0107	.	0.1758	0.085	.	0.0184	.	0.03934	0.0139	.	5.752	.	0.1434
1	GIOP-75	57.23	.	.	2.649	.	0.1564	.	0.01048	.	0.1778	0.0875	.	0.0182	.	0.0394	0.014	.	5.761	.	0.143
1	GIOP-68	57.18	.	.	4.126	.	0.0414	.	0.0173	.	0.063	0.1027	.	0.0163	.	0.0555	0.0293	.	5.51	.	0.2228
1	GIOP-61	57.14	.	.	2.523	.	0.1735	.	0.0194	.	0.068	0.228	.	0.0199	.	0.0426	0.0388	.	5.946	.	0.115
1	JSS 821-1	57.05	.	1.24	.	0.159	.	0.0055	.	0.113	.	0.085	.	0.0095	.	0.0415	0.0108	2.28	.	0.0718	.
1	ECRM 689-1	57.05	.	1.185	.	1.183	.	0.462	.	0.980	.	0.1196	.	0.638	.	0.0706	.	(5.4)	.	0.3264	.
1	ASCRM 030	56.76	.	1.42	.	0.245	.	0.009	.	0.108	.	0.079	.	0.0170	.	0.038	0.021	2.71	.	0.089	.
1	JSS 831-2	56.64	1.97	FeII: 21.82	.	1.05	.	0.061	.	2.09	.	0.501	.	0.082	.	0.153	0.0049	1.93	.	4.51	.
1	NCS DC73005	56.60	20.50	.	0.99	.	1.36	.	0.071	.	3.62	0.076	.	0.058	.	0.017	2.44	.	11.48	0.043	.
1	GIOP-142	56.58	.	.	3.032	.	0.2678	.	0.0109	.	0.218	0.0892	.	0.0126	.	0.0412	0.01404	.	6.704	.	0.1782
1	NCS DC28212	56.29	26.9	.	2.53	.	8.04	.	.	.	1.96	.	0.289	.	.	0.032	0.197	.	8.86	.	0.208
1	GIOP-137	56.285	.	.	6.029	.	0.966	.	0.0691	.	0.5292	0.04	.	0.2205	.	0.0579	0.0209	.	7.946	.	0.3815
1	NCS DC28112	56.23	24.15	.	1.39	.	2.73	.	0.133	.	4.89	0.132	.	.	0.070	0.023	0.369	.	7.81	0.620	1.03
1	JSS 820-5	56.17	.	1.63	.	0.112	.	0.0172	.	0.073	.	0.067	.	0.0132	.	0.031	0.0182	2.81	.	0.092	.
1	IMS PBS-73	56.06	.	.	3.19	.	0.129	.	0.027	.	(0.090)	0.138	.	.	0.096	0.076	0.038	.	6.77	.	0.111
1	NCS DC11018	56.02	7.78	.	2.20	.	9.89	.	0.038	.	2.87	.	0.355	.	0.057	0.058	0.023	.	4.50	.	0.108
2	IMZ 313	55.85	0.68	.	1.13	.	0.079	.	0.030	.	0.31	0.03	.	.	0.23	0.031	0.0085	.	17.29	.	0.044
1	NCS DC15002a	55.81	1.86	.	1.93	.	1.10	.	0.433	.	0.36	.	0.026	.	0.33	0.011	0.469	.	13.00	.	0.083
1	VS R5/6	55.8	9.81	.	2.57	.	9.30	.	.	.	1.95	.	0.86	.	.	0.029	0.035	.	5.71	.	0.29
1	IMS PBS-202	55.48	.	.	2.60	.	1.43	.	0.191	.	1.05	0.576	.	.	0.034	0.202	0.095	.	4.29	.	0.192
1	IMS PBS-31	55.24	.	.	6.03	.	0.062	.	0.020	.	(0.096)	0.231	.	.	(0.072)	0.038	0.066	.	4.26	.	0.185
1	NCS DC19016	55.23	1.01	.	3.07	.	1.08	.	0.123	.	1.88	.	0.199	.	0.173	0.037	0.0087	.	6.43	.	7.69
1	GIOP-136	55.22	.	.	6.493	.	1.055	.	0.0757	.	0.5767	0.0402	.	0.241	.	0.0578	0.0241	.	8.632	.	0.4166
1	OREAS 404	55.14	.	.	2.97	.	0.102	.	(0.008)	.	(0.074)	.	(0.007)	.	(0.014)	0.151	0.032	.	7.88	.	0.385
2	IMZ 343	55.09	6.37	.	0.74	.	10.93	.	0.037	.	1.21	0.0200	.	.	(0.040)	0.030	0.021	.	9.31	.	0.032
1	NCS DC28225	54.96	10.7	.	2.93	.	11.49	.	.	.	0.98	.	0.171	.	.	0.050	0.032	.	5.89	.	0.152
1	NCS DC18018	54.90	7.87	.	2.34	.	10.36	.	.	.	2.41	.	0.29	.	.	0.064	0.036	.	5.81	.	0.50
1	NCS DC11004a	54.86	1.17	.	2.85	.	0.630	.	0.26	.	0.524	.	1.04	.	0.047	0.119	0.258	.	8.27	.	0.120
1	VS 5405-90	54.83	.	.	2.04	.	.	.	0.33	.	0.29	0.62	.	.	.	0.034	0.018	.	16.23	.	0.092
1	NCS DC11006a	54.74	3.90	.	1.48	.	1.02	.	0.214	.	0.657	.	1.31	.	0.048	0.036	0.439	.	8.53	.	0.154
1	NCS DC18019	54.03	7.98	.	2.57	.	10.50	.	.	.	2.71	.	0.70	.	.	0.073	0.027	.	6.11	.	0.24
1	NM 161.5A	53.91	.	.	7.50	0.07	0.009	.	7.14	.	0.29
1	IMS PBS-28	53.74	.	.	4.34	.	0.058	.	0.073	.	(0.094)	0.851	.	.	(0.098)	0.074	0.029	.	7.12	.	0.190
1	IRSID 603-1	53.65	.	4.20	.	(0.91)	.	.	.	(0.2)	.	0.440	.	.	.	0.084	0.097	1.28	.	0.137	.
1	NCS DC28034	53.42	15.27	.	0.57	.	0.31	.	0.086	.	11.21	0.065	.	.	0.25	0.018	0.192	.	5.22	0.044	.

#	Number	As	Ba	C	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other	
	VS R36	Insoluble Residue: 16.5	100 g				
	NCS DC28081	0.0014	0.032	.	0.0038	0.0027	50 g				
	GIOP-86	0.00336	.	0.0094	10 g				
	GIOP-75	0.00312	.	0.0092	10 g				
	GIOP-68	.	.	.	0.011	.	0.0051	0.00353	.	.	10 g				
	GIOP-61	.	.	.	0.0094	0.0042	10 g				
	JSS 821-1	0.0027	.	0.0007	0.0035	0.0006	0.0040	.	.	0.0074	70 g				
	ECRM 689-1	.	.	.	0.0103	.	0.0068	0.00195	0.0120	.	0.0042	.	.	0.0042	100 g				
	ASCRM 030	0.0014	0.0034	.	0.0101	0.0014	0.0020	0.0016	0.0019	0.0008	0.0042	.	.	0.0096	0.0037	9.24	10x10 g	Sr: 0.0010	
	JSS 831-2	0.028	.	0.0068	0.0077	.	0.299	.	.	0.074	.	(0.11)	100 g		
	NCS DC73005	0.068	0.0023	0.00065	0.0042	.	.	0.0032	.	8.78	70 g		
	GIOP-142	(0.0015)	(0.0052)	.	(0.0035)	0.00182	0.00206	(0.0019)	0.002	(0.0038)	0.00499	.	.	0.00871	0.0054	8.368	10 g	Sr:0.004	
	NCS DC28212	50 g		
	GIOP-137	(0.001)	0.0053	.	(0.0032)	(0.0017)	0.0051	(0.0019)	0.00175	(0.0026)	0.00726	.	.	0.00233	0.0079	3.111	10 g	Sr: 0.0056	
	NCS DC28112	0.167	0.527	0.037	.	.	70 g		
	JSS 820-5	0.0032	.	0.00068	0.0023	0.00065	0.0042	.	0.0032	.	8.78	70 g		
	IMS PBS-73	(0.022)	0.039	.	(0.082)	0.042	0.043	.	0.049	0.046	0.056	0.034	Sr:0.070	0.057	(0.045)	8.36	250 g	Sn: 0.045	
	NCS DC11018	0.0014	0.0044	.	0.0044	.	0.0031	.	.	0.065	.	.	70 g		
	IMZ 313	(0.0008)	0.0017	0.031	(0.29)	0.0002	0.0067	.	0.0015	0.0024	0.0009	(0.001)	.	0.0028	.	-1.31	100 g		
	NCS DC15002a	0.23	0.134	.	0.319	.	.	0.161	.	.	50 g		
	VS R5/6	150 g		
	IMS PBS-202	0.013	(0.006)	.	(0.018)	(0.004)	0.007	.	0.002	0.010	0.004	0.007	.	0.014	(0.005)	9.46	250 g	17034	
	IMS PBS-31	0.081	(0.002)	.	(0.055)	(0.003)	.	0.009	(0.002)	(0.005)	(0.003)	(0.006)	.	0.019	(0.007)	9.56	250 g		
	NCS DC19016	.	.	.	0.010	.	0.34	.	0.021	.	.	.	0.51	0.033	.	.	100 g		
	GIOP-136	(0.001)	0.0056	.	0.0036	(0.0018)	0.00537	.	(0.0016)	0.00194	(0.003)	0.00768	.	0.00257	0.0087	3.266	10 g	Sr: 0.0053	
	OREAS 404	(0.00176)	(0.00312)	.	(0.00379)	.	.	0.0124	(0.0018)	(0.0031)	(0.0006)	(0.00422)	.	(0.0018)	(0.0107)	9.40	10 g	Sr: (23.6*)	
	IMZ 343	0.004	0.005	.	.	100 g		
	NCS DC28225	50 g		
	NCS DC18018	100 g		
	NCS DC11004a	0.096	(BaO:0.86)	0.310	.	0.0054	.	.	0.066	.	0.101	.	.	0.144	.	.	50 g		
	VS 5405-90	0.23	.	.	0.089	.	.	50 g		Ge: 5.1*
	NCS DC11006a	0.215	(BaO:1.08)	0.227	.	0.0086	.	.	0.102	.	0.182	.	.	0.30	.	.	50 g		
	NCS DC18019	0.021	100 g		
	NM 161.5A	100 g		
	IMS PBS-28	(0.003)	(0.010)	.	0.080	(0.002)	.	(0.007)	(0.002)	(0.005)	(0.003)	(0.003)	.	(0.008)	(0.003)	9.75	250 g		
	IRSID 603-1	100 g		
	NCS DC28034	70 g		B ₂ O ₃ : 3.62

Number	As	Ba	C	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other
--------	----	----	---	----	----	----	--------------------------------	----	----	----	---	-------------------------------	----	----	-----	-------	-------

CRM		IRON ORE, chart 7 of 9														# = class, where 1 = CRM and 2 = RM											analysis listed in mass % except * which is mg/kg	
#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂							
1	SARM 147	52.67	.	.	0.96	.	7.05	.	(0.21)	.	5.28	.	0.23	.	.	.	0.13	.	3.35	.	1.72							
1	OREAS 403	52.31	.	.	2.63	.	0.106	.	0.011	.	0.077	.	(0.007)	.	(0.015)	0.123	0.026	.	13.67	.	0.289							
1	NCS DC11007a	52.24	4.21	.	6.84	.	0.561	.	0.61	.	0.606	.	0.194	.	0.093	0.346	0.094	.	10.20	.	0.237							
2	IMZ 263/1	52.10	.	.	1.14	.	0.17	.	0.17	(0.04)	0.045	.	0.17	.	.	(0.026)	0.036	.	22.78	.	.							
1	IMS PBS-222	52.08	.	.	9.60	.	0.073	.	0.024	.	0.080	0.126	.	.	0.027	0.039	0.034	.	9.33	.	0.760							
1	NCS DC11029	51.67	27.30	.	4.97	.	0.52	.	0.0081	.	2.02	.	0.238	.	0.023	0.046	0.259	.	4.06	.	13.54							
1	ECRM 677-1	51.54	.	0.32	.	0.038	.	0.008	.	0.012	.	0.016	.	0.007	.	0.0170	(0.005)	11.78	.	0.013	.							
1	NCS DC28064	51.48	0.25	.	5.65	.	0.014	.	.	0.70	0.70	0.0045	0.17	.	2.30	.	0.15							
1	NCS DC28067	51.36	0.26	.	4.16	.	0.022	.	0.022	.	1.05	0.80	.	.	.	0.0055	0.095	.	3.11	.	0.091							
1	IMS PBS-29	51.21	.	.	3.69	.	0.085	.	0.090	.	(0.093)	1.284	.	.	(0.052)	0.054	0.030	.	12.56	.	0.245							
1	NCS DC28083	50.98	8.92	.	5.03	.	3.44	.	.	1.05	.	0.306	.	.	0.963	0.112	.	9.40	.	0.125								
1	NCS DC28111	50.94	20.67	.	1.42	.	4.85	.	0.204	.	3.95	0.098	.	0.14	0.033	0.430	.	13.83	0.065	0.108								
1	NCS DC28213	50.92	19.9	.	3.28	.	6.90	.	.	3.40	.	0.943	.	.	0.050	0.130	.	13.68	.	0.241								
1	CGL 206	50.87	Sr:0.002238	.	1.25	.	5.87	.	0.24	.	4.93	.	0.11	.	(0.10)	.	(2.60)	.	5.86	.	0.08							
1	GIOP-15	50.68	.	.	4.1	0.032	.	.	.	20.10	.	0.04							
1	VS R33	50.42	8.35	.	.	1.33	0.039	3.10	.	10.62	.	.							
1	NCS DC28082	49.53	0.05	.	7.45	.	0.032	.	0.107	.	0.107	.	3.39	.	.	0.083	0.029	.	7.44	.	0.370							
1	NCS DC73004	49.50	7.66	.	2.58	.	0.91	.	0.91	.	0.98	0.198	.	.	0.035	0.138	0.065	.	16.30	0.083	.							
1	GIOP-36	49.5	.	.	5.51	.	0.011	.	.	2.657	0.200	0.008	0.014	.	0.85	.	20.10							
1	GIOP-35	49.4	.	.	5.53	2.569	0.200	0.008	0.014	.	0.85	.	20.20							
1	NCS DC11030	49.12	26.44	.	5.09	.	1.16	.	0.023	.	2.30	.	0.240	.	0.073	0.179	0.382	.	5.52	.	12.80							
1	NCS DC18017	48.44	11.17	.	2.98	.	15.52	.	.	2.32	.	0.81	.	.	.	0.065	0.155	.	8.40	.	0.23							
1	OREAS 402	48.41	.	.	2.49	.	0.090	.	0.010	.	0.072	.	(0.007)	.	(0.016)	0.119	0.024	.	19.77	.	0.288							
1	NCS DC28082a	48.00	0.05	.	3.44	.	0.15	.	0.33	.	0.268	.	3.40	.	.	0.076	0.111	.	12.74	.	0.146							
1	NCS DC15004	47.86	21.99	.	1.12	.	1.72	.	0.062	.	0.96	.	0.082	.	0.043	0.032	0.235	.	28.01	.	0.070							
1	NCS DC26706	47.72	.	.	4.65	.	0.13	.	.	2.34	0.89	0.0027	0.12	.	5.16	.	.							
1	GIOP-134	47.52	.	.	9.953	.	1.688	.	0.1171	.	0.934	0.05982	.	0.3921	.	0.0577	0.0258	.	13.474	.	0.6576							
2	IMZ 341	47.52	.	.	1.22	.	0.52	.	0.11	.	0.35	0.021	.	.	(0.09)	0.164	0.006	.	28.49	.	0.041							
1	NCS DC28108	46.93	19.95	.	2.05	.	7.12	.	0.33	.	5.54	0.058	.	.	0.220	0.039	0.637	.	14.75	0.067	0.112							
1	NCS DC11031	46.74	24.39	.	5.49	.	1.18	.	0.021	.	2.60	.	0.226	.	0.057	0.101	0.21	.	8.19	.	12.24							
1	OREAS 401	45.63	.	.	2.36	.	0.094	.	0.010	.	0.061	.	(0.007)	.	(0.016)	0.105	0.022	.	24.88	.	0.247							
1	GIOP-133	45.481	.	.	10.86	.	1.863	.	0.1277	.	1.029	0.06048	.	0.4342	.	0.0573	0.0277	.	14.796	.	0.7211							
1	NCS DC62001d	44.99=Fe ₂ O ₃	.	.	4.37	.	9.92	.	0.89	.	1.55	.	.	0.37	.	s03:3.15	0.024	.	26.64	.	0.27							
1	NCS DC11001	44.73	12.91	.	0.75	.	7.14	.	.	4.18	.	0.20	.	.	.	0.013	1.50	.	18.22	.	.							
1	NM 161.4A	44.52	.	.	12.33	0.09	0.01	.	12.23	.	0.47							
1	IMS PBS-11	44.56	.	.	6.12	.	0.146	.	0.122	.	(0.118)	0.814	.	.	(0.028)	0.047	0.033	.	21.51	.	0.528							
1	AMIS 0346	44.34	15.02	.	.							
2	IMZ 264/1	44.25	.	.	1.14	.	0.23	.	.	0.22	(0.04)	0.043	.	.	.	0.025	0.055	.	33.56	.	.							
1	GIOP-132	43.12	.	.	11.89	.	2.062	.	0.1405	.	1.141	0.0608	.	0.4797	.	0.0567	0.0302	.	16.33	.	0.7943							
1	NCS DC19013	42.89	.	.	4.10	.	0.124	.	.	0.517	.	1.67	.	.	.	0.099	.	.	22.06	.	0.26							

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂	
1	SARM 147	.	.	C:1.36	CuO:(0.13)	.	(0.04)	0.104	.	.	.	3.37	100 g	P ₂ O ₅ : 1.17	
1	OREAS 403	(0.00137)	.	.	(0.00366)	.	.	0.0109	(0.0016)	(0.0020)	.	(0.0018)	.	0.00345	.	(0.0020)	.	(0.0085)	8.00	10 g		
1	NCS DC11007a	0.051	.	C:0.549	.	0.0043	.	.	0.015	.	.	0.034	.	.	0.066	.	.	.	50 g		BaO: (0.028)	
1	IMZ 263/1	100 g			
1	IMS PBS-222	0.005	(0.002)	.	(0.007)	(0.001)	.	(0.007)	0.002	(0.002)	.	(0.003)	0.007	0.002	.	17034	(0.018)	5.22	250 g		Sr: 0.008	
1	NCS DC11029	(0.0015)	0.590	0.045	.	.	.	70 g		
1	ECRM 677-1	100 g		
1	NCS DC28064	0.10	1.80	.	.	0.72	50 g		
1	NCS DC28067	0.098	2.00	.	.	0.94	50 g		
1	IMS PBS-29	(0.004)	(0.012)	.	(0.027)	(0.002)	.	(0.009)	(0.002)	(0.005)	.	(0.003)	(0.006)	(0.008)	.	.	(0.007)	7.86	250 g			
1	NCS DC28083	.	.	C:0.89	50 g		
1	NCS DC28111	0.083	0.305	0.017	.	.	.	70 g			
1	NCS DC28213	50 g			
1	CGL 206	(0.00270)	(0.00251)	.	.	0.00905	(0.00202)	.	0.04181	0.01143	.	0.004446	0.02655	.	0.07032	.	.	(4.59)	100 g		P ₂ O ₅ : 0.048	
1	GIOP-15	1.3	10 g		
1	VS R33	100 g		
1	NCS DC28082	50 g		C: 0.071
1	NCS DC73004	0.0014	50 g			
1	GIOP-36	.	.	0.008	0.022	0.067	.	.	0.038	.	.	0.313	.	0.063	.	.	.	0.64	10 g			
1	GIOP-35	.	.	0.008	0.022	0.068	.	.	0.038	.	.	0.313	.	0.062	.	.	.	0.51	10 g		Sn: 0.003	
1	NCS DC11030	0.553	0.043	.	.	.	70 g			
1	NCS DC18017	0.030	0.061	.	.	0.13	100 g			
1	OREAS 402	(0.00114)	.	(0.00343)	.	.	.	0.0109	(0.0018)	(0.00148)	.	(0.00090)	(0.00351)	.	(0.00193)	.	(0.0083)	7.64	10 g			
1	NCS DC28082a	0.283	.	.	0.49	50 g		C: 0.072	
1	NCS DC15004	0.0023	100 g			
1	NCS DC26706	0.14	2.34	.	.	1.05	25 g		C: 0.25	
1	GIOP-134	(0.001)	0.008	.	0.0036	(0.0015)	0.0077	.	(0.002)	0.00227	.	(0.0027)	0.0122	.	0.00251	.	0.0125	4.452	10 g		Sr: 0.007	
1	IMZ 341	.	.	C:(0.037)	(1.1)	100 g		
1	NCS DC28108	0.119	0.0038	.	.	.	70 g			
1	NCS DC11031	0.539	0.041	.	.	.	70 g			
1	OREAS 401	(0.00109)	.	(0.00328)	.	.	.	0.0107	(0.0018)	(0.00289)	.	(0.00112)	(0.00322)	.	(0.00211)	.	(0.0074)	6.71	10 g			
1	GIOP-133	(0.001)	0.0081	.	0.00357	(0.0014)	0.00784	.	(0.0013)	0.00233	.	(0.0021)	0.129	.	0.00297	.	0.136	4.762	10 g		Sr: 0.0075	
1	NCS DC62001d	7.51	20 g		
1	NCS DC11001	60 g			
1	NM 161.4A	100 g			
1	IMS PBS-11	(0.003)	(0.013)	.	(0.009)	(0.001)	.	(0.021)	(0.003)	(0.004)	.	(0.004)	0.011	(0.006)	.	.	(0.014)	6.28	250 g			
1	AMIS 0346	0.27	.	.	.	Density: 4.39	.	100 g		or 1kg	
1	IMZ 264/1	100 g			
1	GIOP-132	(0.001)	0.0083	.	0.00413	(0.0016)	0.0089</															

CRM IRON ORE, chart 8 of 9 # = class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
1	IRSID 612-1	42.4	.	3.00	.	12.06	.	.	1.20	.	.	0.363	.	.	.	0.885	0.053	5.94	.	0.151	.
1	NCS DC18020	41.81	21.87	.	3.23	.	18.30	.	.	4.85	.	1.80	.	.	.	0.159	0.302	.	10.21	.	0.50
1	IMS PBS-30	41.13	.	.	4.57	.	0.070	.	0.382	.	(0.089)	12.78	.	.	(0.093)	0.038	0.033	.	7.02	.	0.231
1	GIOP 131	41.08	.	.	12.77	.	2.23	.	0.151	.	1.231	0.0612	.	0.5184	.	0.0561	0.0329	.	17.619	.	0.8557
1	NCS DC73003	40.51	(14.5)	.	2.27	.	2.00	.	0.27	.	2.22	0.122	.	.	0.16	0.032	0.94	.	33.93	0.067	.
1	NCS DC28065	39.68	0.10	.	9.98	.	0.30	.	.	2.54	0.59	0.010	0.23	.	10.00	.	0.14
1	CGL 133	39.32	.	.	1.69	.	9.34	.	0.35	.	8.04	.	0.133	.	(0.162)	.	(2.727)	.	9.29	.	0.095
1	KZ 182-89	38.63	1.61	.	1.04	.	0.14	.	0.11	.	.	0.044	.	.	.	0.065	.	.	42.64	.	0.144
1	VS R0/3	38.2	.	.	10.35	.	0.89	.	.	2.17	.	0.432	.	.	.	0.165	0.031	.	16.57	.	0.85
2	IMZ 265/1	37.74	.	.	3.10	.	1.50	.	.	0.53	0.056	0.039	0.047	.	37.02	.	.
1	IRSID 601-1	36.76	.	2.33	.	4.05	.	.	1.21	.	.	0.370	.	.	.	0.590	0.065	8.95	.	0.114	.
1	NCS DC13033	35.36	5.18	.	(0.11)	.	(0.13)	.	.	.	0.20	.	0.125	.	.	0.022	0.0064	.	48.50	.	0.007
1	KZ 183-89	35.16	1.32	.	1.66	.	.	.	0.35	.	.	0.046	.	.	.	0.019	0.7	.	41.56	.	0.073
1	VS R20/3	34.7	.	.	0.67	.	2.54	Magnetic Iron: 27.6%	.	3.42	0.073	.	37.6	.	.
1	NCS DC28069	34.18	0.11	.	2.39	.	0.12	.	.	12.12	0.78	0.0015	0.082	.	18.28	.	0.030
1	NCS DC11013	34.07	20.15	.	0.74	.	0.99	.	0.165	.	2.86	.	0.093	.	0.065	0.054	0.118	.	48.27	.	0.043
1	VS R24/2	33.73	.	.	1.52	.	2.12	.	.	8.29	0.0055	0.065	.	5.46	.	.
1	VS R9/1	33.48	42.9	.	0.86	.	2.29	.	.	9.64	0.0051	0.059	.	3.47	.	.
1	GIOP 110	33.21	.	.	0.0893	.	1.417	.	0.0159	.	1.778	0.021	.	0.0152	.	0.0928	0.0042	.	56.09	.	0.0141
1	IMS-441	32.71	.	.	2.01	.	1.43	.	0.708	.	2.37	0.458	.	.	0.100	0.102	0.113	.	39.11	.	0.104
1	GIOP 98	32.63	.	.	0.1008	.	1.409	.	0.0121	.	1.875	0.0179	.	0.0163	.	0.1103	0.0273	.	56.88	.	0.136
1	NCS HCl19820	32.30	.	.	3.98	.	2.12	.	.	3.37	.	7.36	.	.	.	0.040	0.195	.	16.47	.	10.80
1	GIOP 107	32.23	.	.	0.246	.	3.523	.	0.0135	.	1.257	0.037	.	0.0279	.	0.0497	0.1871	.	49.76	.	0.044
1	GIOP 113	32.11	.	.	0.5359	.	2.403	.	0.0218	.	2.343	0.1712	.	0.0276	.	0.0793	0.453	.	48.98	.	0.0298
1	GIOP 99	31.7	.	.	0.2553	.	1.5672	.	0.039	.	1.967	0.0248	.	0.0197	.	0.1066	0.003	.	51.54	.	0.0278
1	GIOP-105	31.04	.	.	0.438	.	1.841	.	0.075	.	2.289	0.0446	.	0.0238	.	0.0876	0.1507	.	51.51	.	0.0374
1	IMS-440	30.93	.	.	0.53	.	0.580	.	0.078	.	0.844	0.092	.	.	0.071	0.045	0.054	.	53.85	.	0.040
1	IRSID 607-1	30.89	.	2.48	.	13.74	.	.	.	0.77	.	0.254	.	.	.	0.529	0.050	3.07	.	0.123	.
1	NCS HCl19819	30.08	.	.	4.15	.	1.79	.	.	.	3.41	.	8.36	.	.	0.026	0.201	.	15.79	.	11.37

#	Number	As	Ba	CO ₂	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	NiO	Pb	V	V ₂ O ₅	Zn	ZnO	Zr	LOI	Units	Other		
	IRSID 612-1	100 g		
	NCS DC18020	0.051	0.208	.	.	.	0.223	.	.	.	100 g		
	IMS PBS-30	(0.002)	0.088	.	(0.008)	(0.015)	.	(0.007)	(0.002)	(0.007)	.	(0.004)	(0.004)	.	(0.005)	.	(0.007)	10.80	250 g			
	GIOP 131	(0.001)	0.0081	.	0.004	(0.0015)	0.009	.	(0.0017)	0.00236	.	(0.0016)	0.0166	.	0.00326	.	0.0173	5.405	10 g	Sr: 0.0086		
	NCS DC73003	0.028	50 g		
	NCS DC28065	0.085	1.71	.	.	1.30	50 g		
	CGL 133	(0.0036)	(0.0042)	.	.	0.0072	0.0027	.	0.0397	0.0081	.	(0.0021)	0.0054	.	0.0234	.	.	(10.22)	100 g	P ₂ O ₅ :0.063		
	KZ 182-89	100 g		
	VS R0/3	(0.06)	.	2.53	.	.	0.67	16.4	75 g			
	IMZ 265/1	100 g		
	IRSID 601-1	100 g		
	NCS DC13033	50 g		
	KZ 183-89	.	3.10	0.026	100 g	Ge: 36.6*		
	VS R20/3	100 g			
	NCS DC28069	0.13	1.48	.	.	1.50	50 g			
	NCS DC11013	0.0003	0.0031	.	0.028	.	.	.	0.0045	.	.	.	70 g			
	VS R24/2	100 or	125 g		
	VS R9/1	.	.	CO ₃ : (11.0)	100 g			
	GIOP 110	(0.0032)	(0.0046)	.	(0.0047)	(0.0032)	(0.0048)	.	(0.0055)	(0.0064)	.	(0.0022)	(0.001)	.	0.0031	.	(0.0015)	1.17	10 g			
	IMS-441	(0.001)	0.010	.	(0.004)	(0.002)	0.016	.	0.001	0.007	.	(0.002)	0.003	.	0.004	.	0.003	6.21	10 g	Sr: 0.006	17034	
	GIOP 98	(0.0044)	0.0067	.	(0.0045)	(0.0037)	(0.01)	.	(0.0047)	(0.004)	.	(0.0062)	(0.001)	.	(0.0041)	.	(0.002)	1.217	10 g			
	NCS HCl19820	2.00	1.78	100 g			
	GIOP 107	(0.0044)	(0.0047)	.	0.0058	(0.0028)	(0.0026)	.	(0.0045)	(0.0032)	.	(0.0032)	(0.0017)	.	0.0047	.	(0.0022)	1.224	10 g			
	GIOP 113	(0.0033)	(0.0042)	.	0.0117	0.0034	(0.0019)	.	(0.0048)	(0.0048)	.	(0.0042)	(0.0021)	.	0.0107	.	(0.0021)	0.719	10 g			
	GIOP 99	(0.0055)	(0.0041)	.	(0.0045)	(0.0032)	(0.0046)	.	(0.0051)	(0.003)	.	(0.0032)	(0.0016)	.	(0.0036)	.	(0.0023)	0.984	10 g			
	GIOP-105	(0.004)	0.0077	.	0.0078	(0.0032)	(0.0036)	.	(0.004)	(0.003)	.	(0.0026)	(0.0023)	.	(0.0049)	.	(0.0021)	-0.997	10 g			
	IMS-440	(0.002)	(0.002)	.	0.010	(0.002)	0.004	.	0.002	(0.002)	.	0.003	(0.002)	.	0.002	.	0.004	-0.55	10 g		17034	
	IRSID 607-1	100 g			
	NCS HCl19819	2.60	2.20	.	.	.	100 g			

Number	As	Ba	CO ₂	Cl	Co	Cr	Cr ₂ O ₃	Cu	Ni	NiO	Pb	V	V ₂ O ₅	Zn	ZnO	Zr	LOI	Units	Other
--------	----	----	-----------------	----	----	----	--------------------------------	----	----	-----	----	---	-------------------------------	----	-----	----	-----	-------	-------

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

CRM IRON ORE, chart 9 of 9 # = class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Fe	FeO	Al	Al ₂ O ₃	Ca	CaO	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P	S	Si	SiO ₂	Ti	TiO ₂
2	IMZ 266/1	29.04	.	.	3.13	.	3.42	.	.	.	0.95	.	0.078	.	.	0.030	0.10	.	44.94	.	.
1	GIOP 104	29.83	.	.	0.526	.	2.168	.	0.0409	.	2.535	0.0762	.	0.0235	.	0.1065	0.2414	.	52.59	.	0.0289
1	GIOP 112	29.46	.	.	0.405	.	2.047	.	0.0267	.	2.323	0.0678	.	0.0248	.	0.0876	0.3007	.	53.57	.	0.0207
1	GIOP-97	28.234	.	.	0.746	.	3.028	.	0.0522	.	2.093	0.0742	.	0.0552	.	0.0396	0.554	.	54.4	.	0.0279
1	VS R39	28.03	.	.	3.92	.	1.69	.	1.29	.	1.97	.	0.069	.	0.083	0.073	0.245	.	49.1	.	0.155
1	GIOP-96	27.442	.	.	0.723	.	2.884	.	0.051	.	2.819	0.107	.	0.038	.	0.0507	0.94	.	54.38	.	0.0289
1	NCS DC28071	25.15	20.15	.	6.68	.	11.80	.	.	.	12.48	0.54	.	.	.	0.017	0.22	.	29.18	.	0.17
1	GIOP 95	24.215	34.86	.	1.259	.	4.804	.	0.0806	.	4.374	0.2045	.	0.049	.	0.066	0.497	.	54.85	.	0.0584
1	ECRM 651-1	23.85	.	2.25	.	16.15	.	0.27	.	1.04	.	0.97	.	.	.	0.35	0.40	3.46	.	0.10	.
1	IMS PBS-310	22.98	.	.	14.20	.	2.84	.	0.981	.	2.64	1.73	.	0.05	1.70	0.040	0.027	.	30.24	.	0.830
1	GIOP 139	22.43	.	.	4.974	.	1.316	.	2.617	.	1.978	0.068	.	0.5068	.	0.0995	0.39	.	53.76	.	0.1922
1	NCS DC73001	20.17	(7.5)	.	3.57	.	2.84	.	0.53	.	1.68	0.168	.	.	0.28	0.045	0.051	.	60.86	0.085	.
2	IMZ 267/1	19.75	.	.	4.05	.	4.73	.	.	.	1.22	(0.16)	0.16	.	.	0.030	0.17	.	53.72	.	.
1	NCS DC28070	19.43	10.20	.	7.10	.	20.02	.	.	.	11.58	0.50	.	.	.	0.024	0.35	.	28.78	.	0.24
1	NCS DC28068	16.83	0.10	.	2.06	.	0.16	.	.	.	21.32	0.40	.	.	.	0.0018	0.025	.	34.93	.	0.043
1	GIOP-128	16.494	.	.	34.64	.	0.0207	.	0.1797	.	0.035	0.0336	.	0.0194	.	0.012	0.0518	.	21.726	.	1.581

Number	As	Ba	Cl	Co	Cr	Cu	Ni	Pb	V	V ₂ O ₅	Zn	Zr	LOI	Units	Other
IMZ 266/1	100 g	.
GIOP 104	(0.006)	(0.0047)	0.0099	(0.0031)	(0.0013)	(0.0043)	(0.0045)	(0.0042)	(0.0016)	.	0.006	(0.0017)	0.992	10 g	.
GIOP 112	(0.0063)	(0.0038)	0.0104	(0.0033)	(0.0016)	(0.0045)	(0.0031)	(0.0045)	(0.0013)	.	0.0061	(0.002)	0.922	10 g	.
GIOP-97	(0.0085)	(0.0037)	0.0095	(0.003)	(0.0011)	0.0062	(0.004)	(0.0041)	(0.0012)	.	0.006	(0.0021)	-0.92	10 g	.
VS R39	23.1%	Iron Magnetite	100 g	Fe ₂ O ₃ : 14.96
GIOP-96	(0.0081)	(0.0059)	0.0201	(0.0032)	(0.0034)	(0.0064)	(0.0046)	(0.004)	(0.0018)	.	0.0076	(0.0027)	-0.454	10 g	.
NCS DC28071	.	.	.	0.066	1.16	.	1.41	50 g	.
GIOP 95	(0.0084)	(0.002)	0.0184	(0.0031)	(0.0031)	0.005	(0.0055)	(0.0056)	(0.003)	.	0.0087	(0.002)	0.546	10 g	.
ECRM 651-1	100 g	.
IMS PBS-310	(0.003)	0.021	1.73	(0.004)	0.012	0.007	0.009	(0.004)	(0.013)	.	0.007	(0.020)	10.93	10 g	17034
GIOP 139	0.0075	0.0183	(0.006)	(0.0017)	(0.0023)	0.0041	(0.0019)	0.0054	0.00332	.	0.155	0.0081	1.63	10 g	Sr: 0.0101
NCS DC73001	0.0028	50 g	.
IMZ 267/1	100 g	.
NCS DC28070	.	.	.	0.055	0.81	.	1.07	50 g	.
NCS DC28068	.	.	.	0.064	0.81	.	1.74	50 g	.
GIOP-128	0.0034	(0.0063)	0.0085	(0.0095)	0.0151	(0.004)	(0.0038)	(0.0066)	0.0424	.	(0.0033)	0.049	17.964	10 g	Sr: 0.0047

CRM COARSE AND RAW IRON ORE 2kg of raw, coarse material

Number	Fe	Al ₂ O ₃	CaO	K ₂ O	MgO	Mn	Na	P	S	SiO ₂	Sr	TiO ₂	LOI
GIOC-16	57.72	2.69	0.041	0.040	0.096	0.537	(0.016)	0.069	0.026	5.13	(0.002)	0.183	8.30
GIOC-15	57.43	3.40	0.047	0.021	0.080	0.361	(0.011)	0.117	0.068	4.24	(0.002)	0.166	9.01
GIOC-8	57.28	2.42	0.120	0.006	0.145	0.072	(0.011)	0.040	0.014	5.38	0.051	0.147	9.66

Number	As	Ba	Cl	Co	Cr	Cu	Ni	Pb	Sn	V	Zn	Zr
GIOC-16	(0.002)	(0.007)	0.007	(0.003)	(0.003)	(0.003)	(0.003)	(0.003)	(0.001)	0.004	(0.004)	(0.005)
GIOC-15	0.007	(0.005)	0.008	(0.002)	(0.002)	(0.003)	(0.003)	(0.002)	(0.001)	0.003	(0.003)	0.007
GIOC-8	0.002	(0.002)	(0.004)	(0.001)	(0.002)	(0.001)	(0.002)	(0.002)	(0.006)	(0.003)	0.007	(0.005)

IRON ORE SINTER

= class, where 1 = CRM and 2 = RM analysis listed in mass %

# Number	Fe	FeO	Al	Al ₂ O ₃	C	CO ₂	Ca	CaO	Cr ₂ O ₃	Cu	CuO	F	K	K ₂ O	Mg	MgO	LOI 900°C
2 DH 5630	60.62	4.86	.	1.134	.	.	.	6.99	0.040	.	0.654	.
2 DH 5635	59.22	5.27	.	1.392	.	.	.	6.11	0.031	0.066	.	0.882	1.27
2 DH 5631	58.54	5.41	.	1.43	.	.	.	6.28	0.247	.	2.01	.
1 NCS DC14203	57.63	10.80	.	1.37	.	.	.	8.17	.	0.0063	.	.	.	0.065	.	1.65	.
2 DH X5642	57.31	7.74	.	1.18	.	.	.	9.64	0.044	.	0.005	.	.	0.042	.	1.45	.
2 DH 5616	57.29	6.58	.	1.331	.	.	.	9.51	0.045	0.045	.	1.491	.
2 DH X5638	57.22	1.00	.	2.36	.	.	.	5.04	0.155	.	1.094	.
2 DH X5639	56.99	2.89	.	1.664	.	.	.	6.45	0.087	.	1.402	.
1 JSS 851-5	56.67	.	0.89	.	.	.	7.94	.	Cr:0.0163	0.0034	.	Fe II: 5.99	.	.	0.48	.	0.041
1 NCS DC28231	56.53	22.9	.	1.90	.	.	.	11.46	1.75	.
2 DH X5640	56.27	7.78	.	1.384	.	.	.	10.84	0.045	.	1.499	.
2 DH X5641	56.20	7.82	.	1.25	.	.	.	11.07	0.041	.	1.569	.
1 NCS DC28046	56.14	9.17	.	2.07	.	.	.	10.35	0.125	.	2.21	.
1 NCS DC14009a	55.58	20.06	.	2.38	.	.	.	3.62	.	0.017	.	.	.	0.316	.	5.99	.
1 NCS DC28046a	55.49	7.93	.	1.84	.	.	.	11.66	.	0.0034	.	.	.	0.045	.	2.83	.
1 NCS DC11024	55.37	(8.20)	.	2.19	.	.	.	10.76	0.082	.	2.14	.
2 BS 104	55.32	.	.	1.26	.	.	.	8.72	(0.15)	.	3.06	.
1 NCS DC28038	55.19	6.23	.	1.83	.	.	.	9.19	0.070	.	2.22	.
1 NCS DC28023a	53.10	7.49	.	2.76	.	.	.	11.78	0.079	.	2.69	.
2 DH 5632	55.03	4.06	.	1.281	.	.	.	10.79	0.174	.	2.070	.
1 BS 104A	54.8	.	.	1.04	0.22	.	.	10.5	0.14	.	1.24	.
1 BCS 377/6	54.78	.	0.783	.	.	.	5.74	.	Cr:0.0154	0.907	.	.
1 NCS DC14204	54.62	9.26	.	1.49	.	.	.	9.29	.	0.014	.	.	.	0.046	.	1.74	.
1 NCS DC28023b	53.74	8.52	.	3.05	As:0.020	.	Cr:0.021	9.67	.	0.017	.	.	.	0.145	.	3.45	.
1 NCS DC28050	53.26	9.53	.	2.24	.	.	.	11.31	0.084	.	2.70	.
1 NCS DC14202	52.77	6.55	.	2.54	.	.	.	11.33	.	0.012	.	.	.	0.078	.	2.02	.
1 NCS DC28049	52.16	8.06	.	2.17	.	.	.	13.05	0.082	.	1.63	.
1 NCS DC14206	51.13	9.22	.	2.44	.	.	.	9.46	.	(0.007)	.	.	.	0.080	.	4.40	.
1 NCS DC28047	50.04	8.07	.	2.11	.	.	.	13.72	0.091	.	2.08	.
1 JSS 851-6	54.16	FeII: 7.55%	1.06	.	.	.	9.30	.	Cr:0.0239	0.0039	0.644	.	(0.147)
1 VS R5/7	53.7	17.22	.	3.60	.	.	.	3.85	6.38	.
1 ECRM 676-1	39.76	.	3.40	.	.	.	12.78	0.10	0.43	.	1.16	.	.

continued analysis listed in mass % except * which is mg/kg

Number	Mn	MnO	Na	Na ₂ O	Ni*	NiO	P	P ₂ O ₅	PbO	S	Si	SiO ₂	SrO	Ti	TiO ₂	V	V ₂ O ₅	ZnO	Units
DH 5630	0.298	.	.	0.032	.	.	.	0.112	.	0.011	.	3.98	.	.	0.085	.	.	0.016	100 g
DH 5635	0.368	.	.	0.047	.	.	.	0.120	.	0.013	.	4.81	.	.	0.224	.	.	0.010	100 g
DH 5631	0.945	0.107	.	.	.	5.08	.	.	0.076	.	.	0.040	100 g
NCS DC14203	0.174	.	.	0.046	.	.	0.102	.	.	0.025	.	5.38	.	0.113	50 g
DH X5642	0.533	.	.	0.035	.	0.009	.	0.144	.	0.016	.	4.64	0.008	.	0.105	.	.	0.018	100 g
DH 5616	0.477	.	.	0.025	.	.	.	0.140	.	.	.	5.18	.	.	0.101	.	0.018	0.013	100 g
DH X5638	0.050	.	.	0.040	.	.	.	0.110	.	0.110	.	8.40	0.026	.	0.113	.	.	0.052	100 g
DH X5639	0.174	.	.	0.060	.	.	.	0.059	.	0.081	.	8.43	.	.	0.112	.	.	0.005	100 g
JSS 851-5	0.241	.	.	.	58	.	0.060	.	0.016	2.48	.	.	.	0.065	.	0.0084	.	Zn:0.0075	100 g
NCS DC28231	.	0.202	0.027	.	.	0.063	.	5.57	.	.	0.103	.	.	.	50 g
DH X5640	0.342	.	.	0.037	.	0.008	.	0.158	.	0.023	.	5.26	0.010	.	0.113	.	.	0.014	100 g
DH X5641	0.326	.	.	0.034	.	.	.	0.145	.	0.022	.	5.17	.	.	0.106	.	.	0.014	100 g
NCS DC28046	0.227	.	.	0.048	.	.	0.064	.	.	0.032	.	5.54	.	0.076	70 g
NCS DC14009a	.	0.097	.	0.068	.	.	0.017	.	.	0.106	.	9.95	.	.	0.266	.	.	0.011	50 g
NCS DC28046a	.	0.289	.	0.034	.	.	0.045	.	.	0.040	.	4.85	.	.	0.109	.	.	0.0078	50 g
NCS DC11024	.	0.36	.	0.045	.	.	0.056	.	.	0.017	.	5.64	.	.	0.125	.	.	0.0062	70 g
BS 104	.	0.79	.	(0.06)	.	.	.	0.127	.	0.011	.	7.70	.	.	0.088	.	.	.	100 g
NCS DC28038	0.222	.	.	0.057	.	.	0.057	.	.	0.028	.	6.79	.	0.123	70 g
NCS DC28023a	.	0.740	.	0.049	.	.	0.059	.	.	0.042	.	6.49	.	.	0.144	.	.	.	50 g
DH 5632	0.708	0.104	.	0.059	.	5.55	.	.	0.068	.	.	0.026	100 g
BS 104A	.	1.06	.	0.022	.	.	.	0.101	.	0.015	.	7.97	.	.	0.094	.	.	17025	100 g
BCS 377/6	0.604	0.0586	.	Pb:0.1485	.	2.982	.	.	0.1001	.	0.0178	.	Zn:1.002	100 g
NCS DC14204	0.193	.	.	0.019	.	.	0.039	.	.	0.024	.	7.94	.	0.092	50 g
NCS DC28023b	.	0.185	.	0.090	.	.	0.036	.	Pb:0.012	0.022	.	7.11	.	.	0.290	.	last	0.018	50 g
NCS DC28050	0.286	.	.	0.44	.	.	0.049	.	.	0.075	.	6.24	.	0.082	70 g
NCS DC14202	0.199	.	.	0.033	.	.	0.060	.	.	0.033	.	7.51	.	0.062	50 g
NCS DC28049	0.440	.	.	0.38	.	.	0.024	.	.	0.096	.	6.92	.	0.067	70 g
NCS DC14206	0.179	.	.	0.040	.	.	0.066	.	.	0.059	.	8.58	.	0.094	50 g
NCS DC28047	0.390	.	.	0.53	.	.	0.028	.	.	0.125	.	7.60	.	0.067	70 g
JSS 851-6	0.345	.	.	.	30.3	.	0.076	.	.	0.0298	2.76	.	.	0.111	.	0.0164	.	Zn:0.0134	100 g
VS R5/7	.	1.07	0.0281	.	.	0.038	.	9.16	.	.	0.50	.	.	.	100 g
1 ECRM 676-1	0.83	.	0.095	.	.	.	0.59	.	.	0.12	6.40	.	.	0.19	.	0.070	.	.	100 g

CRM

KAOLIN

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	TiO ₂	LOI	Units
NCS DC72002	58.47	27.16	1.01	0.80	.	0.90	0.29	0.019	0.19	0.22	0.43	0.30	10.11	1 kg
UNS KK	47.06	36.77	0.236	0.982	12.75	1.063	0.192	0.015	0.032	.	.	0.166	.	100 g
NCS DC60123a	45.30	37.70	0.064	0.35	15.26	0.042	0.021	0.0018	0.045	0.16	0.76	0.060	14.81	50 g
NCS DC72001	44.67	36.53	0.17	0.63	.	0.70	0.14	0.005	0.11	0.17	3.13	0.14	16.09	1 kg
NCS DC60122a	43.41	34.77	0.038	1.50	13.24	0.78	0.069	0.0020	0.045	0.21	5.51	0.25	17.31	50 g

CRM KIMBERLITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %														70 g units					
Number	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI					
NCS DC71312	3.73	(16.78)	12.64	3.71	(6.53)	(4.47)	0.49	17.56	(0.1)	0.30	0.68	35.88	0.71	20.73					
continued analysis listed in mg/kg except % which is mass %																			
Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu	F%	Ga	Gd
NCS DC71312	(0.06)	3.5	(31.8)	(0.177)	1.3	(0.1)	0.46	127	(0.04)	40.0	795	5.2	26.2	2.6	(1.2)	1.6	(0.11)	7.1	4.7
Number	Ge	Hf	Hg	Ho	La	Li	Lu	Mn%	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm
NCS DC71312	0.89	4.9	0.010	0.49	69.8	75.7	0.16	(0.09)	1.4	60.4	49.0	516	20.7	13.8	28.4	(0.22)	10.9	0.10	6.5
Number	Sn	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb	Zn	Zr						
NCS DC71312	1.7	262	3.9	0.54	10.8	0.17	2.2	86	2.4	11.6	1.1	190	182						

CRM LATERITE - NICKEL ORE

analysis listed in mass %, ICP values by fusion ICP, C and S: <0.01% from IR combustion furnace, all others fusion XRF including Cl: <50 ppm 10g or 1kg

Number	Ni	Co	Al ₂ O ₃	C	CaO	Cr ₂ O ₃	Cu	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	Zn	LOI
OREAS 195	2.94	0.0477	3.13	0.08	0.390	0.958	<0.0050	18.29	<0.01	19.01	0.288	0.034	<0.01	<0.01	44.00	0.037	0.0300	9.71
OREAS 195 ICP	2.89	0.0465	3.07	.	0.397	0.938	(0.0050)	18.16	<0.1	18.88	0.285	(0.03)	<0.01	<0.05	43.30	0.037	0.0293	.
OREAS 194	2.13	0.0428	2.74	0.07	0.311	0.819	(0.0040)	16.47	<0.01	22.83	0.261	(0.03)	<0.01	<0.01	43.02	0.035	0.0174	10.53
OREAS 194 ICP	2.10	0.0424	2.73	.	0.32	0.814	0.0041	16.42	<0.01	22.77	0.262	0.027	<0.01	<0.05	42.90	0.033	0.0184	.
OREAS 193	1.93	0.0495	3.08	0.07	0.362	0.962	<0.0050	19.51	<0.01	20.25	0.317	(0.03)	0.012	<0.01	42.72	0.053	0.0219	9.87
OREAS 193 ICP	1.91	0.0483	3.05	.	0.373	0.956	(0.0040)	19.49	(0.08)	20.26	0.316	0.030	<0.02	<0.05	42.49	0.051	0.0199	.
OREAS 192	1.77	0.0404	2.76	0.07	0.313	0.913	<0.0050	18.10	<0.01	21.32	0.277	0.028	<0.01	(0.004)	43.58	0.036	0.0176	10.17
OREAS 192 ICP	1.75	0.0398	2.75	.	0.316	0.910	(0.0038)	18.14	<0.1	21.26	0.278	0.022	<0.02	<0.02	43.45	0.033	0.0193	.
OREAS 191	1.75	0.0665	4.27	0.09	0.276	1.22	(0.0050)	24.86	<0.01	10.06	0.397	(0.02)	<0.01	<0.01	47.97	0.052	0.0302	8.10
OREAS 191 ICP	1.73	0.0652	4.19	.	0.287	1.21	(0.0050)	24.63	(0.1)	9.95	0.397	0.018	<0.02	<0.05	47.67	0.050	0.0297	.
OREAS 190	1.64	0.0889	6.00	0.07	0.133	1.73	(0.0070)	35.48	<0.01	6.91	0.577	(0.02)	<0.01	<0.01	38.22	0.064	0.0353	8.38
OREAS 190 ICP	1.62	0.0875	5.86	.	0.133	1.71	0.0068	35.40	<0.01	6.85	0.574	(0.01)	<0.02	<0.02	38.06	0.062	0.0327	.
OREAS 189	1.48	0.0326	2.09	0.10	0.326	0.765	<0.0050	15.04	<0.01	23.09	0.227	(0.03)	<0.01	<0.01	46.20	0.029	0.0125	10.13
OREAS 189 ICP	1.47	0.0327	2.08	.	0.328	0.764	(0.0030)	14.94	(0.08)	23.06	0.228	0.021	<0.02	<0.05	46.08	0.026	0.0103	.
OREAS 187	1.37	0.0636	2.80	0.11	0.341	0.987	(0.0040)	19.45	<0.01	17.99	0.356	<0.03	<0.01	<0.01	46.66	0.033	0.0196	9.27
OREAS 187 ICP	1.37	0.0629	2.77	.	0.352	0.987	<0.0050	19.40	<0.1	17.96	0.358	<0.03	<0.02	<0.05	46.37	(0.03)	0.0190	.
OREAS 186	1.23	0.0692	5.19	0.07	0.562	1.42	0.0061	32.04	<0.01	4.89	0.522	(0.02)	(0.01)	<0.01	46.29	0.069	0.0265	6.83
OREAS 186 ICP	1.22	0.0680	5.11	.	0.564	1.41	0.0057	31.72	<0.1	4.82	0.519	<0.01	<0.02	<0.05	46.24	0.070	0.0276	.
OREAS 185	1.14	0.0388	2.48	0.10	0.385	0.914	<0.0050	18.42	<0.01	20.22	0.297	0.027	<0.01	<0.01	45.93	0.033	0.0143	9.61
OREAS 185 ICP	1.12	0.0385	2.47	.	0.39	0.91	<0.0050	18.27	<0.01	20.17	0.295	0.024	<0.02	<0.05	45.58	0.031	0.0128	.
OREAS 184	1.02	0.0903	4.62	0.07	0.216	1.75	0.0070	39.30	<0.01	3.05	0.676	<0.01	0.017	<0.01	42.25	0.060	0.0278	6.24
OREAS 184 ICP	1.02	0.0899	4.58	.	0.231	1.75	0.0060	39.42	<0.1	3.00	0.678	<0.01	(0.02)	<0.05	42.19	0.058	0.0287	.
OREAS 183	0.995	0.0225	1.60	0.22	0.710	0.653	<0.0030	12.73	<0.01	27.31	0.180	(0.03)	0.005	<0.01	44.49	0.023	0.0078	10.90
OREAS 183 ICP	0.983	0.0222	1.60	.	0.72	0.651	0.0021	12.72	<0.1	27.43	0.181	0.030	<0.01	<0.02	44.13	0.020	0.0082	.
OREAS 182	0.707	0.0728	4.07	0.09	0.251	1.29	0.0052	29.40	<0.01	9.16	0.580	0.019	0.010	0.006	46.77	0.053	0.0181	7.14
OREAS 182 ICP	0.706	0.0723	4.02	.	0.253	1.28	0.0049	29.62	<0.1	9.12	0.587	0.014	<0.02	<0.05	46.54	0.051	0.0189	.

RM LEAD BASILICATE

analysis listed in mass % 25 or 100 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	PbO	SiO ₂	TiO ₂	LOI
CERAM AN28	2.46	0.05	0.018	0.05	<0.01	0.05	64.33	32.76	<0.01	0.15

CRM LEAD ORE TAILINGS WITH EXTENSIVE ANALYSIS

analysis listed mass % * BCS 362 lists AQUA REGIA results where indicated BCS: 100 g units others: 50 g units

Number	Pb	PbO	Al ₂ O ₃	CaO	Cu	F	Fe ₂ O ₃	K ₂ O	MgO	MnO	Mn ₃ O ₄	Na ₂ O	S	SiO ₂	SrO	TiO ₂	Zn	ZnO	LOI
NCS DC11048	58.98	.	0.35	0.148	0.225	0.020	Fe:4.49	0.074	0.16	Mn:0.063	0.010	17.58	17.58	3.03	.	.	5.61	.	.
GBW 07235	4.17	.	12.88	19.51	0.20	0.27	4.37	1.42	1.62	1.40	.	1.61	0.86	43.63	.	0.53	0.062	.	.
BCS 362 *	2.30*	2.63	0.667	44.21	0.0056*	.	0.483	0.14	0.068	.	0.829	0.084	1.48	9.03	0.034	0.047	2.03*	2.59	32.81

continued analysis listed in mg/kg

Number	Ag	As	Au%	Bi	Cd	Ce	Co	Cr	Cs	Dy	Eu	Er	Ga	Gd	Ge	Hg	Ho	In	La	Li
NCS DC11048	0.76%	0.44%	(0.08)	12	460	.	.	13	(3)	(8)
GBW 07235	14.7	85.1	.	15.6	3.2	78.3	.	(29)	(6)	3.0	1.2	1.5	16.7	3.7	0.90	.	0.61	0.12	40.5	(19)
BCS 362 *	.	30*	.	.	200*	.	.	11*

Number	Lu	Mo	Nd	Ni	Pr	Rb	Sb	Sc	Se	Sm	Sn	Tb	Te	Th	Tl	Tm	W	Y	Yb	pH
NCS DC11048	5.12%	(25)	.	0.027%
GBW 07235	0.24	1.6	28.2	27.7	8.1	(55)	39.3	7.5	1.7	5.1	3.0	0.58	3.9	10.2	0.43	0.23	17.6	15.4	1.5	.
BCS 362 *	.	.	.	12*	8.14*

CRM LEAD ORE analysis listed in mass %

Number	Pb	Ag	As	Ba	Co	Cu	Fe	Ni	S	Zn	Zr	Units
KZ 6586-93	3.5	0.0019	.	0.38	.	0.013	2.03	.	0.55	0.045	0.019	100 g
GBM920-1	3.1136	0.01575	0.0491	.	0.0327	0.3431	.	0.0010	.	0.3642	.	10 or 250 g
KZ 5177-90	1.84	0.00181	.	10.3	2.96	.	.	100 g last

CRM LEAD ORE analysis listed in mass % 25 g units

Number	Pb	Ag	Al ₂ O ₃	As	Bi	CaO	Cd	Cu	Fe	MgO	Mn	S	Sb	SiO ₂	Zn
NCS DC28180	73.42	0.0250	0.54	0.0013	0.0051	0.30	0.022	0.058	1.70	0.042	0.570	14.22	0.0050	1.81	.
NCS DC28179	57.44	0.0240	1.13	0.019	0.026	4.86	0.019	0.290	3.08	0.374	0.427	15.71	0.0061	3.52	.
NCS DC28178	42.84	0.0933	2.01	0.816	0.0046	1.73	0.005	0.350	15.38	0.412	0.345	3.94	0.159	6.55	.
NCS DC28116	15.09	0.022	2.56	0.068	0.085	17.16	0.0097	0.85	6.78	1.28	0.029	19.26	0.0084	7.92	1.44

CRM LEAD ORE analysis listed in mass % except* which is mg/kg

Number	Pb	S	Zn	Ag	Al	As	Au*	Ba*	C	Ca	Cd	Co*	Cr	Cu	Fe
CAN CPB-3	58.02	(17.03)	5.96	0.2790	0.203	(0.0391)	(0.119)	(60)	1.03	0.059	0.065	13.6	0.0102	0.240	8.45

Number	Hg*	K	La*	Mg	Mn	Na	Ni*	Sb	SiO ₂	Sn*	Sr*	Th*	Y*	LOI	Units
CAN CPB-3	40.8	(0.09)	(2)	0.106	(0.421)	(0.01)	16.8	0.58	2.62	(6)	(3)	(0.4)	(2)	(0.15)	100g

CRM LIMESTONE AND DOLOMITE

analysis listed in mass % 100 g

Number	CaO	CO ₂	Al ₂ O ₃	BaO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO ₂	Na ₂ O	SiO ₂	SO ₃	SrO	TiO ₂	LOI
DK KSTM 1	46.57	36.11	3.24	0.0049	1.24	0.57	0.56	0.47	0.14	0.04	8.79	0.12	0.1394	0.16	38.07
DK KSTM 2	55.04	43.20	0.19	0.002142	0.12	0.11	0.05	0.39	0.04	0.02	0.51	0.05	0.0197	0.01	43.57
DK KSTM 3	55.17	43.33	0.13	0.001178	0.07	0.07	0.02	0.48	0.02	0.02	0.28	0.02	0.0214	0.01	43.44
DK KSTM 4	30.23	45.53	0.14	0.002180	0.12	0.11	0.03	21.65	0.06	0.04	0.46	0.03	0.009052	0.01	47.25

continued analysis listed in mg/kg

Number	As	Cd	Co	Cr	Cu	Hg	Ni	Pb	Sb	Se	Zn
DK KSTM 1	2.01	0.11	6.04	11.72	8.45	0.015	18.58	5.69	0.08	0.02	23.59
DK KSTM 2	2.20	0.17	0.62	1.70	1.07	0.01	1.85	33.84	0.13	0.01	12.71
DK KSTM 3	0.32	0.11	0.45	1.21	1.02	0.01	0.85	0.67	0.76	0.01	2.56
DK KSTM 4	0.74	0.14	0.27	2.04	1.62	0.025	1.31	17.62	0.04	0.01	16.98

CRM LIMESTONE WITH EXTENSIVE ANALYSIS

analysis listed in mass %																			CGL: 100 g	JLs: 20 or 100 g	NCS: 50 g
Number	CaO	MgO	CO ₂	SiO ₂	LOI	Al ₂ O ₃	Org.C	FeO	T.Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MnO	Na ₂ O	F ₂ O ₅	SO ₃	Ti%	TiO ₂			
JLs-1	55.09	0.606	43.58	0.120	.	0.0207	Fe ₂ O ₃ :0.0178	0.0168	0.105	(0.140)	0.00297	0.00209	0.00194	0.0295	S:0.0123	.	.	(0.0020)			
CGL 020	50.32	1.385	.	5.76	40.29	1.16	.	0.349	H ₂ O:(0.16)	0.229	0.0231	0.228	0.0659	0.043			
NCS DC70301	47.89	6.76	44.39	0.55	43.92	0.17	(0.03)	0.15	0.193	(0.20)	0.37	0.043	0.009	0.022	0.008	0.017	0.0066	0.011			
NCS DC70302	41.95	11.62	44.89	0.72	44.75	0.22	(0.03)	0.16	0.205	(0.20)	0.31	0.052	0.009	0.029	0.014	0.013	0.0132	0.022			
NCS DC70308	38.08	14.96	45.62	1.17	44.61	0.18	(0.04)	0.05	0.448	(0.17)	0.42	0.026	0.027	0.030	0.009	0.041	0.0054	0.009			
NCS DC70305	30.93	20.14	45.58	1.15	45.73	0.29	(0.07)	0.07	0.17	(0.07)	0.39	0.16	0.012	0.036	0.035	0.33	0.0078	0.013			

analysis listed in mg/kg except % which is mass %																				
Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd
JLs-1	(0.0013)	(0.145)	.	476	.	.	.	0.159	0.521	.	0.0825	3.37	0.0201	0.268	0.0283	.	0.0072	57.5	.	(0.03)
CGL 020	.	.	.	51	0.58	.	.	(0.04)	6.08	.	1.1	5.3	2.01	1.3	0.528	0.298	0.143	.	1.48	0.611
NCS DC70301	0.020	0.50	(1.9)	9.7	0.08	0.015	(0.2)	0.10	1.4	34	0.45	4.8	0.07	2.2	0.12	0.09	0.037	76	0.3	0.13
NCS DC70302	0.021	0.29	(2.2)	11.6	0.12	0.020	(0.3)	0.09	1.9	34	0.5	5.6	0.09	2.2	0.15	0.12	0.052	91	0.33	0.16
NCS DC70308	0.035	5.5	(2.3)	10.6	0.15	0.012	0.9	0.39	1.5	123	0.5	9.7	0.10	2.9	0.20	0.15	0.049	179	0.4	0.19
NCS DC70305	(0.016)	0.96	(6.4)	0.52%	0.08	0.025	6.1	0.02	2.5	343	0.52	3.4	0.13	2.8	0.17	0.10	0.14	459	0.31	0.22

Number	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	Sb
JLs-1	0.126	.	(0.0056)	.	.	.	0.153	(0.2)	0.022	.	.	(1.0)	(0.136)	0.362	.	(0.7)	(0.032)	(0.18)	(0.0166)
CGL 020	.	0.395	.	0.103	.	.	3.71	9.7	0.0412	.	(0.13)	0.8	3.32	5	.	2.9	0.85	11.5	(0.25)
NCS DC70301	0.11	1.4	0.004	0.034	(0.5)	(0.03)	0.9	2.9	0.019	70	0.35	0.3	0.66	5.8	35	2.9	0.22	1.2	0.08
NCS DC70302	0.12	2.1	0.015	0.034	(0.3)	(0.02)	1.2	3.1	0.022	70	0.26	0.46	0.86	4.3	62	3.9	0.24	1.6	0.09
NCS DC70308	0.11	3.1	0.031	0.046	(0.2)	(0.02)	0.9	3.0	0.035	209	0.80	0.4	0.89	5.6	40	7.8	0.21	1.1	0.59
NCS DC70305	0.12	0.13	0.006	0.034	(0.2)	(0.02)	1.3	3.1	0.015	93	0.19	0.4	1.10	2.9	155	2.9	0.28	2.6	0.06

Number	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W%	Y	Yb	Zn	Zr%
JLs-1	0.0307	.	0.135	.	295	(0.014)	(0.0041)	.	0.0287	(0.003)	.	1.75	3.59	.	0.223	0.0164	3.19	(0.000419)
CGL 020	0.71	.	0.638	0.66	1018	0.093	0.092	.	0.71	(0.083)	0.0437	1.08	5.9	8ppm	3.43	0.276	8	(0.0016)
NCS DC70301	0.40	0.014	0.15	(0.7)	227	(0.06)	0.022	0.008	0.25	0.022	0.018	0.59	4.8	0.17	1.2	0.11	8.1	0.00537
NCS DC70302	0.5	0.015	0.19	(0.6)	191	0.05	0.031	0.008	0.25	0.023	0.020	0.39	5.0	0.18	1.4	0.13	9.5	0.00768
NCS DC70308	0.5	0.10	0.21	(0.9)	85	0.030	0.035	0.016	0.29	0.02	0.030	1.13	7.5	0.13	1.8	0.19	35.7	0.0113
NCS DC70305	0.4	0.013	0.26	(0.7)	158	0.06	0.032	0.008	0.45	0.04	0.017	0.70	5.1	0.17	1.1	0.10	3.6	0.00049

CRM LIMESTONE

Number	Al	Ca	Fe	Mg	Mn	P	S	Si	Ti	Units
IRSID 702-1	0.21	21.48	0.440	12.37	0.098	0.024	0.027	1.04	0.013	100 g

CRM LIMESTONE AND DOLOMITE

analysis listed in mass %															FLX: RM, 30g	NCS: CRM, 50g
Number	CaO	MgO	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	K ₂ O	Mn ₂ O ₃	MnO	Na ₂ O	P	S	SO ₃	SrO	TiO ₂	LOI	
FLX 136	55.06	0.377	0.548	0.181	0.126	0.051	0.038	0.033	0.022	.	.	
NCS DC28246	54.92	0.37	0.47	0.203	0.107	.	0.0081	.	.	0.0017	0.010	.	0.017	0.0092	43.54	
NCS DC28160	54.20	0.82	0.960	0.328	0.146	0.084	.	0.0049	0.006	0.0019	0.019	.	0.018	0.016	43.27	
NCS DC28157	53.79	1.17	1.32	0.225	0.151	0.066	.	0.0037	0.0058	0.0027	0.020	.	0.018	0.014	43.22	
NCS DC28161	53.76	1.50	0.835	0.242	0.143	0.048	.	0.0058	0.006	0.0012	0.018	.	0.017	0.011	43.37	
NCS DC28245	53.40	1.90	0.37	0.17	0.125	.	.	0.0092	.	0.0015	0.014	.	0.024	0.0085	43.93	
NCS DC28159	51.95	1.23	2.36	0.811	0.296	0.165	.	0.0077	0.009	0.0017	0.016	.	0.020	0.036	42.39	
NCS DC28244	51.32	2.94	1.49	0.39	0.171	.	.	0.0026	.	0.0022	0.0082	.	0.018	0.018	43.47	
NCS DC28156	51.22	2.43	3.32	0.340	0.181	0.094	.	0.0042	0.0074	0.0019	0.030	.	0.021	0.020	42.26	
NCS DC28154	50.61	2.88	3.02	0.622	0.289	0.164	.	0.0054	0.026	0.0028	0.055	.	0.024	0.032	41.92	
NCS DC28171b	49.64	4.13	2.23	0.462	0.187	0.272	.	0.0039	0.012	0.0032	0.035	.	0.019	0.022	43.18	
NCS DC28170b	49.25	5.31	0.82	0.17	0.194	0.030	.	0.0069	0.007	0.0015	0.007	.	0.016	0.0080	43.96	
NCS DC28158	48.56	4.31	3.99	0.657	0.302	0.184	.	0.0055	0.028	0.0044	0.044	.	0.022	0.051	41.70	
NCS DC28247	47.82	6.13	0.70	0.222	0.201	.	.	0.0095	.	0.0066	0.014	.	0.018	0.013	44.46	
NCS DC28152	46.71	6.55	2.42	0.374	0.25	0.050	.	0.0046	0.011	0.0017	0.042	.	0.016	0.023	43.22	
NCS DC28155	46.09	5.98	4.60	0.283	0.187	0.038	.	0.0046	0.010	0.0016	0.033	.	0.020	0.015	42.55	
NCS DC28248	45.88	7.68	0.76	0.240	0.229	.	.	0.010	.	0.0078	0.016	.	0.018	0.014	44.51	
NCS DC28175b	41.91	11.15	0.76	0.272	0.316	0.041	.	0.013	0.003	0.0023	0.002	.	0.0066	0.011	44.86	
NCS DC28153	41.81	10.37	2.35	0.543	0.417	0.074	.	0.0070	0.011	0.0032	0.050	.	0.014	0.031	43.81	
NCS DC28163	30.22	20.85	1.87	0.205	0.244	0.018	.	0.015	0.012	0.0015	0.038	.	0.013	0.0079	45.31	
NCS DC28164	30.15	20.91	2.16	0.250	0.248	0.027	.	0.016	0.011	0.0013	0.039	.	0.013	0.012	45.04	
NCS DC28165	29.50	20.43	5.22	0.706	0.357	0.033	.	0.018	0.023	0.0020	0.056	.	0.016	0.021	43.07	
NCS DC28162	28.73	19.76	8.42	1.20	0.475	0.039	.	0.020	0.033	0.0028	0.072	.	0.019	0.036	40.56	
Number	CaO	MgO	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	K ₂ O	Mn ₂ O ₃	MnO	Na ₂ O	P	S	SO ₃	SrO	TiO ₂	LOI	

LIMESTONE AND DOLOMITE

analysis listed in mass %

GUV, UL: 50 g

GBW, NCS: 70 g

others: 100 g

Number	CaO	Al ₂ O ₃	CO ₂	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	F ₂ O ₅	SiO ₂	TiO ₂	LOI
SRM 1d	52.85	0.526	.	.	0.3191	.	.	0.1358	0.301	.	0.0109	0.0413	4.080	(0.0306)	(41.57)
UL CCH1	52.05	0.32	.	.	.	0.18	.	0.08	2.71	0.01	0.05	0.05	0.95	0.02	43.20
NCS DC73375	51.1	0.68	39.8	(0.06)	.	0.21	(0.4)	0.15	0.71	.	0.03	.	6.65	.	40.2
GUV KH	47.8	2.39	37.6	0.33	0.92	.	.	0.41	0.74	0.088	.	0.121	8.60	(0.130)	.
GUV KH2	47.64	2.365	37.51	(0.31)	0.855	.	(1.26)	0.437	0.656	0.0848	0.106	0.117	8.66	0.130	.
GUV KH3	47.6	2.40	37.6	0.32	0.87	.	(1.4)	0.43	0.65	0.080	0.10	0.117	8.59	0.130	38.6
VS 3193-85	38.5	1.87	.	1.89	.	2.48	.	0.49	6.04	0.28	0.48	0.027	12.35	0.09	.
VS 3193-89	38.46	1.89	.	1.8	.	2.43	.	0.49	5.97	0.28	0.46	0.030	12.40	0.093	.
GBW 07108	35.67	5.03	32.4	1.64	.	2.52	+(2.12)	0.78	5.19	.	(0.08)	.	15.60	.	34.1
JDo-1	33.96	0.0174	46.50	(0.071)	0.0222	0.0208	+0.395 -0.145	0.00232	18.47	0.00657	0.0129	0.0343	0.216	.	.
VS 813-89	29.48	0.43	45.6	0.36	0.47	.	0.4	0.35	20.75	0.050	0.07	0.011	2.69	0.025	.
VS 3192-89	21.56	5.48	.	1.8	.	3.15	.	2.75	12.89	0.30	1.38	0.060	19.92	0.28	.

analysis listed in mg/kg except % which is mass % and * which is ng/g

Number	Ag	As	Au*	B	Ba	Be	Bi	Br	Carbon%	Cd	Ce	Cl	Co	Cr	Cs	Cu
SRM 1d	.	.	.	BaO: (33)	(0.1)	.	.	.	(11.50)	(0.3)	(4)	(130)	.	.	(0.4)	.
UL CCH1	<(1)	(1.3)	.	(10)	26	<(4)	<(5)	.	.	.	3.7	(370)	0.23	(5.4)	(0.13)	<(10)
NCS DC73375	(0.025)	0.66	.	(12)	9	0.14	0.032	(0.3)	(0.15 Org)	0.016	4.6	(24)	0.8	3.4	(0.10)	2.2
GUV KH	50	5.3	15	1.4	10
GUV KH2	46.3	18.1	.	(10)	14.2	12.2	8
GUV KH3	(0.14 Org)
VS 3193-85	.	.	.	(10)	60	(1)	18	.	2.2	13	(0.7)	4
VS 3193-89	50	16	.	2.3	9	.	4
GBW 07108	0.043	4.7	(0.94)	16	120	0.8	0.16	.	9.0 tot (0.11 org)	0.07	25	78	9	32	3.2	23
JDo-1	(0.0019)	(0.114)	trace	.	6.14	.	.	(0.79)	(12.760)	0.644	2.49	.	0.168	7.93	.	1.41
VS 813-89	.	.	.	5	30	1.3	3.0	6	.	8
VS 3192-89	400	27	.	12	30	.	29

Number	Dy	Er	Eu	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Li ₂ O	Lu	Mn	Mo
SRM 1d	(0.6)	(0.4)	(0.1)	(160)	(1)	(0.5)	.	.	.	(0.1)	.	.	(4)	.	.	.	209	.
UL CCH1	(0.27)	.	0.17	(367)	<(4)	(0.38)	<(10)	0.11	.	(0.4)	.	<(5)	5.0	0.03	.	.	.	<(5)
NCS DC73375	0.28	(0.17)	0.082	249	0.87	0.36	0.14	0.22	0.005	(0.045)	(0.1)	(0.02)	2.3	4.8	.	0.023	28	0.18
GUV KH	.	.	0.5	570	.	.	.	0.78	8.6	.	0.12	.	.
GUV KH2	.	.	0.47	610	(7)	.	0.127	.	.
GUV KH3	.	.	.	(610)	(21)	.	.	.
VS 3193-85	other impurities:	37.46%	(7)	.	.	(0.1)	.	.
VS 3193-89	8
GBW 07108	1.6	1.0	0.51	406	7.1	1.9	0.67	1.8	0.016	0.33	0.23	(0.04)	15	20	.	0.14	434	0.38
JDo-1	0.814	.	0.176	246	.	(1.3)	.	(0.0897)	(0.0095)	(0.42)	.	.	7.93	(0.4)	.	0.0494	.	(0.78)
VS 813-89	.	.	.	200
VS 3192-89	13	40	.	.	.	0.08

Number	Nb	Nd	Ni	P	Pd	Pb	Pr	Pt	Ra	Rb	S	SO ₃ %	Sb	Sc	Se	Sm	Sn
SRM 1d	(0.7)	(3)	(4)	.	.	.	(0.6)	.	.	(6)	1028	(0.5)	(1)
UL CCH1	.	4.2	11	.	.	6	.	.	.	(2.6)	1283	.	(0.25)	0.45	.	0.77	<(5)
NCS DC73375	0.8	1.96	(4)	57	N: (68)	5	0.60	.	.	4.0	36	.	0.072	(0.7)	0.021	0.40	(0.5)
GUV KH	.	.	20	25	.	.	.	3	.	2.2	.
GUV KH2	.	.	20.3	.	.	(6)	.	.	.	22	.	.	.	2.83	.	.	.
GUV KH3	900	(0.2)
VS 3193-85	(8)	.	7	.	.	16	.	.	.	15	.	.	.	(2)	.	.	.
VS 3193-89	7	.	5	.	.	10	.	.	.	15	.	.	.	2.2	.	.	.
GBW 07108	6.6	12.0	18	226	.	18	3.4	.	.	32	(370)	.	0.43	6.0	0.09	2.4	(0.98)
JDo-1	(0.4)	5.25	2.90	trace	.	(0.95)	0.956	trace	.	(1.75)	(90.5)	.	(0.036)	0.136	(0.0468)	0.788	.
VS 813-89	.	.	5	.	.	8	.	.	2e-10	5	200
VS 3192-89	37	.	18	.	.	13	.	.	.	57	.	.	.	8	.	.	1.7

Number	Sr	SrO	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn	ZnO	Zr
SRM 1d	.	303	.	(0.09)	.	(0.5)	.	.	.	(1)	(10)	.	(5)	(0.3)	.	22	.
UL CCH1	267	.	(0.03)	0.11	.	0.30	.	.	.	3.9	27	.	(7)	0.24	29	.	(35)
NCS DC73375	107	.	(0.05)	0.054	.	0.86	0.230	(0.03)	(0.024)	0.24	5.4	0.13	1.9	0.15	7	.	11
GUV KH	545	.	0.19	.	.	2.6	24	.	.	0.86	22	.	35
GUV KH2	532	2.08	.	.	.	(8)	22.9	.	.
GUV KH3
VS 3193-85	500	(2)	.	.	.	(1)	24	.	(9)	(1)	25	.	26
VS 3193-89	440	1.8	.	.	.	1.0	.	.	.	0.9	30	.	27
GBW 07108	913	.	0.42	0.35	(0.024)	4.1	0.1960	0.33	0.17	1.9	36	0.67	9.1	0.90	52	.	62
JDo-1	116	.	(0.009)	0.116	.	0.0429	.	(0.003)	(0.059)	0.858	3.14	.	10.3	0.323	35.4	.	6.21
VS 813-89	90	1.0	.	.	.	1.5	25	.	.	.	30	.	30
VS 3192-89	44	15	.	.	.	0.8	22	.	.	2.5	30	.	70

LIMESTONE AND DOLOMITE

= class, where 1 = CRM and 2 = RM

f.SiO₂ = free SiO₂

#	Number	CaO	Al ₂ O ₃	Fe	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P	P ₂ O ₅	S	SO ₃	SiO ₂	f.SiO ₂	TiO ₂	LOI
1	NCS DC16006	65.20	0.885	.	0.46	0.19	4.55	0.013	0.021	0.0054	.	0.101	.	3.72	.	.	25.06
1	VS W10/3	55.8	0.012	.	.	.	0.32	.	.	0.0035	.	0.0053	.	0.050	.	.	.
1	ECRM 752-1	55.4	0.12	.	0.045	0.02	0.15	0.01	<0.03	.	(0.01)	0.007	.	0.70	.	0.009	43.4
1	BCS 513	55.59	0.108	.	0.0275	0.0150	0.182	0.0095	<0.3	.	(0.005)	0.0097	.	0.228	.	(0.004)	43.61
1	DK 1a	55.4	0.05	.	0.04	0.01	0.39	0.01	0.02	0.64	.	<0.01	43.3
1	NCS DC14014b	55.12	0.079	.	0.341	0.0030	0.73	0.0058	0.0075	0.0013	.	0.010	.	0.073	.	Ti:0.0010	43.53
1	NM 711	55.10	0.50	0.52	.	.	43.48
2	DH X3513	55.06	0.097	.	0.082	0.029	0.466	0.017	0.003	.	0.007	.	0.012	0.289	.	0.006	
1	NCS DC60107b	54.71	0.24	.	0.098	0.049	0.66	0.0098	0.0063	.	0.0055	.	0.024	0.43	0.16	0.010	43.30
1	VB K1	54.58	0.11	.	0.097	(0.028)	0.72	0.0095	0.020	.	(0.016)	.	(0.051)	0.44	.	(0.011)	43.70
1	NCS DC14017b	54.11	0.61	.	0.319	0.0038	0.79	0.0074	0.021	0.0017	.	0.182	.	0.85	.	Ti:0.0021	42.79
1	GBW 03105a	54.03	0.24	.	0.11	0.084	0.81	0.0067	0.017	.	0.0081	.	0.018	1.09	0.67	0.010	43.12
1	CGL 028	53.73	(0.12)	.	(0.049)	(0.048)	1.39	(0.021)	(0.15)	.	(0.036)	.	.	1.52	.	.	(42.51)
1	NM 172	52.74	0.25	.	0.26	.	1.54	0.009	.	1.92	.	0.011	42.58
1	FLX 2002	53.45	0.653	.	0.396	0.083	0.549	.	(0.020)	.	0.011	.	(0.036)	1.74	.	0.038	(43.20)
1	NCS DC28205	52.42	0.39	.	0.197	.	1.92	0.0054	.	0.0019	.	0.012	.	2.17	.	0.0093	42.53
1	NCS DC60108a	51.61	0.33	.	0.17	0.17	2.25	0.0089	0.017	.	0.0061	.	0.016	2.09	1.38	0.015	42.84
1	NCS DC14015b	51.41	0.74	.	0.838	0.0062	2.31	0.013	0.0073	0.0021	.	0.273	.	2.06	.	Ti:0.0071	41.79
1	NCS DC28204	50.72	0.18	.	0.208	.	3.96	0.012	.	0.0076	.	0.016	.	0.83	.	0.0060	43.70
1	NCS DC60109a	50.09	0.94	.	0.58	(0.42)	1.79	(0.014)	(0.027)	.	0.033	.	(0.054)	4.05	(2.02)	(0.052)	41.53
2	DH X3515	48.91	0.787	.	1.293	0.187	0.379	0.028	0.032	.	0.036	.	0.055	8.75	.	0.048	.
1	NCS DC62002d	48.16	1.67	.	1.17	0.61	0.93	.	0.09	.	.	.	0.06	7.88	.	0.12	38.96
1	NCS DC60110a	47.07	0.60	.	0.38	(0.20)	5.81	(0.012)	(0.016)	.	(0.037)	.	(0.032)	2.25	(1.21)	(0.030)	43.22
1	DK 1b	43.6	3.20	.	1.25	0.96	3.00	0.02	0.13	.	.	.	0.13	9.5	.	0.15	37.7
1	VB K2	43.19	3.93	.	1.39	0.82	0.65	0.025	0.064	.	.	.	0.22	13.38	.	(0.21)	35.61
1	NCS DC14050	42.62	0.36	.	0.260	0.021	9.45	0.015	0.015	0.0033	.	0.039	.	7.97	.	Ti:0.0096	38.80
1	IPT 122	32.0	1.24	.	0.65	0.43	17.5	0.042	0.019	.	0.048	.	.	4.3	.	0.06	43.3
1	VS K4/4	31.2	0.47	.	0.56	.	20.1	0.034	0.96	.	.	.
1	SRM 88b *	29.95	0.336	.	0.277	0.1030	21.03	0.0160	0.0290	.	0.0044	.	.	1.13	.	(0.016)	(46.98)
1	DK 2a **	29.2	0.91	.	1.01	0.37	19.5	0.06	0.04	.	.	.	0.06	4.3	.	0.07	44.3

continued

Number	CO ₂	Cl ⁻	Cr	Cr ₂ O ₃	Cu	Pb	SrO	Zn	Ins.Res	Units
NCS DC16006	15 g
VS W10/3	75 g
ECRM 752-1	0.019	.	.	100 g
BCS 513	.	.	.	0.0012	.	0.0009	0.0176	0.0014	.	100 g
DK 1a	60 g
NCS DC14014b	Sr:0.025	.	.	50 g
NM 711	100 g
DH X3513	43.80	0.019	.	.	100 g
NCS DC60107b	(43.28)	0.014	50 g
VB K1	(43.54)	.	(0.0025)	.	(0.00055)	100 g
NCS DC14017b	Sr:0.024	.	.	50 g
GBW 03105a	(43.12)	0.0028	50 g
CGL 028	Sr:(0.1057)	.	.	100 g
NM 172	100 g
FLX 2002	BaO:(0.005)	Mn ₂ O ₃ : 0.012	(0.028)	.	.	30 g
NCS DC28205	0.023	.	.	50 or 100 g
NCS DC60108a	(42.59)	0.0066	50 g
NCS DC14015b	Sr:0.023	.	.	50 g
NCS DC28204	0.046	.	.	50 or 100 g
NCS DC60109a	(41.32)	(0.0062)	50 g
DH X3515	0.050	.	.	100 g
NCS DC62002d	20 g
NCS DC60110a	(43.02)	(0.0054)	50 g
DK 1b	60 g
VB K2	100 g
NCS DC14050	Sr:0.017	.	.	50 g
IPT 122	0.018	.	.	80 g
VS K4/4	1.30	75 g
SRM 88b *	46.37	0.0076	.	.	75 g
DK 2a **	60 g

-H₂O @ 900°C: 0.099

17034

** SRM 88b lists Mn as MnO
DK 2a lists Mn₃O₄ as MnO

CRM SYNTHETIC LIMESTONE WITH TRACE ELEMENTS

Material base: CaCO₃ 85%, MgCO₃ 8%, SiO₂ 5.2%, Al₂O₃ 1.1%, Fe₂O₃ 0.3%, Na₂SO₄ 0.2%, K₂SO₄ 0.2% analysis listed in mg/kg 70 g units

Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Co	Cr	Cu	Ga	La	Li	Mn
GBW 07712	(0.030)	2.2	2.2	24	0.22	0.23	(0.023)	2.8	2.3	2.3	2.2	2.8	2.6	3.2	37
GBW 07713	0.060	5.2	5	54	0.52	0.53	0.053	5.8	5.3	5.3	5.2	5.8	5.6	6.2	67
GBW 07714	0.11	10.2	10	104	1.0	1.0	0.10	11	10.3	10.3	10.2	10.8	10.6	11.2	117
GBW 07715	0.21	20	20	204	2.0	2.0	0.20	21	20.3	20.3	20	20.8	20.6	21	217
GBW 07717	1.0	100	100	1000	10	10	1.0	101	100	100	100	101	101	101	1020
GBW 07718	2.0	200	200	2000	20	20	2.0	200	200	200	200	200	200	200	2020
GBW 07719	5.0	500	500	5000	50	50	5.0	500	.	.	500	.	.	500	5000
GBW 07720	10	.	.	.	100	100	10	.	.	.	1000	.	.	.	10000

continued

Number	Mo	Nb	Ni	Pb	Sb	Sn	Sr	Ti	V	W	Y	Yb	Zn	Zr
GBW 07712	0.21	2.5	2.1	2.4	0.21	0.28	170	31	3.2	0.22	2.1	0.22	3.0	4.0
GBW 07713	0.51	5.5	5.1	5.4	0.51	0.58	200	61	6.2	0.52	5.1	0.52	6.0	7.0
GBW 07714	1.0	10.5	10	10.4	1.0	1.1	250	111	11.2	1.0	10	1.0	11	12
GBW 07715	2.0	20.5	20	20.4	2.0	2.1	350	210	21	2.0	20	2.0	21	22
GBW 07717	10	100	100	100	10	10	1150	1010	101	10	100	10	101	102
GBW 07718	20	200	200	200	20	20	2200	2000	200	20	200	20	200	202
GBW 07719	50	.	500	500	50	50	5200	5000	500	50	.	50	500	500
GBW 07720	100	.	.	1000	100	100	.	.	.	100	.	100	1000	.

CRM		LITHIUM ORE WITH EXTENSIVE ANALYSIS													analysis listed in mass %		17025				
Number	Al ₂ O ₃	Bi	CaO	Fe ₂ O ₃ T	K ₂ O	Li ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Pb	S	SiO ₂	TiO ₂	Zn	LOI	Units				
CGL 128	13.66	0.0185	0.746	0.663	6.28	0.578	0.033	0.603	(0.603)	(0.029)	0.0558	(0.223)	73.40	(0.053)	0.0594	(2.14)	100 g				
continued analysis listed in mg/kg																					
Number	As	Ba	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Ho	In	La	Lu	Mo	
CGL 128	61.75	83.51	185	(3.64)	(46.93)	(0.401)	(105)	(67.38)	186	(1.37)	(1.18)	(0.091)	(29.69)	(1.22)	(5.64)	(0.313)	(0.303)	(28.92)	(0.421)	(7.26)	
Number	Nb	Nd	Ni	Pr	Rb	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	W	Y	Yb	Zr
CGL 128	(77.63)	(8.64)	(1.76)	(3.41)	(2135)	(20.50)	(9.62)	(2.26)	(11.43)	24.54	(9.74)	(0.208)	(1.12)	(24.20)	(14.65)	(0.240)	45.28	107	(12.33)	(2.19)	69.94

CRM		LITHIUM ORE WITH EXTENSIVE ANALYSIS													analysis listed in mass %		17034		40 g		
Number	Al	C	C.Graphitic	Ca	Cu	F	Fe	H ₂ O-	K	Li	Mg	Mn	Na	Ni	P	S	Si	Ti	Zn	Zr	
AC18.10664	7.47	21.39	(11.60)	0.663	2.336	2.44	1.114	(0.33)	0.080	4.134	0.525	5.339	0.271	23.134	0.350	0.376	2.85	0.133	0.00486	0.248	
AC18.10665	4.559	54.21	(35.36)	0.242	0.564	1.43	0.873	(1.18)	0.0398	1.816	0.1069	2.838	0.294	9.200	0.145	0.556	0.755	0.0282	0.0754	0.114	
analysis listed in mg/kg																					
Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Cl	Co	Cr	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf	Hg	
AC18.10664	(1.72)	(6.99)	(241)	34.6	(0.30)	(0.15)	(1.12)	7.5	283	6.100	122	(0.074)	0.548	(0.32)	(0.17)	11.6	0.64	(1.46)	(43.3)	(1.14)	
AC18.10665	(2.69)	15.9	(148)	15.1	(0.14)	(0.92)	2.37	1.66	240	2.968	22.4	(0.30)	0.174	(0.11)	(0.050)	(5.96)	(0.20)	(0.55)	(19.4)	(0.23)	
Number	Ho	In	La	Lu	Mo	Nb	Nd	Pb	Pr	Rb	Re	Sb	Sc	Se	Sm	Sn	Sr				
AC18.10664	(0.10)	(0.17)	45.7	(0.049)	2.94	(2.86)	(5.16)	(6.14)	1.38	(2.69)	(0.015)	(10.4)	(2.74)	(3.79)	(0.54)	66	38.2				
AC18.10665	(0.035)	0.179	1.13	(0.039)	1.21	(0.92)	(0.83)	(35.6)	0.213	(2.81)	(0.007)	(0.22)	(1.71)	(5.72)	(0.20)	1.17	15.7				
Number	Ta	Tb	Th	Tl	U	V	W	Y	Yb												
AC18.10664	(0.24)	Tb:0.117	(0.31)	(0.021)	(0.21)	25.6	(515)	17.6	(0.22)												
AC18.10665	(0.073)	Te:(0.30)	(0.23)	(0.047)	(0.18)	7.80	98	3.01	(0.10)												

CRM		LITHIUM ORE										analysis listed in mass %		10 g units	
Number	Li	Ta	Al	Ca	Fe	K	Mg	Mn	Na	Nb	Si	SiO ₂	Sn	LOI	
GTA-12	1.7412	0.0556	11.5	0.8	1.85	2.4	0.38	0.0770	.	0.0183	30.8	.	0.0325	1.05	

CRM		LITHIUM ORE													analysis listed in mass %		RE _x O _y : Rare Earth Oxide		50 or 70 g		
Number	Li ₂ O	Al ₂ O ₃	BeO	CaO	Cs ₂ O	F-	FeO	T.Fe ₂ O ₃	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Rb ₂ O	RE _x O _y	SiO ₂	Ta ₂ O ₅	TiO ₂	LOI	
NCS DC86303	0.460	14.76	0.018	0.335	0.037	0.667	(0.062)	0.394	1.06	3.17	0.054	0.070	4.19	0.173	0.145	47.0	74.37	0.00494	0.018	1.48	
continued analysis listed in mg/kg except % which is mass %																					
Number	CeO ₂	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Lu ₂ O ₃	Nb ₂ O ₅	Nd ₂ O ₃	Pr ₆ O ₁₁	Sc ₂ O ₃	Sm ₂ O ₃	Sn	Tb ₄ O ₇	Tm ₂ O ₃	W	Y ₂ O ₃	Yb ₂ O ₃		
NCS DC86303	9.0	2.5	1.2	(0.14)	2.1	0.45	5.1	0.18	27.0	5.0	1.3	0.98	1.6	(36)	0.43	0.18	8.9	16.9	1.3		

CRM		LITHIUM ORE	
		45 g units	
Number	Li ₂ O%		
SRM 183	4.12		

CRM LUJAVRITE

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	TiO ₂	Ba	Be	Co	Cr	Cu	Ga	Ge
VS 2124-81	56.13	16.96	1.25	1.14	5.52	6.23	0.74	0.254	9.26	0.92	0.080	0.00139	0.00063	0.00125	0.00111	0.0063	0.00013

continued

Number	La	Li	Mo	Nb	Ni	Pb	Rb	Sn	Sr	V	Y	Yb	Zn	Units
VS 2124-81	0.040	0.0037	0.00028	0.034	0.00078	0.0020	0.0250	0.0014	0.080	0.0086	0.0081	0.00057	0.012	40 g

CRM LOW BORON MAGNESITE

Number	Al	B	Ca	Cr	Fe	K	Mg	Mn	Na	P	Si	Ti	Units
ECRM 779-1	0.105	0.0116	1.691	(0.0030)	3.73	(0.0020)	(54.57)	0.503	(0.0058)	0.0267	0.182	0.0081	100 g

MAGNESITE

= class, where 1 = CRM and 2 = RM analysis listed in mass %

# Number	MgO	Al ₂ O ₃	B ₂ O ₃	CaO	CO ₂	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	Mn ₃ O ₄	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	SrO	TiO ₂	V ₂ O ₅	ZnO	ZrO ₂	LOI	
1 BCS 389/1	97.89	0.104	.	0.880	.	.	0.607	.	.	0.100	.	0.0295	.	0.274	.	0.0052	
2 BCS 319/1	95.38	0.109	.	3.00	.	0.0035	0.291	.	.	0.108	.	.	.	1.093	.	0.0070	
2 CERAM AN37	94.00	1.06	0.09	1.46	.	0.005	1.80	<0.01	0.12	.	<0.05	0.02	.	1.39	.	0.03	
2 CERAM AN36	93.30	0.42	0.09	0.94	.	0.004	4.66	<0.01	0.11	.	<0.05	0.008	.	0.48	.	0.01	
1 NCS DC87115	81.26	0.26	.	1.67	8.59	.	0.33	0.014	.	0.018	0.024	0.08	0.048	6.28	.	0.0098	.	.	.	9.71	
1 ECRM 778-1	81.02	0.56	.	1.23	.	0.15	0.96	.	.	0.014	.	(0.009)	.	1.05	.	(0.013)	
2 DH 4208	47.83	41.66	.	2.06	0.580	0.040	1.49	0.037	0.070	.	.	0.077	0.007	5.09	.	0.066	0.001	0.006	0.091	0.894	
1 NCS DC87111	47.16	0.073	.	0.76	45.84	.	0.19	0.0052	.	0.013	0.011	0.013	0.0024	0.35	.	0.0024	.	.	.	51.04	
1 NCS DC28090	46.40	0.10	.	0.53	.	.	0.65	0.0050	.	0.016	0.017	0.013	0.0027	0.32	0.0005	0.0060	.	.	.	51.58	
1 USZ 37-2003	45.80	0.04	.	1.69	48.31	.	0.05	0.011	0.25	51.35	
1 NCS DC87112	45.61	0.83	.	0.44	42.40	.	0.65	0.0048	.	0.015	0.025	0.019	0.0023	5.15	.	0.021	.	.	.	47.15	
1 UNS MK	45.22	0.414	.	0.581	.	.	.	0.013	.	0.160	0.024	0.055	.	0.593	.	0.019	
1 NCS DC87114	44.24	0.35	.	1.99	44.97	.	1.79	0.012	.	0.050	0.013	0.025	0.0031	1.71	.	0.010	.	.	.	49.81	
1 SARM 43	44.11	(0.06)	.	0.89	.	.	0.26	(0.04)	.	(0.1)	(0.05)	(0.02)	.	5.99	.	(0.01)	
1 NCS DC87113	43.64	1.71	.	2.51	39.96	.	0.71	0.0098	.	0.016	0.020	0.023	0.0034	5.45	.	0.053	.	.	.	45.76	
1 NCS DC28089	43.45	1.14	.	1.52	.	.	1.74	0.037	.	0.095	0.018	0.036	0.015	4.13	0.0013	0.041	.	.	.	47.35	
1 NCS DC28089a	43.44	1.46	.	1.26	.	.	1.66	0.044	.	0.083	0.020	0.037	0.015	4.95	0.0014	0.048	.	.	.	46.57	
2 CERAM AN43	.	.	0.005	(0.06)	last	.
2 CERAM AN45	.	.	0.222	last	.

continued analysis listed in mg/kg

Number	As	Ba	Ce	Co	Cr	Cu	La	Li	Ni	Pb	Sc	Sr	Th	U	V	Y	Zn	Units	Other
BCS 389/1	100 g	
BCS 319/1	100 g	
CERAM AN37	25 or 100 g	
CERAM AN36	25 or 100 g	
NCS DC87115	4.28	6.47	2.87	0.73	3.33	2.9	1.1	2.4	2.85	3.03	2.27	22.2	0.18	1.2	7.95	2.01	8.53	80 g	
ECRM 778-1	100 g	
DH 4208	100 g	C: 3.53%
NCS DC87111	0.41	1.4	1.6	0.53	2.12	0.81	0.66	2.21	2.14	0.79	0.99	3.49	0.047	0.41	0.96	1.25	1.94	80 g	
NCS DC28090	50 g	
USZ 37-2003	100 g	
NCS DC87112	0.4	2.99	7.77	0.69	10.2	0.77	3.23	2.16	8.31	1.14	3.23	5.06	0.85	0.33	4.09	6.68	2.41	80 g	
UNS MK	100 g	
NCS DC87114	0.68	9.99	1.67	3.14	4.16	16.4	0.57	12.8	12.1	1.05	1.58	10.6	0.2	0.96	1.63	3.25	2.55	80 g	
SARM 43	.	(25)	(20)	4	(195)	(15)	.	.	252	.	.	8	(10)	100 g	FeO: (0.1%)
NCS DC87113	0.25	5.68	8.54	1.7	13.4	0.99	3.33	11.2	9.23	1.35	3.09	30.1	1.95	0.25	7.26	3.32	2.64	80 g	
NCS DC28089	50 g	
NCS DC28089a	50 g	
CERAM AN43	25 or 100 g	
CERAM AN45	25 g	

CRM MAGNETITE ORE

analysis listed in mass % 250 g units

Number	Fe	Al ₂ O ₃	CaO	K ₂ O	MgO	Mn	Na ₂ O	P	S	SiO ₂	TiO ₂	LOI
IMS PBS-59	32.82	0.56	1.23	0.429	2.16	0.064	0.644	0.069	(0.006)	46.45	(0.028)	1.34
IMS PBS-71	30.70	1.46	0.496	0.660	2.23	0.118	0.153	0.103	0.131	47.22	0.073	3.26
IMS PBS-70	30.46	1.49	0.492	0.675	2.26	0.117	0.149	0.102	0.133	47.54	0.073	3.28

Number	As	Ba	Cl	Co	Cr	Cu	Ni	Pb	Sn	Sr	V	Zn	Zr
IMS PBS-59	.	(0.005)	(0.015)	(0.001)	(0.011)	(0.002)	(0.002)	(0.001)	(0.002)	(0.003)	.	(0.002)	(0.003)
IMS PBS-71	(0.002)	(0.006)	(0.043)	(0.002)	(0.008)	(0.001)	(0.002)	(0.002)	(0.002)	(0.003)	(0.002)	(0.002)	(0.004)
IMS PBS-70	(0.001)	(0.006)	(0.043)	(0.001)	(0.007)	(0.002)	(0.002)	(0.003)	(0.001)	(0.003)	(0.002)	(0.002)	(0.004)

MANGANESE ORE

= class, where 1 = CRM and 2 = RM

analysis in mass %

T = Total

#	Number	Mn	MnO ₂	Mn(CO ₃)	Al ₂ O ₃	As	As ₂ O ₃	Ba	BaO	CO ₂	CaO	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	TiO ₂	
1	IGS 29	MnO: 93.38						0.59											
1	VS R13/3	58.88	90.4															2.01	
1	NCS DC26703	58.80	(62.07)		0.74					C:0.034	0.37	1.45			0.17			5.63	Ti:0.025
1	VS P13/1	58.8																2.00	
1	SRM 25d	51.78			(5.33)				(0.21)		(0.052)		(3.91)	(0.928)				2.54	(0.136)
2	DH X4306	50.84	Co ₃ O ₄ :0.145		5.65		C:0.024		0.333		0.073	3.17		0.737	0.071	0.034	2.87	0.145	
1	SARM 16	49.17			(0.3)				0.60		4.70	11.48		0.02	0.76	(0.03)	5.04		
1	NCS DC35015	49.00	68.28			0.015						3.97							
1	JSS 861-2	48.7		Al: 1.57						Ca: 0.063		(5.7)					Si: 2.62		
1	NCS DC26702	48.53	(72.64)		3.28					C:0.085	0.37	4.93			0.25		5.56	Ti:0.102	
1	BAM 633-1	47.85			1.64		(0.004)		1.13		2.02	1.64			0.58		10.39	0.079	
1	AMIS 0403	46.82	MnO: 60.42		0.37					Ca: 3.56	5.12	12.43	18.25	(0.023)	0.66	(0.18)	5.25	(0.02)	
2	RH01	46.8	51.3		1.50				(0.3)		1.77	1.63		1.33	1.10	0.41	11.4		
1	JSS 861-3	46.60		Al:0.161						Ca:4.82		(10.79)					Si: 2.01		
1	AMIS 0404	45.93	MnO: 59.45		(0.40)					Ca: 3.07	4.43	13.63	19.54	(0.06)	0.51	0.79	3.56	(0.02)	
1	NCS DC25008	45.47			6.81						0.071	3.21			0.077		9.51	0.087	
1	NCS DC26704	45.20	(67.71)		6.88					C:0.090	0.103	6.03			0.097		5.55	Ti:0.092	
1	NCS DC28045	44.97T	67.67		2.35	0.042			0.058		0.195	2.75T		1.48	0.182	0.034	16.00	0.105	
1	NCS DC26701	44.95	(32.31)		0.37					C:1.22	7.53	10.50			1.05		5.41	Ti:0.010	
1	NCS DC28210	44.76	66.46		7.28						0.24	5.72			0.257		4.62	0.34	
1	VS R12/2	43.24	52.4		1.87				0.53		2.02	1.56			1.16		15.00		
1	AMIS 0402	43.01	MnO: 56.77		0.38				Ca: 3.88	5.70	15.38	22.12	(0.02)	0.54	(0.11)	4.31	(0.024)		
1	NM 166.4A	38.75			3.52						19.30						2.88		
1	SARM 17	38.81			0.24				(0.08)	(14.4)	4.27		0.09	3.03	0.09	4.69			
1	SARM 149	38.0			0.221				0.050	14.2	5.39		0.132	2.08	0.147	5.89			
1	OREAS 170b	MnO: 59.46			3.90						0.270		7.04	1.80	0.329	0.318	9.49	0.189	
1	OREAS 170a	MnO: 58.17			4.44						0.090		6.49	1.70	0.222	0.276	11.34	0.179	
1	NCS DC28044	36.31T	45.02		2.08	0.039			0.410		3.30	6.90T		0.49	1.29	0.076	17.70	0.085	
1	AMIS 0407	35.72	MnO: 46.81		0.29				Ca: 11.04	15.81	4.10	6.03	0.04	3.17	(0.039)	5.51	(0.02)		
1	NCS DC11023	35.54T	52.73		3.80	0.112			1.62		2.34	10.25T		0.396	0.78	0.053	13.03	0.143	
1	CGL 127	MnO: 45.9			9.27	(0.0131)		(0.9384)			(1.63)		19.51T	(0.017)	0.79	(0.086)	10.84	0.53	
1	NCS DC28062	34.67	51.64		9.97						0.48	8.05		1.14	0.87	0.063	10.70		
1	NCS DC28211	32.70	32.32		3.30						4.21	10.47			3.04		14.40	0.16	
1	AMIS 0406	32.27	MnO: 41.81		0.24				Ca: 12.62	18.13	4.62	6.77	(0.11)	3.51	(0.14)	4.36	(0.02)		
1	NCS DC28043	30.99T	45.61		6.40	0.089			1.11		1.15	10.68T		0.65	0.70	0.058	17.30	0.215	
1	NCS DC11022	29.48T	41.76		6.49	0.062			1.04		1.82	10.22T		0.89	0.65	0.062	19.84	0.224	
1	NM 166.3A	28.20			5.06						24.63						8.98		
1	NCS DC28209	27.76	21.00		1.77						5.44	12.00			4.08		17.54	0.085	
1	NCS DC28063	27.45	39.38		10.05				0.80		0.99	8.10		1.57	1.16	0.064	20.96		
1	NCS DC11021	26.53T	36.60		6.99	0.052					2.31	11.01T		1.01	0.774	0.064	22.10	0.247	
1	NCS DC28061	22.93	33.45		9.88						1.11	6.71		1.95	0.94	0.053	31.42		
1	NCS DC28042	22.18T	18.35		2.80	0.032			0.164		6.20	10.62T		0.83	3.14	0.049	24.73	0.123	
1	NCS DC11020	22.31T	30.34		7.69	0.034			0.54		2.36	9.66T		1.11	1.72	0.056	28.11	0.270	
1	KZ 185-89	21.61T			1.42						25.72	1.11T		0.11	0.95		16.07	0.066	
1	NCS DC11019	18.36T	25.59		5.66	0.031			0.43		12.83	8.89T		1.04	0.611	0.045	21.94	0.206	
1	NCS DC28060	18.22	27.06		10.39						1.22	5.86		2.34	0.84	0.054	38.94		
1	NCS DC28041	14.45T	20.66		8.25	0.013			0.064		2.07	0.85T		3.74	0.60	0.48	56.03	0.177	

#	Number	Mn	MnO ₂	Mn(CO ₃)	Al ₂ O ₃	As	As ₂ O ₃	Ba	BaO	CO ₂	CaO	Fe	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	SiO ₂	TiO ₂	
	Number	Cr	Cu	Ge	Ni	P	P ₂ O ₅	Pb	S	V	Zn	LOI	Units	Other					
	IGS 29												40 g						
	VS R13/3		0.0219		0.101	0.196		0.0013	0.07				100 g						
	NCS DC26701		0.024		(0.002)	0.033		0.013	0.18		0.013		50 g	Co: 0.008					
	VS P13/1					0.197		0.0014	0.070				100 g	MnO: 90.4, last of stock					
	SRM 25d						0.251						60 g	available Oxygen: 14.28, H ₂ O: (0.96)					
	DH X4306		CuO:0.059		NiO:0.067		0.239		0.016	V ₂ O ₅ :0.017	ZnO:0.064		100 g	SrO: 0.022					
	SARM 16					0.033			0.17		0.0364		100 g						
	NCS DC35015		0.006		0.014			0.015			0.036		80 g	Co: 0.025					
	JSS 861-2		0.0064			0.086			0.0084			(3.3)	100 g	Activated O: 13.55					
	NCS DC26702		0.005		0.012	0.080		0.012	0.017		0.016		50 g	Co: 0.014					
	BAM 633-1					0.170			0.227				100 g						
	AMIS 0403		Cr2O3: (0.03)				0.08		specific gravity: 4.63		4.27		100 g	multiple Mn					
	RH01					0.28			(0.025)		12.8		100 g						
	JSS 861-3		0.0169			0.036			0.307		0.66		100 g	Active O:6.24					
	AMIS 0404		Cr2O3: (0.024)				(0.08)		specific gravity: 4.65		4.88		100 g	multiple Fe, Mn					
	NCS DC25008					0.094							50 g	B: 0.0018					
	NCS DC26703		0.033		0.0024	0.009		0.018	0.003		0.219		50 g	Co: 0.0014					
	NCS DC28045	0.038	0.022		0.079	0.230		0.011	0.0086	0.018	0.070		50 g						
	NCS DC26704		0.009		0.039	0.127		(0.007)	0.028		0.052		50 g	Co: 0.096					
	NCS DC28210		0.062		0.057	0.099		0.014			0.088		50 g						
	VS R12/2					0.209			0.029				100 g						
	AMIS 0402		Cr2O3: (0.05)				0.10		specific gravity: 4.62		4.97		100 g	multiple Ca, Fe, Mn					
	NM 166.4A					0.13			0.01				100 g						
	SARM 17					0.018			(0.01)		0.0043		100 g	last of stock					
	SARM 149					0.021							100 g						
	OREAS 170b						0.195					11.95	10 g						
	OREAS 170a						0.152					12.14	10 g						
	NCS DC28044	0.0018	0.0086		0.010	0.105		0.0083	0.021	0.0075	0.027		50 g	</					

CRM MANGANESE NODULE

analysis listed in mass % except * which is mg/kg T = Total * AMIS lists Mn by XRF and M/ICP

Number	MnO	MnO ₂	Al ₂ O ₃	COrg	CO ₂	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Density	Units
US NOD P-1	37.6	.	4.8	.	.	3.1	8.3T	1.2	3.3	2.2	0.46	13.9	0.5	.	.	25 g
AMIS 0104*	35.31*	35.49*	2.20	.	.	1.34	20.78	0.26	(0.35)	(0.10)	(P: 192*)	18.30	0.27	(3.28)	4.32	100 g or 1kg
VS 5374-90	35.09T	41.7	5.68	0.18	0.43	.	9.28T	1.27	3.40	2.94	0.68	16.60	0.74	15.3	.	50 g
JMn-1	33.09	.	4.30	.	.	2.91	14.40T	0.94	3.12	2.80	0.54	14.11	1.06	.	.	100 g
VS 5375-90	25.16T	31.1	5.46	0.22	0.60	3.01	24.87T	0.83	2.24	2.40	0.80	14.50	1.91	13.8	.	50 g
US NOD A-1	23.9	.	3.87	.	.	15.4	15.6T	0.6	4.76	1.0	1.40	3.81	0.53	.	.	25 g
VS 5376-90	19.85T	24.2	6.71	.	0.50	5.13	22.13T	1.18	2.29	2.24	1.61	22.30	1.56	11.4	.	100 g

Number	As	Au*	B*	Ba	Be*	Bi*	C*	Cd*	Ce	Cl	Co	Cr	Cr ₂ O ₃	Cs*	Cu	Dy*
US NOD P-1	.	.	.	0.3350	(0.0290)	.	0.2240	.	.	.	1.1500	(27)
AMIS 0104	(0.0116)	.	.	2.86	(2.1)	(0.61)	.	(0.78)	(0.02994)	.	0.0240	(0.01802)	(0.03)	(0.19)	(0.0192)	(10.6)
VS 5374-90	0.006	0.005	.	0.18	.	.	.	17	0.020	0.7	0.220	0.0018	.	.	1.01	.
JMn-1	0.00754	(0.00095)	(138)	0.1714	(7.8)	(4.3)	(905)	(15.5)	0.0277	.	0.1732	0.00266	.	0.60	1.1132	(28.3)
VS 5375-90	0.017	0.010	.	0.17	.	.	.	5	0.09	0.9	0.47	0.0019	.	.	0.22	.
US NOD A-1	.	.	.	0.1670	(0.0730)	.	0.3110	.	.	.	0.1100	(23)
VS 5376-90	0.014	.	.	0.16	19	.	.	.	0.10	.	0.27	0.0067	.	.	0.13	.

Number	Er*	Eu*	Ga*	Gd*	Ge*	H ₂ O+	Hf*	Ho*	In*	La	Li	Lu*	Mo	Nb	Nd	Ni
US NOD P-1	(12)	(7.5)	.	(28)	(0.0104)	.	(1.8)	0.0760	.	(0.0120)	1.3400
AMIS 0104	(5.7)	(4.3)	(35.8)	(12.1)	(1.7)	.	(3.0)	(2.0)	(0.05)	(0.00444)	(0.00183)	(0.66)	(0.00047)	(0.00055)	(0.00557)	(0.00421)
VS 5374-90	.	.	.	0.18	0.009	0.014	.	0.052	0.0020	0.008	1.37
JMn-1	14.6	7.6	(37.1)	(29.8)	.	(7.90)	(6.2)	(5.8)	.	0.0122	(0.00717)	2.1	0.0318	(0.00276)	0.0137	1.2632
VS 5375-90	0.014	0.004	.	0.033	0.009	0.014	0.422
US NOD A-1	(12)	(5)	.	(26)	(0.0120)	.	(2.2)	0.0448	.	(0.0094)	0.6360
VS 5376-90	0.012	0.0019	.	0.035	0.006	0.010	0.34

Number	Li	Lu*	Mo	Nb	Nd	Ni	Pb	Pd*	Pr*	Pt*	Rb*	S	Sb*	Sc
US NOD P-1	.	(1.8)	0.0760	.	(0.0120)	1.3400	0.0560
AMIS 0104	(0.00183)	(0.66)	(0.00047)	(0.00055)	(0.00557)	(0.00421)	(0.00507)	.	(12.6)	.	(5.3)	(0.32)	(9.7)	(4.6)
VS 5374-90	0.014	.	0.052	0.0020	0.008	1.37	0.040	.	.	0.10	21	0.10	.	11
JMn-1	(0.00717)	2.1	0.0318	(0.00276)	0.0137	1.2632	0.0430	.	(31.4)	(0.110)	10.9	(0.0940)	37.5	(13.0)
VS 5375-90	0.004	.	0.033	0.009	0.014	0.422	0.098	0.003	.	0.21	10	0.16	.	13
US NOD A-1	.	(2.2)	0.0448	.	(0.0094)	0.6360	0.0846
VS 5376-90	0.0019	.	0.035	0.006	0.010	0.34	0.105	.	.	.	19	0.16	.	19

Number	Sm	Sn*	Sr	Ta*	Tb*	Th*	Tl	Tm*	U*	V	W*	Y	Yb*	Zn	Zr
US NOD P-1	(0.0030)	.	0.0680	0.0570	.	.	(1.3)	0.1600	.
AMIS 0104	(0.00128)	(2.0)	(0.0309)	(0.21)	(1.8)	(9.5)	(0.42*)	(0.78)	(8.1)	(0.0108)	(3.5)	(0.00412)	(4.9)	0.0142	(0.01341)
VS 5374-90	0.0022	.	0.064	.	.	17	.	.	4	0.043	.	0.011	13	0.12	0.032
JMn-1	0.00302	(4.4)	0.0792	(0.64)	4.8	11.7	.	2.1	5.0	0.0424	(45.3)	0.0111	13.8	0.1068	0.0344
VS 5375-90	0.003	.	0.11	.	.	38	.	.	8	0.048	.	0.014	14	0.058	0.060
US NOD A-1	(0.0021)	.	0.1750	0.0770	.	.	(14)	0.0590	.
VS 5376-90	0.0027	.	0.11	.	.	28	0.010%	.	6	0.054	.	0.016	6	0.060	0.055

CRM MANGANESE NODULE

analysis in mass %

Number	SiO ₂	Co	Cu	T.Fe	T.Mn	Ni	Units
NM 2388	16.07	0.14	0.49	14.94	21.28	0.71	100 g

CRM MARIPOLITE

analysis listed in mass %

40 g units

Number	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	K ₂ O	MnO	Na ₂ O	Nb	Rb	SiO ₂	TiO ₂
VS 2122-81	21.96	0.72	1.20	0.88	2.05	4.30	0.085	10.79	0.034	0.030	56.29	0.045

continued

analysis listed in mg/kg

Number	Ba	Be	Cr	Cu	Ga	Ge	La	Li	Mo	Ni	Pb	Sn	Sr	V	Y	Yb	Zn	Zr
VS 2122-81	170	86	9.8	21	80	1.4	130	4.3	5.2	6.5	25	15	120	13	64	5	69	70

CRM MERCURY ORE

analysis listed in mass %

100 g units

Number	Hg	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	SiO ₂	TiO ₂	Co	Cr	Cu	Ni	Sr	V	LOI
USZ 43-2006	0.0689	0.53	17.39	0.49	4.66	0.03	9.93	0.29	0.07	41.01	0.018	0.0047	0.21	0.0007	0.10	0.0382	0.0038	25.28

RM	MOLOCHITE													analysis listed in mass %		25 g units	
Number	Al ₂ O ₃	BaO	CaO	Fe ₂ O ₃	K ₂ O	MgO	Mn ₃ O ₄	Na ₂ O	F ₂ O ₅	SiO ₂	SrO	TiO ₂	ZrO ₂				
CBRAM AN40	37.9	0.03	0.14	0.85	1.52	0.24	0.01	0.12	0.11	58.8	0.02	0.06	0.016				

CRM	MOLYBDENUM ORE AND CONCENTRATE													analysis listed in mass %		50 g units		
Number	Mo	Al ₂ O ₃	As	Bi	C	CaO	Co	Cr	Cu	F	Fe ₂ O ₃	K ₂ O	MgO	Mn				
NCS DC28184	54.29	1.35	0.0075	0.0008	0.35	0.43	0.001	0.0006	0.251	0.034	0.964	0.18	0.16	0.0064				
NCS DC28183	46.18	1.52	0.004	0.029	0.62	0.91	0.0014	0.0029	0.354	0.17	5.62	0.40	0.24	0.030				
NCS DC28186	5.67	8.69	0.0049	.	0.27	1.42	0.0011	0.0015	0.329	0.14	3.29	4.27	0.83	0.032				
NCS DC28185	2.04	9.53	0.0049	.	0.24	1.52	0.0008	0.0018	0.322	0.14	3.08	4.43	0.86	0.037				
NCS DC28182	0.24	9.76	0.0054	.	0.23	1.41	0.0011	0.0008	0.312	0.14	2.93	4.71	0.91	0.036				

Number	Na ₂ O	Ni	P	Pb	Re	S	Sb	SiO ₂	Sn	TiO ₂	W	Zn				
NCS DC28184	0.078	<0.0020	0.0044	0.057	0.0022	36.88	0.0002	4.52	0.0013	0.019	0.0071	0.018				
NCS DC28183	0.068	0.0016	0.013	0.432	0.0022	35.50	0.0004	8.35	<0.004	0.048	0.0046	0.088				
NCS DC28186	1.22	0.0006	0.036	0.032	.	5.73	.	66.50	0.0011	0.21	0.0019	0.019				
NCS DC28185	1.28	0.0008	0.034	0.016	.	3.00	.	71.32	0.0013	0.237	0.0019	0.014				
NCS DC28182	1.34	0.0012	0.038	<0.008	.	1.74	.	72.60	0.0014	0.212	0.0019	0.011				

CRM	MOLYBDENUM ORE WITH EXTENSIVE ANALYSIS													analysis listed in mass %		50 g units	
Number	Mo	Al ₂ O ₃	Ba	CaO	F	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SiO ₂	TiO ₂	W	WO ₂	Zn	Zr
NCS DC93010a*	55.4	0.23	.	0.95	C:0.34	1.44	.	0.47	.	Cu:0.06	.	2.56	.	0.12	.	0.014	.
NCS DC73522	50.08	(1.16)	.	1.95	.	1.23	(0.06)	1.96	.	(0.21)	33.72	7.58	.	0.0732	.	0.0068	.
GBW 07238	1.51	3.46	.	31.44	4.08	21.34	0.046	0.86	1.40	0.075	1.64	34.10	0.13	0.36	.	0.000655	.
NCS DC73521	0.54	5.12	.	18.09	.	9.88	0.66	4.35	.	0.90	0.68	56.87	.	0.0557	.	0.0360	.
NCS DC73520	0.15	5.20	.	18.13	.	9.89	0.66	4.37	.	0.91	0.44	57.47	.	0.0518	.	0.0365	.
KZ 7025-93	0.067	.	0.27	0.04	.	0.013
NCS DC73519 *	0.066	5.20	.	18.37	.	10.05	0.66	4.29	.	0.90	0.38	57.23	.	0.0489	.	0.0357	.

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As	Be	Bi	Cd	Co	Ce	Cr	Cu	Dy	Eu	Er	Ga	Gd	Ge	Ho	In	La	Li	Lu	Mn
NCS DC93010a*	.	.	52	600	0.033
NCS DC73522	(2.1)	(2.2)	86	0.20	10.2	.	30	266	(0.67)	0.15
GBW 07238	0.09	1.6	.	2.2	0.12	20.8	(24)	93.6	1.8	0.59	1.0	25.1	1.9	19.0	0.36	2.9	7.1	(3.2)	0.16	.	
NCS DC73521	0.13	4.7	.	8.2	0.52	13.2	.	23	48	6.2	0.91
NCS DC73520	0.10	4.8	.	7.4	0.52	12.9	.	23	46	6.0	0.91
KZ 7025-93	0.8	.	19	51	.	.	.	0.077%
NCS DC73519 *	(0.11)	5.2	.	6.9	0.50	13.3	.	23	46	6.2	0.92

Number	Nb	Nd	Ni	P	Pb	Pr	Re	Sb	Sc	Se	Sm	Sn	Tb	Te	Th	Tl	Tm	Y	Yb	
NCS DC93010a*	.	.	55	440	.	26	*	also contains	Total Oil and Water:	(0.34%)	.	.
NCS DC73522	.	.	(20)	(130)	316	.	23	13.2	.	.	.	(11.9)
GBW 07238	.	11.3	17.8	.	18.7	3.0	(0.35)	1.2	3.4	2.1	2.1	86.7	0.34	0.40	2.3	0.06	0.14	11.4	1.0	
NCS DC73521	.	.	52	(1210)	13.7	.	0.31	0.73	.	.	.	4.7
NCS DC73520	.	.	52	(1231)	10.5	.	0.12	0.60	.	.	.	4.5
KZ 7025-93	13
NCS DC73519 *	.	.	54	(1160)	9.1	.	(0.07)	0.58	.	.	.	4.7	.	.	*	also contains	Total Oil and Water:	0.85%	.	

CRM	MOLYBDENUM ORE AND CONCENTRATE													% = mass %		* = mg/kg		Insol = Insoluble Residue	
Number	Mo%	Ag*	As*	Bi*	Cu%	Fe%	Insol%	Na%	P%	Pb%	Re%	S%	Sb*	SiO ₂ %	W*	Zn%	Units/g		
SRM 423	58.61	(29)	.	(60)	0.0640	1.708	7.69	(0.2)	.	0.0433	(0.004)	(0.063)	(24)	.	.	(0.017)	50		
CGL 202	51.5	.	(278)	.	(1.34)	(1.44)	.	.	(0.014)	(0.0160)	(0.05)	(35.66)	.	(4.50)	.	.	150		
GMO-04	0.7949	1.93	4.52	95	0.0240	0.0046	.	.	8.9	.	.	0.0128	10 or 250		
GMO-03	0.5329	1.47	3.50	72	0.0191	0.0037	.	.	6.8	.	.	0.0122	10 or 250		
GMO-12	0.4797	1.04	3.5	50.0	0.01425	0.00346	.	0.39	4.41	.	1.2	0.0104	10 or 250		
GMO-11	0.2937	0.89	3.3	40.2	0.01155	0.00319	.	0.26	3.40	.	0.8	0.0101	10 or 250		
GMO-10	0.0953	0.55	2.6	15.3	0.00698	0.00262	.	0.13	1.36	.	0.6	0.0096	10 or 250		
GMO-07	0.00447	6.10	74.00	0.3	0.0014	0.0011	.	.	0.1	.	last	0.0011	10 or 250		
GMO-05	0.00277	0.88	12.71	11	0.0639	0.0013	.	.	0.5	.	.	0.0087	10 or 250		

RM	MOLYBDENUM CONCENTRATE													analysis listed in mass %		100 g units	
Number	Mo	Al ₂ O ₃	Tot.C	CaO	Cr ₂ O ₃	CuO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SiO ₂	SrO	TiO ₂	V ₂ O ₅	ZnO
DH X4710	62.63	0.435	.	0.160	.	0.197	1.659	0.116	0.058	.	.	0.034	3.16	.	0.028	.	0.024
DH 4707	61.08	0.702	0.040	1.61	0.004	0.504	1.80	0.182	0.117	0.008	0.045	0.069	4.38	.	0.040	.	0.064
DH 4706	57.55	1.178	0.016	0.644	.	0.106	3.83	0.407	0.207	0.036	1.009	0.050	7.52	.	0.092	.	.

CRM MULTI-METAL ORE

analysis listed in mass % 50 g units

Number	Fe	Cu	Pb	S	Zn	Al ₂ O ₃	As	C	CaO	K ₂ O	MgO	Mn	Na ₂ O	SiO ₂	W
NCS DC73511a	28.14	21.67	0.64	30.7	1.35	0.52	0.0253	(0.3)	2.03	0.10	0.74	0.019	(0.06)	3.91	0.00052
NCS DC73507a	27.85	0.72	0.72	7.07	0.94	3.38	0.0243	1.54	13.37	0.34	4.70	0.12	0.80	23.79	0.00050
NCS DC73510a	20.71	0.081	4.85	30.8	13.73	2.09	0.1244	1.90	7.91	0.64	0.71	0.056	0.033	9.61	0.00381
NCS DC73513a	7.33	1.79	0.80	31.6	50.59	0.45	0.0363	0.33	0.89	0.13	0.15	0.022	(0.02)	2.80	0.00068
NCS DC73508a	6.18	1.94	5.97	5.67	3.30	7.03	0.228	(0.1)	1.27	2.83	0.23	0.42	0.63	57.8	0.398
NCS DC73509a	5.75	2.81	0.34	3.32	0.36	8.10	0.0136	(0.06)	0.77	3.32	0.09	0.46	0.73	68.4	0.1288

continued analysis listed in mg/kg

Number	Ag	Bi	Cd	Ce	Ga	Ge	Hg	In	Mo	Re	Sb	Se	Sn	Te	Tl
NCS DC73511a	45.5	8.0	39.4	19.5	8.8	2.8	11.1	5.8	18.3	(0.004)	32.8	(15.5)	2.8	(2)	0.32
NCS DC73507a	14.7	0.89	24.6	112	24.7	4.3	9.6	0.47	2.1	(0.0016)	18.4	(1.8)	2.0	(0.2)	0.11
NCS DC73510a	104	9.4	357	12.7	69.2	31.5	120	0.80	3.3	(0.007)	111	(0.7)	(10)	(0.2)	0.34
NCS DC73513a	126	1.1	1207	5.0	103	65.5	472	1.5	2.7	(0.007)	93.5	(1.4)	(4)	(0.3)	(0.2)
NCS DC73508a	392	1640	317	25.2	11.9	2.8	1.3	13.1	189	(0.015)	787	(17)	944	(5)	6.5
NCS DC73509a	150	570	59.1	24.4	13.6	3.3	0.95	14.3	138	(0.068)	63.3	(7)	991	(0.5)	4.4

CRM MULTI-METAL ORE

analysis in mass % except g/T for grams per ton and * for mg/kg

Number	Ag	Al ₂ O ₃	As	Bi	Cd	Cu	Fe	Hg*	Pb	S	Sb	SiO ₂	Sn	Zn	LOI	Units
NCS DC29114	0.03679	(1.42)	0.138	.	0.066	0.071	(11.48T)	(270)	22.96	(15.92)	0.044	(20.20)	.	16.22	(12.14)	50 g
NCS DC29112	0.0362	(7.83)	0.082	.	.	0.10	(11.61T)	(0.233)	2.93	(8.17)	0.011	(59.40)	.	0.51	(10.49)	50 g
NCS DC29113	0.0103	(3.97)	0.040	.	.	0.075	(8.65T)	(0.074)	2.19	(6.02)	0.00383	(31.99)	.	1.54	(13.40)	50 g
NCS DC35008	19.8 g/T	.	0.084	.	.	0.037	22.62	.	2.07	.	0.013	.	0.125	0.51	.	60 g
NCS DC29115	0.000530	(3.25)	0.0095	.	0.119	0.021	(3.93T)	(84.8)	1.25	(16.30)	0.00205	(41.23)	.	30.19	(9.52)	50 g
NCS DC29111	0.00129	(9.96)	0.0090	.	0.019	0.020	(2.62T)	(12.6)	0.48	(3.13)	0.00090	(69.88)	.	4.94	(3.70)	50 g
NCS DC35009	.	6.70	2.17	0.120	.	1.09	.	.	0.095	.	.	4.99	0.930	1.49	.	60 g

T = Total Fe as Fe₂O₃

CRM MULTI-METAL ORE WITH EXTENSIVE ANALYSIS

analysis listed in mass % CAN PTC-1b shows classical and instrumental values for Cu and Ni # SiO₂* RTS-5: 100 g others: 200 g

Number	Al	As	Ca	Cu	Fe	Mg	Mo	Ni	Pb	S	Si	Sn	W	Zn	LOI
CAN RTS-5	6.25	0.1286	3.86	0.0647	11.9	3.31	(0.0001338)	0.1104	0.00663	1.924	19.20	.	.	0.0105	(9.90)
CAN MP-2a	5.99	(0.558)	3.22	0.0459	5.00	0.0923	0.1586	(0.00098)	0.277	0.716	31.2	0.0537	0.338	0.566	(4)
CAN SU-1b	4.30	0.000249	2.21	1.185	25.54	1.790	(0.0004)	1.953	0.0058	14.14	15.23	.	.	0.0235	(8)
CAN PTC-1b	(0.7518)	0.0222	(0.571)	7.919, 7.97#	36.78	0.441	(0.0011)	11.256, 11.29#	0.0795	29.95	2.468	(0.0120)	.	0.2083	(13.44)
CAN MP-1b	.	2.30	2.47	3.069	8.19	0.024	0.0285	.	2.091	13.79	16.79*	1.61	(0.1100)	16.67	.
CAN RTS-5	6.25	0.1286	3.86	0.0647	11.9	3.31	(0.0001338)	0.1104	0.00663	1.924	19.20	.	.	0.0105	(9.90)

continued analysis listed in mg/kg except % for mass %

Number	Ag	Au	Ba	Be	Bi	C%	Cd	Ce	Co	Cr	Cs	Dy	Er	Eu	Ga	Gd	Ge
CAN RTS-5	1.50	0.408	252	(0.7)	(2.05)	(1.617)	.	(17.0)	76.9	261	(1.0)	(2)	(2)	(0.6)	(14)	.	.
CAN MP-2a	4.82	(0.06)	12.3	1.25	989	(0.04)	14.5	357	5.50	150	5.78	32.5	(22.8)	(0.1)	(26.2)	24.8	(8)
CAN SU-1b	6.39	(0.2)	(350)	(0.4)	(2.73)	(0.04)	(3)	(35)	672	(320)	(0.3)	(1.4)	(0.7)	(0.7)	(10)	(2)	.
CAN PTC-1b	53.1	1.99	(61.5)	.	.	.	(38)	.	3253	(40)
CAN MP-1b	470	.	.	.	954	(0.028)	527	.	(4)	(1)	.	.	.

Number	H ₂ O%	Hf	Ho	In	Ir	K%	La	Li	Lu	Mn%	Na%	Nb	Nd	P%	Pd	Pr	Pt
CAN RTS-5	(1.4)	0.850	(9.7)	(16.9)	(0.3)	0.1092	1.285	(4)	(8)	0.0369	(0.14)	.	(0.2)
CAN MP-2a	.	9.40	(7.04)	(12.09)	.	(1.226)	157	81	4.36	0.1018	(0.03)	97	117.9	(0.0090)	.	38.5	.
CAN SU-1b	.	.	(0.3)	.	.	(0.6)	(17)	.	(0.09)	0.0703	(1.6)	(3)	(15)	(0.06)	0.791	.	0.491
CAN PTC-1b	0.81	.	.	.	(0.2)	(0.15)	.	.	.	(0.0193)	(0.17)	.	.	.	9.46	.	6.47
CAN MP-1b	.	(6)	.	(565)	.	(0.2)	.	.	(4)	(0.0480)	.	.	.	(0.02)	.	.	.

Number	Rb	Rh	Sb	Sc	Se	Sm	Sr	Ta	Tb	Te	Th	Ti	Tl	Tm	U	V	Y	Yb	Zr
CAN RTS-5	(30.5)	.	SO ₄ : (1.23%)	.	(8.03)	.	130.6	.	.	.	(2.25)	3132	.	.	.	(61.2)	(10.1)	.	.
CAN MP-2a	229	.	(7.84)	4.87	.	26.7	12.3	11.6	4.82	(5.75)	61.3	268	(3.16)	4.10	37	.	(229)	28.8	134
CAN SU-1b	(13)	.	(0.2)	(9)	(20.7)	(3)	(280)	(0.3)	.	(0.2)	(82.5)	(7)	(0.6)	.
CAN PTC-1b	.	(0.5)	(6)	.	(120)	.	(30)	.	(30)	.	.	(696)	.	.	.	(20)	(3)	.	.
CAN MP-1b	.	.	(54.0)	(3)	(5)	.	(50)	.	.	.	(20)	.	.	.	(150)

CRM MULTI-METAL ORE									10 or 250 g units				
Number	Pb%	Cu%	Ni%	S%	Zn%	Ag*	As*	Co*					
OREAS 317	12.13				17.45	232							
GBM920-7	3.0808	2.9848	0.0079		4.1046	133.9	586	89					
GBM995-8	2.5919	0.0264	0.0060		12.4308	52.0	53						
GBM339-5	2.1173	2.9424	2.4412		0.9493	24.2	320	46					
GBM323-5	1.0556	1.4364	0.0075		3.0969	19.9	1257	68					
GBM922-15	0.4723	3.4460	0.0066	4.91	1.5326	51.2							
GBM914-10	0.4671	0.1864	0.0011		0.9697	9.4	11	20					
GBM315-9	0.4600	3.4274	0.0071		1.5131	50.2	278	135					
GBM323-13	0.4036	0.4607	0.0447	0.64	0.3852	7.3							
GBM319-5	0.4022	0.4574	0.0443		0.3853	7.4	805	539					
GBM311-12	0.1342	0.1698	0.0668	4.4	1.4425	20.6							
GBM311-3	0.3522	1.0089	0.0642		1.4291	20.4	359	122					
GBM921-7	0.3048	0.5834	0.0042		0.9688	19.2	346	42					
GBM321-10	0.2592	0.3329	0.0121		0.3417	6.7	111	33					
GBM915-7	0.2487	0.5934	0.0073		0.5037	12.8	329	47					
GBM321-8	0.2039	0.3605	0.2236		0.1053	3	57	27					
GBM322-8	0.1970	0.2951	0.2136		0.7016	8.4	735	165					
GBM396-1	0.1916	0.2873	0.2140		0.6990	8.1	743						
GBM921-10	0.1902	0.2292	0.0397		0.1959	10.2	745	59					
GBM319-6	0.1887	0.2186	0.0225		0.1842	3.5	375	271					
GBM319-6	0.1887	0.2186	0.0225		0.1842	3.5	375	271					
GBM901-8	0.1657	0.0837	0.0132		0.0272	2.2	82	35					
GBM322-15	0.1343	0.1698	0.0223	2.21	0.8817	29.2	917	113					
GBM916-2	0.1335	0.1675	0.0223		0.8792	29.0	72	10					
GBM906-10	0.1252	0.1916	0.0036		0.0595	1.6	18	27					
GBM316-1	0.1248	0.2966	0.0052		0.2572	6.3	163	40					
GBM319-3	0.1116	0.4055	0.0025		0.4067	7.4	887	211					
GBM999-8	0.1061	0.1852	0.3014		0.0537	1.8	185	25					
GBM913-8	0.0923	0.4379	0.0006		0.0127	6.7	1409	12					
GBM322-10	0.0904	0.0707	0.0261		0.0809	3	759	53					
GBM914-8	0.0849	0.6241	0.0414		0.3786	8.5	316	90					
GBM396-6	0.0774	1.3903	0.0083		0.0260	5.4	541						
GBM313-1	0.0738	0.3079	0.0015		0.1170	4.9	26	10					
GBM913-7	0.0653	0.7990	0.0010		0.0431	7.0	2052	17					
GBM316-2	0.0626	0.1523	0.0041		0.1331	3.2	82	35					
GBM910-7	0.0592	0.5335	0.0117		0.1249	7.1	80	86					
GBM323-12	0.0580	0.7868	0.0010	6.44	0.0421	6.9							
GBM314-2	0.0532	0.0419	0.0029		0.0975	3.3	4912	7					
GBM320-1	0.0527	0.0872	0.0023		0.0486	1.9	657	7					
GBM919-9	0.0520	0.1526	0.0069		0.5198	6.0	98	44					
GBM319-4	0.0505	0.1756	0.0017		0.1791	3.3	390	95					
GBM913-1	0.0477	0.3964	0.0005		0.0787	10.0	705	9					
GBM320-10	0.0476	0.1531	0.0563		0.1139	6.2	142	45					
GBM900-2	0.0464	0.0859	0.0886		0.0334	1.2	786	61					
GBM908-6	0.0461	0.0441	0.4736		0.1354	1.2	14	832					
GBM914-4	0.0439	0.3948	0.0128		0.0387	1.1	19	204					
GBM922-9	0.0436	0.7535	0.0027		0.0037	4.9	257	49					
GBM305-4	0.0416	0.1138	0.0475		0.1199	2.6	263	70					
GBM913-9	0.0404	0.4542	0.0006		0.0158	3.8	611	13					
GBM907-8	0.0388	0.0339	0.4295		0.1234	1.0	11	219					
GBM318-2	0.0373	0.2149	0.0026		0.2103	3.5	573	535					
GBM317-2	0.0338	0.7414	0.0011		0.2356	7.4	166	388					
GBM996-4	0.0336	0.0492	0.0036		0.0968	3.6	442						
GBM323-14	0.0317	6.1400	4.7118	7.33	0.0098	66.5							
GBM917-4	0.0305	6.1310	4.7052		0.0090	65.7	2.04%	1.16%					
GBM913-10	0.0300	0.3019	0.0007		0.0380	3.0	823	10					
GBM913-4	0.0291	0.1556	0.0104		0.0282	2.0	255	193					
GBM906-6	0.0288	0.0171	0.0013		0.0210	1.0	392.8	10					
GBM916-10	0.0282	0.2393	0.0011		0.1235	4.5	135	319					
GBM323-10	0.0272	0.1360	0.2587		0.0317	1.1	57	158					
GBM322-9	0.0258	0.1457	0.1765		0.0696	3.2	936	50					
GBM919-7	0.0246	0.1250	0.1954		0.0226	3.6	288	85					
GBM322-7	0.0245	0.1089	0.0060		0.0924	1.6	176	24					
GBM302-5	0.0239	0.0559	0.0498		0.0359	1.8	1873	50					
GBM313-3	0.0239	0.0875	0.0256		0.1012	4.0	1039	37					
GBM316-10	0.0223	0.4554	0.0006		0.0178	1.3	179	8					
GBM300-7	0.0219	0.045	0.0013		0.0163	153.8	9	9					
GBM318-1	0.0215	0.1187	0.0031		0.1061	3.2	329	243					
GBM917-1	0.0209	0.0079	0.0017		0.1646	1.0	384	15					
GBM916-6	0.0207	0.3321	0.0004		0.0029	0.5	1104	6					
GBM907-11	0.0191	0.3873	4.5163	7.56	0.1033	4.7							
GBM397-8	0.0189	0.1419	0.1320		0.0363	1.5	553						
GBM922-12	0.0184	1.3975	2.0429	6.90	0.3402	4.4							
GBM914-2	0.0175	0.1824	0.0099		0.0626	2.9	9	26					
GBM321-6	0.0157	0.0051	0.0052		0.2169	2.9	340	20					
GBM916-5	0.0149	0.7006	0.0005		0.0268	2.3	22	10					
GBM921-9	0.0149	0.1248	0.0214		0.0632	5.9	394	36					
GBM917-5	0.0148	2.5667	2.1664		0.0042	29.3	9335	0.51%					
GBM310-5	0.0140	0.0335	0.3691		0.0483	0.5	12	247					
GBM323-3	0.0137	0.0055	0.0060		0.0570	3.5	113	31					
GBM915-1	0.0135	0.0485	0.0176		0.0513	7.2	246	89					
GBM305-3	0.0135	0.0451	0.0272		0.0372	1.7	656	46					
GBM311-7	0.0134	0.0948	0.0126		0.0452	2.0	830	28					
GBM321-3	0.0132	0.0050	0.0044		0.0775	5.9	635	19					
GBM914-1	0.0118	0.1152	0.0069		0.0427	4.8	6	24					
GBM922-5	0.0118	0.0580	0.2552		0.0110	0.6	228	49					
GBM323-6	0.0112	0.5353	0.0036		0.0388	1.8	39	72					
GBM313-4	0.0110	0.0342	0.0250		0.0337	2.7	385	33					
GBM908-1	0.0110	0.0074	0.0053		0.0102	1.7	10	34					
GBM323-8	0.0107	0.1491	0.0063		0.0696	0.9	6	26					
GBM323-7	0.0104	0.2993	0.0299		0.0371	2.4	1137	36					
GBM319-2	0.0101	0.0155	0.0109		0.0101	0.3	65	88					
GBM919-5	0.0100	0.1670	0.2419		0.0172	0.6	10	83					
GBM914-5	0.0097	0.0989	0.0054		0.0057	0.8	15	15					
GBM305-2	0.0094	1.2970	0.0210		0.0592	4.1	43	40					
GBM904-9	0.0091	0.0054	0.0045		0.0080	1.2	2	27					
GBM904-9	0.0091	0.0351	0.1122		0.0287	1.8	6474	117					
GBM323-4	0.0089	0.1540	0.0027		0.5232	6	94	27					
GBM915-5	0.0087	0.0307	0.0106		0.0333	3.9	128	61					
GBM314-12	0.0077	2.9880	0.0127	7.79	0.5516	3.1							
GBM903-10	0.0074	0.0198	0.0559		0.0140	1.2	2779	57					
GBM319-10	0.0075	0.0122	0.0006		0.0831	1.1	2196	3					
GBM918-1	0.0075	0.0094	0.0066		0.0166	0.3	18	54					

CRM MULTI-METAL ORE									10 or 250 g units				
Number	Pb%	Cu%	Ni%	S%	Zn%	Ag*	As*	Co*					
GBM305-6	0.0069	0.0242	0.0062		0.0120	1.5	315	31					
GBM315-5	0.0067	0.0045	0.0005		0.0154	14.8	72	9					
GBM918-2	0.0065	0.0081	0.0072		0.0101	0.2	22	29					
GBM921-3	0.0063	0.0038	0.0045		0.0476	1.6	100	19					
GBM321-5	0.0059	0.0157	0.0027		0.1495	1	89	18					
GBM321-15	0.0058	1.5473	2.3789	24.07	0.0105	3.5							
GBM320-2	0.0056	0.0117	0.0005		0.0012	27.1	42	4					
GBM919-6	0.0055	0.2756	0.5208		0.0218	1.9	591	358					

CRM MULTI-METAL ORE

10 or 250 g units

Number	Pb%	Cu%	Ni%	S%	Zn%	Ag*	As*	Co*
GBM316-6	0.0011	0.701	0.0003	.	0.0045	0.5	3	8
GBM919-3	0.0011	0.6054	0.0019	.	0.00117	3.6	2	31
GBM916-8	0.0011	0.2692	0.0772	.	0.0095	0.4	30	52
GBM318-6	0.0011	0.2446	0.0819	.	0.0204	6.9	200	53
GBM920-5	0.0011	0.0773	0.0047	.	0.0065	0.5	22	14
GBM922-1	0.0011	0.0184	0.0059	.	0.0207	0.8	76	26
GBM320-7	0.0010	0.4445	0.0021	.	0.0097	2.7	3	73
GBM318-5	0.0010	0.2993	0.0827	.	0.0127	4.7	179	56
GBM320-6	0.0010	0.2702	0.0021	.	0.0043	1.4	3	37
GBM919-2	0.0010	0.1592	0.0015	.	0.0039	0.8	3	41
GBM916-3	0.0010	0.1293	0.0048	.	0.0079	1.0	12	14
GBM918-10	0.0010	0.0992	0.0038	.	0.0077	0.8	14	13
GBM914-9	0.0010	0.0952	0.0058	.	0.0070	0.8	10	15
GBM920-6	0.0010	0.0760	0.0056	.	0.0075	0.7	30	16
GBM317-3	0.0010	0.0736	0.0066	.	0.0071	0.7	17	17
GBM316-9	0.0010	0.0710	0.0003	.	0.0040	0.5	3	7
GBM300-9	0.0010	0.0317	0.3765	.	0.0084	0.8	11	182
GBM300-4	0.0010	0.0266	0.8118	.	0.0098	0.7	18	258
GBM921-5	0.0010	0.0558	0.0032	.	0.0098	2.6	156	24
GBM904-1	0.001	0.0077	0.0035	.	0.0092	0.6	7	28
GBM920-4	0.0009	0.2746	0.0719	.	0.0085	0.4	35	47
GBM320-5	0.0009	0.1259	0.0021	.	0.0037	0.6	2	57
GBM323-1	0.0009	0.0702	0.0033	.	0.0099	1.2	178	22
GBM322-1	0.0008	0.0868	0.0048	.	0.0066	0.6	4	14
GBM922-2	0.0008	0.0256	0.0034	.	0.0091	0.8	67	24
GBM322-6	0.0007	0.0794	0.0030	.	0.0075	1.3	241	26
GBM920-9	0.0006	0.0020	0.0014	.	0.0039	50.9	2	10
GBM900-8	0.0010	0.0046	3.8468	.	0.0053	4.7	8	50
GBM320-4	0.0009	0.3238	0.0743	.	0.0090	0.5	32	49
GBM320-5	0.0009	0.1259	0.0021	.	0.0037	0.6	2	57
GBM901-4	0.0009	0.0946	0.0018	.	0.0069	0.7	6	21
GBM910-15	0.0009	0.0381	0.5621	0.1	0.0062	1.1	.	.
GBM397-9	0.0009	0.0059	0.0042	.	0.0073	0.9	11	.
GBM998-9	0.0009	0.0023	0.0013	.	0.0027	101.9	7	8
GBM307-2	0.0009	0.0089	0.0034	.	0.0094	0.5	8	31
GBM314-6	0.0008	0.4290	0.0072	.	0.0117	0.6	14	205
GBM916-7	0.0008	0.3170	0.0769	.	0.0090	0.3	31	49
GBM316-7	0.0008	0.2742	0.0849	.	0.0077	0.5	44	52
GBM907-9	0.0008	0.0365	0.5442	.	0.0053	0.8	12	305
GBM906-7	0.0008	0.0362	0.5562	.	0.0051	0.9	25	210
GBM305-5	0.0008	0.0194	0.1785	.	0.0056	0.5	67	51
GBM998-5	0.0008	0.0056	0.0025	.	0.0084	0.6	10	28
GBM910-8	0.0008	0.0055	0.0024	.	0.0087	0.7	5	28
GBM307-4	0.0007	0.0059	0.0025	.	0.0077	3.9	6	25
GBM915-2	0.0007	0.0065	0.0036	.	0.0119	9.9	8	37
GBM314-10	0.0006	0.0061	0.0036	.	0.0121	0.7	4	39
GBM313-8	0.0006	0.0058	0.0035	.	0.0114	0.4	2	36
GBM910-9	0.0006	0.0055	0.0023	.	0.0081	0.5	2	27
GBM911-8	0.0006	0.0055	0.0023	.	0.0088	0.7	4	27
GBM918-6	0.0005	0.0478	0.1437	.	0.0370	1.4	12	71
GBM912-4	0.0005	0.0054	0.0025	.	0.0084	0.4	3	26
GBM318-3	0.0005	0.0054	0.9874	.	0.0327	0.5	3	807
GBM318-7	0.0002	0.0003	0.0002	.	0.0002	0.1	2	1
GBM316-5	0.0004	0.0057	0.0036	.	0.0114	0.4	1	37

Number	Pb%	Cu%	Ni%	S%	Zn%	Ag*	As*	Co*
--------	-----	-----	-----	----	-----	-----	-----	-----

NICKEL ORE

listed in mass % except * which is mg/kg

GBM: CRM, 10 or 250g

IGS, NCS: CRM, 50g

JSM: RM, 50g

Number	Ni	Cd	Co	Cr	Cu	Fe	Mn	Pb	S	Zn	Ag*	Al ₂ O ₃	CaO	MgO	P	SiO ₂	Ti
GBM909-15	11.5901	.	.	.	1.3120	.	.	0.2120	26.7	2.6608	13.5
NCS DC28072	5.71	0.047	0.042	0.015	0.270	23.73	0.037	0.040	2.51	4.65	.	3.91	6.47	1.14	1.61	21.10	0.15
NCS DC28079	3.98	0.028	0.041	0.364	0.169	20.74	0.147	0.030	1.41	2.85	.	3.55	4.54	8.67	1.08	27.48	0.098
GBM911-14	3.2361	.	.	.	0.2856	.	.	0.0091	10.5	0.0180	1.7
GBM910-13	2.6969	.	.	.	0.2306	.	.	0.0034	8.2	0.0152	1.9
GBM911-15	2.2856	.	.	.	0.5003	.	.	0.0253	8.1	0.0288	2.9
JSM 0800-1	2.27	.	0.053	0.70	.	14.2	0.98	0.030	26.2	.	35.7	.
NCS DC28078	2.18	(<0.0015)	0.055	0.76	0.0058	14.89	0.254	0.0020	0.034	0.079	.	1.59	0.46	21.28	0.029	39.20	0.027
JSM 0800-2	2.07	.	0.036	0.57	.	11.5	1.27	0.37	23.3	.	45.4	.
GBM915-12	2.0155	.	.	.	0.9137	.	.	0.0051	6.35	0.0573	2.5
GBM307-13	1.9995	.	.	.	0.1251	.	.	0.0045	6.78	0.0117
NCS DC28077	1.97	(<0.0015)	0.060	0.823	0.0016	14.84	0.263	0.0015	0.016	0.021	.	1.03	0.14	25.49	0.0043	36.00	0.017
IGS 21	1.97	.	0.069	0.84	0.798	23.40
JSM 0800-3	1.90	.	0.072	0.84	.	15.0	0.84	0.034	26.1	.	34.9	.
NCS DC28076	1.86	(<0.0015)	0.065	0.92	0.0017	15.20	0.282	0.0016	0.016	0.021	.	1.04	0.10	25.70	(<0.007)	34.70	0.015
NCS DC28075	1.70	(<0.0015)	0.043	0.80	0.0025	14.92	0.294	0.0013	0.014	0.019	.	2.00	0.385	21.05	0.0043	38.77	0.039
GBM921-15	1.6906	.	.	.	0.0057	.	.	0.0033	0.45	0.0249	0.6
GBM919-14	1.6566	.	.	.	0.0288	.	.	0.0361	2.90	0.1391	1.1
GBM309-6	1.6113	.	0.0909	.	0.0277	.	.	0.0341	.	0.1344	1.2	.	As:0.0018
NCS DC28080	1.30	(<0.0025)	0.033	1.38	0.0071	34.55	0.192	0.0019	0.180	0.022	.	6.53	0.070	10.54	0.020	15.48	0.092
GBM318-8	1.2863	.	0.3258	.	1.7336	.	.	0.0097	.	0.0035	18.5	.	As:0.5606
GBM323-15	1.2702	.	.	.	0.0055	.	.	0.0012	0.10	0.0237	1.1
GBM316-15	1.2308	.	.	.	0.0056	.	.	0.0022	0.10	0.0257	1.0
NCS DC28073	1.17	(<0.0015)	0.042	0.95	0.0049	18.57	0.327	0.0024	0.024	0.019	.	2.90	0.82	20.75	(<0.007)	37.41	0.024
GBM922-11	1.1664	.	.	.	0.0016	.	.	0.0014	0.03	0.0145	0.6
GBM919-15	1.1621	.	.	.	0.0158	.	.	0.0111	0.81	0.0670	1.6
NCS DC28074	0.892	(<0.0020)	0.014	1.84	0.012	46.99	0.149	0.0023	0.288	0.023	.	10.29	0.033	0.51	0.030	2.52	0.145
GBM305-16	0.6503	.	.	.	0.0381	.	.	0.0026	.	0.0092

Number	Ni	Cd	Co	Cr	Cu	Fe	Mn	Pb	S	Zn	Ag*	Al ₂ O ₃	CaO	MgO	P	SiO ₂	Ti
--------	----	----	----	----	----	----	----	----	---	----	-----	--------------------------------	-----	-----	---	------------------	----

CRM NOBLE METAL ORE - CERTIFIED BY ANALYTICAL METHOD

analysis listed in mg/kg Ni = Nickel Sulfide, Pb = Lead Extraction analysis listed in mass % AR = Aqua Regia, M = M/ICP, X = XRF

Number	Pd(Ni)	Pd(Pb)	Pt(Ni)	Pt(Pb)	Rh(Ni)	Ru(Ni)	Au(Ni)	Au(Pb)	Ir(Ni)	Co(M)	Co(AR)	Cu(M)	Cu(AR)	Cu(X)	Ni(M)	Ni(AR)	Ni(X)
AMIS 0314	11.74	11.35	34.17	32.20	(1.89)	5.13	2.50	2.53	(0.91)	0.0242	0.0212	0.7326	0.7115	0.7183	0.8790	0.8429	0.9073
AMIS 0354	(1.33)	1.34	(2.19)	2.25	(0.25)	(0.39)	(0.68)	0.71	(0.08)	(0.0145)	(0.00911)	0.0582	0.0586	0.0587	(0.1839)	0.1493	(0.1886)
AMIS 0443	.	0.97	.	0.78	(0.07)	.	.	(0.14)	.	0.00988	(0.00700)	0.0951	0.0935	0.0879	0.1918	0.1678	(0.1833)
AMIS 0451	.	(0.254)	(0.534)	(0.518)	.	.	.	(0.044)	.	(0.0142)	(0.001312)	0.00755	0.00757	.	0.0903	0.0214	.

analysis listed in mass % S by combustion, rest by XRF SP.G = Specific Gravity 4E = sum Pd + Pt + Rh + Au 100 g units

Number	Al ₂ O ₃	CaO	Co	Cr	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SiO ₂	TiO ₂	Sp.G	LOI	4E g/t
AMIS 0314	7.75	5.46	(0.0271)	.	0.96	15.68	0.14	17.04	0.15	0.58	3.49	44.23	0.22	3.11	(4.92)	50.30
AMIS 0354	5.50	4.01	.	.	1.94	18.32	0.09	23.65	0.24	0.37	0.36	44.63	0.59	3.330	.	4.45
AMIS 0443	8.10	7.08	.	.	1.72	11.61	0.26	20.06	0.32	0.62	.	44.67	0.25	3.03	(4.77)	1.96
AMIS 0451	11.61	4.05	.	.	13.42	16.89	0.13	16.69	(0.19)	0.62	.	36.19	0.46	3.46	.	0.83 last

CRM NOBLE METAL ORE

analysis listed in ppb (ng/g) mass % except * which is mg/kg GPP: 10g or 1kg NCS: 500g or 1kg CAN WMS-1A: 200g other CAN: 400g

Number	Au	Ir	Os	Pd	Pt	Rh	Ru	Hg	Al ₂ O ₃	As*	Cr*	Cu	Fe ₂ O ₃	K ₂ O	MnO	Ni	S
NCS DC29116 (2310)	1.6	1.9	1680	2430	1.9	1.5	(0.70)	(1.47)	(12.24)	(0.17)	3.58	(13.10)	(0.12)	(0.11)	1.78	(7.44)	
NCS DC29119 (2120)	1.9	1.6	1330	4440	1.4	0.71	(7.01)	(0.87)	(537.6)	(0.06)	0.62	(1.59)	(0.12)	(0.047)	1.76	(0.19)	
GPP-10	1576	.	2008	2349
NCS DC29118 (1450)	3.2	3.0	700	900	3.2	3.5	(1.01)	(4.90)	(21.58)	(0.093)	3.25	(24.09)	(0.35)	(0.13)	1.76	(13.41)	
NCS DC29118 (1450)	3.2	3.0	700	900	3.2	3.5	(1.01)	(4.90)	(21.58)	(0.093)	3.25	(24.09)	(0.35)	(0.13)	1.76	(13.41)	
NCS DC29117 (1430)	4.4	3.7	600	10610	3.6	4.2	(1.39)	(4.50)	(22.6)	(0.16)	3.01	(26.66)	(0.39)	(0.12)	0.053	(13.57)	
GPP-06	980	.	709	938
GPP-02	929	.	523	505
GPP-14	909	.	481	503
GPP-05	859	.	699	912
GPP-11	722	.	567	592	last
GPP-13	612	.	390	307
GPP-09	603	.	408	343
CAN WMS-1A	300	(322)	(150)	1450	1910	222	(145)	.	Al:1.350	30.9	(68)	1.396	45.4 Fe	.	.	.	28.17
NCS DC29120 (170)	23.6	8.2	400	380	18.0	7.8	(58.1)	(2.83)	(66.0)	(0.30)	0.11	(9.30)	(0.12)	(0.14)	0.22	(0.17)	
GPP-04	80	.	98	88
GPP-12	50	.	47	48
GPP-08	49	.	45	54	last
CAN UMT-1	48	8.8	106	128	9.5	10.9
NCS DC73357 (45)	28	15.6	568	440	22	13
GPP-07	25	.	23	28	last
NCS DC73353	10	0.05	0.06	2.3	1.6	0.95	(0.10)
CAN TDB-1	6.3	.	22.4	5.8
GPP-03	4	.	7	8
CAN WGB-1	2.9	(0.33)	.	13.9	6.1	(0.32)	(0.3)	.	.	291	.	6.71	0.94	MgO: 9.40	.	.	.
NCS DC73358	(1.8)	1.2	0.64	15.2	14.7	1.1	0.66
NCS DC73354	1.1	4.3	9.6	4.6	6.4	1.3	14.8
NCS DC73352	0.9	0.032	0.05	0.26	0.26	0.017	(0.05)
NCS DC73356	.	136	353	11.3	20	10	527
NCS DC73398	.	28	43	570	1900	7.3	74
NCS DC73399	.	2.1	(2)	1670	5700	1.5	(2)

Number	Au	Ir	Os	Pd	Pt	Rh	Ru	Hg	Al ₂ O ₃	As*	Cr*	Cu	Fe ₂ O ₃	K ₂ O	MnO	Ni	S
--------	----	----	----	----	----	----	----	----	--------------------------------	-----	-----	----	--------------------------------	------------------	-----	----	---

CRM **OBSIDIAN**

analysis listed in mass %											35 g units		analysis listed in mg/kg							
Number	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	Cu	Ni	Pb	Rb	Sr	Th	Ti	U	
SRM 278	14.15	0.983	1.36	2.04	4.16	(0.23)	0.052	4.84	0.036	73.05	0.245	5.9	3.6	16.4	127.5	63.5	12.4	0.54	4.58	

RM **OLIVINE WITH EXTENSIVE ANALYSIS**

analysis listed in mass %														100 g units		
Number	Al ₂ O ₃	CaO	Co	Cr	TFe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	Ni	P ₂ O ₅	SiO ₂	TiO ₂	LOI		
IAG MUH-1	1.33	1.21	0.0106	(0.2710)	8.59	0.012	38.2	0.117	0.10	0.210	0.007	40.3	0.034	9.38		
continued analysis listed in mg/kg																
Number	As	Ba	Ce	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Ho	La	Li	Lu	Nb
IAG MUH-1	(3.6)	4.9	(0.20)	0.099	19	0.153	0.108	0.026	1.38	(0.110)	0.04	0.035	(0.134)	(1.8)	0.019	(0.062)
Number	Nd	Pb	Pr	Rb	Sb	Sc	Sm	Sr	Tb	Th	Tm	U	V	Y	Yb	Zn
IAG MUH-1	0.177	(0.42)	0.035	0.27	(0.134)	9.0	0.067	(8.5)	0.0212	0.018	0.0170	(0.014)	(41)	(0.97)	0.118	44

RM **OLIVINE**

typical analysis listed in mass %															100 g units	
Number	MgO	SiO ₂	Fe	Al ₂ O ₃	C tot	CO ₂	CaO	Co ₃ O ₄	Cr ₂ O ₃	K ₂ O	Mn ₃ O ₄	NiO	P ₂ O ₅	TiO ₂	-H ₂ O at 900°C	
DH 4912	49.18	41.6	5.07	0.432	0.054	0.046	0.081	0.016	0.383	0.014	0.103	0.354	.	0.002	1.25	

CRM **OOZE**

Number	Type	SiO ₂	Al ₂ O ₃	Ba	CO ₂	CaO	Ce	Cr	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	
VS 5370-90	Calcerous	11.90	3.60	0.010	32.20	39.23	.	0.0034	0.17	2.44	0.51	3.44	0.218	1.86	0.23	0.30	36.6	
VS 5371-90	Siliceous	59.60	8.96	0.15	2.70	6.40	0.033	0.0080	1.2	5.05	1.39	3.16	0.37	4.52	0.12	0.59	9.6	
continued																		
analysis listed in mass %																		
Number	As	B	Org.C	Cu	Ni	S	Sn	Sr	V	Zn	Zr							
VS 5370-90	.	.	.	0.0030	0.0038	0.19	0.021	0.12	0.0057	0.010	0.008							
VS 5371-90	0.0020	0.007	0.34	0.014	0.010	0.17	0.00032	0.034	0.0085	0.0090	0.010							
continued																		
analysis listed in mg/kg																		
Number	Au	Be	Co	Cs	Ga	La	Li	Mo	Nb	Nd	Pb	Rb	Sc	Sm	Th	U	Y	Yb
VS 5370-90	.	1.0	12	.	5	7	13	4	.	.	11	11	6	3	.	9	.	.
VS 5371-90	0.004	1.6	30	3.0	11	15	18	2.8	10	13	24	46	17	2.5	5	1.5	16	2.2

PEGMATITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %				IAG: RM, ~35 g units							NCS: CRM, 70 g units				VS: CRM, 50 g units			
Number	Al ₂ O ₃	CO ₂	CaO	F	FeO	Fe ₂ O ₃	H ₂ O ⁺	K ₂ O	MgO	Mn	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI	
VS 6318-92	18.81	.	0.43	0.107	0.49	0.80T	.	1.33	0.27	.	0.054	8.44	0.29	.	68.06	0.100	0.91	
NCS DC71313	13.19	(0.05)	(0.1)	(0.03)	(0.04)	(0.24T)	(1.02)	6.22	0.13	(0.01)	.	1.60	0.18	0.07	76.40	0.61	1.27	
IAG OU-9	12.35	.	0.29	.	.	0.74	.	1.36	.	.	0.11	4.17	0.03	.	79.5	0.057	0.78	

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As	B	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd
VS 6318-92	56	13	95	35	.
NCS DC71313	(0.09)	3.1	(1.9)	(728)	1.3	(0.07)	0.15	(5)	(1.5)	4.8	1.8	4.2	0.20	0.12	(0.16)	13.5	0.22
IAG OU-9	.	.	.	8.75	.	.	.	7.24	.	.	403.3	.	1.70	0.30	0.05	56.6	2.53

Number	Ge	Hf	Hg	Ho	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se
VS 6318-92	8.6	220	.	.	72	450	.	.	(0.015)
NCS DC71313	1.5	(0.8)	(0.008)	(0.04)	(3.3)	14.4	0.03	(0.29)	14.6	1.5	(1.6)	34.6	0.48	155	0.64	(2.85)	.
IAG OU-9	4.95	.	.	0.15	2.03	694.6	0.04	.	155.3	5.07	.	.	1.24	2501	7.67	2.77	.

Number	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
VS 6318-92	.	600	68	69	14	.	.	.	49	56	.
NCS DC71313	(0.24)	3.5	45.5	1.3	(0.04)	0.66	.	(0.02)	(0.75)	44.5	3.2	1.6	0.21	20.3	22.6
IAG OU-9	3.15	.	.	124.7	0.46	5.08	13.8	0.05	4.37	.	6.1	8.14	.	28.15	.

CRM PERIDOTITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	Al	Al ₂ O ₃	C	CO ₂	Ca	CaO	Co	Cr	Cu	Fe	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O ⁻	H ₂ O ⁺	K	K ₂ O
VS 2111-81	.	1.84	.	0.69	.	1.26	0.0159	0.320	0.0140	.	0.83	.	11.58	.	.	.	0.044
CAN WPR-1a	2.621	.	(0.15)	.	2.528	.	0.0213	(0.322)	0.299	11.34	0.156	.
JP-1	0.35	0.66	(0.0764)	.	0.39	0.55	0.0116	0.2807	0.000672	5.85	5.99	1.98	8.37	0.44	2.39	0.002	0.003

Number	Mg	MgO	Mn	MnO	Na	Na ₂ O	Ni	P	P ₂ O ₅	S	Si	SiO ₂	Ti	TiO ₂	V	Zn	LOI
VS 2111-81	.	37.12	.	0.183	.	0.105	0.160	.	0.030	.	45.54	.	.	0.107	0.0039	0.0137	.
CAN WPR-1a	(15.22)	.	0.138	.	(0.050)	.	0.439	0.0303	.	1.768	17.62	.	0.3527	.	0.0135	0.0160	(8.42)
JP-1	26.9	44.60	0.094	0.121	0.02	0.021	0.2460	.	(0.002)	(0.00269)	19.81	42.38	.	(0.006)	0.00276	0.00418	.

continued analysis listed in mg/kg

Number	Ag	As	Au	B	Ba	Be	Bi	Cd	Ce	Cl	Cs	Dy	Er	Eu	F	Ga	Gd
VS 2111-81	66	5.9	.
CAN WPR-1a	1.02	9.3	(0.05)	.	70.6	(0.2)	0.122	0.598	9.69	.	2.38	1.624	0.886	0.497	.	7.04	1.76
JP-1	(1.5)	0.34	(0.00023)	(1.4)	(19.5)	.	.	(0.011)	(0.19)	(97)	(0.15)	(0.022)	(0.016)	(0.004)	(14)	(0.7)	(0.015)

Number	Ge	Hf	Hg	Ho	In	Ir	La	Li	Lu	Mo	Nb	Nd	Os	Pb	Pd	Pr
VS 2111-81	1.6	1.3	.	.	.	6.7	.	.
CAN WPR-1a	(0.3)	1.142	(0.05)	0.322	(0.0899)	(0.2)	4.04	25.6	0.121	(0.9)	(3.88)	6.26	.	7.92	0.614	1.362
JP-1	(0.49)	0.2	(0.0053)	(0.018)	.	(2)	0.084	(1.79)	(0.0044)	(0.087)	1.48	(0.072)	(0.0079)	(0.12)	(0.0013)	(0.02)

Number	Pt	Rb	Re	Ru	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm
VS 2111-81	11.3	.	.	3.2
CAN WPR-1a	0.452	7.06	.	.	3.13	17.3	(7.7)	1.617	(1.16)	19.5	(0.242)	0.269	(0.958)	(0.64)	(0.0752)	0.126
JP-1	(0.0049)	(0.8)	(0.00001)	(0.0065)	(0.034)	7.24	.	0.019	(0.05)	(3.32)	(0.02)	(0.003)	.	0.19	(0.003)	.

Number	U	W	Y	Yb	Zr	Units
VS 2111-81	.	.	.	1.5	21	40 g
CAN WPR-1a	.	.	8.39	0.79	(41.8)	400 g
JP-1	0.036	(0.85)	1.54	0.022	5.92	20 g

CRM PHOSPHATE ROCK

* CaO+SrO ** AFPC Method (s) = soluble analysis listed in mass % GPO: 10 g units SRM: 90 g units others: 100 g units

Number	P ₂ O ₅	CaO	Al ₂ O ₃	CO ₂	F	Fe ₂ O ₃	TFe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	S	SO ₃	SiO ₂	SrO	TiO ₂	LOI
SARM 32	39.96	54.44	(0.05)	1.61	2.49	0.14	.	.	0.50	(0.026)	.	.	.	(0.4)	0.52	.	.
GBW 07210	36.89	51.32*	0.58	2.15	3.54	.	1.04	0.17	0.43	0.024	0.33	.	.	3.26	0.077	0.037	.
IPT 18B	35.7	52.6	0.35	.	1.33	0.21	.	0.23	1.65(s)	.	0.14(s)	.	.	1.15	0.48(s)	.	.
SRM 120c	33.34**	48.02**	1.30	3.27**	3.82**	1.08	.	0.147	0.32**	0.027	0.52	(0.37)	.	5.5**	(0.1)	0.103	.
BCR 032	32.98	51.76	0.55	5.10	4.04	0.231	.	.	0.403	.	.	.	1.84	2.09	.	.	.
SRM 694	30.2	43.6	1.8	.	3.2	0.79	.	0.51	0.33	0.0116	0.86	.	.	11.2	.	(0.11)	.
GPO-01	28.66	40.08	6.92	.	.	3.412	.	0.10	0.83	0.093	0.307	.	1.318	4.381	.	0.37	12.45
USZ 14-94	26.38	38.85	0.85	5.84	.	.	0.63	0.092	2.26	20.57	.	.	6.43
GPO 15	25.22	45.12	0.74	.	.	0.803	.	0.25	2.90	0.010	1.039	.	2.426	7.77	.	0.05	12.32
GPO-14	24.52	44.77	0.78	.	.	0.819	.	0.26	3.07	0.047	0.979	.	2.284	8.13	.	0.05	12.96
GBW 07211	20.86	40.71*	2.58	18.46	2.05	.	1.08	0.28	8.19	0.015	0.059	0.79	.	3.61	0.16	0.14	.
USZ HF	13.81	33.80	0.37	0.077	8.30	.	0.12	.	.	28.04	.	.	.
GBW 07212	6.06	19.42*	4.06	16.41	0.51	.	3.08	2.63	7.12	0.026	0.14	.	.	38.80	0.055	0.48	.
GPO-13	4.94	6.84	10.02	.	.	5.391	.	3.75	0.68	0.030	1.454	.	0.239	62.622	.	0.16	3.43

continued

analysis listed in mass %

analysis listed in mg/kg

Number	BaO	CdO	U	U ₃ O ₈	V ₂ O ₃	V ₂ O ₅	As	B	Cd	Cl	Co	Cr	Cu	Hg	I	Mn	Ni	Ti	V	Zn
SARM 32	(640)
GBW 07210	52
IPT 18B
SRM 120c	.	.	.	0.0135	0.016
BCR 032	9.5	22.6	20.8	.	0.59	257	33.7	0.0551	.	18.8	34.6	171	153	253
SRM 694	.	0.015	0.01414	.	.	0.31
GPO-01	0.05	last of stock
USZ 14-94
GPO 15	0.015	.	(0.00568)	52
GPO-14	0.015	.	(0.00566)	52	last of stock
GBW 07211	59
USZ HF
GBW 07212
GPO-13	0.01	last of stock

CRM PLAGIOGNEISS WITH EXTENSIVE ANALYSIS

analysis listed in mass %

100 g units

Number	Al ₂ O ₃	Ba	CO ₂	CaO	Cr	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	Zr	LOI	
VS 8871-2007	15.90	0.091	(0.13)	2.85	0.0182	0.0573	4.14	6.06	(1.1)	3.56	2.59	0.069	2.25	0.080	64.92	0.70	0.0234	0.76	last

analysis listed in mg/kg

Number	Ag	As	B	Be	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge	Hf	Ho	La	Li	Lu	Mo
VS 8871-2007	(0.09)	(2.0)	(100)	0.97	(0.10)	104	19.7	182	0.32	31	3.3	2.1	1.8	18.5	4.7	(1.1)	6.2	0.69	53	21	0.31	1.7

Number	Nb	Nd	Ni	Pb	Pr	Rb	S	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn
VS 8871-2007	10.0	43.8	60	14.2	11.5	55	(74)	(0.05)	14.3	6.9	(0.6)	364	0.40	0.6	11.3	0.31	0.33	0.8	98	(0.3)	17.8	2.02	81

CRM PROPHILITE

analysis listed in mass %

50 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	SiO ₂	TiO ₂	LOI
JCRM R802	32.3	0.04	0.23	.	.	0.07	<0.01	.	0.09	0.05	.	60.7	0.19	6.0
NCS DC60127	23.58	0.17	.	1.94	4.15	0.38	0.087	0.0037	0.34	0.20	0.61	66.84	0.70	5.48
NCS DC60128	22.20	0.066	.	0.22	5.57	0.028	0.041	0.0040	0.043	0.11	0.17	70.34	0.18	6.34

CRM QUARTZ analysis listed in mass % T = Total US: 25 g

Number	SiO ₂	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	K ₂ O	MgO	Mn	Na ₂ O	P ₂ O ₅	TiO ₂
US QLO 1A	65.6	16.2	3.17	2.97	1.02	4.35	3.60	1.00	.	4.20	0.25	0.62

CRM QUARTZITE

Number	analysis listed in mass %										analysis listed in mg/kg						
	SiO ₂	Al ₂ O ₃	CaO	Cr ₂ O ₃	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	As	Ba	Be	Bi	Cd
NCS DC71325	99.18	0.29	0.036	0.0053	0.16	0.050	0.022	0.0049	0.010	0.0036	0.014	0.14	0.48	17.4	0.09	0.034	0.015
NCS DC71324	95.97	1.33	0.59	0.0083	0.61	0.28	0.15	0.0080	0.13	0.018	0.059	0.69	1.3	56.8	0.21	0.050	0.025
NCS DC71323	92.93	2.43	1.20	0.0077	0.62	0.60	0.29	0.015	0.28	0.025	0.10	1.35	0.89	84.2	0.41	0.036	0.037

analysis listed in mg/kg

80 g units

Number	Ce	Cl	Co	Cu	Hg	La	Li	Mo	Ni	Pb	Rb	Sb	Sr	Th	U	V	W	Zn	Zr
NCS DC71325	1.1	(15)	1.6	8.9	(0.002)	0.54	2.5	3.8	15.8	31.7	3.0	0.20	3.0	0.14	0.10	1.8	0.19	3.7	(1.7)
NCS DC71324	19.3	(38)	1.4	13.4	(0.002)	9.3	2.7	2.1	23.9	69.4	10.3	0.22	20.0	1.8	0.48	7.4	0.27	7.8	53
NCS DC71323	16.7	(34)	1.8	14.6	(0.003)	8.8	3.4	1.6	21.5	39.7	16.7	0.20	33.9	2.9	0.58	11.9	0.47	11.2	93

CRM RARE EARTH ORE WITH EXTENSIVE ANALYSIS

analysis listed in mass & except * which is mg/kg (ppm)

powder 10 g units

Number	Ag*	Al	Al ₂ O ₃	As*	B	Ba	BaO	Be*	Bi*	Ca	CaO	Cd*	Ce	CeO ₂	Co*	Cr	Cr ₂ O ₃
OREAS 460b	0.331	7.22	13.64	286	.	0.0794	0.0887	2.58	13.0	0.559	0.782	<10	0.168	0.206	6.21	0.0280	0.0409
OREAS 461	<2	5.99	11.31	33.6	(0.0151)	0.0929	0.1037	2.3	2.49	1.26	1.76	<1	0.3510	0.4311	11.5	0.0599	0.0875
OREAS 462	<2	5.79	10.95	30.8	(0.0150)	0.1025	0.1144	3.76	2.58	1.28	1.79	<2	0.4951	0.6082	12.5	0.0609	0.0890
OREAS 463	<3	5.63	10.64	31.3	(0.0147)	0.1106	0.1235	5.62	2.75	1.22	1.71	<1	0.659	0.810	15.2	0.0574	0.0838
OREAS 464	4.4	4.63	8.75	32.9	(0.0108)	0.1657	0.1850	15.6	3.8	0.896	1.25	0.52	1.53	1.88	18	0.0395	0.0577

Number	Cs*	Cu*	Dy	Dy ₂ O ₃	Er	Er ₂ O ₃	Eu	Eu ₂ O ₃	Fe	Fe ₂ O ₃	Ga	Gd	Gd ₂ O ₃	Ge*	H ₂ O-	Hf
OREAS 460b	6.52	43.8	0.00177	0.00203	0.000550	0.000629	0.00205	0.00236	16.05	22.95	0.00261	0.00453	0.0052	.	.	0.00100
OREAS 461	0.79	60	0.00348	0.00400	0.000880	0.00101	0.00467	0.0054	31.77	46.09	0.0050	0.0100	0.0116	(3.60)	0.697	0.00141
OREAS 462	0.44	61	0.0051	0.0059	0.00122	0.00140	0.0079	0.0091	33.84	48.69	0.0052	0.0165	0.0190	(6.00)	0.667	0.00140
OREAS 463	0.42	74	0.0070	0.0081	0.00160	0.00183	0.0115	0.0133	34.47	49.29	0.0063	0.0241	0.0278	(9.08)	0.64	0.00138
OREAS 464	0.27	92	0.0178	0.0204	0.00382	0.00436	0.0324	0.0375	37.24	53.24	0.0106	0.0676	0.0779	(43.3)	0.503	0.00125

Number	HfO ₂	Ho*	Ho ₂ O ₃ *	In*	K	K ₂ O	La	La ₂ O ₃	Li*	Lu*	Lu ₂ O ₃ *	Mg	MgO	Mn	MnO	Mo*	Na
OREAS 460b	0.00118	2.54	2.91	0.33	1.46	1.73	0.122	0.143	30.8	0.46	0.53	0.648	1.08	0.031	0.0404	22.9	0.152
OREAS 461	0.00166	4.56	5.22	0.6	0.237	0.285	0.2690	0.3115	12	0.52	0.59	1.05	1.74	0.0653	0.0843	45.7	0.178
OREAS 462	0.00165	6.50	7.44	0.75	0.120	0.145	0.3794	0.4517	11.3	0.63	0.72	1.08	1.80	0.0933	0.1204	51	0.178
OREAS 463	0.00163	8.71	9.98	1.01	0.119	0.143	0.4773	0.5824	10.5	0.79	0.9	1.02	1.70	0.121	0.156	56	0.173
OREAS 464	0.00148	21.3	24.4	2.14	0.086	0.104	1.17	1.37	8.26	1.57	1.92	0.825	1.40	0.270	0.365	77	0.149

Number	Nb	Nb ₂ O ₅	Nd	Nd ₂ O ₃	Ni	NiO	P	P ₂ O ₅	Pb	PbO	Pr	Pr ₆ O ₁₁	Rb*	Re*	S	Sb*	Sc*
OREAS 460b	0.0645	.	0.075	0.088	0.00366	.	0.173	0.396	0.0056	.	0.0217	0.0262	82	.	0.028	.	29.4
OREAS 461	0.1296	0.1854	0.1629	0.1900	0.0064	0.0081	0.359	0.822	0.0106	0.0114	0.0489	0.0590	13.5	<0.1	0.0518	2.76	38.8
OREAS 462	0.1447	0.2070	0.2560	0.2985	0.0066	0.0085	0.492	1.13	0.0114	0.0123	0.0735	0.0888	6.58	<0.01	0.0587	2.57	51
OREAS 463	0.1495	0.2139	0.3682	0.4295	0.0071	0.0090	0.629	1.44	0.0122	0.0132	0.1004	0.1201	6.08	<0.02	0.0671	2.31	66
OREAS 464	0.1903	0.2723	0.994	1.16	0.0082	0.0104	1.41	3.23	0.0174	0.0187	0.2597	0.3138	4.39	<0.03	0.1028	1.8	141

Number	Se*	Si	SiO ₂	Sm	Sm ₂ O ₃	Sn	SnO ₂	Sr	SrO	Ta*	Ta ₂ O ₅ *	Tb*	Tb ₄ O ₇ *	Te*	Th	ThO ₂	Ti	TiO ₂
OREAS 460b	.	24.01	51.36	0.0094	0.0109	0.00225	.	0.0287	.	11.7	.	4.34	5.11	.	0.0104	.	1.11	1.85
OREAS 461	.	14.71	31.46	0.0220	0.0255	0.00256	0.00325	0.0579	0.0685	25.1	30.7	9.08	10.7	0.34	0.0210	0.0239	1.84	3.07
OREAS 462	.	13.18	28.19	0.0369	0.0428	0.00292	0.00371	0.0765	0.0904	25.7	31.3	14.4	16.9	0.33	0.0249	0.0283	1.91	3.18
OREAS 463	<20	12.85	27.50	0.0538	0.0597	0.00314	0.00399	0.0961	0.1136	25.2	30.8	20.3	23.9	0.35	0.0292	0.0332	1.92	3.19
OREAS 464	<50	9.52	20.36	0.1498	0.1738	0.00459	0.0058	0.2060	0.2437	24.3	29.7	54	63	0.36	0.0527	0.0600	1.95	3.26

Number	Tl*	Tm*	Tm ₂ O ₃ *	U*	U ₃ O ₈ *	V	V ₂ O ₅	W*	WO ₃ *	Y	Y ₂ O ₃	Yb*	Yb ₂ O ₃ *	Zn	ZnO	Zr	ZrO ₂	LOI
OREAS 460b	.	0.61	0.70	3.80	.	0.0233	0.0416	48.8	.	0.0055	0.0070	3.47	3.95	0.0076	.	0.0415	.	6.08
OREAS 461	0.1	0.89	1.02	4.79	5.65	0.0385	0.0687	3.88	4.89	0.0091	0.0116	4.39	5.00	0.0162	0.0201	0.0603	0.0815	0.996
OREAS 462	0.083	1.2	1.37	6.15	7.25	0.0380	0.0679	3.60	4.53	0.0133	0.0168	5.51	6.28	0.0269	0.0335	0.0593	0.0801	0.771
OREAS 463	0.094	1.33	1.8	7.55	9.26	0.0327	0.0683	2.45	4.71	0.0176	0.0229	5.86	8.00	0.0391	0.0526	0.0256	0.0778	0.781
OREAS 464	0.15	3.56	4.06	17.6	20.7	0.0231	0.0412	<6	<7	0.0449	0.0570	15.7	17.9	0.1232	0.1533	0.462	0.0624	0.697

CRM RARE EARTH ORE

analysis listed in mass %

Number	RE _x O _y	Al ₂ O ₃	CaO	F-	FeO	Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI
NCS DC86318	4.30	(14.26)	0.29	0.017	0.20	2.24	3.60	5.52	(0.11)	0.052	0.66	(0.020)	66.90	0.17	5.43
NCS DC86317	1.83	16.59	(0.11)	0.15	0.18	0.71	4.63	4.03	0.13	0.10	0.13	(0.0073)	70.92	(0.018)	5.42
NCS DC86312	0.784	19.00	0.029	0.014	(0.072)	3.46	6.64	2.11	0.231	0.069	0.064	(0.029)	66.72	0.530	6.80
NCS DC86311	0.406	14.65	(0.031)	0.034	(0.039)	1.13	3.61	4.92	0.080	0.016	0.155	(0.0025)	74.34	(0.023)	3.70
NCS DC86310	0.085	14.70	(0.026)	0.034	0.054	1.15	3.61	4.98	0.077	0.017	0.158	(0.0027)	74.55	0.022	3.77
NCS DC86309	0.092	19.04	(0.033)	0.016	(0.071)	3.49	6.64	2.13	0.229	0.070	0.062	0.029	67.28	0.537	6.73

Number	CeO ₂	Cs ₂ O	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Li ₂ O	Lu ₂ O ₃
NCS DC86318	0.053	0.00126	0.37	0.20	0.00219	0.25	(0.064)	0.23	0.0121	0.030
NCS DC86317	0.021	0.0148	0.12	0.068	0.000956	0.091	(0.023)	0.25	0.0396	0.00645
NCS DC86312	0.023	0.00055	0.021	0.011	0.00750	0.026	0.00409	0.277	0.00398	0.00136
NCS DC86311	0.00348	0.00178	0.036	0.022	0.00018	(0.027)	0.00750	0.011	0.015	0.00304
NCS DC86310	0.00217	0.00177	0.00563	0.00364	0.000036	0.00324	0.00120	0.00200	0.015	0.00055
NCS DC86309	0.00915	0.00056	0.00273	(0.0016)	0.00081	0.00317	0.00057	0.031	0.00403	0.00020

Number	Nd ₂ O ₃	Pr ₆ O ₁₁	Rb ₂ O	Sc ₂ O ₃	Sm ₂ O ₃	Tb ₄ O ₇	Th	Tm ₂ O ₃	Y ₂ O ₃	Yb ₂ O ₃	Units
NCS DC86318	0.40	0.089	0.0404	0.00072	0.20	0.055	0.00670	0.031	2.16	0.21	50 g
NCS DC86317	0.24	0.066	0.12	0.00101	0.066	0.019	0.00210	0.00029	0.80	0.051	50 g
NCS DC86312	0.186	0.054	0.011	0.00118	0.033	0.00407	0.00236	0.00151	0.124	0.0100	70 g
NCS DC86311	0.022	(0.0045)	0.067	0.00089	0.015	0.00577	0.00390	0.00316	0.303	0.022	50 g
NCS DC86310	0.00276	0.00063	0.069	0.00095	0.00157	0.00082	0.00405	0.00057	0.057	0.00366	50 g
NCS DC86309	0.017	0.00492	0.012	0.00113	0.00338	0.00054	0.00245	0.00024	(0.018)	0.00141	50 g

CRM RARE EARTH ORE

analysis listed in mass % and mg/kg * RE_xO_y = total rare earth oxides

Number	RE _x O _y %	CeO ₂ %	Dy*	Er*	Eu ₂ O ₃ %	Gd ₂ O ₃ %	Ho*	La ₂ O ₃ %	Lu*	Nd ₂ O ₃ %	Pr ₂ O ₃ %	Sc*	Sm ₂ O ₃ %	Tb*	ThO ₂ %	Tm*	Y ₂ O ₃ %	Yb*
UNS TRV	13.82	6.64	(207.1)	(41.2)	0.042	(0.089)	(41.5)	(4.23)	(6.7)	(1.94)	(0.71)	(22.5)	0.22	(82.3)	(0.29)	(14.8)	(0.048)	(21.6)

continued analysis listed in mass % T = total

Number	Al ₂ O ₃	BaO	CO ₂	CaO	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	T.S	SO ₃	SiO ₂	SrO	TiO ₂	LOI
UNS TRV	(0.52)	17.02	(16.5)	13.54	1.57	3.61	8.34	(1.24)	0.15	2.27	1.15	(0.07)	(0.12)	6.05	(13.58)	(2.47)	5.92	0.079	17.16

continued analysis listed in mg/kg

Number	Ag	As	Be	Bi	Cd	Co	Cr	Cu	Li	Mo	Ni	Pb	V	Zn	Units
UNS TRV	(6.7)	(335)	(4.2)	(72.9)	(7.5)	(26.5)	(40.6)	(41.5)	(28.8)	71.4	(44.0)	(332.9)	(74.2)	767.9	100 g

CRM RARE EARTH ORE

analysis listed in mass %

100 g units

Number	Al	Ba	C	Ca	Fe	H ₂ O	K	Mg	Mn	Na	P	S	Si	Zr	LOI
CAN REE-1	3.59	0.01001	(0.0786)	2.30	(4.16)	(0.6)	3.09	(0.895)	(0.155)	1.445	0.0261	(0.03)	31.36	1.91	(2)
CAN REE-2	0.761	5.02	(9.06)	13.68	12.14	(0.4)	(0.0172)	6.26	1.316	(0.120)	0.461	1.745	1.377	(0.00322)	31.38
CAN REE-3	4.372	0.00691	(0.08)	1.644	8.28	(0.1)	3.76	0.0594	(0.313)	(2.328)	0.0201	(0.04)	29.66	1.8660	0.346

continued analysis listed in mg/kg

Number	Ag	As	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd
CAN REE-1	.	124	(590)	(0.652)	.	3960	1.58	277	1.07	79.7	847	701	23.5	(64)	433
CAN REE-2	(1)	.	(3.31)	(2.00)	(1.11)	9610	7.71	(32.7)	(0.09)	(5.55)	69.2	14.0	96.6	(60)	(219)
CAN REE-3	(2)	.	82.3	(1.171)	(4.2)	4540	(0.92)	82	1.118	16.3	330.3	187.2	20.85	(80)	346

Number	Ge	Hf	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb
CAN REE-1	(3)	479	208	(0.2)	1661	(205)	(92.4)	(36.6)	4050	1456	24.7	1137	435	1047	(3.16)
CAN REE-2	(7)	(0.95)	7.87	(1.403)	5130	9.61	(0.92)	(154)	(1060)	3660	(13.1)	(40.8)	1075	1.22	(0.89)
CAN REE-3	.	448	65.0	(0.4)	2121	(60)	21.53	59.7	1073	2083	10.83	534	550	887	(0.2)

Number	Sc	Sm	Sn	Sr	Ta	Tb	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn
CAN REE-1	(8)	381	498	129	(231)	106.2	719	(3840)	(1.85)	106	137	(9.9)	(10)	5480	678	(1870)
CAN REE-2	57.5	410	24.1	2300	1.17	20.3	737	1969	(0.240)	1.383	3.73	(79)	9.9	176	(7.2)	(420)
CAN REE-3	(3)	398	121.1	133.7	60.7	55.2	135.5	3202	(2.341)	25.8	(29.9)	(4)	(1)	1.725	159.4	1499

CRM SANDSTONE

analysis listed in mass % and * mg/kg

Number	S%	Cu%	Ag*	Re*	Units
KZ 8077-94	0.33	0.11	10.2	0.14	100 g last
KZ 8076-94	.	0.036	0.64	0.023	100 g last

CRM SANDSTONE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	C(org)	C(tot)	CO ₂	CaO	F	FeO	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI
GBW 07106	90.36	3.52	(0.05)	(0.10)	(0.19)	0.30	0.0183	0.61	3.22	1.01	0.65	0.082	.	0.061	.	.	1.10
UL PRI-1	68.60	10.84	.	.	(2.62)	2.49	(0.0383)	(2.07)	3.32	.	3.79	3.24	0.04	1.71	0.18	0.71	4.99
IAG OU-8	54.120	6.548	.	.	.	16.711	.	.	1.304	.	2.967	1.879	0.138	0.677	.	0.244	15.301

continued analysis listed in mg/kg except * which is ng/g continued analysis listed in mg/kg except * which is ng/g

Number	Ag	As	Au*	B	Ba	Be	Bi	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge	Hf
GBW 07106	0.062	9.1	(1.8)	34	143	0.97	0.18	0.060	48	(44)	6.4	20	1.8	19	4.1	2.0	1.02	5.3	4.5	1.16	6.6
UL PRI-1	.	(4.7)	.	(52)	531	1.4	(0.1)	.	82	.	7.4	78	(2.2)	(3.5)	4.3	(2.7)	1.29	(13)	5.3	(<5)	10.7
IAG OU-8	528	1.42	(0.043)	.	41.8	.	.	(21.5)	3.23	8.36	2.25	1.59	0.67	6.28	2.32	(1.10)	4.72

Number	Hg	Ho	I	In	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	S	Sb
GBW 07106	0.008	0.75	(0.2)	(0.026)	21	11.1	0.30	155	0.76	5.9	21	16.6	970	7.6	5.4	29	860	0.60
UL PRI-1	.	(1)	.	(<1)	38	.	0.41	.	(0.7)	13	36	21	.	(13)	(9.5)	90	(357)	(0.3)
IAG OU-8	.	0.51	.	.	13.8	10.3	0.26	.	.	(4.46)	12.4	.	.	9.64	3.12	64.6	.	0.22

Number	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Class	Units
GBW 07106	4.2	0.08	4.7	1.1	58	0.38	0.79	0.038	7.0	1580	0.36	0.32	2.1	33	1.2	21.5	1.9	20	214	CRM	70 g
UL PRI-1	9.7	.	6.6	(2)	88	1	0.85	.	11.3	.	(0.2)	(0.39)	2.5	65	(2.2)	25	2.8	47	386	CRM	50 g
IAG OU-8	(3.63)	.	2.42	.	264.4	0.32	0.36	.	9.5	.	1.01	0.24	0.74	29.8	.	16.0	1.66	.	182.7	RM	~35 g

CRM SCHIST

analysis listed in mass %

UL: 50 g units

UNS, VS: 100 g units

US: 25 g units

Number	SiO ₂	Al ₂ O ₃	BaO	CO ₂	CaO	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SrO	TiO ₂	LOI
US SDC 1	65.8	15.8	.	.	1.40	3.93	2.62	6.32	.	3.28	1.69	.	2.05	0.16	.	1.01	.
VS 3191-85	63.40	16.71	.	.	0.09	4.65	.	7.6	.	3.56	2.52	0.13	0.08	0.030	.	1.01	4.54
UNS MI	62.19	14.54	0.10	2.13	1.96	(6)	.	6.41	(12)	2.15	3.28	0.25	3.33	(10)	0.016	0.71	(16)
UL SBO1	55.16	18.24	.	.	1.76	(5.61)	.	7.15	.	3.55	(1.97)	0.18	0.66	0.17	.	0.94	9.67

continued analysis listed in mg/kg

Number	Ag	As	B	Ba	Be	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F
US SDC 1	.	0.22	(13)	630	3	.	93	(32)	18	64	4	30	(6.7)	(4.1)	(1.7)	600
VS 3191-85	.	.	100	950	3.5	.	90	.	27	70	(7)	46
UNS MI	(0.006)	(0.007)	(0.005)	.	(0.006)	0.0100	.	.	0.0120	0.1073	.	0.0438
UL SBO1	.	(32)	.	549	(3.2)	.	101	.	22	116	(6.8)	33	(5.1)	(3.4)	1.64	.

Number	Ga	Gd	Ge	Hf	Hg	Ho	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	Pb	Pr	Rb	S
US SDC 1	21	7	.	8.3	(0.2)	(1.5)	42	34	.	880	.	(21)	40	(38)	25	.	127	.
VS 3191-85	(15)	.	(2)	.	.	.	(60)	(0.6)	.	(1.6)	16	.	45	15	.	150	.	
UNS MI	(0.010)	(0.003)	.	0.0372	0.0945	.	0.0539	3300	.	
UL SBO1	(23)	6.2	.	5	.	(1.3)	48	.	0.49	.	.	17	42	60	27	11.1	163	.

Number	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
US SDC 1	0.54	17	8.2	3.0	180	(1.2)	(1.2)	12	(0.7)	(0.65)	3.1	102	(0.80)	.	(4)	103	290
VS 3191-85	.	22	.	(4)	39	.	.	(12)	.	.	(2)	100	.	48	5	100	230
UNS MI	0.1052	(0.003)	0.0198	(0.003)	3000	0.1518
UL SBO1	.	17	7.8	.	150	1.4	1	15.2	.	(0.43)	3.1	153	.	32	3.2	82	183

RM		SEDIMENT													analysis listed in mass %	
Number	Al ₂ O ₃	CO ₂	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Type			
IAG OU-10	10.97	.	2.34	4.92	1.28	1.77	0.120	2.43	0.090	73.12	0.534	(2.20)	Longmyndian Greywacke			
IAG UoK	6.2	14.94	16.31	2.1	1.3	2.9	0.0644	1.058	0.13	53.24	0.423	16.03	Loess			
analysis listed in mg/kg																
Number	As	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	
IAG OU-10	.	311	(1.1)	.	(2.8)	(38.0)	12.0	34.0	1.68	22.3	3.65	2.2	1.00	12.0	3.7	
IAG UoK	6.7	200.97	1.102	0.1	.	53	5.95	105.7	2.72	11.31	4.02	2.382	0.888	7.087	4.465	
Number	Hf	Ho	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Sm	Sr
IAG OU-10	3.3	0.75	18.8	(26.0)	0.34	(0.98)	7.6	18.7	(17.7)	26.9	4.7	35.9	.	11.3	(3.9)	174
IAG UoK	(9.10)	0.80	25.54	21.90	0.37	(1.40)	8.61	24.32	42.71	11.34	6.24	51.2	0.580	(5.93)	5.01	278.5
Number	Ta	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units			
IAG OU-10	0.56	0.61	5.0	(0.23)	0.34	1.09	77	.	20.5	2.2	54	123	~35 g			
IAG UoK	(0.73)	0.687	8.111	0.338	0.339	2.697	(37.56)	(1.45)	23.18	2.420	34.4	.	~60 g			

LAKE SEDIMENT - SEQUENTIAL EXTRACTION METHOD

BCR 701, CRM 20g	Cd	Cr	Cu	Ni	Pb	Zn
Step 1	7.34	2.26	49.3	15.4	3.18	205
Step 2	3.77	45.7	124	26.6	126	114
Step 3	0.27	143	55.2	15.3	9.3	45.7
Concentration	(0.13)	(62.5)	(38.5)	(41.4)	(11.0)	(95)

LAKE SEDIMENT WITH ACID EXTRACTION analysis in mass % except * for mg/kg CRM, powder 20 g

Number	Analysis	Al	As	Ba	Ca	Cd*	Co	Cr	Cu	Fe	K	La
NIES 31	whole material	9.17	(0.00139)	(0.0338)	1.25	(0.342)	(0.00181)	0.00433	0.00531	5.38	(0.991)	(0.00204)
NIES 31	acid extract	(0.285)	.	(0.00337)	0.00506	.	.	.
Number	Analysis	Mg	Mn	Na	Ni	P	Pb	Sc	Sr	Ti	V	Zn
NIES 31	whole material	(0.836)	0.0978	0.882	0.00253	0.0925	0.00251	(0.00191)	(0.0125)	0.442	0.0154	0.0121
NIES 31	acid extract	.	0.0881	.	0.00222	.	0.00220	.	.	.	0.0133	0.0110

CRM LAKE SEDIMENT analysis listed in mass %

Number	Al ₂ O ₃	C	CaO	Fe	FeO	Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI	Other			
JLk-1	16.73	.	0.686	.	2.191	4.251	3.701	6.372	2.805	1.736	0.266	1.051	0.208	0.1052	57.16	0.668	.	T.Fe ₂ O ₃ : 6.929			
VS 7176-95	14.22	.	7.09	.	3.50	5.39T	(0.22)	.	1.51	3.12	0.12	3.11	0.139	.	62.46	0.76	1.78	CO ₂ : (0.74)			
VS 7126-94	13.57	(2.24)	1.85	.	1.60	7.02T	(2.15)	(4.5)	2.21	2.00	0.40	1.96	0.345	0.165	61.07	0.69	8.34	SO ₃ : (0.35)			
BCR 280R			
continued analysis listed in mg/kg except % which is mass %																					
Number	Ag	Al%	As	Au	B	Ba	Be	Bi	Br	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	
JLk-1	.	.	26.8	.	.	574	87.9	18.0	69.0	10.9	62.9	6.57	3.59	1.27	589	.	
VS 7176-95	(0.04)	.	.	.	(12)	530	(1.3)	.	.	.	(41)	17	158	.	18	.	.	(1.4)	(380)	.	
VS 7126-94	(0.17)	.	18	(0.004)	34	710	2.7	.	.	.	80	18	66	6	52	(4.6)	(2.6)	1.4	600	16	
BCR 280R	33.4	0.85	.	.	16.8	126	.	53	1.46	69	224	.	.	
Number	Gd	Ge	Hf	Hg	Ho	K%	La	Li	Lu	Mg%	Mn	Mo	Na	Nb	Nd	Ni	P	Pb	Pr	Rb	
JLk-1	6.02	.	3.78	.	1.06	.	40.6	.	0.571	15.8	35.7	35.0	.	43.7	8.53	147	
VS 7176-95	19	8.5	10	.	31	.	14	.	39	
VS 7126-94	(5.8)	1.4	3.9	(0.03)	(1)	.	45	37	0.40	.	.	2.9	12	39	54	.	21	(8)	93		
BCR 280R	.	.	1.46	69	
Number	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units (g)	
JLk-1	.	15.9	.	7.87	.	67.5	1.57	1.23	19.5	.	1.17	.	3.83	117	.	40.0	3.99	152	137	20 or 100	
VS 7176-95	.	19	.	3.7	580	105	.	24	2.7	64	204	100	
VS 7126-94	(0.95)	13	(0.97)	7	3.2	266	0.84	0.9	12.7	.	.	(0.42)	12.0	110	(4.3)	30	2.9	96	156	100	
BCR 280R	224	.	.	30

CRM ESTUARY AND MARINE SEDIMENT

analysis listed in mg/kg except % which is mass %

Number	Hg	CH ₃ Hg	Ag	Al%	As	Ba	Be	Ca%	Cd	Ce	Co	Cr	Cu	Fe%	Ga
ERM-CC580	132 tot	0.075
NMIJ 7302a	0.52	.	0.49	.	22.1	.	.	.	1.32	.	12.4	145	57.8	.	.
BCR 277R	0.128	.	.	.	18.3	.	.	.	0.61	.	22.5	188	63	.	.
NMIJ 7303a	0.067	.	0.098	.	8.6	.	.	.	0.342	.	11.1	39.1	23.1	.	.
SRM 1646a	(0.04)	.	(<0.3)	2.297	6.23	(210)	(<1)	0.519	0.148	(34)	(5)	40.9	10.01	2.008	(5)

Number	K%	La	Li	Mg%	Mn	Mo	Na%	Nd	Ni	P%	Pb	Rb	S%	Sb	Sc	Se
ERM-CC580
NMIJ 7302a	1.98	.	.	25.8	.	82.7	.	.	1.22	.	0.61
BCR 277R	130
NMIJ 7303a	0.96	.	.	21.8	.	31.3	.	.	0.69	.	0.24
SRM 1646a	0.864	(17)	(18)	0.388	2345	.	0.741	(15)	22.5	0.027	11.7	(38)	0.352	(0.3)	(5)	0.193

Number	Si%	Sn	Sr	Th	Ti%	Tl	U	V	Zn	Units
ERM-CC580	40 g
NMIJ 7302a	.	18.5	401	60 g
BCR 277R	178	40 g
NMIJ 7303a	.	4.21	107	60 g
SRM 1646a	40.0	(1)	(68)	(5.8)	0.456	(<0.5)	(2)	44.84	48.9	70 g

CRM MARINE SEDIMENT

analysis listed in mass % T = Total

Number	Al ₂ O ₃	C(org)	T.C	CO ₃ ²⁻	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI
JMs-1	15.82	.	1.69	.	2.13	2.12	4.54	6.90	6.79	2.24	2.87	0.102	4.07	0.18	1.32T	53.74	0.70	15.44
JMs-2	14.18	.	0.39	.	4.68	<0.04	10.96	10.96	7.13	2.70	3.24	2.26	5.79	1.26	0.29T	41.78	1.40	19.15
SRM 2702	8.41	(3.27)	(3.36)	.	(0.343)	.	.	7.91	.	2.054	(0.990)	0.1757	0.681	0.1552	(1.5T)	.	.	0.884
SRM 2703	8.33	.	.	.	(0.31)	.	.	7.38	.	2.08	(1.0)	0.1734	0.693	(0.16)	.	.	.	0.880
NRC MESS-4	7.91	.	(1.79)	.	1.31	.	.	3.79	.	2.38	1.58	0.0298	1.26	0.104	0.158	27.8	.	0.384
NRC PACS-3	6.58	.	.	.	1.89	.	.	4.106	.	1.253	1.402	0.0432	3.52	0.0937	1.17	26.1	0.442	.
NRC HISS-1	0.73	.	.	.	1.14	.	.	0.246	.	0.332	0.075	0.00661	0.373	.	.	(44)	0.076	.
BCR 320R	2.5700	.	.	.	0.0910

continued analysis listed in mg/kg except % which is mass % SRM 2703 is intended for small sample techniques <10mg

Number	Ag	As	B	Ba%	Be	Bi	Br	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Dy	Er	Eu
JMs-1	.	18	81	0.0307	1.3	.	.	.	2.69	18.1	133	5.9	88	.	.	.	
JMs-2	.	35	106	0.1856	1.8	.	.	.	4.05	226	78	3.0	447	.	.	.	
SRM 2702	(0.622)	45.3	.	0.03974	(3.0)	.	.	0.817	123.4	.	27.76	352	(7.1)	(117.7)	.	.	.
SRM 2703	(0.59)	45.5	.	0.0416	.	.	.	0.811	125.5	.	27.70	.	(7.7)	(120)	.	.	.
NRC MESS-4	0.161	21.7	.	(0.0920)	2.09	(2.7)	(60)	0.28	(72)	1.31%	13.0	94.3	(10)	32.9	.	.	(1.3)
NRC PACS-3	(1.10)	30.3	.	.	1.06	.	.	2.23	.	.	(12.1)	90.6	.	326	.	.	.
NRC HISS-1	0.016	0.801	.	.	0.129	.	.	0.024	.	(0.35)	(0.65)	30.0	.	2.29	.	.	.
BCR 320R	.	21.7	2.64	.	.	9.7	59	.	46.3	.	.	.

Number	Ga	Gd	Hf	Hg	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc
JMs-1	0.101	.	62	53	49	.	88	1.4	.
JMs-2	0.178	.	43	311	88	.	65	4.5	.
SRM 2702	(24.3)	.	(12.6)	0.4474	.	.	73.5	(78.2)	.	(10.8)	(63)	(56)	75.4	132.8	.	127.7	5.60	25.9
SRM 2703	.	.	(11.8)	0.474	.	.	75.9	.	.	(11)	(63)	(72)	(75)	130	.	130	5.62	25.95
NRC MESS-4	(18) Ge:	(0.16)	(3.0)	(0.08)	.	(0.10)	(35)	65.3	(0.11)	(2.53)	(12)	(42)	42.8	21.5	.	(180)	1.07	(13.4)
NRC PACS-3	.	.	.	2.98	.	.	.	31.9	.	(5.9)	.	.	39.5	188.0	.	.	14.7	.
NRC HISS-1	.	.	.	(0.01)	.	.	.	2.83	.	(0.13)	.	.	2.16	3.13	.	.	(0.13)	.
BCR 320R	.	.	.	0.85	27.1	85	.	.	.	5.2

* BUTILYN CONTENT DETAILED ON CERTIFICATES

Number	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr	Units
JMs-1	.	.	.	154	.	.	0.132	127	.	24.3	.	264	132	100 g
JMs-2	.	.	.	454	.	.	1.38	183	.	254	.	166	220	100 g
SRM 2702	(4.95)	(10.8)	31.6	119.7	.	.	.	20.51	0.8267	.	(10.4)	357.6	(6.2)	.	.	485.3	.	50 g
SRM 2703	(4.9)	(10.8)	(32)	(118)	.	.	.	20.22	(0.83)	.	(11)	360	(6.4)	.	.	480	.	5 g
NRC MESS-4 *	(1.5)	(5.5)	2.35	132	(1)	.	(0.1)	(12)	0.85	.	3.4	216	(1.3)	(20)	(2)	147	(96)	50 g last Re: (0.004)
NRC PACS-3 *	.	.	22.0	267	(2.6)	129	376	.	50 g
NRC HISS-1	0.050	.	(0.11)	96.9	.	.	.	(0.06)	.	(0.26)	6.80	4.94	.	100 g
BCR 320R	5.3	0.65	.	1.56	46.5	.	.	.	319	.	40 g

RIVER SEDIMENT

analysis listed in mg/kg except % which is mass % SRM 1944: CRM, 50 g SRM 8704: RM, 50 g

Number	Ag	Al%	As	Au	Ba	Be	Br	C%	Ca%	Cd	Ce	Cl%	Co	Cr	Cs	Cu	Eu	Hf	Hg	Fe
SRM 1944	6.4	5.33	18.9	(0.1)	.	1.6	86	.	1.0	8.8	(65)	1.4	14	266	3	380	(1.3)	.	3.4	3.53%
SRM 8704	.	6.10	(17)	.	413	.	.	3.351	2.641	2.94	66.5	.	13.57	121.9	5.83	.	1.31	8.4	.	3.97%

continued

Number	K%	Mg%	Mn	Na%	Ni	Pb	Rb	Sb	Sc	Se	Si%	Sn	Th	Ti%	Tl	U	V	Zn
SRM 1944	1.6	(1.0)	505	1.9	76.1	330	75	(5)	10.2	1.4	31	42	(13)	0.4300	0.59	(3.1)	100	656
SRM 8704	2.001	1.200	544	0.553	12.9	150	.	3.07	11.26	.	.	.	9.07	0.457	.	3.09	94.6	408

CRM STREAM SEDIMENT

analysis listed in mass % BCR: 40 g Jsd 1-3: 20 g CAN, Jsd-4, SARM: 100 g

Number	SiO ₂	Al ₂ O ₃	Org.C	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	H ₂ O+	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	LOI	
Jsd-3	76.00	9.908	.	.	0.560	1.161	3.057	4.368	2.838	0.964	1.971	1.17	0.149	0.411	0.0817	0.403	.	
Jsd-1	66.55	14.65	.	(0.0867)	3.034	1.363	3.526	5.059	(2.301)	0.836	2.183	1.813	0.0924	2.727	0.122	0.643	.	
Jsd-2	60.78	12.31	.	(0.501)	3.658	5.955	4.552	11.65	2.554	0.451	1.145	2.731	0.120	2.438	0.105	0.614	.	
CAN STSD-5	57.53	11.83	C:3.71	.	5.10	.	5.22	.	.	.	1.657	3.000	0.1087	2.055	0.2256	0.707	.	
Jsd-4	51.12	13.22	.	.	5.57	(2.08)	.	8.06	.	.	1.40	4.04	0.107	2.28	0.45	0.64	.	
SARM 46	35.90	6.71	.	.	1.32	(18.0)	28.16	.	.	.	0.35	3.16	1.14	0.28	0.11	0.60	.	
BCR 667	estuary sediment																	

continued analysis listed in mg/kg except * which is ng/g and % which is mass %

Number	Ag	As	Au*	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Fe
Jsd-3	(3.38)	252	(5.66)	.	462	.	.	.	42.0	.	12.7	35.3	30.6	426	2.22	1.07	0.686	3200	.	
Jsd-1	(0.036)	2.42	(0.64)	.	520	1.40	.	.	34.4	.	11.2	21.5	1.89	22.0	2.23	0.906	0.925	306	.	
Jsd-2	(1.04)	38.6	(54.6)	.	1199	.	.	.	23.4	.	48.4	108	1.07	1117	2.86	1.48	0.81	259	.	
CAN STSD-5	0.241	11.9	.	.	311	1.407	0.252	.	0.829	60.3	.	11.12	40	3.14	41.8	4.54	2.67	1.22	.	2.63%
Jsd-4	(888)	(21)	(1215)	.	(486)
SARM 46	(180)	.	.	.	(110)	.	56	559	566
BCR 667	(99.7)	(0.67)	56.7	.	(23.0)	(178)	(7.8)	(60)	4.01	2.35	1.00	.	(44.48)

continued

Number	Gd	Ge	Hf	Hg*	Ho	I	In	La	Li	Lu	Mn	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	S
Jsd-3	.	.	3.21	(254)	.	.	.	19.8	151	0.196	.	.	7.80	15.7	19.6	.	82.1	3.09	285	(399)
Jsd-1	2.71	.	3.55	(15.5)	.	.	.	18.1	22.8	0.186	.	.	11.1	17.6	7.04	.	12.9	4.05	67.4	(68)
Jsd-2	.	.	2.70	(106)	.	.	.	11.3	(19.2)	0.252	.	11.5	4.56	13.2	92.8	.	146	2.40	26.9	1.31%
CAN STSD-5	4.91	Ga:4.05	1.92	.	0.891	.	0.0817	14.17	24.3	(0.385)	591	3.33	10.4	28.4	29.83	890	16.4	7.44	59.5	(861)
Jsd-4	(16)	(32)	(114)	.	(240)	.	(57)	.
SARM 46	(10)	.	.	.	(125)	.	(1.3)	.	(20)	(0.17%)
BCR 667	4.41	.	.	.	0.80	.	.	27.8	.	0.325	(920)	.	.	25.0	(128)	.	(31.9)	6.1	.	.

continued

Number	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
Jsd-3	.	10.5	.	3.26	.	58.7	0.687	0.368	.	7.79	.	.	.	1.66	70.4	.	14.9	1.40	136	124
Jsd-1	.	10.9	.	3.48	.	340	0.893	0.431	.	4.44	.	.	.	1.00	76.0	.	14.8	1.18	96.5	132
Jsd-2	.	17.5	.	2.68	.	202	.	0.440	.	2.33	.	.	.	1.10	125	.	17.4	1.67	2056	111
CAN STSD-5	0.8	4.38	(0.91)	5.52	(1.79)	61.5	0.81	0.714	(0.072)	3.41	0.072	0.471	(0.380)	2.35	53.6	(0.61)	21.3	2.51	193.1	67
Jsd-4	.	(17)	.	.	.	(220)	(152)	.	(21)	.	(1485)	(90)
SARM 46	25	225	.	(20)	.	0.59%	101
BCR 667	(0.96)	13.7	(1.59)	4.66	.	.	(0.876)	0.682	.	10.0	.	.	0.326	2.26	.	.	.	2.20	(175)	.

CRM **STREAM SEDIMENT**

analysis listed in mass %

DC730xx: 70 g units

Number	SiO ₂	Al ₂ O ₃	C	C.Org	CO ₂	CaO	FeO	Fe ₂ O ₃ T	H ₂ O+	K ₂ O	MgO	Mn	N	Na ₂ O	P	S	Ti
NCS DC73017	77.42	11.44	(0.25)	0.20	(0.11)	0.85	(0.2)	1.86	(1.0)	3.89	0.18	0.122	0.0218	2.53	0.0234	0.0066	0.151
NCS DC73015	74.33	11.65	(0.46)	(0.08)	(1.34)	2.85	(0.57)	1.79	0.98	2.96	0.71	0.0290	(0.0079)	2.85	0.0335	0.0087	0.146
NCS DC73014	69.40	11.06	(0.48)	0.28	(0.76)	2.96	(1.83)	7.00	2.31	2.35	1.70	0.142	(0.0150)	1.40	0.0568	0.0432	0.32
NCS DC73018	66.02	11.25	1.01	0.34	2.57	3.82	(2.1)	6.31	3.23	2.41	2.34	0.0798	0.0291	0.83	0.0459	0.0110	0.53

continued analysis listed in mg/kg except % which is mass %

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga
NCS DC73017	0.044	4.4	5.5	1054	1.6	0.33	1.0	0.095	32	(30)	12.5	8.4	1.5	3.9	1.3	0.8	0.54	131	12.0
NCS DC73015	0.050	3.6	48	600	3.6	0.48	0.61	0.093	24	33	4.4	21	7.2	7.2	1.7	0.93	0.62	279	12.4
NCS DC73014	0.14	14.3	53	455	2.2	0.51	0.8	0.34	47	53	10.2	61	5.8	132	4.1	2.5	1.20	550	14.6
NCS DC73018	0.092	3.0	14	567	1.9	0.22	1.0	0.12	90	62	19.5	79	4.6	43	6.5	3.7	1.4	664	16.5

Number	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc
NCS DC73017	1.4	1.21	2.7	0.016	0.26	0.46	(0.014)	11.8	8.1	0.14	0.64	9.5	8.9	4.7	22	2.5	81	0.29	2.1
NCS DC73015	1.7	1.64	2.1	(0.007)	0.33	0.27	0.018	13.9	40	0.16	0.33	5.1	9.8	7.0	31	2.9	118	0.16	4.9
NCS DC73014	4.1	1.87	3.8	0.018	0.83	0.47	0.14	24	20.7	0.42	0.94	9.4	22	18.9	210	5.9	96	1.18	11.4
NCS DC73018	7.0	1.45	7.8	(0.014)	1.27	0.4	0.068	45	43	0.60	0.84	15.3	40	70	19	11.0	121	0.15	16.9

Number	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
NCS DC73017	0.072	1.6	(1.0)	167	0.81	0.22	(0.03)	5.4	0.44	0.13	1.1	28	0.58	7.0	0.83	19	100
NCS DC73015	0.053	1.9	2.3	253	0.72	0.29	(0.02)	4.1	0.83	0.16	1.9	31	0.66	9.7	1.0	27	71
NCS DC73014	0.47	4.5	2.5	171	0.65	0.68	(0.05)	8.3	0.91	0.40	2.2	77	2.0	23	2.6	209	132
NCS DC73018	0.24	7.5	1.9	117	1.04	1.14	(0.05)	15.4	0.77	0.59	3.5	120	1.7	34	3.8	74	275

last

CRM **STREAM SEDIMENT**

analysis listed in mass %

T = total Fe reported

Number	Al ₂ O ₃	Ba	CaO	Cr ₂ O ₃	Cu	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Pb	S	SiO ₂	TiO ₂	Zn	Zr
SARM 52	9.38	(0.0410)	0.37	0.19	0.0219	(4.0)	19.71	0.25	0.60	0.27	(0.1)	0.09	0.12	(0.02)	57.81	1.30	0.0264	0.0250

continued analysis listed in mg/kg except % for mass %

Number	Ce	Co	Ga	Nb	Ni	Rb	Sr	Th	V	Y	Units
SARM 52	(210)	81	(15)	11	182	20	25	(11)	346	20	100 g

CRM SEDIMENT

analysis listed in mass %															348x series: 100 g units					536x series: 50 g units				
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI									
VS 3486-86	70.54	11.29	.	0.52	.	(3.5)	5.24	2.21	0.48	0.11	1.67	0.28	0.43	0.62	.									
VS 5361-90	70.5	11.31	.	0.48	1.3	.	5.24	2.23	0.49	0.105	1.65	0.27	0.44	0.61	5.5									
VS 5365-90	60.4	16.49	0.13	0.40	3.3	.	8.80	2.44	1.62	0.132	1.57	0.19	0.03	0.98	6.8									
VS 5363-90	51.9	16.65	.	1.11	2.2	.	6.28	2.50	1.54	0.070	1.34	0.19	0.04	0.83	17.1									
VS 5362-90	45.4	11.58	.	7.04	1.5	.	4.59	2.96	5.72	0.074	0.85	0.14	0.04	0.63	20.3									
VS 3485-86	25.07	5.03	.	17.76	(0.24)	(0.2)	10.59	1.13	11.70	0.50	0.61	1.82	0.05	0.27	(25.14)									
VS 5364-90	25.0	4.98	21.6	17.83	0.4	.	10.56	1.13	11.7	0.48	0.63	1.82	0.05	0.26	25.1									
continued analysis listed in mg/kg except % which is mass %																								
Number	Ag	As%	Au	B%	Ba%	Be%	Bi%	Cd	Ce	Co	Cr	Cs	Cu%	F%	Ga	Ge	La%							
VS 3486-86	.	.	.	0.016	0.039	0.00036	.	9	.	9	0.0076	.	0.025	.	16	.	0.0032							
VS 5361-90	35	0.8	0.11	0.015	0.038	0.004	0.009	9	0.004	9.0	0.0075	17	0.025	0.21	16	15	0.0030							
VS 5365-90	.	.	.	0.007	0.055	0.0003	.	.	0.006	29	0.013	4	0.0049	.	17	.	0.0032							
VS 5363-90	0.10	0.004	0.016	0.008	0.050	0.00021	.	.	.	17	0.012	6	0.0050	0.09	17	12	0.0029							
VS 5362-90	0.06	.	0.03	0.008	0.050	0.00020	.	.	0.005	13	0.0065	4	0.0044	0.12	12	12	0.0030							
VS 3485-86	2.6	(0.009)	1.3	(0.0014)	0.035	0.00025	.	(3.5)	.	11	0.0028	.	0.026	.	9	.	0.026							
VS 5364-90	2.3	0.006	1.2	0.0013	0.034	0.0003	0.0006	3	0.05	12	0.0029	4	0.024	0.19	8	16	0.022							
Number	Li%	Mo	Nb	Ni	Pb%	Rb%	Sb%	Sc	Sn%	Sr%	V%	W%	Y%	Yb	Zn%	Zr%	Others							
VS 3486-86	0.015	.	17	25	0.011	0.019	0.017	8	0.04	0.020	0.006	.	0.0016	2.24	0.039	0.021								
VS 5361-90	0.014	2.7	17	24	0.010	0.019	0.015	8	0.040	0.018	0.0058	0.20	0.0018	2.5	0.039	0.020								
VS 5365-90	0.007	2.1	13	72	0.0024	0.0080	.	18	0.00036	0.013	0.018	.	0.0030	4	0.012	0.021	Nd: 25, Sm: 4							
VS 5363-90	0.006	1.1	10	55	0.0015	0.0095	.	16	0.00040	0.019	0.014	.	0.0023	3	0.0086	0.018								
VS 5362-90	0.009	1.0	12	31	0.0014	0.0085	.	11	0.00040	0.025	0.0087	.	0.0020	2.6	0.0054	0.015								
VS 3485-86	0.0020	29	(7)	19	(0.020)	0.004	.	9	0.0004	0.018	0.007	.	0.004	3.3	0.014	0.007	Th: 40							
VS 5364-90	0.0020	27	7	18	0.015	0.0045	.	7	0.00033	0.017	0.0075	0.0025	0.0040	2.9	0.014	0.007								

CRM SEDIMENT

analysis listed in mass %															M2: 85 g		others: 80 g units	
Number	Al ₂ O ₃	Ba	Tot.C	CaO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Pb	S	SiO ₂	TiO ₂	Zn	LOI		
US SDAR M2	12.47	0.0990	.	0.84	2.63	5.00	(0.49)	0.134	2.58	(0.079)	0.0808	(0.0970)	73.45	0.300	0.0760	(1.6)		
US SDAR H1	11.83	0.0866	(0.9)	1.46	6.45	4.17	1.53	0.515	(1.1)	0.185	0.3890	.	65.45	0.560	0.3680	.		
US SDAR L2	11.58	0.0809	(0.1500)	1.06	3.63	4.10	(0.43)	0.099	2.66	0.080	0.0183	.	74.48	0.620	0.0201	(0.94)		
continued analysis listed in mg/kg																		
Number	Ag	As	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Ge	Hf	
US SDAR M2	(15)	(76)	6.6	1.05	5.1	98.8	12.4	49.6	1.82	236	5.88	3.58	1.44	17.6	6.28	(1.5)	7.29	
US SDAR H1	(76)	(396)	(22)	(5.1)	(25)	89.3	55.6	.	4.78	1160	4.41	2.60	1.25	15.6	5.35	.	(6.9)	
US SDAR L2	(3.2)	16.9	3.38	0.26	(1.2)	140	5.41	26.0	1.14	50.8	9.83	5.98	1.44	17.0	9.73	(1.6)	(16)	
Number	Hg	Ho	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pr	Rb	Sb	Sc	Se	Sm	Sn	
US SDAR M2	1.44	1.21	(2.1)	46.6	17.9	0.54	13.3	26.2	39.4	48.8	11.0	149	(107)	4.1	(2.7)	7.18	(2.4)	
US SDAR H1	(7.3)	0.900	(9.5)	44.9	50.5	0.398	64	21.9	36.2	230	9.97	152	(505)	(8.2)	(15)	6.39	(2.9)	
US SDAR L2	(0.33)	2.08	(0.47)	67.9	11.8	0.93	3.66	63.0	60.3	14.3	16.2	120	21.8	5.6	(0.9)	11.5	(3.2)	
Number	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zr	Source				
US SDAR M2	144	1.8	0.97	(2.1)	14.2	(2.8)	0.54	2.53	25.2	(3.5)	32.7	3.63	259	river				
US SDAR H1	182	1.41	0.78	(9.5)	17.7	11.1	0.394	4.07	73.2	(13)	(25.4)	2.60	(258)	metalliferous				
US SDAR L2	150	3.81	1.58	(0.44)	22.0	0.99	0.92	3.34	35.0	(1.72)	54.6	6.10	618	blended				

CRM CONTAMINATED RIVER SEDIMENT

certified analysis listed in mg/kg											informational analysis listed in mass %									
Number	As	Cd	Co	Cr	Cu	Hg	Ni	Pb	V	Zn	Al	C.Inorg	C.Org	Ca	Fe	K	Mg	Si	LOI	Units
BAM CC020	56.6	20.8	32.8	290	560	27.4	158	255	53	2030	5.5	0.2	9.7	2.9	5.1	1.7	0.9	25.3	18.5	52 g

CRM TIBET SEDIMENT

analysis listed in mass % T = Total 50 g units

Number	SiO ₂	Al ₂ O ₃	Ba	CaO	F	Fe ₂ O ₃ T	K ₂ O	MgO	Mn	MnO	Na ₂ O	P	P ₂ O ₅	Sr	Ti	TiO ₂
NCS DC70318	73.37	12.73	0.0437	1.32	0.0456	3.19	3.56	1.07	0.0422	0.055	2.09	0.0420	0.097	0.0165	0.253	0.422
NCS DC70319	71.23	13.22	0.0470	1.40	0.0459	4.11	3.65	0.70	0.0527	0.069	2.72	0.0484	0.111	0.0256	0.344	0.589
NCS DC70320	70.36	13.95	0.0483	2.40	0.0505	3.20	3.18	0.93	0.0451	0.059	3.26	0.0564	0.129	0.0404	0.274	0.461
NCS DC70313	69.70	13.19	0.0508	0.39	0.0622	5.85	2.56	1.58	0.0876	0.113	1.23	0.0613	0.140	0.00593	0.439	0.725
NCS DC70315	66.50	10.17	0.0384	6.50	0.0539	3.70	2.26	1.14	0.0567	0.074	1.17	0.0501	0.115	0.0132	0.290	0.491
NCS DC70323	60.95	11.89	0.0475	7.77	0.0555	5.47	2.01	0.78	0.0608	0.078	1.09	0.0542	0.124	0.0327	0.339	0.558

continued analysis listed in mg/kg except * for ng/g and % for mass percent

Number	Ag	As	Au*	B	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd
NCS DC70318	0.06	18.0	1.4	30.6	3.32	0.49	0.9	0.10	89.6	207	6.7	47.6	20.2	16.2	4.92	2.90	1.07	16.3	5.83
NCS DC70319	0.21	19.6	1.2	66.2	2.31	0.80	1.4	0.19	78.1	244	7.6	22.6	15.0	151	3.91	2.39	0.97	15.8	4.57
NCS DC70320	0.14	12.3	1.1	41.5	2.56	0.70	1.1	0.17	60	152	7.3	24.4	13.0	49.0	2.94	1.64	0.96	16.9	3.74
NCS DC70313	0.09	22.0	1.4	77.0	2.34	0.50	1.0	0.54	74.0	63	17.9	93.8	11.9	27.1	4.73	2.81	1.21	17.8	5.40
NCS DC70315	0.10	22.5	1.6	59.5	2.13	0.46	1.5	0.33	71.3	96.7	9.2	37.5	7.9	16.6	4.40	2.60	1.04	14.1	5.15
NCS DC70323	0.10	54.6	2.9	134	3.88	0.48	1.3	0.08	90.1	71	13.2	59.0	42.5	44.0	5.56	2.98	1.40	17.1	6.58

Number	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pd*	Pr	Pt*	Rb
NCS DC70318	1.33	6.7	0.030	0.97	(0.3)	(0.04)	47.8	36.6	0.44	0.59	14.7	35.8	16.9	35.8	(0.4)	9.78	(0.3)	180
NCS DC70319	1.13	9.5	0.028	0.79	(0.3)	(0.04)	42.6	26.1	0.39	7.0	16.1	30.6	9.5	46.8	(0.3)	8.57	(0.3)	154
NCS DC70320	1.12	5.5	0.012	0.58	(0.3)	(0.04)	32.5	25.6	0.25	2.7	10.5	25.7	11.1	45.4	(0.3)	6.94	(0.3)	136
NCS DC70313	1.34	6.5	0.033	0.95	(0.8)	(0.06)	38.8	53.9	0.41	0.60	15.9	31.1	51.9	61.9	(0.6)	8.33	(0.4)	115
NCS DC70315	1.09	6.0	0.026	0.87	(0.5)	(0.05)	37.0	27.9	0.38	0.83	15.6	29.3	20.1	31.7	(0.4)	8.10	(0.3)	104
NCS DC70323	1.66	6.3	0.066	1.06	(0.5)	(0.07)	42.6	69.8	0.38	0.66	15.5	36.3	37.2	27.7	(0.8)	10.1	(0.6)	110

Number	S	Sb	Sc	Se	Sm	Sn	Ta	Tb	Te	Tm	Th	Tl	U	V	W	Y	Yb	Zn	Zr
NCS DC70318	(48)	0.84	7.3	0.05	6.62	3.8	1.8	0.91	(0.03)	0.46	25.1	1.0	4.8	52.5	4.1	26.5	2.83	54.1	225
NCS DC70319	(480)	2.70	6.2	0.18	5.42	2.7	1.8	0.70	0.10	0.38	25.5	1.1	4.8	74.7	9.3	21.6	2.55	62.9	299
NCS DC70320	(183)	1.27	6.0	0.11	4.49	2.0	1.2	0.54	0.07	0.25	16.7	0.91	3.6	59.4	4.2	15.3	1.63	61.1	184
NCS DC70313	(123)	1.91	12.0	0.16	5.99	14.9	1.2	0.83	0.05	0.43	12.1	0.64	2.6	101	2.6	24.4	2.73	176	222
NCS DC70315	(177)	0.82	7.9	0.12	5.61	3.3	1.3	0.78	(0.03)	0.40	12.3	0.62	2.5	57.4	2.4	23.7	2.55	91.1	206
NCS DC70323	(528)	10.4	10.5	0.39	7.19	4.6	1.2	1.01	0.15	0.44	15.6	0.66	2.1	85.0	6.5	29.5	2.67	77.1	210

CRM SERPENTINITE

analysis listed in mass % T = total GUV: 50 g units all others: 100 g units

Number	Al ₂ O ₃	CO ₂	CaO	Cr ₂ O ₃	FeO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	Ni	P ₂ O ₅	SiO ₂	TiO ₂	LOI
NCS DC21001	3.34	.	2.97	.	T.Fe:5.47	.	.	.	34.25	0.131	.	.	P:0.012	41.37	0.180	8.86
SARM 47	1.09	.	(0.1)	0.29	(0.4)	4.14	.	(0.02)	42.09	0.06	(0.05)	0.2221	(0.02)	36.30	(0.01)	.
GUV SW	0.66	0.28	0.18	.	2.00	7.40	13.6	(0.0014)	38.5	0.084	0.013	0.22	(0.0017)	39.04	0.016	.
USZ 24-99	(0.475)	(0.84)	(0.681)	.	(0.27)	8.00T	(0.58-)	(0.018)	38.22	0.082	(0.038)	0.2300	(0.023)	38.54	(0.022)	13.33

continued analysis listed in mg/kg except % which is mass %

Number	As	B	Ba	Ce	Co	Cr%	Cs	Cu	F	Ga	Li ₂ O	Nd	Pb	Rb	S	Sc	Sn	Sr	U	V	W	Y	Zn
NCS DC21001	0.066%
SARM 47	.	.	(75)	(20)	79	.	.	(5)	.	(5)	.	.	(60)	(3)	.	(16)	.	(5)	45
GUV SW	(5)	37	19	.	102	0.24	(5)	7	66	(4)	(3)	(4)	(6)	(5)	(3)	(5)	(5)	.	(5)	20	(5)	.	58
USZ 24-99	106	0.2780	7.3	0.80	33.4	.	.	39

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

CRM	SHALE WITH EXTENSIVE ANALYSIS										analysis listed in mass %						* Provisional Analysis		
Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	Fe ₂ O ₃ T	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SO ₃	TiO ₂	ZrO ₂ +HfO ₂	LOI	Units	
GBW 03104	69.63	14.82	0.13	0.22	(0.40)	5.67	.	(3.71)	3.76	0.67	0.024	0.20	0.043	0.028	0.68	.	4.17	60 g	
NCS DC60106a	69.34	15.03	0.12	0.19	0.37	5.65	.	(3.73)	3.49	0.64	0.020	0.16	0.043	0.029	0.68	.	4.54	50 g	
GUV TS	62.8	15.96	(0.03)	0.12	0.70	7.40	.	4.01	4.86	1.77	0.037	0.078	0.28	.	0.69	.	.	50 g	
US sco-2 *	61.87	13.13	.	3.94	.	.	4.64	.	2.45	2.85	.	1.02	0.181	0.565	.	.	.	50 g	
VS 8549-04	61.21	16.80	1.41	1.14	(3.17)	.	5.57	.	3.72	2.67	0.057	0.95	0.086	(1.53)	0.91	.	6.00	100 g	
UL AWI 1	60.46	16.44	.	0.69	(5.52)	7.21	.	.	3.06	(2.09)	0.14	0.74	(0.15)	.	0.92	.	7.75	50 g	
GBW 07107	59.23	18.82	(0.10)	0.60	1.39	.	7.60	+5.6	4.16	2.01	.	0.35	(5.95)	70 g	
VS 8550-04	57.60	15.53	(3.8)	1.06	(5.3)	.	7.47	.	2.85	3.06	0.110	1.28	0.115	.	0.88	.	(9.5)	100 g	
SARM 41	56.67	13.50	.	1.50	(0.3)	4.23	.	.	1.39	8.10	0.06	0.93	0.05	.	0.55	.	.	100 g	
US SBC-1 *	47.64	21.0	.	2.95	.	.	9.71	.	3.45	2.60	0.15	0.15	0.37	.	0.855	.	10.2	50 g	
US ShPYR-1 *	28.7	6.14	.	14.9	Fe:1.75	.	2.50	.	1.53	5.23	.	1.85	0.28	0.22	.	.	.	200 g	
US SGR-1b	28.24	6.52	.	8.38	(1.41)	(1.46)	3.03	.	1.66	4.44	.	2.99	0.328	.	0.253	.	.	30 g	
US ShBOO-1 *	25.13	4.00	.	32.95	.	.	1.61	.	0.34	0.42	0.012	0.05	0.099	.	0.18	.	31.6	80 g	
JCRM R651	21.74	71.7	.	0.19	.	.	1.48	.	0.65	0.10	.	0.03	0.19	.	3.15	0.18	0.58	100 g	

continued analysis listed in mg/kg except % which is mass % and ** which is ng/g # US SBC-1 also contains 0.85% inorganic C

Number	Ag	As	Au	B	Ba%	Be	Bi	C Org%	T.C%	Cd	Ce	Cl%	Co	Cr	Cs	Cu
GBW 03104	0.014
NCS DC60106a	0.011
GUV TS	(0.8)	27.5	.	74	(0.18)	4	.	1.42	.	.	(168)	.	41	280	13	460
US sco-2 *	.	11.8	.	.	0.0580	1.75	54.5	.	10.8	68.3	7.1	23.5
VS 8549-04	0.10	40	0.10	103	0.072	2.0	.	(1.31)	.	(0.27)	58	.	13	128	4.4	34
UL AWI 1	.	(15)	.	.	0.0378	(2.7)	80	.	20	119	(7)	34
GBW 07107	0.047	1.4	(1.0**)	154	0.0450	3.0	0.23	(0.16)	(0.19)	0.033	109	0.0041	21	99	14	42
VS 8550-04	0.47	46	2.5	(118)	0.0376	(2.4)	.	(0.93)	.	(0.4)	53	.	20	116	4.0	39
SARM 41	0.820	(60)	.	(15)	123	.	53
US SBC-1 *	.	25.7	.	.	0.0788	3.2	0.7	1.23#	2.08	0.4	108	.	22.7	109	8.2	31
US ShPYR-1 *	.	50	.	.	0.0538	.	.	(13.7)	(20.1)	.	32	42
US SGR-1b	.	67	.	54	0.0290	.	.	(3.2N)	(28)	(0.9)	36	(0.0032)	12	30	5.2	66
US ShBOO-1 *	.	(15.1)	.	.	0.00730	(1.0)	(0.24)	4.61	11.9	2.0	24.8	.	6.4	29.6	3.1	33.8
JCRM R651

Number	Dy	Er	Eu	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mn	Mo
GBW 03104
NCS DC60106a
GUV TS	.	.	(3.2)	1150	21	.	.	(7)	(80)	40	(3.6)	.	130
US sco-2 *	3.9	2.3	1.1	.	15.7	4.4	.	.	.	0.78	.	.	28.4	38.2	0.34	.	1.2
VS 8549-04	5.6	(3.3)	1.2	(0.12%)	21	6.1	(2.1)	4.1	.	(1.1)	.	.	30	56	0.44	.	1.7
UL AWI 1	5.1	2.9	1.47	.	22	6	.	6.3	.	1.1	.	.	38	.	0.45	.	.
GBW 07107	5.1	2.7	1.7	1290	26	6.7	3.1	2.9	0.010	0.98	0.24	0.082	62	44	0.41	173	0.35
VS 8550-04	(4.4)	(2.4)	1.2	.	18	4.5	(2.1)	4.7	.	(0.92)	.	.	28	50	0.40	.	(0.95)
SARM 41	(20)	(5)
US SBC-1 *	7.1	3.8	1.98	.	27	8.5	.	3.7	.	1.4	.	.	52.5	163	0.54	.	2.4
US ShPYR-1 *	294	23
US SGR-1b	(1.9)	1.1	0.56	1960	(12)	(2)	.	1.4	(0.3)	(0.4)	.	.	20	147	.	267	35
US ShBOO-1 *	1.67	0.97	0.45	.	6.27	1.95	.	(1.18)	.	0.34	.	.	13.5	24.1	0.15	.	47.8
JCRM R651

Number	N	Nb	Nd	Ni	P	Pb	Pd	Pr	Pt	Rb	Rh	S%	Sb	Sc	Se	Sm	
GBW 03104	
NCS DC60106a	
GUV TS	.	(13)	(108)	170	.	33	.	.	.	230	.	.	0.022	(8.2)	22	(22.9)	
US sco-2 *	.	11.2	25	27.8	.	20	.	6.6	.	101	.	.	0.9	11.4	.	4.9	
VS 8549-04	.	11	28	39	.	8.2	(0.0013)	(6.5)	(0.0012)	0.014%	.	.	0.62	23	.	5.7	
UL AWI 1	.	17	37	61	.	(24)	.	9.3	.	130	.	.	.	16	.	7	
GBW 07107	540	14.3	48	37	690	8.7	.	13.6	.	205	.	.	(0.0066)	0.18	18.5	0.075	8.4
VS 8550-04	.	12	25	50	.	14.9	(0.0023)	6.2	(0.0022)	112	(0.001)	.	1.02	(1)	20	.	5.4
SARM 41	.	(8)	.	122	.	(30)	.	.	.	59	.	.	(0.15)
US SBC-1 *	.	15.3	49.2	82.8	.	35	.	12.6	.	147	.	.	0.715	1.01	20	.	9.6
US ShPYR-1 *	.	.	.	19	1200	24	.	.	.	64
US SGR-1b	.	(5.2)	16	(29)	.	38	1.53 T	3.4	4.6	(3.5)	2.7
US ShBOO-1 *	.	(5.6)	11	74.9	.	(6.1)	.	2.94	.	16.9	.	.	1.64	3.28	(3.6)	.	2.1
JCRM R651

Number	Sn	Sr	Ta	Tb	Te	Th	Ti	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
GBW 03104
NCS DC60106a
GUV TS	(4.1)	88	(0.97)	(2.4)	.	(9.1)	.	.	.	(22)	960	.	150	(15)	63	290
US sco-2 *	.	195	0.82	0.68	.	9	.	.	0.34	3.2	117	.	23.1	2.2	97	.
VS 8549-04	2.2	150	0.86	0.95	.	8.2	.	.	(0.5)	2.1	148	(3.5)	28	2.9	96	176
UL AWI 1	.	108	1.2	0.94	.	12	.	.	0.42	3	134	.	29	3	99	223
GBW 07107	2.0	90	0.9	1.02	(0.023)	12.8	3950	0.71	0.43	1.5	87	0.79	26	2.6	55	96
VS 8550-04	(3.2)	142	(0.7)	(0.74)	.	7.1	.	.	(0.33)	1.65	122	(3.3)	26	2.7	97	176
SARM 41	.	54	.	.	.	(12)	139	.	17	.	76	146
US SBC-1 *	3.3	178	1.1	1.2	.	15.8	.	0.89	0.56	5.76	220	1.6	36.5	3.64	186	134
US ShPYR-1 *	.	753	.	.	.	5	1300	.	.	4	92	.	.	.	62	.
US SGR-1b	(1.9)	420	.	.	.	4.8	.	.	(0.18)	5.4	130	2.6	(13)	(0.94)	74	(53)
US ShBOO-1 *	(3.8)	1078	.	0.29	.	2.74	.	(2.7)	0.15	(9)	419	.	9.6	0.98	97.8	52.6
JCRM R651

Sample US ShPYR-1 also shows much more information on the certificate, such as oil yiled, particle size, programmed prolysis and minerology.

SILLIMANITE

= class, where 1 = CRM and 2 = RM

#	Number	Al ₂ O ₃	SiO ₂	CaO	Fe ₂ O ₃	K ₂ O	Li ₂ O	MgO	MnO	Na ₂ O	TiO ₂	LOI	Units
2	CERAM 2CAS12	63.8	33.9	0.25	0.31	0.13	.	0.12	.	0.15	1.31	0.13	25 or 100 g
1	BCS 309	61.1	34.1	0.22	1.51	0.46	(0.01)	0.17	(0.03)	0.34	1.92	.	100 g

CRM SILLIMANITE SCHIST

analysis listed in mass %

100 g units

Number	Al ₂ O ₃	CaO	Fe ₂ O ₃	FeO	K ₂ O	MgO	MnO	Na ₂ O	F ₂ O ₅	SiO ₂	TiO ₂
SARM 44	58.80	0.14	2.06	(1.0)	(0.18)	(0.1)	(0.03)	(0.05)	(0.10)	34.84	1.83

continued analysis listed in mg/kg

Number	Ba	Ce	Co	Cr	Cu	Ga	Mo	Nb	Ni	Pb	Rb	Sr	Th	V	Y	Zn	Zr
SARM 44	(50)	(220)	(8)	384	(10)	(55)	(15)	96	(15)	(30)	13	5	50	395	84	271	406

CRM SILICA ROCK

analysis listed in mass %

50 g

Number	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	F ₂ O ₅	TiO ₂
NCS DC28016	99.42	0.250	0.045	0.050	0.077	0.0083	0.00074	0.055	0.0015	0.0073
NCS DC28019	94.92	2.42	0.043	0.37	1.41	0.042	0.0050	0.32	0.0045	0.0083

CRM SILICEOUS MINERAL SETS

available in SETS/3, as grouped

50 g units

Number	Material	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	F ₂ O ₅	S	TiO ₂	LOI
JCRM R702	Albite	67.69	19.64	0.546	0.058	0.137	0.103	0.004	11.31	0.139	.	0.030	0.23
JCRM R703	Potassium Feldspar	66.99	17.93	0.095	0.082	11.02	0.040	0.003	3.32	0.008	.	0.005	0.36
JCRM R803	Prophyllite	68.52	23.95	0.033	0.047	2.32	0.017	0.0014	0.165	0.018	0.02	0.104	4.40
JCRM R604	Gairome Clay	47.88	35.37	0.216	1.357	0.468	0.251	0.006	0.083	0.020	(0.014)	0.865	13.37
JCRM R605	Kaolin	49.77	35.64	0.004	0.283	(0.008)	0.004	.	0.032	0.105	(0.023)	0.068	13.90
JCRM R751	Pottery Stone	79.32	14.15	0.033	0.340	(3.00)	0.049	0.003	0.121	0.009	(0.0010)	0.010	2.73

Also see our Industrial Materials catalog for more Siliceous Materials
<http://www.brammerstandard.com/pdf/industrial.pdf>

CRM SILT

analysis listed in mass %

Number	SiO ₂	Al ₂ O ₃	Co ₂	CaO	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	F ₂ O ₅	S	TiO ₂	L.O.I.	Units
VS 5366-90	60.9	14.35	2.4	2.95	1.9	5.44	3.58	2.54	0.088	2.33	0.18	0.08	0.62	6.5	50 g
VS 3133-85	60.85	14.40	.	2.95	.	5.45	3.56	2.54	0.087	2.33	0.18	(0.10)	0.62	6.39	100 g
VS 3132-85	60.54	16.46	.	0.41	.	8.76	2.43	1.60	0.13	1.61	0.19	(0.027)	0.98	6.78	100 g
VS 3131-85	47.0	9.48	.	7.76	.	5.92	2.26	6.06	0.30	0.53	0.13	(0.037)	0.50	20.10	100 g
VS 5367-90	46.7	9.45	9.8	7.74	1.1	5.88	2.24	6.0	0.30	0.53	0.13	0.03	0.50	20.0	50 g

continued analysis listed mass %

Number	As	B	Ba	Ce	Cr	Cu	Li	Ni	Rb	Sb	Sr	V	Zn	Zr
VS 5366-90	0.04	0.007	0.09	0.007	0.008	0.019	0.0035	0.0036	0.011	0.013	0.027	0.011	0.0094	0.023
VS 3133-85	(0.043)	0.006	0.091	0.008	0.0088	0.019	0.0037	0.0036	0.012	(0.0015)	0.028	0.011	0.009	0.023
VS 3132-85	(0.0038)	0.007	0.057	(0.006)	0.014	0.0048	0.00716	0.0072	0.0077	(0.00019)	0.013	0.018	0.012	0.022
VS 3131-85	(0.0016)	0.007	0.062	(0.006)	0.0068	0.0037	0.0096	0.0040	0.0061	.	0.025	0.011	0.005	0.013
VS 5367-90	.	0.008	0.059	0.005	0.0062	0.0037	0.009	0.0040	0.0062	.	0.025	0.0097	0.0049	0.013

continued analysis listed in mg/kg

Number	Ag	Be	Cd	Co	Cs	Ga	Ge	La	Mo	Nb	Nd	Pb	Sc	Sm	Sn	W	Y	Yb
VS 5366-90	.	4	.	13	5	18	.	55	6.5	11	30	55	12	5	5	12	25	2.9
VS 3133-85	(0.8)	3.7	(1.5)	13	5.8	16	1.4	61	10	17	.	58	17	.	5	.	26	3.3
VS 3132-85	(0.17)	2.8	(0.2)	30	4.1	16	1.6	43	2.5	13	.	23	20	.	3.9	.	30	4.3
VS 3131-85	(0.2)	2.4	(2.3)	21	4	11	(1.2)	(38)	2.4	11	.	20	11	.	5	.	22	(2.8)
VS 5367-90	.	2.1	.	21	3.2	11	.	35	2.1	9	15	17	10	3	3.6	.	21	3

CRM SILVER ORE

analysis listed in mass % except * which is mg/kg

USZ: 250g

KZ: 100g

SRM: 200g

Number	Ag*	Ba	Cu	Fe	Fe ₂ O ₃	Pb	S	SO ₃	Zn	Al ₂ O ₃	As	Bi	CO ₂	CaO	Cd	Co*	F	Ge*	
USZ 9-92	740	.	2.25	.	.	0.041	.	.	0.20
USZ 17-94	347.92	.	0.44	.	7.425	10.00	.	21.25	8.72	5.82	.	.	.	3.87
USZ 8-91	331	.	0.83	.	48.40	0.13	.	6.85	0.59	2.11	0.53	0.11	.	0.25	0.0020
USZ 7-91	169	.	0.46	.	.	0.101	.	.	0.42	0.0015
KZ 6587-93	60.2	33.6	0.019	2.5	.	2.86	11.5	.	2.72	.	0.016	.	.	.	0.012
KZ 3031-84	37.4	.	3.37	15.17T	.	.	2.78	.	.	4.93	.	.	2.87	28.05	.	.	0.056	.	.
KZ 6586-93	19	0.38	0.013	2.03	.	3.5	0.55	.	0.045
KZ 6588-93	13.7	0.42	.	3.67	.	1.57	5.88	.	4.68	0.013	.	.	.	4.4
KZ 47-85	8.7	.	0.42	21.0	.	.	2.70
KZ 3030-84	8.6	.	.	13.84T	.	.	2.04	.	.	10.85	.	.	1.04	18.94	.	.	0.048	.	.
KZ 8079-94	3.7	.	0.73	.	.	0.62	1.25	.	0.41	0.016	.	.	.
KZ 3029-84	2.1	.	0.30	3.11T	.	.	1.59	.	.	15.18	0.074	.
KZ 8078-94	1.6	.	0.38	.	.	0.21	0.75	.	0.15	0.0036

continued

Number	K ₂ O	MgO	MnO	Mo	Na ₂ O	Ni	P ₂ O ₅	Re*	Sb	Se*	SiO ₂	Sr	Te*	TiO ₂	Zr
USZ 9-92
USZ 17-94	1.56	0.45	(2.39)	.	(0.13)	.	0.12	.	.	.	42.08	.	.	0.30	.
USZ 8-91	0.53	1.48	2.77	.	.	.	0.54	.	0.50	.	17.80	.	.	0.12	.
USZ 7-91
KZ 6587-93	0.013	.	.	0.69	.	.	.
KZ 3031-84	0.26	1.33	0.33	0.18	0.18	.	.	0.40	.	13.1	33.56	.	9.1	0.19	.
KZ 6586-93	0.029	.	.	0.019
KZ 6588-93	0.0066
KZ 47-85	.	.	.	0.012
KZ 3030-84	0.48	2.06	0.41	0.38	0.16	.	0.17	0.30	.	.	42.32	.	.	0.54	.
KZ 8079-94	0.29	last
KZ 3029-84	4.06	.	0.081	0.0086	1.95	.	0.094	0.043	.	.	68.09	.	.	0.42	last
KZ 8078-94	0.072	last

SLATE WITH EXTENSIVE ANALYSIS

= class, where 1 = CRM and 2 = RM

analysis listed in mass %

#	Number	SiO ₂	Al ₂ O ₃	CO ₂	CaO	FeO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI
1	GUV TB2	60.4	20.5	.	0.20	5.4	6.95T	3.6+	0.86	1.86	0.047	1.29	0.095	.	0.93	3.46
1	GUV TB	60.23	20.64	0.14	.	5.43	6.90	3.78+	3.87	(1.93)	(0.052)	1.32	0.097	.	0.93	.
1	JS1-1	59.47	17.60	(0.769)	1.479	4.523	1.875	+3.92 -0.654	2.845	2.413	0.0599	2.184	0.202	.	0.725	.
1	JS1-2	59.45	18.17	(1.236)	1.885	5.048	0.959	+4.158 -0.362	3.008	2.385	0.0818	1.344	0.164	0.1467	0.754	.
2	IAG OU-6	57.35	20.45	(0.23)	0.74	(1.65)	8.94T	(0.14-)	3.03	2.41	0.28	1.76	0.12	.	0.99	3.62

continued

analysis listed in mg/kg

Number	As	Ba	Be	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd	Hf	Ho	La	Li	Lu
GUV TB2	.	649	.	14	92	11	49	109	.
GUV TB	10.5	780	4.1	104	14	82	9	49	1.8	.	.	740	25	.	5	.	61	111	0.45
JS1-1	14.9	305	2.28	60.6	15.5	60.9	7.60	40.8	(5.11)	.	1.22	598	.	.	4.63	0.688	29.3	(50.7)	0.442
JS1-2	11.4	302	2.68	69.6	15.7	64.7	8.24	44.5	4.71	.	1.14	678	.	.	5.54	(0.671)	32.7	52.6	0.404
IAG OU-6	13.23	480	(2.53)	77.1	29.2	70.7	8.10	40.4	5.06	2.93	1.36	.	24.17	5.30	4.70	1.04	33.2	(95.3)	0.45

Number	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tl	Tm
GUV TB2	.	.	39	.	.	185	.	.	.	5	159
GUV TB	.	50	40	8	.	180	3.4	16	8.4	6	160	1.4	.	18	.	.
JS1-1	9.53	28.8	37.6	17.4	6.07	117	.	16.7	6.02	.	193	0.842	0.717	9.97	.	.
JS1-2	12.3	32.0	40.6	19.7	(6.44)	118	.	16.8	5.95	.	230	1.04	0.727	11.5	.	.
IAG OU-6	14.49	30.2	40.2	28.80	7.91	121.3	(0.56)	23.1	6.01	2.67	131.7	1.02	0.86	11.3	(0.54)	(0.45)

Number	U	V	Y	Yb	Zn	Zr	Units
GUV TB2	.	96	.	3.8	94	180	50 g
GUV TB	.	107	39	3.3	94	180	50 g
JS1-1	2.63	131	30.0	2.81	108	174	100 g
JS1-2	2.92	122	31.3	3.15	101	191	100 g
IAG OU-6	1.92	129.8	27.75	2.98	111.4	174.2	~35 g

B: 0.0090% W: 0.00022%

CRM SOIL - AQUA REGIA METHOD

certified analysis listed in mg/kg

Number	As	Cd	Co	Cr	Cu	Hg	Mn	Ni	Pb	Zn	Units	Method Used
BAM U110 *	13.0	7.0	14.5	190	262	49.3	580	95.6	185	990	60 g	ISO 11466

informational analysis listed in mass %

Number	Si	Al	Ca	Fe	K	S	Mg	Dry Matter	LOI	Org.C	Inorg.C	Tot.C	H	N
BAM U110 *	25.7	5.1	4.1	2.8	1.9	1.1	1.0	97.3 @ 105°C	13.3 @ 550°C	6.7	0.8	7.5	1.2	0.4

* BAM U110 spectroscopic analysis also certified, see "Soil - Contaminated" LATER REPLACED WITH BAM U110a

CRM MERCURY IN SOIL

analysis listed in mass % except * which is mg/kg

Number	Hg*	Al ₂ O ₃	C	CaO	Fe ₂ O ₃ T	K ₂ O	MgO	MnO	N	Na ₂ O	S	SiO ₂	TiO ₂	Dry Mass	Units
USZ 305	2.75	(13.38)	(1.31)	(4.02)	(4.95)	(2.88)	(2.10)	(0.104)	(0.085)	(1.63)	(0.071)	(61.89)	(0.659)	(98.90%)	30 or 50 g
USZ 304	1.52	(11.96)	(1.42)	(4.55)	(4.22)	(2.85)	(1.79)	(0.082)	(0.075)	(1.99)	(0.093)	(64.11)	(0.605)	(99.21%)	30 or 50 g
USZ 303	0.157	(13.10)	(1.19)	(3.39)	(4.68)	(2.98)	(1.68)	(0.097)	(0.088)	(1.84)	(0.021)	(64.39)	(0.65)	(99.05%)	30 or 50 g

CRM AGRICULTURAL SOIL

analysis listed in mass % except * which is mg/kg

50 g units

Number	C	C.Org	Al ₂ O ₃	T.Fe ₂ O ₃	Ti	K ₂ O	MgO	CaO	N	Na ₂ O	P	S	SiO ₂	Mn	Ag*	As*	B*	Ba*
NCS ZC71020	3.85	2.10	14.34	12.09	1.78	1.61	0.906	0.541	0.268	0.187	0.141	0.117	53.61	0.0560	0.093	14.9	63	184
NCS ZC71021	2.02	1.12	14.26	6.59	0.570	3.25	1.12	0.377	0.211	0.168	0.106	0.0437	63.8	0.120	0.155	83	106	531
NCS ZC71022	1.37	0.710	17.68	9.77	0.618	2.25	1.09	0.483	0.158	0.146	0.0704	0.0327	55.9	0.675	0.16	55.7	77	471
NCS ZC71023	0.66	0.368	14.08	4.81	0.372	2.57	1.54	2.15	0.623*	3.216	0.0811	0.0160	66.9	0.0594	0.094	4.45	23.3	733
NCS ZC71024	1.60	0.84	13.26	4.42	0.431	2.66	1.29	1.67	0.129	1.99	0.0613	0.0677	66.9	0.0820	1.07	30.0	44.6	783
NCS ZC71025	1.81	0.995	14.15	5.37	0.435	2.45	1.76	1.98	0.170	2.47	0.152	0.0379	63.1	0.0848	0.399	9.88	34.9	765

continued analysis in mg/kg

Number	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cu	Dy	Er	Eu	F	F.Sol	Ga	Gd	Ge	Hg	Ho
NCS ZC71020	3.40	0.483	4.6	0.57	116	51	32.8	152	98	8.8	4.6	2.80	878	2.29	23.1	9.7	1.59	0.249	1.72
NCS ZC71021	2.57	0.611	4.2	1.47	98	52	19.9	86.1	32.6	5.4	3.22	1.25	960	2.3	19.3	5.4	1.62	12.2	1.13
NCS ZC71022	3.83	0.85	4.0	12.1	107	42	23.9	106	52.2	7.6	4.23	1.87	883	1.91	25.8	8.0	1.89	0.395	1.53
NCS ZC71023	1.78	0.173	2.86	0.130	59.3	104	13.8	82.8	25.2	3.48	1.97	1.24	485	6.1	16.9	4.11	1.21	0.029	0.692
NCS ZC71024	2.11	2.38	9.0	26.2	77.8	410	13.4	61	63.1	4.42	2.57	1.32	503	10.9	16.6	5.11	1.54	4.64	0.88
NCS ZC71025	2.09	1.06	5.5	1.99	71.7	140	16.3	95.2	54.2	4.33	2.44	1.4	521	6.2	18.0	5.01	1.27	0.309	0.86

Number	I	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm	Sn	Sr
NCS ZC71020	1.85	60	56	0.61	3.62	52	57	77.7	26.3	14.3	55	1.36	22.2	1.42	11.1	3.60	96
NCS ZC71021	1.96	45	52.1	0.51	2.37	19.7	34.8	38.1	248	9.5	131	6.3	13.4	0.659	6.4	3.94	80.3
NCS ZC71022	4.85	55.6	67	0.64	2.87	21.3	48	56.1	215	12.8	147	2.2	17.8	0.598	9.3	4.62	42.2
NCS ZC71023	1.63	31.1	21.8	0.305	0.69	11.8	27.8	29.9	19.7	7.33	87.1	0.41	10.8	0.143	5.06	2.22	343
NCS ZC71024	2.54	41.5	35.1	0.404	14.1	14.3	34.3	26.8	182	9.66	99	2.87	9.8	0.75	6.06	4.53	196
NCS ZC71025	2.59	38.2	31.9	0.364	1.35	13.8	33.4	38.3	53.9	8.85	97.7	1.95	11.9	0.451	6.03	5.22	267

Number	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
NCS ZC71020	1.58	11.5	0.43	0.68	6.1	289	1.51	45.2	4.2	185	369
NCS ZC71021	0.92	18.5	1.42	0.51	4.74	112	2.37	29.3	3.26	201	278
NCS ZC71022	1.31	19.7	1.15	0.66	5.91	175	2.87	40.8	4.2	941	277
NCS ZC71023	0.632	8.0	0.528	0.306	1.49	81.4	1.02	18.0	1.93	62.7	278
NCS ZC71024	0.79	11.4	0.865	0.395	2.26	79	3.28	23.3	2.54	100	335
NCS ZC71025	0.781	9.8	0.625	0.367	2.06	91	2.06	22.7	2.36	159	219

CRM SOIL

analysis listed in mass %

100 g units

Number	Al ₂ O ₃	CaO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI
JSo-1	17.99	2.56	11.49	0.34	2.11	0.202	0.66	0.48	.	38.28	1.23	.
USZ 15-94	14.66	2.49	5.65	2.49	1.52	0.103	3.06	0.154	(0.03)	63.28	0.87	(5.22)
USZ 16-94	14.41	2.49	4.99	2.60	1.45	0.109	3.10	0.16	(0.02)	64.37	0.86	(4.81)

continued

analysis listed in mg/kg

Number	As	B	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hg	Ho	In
JSo-1	.	(12)	(269)	(32)	(71)	(1.5)	(169)
USZ 15-94	9.46	.	657	2.17	(0.32)	(0.13)	67.84	14.01	68.88	(3.74)	29.40	(4.43)	(2.61)	(1.43)	(17.92)	(5.54)	(0.02)	(0.96)	(0.07)
USZ 16-94	6.51	.	658	2.44	(0.27)	(0.14)	71.79	(12.88)	357.36	(3.86)	20.51	(4.86)	(2.88)	(1.45)	(17.47)	(5.94)	(0.03)	(1.02)	(0.06)

Number	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th
JSo-1	.	(11.2)	(39)	(13)	.	(14.5)	(196)	.	.	.
USZ 15-94	(33.9)	(23.09)	(0.31)	1.11	(12.21)	(32.46)	31.55	17.26	(8.5)	80.49	(1.09)	11.18	(6.08)	(2.55)	387	(1.19)	(0.75)	8.69
USZ 16-94	(35.12)	22.59	(0.37)	1.03	13.31	(34.61)	43.09	17.88	(9.1)	84.38	(0.78)	11.33	(6.97)	(2.66)	387	(1.17)	(0.78)	9.71

Number	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
JSo-1	.	.	.	(300)	.	(24.9)	.	(105)	(96)
USZ 15-94	(0.42)	(0.32)	1.84	97	(1.36)	22.15	(2.58)	74.67	(298)
USZ 16-94	(0.47)	(0.35)	2.25	87.30	(1.53)	24.43	(2.84)	72.83	(388)

CRM SOIL SET

available in SET/6 ONLY

analysis listed in mg/kg%

25 g units

Number	As	Cd	Cr	Hg	Pb	Se
JSAC 0466	1093	1199	1483	113.5	1214	1175
JSAC 0465	550	607.4	738	57.8	612.4	587
JSAC 0464	271.1	301.0	499	28.6	302.7	291.9
JSAC 0463	137.6	146.8	244	14.76	151.6	141.5
JSAC 0462	71.5	74.2	149.6	7.27	73.7	71.6
JSAC 0461	21.53	(0.30)	97.2	0.075	24.4	(0.44)

CRM SOIL (TILL) REFERENCE MATERIALS WITH ACID EXTRACTION

analysis listed in mass %

100 g units

Number	SiO ₂	Al ₂ O ₃	CaO	Fe	Fe ₂ O ₃	K ₂ O	MgO	Mn	MnO	Na ₂ O	P	P ₂ O ₅	S	Ti	TiO ₂	LOI 1000°C	LOI 500°C	Sum
CAN TILL-3	69.1	12.2	2.63	2.78	3.92	2.42	1.71	0.0520	0.06	2.64	0.0490	0.11	<0.05	0.2910	0.49	4.6	3.6	99.88
CAN TILL-1	60.9	13.7	2.72	4.81	6.82	2.22	2.15	0.1420	0.18	2.71	0.0930	0.22	<0.05	0.5990	0.98	7.3	6.3	99.90
CAN TILL-2	60.8	16.0	1.27	3.84	5.39	3.07	1.83	0.0780	0.10	2.19	0.0750	0.17	<0.05	0.5300	0.88	8.1	6.8	99.80

continued

analysis in mg/kg except % for mass percent and * for parts per billion

Number	As	Au*	Ba	Be	Bi	Br	Ce	Co	Cr	Cs	Cu	Eu	Er	Hf	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Rb	Sb	Sc
CAN TILL-3	87	6	489	2.0	<5	4.5	42	15	123	1.7	22	<1.0	1.4	8	21	21	0.2	2	7	16	39	26	55	0.9	10
CAN TILL-1	18	13	702	2.4	<5	6.4	71	18	65	1.0	47	1.3	3.6	13	28	15	0.6	2	10	26	24	22	44	7.8	13
CAN TILL-2	26	2	540	4.0	<5	12.2	98	15	74	12.	150	1.0	3.7	11	44	47	0.6	14	20	36	32	31	143	0.8	12

continued

partial extraction elements from dilute acid

Number	Sm	Sr	Ta	Tb	Th	U	V	W	Y	Yb	Zn	Zr	Ag	Co	Cu	Fe%	Mn	Mo	Ni	Pb	Zn
CAN TILL-3	3.3	300	<0.5	<0.5	4.6	2.1	62	<1	17	1.5	56	230	49	10	23	2.2	310	1	32	17	43
CAN TILL-1	5.9	291	0.7	1.1	5.6	2.2	99	<1	38	3.9	98	502	<0.2	12	49	3.4	1020	1	17	14	71
CAN TILL-2	7.4	144	1.9	1.2	18.4	5.7	77	5	40	3.7	130	390	12	12	152	3.4	570	13	30	24	116

continued

partial extraction elements from concentrated acid

Number	Ag	As	Ba	Bi	Cd	Co	Cr	Cu	Fe%	Hg*	Mn	Mo	Ni	Pb	V	Zn
CAN TILL-3	1.6	84	43	<3	<0.2	11	73	23	2.0	107	310	<2	32	16	33	43
CAN TILL-1	0.2	13	84	<3	<0.2	12	30	48	3.1	92	950	<2	18	12	48	70
CAN TILL-2	0.2	22	95	4	0.3	13	40	149	3.2	74	530	11	31	21	38	116

CRM SOIL

analysis listed in mass %

100 g units

Number	Type	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	TiO ₂	As	B
VS 2498-83	Sandy, Turf-Ash	91.24	3.36	0.27	0.99	1.23	0.13	0.011	0.51	0.036	0.29	0.0003	0.003
VS 2507-83	Black	71.49	9.81	1.60	3.48	2.42	0.95	0.079	0.81	0.18	0.74	0.0008	0.0056
VS 2508-83	Black	71.49	9.81	1.60	3.48	2.42	0.95	0.079	0.81	0.18	0.74	0.0021	0.0056
VS 2509-83	Black	71.49	9.81	1.60	3.48	2.42	0.95	0.079	0.81	0.18	0.74	0.0004	0.0056
VS 2501-83	Red	59.18	17.01	0.17	7.86	0.98	0.92	0.051	0.15	0.10	1.56	0.0010	0.006
VS 2502-83	Red	59.18	17.01	0.17	7.86	0.98	0.92	0.051	0.15	0.10	1.56	0.0003	0.006
VS 2503-83	Red	59.18	17.01	0.17	7.86	0.98	0.92	0.051	0.15	0.10	1.56	0.0005	0.006
VS 2504-83	Grey	52.65	11.48	11.47	4.60	2.09	2.99	0.089	1.64	0.17	0.64	0.0013	0.0063
VS 2505-83	Grey	52.65	11.48	11.47	4.60	2.09	2.99	0.089	1.64	0.17	0.64	0.0029	0.0063
VS 2506-83	Grey	52.65	11.48	11.47	4.60	2.09	2.99	0.089	1.64	0.17	0.64	0.0006	0.0063

continued analysis listed in mass % except * which is mg/kg

Number	Ba	Be*	Cd*	Ce	Co	Cr	Cs*	Cu	F	Ga*	Hg*	La*	Li	Mo*
VS 2498-83	0.031	1.1	0.1	0.0017	0.00020	0.010	1.6	0.0009	.	5	0.03	10	0.00035	1.5
VS 2507-83	0.050	2.0	0.10	0.007	0.0009	0.0083	4	0.0025	0.028	11	0.05	36	0.0023	1.2
VS 2508-83	0.050	9	1.8	0.007	0.0046	0.0083	4	0.011	0.028	11	0.21	36	0.0023	6
VS 2509-83	0.050	24	4.5	0.007	0.013	0.0083	4	0.027	0.028	11	0.4	36	0.0023	11
VS 2501-83	0.027	1.6	0.12	0.007	0.0014	0.018	9	0.0047	0.04	15	0.08	30	0.005	3
VS 2502-83	0.027	10	2.6	0.007	0.0063	0.018	9	0.017	0.04	15	0.26	30	0.005	8
VS 2503-83	0.027	25	5	0.007	0.015	0.018	9	0.031	0.04	15	0.4	30	0.005	13
VS 2504-83	0.050	2.2	0.3	0.006	0.0012	0.0084	5	0.0034	0.05	13	0.025	29	0.0032	1.4
VS 2505-83	0.050	8	2.1	0.006	0.0057	0.0084	5	0.012	0.05	13	0.18	29	0.0032	6
VS 2506-83	0.050	26	5.5	0.006	0.015	0.0084	5	0.029	0.05	13	0.4	29	0.0032	13

Number	Nb*	Ni	Pb	Rb*	S	Sc*	Se*	Sn	Sr	V	Y*	Yb*	Zn	Zr
VS 2498-83	12	0.0010	0.0008	32	.	2.6	(0.8)	0.00019	0.0069	0.0014	13	1.5	0.0010	0.035
VS 2507-83	14	0.0032	0.0018	88	0.05	11	(3)	0.0003	0.011	0.0072	31	4.1	0.0056	0.047
VS 2508-83	14	0.011	0.009	88	0.05	11	(3)	0.0020	0.011	0.0072	31	4.1	0.018	0.047
VS 2509-83	14	0.030	0.026	88	0.05	11	(3)	0.006	0.011	0.0072	31	4.1	0.046	0.047
VS 2501-83	25	0.0054	0.0023	80	0.04	15	(3)	0.0005	0.005	0.018	27	3.6	0.0087	0.034
VS 2502-83	25	0.016	0.015	80	0.04	15	(3)	0.0022	0.005	0.018	27	3.6	0.027	0.034
VS 2503-83	25	0.038	0.028	80	0.04	15	(3)	0.006	0.005	0.018	27	3.6	0.061	0.034
VS 2504-83	13	0.0045	0.0017	81	0.04	14	(1)	0.0004	0.031	0.009	26	3.3	0.0070	0.019
VS 2505-83	13	0.013	0.010	81	0.04	14	(1)	0.0020	0.031	0.009	26	3.3	0.017	0.019
VS 2506-83	13	0.032	0.028	81	0.04	14	(1)	0.006	0.031	0.009	26	3.3	0.039	0.019

CRM SOIL

analysis listed in mass %

Number	Si	Al	Ca	Fe	K	Mg	Mn	N	Na	P	Ti	Units
GBW 08302	30.57	7.11	2.59	3.34	2.12	1.53	0.0677	0.128	1.52	0.086	0.40	15 g
BCR 142R	0.0970	40 g
ERM-CC690	70 g

continued analysis listed in mg/kg except % which is mass %

Number	As	B	Ba	Be	Br	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Hg	In	La	Lu
GBW 08302	3.8	(25)	(509)	2.96	(1.3)	0.081	83.6	13.1	60.8	(7.3)	24.6	(5)	(239)	1.4	(13)	.	(7.3)	(0.018)	(0.06)	41.9	(0.48)
BCR 142R	0.34	.	12.1	(113)	.	69.7	3.2	.	0.067	.	.	.
ERM-CC690	49.1	2.90	24.4	.

Number	Mo	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb	Zn	
GBW 08302	(0.0)	42.3	31.1	14.2	(9)	135	(0.4)	10.8	0.16	7.1	163	(1.1)	(0.9)	17.6	.	3.84	77.5	(3.5)	(25)	3.1	58	
BCR 142R	.	.	64.5	40.2	(101)	.
ERM-CC690	.	19.1	7.9	.	3.5	.	.	0.50	7.6	0.232	1.90	.	.	.	1.57	.	

CRM SOIL

analysis listed in mass %

70 g units

Number	Al ₂ O ₃	C(tot)	CaO	CO ₂	C.Org	T.Fe ₂ O ₃	FeO	H ₂ O+	K ₂ O	MgO	Mn	N	Na ₂ O	P	S	SiO ₂	Ti	LOI
NCS DC73319a	12.9	7.8	2.7	.	(6.8)	4.4	(2.25)	(4.3)	2.85	1.17	0.131	0.32	1.65	0.23	0.0726	56.6	0.326	15.8
NCS DC73320a	11.7	1.37	4.0	2.4	0.71	4.2	(0.78)	2.8	3.03	1.40	0.092	0.075	2.67	0.0512	0.0316	65.9	0.28	5.8
NCS DC73321a	12.9	0.69	0.84	.	0.65	2.6	(0.55)	2.6	2.91	0.61	0.033	0.085	2.54	0.042	(0.0146)	72.9	0.22	3.7
NCS DC73322a	16.9	0.46	(0.13)	.	0.42	6.9	(0.43)	6.3	3.00	1.33	0.030	0.073	(0.1)	0.031	0.0130	63.3	0.46	(6.97)
NCS DC73323a	16.8	(0.2)	(0.07)	.	(0.2)	9.8	(0.19)	7.0	2.14	0.70	0.051	0.059	(0.1)	0.0353	0.0839	61.5	0.61	7.2
NCS DC73324a	26.6	0.23	0.13	.	(0.2)	12.3	(0.1)	12	0.44	0.20	0.23	0.021	(0.14)	0.024	0.0534	45.3	0.43	(13.22)
NCS DC73325a	27.3	1.3	(0.2)	.	1.18	18.0	(1.46)	13.6	0.35	0.31	0.19	0.13	(0.1)	0.21	0.0432	33.7	2.06	15.3
NCS DC73326a	11.8	1.91	7.5	5.3	0.50	4.3	1.23	3.4	2.30	2.00	0.063	0.06	1.71	0.068	0.0187	60.1	0.37	8.9

analysis listed in mg/kg

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F	Ga	Gd
NCS DC73319a	0.81	33	69	700	3.3	1.4	4.1	2.5	71	(87)	10.3	44	7.2	42	6.0	3.8	0.89	513	18.1	5.5
NCS DC73320a	0.072	18	27	1187	2.6	0.29	4.6	0.2	123	(51)	11.1	52	4.7	20	4.5	2.5	1.8	723	14.8	6.2
NCS DC73321a	0.075	6.2	21	1117	1.7	0.21	3.8	0.079	45	(73)	6.9	35	3.2	13.4	2.8	1.7	0.8	354	15.7	3.1
NCS DC73322a	0.059	9.6	88	312	2.4	1.8	2.8	0.11	99	(30)	20	81	12.5	43	4.4	2.5	1.2	1127	23	5.5
NCS DC73323a	4.6	242	108	343	1.8	23	(1.5)	0.16	85	(31)	18	113	18	147	5.1	3.2	1.0	601	25	4.5
NCS DC73324a	0.24	88	28	181	6.9	89	(1.1)	(0.5)	85	110	20	86	9.4	358	5.4	3.7	0.39	1526	40	4.2
NCS DC73325a	0.08	(4.2)	(19)	237	2.9	(0.37)	6.4	(0.23)	113	(54)	93	379	2.9	84	5.7	2.4	3.0	341	39	8.3
NCS DC73326a	0.067	13.2	51	492	2.0	0.31	3.7	0.14	68	68	12.3	65	7.3	24	4.9	2.7	1.2	555	15.1	5.5

Number	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se
NCS DC73319a	1.3	6.5	0.31	1.3	2.0	0.12	39	28	0.57	2.0	15.3	30.8	16.9	339	8.5	137	2.4	8.3	0.22)
NCS DC73320a	1.2	6.3	0.017	0.9	2.6	0.048	61	22	0.38	1.6	35	55	24	27	14.8	95	0.86	9.5	0.26
NCS DC73321a	1.2	7.1	0.116	0.58	2.5	0.033	21	18	0.28	0.5	10.6	19	15	28	4.9	85	0.69	5.6	0.12
NCS DC73322a	1.7	6.9	0.072	0.85	4.0	0.095	54	27	0.40	0.70	16.1	40	36	37	11.2	152	1.4	15.9	0.31
NCS DC73323a	2.3	8.3	0.7	1.1	2.8	1.4	35	51	0.49	2.3	20	27	38	245	7.3	142	14.9	16.9	0.75
NCS DC73324a	6.2	6.5	0.086	1.1	13.2	4.1	31	43	0.80	169	38	20	75	478	5.6	118	14	17	0.47
NCS DC73325a	1.5	8.9	0.058	1.0	19.0	0.11	56	23	0.30	3.2	80	47	217	18.3	11.7	28	0.53	25	0.34
NCS DC73326a	1.3	6.9	0.027	0.98	1.6	0.053	35	33	0.042	0.76	13.1	31	30	21	8.0	96	1.2	11.5	0.098

Number	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
NCS DC73319a	5.9	9.8	192	1.3	0.98	(0.06)	13.1	1.2	0.61	6.3	61	3.5	38	3.8	475	218
NCS DC73320a	7.9	2.0	249	(0.86)	0.89	(0.037)	13.3	0.63	0.38	1.9	65	1.9	25	2.5	58	219
NCS DC73321a	3.5	2.6	325	1.2	0.50	(0.04)	6.7	0.51	0.28	1.2	45	1.1	16	1.8	39	247
NCS DC73322a	6.8	5.6	58	1.4	0.84	(0.085)	19	1.0	0.4	3.0	125	2.9	23	2.6	92	234
NCS DC73323a	4.5	7.2	39	1.6	0.80	6.6	17.2	1.1	0.5	4.0	136	7.4	29	3.2	172	272
NCS DC73324a	4.7	439	30	16	0.84	(0.5)	35	3.6	0.7	28	108	132	33	5.2	1529	156
NCS DC73325a	9.3	5.0	37	5.7	1.2	(0.06)	10.5	0.3	0.33	2.6	240	2.3	25	2.0	187	370
NCS DC73326a	6.0	2.9	197	1.1	0.86	(0.034)	12.2	0.57	0.43	2.3	80	1.8	26	2.8	66	241

CRM SOIL WITH EXTENSIVE ANALYSIS

analysis listed in mass %																Org = Organic	Sol = Soluble	T = Total	50 g units
Number	Al ₂ O ₃	C	Org.C	CaO	F	T.Fe ₂ O ₃	K ₂ O	MgO	Mn	N	Na ₂ O	P	S	SiO ₂	Ti	Zn			
NCS ZC71008	10.31	7.90	4.73	15.0	0.0532	4.83	1.628	1.24	0.0648	0.281	0.709	0.0887	0.111	43.85	0.315	0.0201			
NCS ZC71009	15.41	2.81	2.75	1.000	0.0566	5.24	1.78	0.932	0.0438	0.276	1.00	0.0660	0.0502	62.54	0.493	0.0221			
NCS ZC71010	13.17	2.45	2.36	1.085	0.0520	4.97	1.732	0.973	0.0517	0.218	1.19	0.0833	0.0447	66.9	0.476	0.0230			
NCS ZC71011	9.45	1.11	1.07	0.412	0.0353	3.89	1.45	0.512	0.0424	0.120	0.475	0.0420	0.0364	77.1	0.571	0.00897			
NCS ZC71012	15.30	0.62	0.59	1.420	0.0762	9.06	3.11	0.783	0.0725	0.0613	1.11	0.106	0.301	61.5	0.410	0.0260			
NCS ZC71013	16.27	1.29	1.12	1.28	0.128	7.23	2.62	1.223	0.117	0.154	0.35	0.0863	0.0222	61.5	0.546	0.0117			
NCS ZC71014	11.77	1.56	1.04	3.65	0.0450	3.68	2.39	1.85	0.0503	0.107	2.17	0.105	0.0238	67.41	0.330	0.00644			
NCS ZC71015	11.94	1.23	1.18	1.22	0.0504	6.37	3.17	1.53	0.104	0.126	1.52	0.110	0.0470	67.4	0.495	0.0269			
NCS ZC71016	12.57	2.66	2.23	3.73	0.0757	4.78	2.74	3.76	0.0864	0.243	2.21	0.339	0.0644	59.7	0.397	0.0302			
NCS ZC71017	18.52	1.61	0.91	0.376	0.0547	4.74	2.65	0.609	0.0498	0.170	0.605	0.125	0.0308	61.8	0.536	0.0133			
NCS ZC71018	12.34	1.44	0.79	0.414	0.0441	5.98	1.79	1.34	0.0417	0.149	0.470	0.0607	0.0281	69.52	0.492	0.0261			
NCS ZC71019	10.52	0.84	0.468	1.51	0.0440	6.54	2.46	0.697	0.297	0.0693	0.428	0.0430	0.0468	72.28	0.306	0.0224			

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cu	Dy	Er	Eu	Sol.F
NCS ZC71008	0.56	22.5	41	448	2.15	1.68	4.5	2.02	67	94	13.4	70	76	4.13	2.36	1.14	8.3
NCS ZC71009	0.44	83.4	60	502	2.62	47.8	6.0	14.2	83	69	14.4	92	69.8	5.63	3.15	1.48	8.7
NCS ZC71010	0.91	12.5	66	480	2.32	0.58	5.2	0.276	79	119	13.7	78.2	104	5.53	3.1	1.44	6.8
NCS ZC71011	0.259	41.9	92	351	1.55	1.99	1.8	0.276	87	45	13.4	59.0	69	5.04	2.99	1.16	1.89
NCS ZC71012	7.5	222	50	713	1.75	6.0	1.8	0.62	70.2	52	9.17	27.5	301	3.23	1.79	1.44	1.53
NCS ZC71013	0.128	19.3	70	386	2.79	0.62	4.55	0.398	87	34	23.9	87.0	53.1	5.41	3.16	1.4	4.3
NCS ZC71014	0.088	8.8	38.2	592	1.75	0.259	5.2	0.238	56.5	91	10.1	60.6	21.7	3.79	2.19	1.12	7.2
NCS ZC71015	5.4	398	64.1	713	1.90	10.9	4.5	2.14	70	74	15.0	65.3	76	4.59	2.64	1.36	8.7
NCS ZC71016	0.46	13.8	29.8	863	1.99	0.559	5.1	2.71	73.8	98	12.5	60.0	244	3.87	2.11	1.41	3.3
NCS ZC71017	0.162	6.2	26.2	515	3.70	0.77	3.93	0.293	135	74	11.7	39.9	56.3	6.7	3.68	1.69	5.1
NCS ZC71018	1.61	349	65	511	2.12	3.29	2.83	2.58	83	54	16.1	215	244	4.39	2.55	1.21	2.2
NCS ZC71019	2.21	8.9	11.5	521	2.25	9.6	2.1	0.636	61	52	8.74	43.5	74	3.43	2.04	0.87	3.9

Number	Ga	Gd	Ge	Hg	Ho	I	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Sb
NCS ZC71008	13.2	4.55	1.33	0.205	0.83	2.77	36.7	38.4	0.361	4.28	11.5	28.7	28.7	92	7.7	78	3.4
NCS ZC71009	19.5	6.15	1.61	0.62	1.12	2.19	45.5	46.7	0.459	1.1	17.0	37.8	40.9	372	10.0	114	22.1
NCS ZC71010	16.7	6.03	1.48	3.44	1.09	1.58	42.7	41.1	0.456	0.63	16.4	36.9	34.7	153	9.9	101	2.03
NCS ZC71011	12.6	5.27	1.35	0.074	1.02	1.11	42.3	29.9	0.45	1.40	19.5	34.2	19.2	42.4	9.3	72	1.62
NCS ZC71012	21.5	4.20	1.35	0.087	0.63	1.37	40.3	18.7	0.272	26.4	14.8	29.1	9.9	340	8.0	109	27.3
NCS ZC71013	21.8	5.8	1.72	0.133	1.12	3.54	43.0	49.0	0.49	1.42	18.1	37.1	43.9	40.9	9.9	129	2.08
NCS ZC71014	14.2	4.20	1.22	0.052	0.76	2.72	30.5	23.9	0.339	0.54	10.9	26.1	23.9	23.2	7.0	85.6	0.69
NCS ZC71015	15.5	5.04	1.4	0.101	0.92	2.38	36.5	33.3	0.406	1.30	16.5	32.0	29.9	1050	8.46	98.1	6.3
NCS ZC71016	16.0	4.77	1.27	0.061	0.76	2.73	39.5	23.7	0.314	2.53	13.1	33.3	22.8	50.9	8.9	85.1	0.84
NCS ZC71017	24.2	7.8	1.4	0.157	1.26	1.79	69.8	25.1	0.57	2.49	24.2	53	17.2	60	14.9	154	0.72
NCS ZC71018	15.8	4.8	1.69	0.231	0.90	1.96	46	43.3	0.396	2.67	18.9	33.3	90.6	166	9.3	99	7.8
NCS ZC71019	14.7	3.65	2.09	0.085	0.70	2.86	32.7	21.6	0.340	7.3	19.4	24.5	10.9	467	6.9	127	0.59

Number	Sc	Se	Sm	Sn	Sr	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zr
NCS ZC71008	10.0	1.96	5.40	7.6	236	0.74	11.0	1.26	0.363	3.19	86.6	4.6	23.7	2.3	169
NCS ZC71009	15.4	1.86	7.03	27.9	99.3	0.99	15.0	1.28	0.479	2.93	112	2.56	30	3.01	232
NCS ZC71010	12.6	0.44	6.95	54	103	0.97	13.5	0.65	0.47	2.64	95.1	2.31	29.1	2.95	270
NCS ZC71011	9.3	0.412	6.20	5.1	72.1	0.85	13.5	0.536	0.461	2.86	81.4	3.13	28.1	2.92	377
NCS ZC71012	7.3	2.82	5.08	10.0	260	0.606	9.9	0.977	0.274	3.19	91	4.63	16.7	1.76	222
NCS ZC71013	16.2	0.52	6.7	11.0	120	0.93	14.6	0.94	0.49	3.73	132	2.28	28.8	3.13	212
NCS ZC71014	9.4	0.259	4.92	2.63	262	0.667	8.1	0.558	0.337	1.46	66.4	1.39	20.4	2.17	246
NCS ZC71015	10.8	0.62	5.92	2.95	163	0.81	9.9	0.598	0.408	2.07	88	3.25	23.9	2.61	296
NCS ZC71016	9.7	0.495	5.78	2.3	304	0.710	7.52	0.699	0.321	1.93	76.1	2.57	20.1	2.05	247
NCS ZC71017	12.2	0.45	9.4	9.1	80	1.22	36.7	1.25	0.54	10.1	100	3.92	34.5	3.6	304
NCS ZC71018	11.5	1.19	5.88	5.6	79	0.76	15.7	0.83	0.394	4.27	96	6.7	22.4	2.5	276
NCS ZC71019	7.2	2.02	4.5	20.3	74	0.60	13.9	1.06	0.326	3.14	55	8.7	17.8	2.2	287

CRM SOIL - CONTAMINATED

certified analysis listed in mg/kg

T = Total

Number	As	B	Be	Cd	Co	Cr	Cu	F	Hg	Mn	Ni	Pb	Se	V	Zn	Type	Units
BAM U110 *	15.8	.	.	7.3	16.2	230	263	.	51.5	621	101	197	.	.	1000		60 g
JSAC 0411	11.3	.	1.04	0.274	.	23.5	26.7	.	.	943	11	18.9	1.32	68.6	64.6	Volcanic Ash Soil	50 g
JSAC 0401	10.62	.	5.28	4.25	.	50.4	15.3	.	.	266	18.9	26	0.27	65.0	66.8	Brown Forest Soil	50 g

* Aqua Regia values for BAM U110 listed under "Soil - Aqua Regia Method" in this catalog, Replaced with BAM U110a

CRM SOIL - CONTAMINATED

analysis listed in mass % except as noted

powder 75 g

Number	Hexavalent Cr	Cr	Fe	Mn	Al	Tot.Org.C	Ca	K	Mg	Na	Si	Ti	V	PH	Redox Potential
SRM 2701	0.05512	4.26	23.73	0.2137	(5.05)	(3.69)	(7.47)	(0.174)	(7.47)	(0.255)	(4.17)	(0.547)	(0.236)	9.6	(526 mV)

CRM SOIL - CYANIDE

analysis in mg/kg powder

Number	Total Cyanide	Uncertainty	Units	
BAM U114	23.1	1.3	66 g	last of stock
CGL 306	12.0	0.8	100 g	

SOIL - CONTAMINATED

= class where 1 = CRM and 2 = RM analysis listed in mg/kg except % which is mass % 50-60 g units

# Number	Ag	Al%	As	Au	B	Ba	Be	Bi	Br	C%	Ca%	Cd	Ce	Co	Cr	Cs	Cu	Dy
2 SRM 2780a	72.5	8.43	65.9	6.6	(27)	930	(1.1)	(45)	.	(0.19)	0.247	(4.8)	67.7	16.5	205	8.3	240	(3.1)
1 SRM 2710a	(40)	5.95	1,540	(0.2)	(20)	792	0.964	12.3	(60)	5.99	(23)	(8.25)	342	(3)
1 IRNT SVM **	(4)	(8.96)	13.6	.	(70)	582	(500)	.	(5)	.	(0.692)	0.214	(100)	15.4	79.8	(6)	30.0	(5)
1 IRNT SSP **	(5)	(7.48)	14.0	.	.	315	6.34	0.285	.	15.6	75.3	.	30.9	.
1 SRM 2709a	.	7.37	(10.5)	.	(74)	979	1.91	0.371	(42)	12.8	130	(5.0)	(33.9)	(3)
1 SRM 2586	.	6.652	8.7	.	.	413	(1.4)	.	.	.	2.218	2.71	58	(35)	301	.	(81)	(5.4)
1 SRM 2587	.	5.86	13.7	.	.	568	(9.2)	.	.	.	0.927	1.92	(57)	(14)	92	.	(160)	.
1 BAM U110a *	.	.	15.8	7.3	.	16.2	230	.	263	.

continued

Number	Er	Eu	Fe%	Ga	Gd	Ge	Hf	Hg	Ho	In	K%	La	Li	Lu	Mg%	Mn%	Mo
SRM 2780a	(2.0)	(0.9)	8.75	(21)	(3.2)	(<6)	(5.5)	(0.2)	(0.7)	(1.65)	3.99	34.4	(14)	(0.33)	0.465	0.0490	25.0
SRM 2710a	.	(0.82)	4.32	.	(3.0)	.	(7)	9.88	.	.	2.17	30.6	.	(0.3)	0.734	0.214	.
IRNT SVM **	.	(2)	3.73	.	(7)	.	(10)	0.171	.	.	3.08	(60)	(30)	(500)	(0.593)	0.0897	.
IRNT SSP **	.	.	3.73	0.0874	.	.	2.63	.	.	.	(1.19)	0.0734	.
SRM 2709a	.	(0.83)	3.36	.	(3.0)	.	(4)	(0.9)	.	.	2.11	(21.7)	.	(0.3)	1.46	0.0529	.
SRM 2586	(3.3)	(1.5)	5.161	(14)	(5.8)	.	.	0.367	(1.1)	.	0.976	29.7	(25)	.	1.707	0.1000	.
SRM 2587	.	.	2.813	(13)	.	.	.	0.29	.	.	1.583	(29)	(32)	.	0.6690	0.0651	.
BAM U110a *	51	0.0621	.

continued

Number	Na%	Nb	Nd	Ni	P%	Pb%	Pr	Rb	Re	S%	Sb	Sc	Se	Si%	Sm	Sn	Sr
SRM 2780a	0.108	(20)	28.3	95	0.0286	0.665	(8)	220	(0.003)	8.85	18.3	15.6	(6)	24.1	4.7	(7.2)	121
SRM 2710a	0.894	.	(22)	(8)	0.105	0.552	.	(117)	.	.	52.5	(9.9)	(1)	31.1	(4.0)	.	255
IRNT SVM **	(0.3)	.	(50)	30.8	(0.000013)	0.00196	.	(200)	.	.	4.58	(15)	(300)	25	(10)	.	(82.0)
IRNT SSP **	.	.	.	37.4	.	0.00413	2.11	274
SRM 2709a	1.22	.	(17)	(85)	0.0688	0.00173	.	(99)	.	.	1.55	(11.1)	(1.5)	30.3	(4)	.	239
SRM 2586	0.468	(6)	26.4	(75)	0.1001	0.0432	(7.3)	(24)	(0.6)	29.15	(6.1)	.	84.1
SRM 2587	1.127	(14)	(25)	(36)	0.0970	0.3242	(11)	.	33.13	.	.	126
BAM U110a *	.	.	.	101	.	0.0197

continued

Number	Ta	Tb	Te	Th	Ti%	Tl	Tm	U	V	W	Y	Yb	Zn%	Zr	
SRM 2780a	(1.2)	(0.5)	(22)	12.0	0.643	(5.5)	(0.31)	4.0	152	(17.4)	(18)	(2)	0.102	206	LOI: (11.1)
SRM 2710a	(0.9)	(0.5)	.	(18.1)	0.311	(1.52)	.	9.11	(82)	(190)	.	(2)	0.418	(200)	.
IRNT SVM **	(1)	(1)	.	(20)	0.55	(<200)	.	(3)	98.3	(3)	.	(4)	0.00888	(350)	last
IRNT SSP **	89.7	.	.	.	0.0119	(200)	last
SRM 2709a	(0.7)	(0.5)	.	(10.9)	0.336	(0.58)	.	(3.15)	110	.	.	(2)	(0.0103)	195	.
SRM 2586	.	(0.09)	.	(7)	0.605	.	(0.5)	.	(160)	.	(21)	2.64	0.0352	.	.
SRM 2587	.	.	.	(7.5)	0.3920	.	.	.	(78)	.	(15)	(1.6)	0.03358	.	.
BAM U110a *	0.1000	.	* Aqua Regia also certified

** IRNT certificates expired, however use and sales continue without problems worldwide

RM STEATITE

analysis listed in mass % 25 or 100 g units

Number	SiO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	TiO ₂	LOI
CERAM 2CAS14	62.7	0.149	0.249	0.314	0.002	31.28	0.008	0.005	5.10

CRM SULPHUR

Number	Recommended S Value (%)	95% Confidence Low%	Limits High%	Standard Deviation of Laboratories (%)		Number of Sets	Results	Units
				Between	Within			
CAN HCC-1	33.92	33.80	34.03	0.14	0.095	9	53	50 g
CAN INM-1	22.17	21.97	22.37	0.24	0.051	9	53	50 g

CRM SULPHUR IN VARIOUS FORMS - SEE ALSO "MULTI-METAL ORE"

analysis listed in mass %

Number	Type	S	SO ₄	Al	CO ₂	Ca	Cu	Fe	H ₂ O	Mg	Pb	Si	Zn	LOI	Units
NCS DC71307	Sulphide	52.72	0.0431	46.08	.	.	(0.00234)	.	0.0219	.	5 g
NCS DC71308	Sulphide	34.69	33.30	30.30	.	.	0.0128	.	0.30	.	5 g
CAN HCC-1	Concentrate	33.92	50 g
NCS DC71310	Sulphide	32.33	0.10	2.14	.	.	0.099	.	62.51	.	5 g
CAN WMS-1A	Sulphide	28.17	.	1.350	.	3.09	1.396	45.4	(0.2)	(0.331)	(0.0033)	(4.7)	(0.0130)	.	200 g
CAN INM-1	Concentrate	22.17	50 g
NCS DC71309	Sulphide	13.30	0.00624	0.0127	.	.	84.26	.	0.0533	.	5 g
CAN RTS-3a	Ore Tailings	9.59	(1.1)	5.12	0.04	2.14	0.2353	20.49	.	2.483	0.0209	18.28	0.2890	(10.6)	100 g

continued analysis listed in mass %

Number	C	Cd	Co	K	Mn	Na	Ni	P	Sb	Sn	Ti
NCS DC71307	.	0.000071	(0.00039)	.	0.00289	.	0.00340	.	0.00011	(0.00027)	.
NCS DC71308	.	0.00202	0.00751	.	0.00475	.	0.00413	.	(0.00027)	(0.00058)	.
CAN HCC-1
NCS DC71310	.	0.15	0.0491	.	0.0169	.	0.00432	.	0.0249	(0.00032)	.
CAN WMS-1A	(0.1)	(0.00014)	(0.145)	(0.0991)	(0.0600)	(0.0329)	3.02	(0.018)	(0.000692)	(0.00023)	(0.0840)
CAN INM-1
NCS DC71309	.	0.00165	(0.00004)	0.43	0.11	.
CAN RTS-3a	(0.04)	0.000921	0.0143	0.460	0.1585	0.684	0.00613	0.0446	0.000283	.	0.351

continued analysis listed in mg/kg

Number	Ag	As	Au	Ba	Bi	Cr	Ga	Ge	In	Pd	Pt	Se	Sr	Te	Tl	Zr
NCS DC71307	0.59	(14.4)	.	.	2.9	.	0.44	(0.2)	.	.	.	5.8	.	0.95	.	.
NCS DC71308	846	(3.1)	.	.	16.1	.	(0.3)	.	(66.6)	.	.	48.3	.	10.4	.	.
CAN HCC-1
NCS DC71310	5.0	(3.3)	.	.	6.1	.	251	6.0	21.0	.	.	(3.0)	.	(0.3)	.	.
CAN WMS-1A	(3.7)	30.9	0.300	(70)	(1.2)	(68)	(4)	.	(0.2)	1.45	1.91	(87)	(31.3)	.	.	(20)
CAN INM-1
NCS DC71309	0.97%	5.3	.	.	1.4	.	(0.3)	1.47	0.29	(0.07)	0.65	.
CAN RTS-3a	11.1	18.2	0.561	106	31.3	176	(30)	.	(1.6)	(0.004)	.	44.8	44.7	(2.0)	(3)	78

CRM SULPHUR ORE

analysis listed in mass %

Number	Al ₂ O ₃	BaO	CaO	Cu	T.Fe	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	Zn	LOI	Units
UNS MII	10.63	0.049	0.49	0.21	6.79	2.22	2.06	0.11	0.93	(12)	(7)	(16)	0.50	1.79	(10)	100 g

continued analysis listed in mg/kg

Number	Ag	As	B	Cd	Co	Cr	Cs	Eu	Ga	Hf	La	Mo	Ni
UNS MII	(0.012)	0.0901	(0.005)	0.0767	0.0223	(0.012)	(0.003)	(0.003)	(0.008)	(0.003)	(0.003)	(0.003)	0.0329

Number	Pb	Rb	Sb	Sc	Sr	Ta	Th	U	V	W	Y	Yb	Zr
UNS MII	0.868	(0.005)	(0.004)	(0.003)	0.0259	(0.003)	(0.006)	(0.004)	0.0845	(0.004)	(0.008)	(0.006)	(0.008)

CRM SULPHUR ORE

Number	S%	C%
GS908-4	30.08	.
GS399-10	28.22	.
GS310-2	27.59	.
GS900-2	26.62	.
GS300-5	26.54	.
GS310-1	26.44	.
GS316-8	25.59	0.07
GS300-7	24.85	.
GS916-8	23.76	0.60
GS322-8	22.27	0.51
GS907-10	21.94	.
GS916-6	19.20	0.48
GS317-2	18.66	0.48
GS316-7	18.13	0.41
GS916-7	17.67	0.52
GS317-3	16.76	0.67
GS916-9	14.55	0.60
GS913-3	10.95	0.03
GS312-7	10.53	2.63
GS916-4	9.95	0.86
GS312-6	9.80	3.10
GS910-4	8.27	.
GS921-9	8.04	3.18
GS913-1	7.90	0.06
GS314-8	7.82	0.26
GS907-4	7.68	.
GS917-1	7.33	0.47
GS913-5	7.30	0.03
GS913-6	7.22	0.04
GS913-7	7.18	0.04
GS307-7	7.04	.
GS921-8	6.90	0.14
GS901-2	6.59	0.30
GS913-8	6.56	0.04
GS314-10	6.50	0.37
GS921-10	6.13	0.28
GS905-3	5.64	.
GS914-4	5.44	1.00
GS908-6	5.01	.
GS311-7	4.41	0.50
GS905-8	4.38	.
GS921-7	4.08	0.09
GS314-3	3.37	0.36
GS310-3	3.3	.
GS901-1	3.20	.
GS399-7	3.09	.
GS917-2	3.09	0.40
GS314-2	2.56	5.15
GS302-7	2.39	.
GS311-1	2.35	.
GS399-5	2.29	.
GS305-1	2.20	.
GS310-5	2.2	.
GS916-3	2.17	0.26
GS915-1	2.06	0.08
GS916-5	2.05	0.07
Number	S%	C%

CRM SULPHUR ORE

Number	S%	C%
GS302-5	1.98	.
GS302-9	1.94	.
GS305-6	1.71	.
GS921-3	1.66	1.93
GS300-4	1.43	.
GS305-7	1.41	.
GS313-8	1.24	0.94
GS310-4	1.17	.
GS311-3	1.12	.
GS322-7	1.10	2.71
GS914-5	1.08	1.39
GS915-7	1.07	0.16
GS315-9	0.94	0.34
GS900-3	0.92	.
GS910-3	0.92	.
GS910-7	0.86	.
GS313-7	0.78	0.74
GS907-3	0.78	.
GS305-2	0.76	.
GS900-4	0.71	.
GS921-5	0.70	0.99
GS921-6	0.70	0.97
GS322-3	0.69	0.57
GS322-2	0.68	1.46
GS314-9	0.64	1.13
GS903-1	0.63	.
GS910-9	0.63	.
GS322-6	0.61	0.03
GS316-4	0.58	0.09
GS316-2	0.56	0.08
GS916-2	0.56	0.17
GS311-4	0.54	.
GS917-5	0.53	0.30
GS322-5	0.52	0.05
GS322-5	0.52	0.05
GS912-3	0.52	0.07
GS312-3	0.47	0.06
GS301-6	0.40	.
GS300-8	0.37	.
GS316-1	0.36	0.04
GS917-4	0.36	0.05
GS921-4	0.36	1.93
GS316-3	0.34	0.06
GS303-9	0.31	.
GS312-5	0.28	0.88
GS312-5	0.28	0.88
GS303-10	0.27	.
GS310-10	0.27	.
GS914-2	0.26	0.06
GS315-8	0.25	0.19
GS322-4	0.24	1.35
GS914-10	0.24	0.21
GS921-1	0.23	0.14
GS921-2	0.23	0.18
GS312-9	0.21	0.03
GS317-1	0.21	0.15
GS322-1	0.21	0.18
GS906-6	0.21	.
GS915-3	0.19	0.11
GS914-1	0.18	0.04
GS915-8	0.13	0.07
GS917-8	0.11	5.78
Number	S%	C%

CRM SULPHUR ORE

Number	S%	C%
GS912-1	0.09	0.03
GS915-6	0.09	0.04
GS917-9	0.09	5.56
GS316-10	0.08	0.03
GS316-9	0.08	0.06
GS311-5	0.07	.
GS307-2	0.06	.
GS912-2	0.06	0.03
GS313-1	0.05	0.03
GS316-5	0.05	0.46
GS316-6	0.05	0.45
GS317-6	0.05	0.05
GS910-5	0.05	.
GS911-5	0.05	.
GS911-9	0.05	.
GS912-10	0.05	0.11
GS912-6	0.05	0.06
GS915-4	0.05	0.03
GS312-10	0.04	0.03
GS312-2	0.04	0.22
GS314-7	0.04	0.09
GS315-4	0.04	0.11
GS317-10	0.04	0.04
GS910-2	0.04	.
GS912-9	0.04	0.12
GS917-3	0.04	0.05
GS313-2	0.03	0.03
GS313-4	0.03	0.26
GS313-5	0.03	0.25

Number	S%	C%
--------	----	----

for all GS Sulfur Ore samples,
unit size is 10 g powder

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

TITANIUM ORE

analysis listed in mass % T = TOTAL

35 g units

Number	Al ₂ O ₃	CaO	T.Fe ₂ O ₃	FeO	H ₂ O	K ₂ O	MgO	Mn	Na ₂ O	P	S	SiO ₂	TiO ₂	Zn	Zr	LOI
NCS DC73523	14.8	3.3	12.6	0.62	(3.1)	3.4	4.6	0.0700	1.4	0.25	0.0062	51.9	3.1	0.0111	0.0340	(3.8)
NCS DC73524	15.3	3.2	10.9	0.52	(3)	2.9	3.6	0.0759	2.4	0.26	0.0055	51.0	6.3	0.0092	0.0701	(3.4)
NCS DC73525	9.2	6.5	29.8	15.0	(1.8)	0.46	5.4	0.44	1.5	0.10	0.28	29.3	16.7	0.0193	0.0158	2.1
NCS DC73526	0.94	0.32	48.1	22.5	0.8	0.030	0.57	1.1	0.08	0.0225	0.0185	2.1	48.1	0.0294	0.0414	(0.7)

Powder 35 g

continued analysis listed in mg/kg

Number	As	Cd	Ce	Co	Cr	Cu	Dy	Er	Eu	Ga	Gd	Ho	La	Lu	Nb	Nd
NCS DC73523	1.8	0.06	103	37	474	46	6.5	3.1	3	22	8.9	1.2	53	0.3	.	55
NCS DC73524	2	0.07	107	26	286	31	6.7	3.3	3	21	9.1	1.3	54	0.35	.	55
NCS DC73525	(2)	0.09	59	70	202	35	3.8	2.1	1.1	17	4.9	0.74	29	0.31	195	28
NCS DC73526	.	(0.005)	143	50	397	18	7	4.1	0.6	11	10	1.3	68	0.6	(707)	62

Number	Ni	Pb	Pr	Rb	Sc	Sm	Sr	Ta	Tb	Th	Tm	U	V	W	Y	Yb
NCS DC73523	182	5.9	13	57	28	10	237	(3.4)	1.3	6	0.45	0.7	202	(0.6)	31	2.4
NCS DC73524	104	6.7	14	48	24	10	298	(8.7)	1.3	7.6	0.5	(2.2)	264	.	32	2.7
NCS DC73525	51	32	7	18	36	5.3	412	(14)	0.7	30	0.35	1.8	690	(2.5)	20	2.1
NCS DC73526	15	104	16	1.5	50	11	21	(40)	1.3	99	0.6	4.7	723	(8)	37	4

TITANIUM ORE

analysis listed in mass %

#	Number	Ilmenite	TiO ₂	Al ₂ O ₃	C	CaO	Co	Cr	Cr ₂ O ₃	Fe	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O
2	OSO Ki-370-99	95.41
1	NCS HC26619	.	98.21	0.65	0.011	0.006
1	DSZU 123.22-95	.	65.33	3.17	.	0.51	.	.	1.32	16.10	.	.	.	0.53	0.92	.
1	VS R31	.	56.5	1.99	2.59	24.4
1	NCS DC28139	.	55.68	2.30	.	0.070	0.0026	.	2.80	22.04	9.15	.	.	1.09	1.26	.
1	DSZU 103.39-07	.	53.9	0.66	0.04	29.1	.	.	.	0.56	0.63	.
1	NCS DC26705	.	51.35	0.75	0.043	0.16	.	(0.07)	31.40	23.81	.	.	.	0.84	0.90	.
1	NCS DC28142	.	50.06	1.30	.	0.68	0.011	.	0.84	30.23	28.85	.	.	1.52	0.875	.
1	NCS DC19019	.	49.78	0.53	.	0.028	.	.	0.054	34.56	25.05	.	.	0.32	1.55	.
1	SARM 165	.	49.3	0.26	.	0.043	.	.	0.10	.	50.4	.	.	0.58	1.11	.
1	NCS DC28138	.	47.82	0.68	.	0.68	0.0087	.	0.014	34.79	39.14	.	.	2.11	0.652	.
1	NCS DC93032	.	47.79	0.64	.	0.64	.	.	.	34.26	37.08	.	.	3.04	0.766	.
1	NCS DC93033	.	45.96	1.08	.	1.17	.	.	.	31.11	35.76	.	.	5.36	0.698	.
1	NCS DC28140	.	45.73	0.95	.	2.23	0.051	.	0.012	33.02	36.68	.	.	1.68	0.882	.
1	NCS DC19017	.	45.71	1.64	.	1.75	.	.	0.014	29.12	32.56	.	.	5.18	0.709	.
1	NCS DC28141	.	45.61	0.867	.	1.65	0.0098	.	0.0067	33.58	37.51	.	.	1.74	0.799	.
1	NCS DC28097	.	45.10	1.79	0.32	1.17	.	.	0.051	33.49	36.43	.	0.025	1.53	0.68	0.053
1	NCS DC28100	.	44.93	1.44	0.037	1.10	.	.	1.96	32.90	18.52	.	0.060	0.79	1.01	0.033
1	AMIS 0454 *	Ti: 26.78	44.45	0.731	.	0.216	.	(0.0713)	(0.114)	see below	52.53	(0.045)	0.74	1.19	(0.03)	.
1	NCS DC28137	.	40.66	1.35	.	4.78	0.010	.	0.0064	30.31	33.33	.	.	1.30	1.20	.
1	NCS DC28098	.	36.78	3.20	0.26	1.13	.	.	0.079	34.87	35.49	.	0.079	2.92	0.65	0.11
1	NCS DC28143	.	35.60	1.65	.	6.25	0.013	.	0.0077	29.29	29.34	.	.	1.55	1.02	.
1	NCS DC19018	.	33.94	4.47	.	3.14	.	.	0.0085	27.30	29.70	.	.	6.88	0.524	.
1	NCS DC28136	.	27.23	2.31	.	9.49	0.015	.	0.0078	26.50	23.62	.	.	2.34	0.802	.
1	NCS DC28099	.	25.78	6.28	0.37	4.50	.	.	0.079	27.53	24.22	0.24	2.34	0.46	1.52	.
1	CGL 129	17025	14.88	9.79	.	1.16	0.0209	0.3068	.	61.86	.	61.86T	0.137	3.05	0.240	(0.086)
1	NCS DC28096	.	14.12	3.29	0.18	0.70	.	.	0.058	50.20	24.52	.	0.052	2.45	0.52	1.09
1	NCS DC28134	.	7.11	8.67	.	12.39	0.0052	.	0.0084	14.85	12.45	.	.	6.33	0.216	.
1	NCS DC28135	.	6.14	8.82	.	9.87	0.0079	.	0.0095	15.07	12.77	.	.	6.78	0.187	.

Number	Ni	P	P ₂ O ₅	S	SiO ₂	Sr	V	V ₂ O ₅	Zn	Zr	LOI	Units
OSO Ki-370-99	1 kg of ~3mm material
NCS HC26619	.	.	.	0.006	20 g
DSZU 123.22-95	.	.	0.15	0.0090	1.45	.	.	0.18	.	.	.	100 g
VS R31	.	.	0.25	.	1.24	100 g
NCS DC28139	0.0007	0.047	.	0.025	1.54	.	.	0.266	0.017	.	.	Cu:0.0093 50 g
DSZU 103.39-07	.	.	0.10	0.59	1.88	.	.	0.25	.	.	.	100 g
NCS DC26705	.	0.045	.	0.004	1.98	.	.	0.22	.	.	.	40 g
NCS DC28142	0.0021	0.048	.	0.172	2.04	.	.	0.700	0.017	.	.	Cu:0.0073 50 g
NCS DC19019	.	0.0048	.	0.010	0.578	.	.	0.137	.	.	.	100 g
SARM 165	Nb ₂ O ₅ :0.076	.	0.022	.	0.72	.	.	0.26	.	ZrO ₂ :0.10	.	100 g
NCS DC28138	0.0029	0.0076	.	0.184	2.65	.	.	0.095	0.016	.	.	Cu:0.0056 50 g
NCS DC93032	.	0.0074	.	0.185	2.08	.	.	0.088	.	.	.	100 g
NCS DC93033	.	0.0032	.	0.201	4.03	.	.	0.075	.	.	.	100 g
NCS DC28140	0.0051	0.048	.	0.74	4.85	.	.	0.203	0.016	.	.	Cu:0.013 50 g
NCS DC19017	.	0.117	.	0.0080	5.99	.	.	0.090	.	.	.	100 g
NCS DC28141	0.0046	0.047	.	0.536	4.16	.	.	0.188	0.015	.	.	Cu:0.011 50 g
NCS DC28097	0.022	.	0.188	.	2.97	.	.	0.086	.	.	.	Cu:0.016 50 g
NCS DC28100	0.0081	.	0.25	0.011	2.34	.	.	0.20	.	.	.	Cu:0.0041 50 g
AMIS 0454 *	.	.	(0.030)	.	2.23	.	.	(0.24)	.	ZrO ₂ : (0.12)	Nb: (0.0576)	100 g Density: 4.63
NCS DC28137	0.0084	0.117	.	1.52	9.21	.	.	0.068	0.014	.	.	Cu:0.022 50 g
NCS DC28098	0.015	0.22	.	0.39	6.78	.	.	0.136	.	.	.	Cu:0.0047 50 g
NCS DC28143	0.011	0.476	.	2.76	10.41	.	.	0.505	0.016	.	.	Cu:0.027 50 g
NCS DC19018	.	0.558	.	0.028	11.73	.	.	0.101	.	.	.	100 g
NCS DC28136	0.013	1.07	.	4.77	14.41	.	.	0.066	0.015	.	.	Cu:0.038 50 g
NCS DC28099	0.048	.	1.82	2.21	16.25	.	.	0.14	.	.	.	Cu:0.033 50 g
CGL 129	0.0306	.	0.022	7.77	0.0152	0.02818	.	.	0.0575	0.00354	.	(-0.25) 150 g
NCS DC28096	0.0090	.	0.144	0.089	6.88	.	.	0.50	.	.	.	Cu:0.0059 50 g
NCS DC28134	0.0037	0.883	.	0.196	38.43	.	.	0.062	0.019	.	.	Cu:0.0082 50 g
NCS DC28135	0.0098	0.232	.	0.021	42.61	.	.	0.092	0.018	.	.	Cu:0.016 50 g

* AMIS 0454 certifies Fe by XRF 36.50%, Titration 37.14%, and M/ICP 36.37%.

Special Note: more Titanium Powders are in our "Other Chips & Powders Catalog."

RM

ILMENITE

typical analysis listed in mass %

100 g

Number	TiO ₂	Al ₂ O ₃	C	CaO	Co ₃ O ₄	Cr ₂ O ₃	CuO	Fe	K ₂ O	MgO	Mn	NiO	P ₂ O ₃	S	SiO ₂	SrO	V ₂ O ₅	ZnO	ZrO ₂
DH 6706	32.37	4.46	0.044	1.179	0.024	0.143	0.017	36.83	0.118	2.82	0.094	0.049	0.017	0.288	7.31	0.016	0.285	0.020	0.044

CRM TUNGSTEN ORE

analysis listed in mass % except * which is mg/kg

CAN: 200 g

GW: 10 g

IGS: 65 g

NCS: 50 g

all others: 100 g

Number	W	WO ₃	Ag*	As	Be	Bi	Cu	Fe	Ge*	Mo	Nb	P	Pb	S	SiO ₂	Sn	Other
VS 1710-79	.	71.96	.	.	.	0.146
NCS DC35018	.	70.50	.	0.028	.	Ca:4.93	0.019	.	.	0.011	.	0.038	.	0.72	1.94	0.020	.
SRM 2430	.	70.26	.	0.002	.	0.078	.	.	.	0.22	.	0.017	.	0.26	.	.	.
NCS DC35019	.	69.19	.	0.052	.	Ca:1.94	0.038	.	.	0.010	.	0.021	.	0.21	1.70	0.13	.
NCS DC35021	.	69.13	0.065	.	Mn:0.042	0.031	.	0.044	.	0.73	.	.	.
SRM 277	.	67.50
NCS DC35020	.	67.18	.	0.083	.	Ca:1.62	0.044	.	.	0.012	.	0.024	.	0.25	1.98	0.14	.
NCS DC35022	.	66.02	0.0034	.	Mn:0.029	0.073	.	0.0079	.	0.35	.	.	.
NCS DC35023	.	57.01	0.13	.	Mn:0.12	0.012	.	0.091	.	1.24	.	.	.
CAN CT-1	1.04
CAN BH-1	0.422
KZ 7027-93	0.17	0.015	.	.	.	0.0093	0.0014	Zr: 0.013
GW-03	0.1744
GW-02	0.1231
KZ 7026-93	0.11	1.2	.	.	0.0022	0.018	0.052	.	3.6	0.00098	0.0015	.	.	Sr:0.017	.	.	Sr: 0.017
CAN TLG-1	0.083
IGS 27	0.036	1.76	.	0.276
VS 1714-79	.	1.04	10.3	.	.	0.009	.	.	.	0.041	0.113	.
VS 1715-79	.	0.60	.	.	0.013	0.054	0.020	.	3.1	0.026	.	.	0.049	.	.	0.068	last Zn: 0.038
VS 2040-81	.	0.49	.	.	.	0.0058	0.053	0.94	.	0.016	last
VS 2042-81	.	0.38	.	.	.	0.0032	0.105	4.17	.	0.039	last
VS 2039-81	.	0.22	.	.	.	0.023	0.27	2.47	.	0.0026	last
VS 1713-79	.	0.17	5.5	.	0.0058	0.015	.	.	2.9	0.011	0.028	last
VS 1711-79	.	0.036	.	.	0.0022	0.0044	.	.	.	0.0026	0.0071	last

CRM TUNGSTEN ORE

analysis listed in mass %

T = Total

GBW: 50 g

USZ: 100 g units

Number	WO ₃	Al ₂ O ₃	As	Bi	CaO	Cy	F	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Mo	Na ₂ O	Pb	Rb	S	SiO ₂
USZ 26-99	0.41	14.14	0.09	0.0067	1.95	.	.	3.72	5.59T	4.32	2.04	0.12	0.079	2.13	0.0076	0.106	.	64.87
GBW 07241	.	11.15	.	0.068	4.17	0.096	4.84	.	5.60	1.58	0.14	0.090	0.098	0.12	.	(0.05)	1.90	71.27
GBW 07240	.	8.24	0.18	0.011	37.73	0.79	9.91	.	7.79	1.94	1.45	0.97	.	0.16	0.26	(0.08)	3.12	13.27

analysis listed in mass %

analysis listed in mg/kg except % which is mass %

Number	Sn	TiO ₂	Zn	Ag	As	Cd	Ce	Co	Cu%	Dy	Eu	Er	Ga	Gd	Ge	Ho	In	La
USZ 26-99	(0.016)	0.82	0.017	11	0.022
GBW 07241	0.17	0.044	0.010	1.8	69.6	0.94	60.3	.	.	20.7	0.17	13.1	16.5	14.8	11.2	4.5	1.3	1.8
GBW 07240	0.14	0.079	0.29	8.3	.	26.1	10.0	.	.	0.46	0.15	0.23	17.8	0.64	2.5	0.11	8.7	5.0

analysis listed in mg/kg except % which is mass %

Number	Lu	Mo	Nd	Ni	Pb	Pr	Sb	Sc	Se	Sm	Sr	Tb	Te	Th	Tl	Tm	Y	V%	Yb	Zr%
USZ 26-99	.	.	35	.	.	(20)	78	0.010	.	.	0.017
GBW 07241	2.4	.	32.9	2.8	81.2	7.9	3.1	5.4	0.96	12.5	.	3.3	2.9	28.3	1.8	2.2	128	.	14.9	.
GBW 07240	0.06	4.2	4.0	4.1	.	1.1	5.1	1.8	0.39	0.79	.	0.15	0.66	2.2	5.0	0.04	2.8	.	0.28	.

CRM TUNGSTEN ORE

analysis in mass % except * is mg/kg

more information on certificates

Number	W	WO ₃	Au*	Cu	Fe	FeO	Fe ₃ O ₄	Mo	SiO ₂	Sn	Mass Recovered	Units
OREAS 701	2.43	3.07	1.11	0.491	23.98	17.35	17.95	0.0254	33.95	0.0197	20.80	10g, 500g, or 1 kg, last of stock
OREAS 700	1.13	1.42	0.506	0.202	16.06	12.07	10.91	0.0081	47.30	0.0182	11.28	10g

RM		ULTRAMAFIC ROCK - KOMATIITE										analysis listed in mass %								continued analysis listed in mg/kg							
Number	Al ₂ O ₃	CaO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Ba	Be	Ce	Co	Cr	Cs	Cu									
IAG OKUM	7.97	7.85	11.81	0.044	21.2	0.188	1.13	0.026	44.1	0.380	(4.49)	(6.2)	(0.065)	1.27	88	2460	0.184	43									
continued analysis listed in mg/kg																											
Number	Dy	Er	Eu	Ga	Gd	Hf	Ho	La	Li	Lu	Nb	Nd	Ni	Pb	Pr	Rb											
IAG OKUM	1.61	1.04	0.300	8.7	(1.17)	0.55	0.355	0.41	(4.4)	0.148	0.37	1.49	88	(0.26)	0.235	0.96											
Number	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Th	Tm	U	V	Y	Yb	Zn	Zr	Units											
IAG OKUM	(0.079)	27	0.71	(0.25)	16	0.026	(0.229)	0.031	(0.155)	(0.012)	167	9.0	1.00	61	17	100 g											

CRM		URANIUM ORE												analysis listed in mass %				CGL: 100g		GU: 10 g	
Number	U	Al ₂ O ₃	CaO	Cu	Fe	TFe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	Zn	Zr	LOI				
GU-10	0.1876			
GU-09	0.1134			
GU-08	0.03124			
GU-07	0.02429			
CGL 503	0.0147	14.28	0.822	0.00148	.	3.18	3.88	0.779	0.044	1.99	0.160	(0.20)	67.95	0.649	0.00797	0.0239	(4.95)				
GU-11	0.003467			
GU-03	0.00048	.	.	0.00210	3.5			
GU-04	0.00042			
GU-06	0.000382			
GU-05	0.000356			
continued analysis for CGL 503 listed in mg/kg																					
Number	As	Ba	Be	Cd	Ce	Co	Cr	Cs	Dy	Er	Eu	Ga	Gd	Ge	Hf	Ho	La	Li	Lu	Mo	Nb
CGL 503	(9.96)	662	(4.96)	(0.23)	87.9	7.5	45.4	12.2	(4.44)	(2.43)	(1.29)	22.2	(5.45)	(1.74)	(2.89)	(0.84)	46.9	(41.31)	(0.30)	8.8	17.2
Number	Nd	Ni	Pb	Pr	Rb	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Th	Ti	Tm	V	W	Y	Yb	
CGL 503	(36.51)	12.6	35.5	(9.67)	234	(0.31)	7.9	(4.31)	(6.49)	(4.44)	269	(0.99)	(0.71)	17.6	(1.45)	(0.33)	82.3	(4.43)	24.4	(1.98)	

CRM		URTITE											analysis listed in mass				40 g units			
Number	SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MnO	MgO	CaO	Na ₂ O	K ₂ O	FeO	P ₂ O ₅	Ba	Sr							
VS 2123-81	42.80	1.79	26.47	2.67	0.084	0.14	3.73	13.33	5.16	1.40	0.388	0.035	0.100							
continued analysis listed in mg/kg																				
Number	Be	Co	Cr	Cu	Ga	La	Li	Mo	Nb	Ni	Pb	Rb	Sn	V	Y	Yb	Zn	Zr		
VS 2123-81	5.1	8.1	9.7	24	48	100	8.9	2.3	97	6.5	5.8	79	3.4	86	26	1.7	44	220		

CRM		VANADIUM ORE														analysis listed in mass %				10 g units			
Number	V ₂ O ₅	Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe	K ₂ O	MgO	MnO	Na ₂ O	SiO ₂	TiO ₂	Co	Cu	Ni	P	S	Zn	LOI					
GV-01	1.233	5.57	0.079	0.721	48.95	0.010	1.30	0.148	0.015	4.27	14.104	0.019	0.022	0.067	0.005	0.067	0.037	2.07					
GV-02	0.790	11.24	2.484	0.560	34.41	0.080	2.80	0.161	0.573	19.76	9.174	0.017	0.033	0.061	0.018	0.220	0.030	2.76					
GV-06	0.343	7.18	6.204	0.007	25.93	0.464	9.73	0.326	0.627	30.57	6.549	0.014	0.007	0.016	0.102	0.018	0.027	0.91					
GV-03	0.327	16.78	2.966	0.044	20.24	0.183	3.59	0.176	0.843	33.96	4.302	0.013	0.013	0.048	0.023	0.073	0.016	7.44					
GV-05	0.223	7.53	4.004	0.008	23.97	0.440	14.33	0.350	1.272	34.61	4.121	0.017	0.006	0.022	0.099	0.013	0.024	-1.28					
GV-04	0.089	11.93	8.822	<0.01	13.15	1.809	4.21	0.263	3.008	45.99	3.568	0.005	0.013	0.004	0.348	0.086	0.020	0.47					

RM		VOLCANIC TUFF WITH EXTENSIVE ANALYSIS												analysis listed in mass %				~35 g units			
Number	Al ₂ O ₃	Ba	CaO	FeO	T.Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	SiO ₂	Sr	TiO ₂	V	LOI						
IAG OU-1	15.136	0.01314	6.488	4.995	8.987	0.215	4.727	0.129	2.463	0.050	58.247	0.010476	0.440	0.022223	3.058						
continued analysis listed in mg/kg																					
Number	As	Be	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Ho	La	Li				
IAG OU-1	8.221	0.43	0.17	12.49	24.41	27.65	0.14	61.55	3.40	2.40	0.52	13.63	2.78	1.65	0.80	5.60	20.35				
Number	Lu	Nb	Nd	Ni	Rb	Sb	Sc	Sm	Ta	Tb	Th	Tm	U	Y	Yb	Zn	Zr				
IAG OU-1	0.39	2.3	7.32	13.00	2.05	0.22	32.69	2.13	0.15	0.49	1.68	0.37	0.40	21.63	2.49	74.40	55.00				

CRM WOLLASTONITE

analysis listed in mass %

50 g units

Number	Al ₂ O ₃	CaO	FeO	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI
GBW 03123	0.39	40.39	0.28	0.10	0.14	0.95	0.096	0.052	0.052	(0.010)	50.50	0.022	6.93

CRM ZEOLITE WITH EXTENSIVE ANALYSIS

analysis listed in mass %

T = Total

Number	Al ₂ O ₃	Ba	CaO	Fe ₂ O ₃	H ₂ O-	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Rb	SiO ₂	Sr	TiO ₂	Zr	LOI	Units
FLX CRM104	33.74	.	0.063	0.014	20.06	.	.	45.98	.	.	.	(22.64)	35 g
USZ 49-2009	12.98	0.0371	1.34	1.27T	.	3.19	0.573	0.033	3.44	0.032	0.0106	67.44	0.0635	0.158	0.0177	8.80	70 g
CGL 017	12.91	0.0383	1.30	0.802T	(4.17)	3.21	(0.55)	0.007	3.35	0.030	0.0107	67.64	0.0651	0.161	(0.0179)	(9.77)	70 g
NH Zeolite 1	12.21	0.0779	4.51	1.75T	.	2.19	1.41	0.045	0.612	0.055	0.00957	67.11	0.0617	0.190	0.0158	.	50 g

continued analysis listed in mg/kg

Number	As	Be	Bi	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Ga	Gd	Hf	Hg	Ho
FLX CRM104
USZ 49-2009	60.5	(2.75)	(11.7)	(7.85)	74.8	20.3	12.7	4.73	79.3	(3.46)	(1.83)	(0.50)	13.8	(3.81)	(5.38)	(1.85)	(0.66)
CGL 017	(63)	(2.6)	.	.	(77)	(0.94)	(7.9)	.	(2.9)	(3.5)	(1.91)	(0.49)	14.84	(4.3)	(7.9)	.	(0.67)
NH Zeolite 1	1.96	1.96	.	.	52.3	.	.	3.88	5.12	.	.	.	13.9	.	.	0.329	.

Number	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Sb	Sc	Sm	Sn	Ta	Tb	Th	Tm
FLX CRM104
USZ 49-2009	37.2	(6.07)	(0.27)	(0.43)	14.1	27.3	14.6	84.2	(7.97)	(50.9)	3.27	(4.82)	(2.27)	(1.16)	(5.9)	17.2	(0.27)
CGL 017	(39.5)	(6.4)	(0.28)	.	14.17	(27.5)	(2.2)	21.78	(8.4)	.	(3.6)	(5.1)	(2.6)	(1.26)	(0.63)	(17.3)	(0.29)
NH Zeolite 1	32.6	20.8	.	0.379

Number	U	V	W	Y	Yb	Zn
FLX CRM104
USZ 49-2009	3.09	42.3	(1.52)	18.6	(1.81)	79.3
CGL 017	(3.1)	(11.1)	.	20.36	(1.8)	25.37
NH Zeolite 1	.	12.6	.	21.8	.	38.2

17025

CRM ZINC ORE

analysis listed in mass % except * which is mg/kg T = Total

Number	Zn	S	Al ₂ O ₃	Ca	CaO	Cd	Cu	Fe	Hg*	Mg	MgO	Ni	Pb	Sb	SiO ₂
IMN TC/P10	60.6	3.07	0.14	.	2.54	.	.	6.7	.	.	1.38	.	2.31	.	0.56
CAN CZN-4	55.24	33.07	Al:0.0715	(0.0419)	.	0.2604	0.403	(9)	4.54	(0.0352)	.	(0.0016)	0.1861	(0.0010)	Si:0.295
BCS 520	52.50	31.78	0.334	.	0.125	.	0.568	9.88	.	.	0.266	.	0.820	.	1.78
NCS DC35017	46.93	.	.	.	2.65	0.199	.	0.432	.	.	1.46	.	1.69	.	6.65
NCS DC28169	43.46	26.70	.	.	2.05	0.309	0.265	6.79	.	.	0.158	.	2.66	.	5.95
GBM305-12	17.0581	0.0119	0.0042	0.4214	.	.
GBM919-13	6.5874	5.78	1.6692	0.0056	0.3986	.	.
GBM916-11	6.0894	9.89	1.0864	0.0009	0.2843	.	.
IMN RG 8	5.4	0.57	0.9	.	26.45	0.047	.	6.34	.	.	12.16	.	0.84	.	2.64
GBM907-14	3.1882	2.90	0.8167	0.0061	0.1973	.	.
IMN RB 7	3.07	(10.3)	.	.	24.35	0.033	.	8.28	.	.	15.26	.	(0.26)	.	(0.8)
GBM921-14	2.9758	4.13	0.5305	0.0025	0.2821	.	.
GBM916-9	2.9716	0.5257	0.0026	0.2710	.	.
GBM321-11	2.0664	2.17	0.6834	0.0031	0.6596	.	.
GBM921-8	2.0559	0.6823	0.0034	0.6515	.	.
GBM919-12	1.6668	23.18	0.7274	0.0048	0.0206	.	.
BCR 109	0.46	0.946	14.51	0.96	0.020	.	.	0.738	.	.

continued

Number	Ag*	As	Au*	Bi*	C	Cl	Co	F	In	Mn	PbO	Se*	Sn	ZnO	Units
IMN TC/P10	240 g
CAN CZN-4	51.4	0.0356	(0.04)	(10)	(0.09)	(0.003)	0.00935	(0.004)	(0.020)	(0.009)	.	86.7	(0.05)	.	200 g
BCS 520	36	0.0228	100 g
NCS DC35017	0.013	50 g
NCS DC28169	48	0.0014	25 g
GBM305-12	10 or 250 g
GBM919-13	17.3
GBM916-11	68.0
IMN RG 8	(0.72)	.	.	(4.36)	130 g
GBM907-14	10 or 250 g
IMN RB 7	170 g
GBM921-14	41.3	10 or 250 g
GBM916-9	40.6	0.0233	0.0044
GBM321-11	45.2	10 or 250 g
GBM921-8	45.3	0.0077	0.0044	10 or 250 g
GBM919-12	5.3
BCR 109	0.0081	10 or 250 g

CRM ZINC ORE WITH EXTENSIVE ANALYSIS

analysis listed in mass % T = Total * Provisional Analysis CGL: 200 g GBW: 50 g JZn-1: 100 g units

Number	Zn	Al ₂ O ₃	CaO	T.C	Cu	F	Fe ₂ O ₃	H ₂ O-	H ₂ O+	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	Pb	S	SiO ₂	TiO ₂	LOI
CGL 207	49.14	0.112	0.850	.	0.1940	.	10.45T	.	.	.	(0.068)	6.20	(0.016)	(0.026)	0.3407	31.12	(1.73)	.	.
GBW 07237	2.75	2.80	1.91	.	0.71	1.20	3.50	.	0.99	0.082	0.026	0.56	.	0.25	0.25	2.87	82.95	0.017	.
JZn-1 *	2.22	6.32	18.1	(1.28)	(0.0029)	.	11.8	(0.61)	(1.71)	0.83	1.94	1.49	0.45	.	0.161	(1.30T)	(43.95)	0.20	(6.61)

continued analysis listed in mg/kg

Number	Ag	As	Ba	Be	Bi	Cd	Ce	Co	Cr	Cs	Dy	Eu	Er	Ga	Gd	Ge	Ho	In	La	Li		
CGL 207	33.43	167.7	(9.48)	(0.254)	309.6	910.5	(9.82)	424.4	(29.86)	(0.425)	.	.	.	(2.83)	.	(0.743)	.	152.9	(7.30)	.		
GBW 07237	13.5	12.4	.	.	56.4	29.3	2.3	.	(62)	.	0.49	0.06	0.28	8.0	0.31	1.4	0.13	0.23	1.3	(86)		
JZn-1 *	.	(99)	(208)	.	.	(114)	.	(24)	(21)	(19.5)	
Number	Lu	Mo	Nd	Ni	Pr	Rb	Sb	Sc	Se	Sm	Sn	Sr	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb
CGL 207	.	255.6	.	11.18	(0.938)	.	(3.24)	(5.65)	.	.	(0.450)	.	7.86	(1.52)
GBW 07237	0.08	2.8	0.92	5.5	0.30	(73)	1.1	0.33	2.3	0.36	6.1	.	0.10	0.17	(1.1)	0.49	0.05	.	.	3.4	4.5	0.42
JZn-1 *	.	.	.	(6)	.	(42)	(31)	(358)	(24)	.	.	.

CRM ZINC ORE - EXTENSIVE ANALYSIS ON CERTIFICATE

analysis listed in mass % except * which is mg/kg

Number	ZnO	Zn	Ag*	Au*	Cu	Pb	S	Units
IMS-485	95.37	.	(0.1)	.	(0.0020)	(0.0004)	.	100 g
OREAS 620	.	3.15	38.5	0.685	0.173	0.774	2.52	60 g

last

CRM ZINC ORE

analysis listed in mass % except * which is mg/kg

50 g units

Number	Zn	Al ₂ O ₃	As	CaO	Cu	F	Fe	K ₂ O	MgO	Na ₂ O	Pb	S	SiO ₂
NCS DC11050	44.05	0.21	0.74	0.81	1.216	0.054	15.77	0.059	0.059	0.013	0.088	31.37	0.81
NCS DC11049	41.72	0.24	1.80	0.69	0.130	0.012	14.03	0.037	0.418	0.009	0.74	29.47	4.13
NCS DC11051	37.08	1.51	1.75	1.06	1.04	0.43	15.33	0.55	0.264	0.090	0.077	27.43	8.02
NCS DC11052	31.23	2.66	2.80	1.35	0.88	0.80	14.78	0.97	0.46	0.163	0.067	24.08	15.15
NCS DC11053	25.87	3.64	3.69	1.52	0.73	1.15	14.72	1.33	0.62	0.24	0.060	21.47	21.04
NCS DC11054	20.33	4.56	4.46	1.76	0.59	1.38	14.36	1.68	0.76	0.29	0.048	18.12	25.96
NCS DC11055	10.38	6.55	6.18	2.15	0.32	1.92	13.78	2.40	1.06	0.39	0.032	12.55	36.84
NCS DC11056	15.30	5.57	5.46	1.93	0.46	1.66	14.00	2.07	0.92	0.35	0.040	15.38	31.71
NCS DC11057	0.31	8.52	7.91	2.55	0.047	2.48	12.99	3.07	1.38	0.52	0.013	6.80	48.03

continued analysis

Number	Ag	Au*	Bi	Cd	Co	Ge*	Hg	Mn	Sb	Se*	Sn
NCS DC11050	0.0090	0.27	0.019	0.242	0.00090	(0.3)	(0.00015)	0.069	0.009	(4)	0.065
NCS DC11049	0.021	(0.05)	0.00017	0.314	0.0051	(0.7)	0.0030	0.114	0.19	(3)	0.026
NCS DC11051	0.0076	0.27	0.017	0.203	0.0022	(0.5)	0.00015	0.067	0.0097	(4)	0.058
NCS DC11052	0.0067	0.27	0.015	0.170	0.0032	(0.5)	0.00013	0.063	0.011	(4)	0.052
NCS DC11053	0.0058	0.26	0.015	0.144	0.0043	(0.6)	0.00011	0.062	0.012	(4)	0.050
NCS DC11054	0.0047	0.27	0.014	0.107	0.0052	(0.6)	0.00009	0.063	0.013	(3)	0.044
NCS DC11055	0.0030	0.24	0.012	0.059	0.0070	(0.7)	0.000040	0.054	0.014	(3)	0.037
NCS DC11056	0.0039	0.25	0.013	0.085	0.0062	(0.7)	0.00007	0.057	0.013	(3)	0.041
NCS DC11057	0.0012	0.24	0.0101	0.0019	0.0089	(0.7)	0.000011	0.047	0.017	(2)	0.025

CRM ZINC ORE

Number	ZnO	CdO	Mn	PbO	LOI	Units
NCS HC35911	99.67	0.00066	0.000051	0.0019	(0.387)	30 g

CRM ZIRCONIUM ORE

analysis listed in mass %

Number	ZrO ₂	Al ₂ O ₃	CaO	F	FeO	Fe ₂ O ₃ (T)	H ₂ O+	HfO ₂	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	RE _x O _y *	SiO ₂	TiO ₂	LOI
NCS DC86316	4.68	(14.57)	0.63	0.027 (F-)	0.10	0.38	0.49	0.084	3.90	0.079	0.021	4.20	0.040	0.0515	70.73	0.64	0.56
NCS DC86308	1.25	14.70	2.64	0.082	1.82	4.69	1.29	0.025	3.31	2.01	0.083	3.74	0.167	0.022	65.66	0.410	1.51
NCS DC86307	0.187	14.74	2.70	0.080	1.83	4.80	1.35	0.00421	3.37	2.10	0.085	3.83	0.163	0.018	66.02	0.420	1.55

* RE_xO_y: Rare Earth Oxide

continued analysis listed in mg/kg

Number	CeO ₂	Dy ₂ O ₃	Er ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Ho ₂ O ₃	La ₂ O ₃	Lu ₂ O ₃	Nd ₂ O ₃	Pr ₆ O ₁₁	Sc ₂ O ₃	Sm ₂ O ₃	Tb ₄ O ₇	Th	Tm ₂ O ₃	W	Y ₂ O ₃	Yb ₂ O ₃	Units
NCS DC86316	146	14.9	16.4	0.55	9.92	3.66	69.2	6.11	53.4	15.7	10.7	10.1	2.02	202	2.84	5.01	142	25.9	50 g
NCS DC86308	74.4	4.6	4.6	1.2	(4.1)	1.3	37.9	1.5	26.9	7.8	14.8	4.9	0.74	15.2	0.92	.	41.9	7.8	50 g
NCS DC86307	70.7	2.8	1.8	1.2	3.4	0.59	36.6	0.38	27.5	7.7	14.1	4.7	0.53	7.8	0.31	.	19.5	2.2	50 g

ZIRCONIUM MATERIALS

CERAM: 25 or 100 g IGS: 50 g NCS: 20 g all others: 100 g units

Number	ZrO ₂	HfO ₂	ZrO ₂ + HfO ₂	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	TiO ₂	LOI	Other
CRM														
NCS HC26618	.	.	99.48	0.009	0.17	0.054	.	0.093	.	.	0.11	.	.	
BCS 358	92.70	1.63	.	0.08	1.50	0.065	.	3.42	.	.	0.21	0.20	0.08	BaO: 0.10 SrO: 0.07
VS K7/3	.	.	92.2	(0.1)	5.39	0.73	0.65	.	.	
VS K8/2	65.9	.	.	1.16	.	0.081	.	.	.	0.110	32.3	0.163	.	S: 0.0064
BCS 388	(64.9)	1.28	66.2	0.291	.	0.049	.	.	.	0.122	32.7	0.232	.	ThO ₂ :0.019 U ₃ O ₈ :0.034 Y ₂ O ₃ : 0.136
SARM 13	64.01	1.29	.	0.61	(0.14)	0.187	.	(0.0440)	.	0.23	32.56	0.295	.	Th:2 (0.0300) ³ U: (0.0328) ²
IGS 35	Zr:48.96 Hf:1.20	Ti:0.16	.	
RM														
CERAM 2CAS15	(63.6)	(1.28)	65.0	0.38	0.28	0.07	0.01	0.07	0.02	.	33.9	0.20	0.23	
CERAM AN46	15.41	0.32	15.68	30.52	0.20	0.85	1.03	5.34	0.15	.	45.46	0.48	0.08	Li ₂ O: 0.02
BCS 204A	.	.	53.8	0.74	0.15	0.18	0.017	0.012	0.014	0.77	37.6	2.22	0.50	SnO ₂ : 1.69

CRM ISO 17025 / 17034 ACCREDITED GEOLOGICAL SAMPLES analysis in mass %

Number	Type	Al	Al ₂ O ₃	Ca	CaO	Fe	T.Fe ₂ O ₃	K	K ₂ O	Mg	MgO	Mn	MnO	Na	Na ₂ O	P ₂ O ₅	Si	SiO ₂
MBH-ASC-21-P	ANORTHOSITE	16.1	30.5	11.0	15.4	1.04	1.48	0.064	0.077	0.78	1.29	0.0167	0.0216	1.57	2.12	.	22.2	47.4
MBH-AU-ORE1-21-P	GOLD ORE	2.90	5.48	2.39	3.35	1.64	2.35	0.60	0.72	0.85	1.41	0.0066	0.0085	(0.0400)	.	0.143	36.8	78.8
MBH-BAS-MC-22-P	BASALT	8.84	16.7	7.05	9.87	8.6	12.3	0.69	0.83	4.80	7.96	0.145	0.187	2.49	3.36	0.722	21.8	46.6
MBH-FCT-21-P	DACITE	8.52	16.1	2.55	3.57	3.32	4.74	3.20	3.86	0.84	1.40	0.081	0.104	2.72	3.67	0.225	30.1	64.4
MBH-NSC-21-P	NORITE	13.4	25.4	10.0	14.0	2.34	3.34	0.041	0.049	4.08	6.77	0.046	0.059	0.91	1.23	.	22.5	48.1

continued analysis in mass %

remainder analysis in mg/gkg except as noted

Number	Ti	TiO ₂	LOI	Ag	As	Au	Ba	Bi	C%	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu
MBH-ASC-21-P	0.035	0.058	(1.34)	.	.	.	32	.	.	(0.03)	1.56	6.2	56	.	17.4	0.206	(0.1)	0.22
MBH-AU-ORE1-21-P	0.167	0.278	(6.3)	0.21	1079	8.9	2311	0.199	(1.03)	0.96	41	4.5	45	3.76	29.9	2.47	1.34	0.7
MBH-BAS-MC-22-P	1.12	1.86	(0.6)	.	(3.6)	.	836	.	.	(0.09)	104	50	86	0.22	55	4.8	2.3	2.4
MBH-FCT-21-P	0.344	0.573	(1.2)	(0.05)	3.3	.	924	(0.1)	.	(0.07)	84	10.3	(5)	.	9	3.9	2.22	1.33
MBH-NSC-21-P	0.038	0.064	(0.78)	.	.	.	16.3	.	.	.	(1)	21.8	586	.	11.4	0.22	0.18	0.134

Number	Ga	Gd	Ge	Hf	Hg	Ho	La	Li	Lu	Mo	Nb	Nd	Ni	P	Pb	Pr	Rb	Re	S
MBH-ASC-21-P	15.7	(0.2)	.	0.07	.	(0.04)	(0.9)	2	(0.02)	(0.1)	.	(0.7)	36	(30)	(0.6)	(0.2)	0.93	.	.
MBH-AU-ORE1-21-P	6.4	3.1	(0.1)	3.9	11.4	0.47	23.7	30.5	0.19	10.4	5.5	19.5	30	620	6.9	5.2	33.6	(0.008)	1.65
MBH-BAS-MC-22-P	20	(6.2)	(0.6)	3.6	.	0.9	53.5	(7.6)	(0.31)	1.6	42	47	91	3150	5.7	12	9.1	.	(140)
MBH-FCT-21-P	18.5	4.6	.	5.6	.	0.74	44.2	19.5	0.33	(0.7)	15.2	34.7	(4)	980	16	9.5	104	.	.
MBH-NSC-21-P	12.1	0.19	.	(0.1)	.	(0.05)	0.52	1.4	(0.05)	.	(0.2)	(0.5)	158	(30)	(0.3)	(0.1)	0.86	.	.

Number	Sb	Sc	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	U	V	W	Y	Yb	Zn	Zr	Units
MBH-ASC-21-P	.	4.4	(0.2)	.	151	.	(0.03)	24	.	1.18	(0.1)	9.5	(2.3)	75 g
MBH-AU-ORE1-21-P	106	4.3	3.6	2.6	35	0.38	0.43	0.29	5.6	17.7	4.9	136	32	15.1	1.23	90	153	200 g
MBH-BAS-MC-22-P	(0.08)	27.1	7.8	(1.3)	978	2.13	0.85	.	6	.	1.4	247	(0.32)	24.4	2	102	158	75 g
MBH-FCT-21-P	(0.3)	8.1	6	1.7	526	1.02	0.66	.	10.8	(0.4)	3.6	69	(0.6)	21.8	2.2	68	209	75 g
MBH-NSC-21-P	.	11	0.13	.	97	.	(0.03)	.	(0.09)	.	(0.04)	44	.	1.37	(0.2)	17.9	2.8	75 g

CRM ISO 17025 / 17034 ACCREDITED RARE EARTH ORE

= class where 1 = CRM and 2 = RM analysis listed in mass %

2	Number	Al	Al ₂ O ₃	Ba	BaO	C	CO ₃	Ca	CaO	Ce	CeO ₂	Dy	Eu	Fe	Fe ₂ O ₃	Ho
2	MBH REE-HI-22-P	0.18	0.33	8.9	9.9	.	.	23.7	33.1	1.9	2.30	0.0025	0.0050	0.93	1.3	0.00033
2	MBH REE-LO-22-P	0.16	0.31	0.67	0.75	.	.	35.94	50.3	0.14	0.18	0.00026	0.00042	0.20	0.29	0.000038
2	MBH REE-MID-22-P	0.15	0.29	1.7	1.9	.	.	34.4	48.1	0.37	0.45	0.00056	0.0010	0.030	0.42	0.000076
1	MBH REE-ORE1-22-P	0.21	0.39	17.8	19.9	4.8	24	10.2	14.3	3.7	4.5	0.0049	0.0100	1.73	2.47T	0.00056

Number	K	K ₂ O	La	La ₂ O ₃	Lu	Mg	MgO	Mn	MnO	Nb	Nd	Nd ₂ O ₃	P	P ₂ O ₅	Pb
MBH REE-HI-22-P	0.093	0.110	1.3	1.5	0.000060	1.8	3.0	0.18	0.23	0.0023	0.45	0.52	0.13	0.30	0.1990
MBH REE-LO-22-P	0.029	0.035	0.10	0.12	0.000007	1.7	2.8	0.028	0.037	0.00025	0.034	0.040	0.041	0.095	0.0149
MBH REE-MID-22-P	0.038	0.045	0.26	0.30	0.000015	1.7	2.9	0.047	0.061	0.00053	0.089	0.10	0.053	0.12	0.0383
MBH REE-ORE1-22-P	0.154	0.186	2.64	3.1	0.000104	1.93	3.2	0.333	0.43	0.0043	0.91	1.06	0.223	0.51	(0.4100)

Number	Pr	Pr ₆ O ₁₁	Rb	RE _x O _y	S	Sc	Si	SiO ₂	Sm	SO ₃	SO ₄	Sm ₂ O ₃
MBH REE-HI-22-P	0.16	0.2	0.00038	4.50	2.7	0.00057	3.3	7.2	0.0303	6.6	.	.
MBH REE-LO-22-P	0.013	0.015	0.00015	0.35	0.20	0.00085	0.88	1.9	0.0024	0.49	.	.
MBH REE-MID-22-P	0.031	0.038	0.00017	0.89	0.51	0.00015	1.2	2.6	0.0061	1.3	.	.
MBH REE-ORE1-22-P	0.34	0.41	0.0006	.	5.2	0.0010	6.1	13.1	0.064	.	15.6	0.074

Number	Sr	SrO	Th	Ti	TiO ₂	U	Y	Yb	LOI	Units
MBH REE-HI-22-P	1.6	1.90	0.0127	0.012	0.021	0.0017	0.0089	0.00041	30.4	90 g
MBH REE-LO-22-P	0.19	0.22	0.00098	0.012	0.019	0.00018	0.0010	0.000050	42.1	90 g
MBH REE-MID-22-P	0.38	0.44	0.0025	0.012	0.019	0.00039	0.0021	0.000098	40.4	90 g
MBH REE-ORE1-22-P	3.1	3.7	0.0246	0.015	0.025	0.0034	0.0165	0.00072	17.5	100 g

CRM		ISO 17025 / 17034 ACCREDITED GEOLOGICAL SAMPLES										analysis in mass %		50 g units					
Number	Type	Al ₂ O ₃	C	CaO	Fe ₂ O ₃	H ₂ O	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	SiO ₂	TiO ₂	LOI				
AC18.10657	Basalt	14.23	(0.068)	8.42	11.34	(1.07)	0.901	7.20	0.145	3.08	0.332	0.0142	51.05	1.80	(1.26)				
AC18.10658	Ophiolite	13.02	(0.453)	10.60	13.14	(0.6)	0.115	6.69	0.208	2.64	0.122	0.1968	47.19	1.20	4.76				
AC18.10659	Gabbro	16.65	(0.032)	9.32	10.40	(0.56)	2.07	5.10	0.166	2.58	0.421	(0.014)	51.68	1.27	(0.184)				
AC18.10660	Flagstone	11.37	(2.31)	6.13	5.48	(0.56)	2.85	5.94	0.0931	1.32	0.200	0.0406	55.46	0.829	10.54				
AC18.10661	Andesite	16.70	(0.130)	5.62	6.14	(1.73)	0.763	3.27	0.0885	4.27	0.233	(0.011)	57.67	0.713	4.90				
AC18.10662	Granodiorite	14.65	(0.092)	2.515	4.654	(0.64)	3.524	1.410	0.0514	2.658	0.203	0.0972	67.75	0.661	1.19				
AC18.10663	Siltstone	16.24	(0.013)	0.070	4.128	(0.68)	3.174	0.669	0.0042	0.227	0.0783	(0.012)	69.99	0.822	3.83				
continued analysis listed in mg/kg																			
Number	Ag	As	Au	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu	F
AC18.10657	<5	<0.5	<0.002	<50	261	1.27	<2	<0.5	<10	36.7	(102)	46.1	252	0.82	52	4.42	2.25	1.66	(195)
AC18.10658	<5	<5	<0.002	<50	75	<5	<2	<0.5	<10	10.6	.	47.7	110	(0.32)	164	4.25	2.73	0.92	(129)
AC18.10659	<5	<5	<0.002	<50	560	1.90	<0.1	<0.5	<10	51	(248)	33.8	104	5.37	64	4.24	2.30	1.68	(262)
AC18.10660	<5	20.3	<0.002	184	345	2.09	1.02	<0.5	<10	62.3	.	13.4	65	6.94	29.1	4.96	2.83	1.16	(809)
AC18.10661	<5	<5	<0.002	<50	292	0.98	<2	<0.5	<10	32.8	.	18.6	66	0.83	47.9	3.47	1.99	1.11	(238)
AC18.10662	<5	7.6	<0.002	24.4	1036	2.42	0.93	<0.5	<10	82.5	(110)	9.7	58	12.03	24.9	6.40	3.26	1.50	(725)
AC18.10663	<5	501	(0.025)	1520	707	3.33	22.5	<0.5	<10	102.2	.	2.08	119	11.81	33	5.87	3.40	1.41	(662)
Number	Ga	Gd	Ge	Hf	Hg	Ho	In	Ir	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb	Re
AC18.10657	19.6	5.26	1.29	(3.57)	<1	0.83	<0.2	<0.005	18.29	(76.2)	0.24	<5	20.6	20.3	146	(5.85)	4.55	22.5	<0.1
AC18.10658	16.1	3.65	1.12	(1.88)	<1	0.89	<0.2	<0.005	4.34	9.72	0.40	<1	3.41	8.61	64	(3.88)	1.62	(2.25)	<0.1
AC18.10659	20.5	5.26	1.66	(2.63)	<1	0.80	<0.2	<0.005	24.6	15.9	0.309	<5	7.55	28.0	45.4	(11.1)	6.56	102	<0.1
AC18.10660	15.8	5.57	1.80	(5.56)	<1	0.95	<0.2	<0.005	32.5	58.2	0.37	<1	10.8	29.3	23.9	20.4	7.65	129.8	<0.1
AC18.10661	18.1	3.92	1.02	(3.34)	<1	0.656	<0.2	<0.005	15.3	15.9	0.285	<5	3.71	18.9	31.3	(10.3)	4.27	17.43	<0.1
AC18.10662	20.3	7.56	1.68	7.0	<1	1.17	<0.2	<0.005	41.9	54.7	0.403	<5	11.8	38.4	(20.9)	30.9	9.91	174.8	<0.1
AC18.10663	21.8	6.44	2.04	(7.62)	<1	1.18	<0.2	<0.005	52.0	48.1	0.47	<5	16.4	41.9	(17.7)	22.6	11.57	150.2	<0.1
Number	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
AC18.10657	<0.1	19.4	<3	5.03	(1.80)	399	1.24	0.78	<1	2.93	<0.5	0.297	0.74	164	<5	21.7	1.76	110	138
AC18.10658	<2	41.2	<3	2.73	<200	126	<5	0.62	<1	0.46	<0.5	0.38	<5	338	<5	23.5	2.57	97	72
AC18.10659	<0.1	25.0	<3	5.90	2.23	578	<5	0.70	<1	8.22	<0.5	0.32	1.80	286	<5	22.0	2.11	96	94
AC18.10660	<2	11.60	<3	5.94	3.88	121.9	<5	0.81	<1	13.44	0.51	0.406	2.41	89.1	<20	26.7	2.64	76.9	197
AC18.10661	<2	15.5	<3	4.06	<200	634	<5	0.56	<1	1.81	<0.5	0.272	0.53	130	<5	18.3	1.85	79.3	127
AC18.10662	<2	8.4	<3	8.1	4.9	157.9	<5	1.10	<1	16.30	0.98	0.446	4.85	65	13.5	32.4	2.82	89.2	244
AC18.10663	6.19	15.8	<3	7.43	19.5	78.0	1.35	0.96	<1	18.35	0.831	0.507	3.44	113.5	93	31.4	3.23	42	238

CRM SOIL WITH EXTENSIVE ANALYSIS - CONTINUED ON THE NEXT PAGE

analysis listed in mass %															70 g units	
Number	Al ₂ O ₃	C	CaO	CO ₂	Org.C	T.Fe ₂ O ₃	FeO	H ₂ O	K ₂ O	MgO	Na ₂ O	S	SiO ₂	Ti	LOI	
NCS DC73058	14.84	2.29	1.39		2.07	5.13	(1.1)	4.90	2.72	1.24	1.73	0.0227	62.32	0.476	(9)	
NCS DC73059	13.21	1.03	2.18	(1.1)	0.76	4.98	1.32	3.13	2.51	2.07	1.95	0.0124	66.74	0.457	5.16	
NCS DC73060	12.70	1.68	1.18		1.51	8.29	1.39	5.03	1.83	0.92	0.13	0.0401	65.60	0.41	7.92	
NCS DC73061	11.04	1.82	0.36		1.63	3.84	(1.1)	4.31	1.76	0.42	0.26	0.0494	73.80	0.425	7.16	
NCS DC73062	12.10	2.25	6.42	4.48	1.06	4.52	(1.5)	3.89	2.46	2.34	1.68	0.0279	59.83	0.392	9.42	
NCS DC73063	11.92	2.35	9.33	6.89	0.52	4.40	1.74	3.67	3.11	3.20	1.83	0.27	53.97	0.313	(10.9)	
NCS DC73064	11.90	2.59	8.03	6.13	0.95	4.47	(1.5)	3.86	2.44	2.70	1.54	0.0348	56.71	0.348	(10.9)	
NCS DC73065	10.54	1.73	4.82	3.70	0.78	4.00	1.56	3.31	2.18	2.79	1.60	0.0368	65.49	0.280	7.70	
NCS DC73066	9.89	0.81	3.00	(1.8)	0.38	2.63	0.64	2.25	2.57	1.04	1.73	0.0141	74.15	0.240	4.31	
NCS DC73067	16.12	2.96	1.23	.	2.75	4.27	(1.71)	.	2.87	1.16	2.42	0.0351	60.21	0.442	(10.57)	
NCS DC73068	12.73	1.41	1.19	.	1.34	2.99	(0.89)	.	2.99	0.73	2.36	0.0229	70.86	0.355	(5.15)	
NCS DC73069	14.23	0.72	1.06	.	0.68	3.96	(0.58)	.	3.27	0.94	1.83	0.0104	68.47	0.336	(5.51)	
NCS DC73070	8.65	0.32	0.73	.	0.28	1.44	(0.64)	.	3.02	0.43	1.82	0.0107	81.68	0.189	(1.59)	
NCS DC73071	13.47	2.02	6.69	.	0.69	5.78	(1.95)	.	2.70	4.18	1.90	0.0000369	53.00	0.361	(11.45)	
NCS DC73072	12.54	0.85	2.59	.	0.71	3.36	(1.52)	.	2.57	1.63	3.21	0.0000213	68.33	0.290	(4.57)	
NCS DC73073	13.70	1.30	5.47	.	0.54	4.84	(1.39)	.	2.69	2.64	2.81	0.0000123	58.84	0.374	(7.41)	
NCS DC73074	11.69	1.95	7.28	.	0.55	3.79	(1.85)	.	2.59	2.38	2.15	(0.0206)	60.93	0.311	(8.31)	
NCS DC73075	11.20	2.44	9.44	.	0.48	3.96	(1.71)	.	2.42	2.61	1.88	0.0262	57.08	0.316	(10.46)	
NCS DC73076	13.03	0.99	4.42	.	0.34	4.08	(0.79)	.	2.70	2.37	2.07	0.0315	63.89	0.298	(6.37)	
NCS DC73077	9.54	3.81	15.26	.	0.44	3.46	(0.86)	.	2.09	1.98	1.01	0.0324	49.83	0.273	(16.17)	
NCS DC73078	13.50	0.80	3.46	.	(0.12)	5.70	(0.69)	.	2.24	1.82	0.54	(0.0087)	64.37	0.394	(7.18)	
NCS DC73079	11.48	0.91	4.22	.	0.17	4.46	(1.35)	.	2.16	1.50	1.44	(0.0073)	68.11	0.351	(5.69)	
NCS DC73080	12.15	0.69	1.95	.	0.66	3.15	(1.10)	.	2.50	0.97	2.29	0.0132	73.16	0.282	(2.72)	
NCS DC73081	10.74	1.70	6.62	.	0.30	4.31	(1.83)	.	2.12	3.09	1.72	0.0000229	61.47	0.334	(8.85)	
NCS DC73082	10.58	1.69	6.28	.	0.36	3.70	(1.69)	.	2.03	1.77	2.10	0.0291	65.18	0.313	(7.49)	
NCS DC73083	11.91	2.12	3.88	.	1.45	4.22	(1.23)	.	2.26	1.78	1.75	0.0322	65.27	0.407	(7.71)	
NCS DC73084	12.47	1.91	7.12	.	0.52	4.67	(1.26)	.	2.40	2.35	1.61	0.0173	58.76	0.385	(9.55)	
NCS DC73085	14.10	1.60	1.43	.	1.50	5.45	(1.53)	.	2.41	1.70	1.62	0.0286	65.32	0.461	(6.77)	
NCS DC73086	12.23	0.60	1.23	.	0.59	4.78	(0.74)	.	2.12	1.15	1.32	0.0119	71.11	0.470	(4.62)	
NCS DC73087	10.57	1.27	0.81	.	1.23	3.62	(1.09)	.	1.60	0.69	1.51	0.0216	74.76	0.500	(5.09)	
NCS DC73088	16.06	2.33	1.22	.	2.23	4.14	(1.90)	.	2.59	2.09	0.99	0.0459	62.03	0.537	(9.35)	
NCS DC73089	12.80	1.41	5.66	.	0.42	4.21	(0.62)	.	2.31	1.43	1.44	0.0170	62.62	0.344	(8.58)	
NCS DC73090	13.71	0.46	0.95	.	0.45	4.85	(0.74)	.	2.48	1.66	1.41	0.0119	68.21	0.434	(5.84)	
NCS DC73091	13.84	0.48	1.37	.	0.34	5.67	(0.65)	.	2.19	1.21	0.85	(0.0102)	67.62	0.539	(5.69)	
NCS DC73092	22.66	(0.25)	(0.06)	.	(0.23)	5.46	(0.62)	.	3.19	0.57	(0.09)	(0.0094)	58.51	0.445	(8.09)	
NCS DC73093	24.45	(0.28)	(0.18)	.	(0.23)	10.94	(0.46)	.	1.65	1.19	(0.13)	0.0184	48.80	0.556	(11.36)	
NCS DC73094	22.48	(0.2)	0.59	.	(0.15)	6.75	(1.31)	.	1.98	2.02	0.62	(0.0107)	56.28	0.505	(7.57)	
NCS DC73095	21.67	0.78	0.46	.	(0.63)	11.5	(0.91)	.	1.49	1.55	(0.13)	(0.0176)	49.13	1.05	(11.49)	
NCS DC73096	18.03	0.41	(0.1)	.	0.40	4.67	(0.48)	.	0.46	0.21	(0.06)	0.0271	67.23	0.424	(8.15)	
NCS DC73097	13.87	(0.2)	(0.13)	.	(0.19)	6.64	(0.54)	.	0.82	0.29	(0.06)	0.0247	71.18	0.465	(6.29)	
NCS DC73098	15.79	1.71	0.69	.	1.63	6.44	(1.90)	.	2.48	1.75	0.46	0.0284	62.60	0.655	(8.40)	
NCS DC73099	11.86	0.57	0.34	.	0.53	2.99	(0.73)	.	2.61	0.31	0.26	0.0120	75.50	0.372	(4.92)	
NCS DC73100	7.77	1.02	0.26	.	0.96	2.54	(0.66)	.	2.03	0.35	0.57	0.0158	81.70	0.413	(3.72)	
NCS DC73101	14.25	0.28	0.30	.	0.26	6.46	(0.65)	.	1.69	0.68	0.42	0.0174	68.94	0.662	(5.90)	
NCS DC73102	18.65	(0.11)	(0.04)	.	(0.11)	4.37	(0.30)	.	2.03	0.44	(0.08)	0.0119	66.91	0.229	(7.09)	
NCS DC73103	17.99	(0.24)	0.38	.	(0.23)	3.82	(0.91)	.	1.48	0.33	0.14	0.0222	67.75	0.397	(7.19)	
NCS DC73104	6.16	(0.17)	(0.15)	.	(0.15)	1.58	(0.37)	.	0.21	0.18	(0.08)	0.0107	88.45	0.343	(3.06)	
Number	Al ₂ O ₃	C	CaO	CO ₂	Org.C	T.Fe ₂ O ₃	FeO	H ₂ O	K ₂ O	MgO	Na ₂ O	S	SiO ₂	Ti	LOI	

CRM SOIL WITH EXTENSIVE ANALYSIS - CONTINUED ON THE NEXT PAGE

continued analysis listed in mg/kg

70 g units

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu
NCS DC73058	0.088	12.4	39	639	2.7	0.38	8.5	0.098	82	53	16.0	69	7.9	23.0	5.6	3.2	1.4
NCS DC73059	0.093	9.3	56	679	2.23	0.31	2.4	0.33	70	48	15.5	72	6.4	31	5.2	2.9	1.4
NCS DC73060	2.3	323	85	255	16.3	301	3.3	2.8	111	44	9.5	62	26	173	7.8	4.6	1.27
NCS DC73061	0.157	12.9	131	314	2.2	0.63	7.0	0.2	82	85	(5.9)	60	7.7	25.3	5.2	2.9	1.29
NCS DC73062	0.086	13.1	57	502	2.06	0.37	4.2	0.31	74	75	12.6	69	7.6	28	5.2	2.9	1.27
NCS DC73063	0.077	13.2	58	557	2.55	0.42	2.3	0.174	70	209	11.0	48	8.6	24	5.1	2.9	1.2
NCS DC73064	0.072	14.2	61	505	2.02	0.36	4.3	0.186	66	113	12.6	67	8.1	25.6	4.6	2.6	1.15
NCS DC73065	0.060	11.4	46	564	1.68	0.25	2.3	0.121	51	91	12.0	84	5.1	24.1	3.6	2.0	0.98
NCS DC73066	0.053	13.5	31	615	1.54	0.22	5.2	0.057	41	72	7.5	38	4.1	23.7	2.9	1.6	0.84
NCS DC73067	0.114	8.3	20	715	2.9	0.37	5.2	0.127	85	53	11.3	48	9.6	12.9	4.8	2.6	1.31
NCS DC73068	0.081	6.0	23	657	2.4	0.24	1.9	0.074	60	56	7.4	38	6	12.6	4.1	2.4	1.13
NCS DC73069	0.068	7.6	28	761	2.2	0.27	3.2	0.078	60	45	10.9	50	6	17.2	4.2	2.44	1.08
NCS DC73070	0.049	3.9	13.2	544	1.6	0.11	1.5	0.042	26	42	3.8	(23)	3.4	(6.4)	1.94	1.17	0.58
NCS DC73071	0.084	19.9	68	614	2.22	0.38	3.4	0.18	64	0.345	18.6	113	8.4	40.3	4.5	2.6	1.16
NCS DC73072	0.059	3.6	47	357	3.2	0.46	11.8	0.108	62	574	8.9	47	7.6	16.9	6.3	3.6	1.34
NCS DC73073	0.084	10.0	37	468	2.2	0.33	2.4	0.19	58	871	12.9	55	6.1	28	5.3	3.07	1.2
NCS DC73074	(0.065)	12.1	60	483	2.2	0.43	2.1	0.138	57	125	10.1	55	12.7	19.8	4.2	2.3	1.05
NCS DC73075	0.069	17.1	54	503	2.0	0.27	1.8	0.160	56	156	11.0	57	14.8	22	4.2	2.40	1.03
NCS DC73076	0.067	21.2	58	457	2.7	0.38	2.1	0.130	58	116	13.4	110	16.3	22	3.8	2.1	1.02
NCS DC73077	0.059	16.8	74	356	1.7	0.25	4.0	0.109	48	57	10.4	70	20.3	18.6	3.07	1.75	0.86
NCS DC73078	0.075	6.8	40	341	2.1	0.29	(0.77)	0.066	69	428	12.9	82	9.0	16.2	4.3	2.45	1.23
NCS DC73079	0.055	15.2	68	383	2.6	0.29	(0.7)	(0.08)	75	(32)	11.7	74	15.5	24	4.0	2.0	1.3
NCS DC73080	0.085	5.7	27	431	2.4	0.31	1.4	0.18	79	71	7.6	34	8.8	16.0	4.7	2.6	1.19
NCS DC73081	(0.07)	12.3	42	572	1.57	0.25	1.5	0.146	55	480	12.6	80	4.8	27.0	4.1	2.3	1.05
NCS DC73082	0.053	14.3	51	429	1.7	0.27	1.6	0.113	54	633	9.6	48	5.9	21	3.9	2.2	1.01
NCS DC73083	0.080	9.1	60	492	1.94	0.34	4.6	0.18	69	141	11.6	64	5.6	57	4.8	2.8	1.22
NCS DC73084	0.071	12.8	49	513	2.07	0.33	3.8	0.156	68	66	13.5	70	8.0	25	4.7	2.7	1.2
NCS DC73085	0.098	13.0	56	600	2.5	0.45	1.8	0.29	80	58	16.1	85	8.7	32.5	5.6	3.2	1.42
NCS DC73086	0.074	11.0	62	509	2.0	0.36	3.6	0.104	76	41	15.0	90	6.9	25.4	5.4	3.1	1.28
NCS DC73087	0.131	6.6	70	435	1.88	0.38	3.0	0.171	88	73	10.9	59	5.3	62	5.5	3.1	1.36
NCS DC73088	0.122	5.0	65	570	2.38	0.45	1.8	0.28	81	65	15.1	(448)	9.6	31	5.5	3.1	1.41
NCS DC73089	0.115	8.9	53	605	2.2	0.31	2.6	0.166	69	58	12.4	66	9.6	27.1	4.6	2.5	1.24
NCS DC73090	0.077	3.9	41	585	2.1	0.29	(1)	0.131	75	55	14.4	63	6.2	26.2	4.3	2.46	1.19
NCS DC73091	0.060	11.7	80	517	2.5	0.35	1.5	0.131	95	(39)	16.7	83	7.7	29.4	6.2	3.4	1.57
NCS DC73092	(0.028)	5.4	14.8	652	2.6	0.28	2.8	(0.03)	121	(33)	15.4	31	11.6	(5)	3.0	1.57	1.16
NCS DC73093	0.071	37	52	297	2.5	0.91	(1.9)	0.104	81	(50)	16.8	121	18.3	59	5.4	3.3	1.25
NCS DC73094	0.087	7.5	88	285	4.7	0.62	(0.8)	0.36	95	(30)	21.9	95	10.3	37.2	7.9	4.6	1.87
NCS DC73095	0.088	33	125	259	2.6	1.00	10.4	0.69	176	(34)	30.3	166	17.3	76	6.3	3.8	1.27
NCS DC73096	0.041	3.8	13.4	(74)	1.89	2.1	2.9	(0.035)	90	49	8.8	37	4.0	16.0	1.7	0.94	0.49
NCS DC73097	(0.049)	18.1	74	171	1.40	1.22	(1.4)	0.114	92	42	6	67	3.8	25.8	2.77	1.71	0.69
NCS DC73098	0.128	35.6	144	615	3.0	0.86	2.7	0.30	94	64	17.6	118	12.4	41	6.0	3.2	1.55
NCS DC73099	0.105	8.1	43	383	2.5	0.69	2.9	0.098	91	46	7	34	7.8	15.1	5.1	3.1	0.90
NCS DC73100	0.076	5.4	74	457	1.66	0.35	1.4	0.17	73	62	5.0	27	6.2	18.3	6.2	3.6	1.08
NCS DC73101	0.085	13.0	60	382	2.13	0.30	(0.75)	0.21	75	39	23.4	(75)	7.3	40	5.8	3.3	1.50
NCS DC73102	(0.042)	7.7	12.8	376	1.8	0.18	(1)	0.042	74	46	13.4	(20)	7.2	(8.9)	8.0	4.6	1.60
NCS DC73103	0.098	13.9	59	184	3.0	1.5	2.4	0.055	79	(53)	5.0	42	13.2	(8)	5.1	(3.2)	0.67
NCS DC73104	(0.028)	3.5	37	(47)	(0.4)	0.35	4.4	.	17.6	34	1.79	31	2.7	9.5	1.39	0.9	0.19
Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cs	Cu	Dy	Er	Eu

CRM SOIL WITH EXTENSIVE ANALYSIS - CONTINUED ON THE NEXT PAGE

continued analysis listed in mg/kg

70 g units

Number	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mn	Mo	N	Nb	Nd
NCS DC73058	455	19.4	6.2	1.39	8.3	0.034	1.12	3.49	0.066	41	35.1	0.50	923	0.68	1799	16.3	37.0
NCS DC73059	603	17.4	5.8	1.39	7.3	0.056	1.04	0.97	0.063	37	34.5	0.43	674	1.11	874	16.9	33.2
NCS DC73060	3069	24	8.0	2.3	7.9	0.24	1.55	3.42	2.3	55	73.6	0.78	1675	12.2	1442	21.4	45.9
NCS DC73061	577	15.2	6.0	1.50	8.3	0.075	1.04	2.93	0.080	42	26.1	0.44	119	3.2	1708	14.9	36.0
NCS DC73062	690	15.4	5.8	1.29	7.4	0.081	1.04	2.30	0.056	38	35.8	0.45	666	0.98	(1191)	13.7	34.3
NCS DC73063	954	17.1	5.5	1.15	5.5	0.015	1.03	1.59	0.062	36	42.6	0.44	721	1.32	606	15.5	31.8
NCS DC73064	675	15.6	5.2	1.21	5.7	0.035	0.91	2.04	0.055	34	40.2	0.40	661	0.78	987	12.5	30.1
NCS DC73065	530	12.8	3.9	1.20	4.0	0.027	0.72	1.33	0.044	26	24.8	0.32	590	0.72	840	10.0	23.1
NCS DC73066	313	11.4	3.1	1.19	5.8	0.018	0.58	2.04	0.031	22	18.1	0.28	399	0.66	440	7.9	18.8
NCS DC73067	603	21.7	5.8	1.26	7.4	0.055	0.94	1.9	0.061	44.6	50	0.41	0.107	2.08	0.247	16.7	38
NCS DC73068	365	15.6	4.5	1.25	9.3	0.019	0.84	0.70	0.044	31.8	27	0.40	505	0.86	0.111	13.4	28.1
NCS DC73069	357	17.5	4.5	1.33	5.6	0.024	0.85	2.33	0.052	31.5	25	0.40	700	0.5	692	12.9	27.1
NCS DC73070	(164)	10.2	2.0	1.06	5.6	0.014	0.40	0.63	0.019	14.4	13.2	0.21	230	0.38	351	7.4	12.1
NCS DC73071	750	17.5	4.9	1.29	4.1	0.031	0.90	2.0	0.063	34.0	39.3	0.40	879	1.92	592	12.8	29.2
NCS DC73072	511	15.5	6.3	1.33	6.3	0.009	1.30	1.9	0.051	34	29	0.56	550	0.99	808	11.2	33.4
NCS DC73073	589	17.4	5.2	1.28	4.9	0.012	1.09	1.7	0.061	30	31	0.52	800	(1.1)	637	12.0	28.2
NCS DC73074	697	15.1	4.6	1.26	5.2	0.02	0.85	0.76	0.059	30	50	0.35	564	0.68	605	13.5	26.2
NCS DC73075	617	14.4	4.5	1.15	4.9	0.029	0.85	1.08	0.050	30	38	0.36	592	0.86	552	12.1	25.6
NCS DC73076	471	15.5	4.1	1.3	4.9	0.025	0.75	1.42	0.046	31	37	0.34	559	0.63	(540)	11.1	25
NCS DC73077	613	12.1	3.4	1.15	4.0	0.028	0.62	2.6	0.039	26	40	0.28	532	0.42	639	10.0	21.3
NCS DC73078	535	16.7	5.0	1.37	5.4	0.011	0.86	0.41	0.053	37.0	39	0.39	669	0.43	356	12.8	31.1
NCS DC73079	403	15	5.2	1.48	5.2	0.015	0.76	(0.44)	0.048	38	46	0.29	496	0.53	366	12.0	33.8
NCS DC73080	422	14.6	5.5	1.24	8.4	0.101	0.94	0.65	0.042	41	22.0	0.38	627	0.62	655	12.5	34.3
NCS DC73081	526	13.4	4.4	1.20	5.2	0.018	0.82	0.90	0.049	28.8	25.2	0.38	626	0.85	276	11.1	25.5
NCS DC73082	459	12.9	4.2	1.20	5.8	0.019	0.79	1.01	0.044	28	30	0.33	509	0.60	418	10.6	24.6
NCS DC73083	537	14.8	5.3	1.32	8.4	0.069	0.97	1.9	0.051	36	33.8	0.44	572	0.79	0.146	14.3	32
NCS DC73084	653	16.0	5.2	1.29	5.7	0.025	0.95	2.0	0.055	36	38	0.42	659	(0.74)	665	13.7	30.5
NCS DC73085	622	18.3	6.2	1.47	7.0	0.161	1.12	0.95	0.065	42	43	0.48	701	0.79	1490	15.9	36.6
NCS DC73086	431	15.1	5.7	1.42	9.8	0.049	1.08	1.5	0.051	39	31.8	0.48	878	0.50	666	15.7	33.6
NCS DC73087	402	13.3	6.1	1.37	9.5	0.134	1.10	1.05	(0.057)	44	29.0	0.47	479	0.58	0.124	17.7	38
NCS DC73088	649	20.5	5.8	1.50	7.0	0.19	1.11	0.56	0.077	41	57	0.49	519	0.66	0.239	16.4	36
NCS DC73089	588	16.6	5.2	1.3	5.8	0.21	0.90	1.51	0.052	38	43	0.40	632	0.64	682	13.1	32
NCS DC73090	531	18.0	4.9	1.39	7.0	0.044	0.87	(0.61)	0.054	40.0	35.6	0.39	749	0.32	591	15.1	31.8
NCS DC73091	532	18.2	7.0	1.55	9.4	0.056	1.22	2.3	0.063	49	42.7	0.51	816	0.67	492	18.7	42
NCS DC73092	540	30.9	5.0	1.01	9.3	0.062	0.56	4.6	0.062	60	24.8	0.23	123	0.67	(261)	19.9	41.8
NCS DC73093	909	32.3	5.8	2.1	5.7	0.33	1.12	2.2	0.122	49	96	0.54	318	3.2	762	19.3	38
NCS DC73094	1250	29.1	8.4	2.22	5.1	0.069	1.6	0.7	0.106	57	106	0.68	919	0.43	696	21.4	45
NCS DC73095	0.162	30.0	6.6	1.78	12.6	0.25	1.30	8.0	0.120	57	76	0.62	0.398	2.7	867	35	39
NCS DC73096	212	21.7	2.4	1.6	8.6	0.053	0.35	5.3	0.069	21.3	23.8	0.17	189	7.3	309	23.2	16.2
NCS DC73097	250	19.5	3.3	2.3	(8.9)	0.047	0.58	3.4	0.101	30.6	13.0	0.32	247	1.35	218	17.6	22.0
NCS DC73098	635	21.9	6.9	1.47	7.8	0.060	1.16	1.25	0.089	47	33	0.44	648	1.01	0.146	20.6	40
NCS DC73099	362	16.0	5.2	1.39	15.5	0.099	1.03	4.1	0.069	42	27.7	0.53	387	0.92	506	21.8	32.5
NCS DC73100	254	11.2	5.8	1.59	14.7	0.038	1.26	0.56	0.048	38	14	0.59	311	0.38	960	17.2	31.6
NCS DC73101	466	18.4	6.1	1.6	7.8	0.055	1.17	1.75	0.069	38	37	0.52	1230	0.44	555	17.7	34.3
NCS DC73102	218	21.0	7.7	1.52	(5.6)	0.032	1.62	3.1	0.052	52	15.0	0.73	435	1.23	(114)	11.7	40.9
NCS DC73103	485	25.2	5.0	1.83	10.8	0.100	1.1	2.9	0.093	46	45	(0.55)	116	1.84	267	35	31
NCS DC73104	134	10.7	1.09	1.28	8.2	0.031	0.31	5.7	0.038	10.3	13.2	0.17	(62)	1.17	198	13.2	6.6
Number	F	Ga	Gd	Ge	Hf	Hg	Ho	I	In	La	Li	Lu	Mn	Mo	N	Nb	Nd

CRM SOIL WITH EXTENSIVE ANALYSIS - CONTINUED ON THE NEXT PAGE

continued analysis listed in mg/kg

70 g units

Number	Ni	P	Pb	Pr	Rb	Re	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl
NCS DC73058	31.0	752	26.6	9.6	124	.	0.80	12.6	0.36	7.1	3.4	186	1.26	1.00	0.049	13.6	0.73
NCS DC73059	33.8	729	22.2	8.5	100	.	0.87	13.1	0.23	6.3	3.1	151	1.27	0.94	(0.05)	11.2	0.58
NCS DC73060	22.3	806	727	12.5	206	.	18.2	11.4	1.3	9.0	411	26.3	2.63	1.34	(1.6)	23.9	2.13
NCS DC73061	17.1	1249	27.0	9.4	94	.	1.1	11.1	1.2	6.6	6.0	80.1	1.26	0.93	(0.05)	13.9	0.81
NCS DC73062	31.3	1278	25	8.7	101	.	1.16	11.8	0.19	6.5	3.0	203	1.12	0.93	0.039	13.0	0.59
NCS DC73063	25.4	924	24.3	8.2	129	.	0.95	9.9	0.21	6.0	3.8	315	1.39	0.90	0.036	14.1	0.70
NCS DC73064	31.7	1121	23.1	7.7	101	.	1.18	11.8	0.25	5.7	2.7	297	1.02	0.82	(0.04)	12.0	0.60
NCS DC73065	38.4	718	19.5	6.0	86	.	1.01	10.7	0.26	4.4	2.1	221	0.85	0.63	0.032	9.8	0.50
NCS DC73066	16.2	241	18.8	4.9	85	.	0.76	6.8	0.14	3.5	1.8	205	0.60	0.51	0.041	7.3	0.53
NCS DC73067	16.8	990	26.4	10.0	130	(0.003)	(0.5)	10.8	0.137	6.8	2.9	252	1.3	0.87	0.039	14.5	0.82
NCS DC73068	13.6	411	21.4	7.3	111	(0.002)	(0.47)	8.2	0.121	5.2	2.4	213	1.04	0.73	0.034	10.1	0.68
NCS DC73069	21.5	499	23.1	7.0	122	(0.002)	0.58	9.6	0.152	5.1	2.7	155	1.03	0.72	0.038	10.5	0.74
NCS DC73070	10.0	162	15.8	3.2	106	(0.002)	0.37	3.2	0.072	2.3	1.4	138	0.60	0.33	(0.021)	4.6	0.67
NCS DC73071	63	559	25.0	7.5	110	(0.004)	1.58	15.6	0.42	5.5	2.7	308	0.99	0.78	0.052	12.5	0.68
NCS DC73072	22.2	862	20.0	8.4	109	(0.003)	0.39	10.7	0.21	7.0	2.7	178	1.05	1.10	(0.033)	11.9	0.62
NCS DC73073	27	885	20.2	7.1	94	(0.002)	1.00	14.0	0.29	5.6	2.4	285	0.93	0.89	0.049	9.7	0.56
NCS DC73074	27.2	890	20.1	6.9	128	(0.002)	0.73	10.6	0.128	5.1	4.0	227	1.3	0.75	0.032	10.5	0.75
NCS DC73075	28.2	671	20.3	6.7	100	(0.002)	1.39	10.7	0.16	5.0	2.7	259	0.98	0.75	0.036	10.4	0.63
NCS DC73076	83	556	26.3	6.7	121	(0.002)	1.31	11.0	0.19	4.7	2.6	219	0.96	0.67	0.047	13.8	0.72
NCS DC73077	36	432	18.0	5.5	93	(0.002)	0.80	8.6	0.11	4.0	1.9	477	0.75	0.55	0.040	9.0	0.52
NCS DC73078	32.4	372	22.8	8.2	118	(0.001)	0.55	12.1	0.074	5.8	2.6	98	0.99	0.78	0.046	13.7	0.64
NCS DC73079	41	491	24.9	8.7	101	(0.002)	2.6	10.1	0.118	6.3	2.6	141	0.89	0.77	(0.054)	11.1	0.57
NCS DC73080	14.1	1100	25	9.2	110	(0.002)	0.33	8.2	0.087	6.3	2.8	214	1.08	0.86	(0.028)	16.0	0.64
NCS DC73081	32.5	556	19.3	6.5	79	(0.001)	0.88	11.7	0.27	4.9	2.1	189	0.85	(0.71)	0.042	9.8	0.51
NCS DC73082	23	612	18.7	6.5	82	(0.004)	1.8	9.2	0.107	4.8	2.3	233	0.81	0.68	0.038	9.0	0.51
NCS DC73083	27.7	(1580)	25	8.3	86	(0.002)	0.90	10.8	0.38	6.0	4.6	174	1.08	0.85	(0.038)	11.4	0.53
NCS DC73084	34	750	22	8.0	101	(0.002)	1.07	12.6	0.168	5.8	3.0	211	1.05	0.84	0.044	11.5	0.63
NCS DC73085	38	876	33	9.5	115	(0.003)	1.19	13.9	0.25	7.0	4.0	162	1.20	1	(0.049)	13.8	0.70
NCS DC73086	34.8	421	24.8	8.7	96	(0.003)	1.02	13.0	0.157	6.3	3.4	105	1.19	0.93	(0.04)	12.7	0.56
NCS DC73087	23.0	584	71	9.8	78	(0.002)	4.3	9.6	0.30	6.9	12.1	111	1.31	0.96	0.040	13.0	0.50
NCS DC73088	38	413	41	9.2	117	(0.004)	0.72	15.9	0.28	6.6	4.2	111	1.19	0.95	0.040	13.7	0.75
NCS DC73089	36	693	24.4	8.3	102	(0.003)	0.70	10.6	0.099	5.9	2.5	130	1.00	0.81	(0.042)	12.3	0.63
NCS DC73090	26.3	362	25.4	8.4	106	(0.002)	0.49	10.5	0.10	5.6	2.6	134	1.11	0.77	(0.042)	11.9	0.64
NCS DC73091	37.1	542	24.4	11.0	109	(0.003)	1.06	13.6	0.165	7.8	3.5	94	1.4	1.09	(0.046)	15.7	0.64
NCS DC73092	10.6	(127)	29.8	11.7	180	(0.002)	0.28	8.3	0.269	6.2	2.9	(16)	1.5	0.62	0.032	27.6	1.12
NCS DC73093	80	578	42.6	10.0	134	(0.001)	2.3	21.7	0.34	6.5	5.1	37	1.6	0.93	0.11	22.8	1.09
NCS DC73094	39.3	720	34	11.8	141	(0.001)	0.64	19.2	0.18	8.9	4.8	196	1.6	1.38	(0.18)	17.6	0.81
NCS DC73095	60	720	71	10.7	128	(0.001)	1.86	21.9	0.28	6.9	6.2	58	2.6	1.06	0.10	26	1.18
NCS DC73096	16.9	176	42	4.4	43	(0.001)	0.33	11.7	0.36	2.8	5.6	(11.5)	2.7	0.33	0.045	16.7	0.47
NCS DC73097	15.5	(319)	56	5.9	43.1	(0.003)	1.2	13.9	0.53	3.8	4.1	(17)	1.4	0.49	(0.07)	(20)	0.44
NCS DC73098	60	938	36.7	10.5	131	(0.004)	2.16	16.1	0.37	7.6	7.1	51	1.66	1.08	0.048	17.7	0.83
NCS DC73099	10.7	440	39.5	8.8	149	(0.002)	0.42	7.9	0.19	6.0	9.3	49	2.2	0.87	0.032	21.7	0.94
NCS DC73100	7.9	375	22.9	8.5	94	(0.002)	0.70	5.6	0.10	6.0	3.2	30	1.21	1.03	(0.029)	13.3	0.57
NCS DC73101	37.5	(180)	21.0	8.7	94	(0.003)	1.3	15.6	0.21	6.6	3.0	60	1.28	0.99	0.052	12.1	0.56
NCS DC73102	12.5	(164)	49	11.0	123	(0.003)	0.25	12.2	0.221	8.1	3.6	(10)	1.3	1.33	0.024	21.0	0.97
NCS DC73103	13.6	177	46	8.7	135	(0.003)	(0.87)	(9.1)	0.57	5.6	11.0	28.5	3.9	0.85	0.047	37	1.11
NCS DC73104	14.9	160	11.3	1.9	17.8	(0.001)	(0.38)	(4.2)	(0.36)	1.19	2.7	(18.7)	1.04	0.20	0.034	8.6	(0.13)
Number	Ni	P	Pb	Pr	Rb	Re	Sb	Sc	Se	Sm	Sn	Sr	Ta	Tb	Te	Th	Tl

CRM SOIL WITH EXTENSIVE ANALYSIS - CONTINUED FROM THE PREVIOUS PAGE

continued analysis listed in mg/kg

70 g units

Number	Tm	U	V	W	Y	Yb	Zn	Zr
NCS DC73058	0.51	3.1	95	2.1	29.9	3.2	75	306
NCS DC73059	0.46	2.1	109	1.8	28.6	2.9	85	260
NCS DC73060	0.75	15.6	79	164	43.7	5.1	514	257
NCS DC73061	0.45	4.4	136	3.0	27.8	2.9	70	280
NCS DC73062	0.47	2.6	83	2.1	27.7	3.0	78	264
NCS DC73063	0.46	5.7	68	2.2	27.7	2.9	82	185
NCS DC73064	0.40	2.8	(82)	1.9	25	2.6	72	201
NCS DC73065	0.33	2.6	77	1.3	19.6	2.1	55	140
NCS DC73066	0.27	1.4	54	1.4	15.8	1.8	35	201
2								
NCS DC73067	0.42	7.9	72	1.92	25.5	2.7	95	260
NCS DC73068	0.39	3.0	51	1.7	22.8	2.6	53	330
NCS DC73069	0.39	2.2	67	1.7	22.6	2.6	63	187
NCS DC73070	0.20	0.97	28	0.64	12.4	1.32	21	206
NCS DC73071	0.40	3.4	107	1.71	23.8	2.60	80	137
NCS DC73072	0.57	12.5	59	2.7	34.9	3.7	53	200
NCS DC73073	0.51	3.2	90	1.4	28.2	3.3	81	171
NCS DC73074	0.37	3.3	66	2.5	23	2.3	65	180
3								
NCS DC73075	0.37	2.7	71	1.8	22.6	2.37	65	165
NCS DC73076	0.34	2.3	75	2.0	20.4	2.18	64	169
NCS DC73077	0.28	2.2	67	1.3	16.5	1.81	52	133
NCS DC73078	0.39	1.94	99	1.5	22.6	2.52	76	184
NCS DC73079	0.32	1.3	79	1.6	20.7	1.9	66	179
NCS DC73080	0.40	2.6	57	1.99	25.7	2.6	67	264
NCS DC73081	0.37	2.6	79	1.42	21.9	2.4	62	176
NCS DC73082	0.34	2.1	60	1.8	21.5	2.19	57	201
4								
NCS DC73083	0.44	2.4	76	1.9	26.2	2.8	120	294
NCS DC73084	0.42	2.5	84	1.84	25	2.7	71	191
NCS DC73085	0.50	2.6	102	2.2	29.8	3.2	101	253
NCS DC73086	0.49	2.5	92	2.1	29.3	3.1	56	348
NCS DC73087	0.49	2.7	70	2.2	30.4	3.1	180	318
NCS DC73088	0.50	3.5	118	1.9	30.1	3.2	111	250
NCS DC73089	0.41	2.4	77	1.5	24	2.5	70	202
NCS DC73090	0.38	2.1	81	1.6	23.6	2.5	75	249
5								
NCS DC73091	0.54	3.3	106	2.5	33.1	3.4	79	322
NCS DC73092	0.24	2.9	76	3.3	16.2	1.50	78	302
NCS DC73093	0.52	6.0	204	3.4	29.1	3.5	180	193
NCS DC73094	0.71	3.3	131	(2.7)	46	4.5	137	171
NCS DC73095	0.62	9.0	358	4.3	35.3	4.1	181	459
NCS DC73096	0.16	5.1	72	5.7	(9.8)	1.06	39	253
NCS DC73097	0.29	4.0	107	15.7	15	2.0	46	317
NCS DC73098	0.48	4.0	132	3.3	31.5	3.0	102	265
6								
NCS DC73099	0.51	5.3	47	4.0	29	3.4	65	477
NCS DC73100	0.58	3.2	37	2.2	35	3.8	59	50.5
NCS DC73101	0.53	2.8	(127)	1.9	31.7	3.4	91	261
NCS DC73102	0.73	8.4	60	(0.84)	44.0	4.8	51	154
NCS DC73103	0.53	9.5	61	7.5	32	3.4	72	332
NCS DC73104	0.16	1.45	39	1.64	(9.9)	1.09	(19.4)	278

Number	Tm	U	V	W	Y	Yb	Zn	Zr
--------	----	---	---	---	---	----	----	----

BRAMMER STANDARD GEOLOGICAL MATERIALS CATALOG

CRM SOIL WITH EXTENSIVE ANALYSIS

analysis listed in mass % except * which is mg/kg 50 g units

Number	Al ₂ O ₃	C	Org.C	CaO	F*	F(sol)*	T.Fe ₂ O ₃	K ₂ O	MgO	Mn	N	Na ₂ O	P	S	SiO ₂	Ti
NCS ZC71026	13.53	2.76	2.53	3.45	439	6.1	5.43	2.54	1.219	0.107	0.269	1.98	0.1074	0.0441	61.4	0.413
NCS ZC71027	13.46	3.38	3.11	2.92	443	6.1	4.93	2.60	1.162	0.0963	0.285	1.99	0.1183	0.0429	61.7	0.390
NCS ZC71028	13.63	3.54	3.19	2.00	429	6.9	4.20	2.72	1.061	0.0782	0.267	1.99	0.1175	0.0432	63.5	0.369
NCS ZC71029	14.28	2.88	1.65	6.78	727	7.6	5.79	2.67	2.63	0.0873	0.184	1.18	0.155	0.0384	52.7	0.377
NCS ZC71030	12.76	1.81	1.70	1.65	506	24	4.59	2.01	1.19	0.0872	0.117	1.53	0.0853	0.0524	68.43	0.380
NCS ZC71031	13.19	0.68	0.66	0.94	466	10.2	3.57	2.98	0.707	0.0654	0.0683	2.04	0.0256	0.0390	71.58	0.264
NCS ZC71032	10.87	1.11	0.92	4.52	625	8.8	7.83	2.54	1.80	0.101	0.0696	1.23	0.0959	1.33	61.4	0.273
NCS ZC71033	13.57	2.69	1.74	4.98	640	14.1	4.81	2.25	2.08	0.0652	0.125	1.43	0.0765	0.0481	59.7	0.411
NCS ZC71034	14.03	3.86	2.72	6.19	810	19.6	14.4	2.43	2.29	0.0717	0.246	0.70	0.212	0.0652	42.5	0.340
NCS ZC71035	12.31	1.88	1.23	2.74	1020	6.6	6.11	2.88	2.86	0.118	0.122	1.21	0.0887	0.0576	62.3	0.443
NCS ZC71036	12.19	1.15	1.13	1.61	558	9.1	5.05	2.56	1.48	0.0690	0.113	1.86	0.0933	0.0499	69.1	0.389
NCS ZC71037	13.69	2.43	2.21	1.81	603	5.7	5.73	2.33	1.73	0.0909	0.233	1.12	0.227	0.0566	62.6	0.424

continued analysis in mg/kg

Number	Ag	As	B	Ba	Be	Bi	Br	Cd	Ce	Cl	Co	Cr	Cu	Dy	Er	Eu
NCS ZC71026	0.78	503	52	600	2.30	4.37	4.9	2.61	64.2	83	12.0	55	128	5.1	2.90	1.39
NCS ZC71027	0.53	323	43	619	2.31	2.84	4.9	1.62	66	88	11.7	54.1	88	4.62	2.61	1.26
NCS ZC71028	0.20	89	32	658	2.51	0.97	4.60	0.53	68	77	11.2	55	37.5	4.39	2.51	1.18
NCS ZC71029	0.094	17.4	55	538	2.42	0.483	10.2	0.66	73	161	16.5	79	37.0	5.21	2.95	1.37
NCS ZC71030	0.131	10.3	62	924	2.28	0.50	7.1	6.48	73	99	50.8	79	30.0	5.00	2.88	1.33
NCS ZC71031	2.11	8.4	27.0	978	1.96	1.19	4.2	0.50	49	85	8.2	54	30.1	3.25	1.96	0.98
NCS ZC71032	7.7	71.3	38	654	1.52	11.0	2.3	16.5	45.8	100	25.6	55.6	358	3.11	1.78	1.00
NCS ZC71033	0.098	13.5	65.8	477	2.37	0.427	6.7	0.218	78	91	13.38	69.1	25.9	5.3	3.04	1.32
NCS ZC71034	0.129	18.6	47	517	2.30	0.511	4.2	0.319	72	137	15.8	2520	70	5.02	2.83	1.32
NCS ZC71035	0.42	11.9	48	1820	2.99	4.0	2.32	0.68	235	55	16.6	75	47	6.5	3.64	2.62
NCS ZC71036	1.11	9.48	45	1277	1.88	2.52	3.1	1.11	85	73	14.2	67	130	4.71	2.67	1.40
NCS ZC71037	1.39	27.2	61	556	2.43	2.58	2.63	13.3	80	63	17.3	121	106	5.6	3.19	1.40

Number	Ga	Gd	Ge	Hg	Ho	I	La	Li	Lu	Mo	Nb	Nd	Ni	Pb	Pr	Rb
NCS ZC71026	17.0	5.35	1.65	0.058	1.04	3.09	36.6	28.5	0.46	2.01	13.6	32.9	20.7	34.9	8.6	102
NCS ZC71027	17.3	4.88	1.61	0.10	0.92	2.65	35.4	29.0	0.414	1.82	13.4	30.6	20.5	33.2	8.0	103
NCS ZC71028	17.6	4.7	1.39	0.14	0.88	2.6	34.2	30.6	0.408	1.25	13.5	29.6	21.1	30.7	7.9	105
NCS ZC71029	18.8	5.6	1.35	0.031	1.04	3.0	38.8	46.9	0.45	0.84	13.4	33.6	41.1	30.8	8.9	121
NCS ZC71030	15.6	5.66	1.57	0.072	1.00	3.3	36.5	41.3	0.459	1.05	13.3	31.8	40.7	190	11.6	84
NCS ZC71031	16.5	3.4	1.31	2.50	0.69	2.49	25.2	22.7	0.331	0.71	10.8	21.3	18.5	179	5.73	103
NCS ZC71032	14.9	3.47	1.89	6.36	0.62	0.94	23.8	29.4	0.264	14.0	8.6	21.9	30.0	538	5.63	102
NCS ZC71033	17.5	5.6	1.48	0.070	1.06	2.93	40.9	46.1	0.457	1.12	15.2	34.1	32.6	28.0	9.1	96
NCS ZC71034	21.7	5.5	2.33	0.121	1.00	2.0	38.2	46.5	0.42	12.5	12.3	33.6	236	34.4	8.8	106
NCS ZC71035	18.2	9.9	1.50	0.120	1.26	1.37	150	38.1	0.52	43	19.6	84	32.3	265	24.9	121
NCS ZC71036	15.7	5.3	1.34	6.3	0.96	1.61	49	28.7	0.410	19.2	13.3	35.9	26.8	637	9.9	99
NCS ZC71037	18.1	6.0	1.53	1.29	1.11	1.78	41	47.0	0.47	1.35	15.3	35.1	40.7	287	9.3	116

Number	Sb	Sc	Se	Sm	Sn	Sr	Tb	Th	Tl	Tm	U	V	W	Y	Yb	Zn	Zr
NCS ZC71026	1.34	10.6	0.36	6.27	11.4	192	0.89	10.7	0.62	0.45	2.69	74	5.9	27.9	2.91	353	272
NCS ZC71027	1.18	9.7	0.29	5.81	9.9	202	0.8	10.8	0.65	0.407	2.65	70	4.6	25.3	2.64	236	270
NCS ZC71028	1.04	9.4	0.23	5.6	4.9	216	0.76	11.0	0.692	0.39	2.52	69	2.60	23.8	2.50	133	273
NCS ZC71029	1.49	14.5	0.297	6.5	3.39	184	0.92	14.4	0.77	0.447	2.6	101	2.10	27.8	2.84	108	180
NCS ZC71030	1.24	10.7	1.47	6.06	26.4	208	0.88	11.6	0.59	0.451	2.47	87	1.72	26.8	2.88	312	837
NCS ZC71031	0.66	7.6	0.26	3.96	2.61	232	0.56	7.6	0.57	0.325	1.73	54.6	2.15	18.3	2.10	96	229
NCS ZC71032	6.0	9.1	0.46	4.10	3.25	166	0.557	6.2	0.97	0.267	2.24	71.9	44	17.0	1.73	2310	123
NCS ZC71033	1.10	12.8	0.606	6.5	3.33	181	0.92	13.4	0.62	0.464	0.273	88.5	1.97	28.8	2.92	77.0	234
NCS ZC71034	1.91	14.3	1.07	6.4	4.5	140	0.88	13.7	0.702	0.43	4.99	106	4.32	26.9	2.81	128	136
NCS ZC71035	1.42	13.0	0.272	11.7	3.5	232	1.26	12.5	0.88	0.54	4.3	100	10.8	33.7	3.45	158	216
NCS ZC71036	1.33	11.5	0.36	6.3	2.78	317	0.83	13.1	0.59	0.415	2.25	82	33.8	25.5	2.55	217	276
NCS ZC71037	6.7	13.7	0.52	6.8	4.81	117	0.96	14.3	0.88	0.48	2.57	97	4.0	30.4	3.05	707	245