

# INDEX

ALUMINUM IN STEEL [7](#)

BORON [3](#)

CALCIUM IN STEEL [7](#)

CARBON STEEL [3, 4](#)

CAST IRON [20, 21, 22, 23, 24](#)

GRAPHITIC CARBON [20](#)

HIGH ALLOY STEEL [19](#)

HIGH NICKEL STEEL [15](#)

IRON [2](#)

LEADED STEEL [7](#)

LOW ALLOY STEEL [5, 6, 7, 9, 10](#)

LOW NICKEL STAINLESS STEEL [16](#)

MANGANESE STEEL [15](#)

MARAGING STEEL [15](#)

MILD STEEL [7, 8, 9](#)

NICKEL BINARY [7](#)

NICKEL STEEL [15](#)

NITROGEN IN STEEL [7](#)

POWDER [2, 13, 17, 19, 25](#)

RARE EARTHS [21](#)

RESULFURIZED STEEL [11](#)

SILICON STEEL [11, 12](#)

SOLUBLE BORON [3](#)

STAINLESS STEEL [16, 17, 18](#)

TOOL STEEL [13, 14](#)

## IRON CHIPS AND POWDER

# = class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Co	Mo	Nb	O	Sn	Ti	V	W
1	NCS HC15014	0.0208	0.246	0.0121	0.007	0.0922	0.020	0.0202	0.013	.	0.046	.	.	.	.	0.0012	.	.	.
1	SRM 2165	(0.0063)	0.144	0.0052	0.003643	(0.0040)	0.0013	0.155	0.050	.	(0.0060)	0.0012	0.0055	0.0004	.	0.002	0.0051	0.0040	.
1	IARM 27G	(0.003)	(0.003)	(0.003)	0.0011	(0.07)	0.040	0.045	0.043	(0.0003)	(0.0013)	(0.0009)	(0.002)	(0.002)	0.025	(0.001)	<0.005	(0.001)	<0.005
1	NCS HC11011b	0.0023	0.013	0.0014	0.0014	0.0023	0.0045	0.0027	0.0066	0.0045	<(0.0001)	0.0012	0.00030	(0.00004)	.	0.00015	<(0.0001)	<(0.0001)	(0.00004)
1	VS SI/4	0.0023	0.0009	0.0010	0.0021	0.0160	0.0048	0.0210	0.0025	0.025	0.041	0.0007	0.00054	.	.	0.00021	0.00019	.	.
2	TL 1669C	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.0024	0.03553	0.0019	0.0011	0.00046	.	0.0071	0.0504	(0.0006)	.
1	NCS HC15002g	0.0013	0.00018	(0.0001)	0.0010	0.0014	0.00024	0.0052	0.00019	.	0.00065	(0.0001)	0.0033	.	Cd:(0.0001)	(0.0001)	(0.0001)	(0.0001)	.
1	Y TSC101	0.0013	0.00018	(0.0001)	0.0010	0.0014	0.00024	0.0052	0.00019	.	0.00065	(0.0001)	0.0033	.	Cd:(0.0001)	(0.0001)	(0.0001)	(0.0001)	.
1	ECRM 088-2	0.0006	0.0809	0.0048	0.0070	0.0052	0.0163	0.0275	0.0244	.	0.0061	.	.	.	.	.	.	0.00029	.
1	JSS 003-8	0.00040	0.00109	0.00040	0.00016	0.00064	0.00039	0.00007	0.00012	0.00068	0.00667	0.000046	0.000020	0.000048	.	0.000020	<0.00006	(0.000006)	(0.00001)
1	JSS 003-7	0.00034	0.00054	0.00038	0.00016	0.00052	0.00032	0.00007	0.00013	0.00061	0.00682	0.000047	0.000017	<0.0002	.	0.000017	<0.00006	trace	trace
1	SRM 937	99.90% Fe	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
1	ECRM 097-2C	.	0.012	0.00538	0.00181	0.00285	0.00793	0.0241	0.0213	0.00294	.	0.0139	0.00370	.	.	0.00043	.	0.00011	0.00386

analysis listed in mg/kg except

Number	Ag	As	B	Bi	Ca	Mg	Pb	Sb	Se	Ta	Te	Zn	Zr	Units
NCS HC15014	.	2	.	.	.	0.85	5	.	.	.	.	.	.	100 g chips
SRM 2165	2	10	9.44	<(1)	.	<(1)	3	10	.	.	.	.	.	150 g chips
IARM 27G	.	(16)	(6)	<70	(2)	(20)	<100	.	<200	.	.	<50	(30)	100 g chips
NCS HC11011b	.	26	2.3	<(0.1)	3	(0.2)	2.9	<0.1	<(0.1)	<0.1	1.5	<0.1	.	50 g chips also trace Cd, Ce, Hf, La, and Mg
VS SI/4	.	2.8	.	.	.	1.2	.	.	.	.	2.2	.	.	100 g chips
TL 1669C	.	17	3.8	.	1.7	(1.6)	1.3	4.9	.	.	.	2.7	(2.1)	100 g chips
NCS HC15002g	.	(1)	.	(1)	17	2.2	(1)	(1)	.	.	(1)	.	.	15 g powder Fe > 99.984%
Y TSC101	.	(1)	.	(1)	17	2.2	(1)	(1)	.	.	(1)	.	.	15 g powder Fe > 99.984%
ECRM 088-2	.	.	.	.	7.2	.	.	.	.	.	.	.	.	100 g chips
JSS 003-8	.	(0.1)	(0.26)	<0.7	<1	<1	0.04	<2	<1	<0.7	<1	(0.2)	<0.5	150 g chips also trace Cd, Ce, and La
JSS 003-7	.	<1	0.18	<0.7	<1	<1	(0.02)	<2	<1	<0.7	<1	(0.2)	<0.5	150 g chips
SRM 937	.	.	.	.	.	.	.	.	.	.	.	.	.	50 g chips
ECRM 097-2C	.	28.1	1.2	.	.	.	.	1.2	.	1.5	.	1.4	.	100 g chips

There are also purity iron powders in our  
Geological catalog, Iron Ore section  
<http://brammerstandard.com/pdf/geological.pdf>

## CRM IRON CHIPS AND POWDER

analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Ins.Al	As	B	Co	Mo	Ti	Units
NCS HC15007	0.091	0.399	0.0246	0.017	0.341	0.201	0.243	0.148	.	0.180	.	.	.	.	.	.	100 g chips
NCS HC15007a	0.080	0.358	0.036	0.031	0.506	0.254	0.203	0.170	0.018	0.432	.	.	.	.	.	.	50 g chips
NCS HC15017	0.061	0.319	0.04	0.005	0.166	0.02	0.02	0.022	0.0146	0.284	.	.	.	.	.	.	50 g chips
BAM 031-3	0.055	0.329	0.014	0.021	0.037	0.020	.	.	0.0050	0.054	.	0.013	.	.	.	.	100 g chips
BAM 031-2	0.0344	0.296	0.053	(0.052)	.	0.083	.	.	0.012	.	.	0.061	.	.	.	.	100 g chips
NCS HC15005a	0.030	0.106	0.0061	0.025	0.182	0.123	0.162	0.147	0.011	0.205	.	.	.	.	.	.	50 g chips
ECRM 083-1	0.028	0.289	0.0077	0.0100	.	0.016	0.014	.	0.00189	.	.	.	.	.	.	.	100 g chips
NCS HC15004	0.0272	0.246	0.0094	0.012	0.0994	0.031	0.0202	0.013	.	0.37	.	.	.	.	.	.	100 g chips
NCS HC15004a	0.027	0.195	0.014	0.0063	0.018	0.089	0.116	0.048	0.016	0.290	.	.	.	.	.	.	50 g chips
NCS HC15016	0.022	0.201	0.0072	0.0027	0.199	0.066	0.066	0.032	0.0123	0.217	.	.	.	.	.	.	50 g chips
NCS HC15003a	0.012	0.034	0.0019	0.020	0.017	0.021	0.030	0.016	0.015	0.060	.	.	.	.	.	.	50 g chips
NCS HC13013	0.0041	0.126	0.0085	0.021	0.018	.	.	.	.	.	.	.	.	.	.	.	150 g powder
IPT 73	0.0034	0.044	0.0034	0.0049	0.0028	0.076	0.033	0.030	0.0076	.	.	.	.	0.004	.	TEMPORARILY UNAVAILABLE	





BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

CRM LOW ALLOY STEEL CHIPS WITH NITROGEN

IPT 96: 120 g JK, JSS, NCS, SRM: 150 g all others: 100 g

Table listing chemical compositions for various CRM items (e.g., BCS 401/2, IMZ C-119, etc.) with columns for elements like C, Mn, P, S, Si, Cu, Ni, Cr, Al, etc.

Table listing chemical compositions for various CRM items (e.g., BAM 032-2, ECRM 017-1, etc.) with columns for elements like C, Mn, P, S, Si, Cu, Ni, Cr, Al, etc.

Table listing chemical compositions for various CRM items (e.g., ECRM 064-1C) with columns for elements like C, Mn, P, S, Si, Cu, Ni, Cr, Al, etc.

\* Clearance Sale Item









**CRM MILD STEEL CHIPS, chart 2 of 2**

JSS: 150 g all others: 100 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Mo	Ti	V	W	B	Ca	Co	Nb	Sn	Zr
JSS 150-19	0.497	0.101	0.0389	0.0292	0.207	0.049	4.00	0.310	0.0157	0.0153	0.195		0.0190	.	.	.	.	.	.	.
IARM 170B	0.400	0.821	(0.005)	(0.004)	0.21	(0.005)	0.197	0.009	0.230	.	(0.003)	(0.19)	(0.002)	.	(0.0004)	.	(0.005)	(0.004)	(0.002)	.
IMZ 1.10/2	0.39	0.48	0.020	0.013	0.24	0.076	0.17	1.46	0.82	.	0.20	.	.	.	.	.	.	.	.	.
IARM Fe434022	0.382	0.739	0.0079	0.0273	0.244	0.174	1.75	0.787	0.022	As:0.0055	0.242	0.0010	0.0047	0.011	.	0.093	(0.003)	0.0083	.	
IMZ 1.9/3	0.38	0.55	0.025	0.016	0.28	0.101	1.62	1.30	.	.	0.16	.	.	.	.	.	.	.	.	.
IMZ 1.11/3	0.35	0.48	0.025	0.020	0.18	0.077	0.12	1.00	.	.	0.19	.	.	.	.	.	.	.	.	.
JSS 152-19	0.295	0.398	0.0202	0.0392	0.412	0.496	2.00	0.507	0.0097	0.0092	0.998	.	0.1016	.	.	.	.	.	.	.
IARM 378A	0.274	1.38	0.018	0.037	0.307	0.299	0.142	0.187	(0.0029)	.	0.031	(0.003)	0.0844	(0.006)	(0.0006)	.	0.013	(0.003)	0.0236	.
IARM 169B	0.232	0.75	(0.004)	(0.004)	(0.32)	(0.005)	(0.010)	0.010	0.36	.	(0.004)	0.23	(0.002)	(0.003)	0.0003	.	(0.003)	(0.004)	(0.002)	.
IMZ 1.85	0.205	1.69	0.026	0.026	0.51	0.29	0.24	0.27	(0.064)	0.064	0.007	.	0.093	.	.	.	.	(0.011)	.	0.026
IMZ 1.19/2	0.20	1.00	0.020	0.017	0.30	0.11	0.096	1.10	.	.	.	0.084	.	.	.	.	.	.	.	.
JSS 153-19	0.198	0.806	0.0098	0.0102	0.305	0.307	1.003	1.010	0.0111	0.0102	0.1289	.	0.200	.	.	.	.	.	.	.
IMZ 1.73/1	0.18	1.24	0.014	0.029	0.34	0.56	0.095	0.15	0.043	0.036	0.056	.	0.073	.	.	.	.	0.088	.	.
IMZ 1.31	0.14	0.81	0.022	(0.025)	0.31	0.33	(0.87)	0.55	.	.	0.50	.	(0.10)	.	0.0013	.	.	.	.	.
IMZ 1.33	0.14	0.69	(0.022)	(0.014)	0.26	0.43	0.88	0.52	.	.	0.51	.	(0.087)	.	0.0057	.	.	.	.	.
IMZ 1.76/1	0.13	1.39	0.022	0.032	0.28	0.058	0.33	0.11	0.042	0.036	0.101	.	.	.	.	.	.	0.068	.	.
IMZ 1.32	0.12	0.80	0.018	0.016	(0.21)	0.37	0.83	0.55	.	.	0.53	.	(0.093)	.	0.0021	.	.	.	.	.
IMZ 1.72/1	0.12	0.56	0.019	0.030	0.55	0.88	0.041	0.45	0.032	0.026	.	.	(0.047)	.	.	.	.	.	.	.
IARM FeF11-21	0.114	0.530	0.0067	0.0141	0.679	0.123	0.069	1.349	0.018	As:0.0048	0.614	0.0015	0.0038	.	0.0004	.	0.0062	.	0.0084	Sb:0.0017
IMZ 1.74/1	0.11	1.95	0.030	0.024	0.20	0.31	0.055	0.25	0.014	(0.009)	.	.	0.094	.	.	.	.	.	.	.
IMZ 1.34	0.11	0.84	0.014	(0.030)	0.31	(0.05)	0.65	0.73	.	.	0.39	.	(0.005)	.	0.0084	.	.	.	.	.
IMZ 1.77/1	0.11	0.37	0.029	0.027	0.18	0.17	0.051	0.32	0.012	(0.008)	.	0.021	0.046	.	.	.	.	.	.	.
IMZ 1.82	0.10	1.11	0.017	0.020	0.27	0.069	0.085	0.21	0.060	.	0.060	.	0.101	.	.	.	.	0.058	.	(0.0015)
IMZ 1.81	0.10	0.28	0.043	0.012	0.28	0.32	0.069	0.58	0.017	.	.	.	.	.	.	.	.	.	.	0.005
JSS 154-18	0.0995	1.212	0.0046	0.00488	0.620	0.201	0.508	2.01	0.0093	0.0086	0.405	.	0.307	.	.	.	.	.	.	.
IARM FeT23-18	0.068	0.82	0.012	0.006	0.18	0.046	0.53	2.47	.	0:0.0044	0.261	(0.004)	0.238	1.60	0.0020	.	0.085	0.052	(0.004)	.
JSS 155-17	0.050	0.205	0.0017	0.0021	0.498	0.407	0.151	3.03	0.0102	0.0095	0.709	.	0.397	.	.	.	.	.	.	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Mo	Ti	V	W	B	Ca	Co	Nb	Sn	Zr
--------	---	----	---	---	----	----	----	----	----	-----	----	----	---	---	---	----	----	----	----	----

**RM LOW ALLOY STEEL CHIPS, chart 1 of 2**

analysis listed in mass % except \* which is mg/kg C12X, DH: typical analysis 50 g chips BS CE: 150 g chips all others: 100 g chips

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Al.sol	Al.insol	Co	Mo	N	Nb	Ti	V
DSZU CX012	1.220	0.237	0.0159	0.0145	0.226	0.071	0.046	0.134	.	.	.	.	.	.	.	.	.
BS CE26 *	0.88	0.18	0.042	0.005	0.24	.	.	.	.	.	.	.	.	.	.	.	.
C12X LA50	0.81	0.98	0.057	0.015	0.67	0.09	0.13	0.12	0.19	.	.	.	0.19	.	.	.	0.58
DSZU CX014	0.802	0.212	0.129	0.0174	0.240	(0.16)	0.125	0.230	.	.	.	.	.	.	.	.	.
C12X LA40	0.67	0.24	0.044	0.021	0.28	0.29	0.46	0.64	0.19	.	.	.	0.46	.	.	.	0.36
BS CE24 *	0.63	0.84	0.016	0.010	0.27	0.066	0.045	0.016	0.044	.	.	0.010	0.006	.	.	.	.
IARM 34A	0.51	0.78	0.01	0.010	0.22	0.18	0.14	0.99	0.014	.	.	0.009	0.044	0.0076	0.003	0.003	0.17
DH E2208	0.4843	0.8406	0.0144	0.0013	0.2616	0.0202	0.0416	0.9596	0.0271	.	.	0.0037	0.0105	.	0.0005	0.0018	0.1325
BS CSN-2C	0.469	0.60	0.012	0.0305	0.17	0.073	0.071	0.072	.	.	.	.	(0.006)	0.0173	.	.	.
DSZU CX03a	0.206	0.369	0.029	0.033	0.014	0.020	0.0155	0.046	.	.	.	.	.	.	.	.	200 g
DH E2110	0.2035	1.483	0.0186	0.0169	0.500	0.056	0.0179	0.023	.	0.0385	0.002	0.0042	0.00249	.	.	0.0014	0.0019
C12X 3550	0.20	0.62	0.028	0.024	0.48	.	.	.	<0.01	.	.	0.05	.	.	0.02	.	0.11

Number	As	B	B.sol	Ca*	O*	Pb	Sb	Sn	W	Zn	Zr
DSZU CX012	.	.	.	.	.	.	.	.	.	.	.
BS CE 26 *	.	.	.	.	.	.	.	.	.	.	.
C12X LA50	.	.	.	.	.	.	.	.	.	.	.
DSZU CX014	.	.	.	.	.	.	.	.	.	.	.
C12X LA40	.	.	.	.	.	.	.	.	.	.	.
BS CE 24 *	0.0029	.	.	.	.	.	.	.	.	.	.
IARM 34A	(0.006)	(0.0002)	.	.	(14)	.	.	0.009	(0.02)	.	.
DH E2208	0.004	.	.	26	.	.	0.0005	0.0004	.	.	.
BS CSN-2C	.	.	.	33	.	.	.	.	.	.	.
DSZU CX03a	.	.	.	.	.	.	.	.	.	.	.
DH E2110	0.006	0.00006	.	3	.	0.00048	0.0008	0.00178	.	0.00053	.
C12X 3550	.	0.001	.	.	.	.	0.08	.	.	.	<0.01

\* Clearance Sale Item, no uncertainties

\* Clearance Sale Items



**RESULFURIZED STEEL**

# = class, where 1 = CRM and 2 = RM

C12X, C14X typical analysis

100 g units

#	Number	S	C	Mn	P	Si	Cu	Ni	Cr	Al	Co	Mo	N	Ti	V	W	As	Pb	Sb	Sn	Zn
1	IMZ C-123	0.38	0.25	1.57	0.030	0.23	0.093	0.057	0.16	0.032	.	.	0.0171	.	.	.	0.033	0.030	0.030	(0.007)	.
1	ECRM 085-1C	0.336	0.067	0.977	0.062	0.008	0.291	.	.	.	0.019	.	.	.	0.0021	.	.	0.0010	0.0073	.	0.0025
1	IARM Fe114422	0.323	0.406	1.34	0.0091	0.171	0.115	0.036	0.061	.	0.0061	0.0112	0.0081	0.0007	0.0023	0.0017	0.0040	.	0.0017	0.0081	.
1	IRSID 022-1	0.300	0.115	0.797	0.057	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
1	IMZ C-124	0.28	0.10	0.60	0.082	(0.019)	0.060	0.046	0.11	0.005	.	.	0.0059	.	.	.	0.004	(0.002)	0.002	0.009	.
1	IMZ C-122	0.21	0.27	1.33	0.073	0.43	0.25	0.25	0.19	(0.027)	.	.	0.0110	.	.	.	0.007	(0.020)	0.019	0.12	.
1	VS U2/7	0.193	0.136	1.19	0.040	0.046	0.082	0.076	0.158	.	.	.	.	.	.	.	(0.005)	0.166	.	.	.
1	ECRM 058-2C	0.1712	0.424	1.186	0.0098	0.1080	0.261	0.199	0.1211	.	.	0.0589	0.0107	.	.	.	0.0095	.	.	.	.
1	ECRM 051-1	0.126	0.181	1.18	(0.025)	(0.11)	(0.15)	(0.14)	(0.05)	.	.	.	.	.	.	.	.	.	.	.	.
1	C12X 3520	0.125	0.30	0.63	0.067	0.33	0.14	0.33	0.415	0.145	0.050	0.255	.	0.28	0.058	0.22	0.010	.	0.022	0.106	.
1	IARM 29E	0.121	0.193	1.19	0.0157	0.239	0.253	0.082	0.105	0.0032	0.008	0.0269	0.0093	0.0014	0.0255	.	0.0085	(0.001)	(0.003)	0.0109	(0.004)
1	IARM 348A	0.102	0.384	1.46	0.0121	0.270	0.230	0.081	0.123	(0.002)	(0.010)	0.026	(0.010)	0.0015	0.0029	(0.009)	(0.007)	(0.002)	(0.003)	0.0112	<0.003
1	IMZ C-121	0.097	0.39	1.18	0.057	(0.056)	0.032	0.029	0.036	0.016	.	.	0.0125	.	.	.	0.002	0.011	0.017	0.059	.
1	IARM 307A	0.096	0.163	1.44	0.0113	0.281	0.190	0.197	0.104	0.032	(0.010)	0.045	0.0108	0.0015	(0.0028)	(0.005)	0.008	(0.002)	<0.004	0.0090	<0.002
1	IARM 307B	(0.094)	0.162	1.45	(0.012)	(0.30)	0.191	0.195	0.105	0.034	0.0101	0.045	(0.011)	(0.003)	(0.003)	.	.	.	.	0.010	.
1	IMZ C-125	(0.057)	0.029	0.95	(0.018)	0.15	0.044	0.023	0.18	(0.007)	.	.	.	.	.	.	0.065	.	0.014	0.002	.

**SILICON STEEL CHIPS WITH NITROGEN**

# = class, where 1 = CRM and 2 = RM

100 g units

#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Nb	Sn	Ti	V	W
1	ECRM 191-2C	3.267	0.0043	0.1334	0.0087	0.0029	0.0165	0.0224	0.0314	0.985	.	0.0018	.	0.0020	0.00105	.	0.0050	0.0024	.	.
1	ECRM 191-3C	3.226	0.0027	0.153	0.0097	0.0005	0.0097	0.0124	0.0242	0.81	.	0.0014	.	0.00127	0.00105	.	0.0013	0.0020	0.00043	.
1	NCS HC14213	3.18	0.076	0.081	0.0090	0.023	0.066	.	.	.	0.031	.	.	.	0.0081	.	.	.	0.138	.
1	VS S9/4 **	3.12	0.040	0.066	0.0063	0.0034	0.139	0.097	0.044	0.0106	0.0074	0.0061	0.0101	0.0050	0.0130	.	0.0040	0.0057	0.0009	.
1	IMZ 1.22/1	2.02	0.090	0.24	0.019	0.026	0.071	0.039	0.045	0.014	0.011	0.020	.	.	0.0039	.	0.0076	(0.004)	.	.
1	ECRM 196-2C	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.00033	0.0138	0.0142	0.00178	.	0.00047	0.00253	0.00368	.
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	(0.004)	0.006	0.39	0.0020	0.015	0.005	0.0098	0.064	(0.005)
1	IMZ 1.8/4	1.31	0.35	0.99	0.020	0.018	0.11	0.16	1.18	.	.	.	.	.	.	.	.	.	.	.
1	IMZ 1.21/1	1.29	0.058	0.16	0.013	0.024	0.068	0.056	0.037	0.005	0.003	0.019	.	.	0.0030	.	0.0067	(0.005)	.	.
1	BCS 404/2	1.121	0.696	0.532	0.0479	0.0228	0.427	0.393	0.774	0.017	.	.	.	0.307	0.0089	.	.	.	0.107	.
1	BCS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.0020	0.0415	0.056	0.0109	0.0487	0.0067	0.0390	0.201	0.012

Number	B	Ca	Mg	O	Pb	Sb	Zn	Zr
ECRM 191-2C	.	.	.	.	.	.	.	.
ECRM 191-3C	0.00024	.	0.0036	.	.	.	.	.
NCS HC14213	.	.	.	.	.	.	.	.
VS S9/4	.	.	0.0007	.	0.0029	0.0009	0.0006	.
IMZ 1.22/1	.	.	.	.	.	0.0028	.	.
ECRM 196-2C	0.00014	0.00071	0.00075	.	.	.	0.00019	.
IARM 340A	0.0004	.	.	(0.0010)	.	0.0021	.	.
IMZ 1.8/4	.	.	.	.	.	.	.	.
IMZ 1.21/1	.	.	.	.	.	0.0025	.	.
BCS 404/2	.	.	.	.	.	.	.	.
BCS 113	0.0066	.	.	.	.	.	0.0029	.

## SILICON STEEL CHIPS

C12X: typical analysis 50 g BS CE: 150 g all others: 100 g

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn
CRM																			
VS S57/1	3.54	0.256	.	0.0051	0.0039	.	0.758	.	.	.	.	.	.	.	.	.	2.98	.	.
ECRM 151-1 *	3.49	0.028	0.085	0.015	(0.025)	.	.	.	.	.	.	.	.	.	.	.	.	.	.
CMSI 1232	3.36	0.057	0.225	0.0124	0.020	0.314	0.316	0.259	0.166	.	.	0.0036	.	.	.	.	.	.	.
NCS HC20210	3.36	0.057	0.225	0.012	0.020	0.314	0.316	0.259	0.1679	0.166	.	0.0036	.	.	.	.	.	.	.
CMSI 1432	2.91	0.400	0.437	0.0064	0.0029	0.64	0.064	0.159	.	0.113	.	0.012	.	.	1.18	.	.	.	.
SRM 125b	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	0.329	.	(0.007)	0.0087	(0.004)	(0.0005)	.	(0.003)	.	.	0.0034
CMSI 1431	2.15	0.051	0.600	0.0149	0.0174	0.195	0.276	0.362	.	0.065	.	0.160	.	0.043	0.77	.	.	.	.
IPT 108	1.96	0.598	0.861	0.028	0.020	0.121	0.052	0.133	.	0.019	0.006	0.017	0.004	.	.	.	.	.	.
CMSI 1435	1.74	0.666	0.725	0.0144	0.0190	0.147	0.081	0.071	.	0.132	.	0.061	.	0.129	0.40	.	.	0.0013	.
ECRM 186-1C	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	.	0.048	.	.	.	.	.	.	.
BCS 405/1	1.71	0.032	1.28	0.018	0.069	0.013	0.22	0.15	.	.	.	0.002	.	0.28	.	.	.	.	.
CMSI 1433	1.69	0.599	1.14	0.0209	0.0291	0.095	0.124	1.13	.	0.018	.	0.071	.	0.081	0.028	.	.	.	.
VS S15/5	1.69	0.558	0.701	0.0140	0.0185	0.205	0.135	0.199	.	.	.	.	.	.	.	(0.005)	.	.	.
IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	N:0.0102	0.008	0.42	0.0028	0.023	(0.005)	(0.006)	O:0.0006	B:0.0004	0.021
BCS 409/1	1.46	0.082	0.44	0.025	0.021	0.048	3.06	0.94	.	.	0.014	0.65	.	0.09	.	.	.	.	.
Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn
CMSI 1108	1.42	1.086	0.308	0.013	0.004	0.036	0.021	0.045	.	0.11	.	0.89	0.30	0.50	.	.	.	0.016	.
IMZ 1.8/4	1.31	0.35	0.99	0.020	0.018	0.11	0.16	1.18	.	.	.	.	.	.	.	.	.	.	.
VS S22/4	1.29	0.348	0.606	0.0090	0.0060	0.167	0.850	2.83	.	.	.	0.426	.	0.189	0.8	(0.005)	.	.	.
VS S58	1.27	0.348	1.25	0.0076	0.0077	0.100	0.086	0.123	.	.	.	.	.	.	.	.	.	.	.
DSZU C58	1.27	0.348	1.25	0.0076	0.0077	0.100	0.086	0.123	.	.	.	.	.	.	.	.	.	.	250 g
BCS 409/2	1.18	0.086	0.559	0.0141	0.0179	0.205	3.02	1.318	0.094	.	.	0.599	.	0.008	.	.	.	.	.
CMSI 1434	1.10	0.706	0.875	0.0256	0.0374	0.303	0.393	0.760	.	0.158	.	0.273	.	0.168	0.176	.	.	0.0012	.
CMSI 1189	1.09	0.283	0.438	0.022	0.023	0.247	0.224	0.300	0.132	0.128	.	.	0.171	0.144	.	.	0.0045	0.0041	last
BCS 409 *	1.07	0.11	0.48	0.025	0.015	0.23	3.14	1.22	.	.	.	0.77	.	0.028	.	.	.	.	.
NCS HC28304	1.06	0.407	0.315	0.015	0.013	0.017	0.037	5.08	0.0096	0.0056	.	1.20	.	.	.	.	.	.	.
BCS 404	1.04	0.67	0.52	0.050	0.018	0.31	0.46	0.68	.	.	.	0.33	.	0.100	.	.	.	.	last
NCS HC20212	0.998	0.162	0.346	0.036	0.030	0.213	0.103	0.471	0.2090	0.208	.	0.0048	.	.	.	.	.	.	.
BAM 128-1	0.949	0.085	0.839	0.007	0.007	0.055	0.046	0.108	0.286	.	.	.	0.890	(0.008)	.	.	.	.	.
BCS 405/2	0.947	0.044	0.903	0.0095	0.058	0.022	0.102	0.206	0.330	.	.	0.025	.	0.411	.	.	.	.	.
RM																			
C12X LA90	1.07	0.47	0.58	0.074	0.065	0.51	2.04	3.10	0.05	.	0.30	1.10	.	0.39	.	.	.	.	0.007
C12X LA20	0.98	0.24	0.55	0.026	0.042	0.44	0.73	0.81	0.03	.	.	0.10	.	0.09	.	.	.	.	.
Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn

BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

CRM	TOOL STEEL CHIPS AND POWDER WITH NITROGEN										BS: 100g powder	JK 49C: 35g chips	other JK, JSS, NCS, SRM: 150g chips	all others: 100 g chips							
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn
ECRM 288-1C	2.08	0.292	0.024	(0.0012)	0.260	0.060	0.298	12.00	0.012	0.018	0.103	0.0151	.	.	0.055	(0.68)	(0.0065)	.	.	.	.
ECRM 274-1C	1.563	0.397	0.0148	0.0096	1.057	0.0281	0.077	8.036	(0.0025)	(0.0230)	1.4551	0.0769	.	(0.0011)	4.010	0.0087	(0.0013)	(0.0005)	(0.0026)	(0.000064)	(0.001)
IARM 41D	1.519	0.256	0.021	0.012	0.256	0.047	0.114	11.5	0.014	(0.020)	0.74	0.0152	(0.004)	(0.003)	0.77	0.034	(0.01)	(0.0006)	(0.003)	(0.0008)	(0.005)
IARM 45B	1.42	0.90	0.010	0.008	0.92	0.018	0.024	0.061	0.010	0.004	0.24	0.0080	(0.002)	0.002	(0.003)	(0.004)	(0.002)	(0.0001)	(0.0005)	.	0.008
IARM FeM4-18	1.42	0.298	0.013	0.062	0.60	0.104	0.127	4.16	.	0.080	5.07	0.042	.	0.0018	3.97	5.55	0.0058	Fe:79.0	.	.	0.0050
IARM FeM62-18	1.32	0.27	0.016	0.015	0.37	0.115	0.129	3.86	(0.006)	0.105	10.2	0.045	(0.017)	(0.003)	2.02	6.31	.	(0.003)	(0.003)	.	.
JSS 602-12	1.256	0.298	0.0173	0.0086	0.250	0.1513	0.1579	0.355	.	.	0.0501	0.0116	.	.	0.219	3.68	.	.	.	.	.
JSS 610-11	1.252	0.301	0.0171	0.00014	0.310	0.0239	0.046	4.04	.	9.72	3.05	0.0349	.	.	3.32	9.22	.	.	.	.	.
ECRM 283-1	1.219	0.217	0.022	0.029	0.345	.	.	4.15	.	10.27	3.41	0.033	.	.	3.28	9.66	.	0.0003	.	.	.
ECRM 268-1C	1.134	0.293	0.0209	0.0154	0.373	0.123	0.143	4.57	.	0.0290	3.20	2.03	.	.	8.47	3.70	0.0062	0.0009	.	Sb:0.0017	0.0078
IMZ C-172	1.03	0.71	0.018	0.047	0.21	0.128	0.12	4.47	0.062	0.012	0.96	0.0192	.	(0.002)	0.20	0.011	.	.	.	.	0.010
<b>BS CSONH</b>	1.02	(0.4)	(0.05)	0.011	(0.4)	(0.11)	(0.2)	(4.3)	H:0.0008	(0.5)	(5.8)	0.025	0.116	.	(3.3)	(5.7)	.	.	.	.	<b>17025</b>
IARM 39E	0.99	0.54	.	0.35	0.004	0.10	.	4.79	0.006	0.014	1.01	0.0096	0.006	0.22	(0.026)	0.14	.	.	0.017	0.003	0.003
IARM 39C	0.99	0.45	0.019	0.007	0.28	0.077	0.144	4.99	0.017	0.013	0.97	0.011	0.0040	0.0029	0.21	0.011	(0.005)	0.001	0.001	(0.0001)	0.005
BAM 227-1	0.950	0.236	0.016	0.022	0.272	0.124	0.114	4.25	.	.	2.64	0.040	.	.	2.44	3.03	.	.	.	.	.
IARM 320A	0.93	0.33	0.021	(0.0015)	0.36	0.091	0.204	4.22	0.023	4.90	4.79	(0.014)	(0.015)	0.0032	1.76	6.01	0.013	0.0011	(0.0021)	.	0.008
ECRM 290-1C	0.91	0.24	0.016	0.016	0.08	0.081	0.33	4.18	.	5.12	4.81	0.0325	.	.	1.92	6.24	.	.	.	.	.
JSS 609-11	0.897	0.287	0.0246	0.00059	0.252	0.0494	0.1234	3.96	.	4.72	4.83	(0.0215)	.	.	1.87	6.15	.	.	.	.	.
JSS 611-12	0.888	0.335	0.0213	0.00063	0.263	0.0495	0.1114	4.00	.	0.206	5.00	0.0181	.	.	1.86	6.15	.	.	.	.	.
JK 12A	0.886	0.312	0.020	0.023	0.30	0.062	0.191	4.04	.	0.189	4.85	0.0259	.	.	1.94	6.42	.	.	.	0.0004	0.007
IARM 304A	0.857	0.260	0.019	0.0016	0.36	0.14	0.133	3.55	0.009	0.278	8.04	0.034	0.021	0.002	1.23	1.65	(0.01)	0.002	0.002	.	0.006
IARM FeM2-18	0.853	0.337	0.025	(0.0010)	0.26	0.098	0.182	4.23	(0.014)	0.28	4.92	0.0148	(0.021)	(0.0016)	1.90	5.81	(0.008)	Fe:81.4	(0.0016)	.	(0.007)
IARM FeM1-18	0.85	0.318	0.013	(0.003)	0.44	0.091	0.104	3.67	0.007	0.226	8.0	0.037	.	0.0044	1.19	1.98	.	.	.	Zr:0.0013	0.0041
IARM 306B	0.84	0.24	0.006	(0.001)	0.21	0.058	0.095	4.12	0.08	0.010	4.2	0.0049	0.007	(0.002)	0.98	(0.01)	(0.003)	(0.001)	Sb:0.0025	(0.0001)	0.004
IARM FeT1-18	0.80	0.295	0.026	(<0.0010)	0.30	0.034	0.14	3.98	0.054	0.096	0.124	0.0195	(0.004)	0.026	1.05	18.0	.	.	(0.0027)	.	(0.010)
JSS 607-10	0.787	0.313	0.0155	0.00161	0.196	0.0325	0.0591	3.96	.	4.78	0.456	0.00328	.	.	0.849	17.25	.	.	.	.	.
IARM 281A	0.74	0.30	0.015	0.019	0.29	0.096	0.15	3.89	0.007	4.8	0.49	0.0064	0.094	0.004	0.90	17.6	(0.02)	(0.003)	(0.003)	.	0.02
IARM 40C	0.72	1.91	0.014	0.012	0.32	0.142	0.255	0.99	0.019	0.010	1.27	0.0083	0.003	0.008	0.010	0.009	0.008	0.0009	0.0013	.	0.008
SRM 50c	0.7193	0.3417	0.0222	0.006367	0.3102	0.0792	0.0686	4.128	.	(0.035)	0.0821	0.0117	.	.	1.158	18.445	0.0225	.	.	.	0.0183
IARM 40B	0.68	1.98	.	0.39	0.004	0.050	(0.0014)	1.04	(0.006)	0.015	1.22	0.0107	0.005	0.014	0.013	0.096	.	(0.0010)	0.012	0.003	0.003
IARM 47B	0.59	0.79	0.017	0.006	1.96	0.17	0.090	0.23	0.014	0.007	0.20	0.0092	(0.002)	0.010	0.17	(0.016)	.	(<0.001)	(0.0014)	(0.0003)	0.008
JSS 605-11	0.554	0.758	0.0197	0.0109	0.256	0.155	1.661	1.008	.	.	0.457	0.0192	.	.	0.1014	0.0104	.	.	.	.	.
JSS 605-12	0.543	0.750	0.0192	0.0101	0.250	0.1493	1.64	0.984	.	.	0.451	0.0175	.	.	0.1017	0.0105	.	.	.	.	.
IARM FeS7-18	0.51	0.271	0.021	0.0032	0.47	0.128	0.170	3.28	(0.015)	0.0106	1.39	0.0102	(0.005)	0.0014	0.233	(0.016)	(0.005)	Fe:(93.6)	0.0023	0.0003	(0.006)
IARM 259A	0.479	0.399	0.020	0.0007	0.44	0.081	0.194	3.27	0.016	0.011	1.43	0.0077	0.003	0.0026	0.256	0.035	0.006	0.0003	0.0014	<0.0005	0.004
IARM 46B	0.45	0.27	0.019	0.0040	0.89	0.147	0.108	1.09	0.011	0.013	0.222	0.0069	0.003	0.007	0.170	1.96	(0.01)	0.0003	0.002	<0.002	0.016
ECRM 276-2C	0.399	0.365	0.0093	0.0189	1.034	0.183	0.203	4.975	.	.	1.134	0.0116	.	.	0.296	.	.	.	.	.	0.0133
IARM 42C	0.382	0.40	0.022	0.0037	0.85	0.066	0.051	4.86	0.018	0.022	1.29	0.0201	(0.004)	0.0125	0.84	0.32	(0.01)	0.0011	0.003	0.0007	(0.006)
ECRM 271-1C	0.3698	0.437	0.0120	0.00045	0.923	0.1371	0.1552	5.002	0.0234	0.0139	1.247	0.0137	.	0.0020	0.850	0.0054	0.0057	Ca: 0.0009	.	.	0.0084
IMZ C-174	0.33	0.32	0.029	0.023	0.93	0.17	0.13	5.10	0.080	0.011	1.24	0.0288	.	(0.001)	0.98	0.021	.	.	.	.	0.010
IMZ C-173	0.30	0.43	0.029	0.020	1.15	0.32	0.42	5.52	0.060	(0.013)	1.50	0.0342	.	(0.002)	0.47	0.10	.	.	.	.	0.012
JSS 603-8	0.30	0.31	0.012	0.012	0.32	0.055	0.084	2.32	.	.	0.13	0.0250	.	.	0.46	5.47	.	.	.	.	.
IARM 341A	0.298	0.226	0.0038	0.0008	0.10	0.143	7.16	0.99	0.032	4.4	1.01	0.0025	(0.005)	0.003	0.086	(0.01)	Ca:0.0011	0.0005	0.0008	(0.001)	(0.005)
IMZ C-178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	0.015	0.20	0.0160	0.105	.	0.011	0.017	.	.	.	.	0.011
IMZ C-171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.036	0.024	1.23	0.057	.	(0.001)	0.26	.	.	.	.	.	0.008
IMZ C-170	0.155	0.50	0.018	0.014	0.32	0.285	0.63	8.82	0.11	(0.022)	0.88	0.065	0.087	(0.002)	0.24	(0.19)	.	.	.	.	0.007
IMZ C-176A	0.15	0.75	0.018	0.003	0.35	0.103	3.62	0.41	(0.058)	(0.010)	0.027	0.0129	.	.	(0.061)	(0.015)	.	.	.	.	0.009
IMZ C-179	0.114	0.83	0.016	0.003	0.375	0.164	9.98	0.20	0.061	0.016	0.12	0.0108	(0.004)	.	0.023	(0.023)	(0.007)	.	.	.	0.010
IARM FeF9-18	0.104	0.459	(0.011)	0.0036	0.345	0.093	0.148	8.72	.	0.013	0.94	0.0323	0.078	0.0028	0.214	0.0030	0.006	.	0.0025	.	0.0062
IMZ C-175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	(0.013)	0.025	0.0099	.	.	0.014	(0.019)	.	.	.	.	0.011
IMZ C-157	0.095	0.63	0.015	0.010	0.59	0.066	0.50	9.51	0.26	.	0.71	0.051	.	0.044	0.26	.	.	.	.	.	.
IMZ C-177	0.076	0.32	0.013	0.003	0.24	0.110	8.33	0.18	0.043	(0.017)	0.022	0.0089	.	.	0.010	.	.	.	.	.	0.008

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn
--------	---	----	---	---	----	----	----	----	----	----	----	---	----	----	---	---	----	---	---	----	----

**TOOL STEEL CHIPS**

# = Class, where 1 = CRM and 2 = RM      C14X: typical analysis 50g      IPT 50: 120g      NCS HC174xx, HC23503: 100g      other NCS, SRM: 150g      others: 100g

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	Sn
1	IARM Fe15V-18	3.51	0.39	0.022	0.010	0.89	0.084	0.123	5.5	.	.	0.018	1.24	.	0.0027	15.6	0.08	0.0054
1	CMSI 1406	2.00	0.294	0.049	0.0053	.	.	0.113	11.71	.	.	.	.	.	.	.	0.96	150g
1	IMZ 1.25/3	1.48	0.26	0.018	0.025	0.28	.	.	0.48	.	.	.	.	.	.	0.29	4.97	.
1	IPT 67	1.27	0.256	0.036	0.007	0.26	0.092	0.32	4.33	.	.	9.79	4.39	.	.	2.58	8.03	.
1	CMSI 1405	1.14	0.287	0.014	0.0046	.	0.040	0.073	0.183	.	.	.	.	.	.	.	2.31	150g
1	VS S26/5	1.0	0.4	0.02	0.01	0.4	0.14	0.2	4.0	.	.	5.5	0.3	.	.	2.3	10.0	.
1	NCS HC17405	0.941	0.441	0.023	0.028	0.521	.	0.095	1.99	.	.	.	0.122	.	.	0.18	19.22	.
1	IPT 50	0.916	0.280	0.031	0.015	0.326	0.091	0.33	4.49	.	.	0.260	5.54	.	.	2.00	6.40	.
1	VS S24/5	0.9	0.4	0.02	0.01	0.2	0.2	0.2	3.0	.	.	0.07	3.4	.	.	2.2	5.5	.
1	ECRM 254-1	0.88	0.30	0.023	0.029	0.19	0.09	0.12	5.12	.	.	0.32	4.92	.	.	1.94	6.97	0.019 last
1	SRM 132b	0.864	0.341	0.012	0.004	0.185	0.088	0.23	4.38	.	.	0.029	4.9	.	.	1.83	6.28	.
1	CMSI 1401	0.855	0.275	0.0261	0.011	0.232	0.041	0.046	4.08	.	.	.	4.84	.	.	2.02	5.99	100g
1	BCS 484	0.85	0.21	0.030	0.024	0.20	.	.	5.17	.	.	10.2	1.07	.	.	0.93	22.4	.
1	NCS HC28402	0.847	0.296	0.023	0.012	0.190	0.122	0.096	3.99	.	0.0020	0.023	5.06	.	0.0013	1.93	6.14	.
2	C14X HS30	0.84	0.59	0.019	0.020	0.58	0.04	0.33	4.65	.	.	10.1	1.06	.	.	1.17	19.1	.
1	ECRM 251-1	0.84	0.27	0.024	0.025	0.21	0.08	0.15	5.35	.	.	5.70	0.53	.	.	1.59	19.9	0.025
1	IMZ 1.14/4	0.83	0.33	0.028	(0.005)	0.35	.	0.16	4.09	.	.	.	0.45	.	.	1.23	17.30	.
1	NCS HC21401	0.828	0.283	0.028	0.0072	0.226	0.140	0.083	4.08	.	0.013	0.018	3.13	.	0.0044	1.33	9.23	0.017
1	SRM 134a	0.808	0.218	0.018	0.007	0.323	0.101	0.088	3.67	.	.	.	8.35	.	.	1.25	2.00	.
2	C14X HS10	0.79	0.29	0.020	0.022	0.195	0.05	0.10	3.93	.	.	0.51	1.11	.	.	0.90	16.8	.
1	NCS HC17406	0.78	0.427	0.024	0.020	0.230	.	0.134	3.64	.	.	.	0.176	.	.	0.44	18.72	.
1	VS S27/4	0.772	0.317	0.0154	0.0138	0.397	0.045	0.288	4.23	.	.	0.017	0.353	.	.	1.19	17.62	.
1	CMSI 1404	0.762	0.280	0.0241	0.026	.	0.038	0.040	4.03	.	.	.	0.245	.	.	1.30	18.16	100g
1	NCS HC20505	0.73	0.26	0.009	0.004	0.25	.	.	.	.	.	.	3.98	.	.	.	.	.
1	NCS HC17407	0.710	0.268	0.029	0.0064	0.183	.	0.187	4.29	.	.	.	0.266	.	.	1.05	17.64	.
1	VS S25/4	0.702	0.192	0.0057	0.0053	0.276	0.143	0.242	3.31	.	.	.	.	.	.	.	.	.
1	BCS 482	0.70	0.28	0.021	0.025	0.13	.	.	4.09	.	.	0.24	0.27	.	.	0.98	18.1	.
1	BCS 481	0.69	0.29	0.021	0.027	0.14	.	.	3.56	.	.	0.21	0.22	.	.	0.52	14.2	.
1	BCS 483	0.67	0.29	0.019	0.025	0.11	.	.	3.21	.	.	1.94	0.17	.	.	0.54	10.8	.
1	NCS HC17408	0.577	0.233	0.015	0.0043	0.383	.	0.231	2.70	.	.	.	0.330	.	.	0.81	16.24	.
1	IPT 145	0.558	0.716	0.016	0.011	0.259	0.051	1.61	1.14	0.023	0.021	0.024	0.494	.	.	0.094	.	.
1	IPT 117	0.515	0.557	0.019	0.011	0.349	0.070	3.01	1.03	.	0.026	0.014	0.292	.	.	0.015	0.060	.
1	VS S28/5	0.503	0.339	0.0091	0.0044	0.888	0.024	0.605	6.02	1.59	.	0.0073	0.599	Pb:0.00015	.	0.64	3.46	Sb: 0.0004 Zn: 0.0012
1	CMSI 1182	0.503	0.326	0.0212	0.015	0.592	0.028	0.140	1.14	.	.	.	.	.	.	.	2.22	.
1	NCS HC17409	0.493	0.343	0.304	0.0048	0.493	.	0.278	4.78	.	.	.	0.411	.	.	1.49	14.96	.
1	VS S60	0.405	0.634	0.0206	0.0071	0.932	0.120	0.405	13.10	.	.	.	0.135	.	.	0.137	.	.
1	IARM 255B	0.389	0.317	0.010	(0.002)	0.91	0.073	0.062	4.82	0.032	.	0.0090	1.30	(0.006)	.	0.515	.	(0.006)
1	IPT 114	0.388	0.361	0.021	0.0023	1.02	0.064	0.165	5.20	.	0.028	0.018	1.29	.	.	0.89	0.174	.
1	CMSI 1402	0.359	0.298	0.0211	0.021	.	0.030	0.0208	2.48	.	.	.	0.055	.	.	0.27	8.39	100g
1	IRSID 112-1	0.348	0.191	.	.	1.00	0.115	0.234	4.78	.	.	.	1.21	.	.	0.604	1.78	.
1	IMZ 1.13/3	0.33	0.38	0.023	0.007	0.23	0.13	1.52	2.61	.	.	.	.	.	.	0.29	8.31	.
1	NCS HC17414	0.322	2.719	0.0228	0.0177	1.16	.	0.862	4.43	1.955	.	2.939	6.16	0.497	.	1.083	9.22	.
1	IMZ 1.26/2	0.31	0.48	0.021	0.009	0.29	0.14	4.05	1.87	.	.	.	0.11	.	.	.	1.70	.
1	CMSI 1254	0.177	0.509	0.021	0.005	0.27	0.083	4.06	1.51	.	.	.	.	.	.	.	1.34	.
1	IMZ 1.43	0.14	0.66	(0.010)	0.013	0.60	.	1.06	10.83	.	.	.	0.82	(0.43)	.	0.69	0.92	last of stock
1	SRM 133b	0.128	1.07	0.018	0.328	0.327	0.080	0.230	12.63	<0.005	.	.	0.052	.	.	0.071	.	(0.004)
1	VS S23/5	0.047	0.216	0.0062	0.0066	0.445	0.024	0.054	5.02	.	.	.	.	.	.	0.515	.	0.74
1	BCS 422	(0.036)	(0.09)	(0.015)	(0.025)	(0.06)	.	.	.	.	.	.	.	.	.	.	1.28	.
1	BCS 423	(0.030)	(0.07)	(0.017)	(0.027)	(0.05)	.	.	.	.	.	.	.	.	.	.	2.06	.
1	BCS 424	(0.024)	(0.09)	(0.02)	(0.024)	(0.05)	.	.	.	.	.	.	.	.	.	.	3.02	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	Sn
---	--------	---	----	---	---	----	----	----	----	----	-----	----	----	----	----	---	---	----



BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

LOW NICKEL STAINLESS STEEL CHIPS WITH NITROGEN

# = Class, where 1 = CRM and 2 = RM analysis listed in mass % except \* which is mg/kg C13X: typical analysis 100g CMSI, JK, JSS, SRM: 150 g chips all others: 100 g chips

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W	
1	IARM 13D	1.040	0.697	0.0195	0.0012	0.614	0.184	0.256	16.36	(0.006)	0.0212	0.488	0.0492	0.0074	0.0035	0.058	(0.008)	0.0005	(7)	0.0031	.	0.011	0.046	
1	IARM 353A	0.98	0.95	0.019	0.025	0.49	0.13	0.265	17.01	0.0018	0.032	0.50	0.027	(0.011)	0.0015	0.116	(0.004)	(0.0006)	(3)	(0.005)	Se:0.17	0.0056	0.041	
1	ECRM 291-1C	0.90	0.81	0.017	0.0088	0.91	0.071	0.56	17.15	.	0.0233	2.10	0.1142	.	.	0.39	.	.	.	.	.	.	.	
1	IARM Fe16-18	0.718	0.605	0.013	0.0017	0.264	0.027	1.34	0.71	0.020	0.007	0.237	0.0064	(0.003)	0.0033	0.008	0.0033	(0.0008)	.	0.0012	.	.	.	
1	IPT 22	0.628	0.804	0.029	0.009	0.449	0.050	0.143	16.21	.	.	.	0.008	.	.	.	.	.	.	.	.	.	.	
1	BAM 226-1	0.416	0.434	0.0207	0.0094	0.514	.	0.139	13.67	.	.	0.024	0.0362	.	.	0.022	.	.	.	.	.	.	.	
1	IARM 352A	0.341	1.13	0.0182	0.21	0.357	0.148	0.269	13.11	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028	(0.005)	(0.0007)	.	(0.005)	.	0.0046	(0.005)	
1	IARM 154C	0.339	0.423	0.0174	0.0043	0.37	0.120	0.215	12.41	(0.0034)	0.016	0.036	0.054	0.014	0.0015	0.043	(0.004)	0.0007	.	(0.0042)	.	0.0058	(0.005)	
1	ECRM 272-1C	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.2445	11.927	0.0046	0.0145	0.0030	0.0508	0.0028	0.00096	0.0167	0.0116	0.0018	9.0	.	.	.	.	
1	IMZ C-168	0.24	1.36	0.019	0.012	1.12	0.093	0.17	13.91	(0.004)	(0.019)	0.026	(0.057)	.	(0.003)	0.053	.	.	.	.	.	0.009	.	
1	IARM 205D	0.232	0.736	0.0209	0.0028	0.257	0.122	0.841	12.18	0.0021	0.043	1.002	0.0484	0.013	0.0022	0.319	0.004	0.0007	(20)	0.0053	(20)	0.0047	1.07	
1	IARM 20C	0.18	0.30	0.018	0.007	0.35	0.060	1.93	12.15	(0.004)	0.031	0.12	0.0222	0.010	(0.003)	0.086	.	.	.	.	0.0068	.	0.004	2.59
1	IMZ C-167	0.175	1.16	0.016	0.0025	0.755	0.106	0.16	13.07	(0.018)	(0.021)	0.024	0.053	.	(0.002)	0.054	.	.	.	.	.	0.009	.	
1	IARM Fe418-18	0.168	0.429	0.016	(0.0005)	0.32	0.22	2.00	12.4	(0.004)	0.029	0.104	0.031	(0.019)	.	0.046	.	.	.	(0.004)	.	(0.005)	2.63	
1	IARM 12C	0.155	0.55	0.022	0.0032	0.34	0.33	2.23	15.78	(0.004)	0.048	0.125	0.056	0.020	(0.002)	0.040	(0.004)	0.0004	7	(0.005)	(5)	0.008	0.015	
1	IARM 335A	0.138	0.85	0.016	0.0005	0.39	0.086	4.27	15.30	0.019	0.063	2.72	0.085	0.015	(0.002)	0.094	(0.01)	0.0007	(10)	0.0020	.	0.0034	0.008	
1	IARM Fe410-18	0.132	0.50	0.017	0.0014	0.29	0.046	0.280	12.2	(0.003)	0.012	0.146	0.046	0.0021	.	0.065	.	.	.	(0.009)	.	.	(0.008)	
1	ECRM 296-1C	0.1166	0.676	0.0178	0.0026	0.242	0.1498	2.790	11.82	0.0275	0.0218	1.700	0.0214	.	.	0.363	0.0139	(0.0003)	.	.	1.6	0.0131	.	
1	IARM Fe416-22	0.114	0.83	0.019	0.37	0.39	0.064	0.230	12.98	(0.0016)	0.019	0.027	0.036	(0.004)	0.0015	0.038	(0.003)	.	.	(0.008)	.	0.0041	(0.004)	
1	IARM 291A	0.11	0.71	0.016	0.009	0.23	0.060	2.62	11.3	(0.004)	0.021	1.61	0.035	0.022	0.0011	0.29	.	0.001	.	0.014	.	0.004	(0.01)	
1	IARM 14C	0.061	0.385	0.021	0.0015	0.63	0.19	0.364	24.9	0.0041	0.043	0.101	0.058	0.013	0.013	0.078	(0.003)	0.0005	.	(0.006)	(1)	0.004	0.031	
1	JSS 670-4	0.0480	1.489	0.0201	0.0093	0.731	0.1093	0.201	11.15	0.0278	.	0.0996	.	.	.	.	.	.	.	.	.	.	.	
1	SRM 345b	(0.043)	0.4902	0.0176	(0.0008)	0.7821	3.000	4.054	16.03	(0.013)	0.0660	0.1541	(0.013)	0.2143	(0.007)	0.0662	(0.0031)	<0.001	.	(0.014)	(20)	0.00568	0.0394	
1	JSS 650-15	0.0356	0.487	0.0369	0.00411	0.257	0.0311	0.215	16.11	0.00203	0.0166	0.0939	0.0446	.	.	0.0239	.	.	.	.	.	.	last	
1	JSS 650-16	0.0334	0.493	0.0268	0.00387	0.238	0.0153	0.1191	16.27	0.00143	0.0110	0.0330	0.0454	.	.	0.0267	.	.	.	.	.	.	.	
1	IARM 355A	0.0274	0.47	0.0186	0.31	0.435	0.083	0.427	17.81	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038	(0.004)	(0.0011)	.	(0.010)	(2)	(0.005)	(0.018)	
1	IARM 317A	0.025	1.26	0.028	0.0007	0.39	0.21	4.19	22.5	0.005	0.064	0.249	0.123	(0.004)	(0.002)	0.061	(0.006)	0.0019	(3)	0.0032	.	0.008	0.015	
1	NCS HC41318	0.023	1.25	0.030	0.0013	0.421	0.136	4.85	22.26	.	0.047	3.11	0.175	0.014	0.0014	0.038	0.0085	.	.	.	.	0.0032	0.011	
1	IARM 327A	0.018	0.54	0.018	0.0010	0.43	0.082	3.83	12.73	(0.003)	0.019	0.53	0.0157	0.008	0.0026	0.036	(0.004)	(0.001)	.	0.0047	.	0.006	0.009	
1	IARME155PH-18	0.015	0.616	0.021	(0.0004)	0.430	3.35	4.79	15.13	0.014	0.024	0.129	0.0494	0.273	.	0.055	(0.0026)	(0.0005)	.	0.0028	.	0.0021	0.019	
1	IARM Fe409-20	0.010	0.387	0.021	(0.0007)	0.52	0.0655	0.110	11.28	0.017	0.019	0.011	0.010	0.0041	0.141	0.075	0.0026	.	Zn:0.010	.	Sb:0.0011	0.0053	0.0036	
1	JSS 670-3	0.008	0.53	0.020	(0.0005)	0.55	0.044	0.21	11.23	(0.0055)	.	0.020	0.0064	.	0.26	.	.	.	.	.	.	.	.	

LOW NICKEL STAINLESS STEEL CHIPS

# = Class, where 1 = CRM and 2 = RM C13X: typical analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units
1	IMZ 1.38	1.08	1.14	0.010	0.016	0.94	0.34	0.63	19.12	.	0.021	.	.	.	0.033	0.0023	.	.	.	.	100 g
1	ECRM 278-1	0.903	0.405	0.0154	0.0052	0.336	0.077	0.236	18.11	.	.	1.040	.	.	0.077	.	.	.	.	.	100 g
1	IMZ 1.44	0.43	0.86	0.015	0.013	0.87	0.077	1.08	17.07	.	.	1.29	.	.	.	.	.	.	.	.	100 g
1	IRSID 201-1	0.291	0.363	.	.	0.843	0.099	0.202	12.33	.	.	0.050	.	.	.	.	.	.	.	.	100 g
1	BCS 339	0.29	0.41	0.022	0.022	0.36	(0.08)	0.37	12.40	.	.	.	.	.	.	.	.	.	.	.	100 g
1	BCS 469	0.279	0.598	0.015	0.020	0.421	(0.02)	0.246	11.93	.	.	.	.	.	(0.02)	.	.	.	.	.	100 g
1	BCS 472	0.227	1.02	0.032	0.029	1.05	(0.02)	1.95	15.82	.	.	0.661	.	.	(0.02)	.	.	.	.	.	100 g
1	IPT 26	0.201	0.713	0.022	0.012	0.306	0.029	0.413	13.69	.	.	0.070	.	.	.	.	.	.	.	.	100 g
2	C13X 150240	0.20	0.66	0.042	0.035	0.77	0.36	3.00	14.9	.	0.10	0.26	0.17	.	.	.	.	.	.	.	50 g
1	BCS 342	0.18	0.91	0.030	0.026	0.92	(0.08)	2.16	16.15	.	.	0.69	.	.	.	.	.	.	.	.	100 g
1	BCS 340	0.18	0.38	0.024	0.020	0.35	(0.06)	0.40	16.35	.	.	.	.	.	.	.	.	.	.	.	100 g
1	BCS 473	0.172	0.494	0.019	0.030	0.604	(0.03)	(0.06)	9.06	.	.	0.95	.	.	(0.02)	.	.	.	.	.	100 g
1	BCS 470	0.153	0.235	0.024	0.035	0.335	(0.02)	0.369	17.68	.	.	.	.	.	(0.02)	.	.	.	.	.	100 g
1	VS S32/4	0.136	0.368	0.0115	0.0141	0.338	0.152	2.97	13.73	.	.	0.050	.	.	0.205	.	.	.	W:1.82	.	100 g
1	NCS HC28318	0.134	0.456	0.027	0.0067	0.505	0.127	1.78	16.26	.	0.051	0.152	.	(0.002)	0.074	0.0064	.	.	(0.0001)	0.0058	50 g
2	C13X 147750	0.13	1.47	0.060	0.074	0.59	0.22	1.79	17.84	.	0.16	0.51	0.72	.	.	.	.	.	.	.	50 g
1	VS S34/5	0.106	0.232	0.0135	0.0035	0.519	0.159	3.97	15.52	.	.	.	0.089	.	0.511	0.58	.	.	.	.	100 g
1	IMZ C-156	0.101	0.84	0.031	0.008	1.11	0.071	0.64	16.96	(0.034)	(0.033)	0.035	.	(0.032)	0.073	.	.	.	.	.	100 g
1	BCS 341	0.100	0.43	0.016	0.024	0.31	(0.10)	0.56	24.00	.	.	.	.	.	.	.	.	.	.	.	100 g
1	BCS 471	0.095	0.417	0.018	0.023	0.326	(0.02)	0.96	23.85	.	.	.	.	.	(0.03)	.	.	.	.	.	100 g
1	IMZ C-158	0.091	1.34	0.015	0.007	2.23	0.097	0.24	25.51	1.56	.	0.025	.</								



STAINLESS STEEL CHIPS AND POWDER WITH NITROGEN

# = Class, where 1 = CRM and 2 = RM		analysis listed in mass % except * which is mg/kg											Cl3X: typical analysis					JK, JSS, VS S44-2: 150 g chips								NILAB: 150 g powder				all others: 100 g chips							
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W														
1	IARM 339A	0.16	1.71	0.004	0.009	0.64	0.021	12.9	17.0	0.004	0.007	2.79	0.0060	(0.005)	(0.002)	0.007	(0.001)	0.0006	14	0.016		(0.002)	(0.019)														
1	IARM 241D	0.125	1.94	(0.003)	0.0023	1.00	0.242	8.98	18.12	0.022	0.022	(0.02)	(0.008)	0.028	0.018	0.031	(0.001)	0.0016	(12)	(0.005)	(3)	(0.022)	(0.012)														
1	IMZ C-166A	0.108	1.99	0.019	0.005	2.51	0.025	21.93	25.53	0.036	0.030	(0.025)	0.077	.	0.003	0.038	(0.0026)	.	.	.	.	(0.0035)	.														
1	IMZ C-164	0.100	1.77	0.019	0.002	0.82	0.26	6.75	20.96	0.040	0.035	3.48	0.249	0.049	(0.003)	0.053	(0.005)	.	.	.	.	(0.003)	(0.025)														
1	IARM 234C	0.092	1.93	0.0090	(0.0027)	0.88	3.41	9.00	18.15	0.035	0.034	0.012	(0.01)	0.053	0.026	0.055	(0.001)	0.0023	(17)	(0.005)	(10)	0.0017	(0.006)														
1	VS S41/5	0.085	1.51	0.018	0.0069	1.41	0.155	8.85	18.65	.	.	.	0.142	.	.	2.04	(0.005)	.	.	.	.	(0.002)	.														
1	IMZ C-165	0.082	0.98	0.017	0.007	1.42	0.040	19.01	23.28	0.038	0.029	0.025	0.105	.	(0.002)	0.042	(0.003)	.	.	.	.	0.003	.														
1	IARMF177PH-18	0.080	0.730	0.020	(0.0005)	0.51	0.36	7.11	17.08	1.09	0.048	0.350	0.0153	0.009	0.083	0.062	.	(0.0017)	.	.	.	(0.006)	(0.011)														
1	ECRM 270-1C	0.0742	0.540	0.0196	0.0007	1.517	0.1076	10.86	20.88	(0.0023)	0.0685	0.2099	0.1417	.	(0.0019)	0.0256	(0.0034)	Ce:0.0487	17	0.0052	(1)	0.006	(0.0244)														
1	IARM 316A	0.070	0.61	0.023	0.0011	1.50	0.19	10.81	21.07	0.006	0.118	0.250	0.16	(0.003)	(0.002)	0.042	0.007	Ce:0.064	17	0.0052	(1)	0.006	0.022														
1	BAM 237-1	0.068	1.443	0.032	0.012	0.482	0.123	10.32	17.24	.	0.221	0.306	0.035	0.660	.	0.057	.	.	.	.	.	.	.														
1	BCS 465/1	0.066	1.380	0.021	0.012	0.405	0.098	9.24	17.31	0.026	0.053	0.092	0.010	.	0.40	0.102	.	0.0006	.	.	.	.	.														
1	ECRM 286-2	0.0640	1.919	0.0306	0.305	0.394	0.370	8.436	17.65	.	0.1490	0.413	0.0350	.	.	0.0951	.	.	.	.	.	0.0097	.														
1	IARM Fe304H-18	0.052	1.82	0.031	0.027	0.298	0.460	8.35	18.4	(0.005)	0.136	0.43	0.072	(0.010)	.	0.075	0.0076	.	.	(0.008)	.	(0.014)	0.027														
1	JSS 651-16	0.0514	0.925	0.0353	0.00384	0.557	0.350	8.04	18.12	0.0017	0.217	0.278	0.0604	.	.	0.074	.	.	.	.	.	.	.														
1	IARM 253B	0.051	1.61	0.13	0.011	0.46	0.44	9.11	17.64	(0.004)	0.145	0.59	0.031	0.021	0.0027	0.092	0.0052	0.0007	.	0.007	Se:0.13	(0.012)	(0.05)														
1	IPT 98 **	0.050	1.88	0.042	0.016	0.26	0.292	11.01	16.75	0.073	0.125	1.92	0.0112	.	0.41	0.053	.	.	.	.	.	0.019	0.053														
1	ECRM 269-1C	0.0499	1.262	0.0313	0.0010	0.441	0.366	8.044	18.150	.	0.1116	0.397	0.0460	0.0242	0.0006	0.0991	0.0061	.	.	.	.	0.0099	0.0306														
1	IARM 8H	0.049	1.81	0.0250	(0.002)	0.40	0.192	9.08	17.14	(0.005)	0.083	0.237	0.027	0.48	0.0027	0.049	.	(0.0002)	.	(0.004)	.	(0.008)	(0.016)														
1	IARM 6i	0.049	1.76	0.0208	(0.023)	0.31	0.202	9.20	17.76	0.084	0.052	0.133	(0.013)	(0.018)	0.60	0.048	(0.005)	0.0034	.	0.0012	.	(0.0060)	(0.023)														
1	JSS 654-16	0.0486	0.924	0.0210	0.00051	0.663	0.0634	19.16	24.61	0.00230	0.0996	0.0603	0.0345	.	.	0.0552	.	.	.	.	.	.	.														
1	IPT 24A	0.048	1.53	0.035	0.020	0.510	0.32	11.12	17.37	.	(0.16)	2.47	(0.036)	.	.	.	.	.	.	.	.	.	.														
1	ECRM 281-1	0.048	0.786	0.012	0.016	0.929	0.076	9.37	18.17	.	0.023	.	0.023	.	0.216	.	0.0012	.	.	.	5	.	.														
1	IARM 4F	0.047	1.17	0.0195	0.0015	0.494	0.146	20.1	24.5	0.015	0.067	0.142	0.056	0.007	0.0031	0.146	(0.003)	(0.0012)	(20)	(0.004)	.	(0.005)	0.012														
1	IARM Fe303-18	0.046	1.55	0.033	0.35	0.47	0.61	8.12	17.2	.	0.140	0.42	0.069	0.015	.	0.072	0.007	(0.0012)	.	(0.006)	.	(0.015)	0.029														
1	JSS 651-14	0.046	1.19	0.027	0.0058	0.67	0.12	9.03	18.26	(0.002)	0.17	0.11	(0.0426)	.	.	.	.	.	.	.	.	.	.	last of stock													
1	IARM 4G	0.0454	1.36	0.027	0.0008	0.630	0.320	19.2	24.9	0.008	0.085	0.580	0.058	0.008	0.029	0.092	(0.005)	0.0032	(10)	(0.003)	(5)	0.008	0.017														
1	JSS 655-10	0.045	0.96	0.024	(0.0005)	0.63	0.045	9.75	17.53	(0.003)	(0.073)	0.033	0.0072	0.49	.	.	.	.	.	.	.	.	.														
1	IARM 4E	0.044	1.07	0.0224	0.0006	0.514	0.234	20.18	24.25	0.004	0.066	0.32	0.038	0.024	Ta:0.005	0.052	(0.005)	0.0011	.	0.0021	.	0.0060	0.046														
1	IARM 8i	0.0424	1.395	0.0352	0.0118	0.38	0.441	9.01	17.08	(0.0030)	0.301	0.416	0.052	0.60	(0.008)	0.057	.	(0.0005)	.	(0.004)	.	(0.012)	0.060														
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W														
1	IARM 8G	0.042	1.468	0.0327	0.0126	0.36	0.390	9.02	17.20	0.0030	0.162	0.359	0.046	0.53	0.0024	0.062	(0.007)	(0.0005)	(5)	(0.003)	.	0.0107	0.032														
1	IARM 17D	0.041	4.15	0.026	0.0018	0.416	0.412	11.83	21.06	0.0032	0.23	1.52	0.311	0.14	0.010	0.118	0.005	0.001	(20)	0.003	(2)	0.0044	0.056														
1	NILAB 500HAC	0.041	1.541	0.024	0.012	0.720	0.182	11.00	16.93	.	0.139	2.73	0.1154	0.023	.	0.074	.	.	.	.	.	.	.														
1	IARM 6G	0.040	1.39	0.030	0.0006	0.37	0.41	9.14	17.15	0.030	0.150	0.330	0.011	0.013	0.440	0.089	.	0.0004	.	0.0017	.	0.014	0.033														
1	JSS 653-16	0.0387	1.426	0.0252	0.00034	0.610	0.106	14.26	23.18	0.022	0.167	0.119	0.0384	.	.	0.071	.	.	.	.	.	.	.														
1	JSS 652-16	0.0369	0.938	0.0327	0.00148	0.628	0.272	10.06	16.80	0.0022	0.209	2.06	0.0224	.	.	0.089	.	.	.	.	.	.	.														
1	ECRM 292-1C	0.0367	1.744	0.0175	0.0055	0.402	0.0391	10.09	18.00	(0.002)	0.0255	0.0464	0.0640	0.571	.	.	(0.008)	.	(6)	.	.	.	.														
1	IARM 21D	0.032	0.052	0.008	(0.0014)	0.039	0.017	8.29	12.69	1.03	0.078	2.23	0.0037	(0.005)	0.016	0.017	.	.	.	.	.	.	(0.012)														
1	IARM 15C	0.032	0.760	0.019	0.0018	0.26	1.54	6.35	14.39	(0.005)	0.024	0.722	0.0148	0.63	(0.002)	0.041																					

## STAINLESS STEEL CHIPS AND POWDER

# = Class, where 1 = CRM and 2 = RM

C13X: typical analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units
1	IMZ 1.45	0.34	0.84	0.028	0.012	2.67	0.38	5.23	27.89	.	.	0.59	.	.	.	.	.	.	.	.	100 g
1	VS S30/4	0.293	0.510	0.0117	0.0053	2.51	.	6.39	12.74	.	.	.	0.060	.	.	.	.	.	.	.	100 g
1	BCS 468/1	0.143	1.70	0.014	0.020	1.41	.	8.90	17.96	.	0.018	.	.	.	.	.	.	.	.	.	100 g
1	NCS HC28315	0.110	0.841	0.024	0.0082	0.780	0.089	18.02	23.71	0.0056	0.102	0.115	0.016	(0.003)	0.077	0.0042	.	.	0.0004	0.0025	50 g
1	BCS 462	0.092	0.74	0.010	0.018	0.46	.	12.55	12.35	.	.	.	.	.	.	0.007	.	.	0.0005	.	100 g
last of stock																					
2	C13X 190030	0.09	1.60	0.063	0.029	0.59	0.08	13.1	18.9	.	.	2.50	0.11	.	.	.	.	.	.	.	50 g
2	C13X 180040	0.09	1.53	0.077	0.017	1.30	0.02	11.98	21.84	.	0.16	0.60	0.78	.	.	.	.	.	.	.	50 g
1	BCS 463	0.088	0.77	0.015	0.017	0.51	.	9.65	18.29	.	.	.	.	.	.	.	(0.0004)	.	.	.	100 g
1	ECRM 282-1	0.086	1.64	0.019	0.0042	0.734	0.109	10.86	16.72	.	.	2.19	.	0.488	.	.	.	.	.	.	100 g
1	IMZ 1.12/4	0.084	1.47	0.040	0.013	0.30	.	10.14	17.41	.	.	1.96	.	0.52	.	.	.	.	.	.	100 g
1	NM 220	0.084	1.35	(0.030)	0.013	0.56	0.12	8.70	19.26	.	0.16	.	.	.	.	.	.	.	.	.	100 g
1	DSZU CX06	0.082	1.20	0.026	0.0118	0.64	0.16	10.23	18.40	(0.1)	(0.04)	(0.13)	.	0.56	(0.03)	(0.01)	.	.	.	.	100 g
1	IMZ C-154	0.076	2.18	0.040	0.16	0.89	0.33	9.86	17.71	(0.16)	0.105	2.58	.	1.00	0.073	.	.	.	.	.	100 g
1	VS S62	0.071	0.064	(<0.001)	0.0128	0.032	0.0083	13.00	17.24	(0.02)	.	.	.	0.030	.	.	Ca:0.058	.	O:(0.35)	.	100 g
2	C13X 190020	0.07	1.05	0.031	0.053	0.76	0.105	9.18	17.1	.	.	1.99	0.07	.	.	.	.	.	.	.	50 g
1	NCS HC28316	0.067	1.10	0.028	0.021	0.435	0.166	10.39	16.80	0.012	0.063	2.01	0.027	(0.006)	0.048	0.0037	.	.	0.0005	0.0034	50 g
1	IARM Fe309-18	0.066	1.61	0.029	(0.002)	0.30	0.430	12.2	22.42	.	0.248	0.357	0.021	W:0.063	0.073	0.0065	.	.	Sb:0.0018	0.012	100 g
1	IMZ C-152	0.065	1.42	0.010	0.0025	0.52	0.061	9.48	18.04	.	.	0.017	.	.	0.030	.	.	.	.	.	100 g
1	BCS 332	0.063	0.80	0.015	0.020	0.44	(0.10)	12.45	12.80	.	(0.037)	.	.	.	.	(0.02)	.	.	.	.	100 g
1	BCS 333	0.066	0.79	0.016	0.020	0.45	.	9.49	18.7	.	.	.	.	.	.	.	.	.	.	.	100 g
1	VS S43/4	0.058	0.408	0.0153	0.0048	0.717	0.122	10.20	19.69	.	.	5.02	0.78	0.686	.	(0.004)	.	.	.	.	100 g
1	VS S38/6	0.056	1.60	0.0135	0.0030	0.970	0.096	8.47	17.06	.	.	.	.	0.445	.	.	.	.	.	.	100 g
1	IRSID 202-1	0.055	.	.	.	0.68	.	9.8	16.	.	.	2.30	.	0.54	.	.	.	.	.	.	100 g
1	IMZ 1.40	0.054	1.60	0.011	0.017	0.93	0.098	16.10	17.59	.	.	3.70	.	0.47	.	.	.	.	.	.	100 g
1	NCS HC41317	0.053	1.03	0.032	0.00071	0.571	0.383	9.19	17.17	.	0.132	0.154	0.0095	0.309	0.059	0.0047	.	.	W:0.018	0.013	50 g
1	SRM 339	0.052	0.738	0.129	0.013	0.654	0.199	8.89	17.42	.	0.096	0.248	.	.	0.058	.	.	.	Se:0.247	.	150 g
1	NCS HC28313	0.039	1.07	0.037	0.016	0.425	0.399	8.19	18.31	.	0.208	0.027	.	(0.002)	0.106	0.0035	.	.	(0.0001)	0.0051	50 g
1	VS S39/4	0.037	0.97	0.0092	0.0048	0.526	0.019	9.91	18.04	.	.	.	.	.	.	.	.	.	Se:0.213	.	100 g
1	BCS 462/1	0.0345	0.722	0.0053	0.0041	0.463	0.0112	12.85	11.8	.	.	0.0304	.	.	.	.	.	.	.	.	100 g
1	NCS HC28314	0.021	0.940	0.034	0.0028	0.414	0.043	8.11	18.21	.	0.216	0.025	.	0.006	0.089	0.0025	.	.	(0.0001)	(0.0001)	50 g
1	VS S37/5	0.018	1.43	0.0067	0.0079	0.696	0.133	12.28	17.39	.	0.0069	.	1.03	.	.	.	.	.	.	.	100 g
1	NCS HC28317	0.018	1.17	0.042	0.0057	0.317	0.334	10.34	16.61	.	0.185	2.05	.	(0.002)	0.070	0.0055	.	.	(0.0001)	0.0073	50 g
1	VS S29/4	0.017	0.636	0.0099	0.0026	0.751	0.018	19.02	11.39	0.149	.	.	.	2.88	0.0099	Sb:0.00027	.	.	0.00017	0.0006	100 g
1	NCS HC28320	0.013	1.17	0.033	0.0021	0.464	1.49	24.23	19.67	0.024	0.096	4.47	0.042	(0.002)	0.086	0.0053	.	.	(0.0001)	0.0043	50 g
1	BCS 461/1	0.0103	0.686	0.0053	0.0051	0.374	0.0091	6.124	14.727	.	(0.004)	0.0138	.	.	.	.	.	.	.	.	100 g
1	IARM 99D	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	9.24	4.8	(0.011)	0.67	(0.037)	.	0.0026	.	(0.010)	.	100 g
1	JK 25	.	(1.7)	.	.	.	.	(11.3)	(22.3)	.	.	(0.1)	.	.	.	.	.	0.096	.	.	150 g
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units

HIGH ALLOY STEEL CHIPS AND POWDER

# = Class, where 1 = CRM and 2 = RM		C13X: typical analysis 50 g chips										CMSI, JSS, JK, and SRM 126c: 150 g chips					NILAB: 150 g powder			all others: 100 g chips				
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other	
1	IMZ 1.39	0.23	1.75	0.022	0.009	1.96	.	35.23	15.57	.	.	.	.	.	.	.	.	.	.	.	.	.	.	
1	BAM 327-2	0.152	1.289	0.0228	0.0046	2.052	0.060	19.72	24.35	0.070	0.159	0.174	0.059	.	.	0.044	.	.	.	.	.	.	.	
1	BCS 464/1	0.086	0.791	0.020	0.028	0.57	.	20.05	25.39	.	0.054	.	.	.	.	.	.	(0.003)	.	.	0.0004	.	.	
1	BCS 467/1	0.082	0.788	0.018	0.019	0.52	.	9.21	18.09	.	.	.	.	0.99	.	.	.	0.004	.	.	0.004	.	.	
2	C13X 142110	0.08	0.70	0.006	0.016	1.72	0.31	12.4	26.05	.	0.08	0.30	.	0.18	.	.	3.29	.	.	.	.	.	.	
1	NCS HC41503	0.071	0.807	0.015	0.0006	0.36	0.038	32.27	20.72	0.299	0.050	0.297	.	.	0.49	.	.	.	.	.	.	.	.	
1	IARM 24B	0.053	0.82	0.009	0.0010	0.28	0.052	35.86	0.121	0.002	0.036	0.011	0.0017	<0.01	0.002	<0.005	<0.04	<0.005	(0.001)	0.003	.	0.0018	Se: 0.19	
1	BCS 479	0.0529	0.680	0.0029	0.0030	0.553	0.0052	24.87	19.922	(0.013)	(0.002)	(0.003)	0.0057	0.625	0.0306	0.0052	.	(0.002)	<0.0005	.	.	.	.	
1	BCS 475	0.050	0.89	0.037	0.008	0.21	1.94	5.66	14.14	0.013	0.22	1.59	.	0.22	.	.	.	.	.	.	.	0.015	.	
1	ECRM 289-1C	0.0489	1.016	0.0114	0.0027	0.531	.	24.68	14.63	0.199	0.065	1.102	.	.	2.01	0.260	.	.	0.0044	.	.	0.111	.	
1	IARM 15B	0.047	0.39	0.013	0.001	0.33	1.53	6.94	14.53	0.006	0.24	0.82	0.0355	0.65	0.005	0.033	0.12	.	.	0.0039	.	0.009	last	
1	IARM 26D	0.038	0.224	0.013	(0.0008)	(0.05)	0.047	24.6	14.29	0.29	0.040	1.23	0.0035	(0.007)	2.17	0.223	0.036	.	0.0063	.	.	0.0039	.	
1	VS S47/4	0.036	0.402	0.0062	0.0083	0.366	0.686	30.84	.	.	4.06	.	.	.	.	.	.	.	.	.	.	.	.	
1	ECRM 273-1	0.0336	0.785	0.0131	0.0004	0.378	3.046	4.85	14.747	.	0.0391	0.2462	0.0444	0.221	.	0.0512	.	0.0030	.	.	.	0.0021	.	
1	CMSI 1320	0.032	0.578	0.013	0.0036	0.238	0.030	22.43	4.04	0.0024	0.011	0.0019	(0.011)	.	0.0018	0.0047	(0.001)	0.0026	.	.	.	0.0022	last	
1	SRM 126c	0.02540	0.4684	(0.00350)	(0.0050)	0.1936	(0.0396)	36.054	(0.0625)	.	(0.0080)	(0.0110)	.	.	.	(0.001)	.	.	.	.	.	.	.	
1	BCS 474	0.022	1.70	0.008	0.020	0.17	0.35	14.74	19.06	.	(0.02)	3.55	.	.	.	0.30	.	0.030	.	.	.	.	.	
1	SRM 868	0.022	0.052	<0.003	0.0025	0.097	0.022	37.78	0.077	0.99	16.1	0.014	.	2.99	1.48	0.077	.	.	0.0078	.	.	.	.	
1	VS S33/4	0.020	0.733	0.0095	0.0058	0.354	.	22.48	15.25	.	.	.	.	.	1.38	.	4.38	.	0.0079	.	.	.	.	
1	VS S64	0.017	0.147	0.0023	0.0037	0.267	0.044	33.20	0.146	.	16.57	.	.	.	.	.	.	.	.	.	.	.	.	
1	ECRM 295-1C	0.0166	1.758	0.0167	0.0004	0.418	1.481	24.40	19.51	0.0203	0.0450	3.996	0.0615	.	.	0.0453	.	0.0041	0.0018	.	.	0.0025	last	
1	IARM 157D	0.0154	0.626	0.016	0.0005	0.28	0.196	23.9	20.31	0.020	0.102	6.08	0.203	0.149	0.009	0.050	0.036	.	0.0007	.	.	0.0036	Fe: 48.0	
1	ECRM 299-1C	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.172	22.32	5.33	0.0187	0.0186	0.0198	.	0.1289	0.0329	.	0.0054	0.0002	.	.	.	Zr: 0.1775	
1	NILAB 501HAC	0.014	0.858	0.020	0.003	.	0.761	17.69	19.79	0.003	0.159	6.14	0.2243	0.007	.	0.044	.	.	.	.	.	.	.	
1	VS S42/4	0.014	0.604	0.0105	0.0049	0.958	2.85	26.43	23.30	0.0140	.	2.68	.	.	0.270	.	.	.	.	.	.	.	.	
1	VS S66	0.0124	0.0270	.	0.0054	0.050	3.30	28.28	17.54	.	.	1.78	.	.	0.486	.	.	.	Ca:0.202	.	.	.	.	
1	ECRM 379-1D	0.0121	1.804	0.0166	0.0006	0.393	0.984	30.83	26.79	(0.00246)	0.0390	3.290	0.0550	(0.0028)	(0.0014)	0.0663	(0.0091)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.0021	Sb: 0.00057	
1	BCS 477	0.0102	1.623	0.0209	0.00039	0.473	1.340	25.07	20.38	0.0303	0.0875	4.23	0.0562	.	.	0.0527	.	0.00399	0.00198	.	Mg:0.00053	0.00453	Sb: 0.0078	
1	VS S46/5	0.01	0.4	0.002	0.003	0.1	.	29.3	.	.	17.2	.	.	.	.	.	.	.	.	.	.	.	.	
2	DH E2401	0.0048	0.0203	0.0013	0.0026	0.0222	0.0161	18.85	0.0405	.	11.46	4.64	Ca:0.0002	0.0023	1.28	0.0029	.	0.0038	.	Sb:0.0003	<0.0001	0.0016	Al.s:0.1013	
1	VS S65	0.0031	0.275	0.0201	0.0119	0.017	0.469	29.63	0.236	.	13.94	.	.	.	.	.	.	.	.	.	.	.	.	
1	VS S63	0.0024	0.402	0.0166	0.0113	0.175	0.284	27.73	0.016	.	18.63	.	.	.	.	.	.	.	.	.	.	.	.	

\* ECRM 295-1C also contains Fe: 48.36, Mg: (0.0003), and Sb: 0.0007      \*\* Provisional Analysis

## CAST IRON CHIPS WITH GRAPHITIC CARBON

analysis listed in mass %

IPT: 80 g

SRM: 150 g

all others: 100 g

Number	C	C.Grph	Mn	P	S	Si	Cu	Ni	Cr	Mo	Ti	V	As	Sn	Mg	N
IPT 75A	3.4	2.7	0.722	0.250	0.033	1.98	0.433	0.425	0.487	0.438	0.022	0.030	.	.	.	.
IPT 69	3.34	2.50	0.715	0.267	0.018	2.07	0.47	0.272	0.353	(0.004)	0.019	.	.	.	.	.
IPT 37B	3.37	2.85	0.737	0.148	0.069	1.66	0.052	0.074	0.088	.	0.034	.	.	.	.	last of stock
SRM 4L	3.21	2.66	0.82	0.149	0.043	1.33	0.240	0.042	0.118	0.040	.	0.024	.	.	.	.
NM 73 **	3.07	2.55	0.82	0.22	0.014	1.21	.	** Combined Carbon:	0.52%	.	.	.	.	.	.	.
VS Ch15/1	3.04	(0.2)	1.08	0.211	0.040	1.49	0.606	0.256	2.04	.	0.70	.	(0.006)	.	.	.
VS Ch6/11	3.01	(1.0)	0.776	0.289	0.031	2.38	.	0.79	0.261	0.318	0.028	.	Co:0.048	.	.	.
SRM 107c	2.99	1.98	0.480	0.079	0.059	1.21	0.205	2.20	0.693	0.83	(0.019)	(0.015)	.	.	.	.
VS Ch1/9	2.94	(2.1)	0.271	0.0125	0.0290	0.293	.	0.061	.	.	0.046	.	(0.004)	.	.	.
DSZU CH02X	2.90	(1.5)	1.08	0.006	0.013	1.36	(0.04)	0.66	0.59	0.23	0.16	.	.	(0.015)	.	.
SRM 6g	2.85	2.01	1.05	0.557	0.124	1.05	0.502	0.135	0.370	0.035	0.059	0.056	(0.042)	.	.	0.005
VS Ch19	2.73	1.73	0.250	0.074	0.028	0.202	.	0.081	0.067	.	0.038	.	0.0125	.	.	.
SRM 115a	2.62	1.96	1.00	0.086	0.064	2.13	5.52	14.49	1.98	0.050	0.020	0.014	.	.	.	.
ECRM 454-1	(2.53)	(1.96)	1.16	0.046	0.068	2.00	(0.07)	(0.21)	.	.	0.052	.	(0.025)	.	.	.
ECRM 453-1	(2.44)	(2.37)	0.72	1.63	0.049	3.17	0.10	0.068	0.053	.	(0.040)	0.050	0.019	.	.	.
VS Ch5/7	2.27	1.02	1.27	0.0115	0.0044	1.86	0.069	0.061	0.327	.	.	.	(0.005)	.	0.042	.
SRM 342a	1.86	1.37	0.274	0.018	0.00214	2.73	0.134	0.058	0.033	0.005	0.020	.	.	.	0.070	.
SRM 341	1.81	1.23	0.92	0.024	0.007	2.44	0.152	20.32	1.98	0.010	0.018	0.012	.	.	0.068	.
VS Ch17/1	1.66	(0.8)	1.32	0.0313	0.0087	2.08	0.0197	0.039	0.299	.	.	.	(0.002)	.	0.044	.

## CRM CAST IRON CHIPS

Number	C	Mn	P	S	Si	As	Units
NCS HC18009	3.83	0.74	0.186	0.023	1.88	0.025	100 g
NCS HC16023	3.8	0.929	0.171	0.016	1.42	.	150 g
NCS HC11003	3.77	0.659	0.230	0.129	1.47	.	100 g
NCS HC37011	3.73	0.565	0.117	0.067	2.58	.	100 g
NCS HC18010	3.66	0.59	0.145	0.041	2.399	0.036	100 g
NCS HC16024	3.59	0.514	0.315	0.033	1.96	.	150 g
NCS HC18011	3.43	0.729	0.079	0.0082	1.93	0.036	100 g
NCS HC18013	3.40	0.79	0.049	0.0087	2.12	0.013	100 g
NCS HC18014	3.36	0.792	0.049	0.0087	2.136	0.012	100 g
NCS HC11003a	3.36	0.561	0.166	0.176	1.39	.	100 g
NCS HC11003b	3.36	0.386	0.135	0.154	1.82	.	100 g
NCS HC18012	3.23	0.74	0.079	0.0080	1.93	0.037	100 g
NCS HC16026	3.22	0.726	0.085	0.059	2.25	.	150 g
NCS HC18016	3.20	0.42	0.104	0.0092	2.91	0.092	100 g
NCS HC18003	3.18	0.732	0.243	0.049	1.43	0.064	100 g
NCS HC11006	3.11	0.850	0.270	0.130	1.37	.	100 g
NM 18A	3.06	0.43	0.05	0.11	2.67	.	100 g
NCS HC13016	2.99	1.30	0.278	0.100	1.29	.	150 g
NCS HC39003	2.95	0.26	0.142	0.085	1.49	.	100 g
NCS HC18005	2.89	0.733	0.108	0.0058	2.01	0.091	100 g
NCS HC39001	2.85	0.38	0.081	0.096	2.48	.	100 g
NCS HC16022	2.83	0.721	0.094	0.067	2.19	.	100 g
NCS HC39002	2.81	0.57	0.062	0.134	1.71	.	100 g
NCS HC39004	2.78	0.78	0.066	0.082	2.17	.	100 g
NCS HC11004	2.72	0.359	0.124	0.115	2.56	.	100 g
NCS HC18002	2.67	1.36	0.051	0.031	2.94	.	150 g
NCS HC18006	2.65	0.75	0.114	0.0057	1.99	0.092	100 g
NCS HC39010	2.65	0.331	0.113	0.134	1.29	.	100 g
NCS HC39008	2.59	0.859	0.187	0.093	2.17	.	100 g
NCS HC15011	2.58	1.00	0.087	0.068	2.76	.	100 g
NCS HC13015	2.51	0.62	0.104	0.020	4.08	.	150 g
CTIF FG20	2.487	0.571	1.440	0.109	1.726	.	100 g
NCS HC39009	2.47	1.56	0.318	0.057	3.33	.	100 g
CTIF FG10	2.322	1.098	0.111	0.016	2.467	.	100 g
NCS HC11005	2.19	0.219	0.047	0.048	3.07	.	100 g

Number	C	Mn	P	S	Si	As	Units
--------	---	----	---	---	----	----	-------

CRM CAST IRON CHIPS WITH MAGNESIUM AND RARE EARTHS

unit sizes have been abbreviated as follows: A = 80 g, B = 100 g, and C = 150 g

Number	C	Mg	T.RE	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	As	Ce	La	Sn	Units	Other
NCS HC18011	3.43	0.030	.	0.729	0.079	0.0082	1.93	.	.	.	.	.	.	.	.	.	0.036	.	.	.	B	Re: 0.024
NM 207.3	3.13	0.026	.	0.83	0.21	0.016	1.23	0.029	1.90	0.37	.	.	.	.	.	.	0.036	.	.	.	B	
NCS HC37019	3.06	0.054	0.049	6.72	0.11	0.0041	5.80	.	.	.	.	.	.	.	.	.	.	.	.	.	A	
BS CE207 *	3.05	0.003	.	1.20	0.090	0.016	2.07	0.222	0.048	0.039	0.005	.	0.031	(0.001)	0.079	0.034	0.004	0.016	0.004	.	C	
ECRM 480-1	3.029	0.0172	.	0.1514	0.0021	0.0086	2.407	(0.0052)	0.4826	.	0.0163	.	.	.	.	.	.	.	.	.	B	
NCS HC28054	3.01	0.047	.	0.645	0.188	0.011	2.03	.	1.19	0.619	.	.	.	0.355	.	.	.	.	.	.	B	Nb: 0.095
NCS HC37020	2.88	0.068	0.047	6.40	0.11	0.0035	3.75	.	.	.	.	.	.	.	.	.	.	.	.	.	A	
NCS HC37021	2.79	0.028	0.045	8.77	0.10	0.0060	6.58	.	.	.	.	.	.	.	.	.	.	.	.	.	A	
NCS HC37018	2.78	0.049	0.041	6.80	0.12	0.0027	5.96	.	.	.	.	.	.	.	.	.	.	.	.	.	A	
NCS HC19017	2.77	0.070	0.070	0.570	0.015	0.014	2.52	0.046	0.031	0.042	.	.	0.037	.	0.072	0.356	.	.	.	.	B	
NCS HC11015	2.74	0.012	0.036	0.473	0.022	0.0009	2.32	0.031	0.627	0.040	.	0.021	0.011	0.0016	0.015	0.031	0.011	0.019	0.013	0.0037	A	N: 0.0047
NCS HC19018	2.70	0.083	0.083	0.625	0.024	0.011	3.10	0.049	0.031	0.043	.	.	0.035	.	0.125	0.405	.	.	.	.	B	
NCS HC19010	2.69	0.028	0.040	0.79	0.029	0.023	2.92	0.042	0.025	0.227	.	.	.	0.0016	0.109	0.236	.	.	.	.	B	
BS CE206 *	2.64	0.0006	.	0.99	0.145	0.018	2.76	0.45	0.048	0.068	0.004	.	0.029	0.007	0.078	0.038	0.004	0.011	0.004	.	C	
NCS HC37008	2.59	0.014	0.011	0.373	0.042	0.012	3.08	0.288	.	.	.	.	.	0.514	.	.	.	.	.	.	A	
CKD 230 *	2.55	0.040	.	0.31	0.049	0.024	1.04	1.05	1.11	0.09	.	0.01	0.01	0.05	0.01	0.02	0.005	0.01	(0.005)	0.010	B	Sb: 0.006
BS CE209 *	(2.47)	0.0013	.	0.39	0.167	0.027	2.13	0.211	0.045	0.010	0.006	.	0.030	(0.001)	0.062	0.030	0.003	0.026	0.008	.	C	
BS CE208 *	2.41	0.0008	.	0.34	0.118	0.041	1.63	0.212	0.047	0.007	0.003	.	0.031	(0.001)	0.048	0.024	0.004	0.018	0.007	.	C	
NCS HC19016	2.21	0.099	0.099	0.420	0.014	0.012	3.78	0.047	0.032	0.040	.	.	0.037	.	0.066	0.310	.	.	.	.	B	
NCS HC37005	1.92	0.073	0.059	0.955	0.041	0.0064	3.36	0.181	.	.	.	.	.	0.128	.	.	.	.	.	.	A	

Number	C	Mg	T.RE	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	As	Ce	La	Sn	Units	Other
--------	---	----	------	----	---	---	----	----	----	----	----	-----	----	----	----	---	----	----	----	----	-------	-------

\* Clearance Sale Item

## ALLOYED CAST IRON

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Als	Co	Mo	Ti	V	W	As	B	Bi	Pb	Sb	Sn	Units	Other
CRM																						
CMSI 1571	3.95	0.27	0.130	0.233	1.30	0.011	0.029	4.31	.	.	0.36	0.016	0.012	.	.	.	.	.	.	.	100 g	
NCS HC37001	3.40	0.99	0.060	0.054	1.35	1.22	0.63	13.54	.	.	1.03	.	.	.	.	.	.	.	.	.	50 g	
NCS HC13010	3.35	0.699	0.147	0.045	2.44	0.018	0.300	0.96	.	.	2.39	.	.	.	.	.	.	.	.	.	100 g	
SRM 892	3.33	0.76	0.054	0.015	1.83	0.270	5.53	10.18	.	0.31	0.20	.	0.041	.	.	.	.	.	.	.	150 g	
NCS HC13011	3.23	1.20	0.310	0.045	4.30	0.243	0.919	1.36	.	.	0.639	.	.	.	.	.	.	.	.	.	100 g	
CKD 227 *	3.2	0.95	0.66	0.037	1.67	0.33	0.05	0.68	0.04	0.03	0.60	0.07	0.11	0.06	0.01	0.007	0.0005	0.001	0.03	0.07	100 g	Zn: 0.01
NCS HC28034	3.15	0.795	0.321	0.082	1.67	1.04	.	0.464	.	.	0.515	0.053	.	.	.	.	.	.	.	.	150 g	
NCS HC37003	2.95	1.72	0.062	0.034	1.32	1.06	1.05	15.39	.	.	1.12	.	.	.	.	.	.	.	.	.	50 g	
CMSI 1569	2.86	1.07	0.058	0.028	0.36	0.42	0.25	22.52	.	.	1.14	0.005	0.039	.	.	.	.	.	.	.	100 g	
ECRM 482-2	2.599	0.728	0.0974	0.0491	1.815	1.231	2.284	0.675	.	.	0.454	.	.	.	.	.	.	.	.	.	100 g	
CMSI 1568	2.46	1.63	0.383	0.013	0.32	0.73	1.20	12.95	.	.	0.76	0.0089	0.026	.	.	.	.	.	.	.	100 g	
NCS HC37002a	2.42	0.71	0.058	0.064	1.05	0.90	0.23	8.93	.	.	1.74	.	.	.	.	.	.	.	.	.	80 g	
NCS HC11013	2.35	1.05	0.010	0.0094	1.05	.	.	15.06	.	.	2.84	0.062	0.16	.	.	.	.	.	.	.	100 g	
CMSI 1570	2.31	0.83	0.064	0.043	0.59	0.36	0.49	26.50	.	.	2.71	0.0051	0.039	.	.	.	.	.	.	.	100 g	
ECRM 451-2	2.059	1.079	0.0593	0.0315	2.092	6.26	14.01	1.097	.	.	.	.	.	.	.	.	.	.	.	.	100 g	
CTIF FA10	1.976	1.063	0.045	.	1.480	0.492	20.05	1.986	.	.	.	.	.	.	.	.	.	.	.	.	100 g	
NCS HC11012	1.95	0.926	0.0084	0.0079	0.59	.	.	13.11	.	.	0.52	0.064	0.137	.	.	.	.	.	.	.	100 g	
VS Ch18	1.91	4.27	0.095	0.0147	1.167	0.257	0.168	15.61	.	.	.	.	.	.	.	.	.	.	.	.	100 g	
CTIF FA20	0.643	0.368	0.045	.	1.519	.	.	28.30	.	.	.	.	.	.	.	.	.	.	.	.	100 g	
RM																						
BS CE 216 *	.	0.80	0.193	0.043	2.60	0.68	0.24	0.41	.	0.014	0.68	0.097	0.032	.	0.0070	.	.	.	0.00043	.	150 g	
BS CE 217 *	.	1.07	0.356	0.029	3.15	0.13	0.002	1.08	.	0.014	0.002	0.093	0.036	.	.	.	.	.	0.00041	.	150 g	
BS CE 219 *	.	1.23	0.505	0.038	2.47	0.415	0.228	0.31	.	0.014	0.283	0.080	0.034	.	.	.	.	.	0.00050	.	150 g	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Als	Co	Mo	Ti	V	W	As	B	Bi	Pb	Sb	Sn	Units	Other

\* BS and CKD Clearance Sale Items, BS CE items have no uncertainties

**CAST IRON CHIPS AND POWDER WITH CARBON OVER 3%**

unit sizes have been abbreviated so that: A = CRM, 100g and B = CRM, 150g and C = RM, 50g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	As	B	Cd	Ga	Pb	Sb	Sn	Tl	Units
ECRM 490-1	4.813	10.83	0.0267	0.0040	(0.03)	0.0088	(0.02)	0.0183	.	.	0.0030	0.0035	0.0152	.	.	.	.	.	.	.	.	A
JSS 102-10	4.66	0.244	0.127	0.0303	0.703	.	.	.	.	.	0.0053	0.0525	.	.	.	.	.	.	.	.	.	B
VS Ch13/1	4.16	1.11	0.067	0.034	2.90	0.91	0.454	1.30	.	1.16	.	.	.	(<0.002)	.	.	.	.	.	.	powder	A
NCS HC16027	4.06	0.094	0.038	0.029	0.725	0.0023	0.0023	0.010	0.038	0.0027	.	0.026	0.0064	0.0011	.	.	.	<0.0002	0.00013	0.00014	.	A
ECRM 478-2	4.003	0.321	0.201	0.0460	2.411	0.1276	0.151	0.251	.	.	0.0023	0.0328	0.0113	(0.0018)	0.0006	.	.	.	.	.	.	A
NCS HC16028	4.00	0.634	0.046	0.0073	1.55	0.0051	0.0045	0.036	.	0.0089	.	0.084	0.018	0.0012	.	.	.	<0.0002	0.00016	0.00018	.	A
ECRM 488-2	3.956	0.201	0.0111	0.1173	0.374	0.0256	0.1247	0.303	.	.	0.0052	0.0636	0.0545	.	.	.	.	.	.	0.0013	.	A
BCS 535	3.875	0.456	0.1438	0.0276	2.702	0.1397	1.349	0.0501	.	0.0037	.	Al:0.0087	.	As:0.0049	.	.	.	.	.	.	powder	A
BCS 527	3.873	0.316	0.1269	0.0366	1.000	0.0104	0.0229	.	.	.	.	0.0187	.	.	.	.	.	.	.	.	.	A
VS Ch14/2	3.81	1.05	0.061	0.034	2.09	0.427	1.52	0.724	0.265	0.625	.	.	.	(<0.005)	.	.	.	.	.	.	powder	A
NCS HC16010c	3.76	0.206	0.35	0.049	0.84	0.026	.	.	.	.	.	0.036	.	.	.	.	.	.	.	.	.	A
VS Ch2/7	3.61	0.079	0.078	0.071	0.836	0.142	0.222	0.218	0.124	0.444	.	0.293	0.521	(<0.002)	.	.	.	.	.	.	powder	A
NCS HC28015	3.58	0.97	0.080	0.014	3.02	0.091	0.0125	0.0075	.	.	.	.	.	.	.	.	.	.	.	.	.	B
ECRM 487-2 *	3.5730	0.0491	0.0065	0.0031	0.0898	0.0136	0.0219	0.0248	0.0151	0.0034	0.004	0.0022	0.0117	0.0045	.	.	.	.	.	.	last	A
CTIF FB20-2	3.557	(0.39)	(0.07)	0.0614	(0.935)	.	.	(0.10)	.	.	.	.	.	.	.	.	.	.	.	.	.	A
CTIF FB20-1	3.552	(0.39)	(0.07)	0.059	(0.935)	.	.	(0.10)	.	.	.	.	.	.	.	.	.	.	.	.	.	A
CMSI 1503B	3.53	1.10	0.066	0.048	1.83	0.258	.	.	.	.	.	0.025	.	.	.	.	.	.	.	.	.	A
NCS HC16004c	3.50	1.00	0.128	0.024	2.33	0.257	.	.	.	.	.	0.027	.	.	.	.	.	.	.	.	.	A
SRM 122i	3.47	0.530	0.28	0.087	0.89	0.033	0.047	0.151	0.28	0.008	.	0.024	0.012	.	.	.	.	.	.	.	.	B
CMSI 1572	3.46	1.05	0.252	0.062	3.15	0.263	0.132	0.202	.	0.047	.	0.047	0.007	.	.	.	.	.	.	.	.	A
NCS HC16008b	3.45	1.84	0.046	0.018	1.44	0.015	.	.	.	.	.	0.019	.	.	.	.	.	.	.	.	.	A
GBW 01108b	3.45	1.84	0.046	0.018	1.44	0.015	.	.	.	.	.	0.019	.	.	.	.	.	.	.	.	.	A
ECRM 476-3	3.390	0.987	0.0908	0.0493	1.813	0.2445	0.0549	0.0648	.	.	0.0038	0.0222	0.0115	0.0145	.	.	.	.	.	.	.	A
ECRM 487-1	3.27	0.094	0.0020	0.0007	0.0060	.	0.040	0.063	0.0088	.	0.0042	.	.	0.011	.	.	.	.	.	.	last	A
ECRM 492-1	3.258	.	.	0.0854	.	.	.	.	.	.	0.0048	.	.	.	.	.	.	.	.	.	.	A
ECRM 484-1	3.20	0.395	0.121	0.230	0.717	.	.	0.155	.	.	.	.	.	.	.	.	.	.	.	.	.	A
CMSI 1530	3.16	0.335	0.066	0.103	0.461	0.065	0.027	0.030	0.033	.	.	.	0.56	.	.	.	0.0078	.	.	last	0.225	A
NCS HC28035	3.15	0.685	0.49	0.076	1.44	0.915	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC28028	3.11	0.605	0.250	0.088	1.71	1.03	.	0.280	.	.	.	0.0494	0.023	.	.	.	.	.	.	.	.	B
NCS HC28014	3.05	0.57	0.300	0.079	2.67	0.194	0.018	0.022	.	.	.	.	.	.	.	.	.	.	.	.	.	B
GBW 01101B	3.04	1.22	0.072	0.052	1.34	0.025	.	.	.	.	.	0.008	.	.	.	.	.	.	.	.	.	A
CMSI 1501B	3.04	1.22	0.072	0.052	1.34	0.025	.	.	.	.	.	0.008	.	.	.	.	.	.	.	.	.	A
CMSI 1533	3.00	0.869	0.048	0.145	1.42	0.066	0.027	0.033	0.033	.	.	.	0.29	.	.	.	0.0077	.	.	.	0.254	A

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	As	B	Cd	Ga	Pb	Sb	Sn	Tl	Units
--------	---	----	---	---	----	----	----	----	----	----	---	----	---	----	---	----	----	----	----	----	----	-------

\* ERM 487-2 also contains: Al: 0.079, As: 0.0063, Te: 0.0064, and Zn: 0.0012

**CAST IRON CHIPS WITH CARBON UNDER 3%**

analysis listed in mass % except \* which is mg/kg

unit sizes have been abbreviated as follows: A = 80 g, B = 100 g, C = 150 g, and D = 200 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units
CRM																								
NM 201.8	2.99	0.44	0.054	0.11	2.64	0.035	0.024	0.030	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC28025	2.98	0.698	1.80	0.087	1.80	0.201	.	0.081	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC39011	2.96	0.57	0.082	0.058	1.67	.	.	.	.	.	.	.	.	.	.	.	0.061	.	.	.	.	.	.	C
VS Ch1-1	2.94	0.271	0.0125	0.0290	0.293	0.101	0.061	0.051	.	.	.	.	.	0.046	.	.	.	.	.	.	.	.	.	B
NCS HC28026	2.90	0.702	1.91	0.124	1.81	0.245	.	0.086	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	C
ECRM 489-1	2.860	(0.510)	0.815	0.155	1.524	0.274	.	.	.	.	.	.	(0.0056)	.	.	.	.	.	.	.	.	.	.	B
NCS HC39013	2.86	0.56	0.106	0.052	2.35	.	.	.	.	.	.	.	.	.	.	.	0.0101	.	.	.	.	.	.	B
NCS HC28029	2.85	0.85	0.086	0.0995	1.91	0.865	.	0.316	.	.	.	.	.	0.033	0.017	.	.	.	.	.	.	.	.	C
JSS 120-1	2.85	0.70	0.053	0.0095	1.32	0.29	0.12	0.28	.	.	.	(0.007)	0.0058	0.006	0.007	last of stock	.	.	.	.	.	.	.	C
VS ch6/1	2.82	0.803	0.267	0.037	2.76	.	0.716	2.73	.	.	0.096	0.215	.	0.093	.	.	.	.	.	.	.	.	.	B
CMSI 1506A	2.809	1.48	0.039	0.062	0.856	0.045	.	.	.	.	.	.	.	0.0118	.	.	.	.	.	.	.	.	.	C
VS Ch4/7	2.78	0.742	0.194	0.0276	1.60	0.221	0.525	0.706	.	.	.	.	.	.	.	(0.006)	.	.	.	.	.	.	.	B
ECRM 428-2	2.747	0.750	0.0691	0.1105	1.751	0.0996	0.0358	0.0366	.	.	.	.	.	0.0311	0.0120	0.0156	.	.	.	.	.	.	.	B
GBW 01106b	2.71	0.98	0.077	0.089	1.14	0.036	.	.	.	.	.	.	.	0.007	.	.	.	.	.	.	.	.	.	B
NCS HC16006b	2.71	0.98	0.077	0.089	1.14	0.036	.	.	.	.	.	.	.	0.007	.	.	.	.	.	.	.	.	.	B
NCS HC11007	2.70	1.66	0.201	0.102	1.72	0.031	.	0.589	.	.	.	.	.	0.014	0.0067	.	.	.	.	.	.	.	.	B
NCS HC28013	2.65	0.575	0.450	0.098	2.29	0.086	0.0675	0.041	.	.	.	.	.	0.041	.	.	.	.	.	.	.	.	.	C
VS Ch16/1	2.64	1.23	0.0237	0.049	0.864	0.242	4.15	1.77	.	.	.	.	.	.	.	(0.007)	.	.	.	.	.	.	.	B
NCS HC41010	2.64	0.540	0.086	0.029	1.49	0.056	0.030	0.086	.	.	.	0.021	.	0.024	0.011	.	.	.	.	.	.	.	.	C
NCS HC41011	2.64	0.725	0.177	0.033	2.23	0.146	0.035	0.151	.	.	.	0.105	.	0.031	0.014	.	.	.	.	.	.	.	.	C
SRM 5m	2.59	0.74	0.32	0.133	1.83	0.89	0.041	0.080	.	.	.	(0.029)	(0.006)	(0.097)	0.033	.	.	.	.	.	.	.	.	C
NCS HC41012	2.52	1.24	0.635	0.032	3.86	0.114	0.037	0.115	0.017	.	.	.	.	0.071	0.033	.	.	.	.	8	11	.	.	C
VS Ch20	2.41	1.84	1.46	0.053	0.594	0.050	0.157	0.170	.	.	.	.	.	0.0040	(0.015)	0.089	.	.	.	.	.	.	.	B
CMSI 1534	2.38	1.28	0.069	0.077	2.12	0.070	0.028	0.030	.	.	0.034	.	.	.	0.40	.	.	.	.	.	73	.	0.314	B
GBW 01109b	2.31	0.509	0.025	0.100	0.28	0.038	.	.	.	.	.	.	.	0.030	.	.	.	.	.	.	.	.	.	B

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units
NCS HC16009b	2.31	0.509	0.025	0.100	0.28	0.038	.	.	.	.	.	.	.	0.030	.	.	.	.	.	.	.	.	.	B
NCS HC37030	2.22	0.869	0.339	0.101	2.20	0.501	.	0.142	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC37041	2.22	0.869	0.339	0.101	2.20	0.501	.	0.142	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
ECRM 486-1	2.21	0.841	1.00	0.023	2.43	0.548	0.057	0.104	.	.	.	.	.	.	0.020	.	.	.	.	.	.	.	0.074	B
CMSI 1509A	2.202	0.528	0.0226	0.080	0.378	0.063	.	.	.	.	.	.	.	0.0094	.	.	.	.	.	.	.	.	.	C
NCS HC37029	2.15	1.08	0.451	0.068	2.69	0.752	.	0.221	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC37040	2.15	1.08	0.451	0.068	2.69	0.752	.	0.221	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
BCS 170/4 *	2.15	0.78	0.70	0.080	2.45	0.60	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
CTIF FB20	2.114	0.464	0.039	0.128	1.012	.	.	0.035	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC37013	2.11	0.353	0.167	0.139	1.70	.	.	0.119	.	.	.	.	.	.	.	.	.	25	.	.	.	.	.	A
IPT 49	2.11	0.272	0.012	0.019	0.78	0.040	0.021	0.020	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	A
NCS HC37028	2.04	1.34	0.479	0.038	3.37	0.642	.	0.197	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC37039	2.04	1.34	0.479	0.038	3.37	0.642	.	0.197	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC37042	2.04	0.670	0.226	0.103	1.86	0.176	.	0.054	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	B
NCS HC37038	2.01	0.677	0.057	0.115	1.44	.	.	0.113	.	.	.	.	.	.	.	.	.	15	.	.	.	.	.	B
NCS HC11008	1.90	1.96	0.060	0.097	2.72	0.041	.	0.766	.	.	.	.	.	0.013	0.0075	.	.	.	.	.	.	.	.	B
NCS HC37037	1.90	0.780	0.110	0.055	2.34	.	.	0.024	.	.	.	.	.	.	.	.	.	38	.	.	.	.	.	B
NCS HC37036	1.67	1.05	0.085	0.024	1.90	.	.	0.055	.	.	.	.	.	.	.	.	.	34	.	.	.	.	.	B
RM																								
VS Ch12-1	2.83	1.32	0.049	0.006	2.41	.	.	.	.	.	.	.	.	0.04	0.05	0.02	.	.	.	.	.	0.048	B	
CKD 215 *	2.46	0.76	0.087	0.17	3.08	0.43	0.081	0.15	.	0.01	.	0.05	.	.	.	.	.	.	.	.	.	.	.	D

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units
--------	---	----	---	---	----	----	----	----	----	-----	----	----	---	----	---	----	---	-----	-----	-----	-----	----	----	-------

\* Clearance Sale Item



CRM OTHER IRON BASE CHIPS AND POWDER

100 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Sn	Ti	V	W	As	B	O	Sb	Other
IARM Fe5140H-18	0.37	0.93	0.014	0.022	0.187	0.253	0.266	0.67	0.13	0.0081	0.031	0.007	(0.0015)	0.0069	0.0015	(0.0024)	(0.003)	(0.011)	.	.	.	.
IARM Fe422-22	0.239	0.687	0.021	0.0095	0.44	0.126	0.616	12.22	0.0024	0.022	0.97	0.050	0.013	0.0035	0.0017	0.210	1.03	0.0039	0.0006	0.0073	0.0009	Ca: 0.0029
IARM FeA100-18	0.222	(0.013)	(0.004)	(<0.0010)	(0.039)	(0.010)	11.2	2.98	(0.007)	13.4	1.19	(0.0010)	(0.003)	.	(0.008)	(0.007)	(0.006)	.	.	(0.0009)	.	.
IARM Fe8620-18	0.211	0.857	0.012	0.026	0.23	0.197	0.446	0.536	0.0246	0.0085	0.197	0.007	(0.0014)	0.0090	0.0015	0.0061	(0.004)	0.009	.	.	.	.
IARM Fe4820-18	0.192	0.541	(0.011)	0.0018	0.26	0.167	3.51	0.144	0.022	0.0107	0.287	0.007	(0.002)	0.0089	(0.0011)	0.0015	(0.004)	(0.006)	.	(0.003)	.	.
IARM FeE9310-18	0.121	0.62	0.009	0.0128	0.256	0.158	3.07	1.09	0.036	0.009	0.086	0.0070	.	0.0072	.	0.0030	.	.	.	(0.0017)	.	.
IARM FeDP1080-18	0.110	1.88	0.014	(0.006)	0.11	0.042	0.554	0.554	(0.002)	0.069	0.445	(0.009)	0.014	(0.0064)	(0.0013)	(0.0043)	(0.030)	.	.	(0.0055)	.	.
IARM Fe91-18	0.099	0.453	0.015	(0.002)	0.27	0.041	0.187	8.24	(0.006)	0.013	0.94	0.046	0.070	(0.004)	(0.0021)	0.198	(0.003)	.	.	(0.003)	.	.
IARM FeP92-18	0.092	0.737	(0.005)	(0.005)	0.20	0.074	0.82	9.4	(0.005)	0.036	0.52	(0.0036)	0.096	(0.006)	(0.003)	0.188	1.97	.	0.0026	(0.013)	.	.
IARM FeINVR36-22	0.0497	0.78	0.0041	0.0019	0.307	0.058	36.0	0.094	0.0023	0.010	0.012	0.0021	(0.0016)	0.0042	(0.0020)	0.0013	(0.0328)	0.0029	0.0019	(0.0042)	(0.0006)	Se: 0.21
IARM Fe174PH-18	0.041	0.47	0.024	(<0.0040)	0.52	3.33	4.73	15.10	0.007	0.047	0.315	0.0436	0.285	0.008	.	0.051	0.015	.	.	0.0035	.	.
IARM FeKovar-18	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068	.	17.3	0.062	.	.	0.0021	.	.	(0.020)	.	.	.	.	.
IARM FE2507-21	0.019	0.85	0.024	0.0005	0.36	0.125	7.12	25.2	(0.0051)	0.039	3.76	0.27	0.022	0.0034	0.0019	0.067	0.026	0.004	0.0024	(0.0048)	0.0015	Zr: 0.0013
IARM Fe254SMO-21	0.017	0.892	0.022	0.0010	0.301	0.77	18.1	19.7	0.022	0.118	6.09	0.200	(0.0083)	0.0041	0.004	0.052	0.041	0.0044	0.0009	0.0025	0.0017	Ca: 0.0024
IARM Fe2205-18	0.018	1.18	0.023	(0.0013)	0.46	0.208	5.57	22.6	(0.007)	0.104	3.20	0.17	(0.011)	(0.006)	(0.003)	0.063	0.024	.	.	(0.004)	.	.
IARM Fe415-21	0.018	0.640	0.028	0.013	0.42	0.198	3.55	11.64	0.0018	0.065	0.537	0.073	0.0049	0.0104	0.0013	0.086	0.042	0.0036	0.0008	0.0075	0.0019	.
IARM Fe904L-22	0.0133	1.14	0.020	0.0007	0.654	1.30	24.0	19.3	0.036	0.126	4.03	0.045	0.017	0.0051	0.0020	0.064	0.024	0.0044	(0.0005)	0.0018	0.0018	Ca: 0.0041
IARM Fe316LP-18	(0.006)	1.56	(0.011)	0.0041	0.29	0.0031	13.9	17.9	(0.006)	(0.006)	2.81	(0.081)	.	.	.	(0.006)	.	.	.	(0.043)	.	POWDER 75g
IARM FeC250-21	0.0028	0.022	0.0033	0.0006	0.0091	(0.0041)	18.6	(0.0093)	0.101	7.92	4.93	0.0004	0.0019	(0.0015)	0.418	(0.0074)	(0.0069)	(0.0011)	0.0029	0.0006	(0.0044)	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Sn	Ti	V	W	As	B	O	Sb	Other
--------	---	----	---	---	----	----	----	----	----	----	----	---	----	----	----	---	---	----	---	---	----	-------