

INDEX

ADMIRALTY BRASS 10
ALUMINUM 2, 3
ALUMINUM BRONZE 12
ANTIMONY 4
ARSENIC 4

BATTERY ALLOY 13
BISMUTH 4
BRASS 9, 10
BRONZE 11, 12

CADMIUM 4
CHROMIUM 4
COBALT 4
COPPER 5, 6, 7, 8, 9, 10, 12
COPPER ANODE 5
COPPER CONCENTRATE 6
COPPER-NICKEL-SILVER 8
CUPRO-NICKEL 8

ENVIROBRASS 6

FEDERALLOY 6

GUN METAL 8

IN 100 18

LEAD 13
LEAD-SILVER 13
LEADED BRASS 10
LEADED BRONZE 12

MAGNESIUM 14
MANGANESE 14
MANGANESE BRASS 10

NAVAL BRASS 10
NICKEL 14, 15, 16, 17, 18

PHOSPHOR BRONZE 12
PHOSPHORUS DEOXIDIZED COPPER 5

SEBILOY 6
SILICON BRASS 10
SOLDER 19
SPELTER 21
SUPERALLOYS 18

TIN 19
TITANIUM 20
TITANIUM POWDER 20
TUNGSTEN 21

ZINC 21, 22, 23
ZINC SPELTER 21
ZIRCALLOY-4 23

CRM ALUMINUM BASE CHIPS

analysis listed in mass % except * which is mg/kg

Number	Si	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sn	Sr	Ti	V	Zn	Zr	Al	B*	Be	Cd	Ga	Units
BAM 201	13.20	.	0.009	0.18	0.0024	0.38	0.20	0.09	0.17	.	0.011	.	0.038	.	.	.	.	.	.	100 g
BCS 595	12.8	.	0.05	0.30	0.05	0.52	0.046	0.056	0.027	.	0.03	.	0.24	.	.	.	.	.	.	100 g
BCS 182/3	11.03	.	0.037	0.51	0.067	0.26	0.37	0.11	0.10	0.018	0.107	(0.014)	0.128	(0.003)	.	Ca:(0.002)	.	.	.	100 g
SRM 856a	9.21	0.060	3.50	0.85	0.063	0.35	0.046	0.056	0.10	.	0.065	.	0.96	.	.	.	.	.	.	30 g
SRM 855a	7.07	0.013	0.13	0.14	0.37	0.060	0.016	0.019	0.010	0.018	0.15	(0.012)	0.085	(0.003)	.	Ca:(0.001)	.	.	.	30 g
NCS HC28974-A1	7.03	.	3.73	0.51	0.071	0.062	0.048	0.093	0.057	.	0.005	<0.01	0.385	.	.	.	.	.	.	50 g
SRM 87a	6.24	0.11	0.30	0.61	0.37	0.26	0.57	.	.	.	0.18	.	0.16	.	.	.	.	0.020	.	75 g
NW 511	6.150	.	0.295	0.790	.	0.195	.	.	.	.	.	.	.	.	.	.	.	.	.	100 g
BCS 268/1	5.49	.	1.35	0.47	0.49	0.24	0.16	0.028	0.031	.	(0.008)	.	0.028	.	.	.	.	.	.	100 g
BCS 380/1	1.93	.	0.91	1.24	0.24	0.094	0.94	.	.	.	0.024	.	0.025	.	.	.	.	.	.	100 g
SRM 2426	1.925	.	.	0.454	.	.	.	.	.	.	.	.	38.92	.	58.18	.	.	.	.	100 g
BCS 349	1.19	(<0.001)	3.40	0.154	0.024	0.111	.	0.077	0.074	.	0.034	.	0.299	.	.	.	.	.	.	100 g
SRM 858	0.79	0.0011	0.84	0.078	1.01	0.48	0.0006	0.006	.	.	0.042	0.0030	1.04	0.086	.	<0.0001	.	.	.	35 g
BCS 216/3	0.74	0.110	5.45	0.77	0.76	0.76	0.24	0.052	0.052	.	0.20	.	0.214	.	.	.	.	.	.	100 g
BCS 343	0.52	0.14	0.28	0.39	0.70	0.69	.	.	.	.	0.024	.	0.028	.	.	.	.	.	.	100 g
BCS 181/3	0.30	0.04	2.48	0.72	1.57	1.40	2.00	0.101	.	.	0.058	.	2.52	.	.	.	.	.	.	100 g
SRM 853a	0.1810	(<0.0005)	0.1504	0.504	1.092	1.251	0.00429	(0.0003)	(0.0003)	(0.0001)	0.0205	0.01842	0.0514	(0.0023)	.	.	.	0.0176	.	40 g
GBW 02202	0.18	.	0.095	0.38	0.021	1.38	0.013	0.032	.	.	0.036	.	0.10	.	.	.	.	.	.	100 g
BCS 262/1	0.16	(0.002)	0.039	0.20	10.75	0.084	0.071	(0.05)	(0.04)	(0.0002)	0.005	0.0174	0.0055	.	.	(0.0006)	.	0.0185	.	100 g
SRM 854a	0.1553	0.0340	0.0494	0.1990	4.474	0.3753	0.0195	.	.	.	0.0335	.	0.0505	.	.	.	.	.	.	40 g
BCS 300/1	0.14	0.13	1.27	0.24	2.74	0.33	.	.	.	.	0.09	.	5.87	0.18	.	.	.	.	.	100 g
BAM 300	0.14	0.216	0.040	0.198	2.68	0.018	.	0.014	.	.	0.012	.	0.128	.	.	.	.	.	.	100 g
BCS 263/2	0.14	0.074	0.019	0.26	4.67	0.36	.	.	.	.	0.022	.	0.056	.	.	(0.001)	.	.	.	100 g
BAM 301	0.062	.	0.0018	0.054	0.0008	(0.001)	.	.	.	.	0.0046	0.0018	0.0036	.	.	.	.	.	.	100 g
BCS 195g	0.035	.	0.001	0.080	.	0.001	.	.	.	.	.	0.004	0.015	.	99.85	.	.	0.009	.	100 g
GBW 02222	0.0069	.	2.30	1.41	2.21	.	.	.	.	.	0.0196	.	6.21	0.127	.	.	.	.	.	50 g
JSAC 0121-C	0.00110	0.000113	0.000348	0.00094	0.000282	0.000173	.	.	.	.	0.000196	.	0.000203	0.000202	.	1.98	.	.	.	50 g

ALUMINUM BASE CHIPS

= class, where 1 = CRM and 2 = RM

typical analysis

#	Number	Si	Co	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sn	Ti	V	Zn	Be	Bi	Cd	Ga	Li	Sb	Zr	Units
1	C55XG28J30	17.5	0.345	0.256	1.58	0.50	0.99	0.378	1.81	0.081	0.059	0.073	0.011	0.32	0.0042	0.020	0.004	.	.	.	.	40 g
2	C55XA30J30	16.5	0.194	0.037	4.02	0.286	0.31	0.259	0.072	0.038	0.083	0.144	0.006	0.258	<0.0005	.	.	.	.	.	.	25 g
1	C55XG28J10	14.33	0.119	0.319	1.82	0.678	1.26	0.024	2.47	0.0938	0.022	0.106	0.0095	0.258	.	.	.	.	.	.	.	40 g
1	C54XG06H50	13.76	<0.005	0.026	0.0229	0.210	0.0222	0.85	0.067	0.0020	0.022	0.0106	0.0088	0.225	.	.	.	.	.	.	.	50 g
1	C54XG06H40	13.21	0.207	0.120	0.237	0.138	0.134	0.691	0.139	0.040	(0.007)	0.124	0.011	0.131	.	.	.	.	.	.	.	50 g
1	C54XG13H40 *	12.55	(0.001)	0.0264	0.643	0.405	0.78	0.617	0.84	0.055	0.068	0.083	.	0.251	0.0048	<0.001	.	.	.	.	0.021	50 g
1	C55XG02J60	12.4	0.018	0.035	0.48	1.28	0.34	0.64	0.027	0.046	<0.01	0.35	0.010	0.083	.	.	.	.	.	.	.	50 g
1	C54XG06H50	11.27	0.021	0.179	0.327	0.500	0.179	0.445	0.295	0.065	0.050	0.084	0.010	0.065	0.0066	0.08	0.0052	0.010	.	.	.	50 g
2	C55XG02J70	10.8	0.095	0.069	0.82	0.90	0.52	0.45	0.235	0.217	0.047	0.161	0.007	0.161	.	.	.	.	.	.	.	50 g
2	C54XG13H30	10.8	.	0.06	0.82	0.72	1.05	0.38	0.94	0.06	0.09	0.17	.	0.31	.	.	.	.	.	.	.	50 g
1	C54XG13H20	10.42	0.004	0.103	1.29	0.767	1.37	0.248	1.15	0.083	0.145	0.166	0.018	0.530	.	0.0027	.	.	.	.	.	50 g
1	C55XG06H20	10.19	0.0086	0.130	0.59	0.640	0.40	0.234	0.55	0.213	0.116	0.179	0.018	0.97	.	0.001	.	.	.	.	.	50 g
2	C55XG02J80	10.04	0.056	0.052	2.27	0.94	0.21	0.45	0.37	0.33	0.116	0.240	0.025	1.32	0.001	(0.0002)	.	.	.	.	.	50 g
2	C55XG23H10	9.82	0.089	0.089	1.19	0.80	0.45	0.029	0.31	0.145	0.082	0.022	0.007	0.60	.	.	.	0.011	0.006	.	.	50 g
1	C55XG26H30	9.6	0.076	0.130	2.19	1.07	1.01	0.45	0.51	0.228	0.16	0.147	0.020	0.79	.	.	.	.	.	.	.	40 g
1	C55XG26H20	9.36	0.052	0.083	4.14	0.71	1.49	0.52	0.41	0.111	0.110	0.120	0.011	0.64	.	0.035	.	.	.	.	.	40 g
2	C55XG02J40	8.98	0.11	0.11	3.16	0.64	0.10	0.18	0.67	0.19	0.26	0.09	.	2.46	.	<0.001	.	.	.	.	.	50 g
1	C54XG13H10	8.91	0.0951	0.062	1.87	0.801	2.89	0.0137	1.83	0.240	0.260	0.112	0.007	0.37	0.0078	<0.001	.	.	.	.	.	50 g
1	C55XG02J90	8.62	0.052	0.11	3.40	0.82	0.21	0.113	0.62	0.106	0.19	0.090	0.007	2.46	0.001	.	.	.	.	.	.	50 g
2	C54XG25J50	8.17	0.003	0.010	0.269	0.191	<0.01	(0.004)	0.008	0.28	0.13	0.006	0.003	0.020	0.021	.	.	.	.	.	.	50 g
2	C55XG26H10	7.69	0.022	0.20	4.34	1.78	0.29	0.015	0.012	0.24	(0.008)	0.21	0.012	1.14	.	0.07	.	.	.	.	.	40 g
1	C55XG04H100	7.32	0.043	0.090	1.36	0.52	0.004	0.53	0.023	0.010	0.010	0.010	0.007	2.28	.	.	.	.	.	.	.	50 g
1	C54XG25J40	7.22	0.047	0.019	0.160	0.13	0.072	0.090	0.10	0.162	0.092	0.09	(0.002)	0.11	0.02	0.09	.	.	.	.	50 g	
1	C55XG02J100	6.55	0.059	0.16	4.65	0.186	<0.01	0.015	0.96	(0.004)	0.9	<0.005	.	4.76	(0.002)	0.09	.	.	.	.	.	50 g
1	C55XG04H90	5.99	0.010	0.005	2.64	0.304	0.079	0.304	0.231	0.062	0.031	0.31	0.009	1.89	.	.	0.0015	.	.	.	.	50 g
Number	Si	Co	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sn	Ti	V	Zn	Be	Bi	Cd	Ga	Li	Sb	Zr	Units	
1	C54XG25J30	5.86	.	0.062	0.113	0.43	0.20	0.29	0.114	0.074	0.06	0.083	0.011	0.092	0.003	.	0.017	.	.	.	.	50 g
2	C55XG04H30	5.55	0.06	0.06	3.60	0.86	0.17	0.40	0.33	0.10	0.10	0.20	0.006	1.30	0.049	.	.	.	.	.	50 g	
1	C54XG25J20	3.93	0.10	0.150	0.130	0.58	0.59	0.48	0.139	0.073	0.042	0.152	(0.006)	0.169	.	0.22	.	.	.	.	50 g	
1	C54XG25J10	3.34	0.14	0.14	0.010	0.72	0.65	0.81	0.26	0.094	<0.01	0.098	0.016	0.36	0.001	0.11	.	.	.	.	50 g	
1	C57XG12H10	2.52	0.113	0.069	5.54	0.88	0.40	0.032	0.31	0.016	0.095	0.114	0.153	1.03	.	0.012	.	0.008	.	.	0.07	50 g
1	C55XG900J40	1.39	.	0.343	0.249	0.306	0.459	0.75	0.351	0.088	0.153	0.171	.	0.149	.	0.285	.	.	.	.	50 g	
1	C51XG09J130	0.74	0.106	0.106	0.623	0.94	0.149	11.3	0.143	0.114	0.153	0.425	0.053	0.221	0.0024	0.063	.	.	.	<0.005	50 g	
1	C51XG00H20	0.61	0.079	0.100	0.173	0.49	0.089	0.305	0.206	0.115	0.122	0.137	0.070	0.072	0.003	0.023	(0.017)	.	0.056	0.045	50 g	
1	C57XG12H50	0.55	0.054	0.16	12.2	0.192	0.028	0.073	0.108	0.068	0.067	0.036	0.033	0.26	0.004	.	.	.	.	.	50 g	
1	C55XG900J20	0.44	.	0.118	0.864	0.378	0.622	0.145	0.133	0.52	0.341	0.054	.	0.309	.	0.55	.	.	.	.	50 g	
1	C511XG05H10	0.42	.	0.240	0.32	0.79	2.02	0.012	0.123	0.023	0.179	0.205	0.053	0.47	(0.0002)	.	0.013	.	.	.	25 g	
1	C511X G6063	0.412	0.0021	0.0014	0.0014	0.185	0.437	0.0239	0.0021	0.0011	(0.0006)	0.0110	0.0087	0.062	.	0.046	0.0115	.	.	.	40 g	
1	C59XG77J30	0.366	<0.005	0.023	2.42	0.712	2.27	0.594	0.43	0.075	0.137	0.107	0.006	4.57	.	.	.	.	0.026	50 g		
1	C511XG05H20	0.35	0.054	0.30	0.37	0.60	3.12	0.186	0.22	0.068	0.154	0.079	(0.001)	0.26	0.004	.	.	.	.	.	40 g	
2	C511XG3000B30	0.35	0.008	0.056	0.120	0.376	0.80	1.06	0.116	0.062	0.028	0.22	<0.005	0.140	0.005	.	.	.	.	.	40 g	
2	C511XG10H40	0.33	.	0.15	0.052	0.19	10.4	0.12	0.085	0.10	0.051	0.097	0.005	0.21	0.023	.	.	.	.	.	25 g	
2	C59XG77J50	0.30	0.050	0.050	0.122	1.32	0.72	0.030	1.38	(0.003)	<0.01	0.058	0.007	7.57	.	.	.	.	.	.	50 g	
1	C56XG25J10	0.26	0.008	0.067	3.82	0.41	0.075	0.040	1.33	0.101	0.125	0.098	0.102	0.28	.	.	.	.	(0.003)	.	50 g	
1	C511XG05H30	0.24	0.06	0.06	0.10	0.54	5.35	0.38	0.09	0.10	0.10	0.07	0.09	0.09	.	.	.	.	.	.	25 g	
2	C511XG3000B20	0.23	0.007	0.200	0.20	0.335	0.68	0.81	0.063	0.137	0.105	0.111	<0.005	0.098	0.0017	.	.	.	.	.	40 g	
1	C56XG25J20	0.211	0.195	0.0063	4.81	0.346	0.060	0.225	1.10	(0.0016)	(0.004)	0.210	0.018	0.155	0.0022	.	.	.	0.324	0.247	50 g	
1	C56XG25J50	0.205	0.34	0.047	4.36	0.535	0.022	0.150	1.77	0.076	0.097	0.051	0.086	0.086	.	.	.	.	0.076	0.22	50 g	
1	C59XG77J10	0.15	0.018	0.018	2.41	0.21	4.83	0.278	0.17	0.125	0.126	0.178	0.005	1.91	0.06	.	.	.	.	.	50 g	
1	C56XG25J30	0.11	0.264	0.024	4.90	0.079	(0.011)	0.278	0.92	0.024	0.031	0.162	0.003	1.03	0.0014	.	.	.	0.35	0.275	50 g	
1	C511XG05H40	0.11	.	0.029	0.056	0.14	5.16	0.547	0.040	0.152	0.144	0.048	.	0.062	0.015	.	.	.	.	.	25 g	
1	C58XG40H60	0.09	0.006	0.005	0.111	0.08	(0.003)	0.004	0.008	<0.002	<0.005	0.064	<0.005	7.55	(0.002)	.	0.032	.	<0.0005	(0.004)	50 g	
1	C56XG2000J10	0.05	.	0.005	3.50	0.13	2.75	1.42	0.01	0.002	0.1	0.004	0.003	1.01	.	0.16	.	.	.	0.2	50 g	
1	C59XG77J60	0.04	.	0.0046	1.13	0.054	2.63	0.0024	0.003	(0.005)	0.006	0.023	0.003	11.62	<0.005	<0.002	.	(0.005)	.	0.29	50 g	
1	C51XG900J110	0.035	.	<0.005	0.046	0.081	(0.001)	6.93	(0.0026)	0.016	0.013	0.0017	0.003	.	.	.	.	.	.	0.184	50 g	
1	C51XG09H10	0.012	0.011	0.027	0.034	0.051	0.039	0.041	0.038	0.018	0.028	0.031	0.016	0.042	0.0004	0.011	.	.	<0.005	.	50 g	
2	BM AL	<0.0001	.	<0.0001	<0.0001	<0.0001	<0.00005	.	.	.	.	.	.	Al: 99.999	As: <0.0001	Ca: <0.0001	Na: <0.00005	.	.	.	100	

* C54XG13H40 also contains Sr: 0.026

RM ARSENIC

Number	As	Units
BM As	99.999	50 g chips

RM ANTIMONY

Number	Sb	As	Fe	Pb	Si	Sn	Units
BM Sb	99.999	<0.0002	<0.0002	<0.0001	<0.0001	<0.0001	100 g chips

RM BISMUTH

Number	Bi	Ag	As	Co	Cu	Fe	Pb	Sb	Zn	Units
BM Bi	99.97	<0.0001	<0.0001	<0.003	<0.0001	<0.001	<0.02	<0.0002	<0.003	100 g chips

RM CADMIUM

Number	Cd	Cu	Fe	Pb	Ti	Zn	Units
BM Cd	99.96	<0.01	<0.002	<0.02	<0.003	<0.004	100 g chips

CRM CHROMIUM

		T = Total analysis listed in mass %										BCS: 100 g powder VS: 100 g chips			
Number	Cr	Al	As	C	Cu	Fe	N	O	P	Pb	S	Si	Sn	Ti	Zn
VS F36	99.9	.	.	0.0027	0.00038	.	0.0026	(0.005)	.	.	0.0019	0.0039	.	0.0069	.
VS F8/2	99.2	0.17	0.00027	0.029	0.0014	0.26	0.025	.	0.0035	0.00033	0.013	0.25	0.0003	.	0.003
BCS 361	.	(0.083T)	.	0.0039	.	0.0920	0.0079	0.1010	.	.	0.0043	0.0449	.	.	.

CRM COBALT BASE CHIPS

100 g units

Number	Grade	Co	Cr	Fe	Mn	Mo	Ni	Si	Ti	W	Al	B	C	Cu
IARM 64C	Ultimet 1233	53.4	25.4	2.99	0.79	4.72	9.47	0.24	0.007	2.39	0.138	0.0010	0.064	0.019
IARM 95D	Stellite 6B	57.9	29.9	0.84	1.47	0.954	2.99	0.64	(0.009)	3.98	0.080	0.0015	1.06	0.009
IARM 96B	Stellite 25	49.4	20.54	2.29	1.39	1.17	10.04	0.16	0.007	14.52	0.035	0.0021	0.132	0.047
IARM 207A	MP35N	33.46	19.98	0.64	0.015	9.62	35.19	0.053	0.91	0.028	0.040	0.011	0.007	0.017

Number	La	Mg	N	Nb	O	P	S	Sn	Ta	V	Zr
IARM 64C	.	0.0043	0.113	0.016	0.0012	0.0064	0.0004	<0.01	0.02	0.020	<0.01
IARM 95D	.	(0.0002)	0.0417	0.024	0.0009	0.0053	(0.0003)	(0.0001)	(0.03)	0.0100	(0.001)
IARM 96B	.	(0.0005)	0.007	0.046	0.002	0.0063	0.0005	.	0.028	0.012	0.007
IARM 207A	.	(0.0005)	0.0031	0.043	0.0011	0.002	0.0027	.	0.007	0.011	0.003

COBALT BASE CHIPS

C11: RM, typical analysis 30 g units

others: CRM, 100 g units

Number	Cr	C	Co	Fe	Mn	Mo	Nb	Ni	Si	W	Al	Cu	N	P	Pb	S	Sn	Ta	V
ECRM 378-1C	28.22	1.181	.	0.606	0.0579	0.0503	.	0.617	1.172	4.43	.	.	.	(0.0023)	.	0.0055	.	.	.
C112X149360	23.0	0.50	.	0.44	0.74	4.97	.	1.57	0.12	0.95	0.50	.	.	.	.	.	.	.	.
C111X126690	22.7	0.51	.	1.2	0.54	.	2.59	0.57	0.62	12.3	.	0.006	.	.	0.001	.	0.01	.	.
BAM 328-1	20.54	0.390	41.65	2.40	1.395	4.41	3.61	20.54	0.629	4.16	0.070	0.013	0.027	0.005	.	.	.	0.18	.
SRM 862	20.0	0.120	51.5	1.80	1.59	.	.	9.74	0.017	15.1	.	0.0010	0.026	0.002	.	0.0008	.	.	0.005

CRM**Co/Fe/V ALLOY PERMENDUR 2V**

analysis listed in mass %

31 mm Ø x 2 or 18 mm

Number	Co	Fe	V	Al	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
IARM 326A	48.4	49.6	1.94	(0.003)	(0.002)	0.003	0.0013	0.0011	0.029	(0.002)	0.037	(0.002)	(0.002)

Number	As	B	Mg	N	Nb	O	Sn	Ta	Ti	W	Zr
IARM 326A	<0.005	(0.001)	(0.001)	0.0004	0.038	0.0082	<0.001	(0.01)	(0.002)	(0.001)	0.002

CRM**COPPER CHIPS AND PINS**

analysis listed in mg/kg except % which is mass %

IMN 001: 50 g of 0.31 g pins

all others: chips as noted

Number Units	Ag	As	Au	Bi	Cd	Co	Cr	Cu%	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn	
SRM 454	286	46	7.5	19	.	.	.	99.84	.	.	.	.	66	.	24	479	.	2.2	27	7	35 g
SRM 400	181	140	.	24.5	.	0.6	.	99.70	41	.	603	.	128	.	102	214	.	.	153	114	50 g
SRM 399	117	47	.	10.5	.	0.5	.	99.79	20.0	.	506	.	114	.	30	95	.	.	50	45	50 g
IMN 001	27.59	3.17	.	1.42	(0.11)	2.04	3.55	.	(13.9)	5.18	3.42	.	4.28	(6.0)	2.33	1.38	.	3.31	1.23	4.57	above
IMN 5	10	4.0	.	0.096	.	8.1	.	.	4.5	(1.3)	4.4	.	27	.	(0.92)	.	(2.6)	4.6	.	(13)	200 g
BAM 366	7.9	1.11	.	(<0.3)	0.27	.	.	.	23.4	.	3.2	263	10.8	8.7	0.99	(<1.1)	.	111	(<0.3)	15.6	100 g
BCR 017B	.	.	.	.	.	.	.	.	.	.	.	6.9	.	10.4	.	.	.	.	.	.	50 g

CRM**COPPER CHIPS**

analysis listed in mass %

C39X: typical analysis 50 g

BAM, BCS, IARM: 100 g

IPT: 50 g

IMN: 200 g

Number	Cu	Ag	Al	As	Au	B	Be	Bi	C	Cd	Co	Cr	Fe	Mg
IPT 64	99.98	0.0010	(<0.0006)	(0.0002)	.	.	.	(<0.0001)	.	.	.	.	0.00045	.
IARM 278A	99.5	(0.001)	<0.002	(0.001)	.	.	.	(0.001)	(0.003)	.	(0.001)	(0.001)	0.004	.
IARM 279A	99.1	(0.003)	(0.002)	(0.002)	.	.	.	(0.001)	(0.002)	.	(0.002)	0.86	0.025	.

BCS 399	REM	.	.	(<0.001)	.	.	.	(0.001)	.	(0.003)	.	.	(0.006)	.
IMN 4	REM	0.21	.	0.054	.	.	.	(0.0011)	.	.	0.0010	<0.00005	0.0010	.

C39X 178700	.	0.0468	0.0012	0.0033	0.0009	.	.	0.0470	.	0.0305	0.0017	.	.	.
C39X 178710	.	0.025	<0.0005	0.029	0.0048	.	.	0.069	.	0.0031	0.0008	.	.	.
C39X 178680	.	0.0249	0.0072	0.0226	0.0101	.	.	0.0308	.	0.0130	0.0248	.	0.110	0.0085
C39X 178660	.	<0.001	<0.002	0.037	.	.	.	0.001	.	<0.001	0.003	0.002	<0.001	<0.001

Number	Mn	Ni	O	P	Pb	S	Sb	Se	Si	Sn	Te	Zn
IPT 64	.	0.00018	.	.	0.00006	.	(0.0002)	(<0.0002)	.	(<0.0005)	(<0.0001)	(0.001)
IARM 278A	(0.0004)	<0.005	(0.0004)	0.011	(0.003)	0.002	<0.005	.	(0.002)	(0.001)	0.53	(0.002)
IARM 279A	(0.002)	0.014	(0.001)	(0.005)	(0.01)	0.0015	(0.004)	.	0.020	0.021	.	(0.01)

BCS 399	.	(0.002)	.	0.045	(0.002)	.	(<0.001)	.	.	(0.003)	.	(0.003)
IMN 4	<0.00003	0.078	.	.	0.20	.	(0.0041)	.	(0.00029)	0.00044	.	(0.0017)

C39X 178700	Ge:0.0076	0.0062	In:0.0078	0.0012	0.0447	0.0026	0.0478	0.0261	.	0.0031	0.0011	0.129
C39X 178710	0.0010	0.027	.	<0.0005	0.0092	0.0080	0.017	0.028	<0.0005	.	0.011	.
C39X 178680	0.0123	0.0222	.	0.0507	0.1040	0.022	0.0295	0.0133	.	0.103	0.0206	0.197
C39X 178660	<0.001	0.034	.	<0.002	<0.001	0.003	<0.001	.	<0.005	0.013	<0.001	0.005

RM**PHOSPHORUS DEOXIDIZED COPPER CHIPS**

analysis listed in mass % except * which is mg/kg

100 g chips

Number	Ag%	Al*	As%	Bi*	Co*	Cu%	Fe*	Mn*	Ni*	P%	Pb%	Sb*	Si%	Sn%	Te%	Zn%
CURM 09.03	0.012	<3	<0.001	<3	<3	99.92	33	<3	<3	0.056	<0.0005	<5	<0.001	<0.001	<0.001	<0.001
CURM 09.01	0.011	<5	<0.001	<3	<3	99.82	19	<3	<3	0.151	<0.0005	<5	<0.001	<0.001	<0.001	0.0008
CURM 09.02	0.0055	<5	<0.001	<5	<5	99.90	42	<5	<5	0.078	<0.001	<5	<0.002	<0.001	<0.001	<0.001

CRM**COPPER ANODE**

analysis listed in mg/kg

425 g chips

Number	Ag	Au	As	Bi	Fe	Pb	Ni	Sb	Se	Sn	Te
CAN CUAR-1	294	2.3	145	.	76	864	.	.	.	113	33
CAN CUPD-1	216	3.9	306	62	40	69	153	147	237	5	.

CRM COPPER CONCENTRATE POWDER

analysis listed in mass %

CETEM: 160 g

VS: 50 g

Number	Cu	S.Cu	Al ₂ O ₃	C	CaO	Cd	Fe	Fe ₂ O ₃	K ₂ O	MgO	Mn	Na ₂ O	P ₂ O ₅	Pb	S	SiO ₂	Zn	LOI
VS 2891-84 CETEM CBPA-2	40.4 27.9	(0.6)	1.57	(0.07)	1.21	0.029 (0.0004)	(5.78) .	39.6	(0.22)	0.79	(0.0048)	0.35	(0.38)	2.25 0.0112	(15.98) (30.6)	(21.74) (6.3)	2.89 0.0096	(14.5)

continued analysis listed in mg/kg

Number	Ag	As	Au	Ce	Co	Cr	F	La	Mo	Ni	Re	Se	Sm	Sr	Th	Ti	U	Zr
VS 2891-94 CETEM CBPA-2	7.077 12	(9)	(8)	(43)	444	20	(322)	(21)	(54)	(2030)	28.2 .	(38)	(3.3)	(25)	(7)	(600)	(3.9)	(21)

CRM COPPER CONCENTRATE POWDER

certified values listed in mass % except * which is mg/kg

200 g units

Number	Ag*	Al	Au*	Ca	Cd*	Co	Cu	Fe	Mg	Mn*	Pb	S	Sb*	SiO ₂	Zn
CAN CCU-1D	120.7	0.191	14.01	0.195	245.9	0.0330	23.95	29.26	0.508	99.4	0.262	32.76	61.9	3.036	2.63

continued informational values listed in mg/kg except % which is mass %

Number	As	Ba	Bi	C%	Ce	Cl	Cr	Cs	F	H ₂ O%	Hg	In	K	La	Mo	Ni	Se	Sr	Te	Ti	Tl	LOI%
CAN CCU-1D	545	12.41	3	0.088	2	60	6	0.08	200	2.03	7	7.0	316	3	18.1	7.6	244	4.9	36.7	66	2.63	19.51

CRM SEBILOY / ENVIROBRASS / FEDERALLOY CHIPS

analysis listed in mass %

C32X: typical analysis

100 g units

Number	Bi	Se	Sn	Zn	Cu	As	Co	Fe	Ni	P	Pb	Sb	Si
C32X SEB10	5.77	0.895	3.83	11.57	(76.7)	0.051	0.0108	0.059	0.118	0.025	0.564	0.354	.
C32X SEB20	4.35	0.027	9.40	3.75	81.8	0.009	0.013	0.078	0.078	0.014	0.42	0.013	.
IARM 264A	3.6	(0.001)	3.03	5.33	(87.3)	(0.004)	(0.001)	0.048	0.54	0.027	0.057	0.074	0.003
IARM 263A	2.55	(0.002)	3.5	15.8	(78)	0.003	0.001	0.047	0.66	0.040	0.022	0.06	0.003
IARM 265A	2.4	(0.002)	4.4	2.45	(90)	(0.005)	(0.001)	0.013	0.69	0.024	0.011	0.015	0.003
IARM 266A	2.37	0.001	6.9	3.48	(87)	0.004	(0.001)	0.035	0.46	0.032	0.010	0.010	0.002
C32X SEB40	2.69	0.115	9.29	8.55	78.58	0.0011	0.476	0.365	0.0092	0.006	0.010	0.0055	.
IARM 227A	2.3	1.21	5.1	4.70	85.9	0.003	0.001	0.060	0.53	0.003	0.042	<0.01	0.002
IARM 226A	1.7	0.93	5.1	4.8	86.7	0.003	0.001	0.054	0.54	0.005	0.040	0.004	0.002
IARM 228A	1.53	0.67	4.1	4.1	89.0	0.003	0.001	0.052	0.45	0.032	0.026	0.010	0.002
C32X SEB50	1.17	0.512	5.28	6.64	85.5	0.0121	0.0048	0.360	0.308	0.183	0.0149	0.0344	.

Number	Ag	Al	B	C	Cd	Cr	Mn	N	O	S
C32X SEB10	.	.	.	.	.	.	.	.	.	.
C32X SEB20	.	.	.	.	.	.	.	.	.	.
IARM 264A	(0.005)	0.003	.	(0.004)	.	(0.002)	(0.002)	.	.	0.0013
IARM 263A	(0.006)	(0.002)	.	<0.005	.	(0.002)	(0.002)	.	.	(0.002)
IARM 265A	(0.002)	0.003	.	.	.	(0.001)	(0.002)	.	.	(0.002)
IARM 266A	(0.001)	0.002	.	(0.002)	.	(0.002)	(0.002)	.	.	(0.002)
C32X SEB40	.	.	0.0021	.	0.0004	.	.	.	.	.
IARM 227A	0.004	0.002	.	0.003	.	(0.001)	0.001	(0.0002)	0.0013	0.005
IARM 226A	0.004	0.002	.	0.003	.	(0.001)	0.002	<0.0005	(0.001)	0.005
IARM 228A	0.003	0.002	.	0.003	.	0.001	0.001	<0.0005	(0.002)	0.004
C32X SEB50	.	.	0.0028	.	0.0067	.	.	.	.	.

COPPER BASE CHIPS

= class, where 1 = CRM and 2 = RM C36X, DH: typical analysis 50 g GBW: 95 g SRM: 50 g others: 100 g

#	Number	Sn	Al	Fe	Mn	Ni	Pb	Zn	Be	Bi	Co	Se
2	DH 0209	11.92	.	.	.	0.265	0.542	.	.	.	.	.
1	BAM 228	9.76	(0.0001)	0.036	(<0.001)	0.109	1.24	3.32	.	0.0086	.	0.0012
2	DH 0201	8.84	0.022	0.677	0.035	0.795	1.17	6.30	.	0.006	.	.
2	DH 0208	4.78	4.15	2.54	0.711	2.82	1.31	1.85	.	.	.	.
2	DH 0206	2.78	0.059	1.79	0.044	0.221	0.891	10.89	.	.	.	.
2	DH 0203	2.17	12.50	5.76	0.057	.	0.59	1.36	.	.	.	.
2	DH 0204	2.16	12.51	5.70	0.057	.	0.58	1.36	.	.	.	.
2	DH 0205	2.14	12.53	5.66	0.056	.	0.76	1.36	.	.	.	.
2	DH 0207	0.74	.	0.936	0.027	0.174	2.16	30.20	.	.	.	.
2	DH 0202	0.381	.	0.911	0.007	0.034	0.139	0.229	.	.	.	.
1	C37X2180	0.018	0.0025	0.075	0.084	2.51	0.0025	0.029	.	.	.	.
1	C36X2740	0.0140	0.0013	0.0781	0.0148	2.54	0.0021	0.0395	.	.	0.0028	.
2	C36XCBC40	0.01	0.06	0.09	0.003	0.04	0.30	0.02	1.82	.	2.44	.
1	IARM 158B	0.01	0.002	0.090	0.019	0.32	0.01	0.014	.	.	0.002	.
1	IARM 158C	0.01	0.002	0.090	0.019	0.32	0.01	0.014	.	.	0.002	.
1	SRM 460	0.006	0.048	0.098	.	0.031	0.258	0.004	1.86	.	0.217	.
1	SRM 459	0.005	0.044	0.079	.	0.039	0.001	0.002	1.82	.	0.221	.
1	IARM 71B	0.005	0.040	0.042	0.0010	0.021	0.006	0.005	1.84	.	0.21	.
1	SRM 458	0.004	0.030	0.060	.	1.60	0.002	0.002	0.360	.	0.076	.
2	C36XCBC20	0.004	0.03	0.02	(<0.01)	0.07	0.004	0.03	0.56	.	0.13	.
1	C37X2260	0.0032	0.0020	1.52	0.582	0.0024	(0.001)	2.82	.	.	.	.
2	C36XCBC10	0.002	0.02	0.03	(<0.01)	1.88	0.002	(<0.01)	0.42	.	0.23	.
2	IARM 160A	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	.	.	(<0.01)	.
2	IARM 159A	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	.	.	(<0.01)	.
2	C36XCBC30	(<0.002)	0.02	0.04	(<0.01)	0.02	0.003	0.02	1.81	.	.	.

Number	Ag	As	C	Cr	Mg	O	P	S	Sb	Si	Zr	Cu
DH 0209	.	.	.	.	.	.	.	.	.	.	.	87.07
BAM 228	.	0.024	.	.	.	.	0.019	0.036	0.078	.	.	85.34
DH 0201	.	0.076	.	.	.	.	0.046	.	0.104	.	.	81.84
DH 0208	.	.	.	0.009	.	.	0.027	.	0.083	0.052	.	81.67
DH 0206	.	0.025	.	.	.	.	0.017	0.059	0.060	0.043	.	83.05
DH 0203	.	.	.	.	.	.	.	.	0.329	0.23	.	76.88
DH 0204	.	.	.	0.009	.	.	0.007	.	0.336	0.22	.	77.00
DH 0205	.	.	.	.	.	.	0.008	.	0.350	0.22	.	76.82
DH 0207	.	.	.	.	.	.	.	.	0.014	.	.	65.66
DH 0202	.	.	.	0.003	.	.	.	0.037	0.008	.	.	98.15
C37X2180	.	.	(0.002)	0.033	.	.	0.0015	0.006	.	0.56	.	96.60
C36X2740	.	0.0011	(0.0029)	0.531	.	.	0.0011	0.0035	.	0.594	<0.005	96.24
C36XCBC40	.	.	0.01	0.01	.	.	.	.	.	0.09	.	.
IARM 158B	(0.01)	(0.001)	0.002	0.85	.	0.002	0.005	0.003	0.002	0.02	.	98.5
IARM 158C	(0.01)	(0.001)	0.002	1.04	.	0.002	0.005	0.003	0.002	0.02	.	98.5
SRM 460	.	.	.	0.005	0.005	.	.	.	.	0.077	.	(97.5)
SRM 459	.	.	.	0.005	0.007	.	.	.	.	0.077	.	(97.7)
IARM 71B	(0.002)	.	0.003	0.0030	.	.	0.004	(0.0004)	(0.002)	0.060	.	97.7
SRM 458	.	.	0.004	0.003	0.003	.	.	.	.	0.035	.	(97.9)
C36XCBC20	.	.	.	0.005	.	.	.	.	.	0.05	.	.
C37X2260	.	.	0.006	0.003	.	.	0.0025	0.0005	.	3.54	.	91.58
C36XCBC10	.	.	0.005	0.005	.	.	.	.	.	0.04	.	.
IARM 160A	3.03	.	0.003	(<0.01)	.	.	(0.004)	(<0.003)	.	(<0.01)	0.40	.
IARM 159A	3.48	.	(0.002)	(<0.01)	.	.	(<0.01)	(<0.01)	.	(<0.01)	.	.
C36XCBC30	.	.	.	0.005	.	.	.	.	.	0.06	.	.

CUPRO-NICKEL AND COPPER-NICKEL-SILVER CHIPS

= class, where 1 = CRM and 2 = RM

C212X: typical analysis 50 g units

all others: 100 g units

#	Number	Ni	Zn	Ag	Al	C	Co	Cr	Cu	Fe	Mg	Mn	P	Pb	S	Si
2	C212X40010	67.6	.	.	0.09	0.10	0.12	0.05	.	0.57	0.13	3.04	.	0.08	0.022	1.48
2	C212X40020	65.2	.	.	0.05	0.04	0.08	0.02	.	1.17	0.02	2.00	.	0.04	0.075	0.10
2	C212X40060	63.3	.	.	3.85	0.03	0.05	0.12	.	1.95	0.016	0.83	.	0.02	0.035	3.94
1	C36XCN60	33.46	0.026	.	(0.0024)	0.0180	0.0440	1.10	63.35	0.878	.	0.451	0.031	0.0066	0.0109	0.144
1	IARM 85C	31.3	0.057	<0.002	<0.01	0.008	0.016	0.002	67.3	0.63	0.01	0.65	(0.003)	0.004	(0.002)	0.01
1	BCS 180/2	30.35	.	.	.	0.04	.	.	68.12	0.68	.	0.75	.	(0.003)	0.006	(0.018)
2	C36XCN40	30.2	.	.	.	.	0.04	.	0.50	0.003	.	0.33	.	0.015	.	0.54
1	IARM 236A	30.0	0.002	.	0.003	0.010	0.004	0.002	66.7	0.91	.	1.04	0.003	0.004	0.003	0.19
1	C36XCN100	29.3	.	.	.	0.064	0.081	1.59	61.01	4.28	0.0026	0.262	(0.020)	0.004	0.055	1.02
2	C36XCN90	28.1	.	.	.	0.02	<0.01	2.19	.	0.93	.	1.20	0.016	0.05	0.002	0.56
1	SRM 880	18.13	27.3	.	.	.	.	.	54.51	(0.004)	.	<0.001	.	(0.002)	.	.
1	C34XNS50	17.16	(23)	0.0102	0.674	.	0.197	0.0014	55.11	0.717	0.704	0.127	0.067	1.29	.	0.158
1	GBW 02104	14.87	20.81	.	.	.	.	.	Rem	0.47	0.033	0.32	0.0048	0.019	.	0.146
2	C34XNS30	14.86	17.94	0.108	0.038	0.014	0.102	.	66.30	0.201	0.0011	0.129	0.013	0.155	0.063	0.018
1	SRM 875	10.42	0.11	.	.	(0.0035)	.	.	87.83	1.45	(0.0010)	<0.0007	0.0020	0.0092	(0.0011)	(0.0008)
1	SRM 874	10.18	(0.002)	.	.	(0.0023)	.	.	88.49	1.22	(0.0002)	0.0020	(0.002)	<0.0005	(0.0011)	(0.0006)
1	IARM 84B	10.03	0.082	0.005	(0.002)	(0.01)	0.013	(0.003)	87.9	1.30	.	0.62	0.004	0.008	0.008	0.01
2	C36XCN10	9.5	.	.	.	.	0.10	.	.	1.94	0.015	1.91	.	0.05	.	0.19
2	CURM 62.12	7.94	0.180	.	.	.	0.081	.	89.42	0.45	0.002	1.59	.	0.053	0.034	0.109
2	C34XNS10	7.67	29.0	.	.	.	.	.	.	0.05	.	0.02	0.010	0.05	<0.002	0.03

Number	As	B	Bi	N	Nb	O	Sb	Sn	Ti	Zr
C212X40010	.	.	.	.	.	.	.	.	0.11	.
C212X40020	.	.	.	.	.	.	.	.	0.06	.
C212X40060	.	.	.	.	.	.	.	.	1.34	.
C36XCN60	.	(0.0015)	0.0058	.	0.514	.	.	0.0307	0.0066	.
IARM 85C	0.0009	.	.	.	.	.	.	0.005	.	.
BCS 180/2	.	.	.	.	.	.	.	.	.	.
C36XCN40	.	.	.	.	.	.	.	.	.	.
IARM 236A	.	.	0.003	0.0002	.	0.002	<0.005	0.005	.	.
C36XCN100	.	0.0029	0.014	.	0.89	.	.	.	0.03	(0.055)
C36XCN90	.	0.005	<0.01	.	.	.	.	.	0.12	0.13
SRM 880	.	.	.	.	.	.	.	.	.	.
C34XNS50	.	.	.	.	.	.	.	0.194	.	.
GBW 02104	0.0098	.	0.0019	.	.	.	0.0020	.	.	.
C34XNS30	.	.	.	.	.	.	.	.	.	.
SRM 875	(0.0010)	.	(0.003)	Cd: 0.0022	(0.14)	<0.001	(0.009)	(0.0002)	Se: (0.0004)	
SRM 874	(0.0006)	.	<0.0002	Cd: <0.0002	(0.06)	<0.001	0.007	(0.0001)	Se: 0.00015	
IARM 84B	.	.	.	.	.	.	(0.002)	0.014	.	.
C36XCN10	.	.	.	.	.	.	.	.	.	.
CURM 62.12	.	.	.	.	.	.	.	0.111	.	.
C34XNS10	.	.	.	.	.	.	.	.	.	.

Number	As	B	Bi	N	Nb	O	Sb	Sn	Ti	Zr
--------	----	---	----	---	----	---	----	----	----	----

GUN METAL CHIPS

= class, where 1 = CRM and 2 = RM

C33X: typical analysis

100 g units

#	Number	Sn	Ni	Pb	Zn	Cu	Ag	Al	As	Bi	Cr	Fe	Mn	P	S	Sb	Si
1	BCS 207/2	9.74	0.28	0.70	1.60	87.35	.	0.013	0.066	0.04	.	0.029	.	(0.018)	.	0.10	0.016
1	C33XGM70	9.23	0.36	0.78	2.06	.	.	0.03	0.12	0.08	.	0.05	0.18	0.067	0.001	0.06	0.09
1	C33XGM60	7.31	1.069	3.11	2.99	84.46	0.0114	0.136	0.175	0.037	0.0019	0.131	0.0912	0.0566	0.07	0.258	0.124
1	BCS 183/4	7.27	1.30	3.15	3.47	84.08	.	(0.002)	0.13	0.005	.	0.056	(0.01)	0.090	0.11	0.23	(0.01)
2	CURM 71.32	6.46	0.70	4.43	6.52	80.48	0.34	0.12	0.25	0.051	0.05	0.35	0.046	0.016	0.08	0.26	0.022
1	C33XGM290	6.12	0.029	0.052	4.27	89.30	0.0025	(0.0004)	0.0017	0.0020	0.0004	0.011	0.0005	0.136	0.002	0.0015	0.0030
1	CURM 71.33	4.96	0.938	6.84	3.60	83.60	<0.002	<0.001	<0.001	<0.002	<0.0005	0.018	<0.0005	<0.001	<0.001	<0.002	<0.005
1	C33XGM50	4.47	0.697	4.81	5.80	83.38	0.0419	0.084	0.0342	0.0493	Cd: 0.0034	0.254	Co: 0.0453	0.042	0.0697	0.0505	0.0283
2	CURM 71.31	4.06	1.98	6.07	3.98	83.00	0.046	0.023	0.110	0.030	0.039	0.118	0.037	0.060	0.059	0.128	0.020
2	C33XGM80	4.03	0.115	6.78	6.21	82.3	0.105	0.0067	.	0.0138	.	0.298	0.0010	0.0213	0.0055	.	(0.0010)
1	C33XGM240	3.85	0.010	3.39	3.67	88.82	0.004	0.0001	0.0008	0.0008	0.0014	0.008	(0.0002)	0.190	0.003	0.0015	0.003
1	C33XRB20	3.19	0.255	3.85	9.14	82.67	0.0029	0.0362	0.0211	0.101	0.0017	0.493	0.0028	0.0208	0.078	0.019	0.0116
1	C33XGM40	2.50	2.05	5.20	7.17	82.6	0.0062	<0.002	0.021	0.041	.	0.051	(0.0019)	<0.005	0.33	0.042	<0.005
1	C33XRB10	2.137	0.0539	5.02	7.95	83.25	0.0174	0.0048	0.0030	0.0029	0.0013	0.928	0.0167	0.020	0.0044	0.432	0.063

#	Number	Sn	Ni	Pb	Zn	Cu	Ag	Al	As	Bi	Cr	Fe	Mn	P	S	Sb	Si
---	--------	----	----	----	----	----	----	----	----	----	----	----	----	---	---	----	----

BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: typical analysis

GBW: 50-100 g

all others: 100 g

#	Number	Zn	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn
1	GBW 02101	Rem	0.26	.	0.0024	58.00	0.89	0.73	.	0.0076	0.19	.	0.0091	.	0.54
1	BAM 224	39.40	0.0012	0.0025	0.0006	57.40	0.136	1.70	0.038	0.0112	1.13	0.0004	0.0026	(0.002)	0.066
1	IPT 40	39.1	0.010	.	.	58.10	0.007	.	0.0012	.	2.45	.	0.023	.	0.18
1	IARM 74B	38.9	0.003	<0.01	(<0.005)	60.4	0.011	<0.01	0.006	(0.008)	0.017	(0.003)	0.003	0.003	0.70
1	BAM 223	38.82	(<0.002)	0.0084	0.0018	58.74	0.091	(<0.001)	0.0214	0.0003	2.13	0.0011	0.0040	(<0.003)	0.089
1	BCS 390	38.6	0.83	.	.	57.1	0.83	1.30	0.033	.	1.04	.	.	(0.023)	0.34
1	IARM 74A	38.14	<0.01	(<0.01)	.	.	0.01	<0.01	0.01	0.006	0.02	0.001	<0.01	(<0.01)	0.50
1	IARM 75B	38.0	(0.005)	(0.004)	(0.001)	60.63	0.06	(0.003)	0.02	0.003	0.63	(0.001)	(0.004)	(0.003)	0.59
1	BAM 229	36.63	.	0.00217	.	63.334	0.01061	.	0.01114	(0.00106)	0.0192	.	0.00072	.	0.00485
1	BAM 179/2	35.8	2.22	(0.008)	.	58.5	1.02	0.86	0.56	.	0.35	.	.	0.044	0.70
2	CURM 48.01	32.6	<0.001	0.067	0.038	66.98	0.049	<0.001	0.134	0.016	0.106	.	0.047	0.041	0.002
2	CURM 48.02	32.58	0.013	0.025	0.004	67.16	0.053	0.067	<0.001	0.012	0.084	0.007	0.037	0.010	0.035
2	CURM 48.05	31.0	<0.002	<0.001	<0.0005	68.69	0.066	0.016	0.117	0.007	<0.003	0.013	<0.0005	0.026	0.083
1	C31X B40	28.39	.	0.046	0.0076	71.10	0.026	0.0074	0.0571	(0.023)	0.064	0.0091	0.0076	0.025	0.073
2	CURM 48.04	26.99	<0.001	0.034	0.014	72.68	0.008	0.012	0.096	0.006	0.043	0.011	0.026	0.004	0.018
1	IARM 313A	21.3	(0.001)	0.0010	(0.001)	75.4	0.011	(0.001)	(0.002)	0.09	0.042	0.0016	0.014	3.09	0.006
1	C31X B70	14.51	0.0015	0.0030	0.060	85.17	0.100	0.0010	0.0251	.	0.0338	.	0.0089	0.013	0.0876
1	IARM 151B	12.94	0.002	(0.002)	.	84.0	0.025	0.002	0.011	0.003	0.013	<0.001	(0.001)	3.11	0.009
1	C31XB80	9.52	(0.0013)	0.0081	0.031	90.28	0.0267	0.0012	0.0083	.	0.072	.	0.0108	0.0051	0.035
2	C31XB950	.	(0.001)	(0.01)	(0.01)	95.0	(0.01)	(<0.001)	(<0.001)	(<0.001)	(<0.001)	(<0.001)	(<0.001)	(0.01)	0.5

Number	Ag	B	C	Cd	Co	Cr	Se
GBW 02101	.	.	.	.	.	.	.
BAM 224	.	.	.	.	.	.	.
IPT 40	0.002	.	.	0.049	.	.	.
IARM 74B	(0.005)	.	.	.	.	.	.
BAM 223	.	.	.	.	.	.	.
BCS 390	.	.	.	(0.011)	.	.	.
IARM 74A	(0.002)	.	(0.012)	.	.	.	.
IARM 75B	(0.005)	.	(0.004)	.	(0.003)	.	.
BAM 229	.	.	.	.	.	0.0034	.
BCS 179/2	.	.	.	(0.003)	.	.	.
CURM 48.01	.	.	.	<0.0003	.	.	.
CURM 48.02	.	.	.	<0.0005	.	0.004	.
CURM 48.05	.	.	.	<0.0003	.	.	.
C31XB40	.	.	.	0.0330	0.033	0.087	.
CURM 48.04	.	.	.	<0.0003	.	.	.
IARM 313A	0.0017	0.0008	(0.002)	(0.0003)	(0.004)	(0.001)	(0.001)
C31X B70	.	0.0029	.	0.0011	0.0124	0.0006	.
IARM 151B	(0.01)	.	0.005	.	.	(0.003)	.
C31XB80	.	0.0021	.	.	.	.	.
C31XB950	.	.	.	.	.	.	.

BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: typical analysis

100 g units

#	Number	Cu	Zn	Al	Fe	Mn	Ni	Pb	Sn	As	Bi	Sb	Si
2	CURM 30.09	89.53	<10.47	<0.001	0.0005	<0.0003	<0.003	<0.001	0.001	<0.001	<0.001	<0.001	<0.001
2	CURM 43.02	76.21	20.82	2.40	0.128	0.035	0.068	0.064	0.060	0.083	<0.001	<0.001	0.038
2	CURM 43.01	74.36	22.44	2.75	0.008	0.064	0.121	<0.002	0.116	0.118	<0.002	<0.001	0.063
1	NM 421	70.48	29.39	.	0.07	.	.	.	.	.	.	.	.
1	BCS 344	68.98	30.98	.	.	.	.	.	.	.	.	.	.
2	CURM 30.18	63.66	32.33	3.28	0.006	<0.001	<0.001	<0.005	0.58	<0.005	<0.001	<0.001	0.131
1	C31XTB20	61.90	37.20	0.083	0.073	0.088	0.090	0.110	0.105	0.099	0.032	0.050	0.042
2	CURM 30.20	61.46	35.71	2.32	<0.005	<0.001	<0.001	<0.002	0.40	<0.001	<0.002	<0.002	0.17
2	CURM 30.15	60.66	<38.88	<0.001	0.50	<0.001	<0.001	<0.005	0.002	<0.005	<0.001	<0.001	<0.005
2	CURM 30.16	60.53	<38.33	<0.001	1.14	<0.001	<0.001	<0.005	0.002	<0.005	<0.001	<0.001	<0.005
1	C31XB20	60.3	.	0.19	0.10	0.31	0.22	0.31	0.18	0.14	0.04	0.10	0.01
2	CURM 30.11	59.86	<38.17	<0.001	0.002	0.23	1.70	0.005	0.002	<0.001	<0.002	<0.001	<0.001
2	CURM 30.24	58.33	<38.32	<0.001	0.001	<0.001	<0.001	3.31	0.002	<0.001	<0.002	<0.001	<0.001
2	CURM 30.21	56.23	40.08	1.44	0.003	<0.001	<0.001	0.004	2.01	<0.001	.	<0.002	0.213
2	DSZU MCX01	Rem	36.3	.	0.01	no uncertainties	.	0.005	0.0002	0.0001	.	0.0005	.

LEADED AND MANGANESE BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: typical analysis

100 g units

#	Number	Pb	Mn	Zn	Al	As	Fe	Ni	P	Sb	Si	Sn	Cu
2	CURM H30.24	3.02	<0.001	37.92	<0.001	<0.001	0.005	<0.001	.	<0.001	<0.001	<0.001	58.87
1	IARM 73C	2.97	(0.003)	35.1	(0.001)	(0.005)	0.199	0.095	(0.003)	0.008	(0.003)	0.256	61.3
1	C31X 783510	2.91	.	35.20	0.0146	0.0011	0.134	0.144	0.0197	0.0047	0.053	0.407	60.96
1	NM 412	2.56	.	38.99	.	.	0.09	.	.	.	.	0.12	58.18
1	BCS 385	2.24	(<0.005)	38.5	(<0.005)	.	0.15	0.13	.	(<0.01)	.	0.27	58.7
2	C31X 783520	2.08	.	32.88	0.199	0.046	0.077	0.0088	0.0149	0.053	.	0.202	64.34
1	C31X 783550	1.64	.	6.23	0.077	0.104	0.126	0.249	0.018	0.114	.	0.116	91.25
1	IARM 87B	1.58	0.006	36.1	0.20	0.007	0.29	0.095	0.008	0.014	0.004	0.78	60.9
2	C31X MNB10	1.44	0.188	29.37	0.596	.	0.268	0.053	.	.	.	0.105	67.77
1	C31X 783530	1.376	.	37.51	0.163	0.110	0.170	0.251	0.0391	0.084	0.038	0.121	60.07
1	C31X 783540	1.03	.	30.09	0.561	0.206	0.020	0.492	0.125	0.188	.	0.046	67.11
1	C31X MNB20	1.02	2.23	32.19	0.268	.	0.66	0.118	.	.	0.233	0.319	63.02
1	C31X MNB50	0.127	0.243	37.91	3.35	.	0.56	1.31	.	.	0.49	1.75	54.14

Number	Ag	B	Bi	C	Cd	Co	Cr	S	Se
C31X 783510	.	0.0005	0.0141	.	.	0.029	.	(0.001)	(0.0045)
IARM 73C	(0.006)	(0.0004)	0.011	(0.003)	0.0014	(0.002)	0.001	(0.002)	.
CURM H30.24	.	.	<0.001	.	.	.	.	0.002	.
NM 412	.	.	.	.	.	.	.	.	.
BCS 385	.	.	.	.	.	.	.	.	.
C31X 783520	.	.	.	.	.	.	.	.	.
C31X 783550	.	.	.	.	.	.	.	.	.
IARM 87B	(0.01)	.	0.003	0.003	.	0.007	(0.002)	(0.001)	.
C31X MNB10	.	.	.	.	.	.	.	.	.
C31X 783530	.	(0.0015)	0.0116	.	0.0039	0.0064	.	.	0.004
C31X 783540	.	.	.	.	.	.	.	.	.
C31X MNB20	.	.	.	.	.	.	.	.	.
C31X MNB50	.	.	.	.	.	.	.	.	.

ADMIRALTY & NAVAL BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: typical analysis

100 g units

#	Number	Sn	Pb	Zn	Cu	Al	As	Bi	Co	Fe	Mn	Ni	P	S	Sb	Si
2	CURM 42.25	2.72	0.0023	39.20	57.78	0.021	0.118	<0.001	.	0.003	0.169	<0.001	0.050	0.005	<0.001	<0.001
2	CURM 42.24	2.25	0.91	33.75	62.45	0.067	0.065	0.054	.	0.066	0.065	0.025	0.226	0.012	0.060	0.093
2	C42.25	2.2	<0.01	rem	58.5	0.02	0.10	<0.002	.	<0.005	0.13	<0.005	0.06	0.001	<0.005	<0.002
2	C31XNB40	2.07	0.09	.	63.8	0.29	0.025	0.09	.	0.11	0.02	0.16	0.20	0.002	0.39	0.22
2	CURM 42.23	1.63	0.575	22.13	74.36	0.008	0.168	0.034	.	0.354	0.019	0.168	0.128	0.045	0.356	0.015
2	CURM 42.22	1.10	1.10	26.32	70.46	0.042	0.217	0.046	.	0.23	0.122	0.061	0.177	<0.001	0.173	0.042
2	CURM 42.21	0.60	0.259	31.61	66.78	0.003	<0.003	0.013	.	0.119	<0.001	0.120	0.087	0.034	0.25	0.15
1	IARM 76C	0.66	1.6	37.2	60.4	(0.004)	(0.003)	.	.	0.013	(0.001)	0.003	0.003	(0.001)	(0.004)	(0.003)
2	C42.21	0.54	0.23	rem	66.1	0.005	<0.005	0.012	.	0.06	<0.005	0.096	0.081	0.007	0.19	0.081
1	C31X NB10	0.535	0.504	29.73	68.35	(0.0004)	0.161	0.0065	(0.0006)	0.0367	0.0508	0.520	0.0223	0.0024	0.0057	0.004

SILICON BRASS CHIPS

= class, where 1 = CRM and 2 = RM

typical analysis listed in mass % except * which is mg/kg

100 g units

#	Number	Si	Zn	Cu	Al	Fe	Mn	Ni	Pb	Sn	As	Co	Cr	Mg	P	S	Sb	Bi*	Cd*
1	C31XWSB50	6.07	0.343	90.06	0.218	0.79	0.496	0.492	0.100	1.050	0.0284	0.057	0.0087	0.0012	0.080	0.0081	0.124	298	47
1	C31XWSB10	5.95	7.55	(82.7)	1.90	0.100	0.099	0.076	0.55	0.23	0.13	0.34	0.017	0.003	0.040	<0.002	0.03	.	.
1	C31XWSB40	4.40	5.61	86.09	0.290	0.592	1.45	0.228	0.204	0.802	0.0286	0.096	0.103	0.006	0.042	(0.002)	0.0335	318	12
1	C31XWSB40	4.58	5.05	85.7	0.48	0.77	1.85	0.25	0.168	0.80	0.040	0.109	0.045	(0.0007)	0.060	<0.005	0.067	.	.
2	C31XWSB60A	2.61	1.12	Rem	0.10	0.05	0.29	0.37	0.96	0.39	0.01	0.05	.	0.004	0.06	0.01	0.10	.	.
1	C31XWSB60D	2.48	0.881	94.74	0.059	0.032	0.248	0.117	0.95	0.056	0.0051	0.247	0.058	(0.001)	(0.020)	(0.002)	0.007	56	71

BRONZE CHIPS

= class, where 1 = CRM and 2 = RM

SRM: 150 g chips

all others: 100 g chips

#	Number	Sn	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Si	Zn
1	IARM 91D	6.43	(0.001)	0.060	81.9	0.023	(0.001)	0.43	0.09	7.8	(0.0016)	3.21
1	IARM 211A	6.23	0.002	5.0	88.4	0.004	(0.003)	0.003	0.19	0.014	0.003	0.006
1	IARM 267A	4.95	0.003	(0.005)	87.8	0.019	(0.002)	5.1	0.037	0.026	0.003	2.06
1	IARM 78B	4.73	(0.002)	(0.001)	87.7	0.02	(0.002)	0.077	0.19	3.87	<0.002	3.55
1	IARM 77B	4.66	(0.001)	(0.004)	95.2	0.002	(0.002)	0.002	0.148	0.016	(0.003)	0.007
1	SRM 158A	0.96	0.46	.	90.93	1.23	1.11	0.001	0.026	0.097	3.03	2.08
1	IARM 83B	0.85	0.002	.	58.7	0.97	0.13	0.010	0.004	0.017	(0.003)	39.3
1	IARM 72B	0.029	.	.	90.08	0.007	.	0.004	0.005	1.99	(0.002)	7.81
1	IARM 80B	0.018	10.19	<0.005	81.2	3.31	0.54	4.69	0.009	0.009	0.030	0.078
1	IARM 235A	0.018	8.9	.	81.2	4.07	1.17	4.44	0.012	0.012	0.061	0.083
1	IARM 79B	0.017	9.19	(0.003)	88.4	2.13	0.16	0.075	0.005	(0.003)	0.019	0.013
1	IARM 82B	0.017	0.002	.	95.3	0.080	1.04	0.011	0.004	0.011	3.22	0.38
1	IARM 79C	0.010	9.20	.	87.6	2.28	0.20	0.55	0.006	<0.005	0.033	0.014
2	IARM 94A	(<0.01)	10.63	.	.	4.04	0.16	4.37	<0.01	0.009	<0.01	0.09
1	IARM 93B	0.009	10.33	.	85.4	3.87	0.024	0.088	(0.002)	0.012	0.024	0.17
1	IARM 81B	0.008	6.70	<0.001	91.2	0.047	0.012	0.003	0.004	0.006	1.84	0.176
1	IARM 204A	0.005	10.55	.	83.3	3.87	0.052	1.95	0.007	0.004	0.034	0.22
1	IARM 94B	(0.003)	10.8	.	80.6	3.99	0.071	4.31	0.011	0.004	0.028	0.14
#	Number	Sn	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Si	Zn

Number	Ag	As	C	Co	Cr	S	Sb	
IARM 91D	0.020	0.008	(0.0020)	0.013	0.0007	0.018	0.112	Cd: 0.0009 last of stock
IARM 211A	0.005	(0.01)	.	(0.001)	(0.002)	0.002	0.057	
IARM 267A	(0.002)	(0.004)	(0.003)	(0.002)	(0.001)	0.0014	<0.03	
IARM 78B	0.008	<0.003	<0.002	<0.0005	.	0.010	0.01	
IARM 77B	(0.002)	(0.001)	0.003	.	.	0.002	0.005	
SRM 158A	.	.	.	.	.	.	.	
IARM 83B	(0.002)	.	0.003	(0.003)	(0.003)	(0.001)	(0.004)	
IARM 72B	(0.002)	(0.003)	0.002	.	.	0.0015	0.006	
IARM 80B	0.006	(0.004)	(0.01)	0.014	0.012	(0.001)	(0.004)	
IARM 235A	<0.005	<0.005	0.009	0.01	0.01	0.002	(0.004)	
IARM 79B	0.002	.	0.002	(0.002)	(0.003)	(0.001)	.	
IARM 82B	.	<0.002	(0.003)	.	0.004	0.003	<0.01	
IARM 79C	<0.005	0.003	0.003	<0.005	(0.002)	<0.001	<0.005	
IARM 94A	.	(<0.01)	(0.014)	0.01	.	(0.003)	(<0.01)	
IARM 93B	(0.004)	<0.01	0.007	0.006	(0.007)	0.002	(0.012)	
IARM 81B	(0.004)	0.058	0.002	.	0.002	<0.001	0.003	
IARM 204A	0.009	(<0.01)	0.006	0.008	0.008	(0.002)	(<0.01)	
IARM 94B	0.017	<0.01	(0.006)	0.011	0.017	0.002	(0.011)	
Number	Ag	As	C	Co	Cr	S	Sb	

ALUMINUM BRONZE CHIPS

= class, where 1 = CRM and 2 = RM

C32X: typical analysis

#	Number	Al	Cu	Fe	Mn	Ni	P	Pb	Si	Sn	Zn	As	C	Cr	Mg	Sb	Units
1	C32XALB30	11.56	79.94	4.15	0.374	3.72	0.025	0.11	0.135	0.10	0.325	0.0060	.	0.0089	0.088	.	50 g
2	CURM 52.52	10.69	79.26	6.02	0.145	3.56	.	0.074	0.011	0.044	0.094	.	.	0.004	0.007	.	100 g
1	C32XALB10	10.3	(80.4)	3.00	0.094	5.90	0.016	0.218	0.132	0.025	0.035	(0.002)	.	0.011	0.0013	.	50 g
1	IARM 80C	10.1	80.5	3.86	0.58	4.71	0.004	(0.004)	0.077	0.003	0.096	0.006	0.008	0.008	Cr:0.013	0:0.0007	100 g
1	BCS 364/1	9.71	80.23	4.64	0.12	4.82	.	0.010	0.08	0.03	0.31	.	.	.	(<0.01)	.	100 g
1	C32XALB20 *	9.6	(80.7)	4.1	0.055	4.6	0.045	0.26	0.29	0.095	0.25	0.007	0.01	0.003	0.003	.	50 g
2	CURM 51.14	8.42	88.57	0.72	0.55	0.219	0.12	0.003	0.286	0.113	0.656	0.44	.	.	.	.	100 g
1	C32XALB80	8.1	(75.3)	6.70	0.31	6.79	0.14	0.009	0.69	0.58	1.02	0.17	.	0.045	(0.002)	.	50 g
1	C32XALB60	8.05	81.98	2.53	0.904	5.31	0.0101	0.096	0.295	0.147	0.685	0.012	(0.0025)	0.0097	0.0019	.	50 g
1	C32XALB40	7.87	79.61	3.55	1.028	7.03	0.036	0.120	0.252	0.085	0.264	0.0130	.	0.022	0.153	.	50 g
2	CURM 52.54	7.85	81.59	3.31	1.20	5.40	.	0.086	0.022	0.135	0.39	.	.	<0.005	<0.005	.	100 g
2	C32XALB50	7.6	.	1.95	1.39	5.11	.	0.04	0.03	0.03	0.16	.	.	.	0.018	.	50 g
2	CURM 51.13	7.30	88.79	1.81	0.898	0.057	0.022	0.104	0.174	0.270	0.335	0.215	.	.	.	.	100 g
2	CURM 51.12	6.36	88.29	2.87	1.33	0.112	<0.001	0.219	0.005	0.196	0.45	0.111	.	.	.	.	100 g
2	CURM 51.11	5.27	93.95	0.060	<0.001	0.012	0.035	0.33	0.159	0.027	0.111	<0.001	.	.	.	.	100 g

* Provisional Analysis

LEADED BRONZE CHIPS

#=class, where 1=CRM and 2=RM

C32X: typical analysis 100 g chips

IPT 74: 60 g chips

IPT 10A, B: 80 g chips

all others: 100 g chips

#	Number	Pb	Sn	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	P	S	Sb	Si	Other
1	IARM 184A	19.0	6.0	0.37	(74)	0.0016	0.010	(0.03)	(0.003)	(0.002)	0.30	0.008	0.021	0.27	(0.002)	
1	GBW 02140	17.62	4.24	5.37	72.25	.	.	.	.	.	.	.	.	.	.	.
2	CURM 50.01	11.74	9.45	1.17	74.08	0.018	0.22	0.029	0.243	0.024	2.24	0.113	0.113	0.59	0.007	
2	CURM 50.02	10.67	10.34	0.006	78.84	<0.001	<0.002	<0.0005	<0.001	<0.0005	<0.0005	0.046	<0.001	<0.0005	<0.002	
2	CURM 50.04	9.94	11.30	0.66	76.11	0.014	0.06	0.10	0.10	0.028	1.10	0.035	0.14	0.50	0.011	
1	C32XLB20	9.42	12.38	0.27	(76.8)	0.04	0.017	0.009	0.40	0.22	0.22	0.04	(0.001)	0.023	<0.01	
2	C32XLB30	9.4	10.3	<0.01	.	<0.01	0.02	0.025	<0.01	<0.01	1.52	0.006	0.020	0.04	.	
1	BCS 364	9.24	9.36	0.13	80.7	(<0.002)	(0.07)	(<0.01)	(<0.005)	.	0.28	0.057	(0.06)	0.18	(<0.005)	
2	CURM 50.03	8.86	8.41	1.72	77.42	0.005	0.11	0.051	0.018	0.037	2.89	0.159	0.064	0.24	0.005	
1	C32X LB130	7.59	5.80	0.520	84.87	0.0011	0.131	0.0721	0.0160	0.0005	0.828	0.0161	0.115	0.0186	(0.0035)	Ag: 0.0063
1	IPT 74	6.24	2.84	9.88	80.41	.	0.002	.	0.315	.	0.15	0.002	0.056	0.016	.	Cd: 0.013
1	GBW 02139	6.16	4.08	6.96	81.45	.	.	.	.	.	.	.	.	.	.	.
1	IARM 86D	5.4	4.9	4.6	(84.5)	(0.002)	0.007	0.042	0.035	0.0011	0.40	0.072	0.029	0.112	Ag:0.022	Co: 0.004
2	C32X SN10	5.15	11.75	0.804	79.96	(<0.002)	.	.	0.0034	0.0018	2.17	0.0025	0.0064	0.006	.	
1	IPT 10B	4.74	4.61	4.73	85.2	.	0.019	.	0.211	.	0.33	0.003	0.068	0.114	.	
1	IPT 10A *	4.72	4.58	4.71	85.13	.	0.020	.	0.211	.	0.33	0.003	(0.068)	0.113	.	
1	C32X SN20	1.97	13.54	1.28	82.8	0.0004	.	.	0.0332	0.0043	0.104	0.082	0.0326	0.100	.	
1	C32X SN40	1.059	18.80	0.342	77.88	0.034	0.0468	.	0.060	0.0065	0.556	0.988	0.040	0.102	(0.004)	Co: 0.151
1	C32X SN30	0.270	16.51	0.43	81.32	0.0004	.	.	0.0782	0.0026	0.513	0.297	0.096	0.260	.	

* IPT 10A certification expired September 2009, our remaining stock is offered at a discounted price.

PHOSPHOR BRONZE CHIPS

= class, where 1 = CRM and 2 = RM

mass % except * which is mg/kg

C, CURM: typical analysis 100 g

GBW, BCS: 150 g

SRM: 100 g

#	Number	P	Sn	Zn	Cu	Al	As	C	Fe	Mg	Mn	Ni	Pb	S	Sb	Se*	Si
2	CURM 54.03	0.954	7.30	0.003	91.74	<0.001	0.006	.	0.005	<0.0003	<0.0005	0.0019	0.003	<0.001	0.0007	.	<0.002
2	C32XPB10	0.84	11.0	0.02	.	<0.01	0.05	.	<0.01	.	<0.01	0.12	0.37	.	0.07	.	0.01
1	C32XPB110	0.72	3.00	1.93	89.6	0.068	0.175	.	0.493	<0.002	0.80	1.01	1.02	0.016	0.54	.	0.52
1	BCS 374	0.59	9.80	0.006	89.5	(<0.005)	.	.	(<0.005)	.	.	0.014	0.064	0.012	(0.01)	.	(<0.005)
1	GBW 02133	0.423	5.79	.	93.72	.	.	.	.	.	.	.	.	.	.	.	.
2	C32XPB120	0.42	4.64	0.49	(92.0)	<0.001	0.098	.	0.31	<0.001	0.39	0.51	0.47	(0.010)	0.024	55	0.01
1	GBW 02136	0.372	5.79	.	93.70	.	.	.	0.011	.	.	.	0.021	.	0.0058	.	0.0012
1	C32X PB230	0.319	7.56	0.0020	92.04	(0.0004)	0.0011	0.004	(0.0005)	.	(0.0006)	0.0033	0.0042	0.0015	0.0025	.	0.0016
1	SRM 872	0.26	4.16	4.0	87.36	.	.	.	(0.003)	.	.	.	4.13	.	.	.	.
1	GBW 02134	0.238	6.82	.	92.85	.	.	.	.	.	.	.	.	.	.	.	.
1	C32XPB130	0.22	6.96	0.27	(91.5)	<0.001	0.052	.	0.14	<0.001	0.096	0.26	0.25	(0.03)	0.12	.	<0.005
2	CURM 54.02	0.107	5.53	0.410	92.87	0.020	0.023	.	0.102	0.0020	0.101	0.109	0.663	0.030	0.026	.	0.012
1	GBW 02135	0.106	7.92	.	91.73	.	.	.	.	.	.	.	.	.	.	.	.
1	SRM 871	0.082	8.14	0.025	91.68	.	.	.	<0.001	.	.	.	0.010	.	.	.	.
2	CURM 54.01	0.053	3.17	0.346	95.42	0.040	0.044	.	0.028	0.008	0.158	0.348	0.307	0.023	0.070	.	0.039
1	C32XPB140	0.032	8.58	0.029	91.0	(0.001)	0.021	.	0.005	<0.001	<0.002	0.092	0.051	0.086	0.061	.	<0.005
2	C32XPB100	0.0236	11.93	0.037	87.70	(0.0008)	0.011	.	0.008	0.004	0.0010	0.057	0.055	0.018	0.0051	.	0.0015

CRM LEAD ORE CONCENTRATE

analysis listed in mass %

200 g units

Number	Pb	Ag	Al	As	Ca	Cd	Cu	Fe	Mg	Mn	Na	S	Sb	SiO ₂	Tl	Zn
CAN CPB-2	63.52	(0.03573)	0.074	(0.04)	(0.0776)	0.0167	0.1213	7.065	0.0683	(0.0395)	(0.01)	(18.02)	(0.423)	(0.652)	(0.0340)	6.04

CRM LEAD

analysis listed in mg/kg

Number	Type	Ag	As	Au	Bi	Cd	Cu	Ni	Sb	Se	Sn	Te	Tl	Zn	Units
VS 2036-2001	Powder	2322	.	32.6	.	.	.	.	.	.	.	.	.	.	100 g powder
VS 2038-81	Powder	415	.	0.21	.	.	.	0.410	.	.	.	.	.	.	100 g powder
BCR 288B	Added impurities	30.5	55.7	.	215.8	33.3	19.3	4.57	32.5	<0.2	30.6	32.8	2.3	8.2	160 g chips
BCR 287B	Thermal refined	15.2	<0.003	.	67.3	0.36	0.98	0.024	0.040	<0.005	<0.05	<0.02	0.73	<0.1	160 g chips
BCR 286B	Electro refined	0.015	<0.0002	.	21.5	0.125	1.49	0.041	0.10	<0.05	<0.05	<0.1	2.5	<0.1	160 g chips

LEAD BASE CHIPS AND POWDER

= class, where 1 = CRM and 2 = RM

analysis listed in mass %

BCS: 100 g powder

SRM: 150-200 g powder

all others: 100 g chips

#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	In	Na	Ni	Se	Te	Zn	Other
1	SRM 1129	62.7	0.13	0.075	0.055	0.13	.	.	0.16	.	.	.	0.010	.	.	.	.
1	SRM 127b	39.3	0.43	0.01	0.01	0.06	.	.	0.011	.	.	.	0.012	.	.	.	.
1	C93XS30APR30	33.0	0.96	0.021	0.018	0.28	.	0.009	0.008	0.003	.	.	0.010	.	.	0.0053	.
1	C93XS30APR20	30.68	1.80	0.049	0.0178	0.168	.	0.0061	0.062	0.0026	0.0199	.	0.042	.	0.0102	0.028	.
1	C93XS30APR10	28.58	2.54	0.0144	0.010	0.059	.	0.0014	0.192	(0.012)	0.0094	.	0.0010	.	0.0024	(0.004)	.
1	GBW 02401	15.97	16.09	.	0.014	0.024	.	.	1.96	.	.	.	.	.	.	.	Pb: 65.72
2	C86XPSS40	10.69	16.97	(0.006)	0.278	0.120	.	0.047	0.328	*1	0.013	.	0.0031	.	.	*2	.
2	C86XPSS20	6.33	8.16	0.004	1.42	0.054	.	0.069	0.118	*1	(0.002)	.	0.0080	.	.	*2	.
1	SRM 53e	5.84	10.26	.	0.057	0.052	.	.	0.054	<0.001	.	.	0.003	.	.	.	.
1	GBW 02402	5.69	15.02	.	0.012	0.0075	.	.	2.88	.	.	.	.	.	.	.	Pb: 76.22
1	BCS 177/2	5.07	10.1	.	0.05	0.028	.	.	0.12	.	.	.	0.007	.	.	.	Pb: 84.5
2	C85XSn20	1.87	0.023	0.002	*5	0.0093	.	*1	0.035	.	.	.	*1	0.0058	*1	*1	.
1	C85X ANTH	1.45	6.05	0.0071	0.217	0.0194	.	0.0046	0.0291	0.010	.	.	0.0062	0.0149	0.0071	(0.0007)	.
1	C85XHRH	0.874	1.13	0.247	0.74	0.092	.	(0.0002)	0.080	.	.	.	0.001	0.037	0.002	.	.
1	C84XBA10	0.85	*1	0.0088	*1	0.0084	0.106	0.0016	0.0041	.	.	.	.	.	0.006	0.0007	.
2	C84XBA20	0.51	0.002	0.008	*05	0.024	0.061	0.0052	0.003	.	.	.	.	.	*2	0.019	.
1	C84XBA80	0.293	0.0009	0.0043	(0.0004)	0.019	0.157	0.0010	0.0007	.	.	.	.	.	<0.002	0.0013	Al: 0.021
2	C85XSb120	0.21	11.4	0.0015	0.11	0.007	.	*1	0.30	*1	.	.	0.0016	*1	*5	0.087	.
2	C83XPR70	0.189	0.795	0.290	0.051	0.479	.	0.455	0.176	(0.0008)	0.653	.	(0.0015)	0.0052	0.0097	(0.0006)	Pt: 0.0047
2	C85XSb30	0.13	2.66	*2	0.14	0.010	.	*1	0.032	*1	.	.	0.0013	0.024	*2	(0.0002)	.
2	C84XBA40	0.11	0.061	0.003	(0.0008)	0.074	(0.014)	0.010	0.031	.	.	.	0.0007	.	0.029	(0.0003)	.
2	C85XSb80	0.085	8.43	0.016	0.02	0.010	.	*1	0.032	*1	.	.	0.0014	0.0007	*5	(0.0002)	.
2	C85XSb100	0.080	10.2	0.0015	0.11	0.007	.	*1	0.14	*5	.	.	0.0013	*1	*2	0.014	.
2	C85X0616Pb10	0.070	1.78	0.002	0.070	0.025	.	0.0023	0.048	*1	.	.	0.001	0.018	0.001	0.001	.
2	C85XSb50	0.057	5.14	0.0017	0.12	0.022	.	*1	0.007	*1	.	.	0.0025	0.0008	*1	*1	.
1	C83XPR40	0.009	0.012	0.014	(0.002)	0.014	0.0026	0.010	0.015	.	0.005	0.001	0.013	0.003	0.025	0.005	Au: 0.002
1	C83XPR10	0.004	0.005	0.088	0.050	0.080	0.004	0.075	0.006	.	0.045	0.01	0.001	<0.002	0.003	0.002	Au: 0.008
2	BM Pb	<0.0005	(5ppm)	<0.0003	<0.0005	<0.004	.	.	<0.0005	.	.	.	<0.0001	.	.	<0.001	Pb: 99.99
#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	In	Na	Ni	Se	Te	Zn	Other

* In the above chart, * represents <0.00 so that, for example, *1=<0.001
C83X-86X, C93X: typical analysis

LEAD-SILVER ALLOY CHIPS

typical analysis

Class	Number	Ag	Al	As	Bi	Cd	Cu	Fe	In	Sb	Sn	Zn	Units
RM	C82XAg6.0	6.0	0.002	0.025	0.54	0.010	0.19	0.001	0.006	0.48	0.50	0.008	100 g
RM	C82XAg3.5	3.48	<0.001	0.022	0.27	0.004	0.075	0.001	0.045	0.11	0.24	0.001	100 g
CRM	C82XAg1.5	1.55	.	0.006	0.06	.	0.27	.	.	0.39	0.04	0.004	100 g

RM LEAD BASE BATTERY ALLOY CHIPS

typical analysis

100 g units

Number	Sn	Ag	As	Bi	Ca	Cd	Cu	Sb	Te	Zn
C84XBA60	0.73	0.002	<0.001	0.008	0.095	(0.002)	0.0010	0.001	<0.001	<0.001
C84XBA70	0.61	0.002	<0.001	0.009	0.036	<0.002	0.0009	0.002	<0.001	<0.0005

CRM MAGNESIUM CHIPS

typical analysis

Number	Ag	Al	Be	Ca	Cd	Ce	Cu	Fe	La	Mn	Ni	Pb	Si	Sn	Zn	Units
C61XMgP30	0.013	0.090	<0.0001	0.053	0.015	0.006	0.030	0.014	0.004	0.015	0.005	0.015	0.050	0.016	0.019	30 g
C61XMgP20	0.003	0.065	<0.0001	0.014	0.006	0.002	0.012	0.006	0.002	0.012	0.003	0.006	0.031	0.007	0.012	30 g
C61XMgP10	<0.001	0.013	<0.0005	<0.001	<0.0005	.	(0.0006)	0.027	.	0.0037	<0.002	0.005	0.005	(0.001)	0.002	30 g

MAGNESIUM BASE CHIPS

= class, where 1 = CRM and 2 = RM

BCS: 100 g units

C: typical analysis 30 g units

#	Number	Al	RE	Ag	Mn	Zn	Be	Ca	Cd	Cu	Fe	Ni	Pb	Si	Sn	Zr	Other
1	C65XMgA50	8.01	.	0.0050	0.399	0.411	0.0013	0.013	0.0035	0.020	0.006	0.020	0.043	0.110	0.013	.	Sr: 0.00034
1	BCS 316	8.01	.	.	0.28	0.68	.	.	.	0.040	0.009	0.004	0.024	0.055	0.005	.	
1	C65XMgA20	7.19	.	.	0.14	0.95	0.0007	(0.005)	.	0.112	0.011	0.003	0.006	0.13	0.050	.	Sr: 0.0005
1	C65XMgA10	5.45	.	0.012	0.060	1.26	0.006	0.029	0.013	0.221	0.021	0.021	0.012	0.20	0.072	(0.0015)	Ce: 0.009 La: 0.007
1	C65XMgB30	3.21	.	(0.002)	0.012	0.60	0.0030	0.029	0.011	0.021	0.007	0.0019	0.004	0.011	0.005	.	
1	C65XMgB10	2.39	.	0.03	0.68	1.71	0.0007	0.41	0.07	0.20	0.016	0.012	0.01	0.17	0.011	.	Ce: 0.015 La: 0.013
2	C65XMgB20	2.32	.	.	0.44	0.95	.	0.008	.	0.096	0.015	0.005	0.012	0.06	0.012	.	
2	C63XMgE20	0.056	.	.	1.58	0.04	.	(0.003)	.	0.058	0.009	0.012	0.013	0.035	0.011	.	
2	C65XMgD30	0.041	0.008	0.005	0.28	1.97	0.0003	(0.07)	.	0.058	0.023	0.002	0.009	0.020	0.007	0.029	
1	C63XMgE30	0.015	.	0.005	2.36	0.022	.	0.13	0.001	0.012	0.004	0.0023	0.005	0.01	0.0057	.	
2	C67XMgF30	0.01	2.40	.	0.015	3.18	.	0.006	.	0.03	0.009	0.002	0.017	0.005	0.006	0.48	
1	BCS 307	(0.008)	2.84	.	0.006	2.08	.	.	.	0.005	0.002	.	.	.	.	0.56	
2	C66XMgC20	0.007	.	.	0.016	5.93	.	0.006	.	0.15	0.013	0.016	0.018	0.007	0.010	0.45	
2	C66XMgD40	0.006	.	.	0.02	2.80	.	0.004	.	0.01	0.003	0.002	0.017	0.01	0.003	0.44	
2	C68XMgH40	0.004	2.4	2.05	0.015	0.17	.	.	.	0.03	0.001	0.004	.	0.002	.	0.46	
2	C68XMgL10	0.002	2.09	1.41	0.016	0.009	.	.	.	0.013	0.009	0.005	.	0.001	.	0.54	Th: 0.24
2	C67XMgG40	0.001	(<0.01)	.	0.015	5.47	.	0.001	.	0.06	0.003	0.007	0.009	0.003	0.005	0.72	Th: 1.85

RE = Total Rare Earths

RM MANGANESE

Number	Mn	As	C	Co	Cu	Fe	Ni	P	Pb	S	Si	V	Units
BM Mn	99.9	<0.0001	<0.0005	<0.0001	<0.0002	<0.0020	<0.0001	<0.0002	<0.0001	0.00040	<0.0010	<0.0001	100 g chips

NICKEL POWDER

certified analysis listed in mg/kg except % which is mass %

Number	Ag	Al	Au	C	Cr	Cu	Fe	Ir	Mn	Mo	Ni%	Os	P	Pb	Pd	Pt	Rh	Ru	S	Si	Units
CRM - nickel ore																					
VS 1702-86	23.4	.	0.84	.	.	(3%)	.	0.11	.	.	5.4	0.06	.	.	30.0	8.6	0.98	0.34	.	.	200 g
RM - nickel powder																					
BS HPN-1	(<0.1)	70	.	268	22	2	202	.	2	3	.	.	5	0.2	.	.	.	.	4	6	100 g

continued informational values

Number	As	B	Ba	Be	Bi	Ca	Cd	Co	Ga	H	In	Mg	N	Na	O	Sb	Se	Sn	Te	Ti	Tl	V	Zn
VS 1702-86	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.
BS HPN-1	<0.5	<2	<1	<1	<0.2	3	<0.1	<2	<0.5	70	<0.2	1	17	4	1400	<0.1	<0.2	<1	<0.2	<1	<0.1	<1	<1

CRM NICKEL CHIPS

= class, where 1 = CRM and 2 = RM

100 g units

#	Number	Ag	Al	As	B	Be	Bi	C	Ca	Cd	Co	Cr	Cu	Fe
2	IARM 190A	0.00109	0.0050	0.0028	<0.0005	(<0.0001)	0.00111	0.0022	<0.0010	0.0005	0.0008	(0.0001)	0.0017	0.0099
2	IARM 189A	0.00024	0.0044	0.00007	(<0.0005)	(<0.0001)	0.00026	0.0023	<0.0010	0.00008	0.00031	(0.0010)	0.00090	0.0038
2	IARM 188A	0.00011	0.0024	0.00007	(<0.0005)	(<0.0001)	0.00009	0.0022	<0.0010	0.00002	0.00017	(0.0006)	0.00018	0.0019
2	IARM 187A	0.00001	0.0011	0.00001	(<0.0005)	(<0.0001)	<0.00001	0.0013	<0.0010	(<0.00001)	0.00010	(0.0003)	0.00022	0.0019
2	IARM 191A	0.00001	0.00015	0.0013	(<0.0005)	(<0.0001)	<0.00001	0.0014	<0.0010	<0.0001	0.0545	0.00021	0.00042	0.00079
1	BAM RS 4	<0.0001	<0.0001	<0.00005	(<0.0002)	.	(<0.00001)	0.00094	<0.0001	<0.00002	<0.0001	<0.00005	<0.0002	0.00042

Number	Ga	Mg	Mn	Mo	N	Ni	O	P	Pb	S	Sb	Se
IARM 190A	<0.00005	(0.0006)	0.00018	(<0.0001)	(0.0001)	.	(0.0019)	0.0034	0.00093	0.00033	0.0011	0.00065
IARM 189A	<0.00005	(0.0008)	0.00019	(<0.0001)	(0.0001)	.	(0.0018)	0.00037	0.00029	0.00018	0.00039	0.00021
IARM 188A	<0.00005	(0.0004)	0.00023	<0.0001	(0.0001)	.	(0.0017)	0.00014	0.00010	0.00018	0.00011	0.00007
IARM 187A	<0.00005	(0.0002)	0.00030	(<0.0001)	(0.0001)	.	(0.0014)	<0.00010	0.000015	0.00019	<0.00005	<0.00001
IARM 191A	<0.00005	(0.0002)	0.00031	(<0.0001)	(0.0002)	.	(0.0030)	<0.00010	0.00003	0.00021	<0.00005	0.00019
BAM RS 4	<0.00002	<0.00008	<0.00005	(<0.00002)	0.00025	99.995	(0.0029)	.	<0.0001	(<0.0002)	<0.00002	<0.0001

Number	Si	Sn	Te	Ti	Tl	V	W	Zn
IARM 190A	0.0028	0.00062	0.00089	(0.0006)	0.00058	(<0.00005)	.	0.00081
IARM 189A	0.0019	0.00022	0.00017	(0.0003)	0.00023	(<0.00005)	.	0.00028
IARM 188A	0.0018	0.00011	0.00008	(0.0002)	(0.00009)	(<0.00005)	.	0.00023
IARM 187A	(0.0018)	0.00004	<0.00001	(0.0003)	<0.00002	(0.00008)	.	<0.00005
IARM 191A	(0.0005)	0.00004	<0.00001	(<0.0001)	<0.00002	(<0.00005)	.	0.00019
BAM RS 4	(<0.0002)	<0.00003	(<0.00002)	.	<0.00002	(<0.00002)	(<0.00001)	<0.0004

NICKEL ALLOY CHIPS

= class, where 1 = CRM and 2 = RM

C212X: typical analysis

#	Number	Al	C	Co	Cr	Cu	Fe	Mg	Mn	Mo	Nb	Ni	Si	Ti	V	W
1	IARM 283A	6.05	0.114	9.8	8.05	(0.01)	0.044	0.0033	(0.001)	5.94	0.020	64.4	0.019	0.98	0.0058	0.056
2	C212X 40060	3.85	0.03	0.05	0.12	.	1.95	0.016	0.83	.	.	63.3	3.94	1.34	.	.
1	SRM 882	2.85	(0.006)	(0.007)	(0.0001)	31.02	(0.009)	(0.001)	0.0007	.	.	65.25	(0.006)	0.57	(0.0001)	.
1	IARM 257A	0.34	0.005	0.024	1.57	0.019	1.47	0.010	0.63	28.0	<0.03	67.9	0.024	0.002	0.01	0.07
2	C215X HB10	0.31	0.056	0.094	0.84	0.054	7.71	.	1.21	33.6	.	.	0.48	(0.026)	0.87	.
1	IARM 63B	0.31	0.0025	0.019	0.47	0.012	1.68	0.005	0.61	27.3	(0.001)	69.6	0.019	0.003	(0.010)	0.060
1	VS N2/3	0.20	0.018	.	5.59	0.083	Rem	.	0.84	.	.	76.3	1.40	.	.	.
1	C215X HB50	0.19	0.150	2.47	0.03	0.05	3.05	.	0.44	26.0	.	.	1.32	0.03	0.14	.
1	IARM 55B	0.09	0.004	0.036	8.25	0.013	1.12	0.011	0.323	24.62	0.08	65.4	0.021	0.002	0.005	0.12
2	C212X 40010	0.09	0.10	0.12	0.05	.	0.57	0.13	3.04	.	.	67.6	1.48	0.11	.	.
2	IARM 202A	0.080	0.13	0.020	0.008	32.3	1.31	0.024	1.03	(<0.01)	.	64.8	0.046	0.005	(<0.01)	(<0.01)
2	IARM 203A	0.066	0.005	12.88	0.72	0.05	40.6	(<0.002)	0.023	0.090	5.00	38.44	0.41	1.58	(<0.01)	(0.02)
2	C212X 40020	0.05	0.04	0.08	0.02	.	1.17	0.02	2.00	.	.	65.2	0.10	0.06	.	.
1	BCS 363/1	0.027	0.140	0.032	(0.05)	31.90	1.86	.	1.26	.	.	64.7	0.028	(0.03)	.	.
1	BCS 371	.	0.30	0.39	.	.	.	0.060	.	.	.	.	0.34	.	.	.
1	VS N10/4	.	0.0074	.	.	(0.005)	0.399	.	0.237	27.04	.	.	0.093	0.085	1.57	.
1	VS N3/4	.	0.0064	.	2.16	4.98	Rem	.	0.424	.	.	.	0.264	.	.	.
1	VS N4/3	.	0.0057	.	0.070	5.65	5.80	.	0.762	4.87	.	.	0.81	.	.	.
1	NCS HC20502	.	0.0015	0.043	0.466	0.027	Rem	.	0.983	4.13	.	80.07	0.317	0.004	.	.

Number	B	N	O	P	Pb	S	Sn	Zr	Units
IARM 283A	0.014	0.0003	0.0004	0.003	Ta: 4.3	0.0006	(0.0002)	0.053	100 g
C212X 40060	.	.	.	.	0.02	0.035	.	.	50 g
SRM 882	(0.0001)	.	.	.	(0.0006)	0.0014	(0.003)	(0.0005)	100 g
IARM 257A	<0.003	0.0039	0.0004	0.004	<0.0005	0.0005	<0.0005	(0.008)	100 g
C215X HB10	(0.0023)	0.042	.	0.006	.	0.026	(0.004)	.	50 g
IARM 63B	(<0.002)	0.0041	0.0010	0.004	.	(0.0004)	.	(0.002)	100 g
VS N2/3	.	.	.	0.0034	.	0.0025	.	.	100 g
C215X HB50	(0.003)	0.008	.	0.053	.	0.002	(0.002)	.	50 g
IARM 55B	0.002	0.016	0.0009	0.005	.	0.0010	.	(0.005)	100 g
C212X 40010	.	.	.	.	0.08	0.022	.	.	50 g
IARM 202A	(<0.002)	0.0004	(0.0018)	0.011	.	0.032	.	0.010	100 g
IARM 203A	(0.002)	.	.	0.006	.	0.0009	.	<0.01	100 g
C212X 40020	.	.	.	.	0.04	0.075	.	.	50 g
BCS 363/1	.	.	.	.	.	(0.002)	.	.	100 g
BCS 371	.	.	.	.	.	0.013	.	.	100 g
VS N10/4	.	.	.	0.0022	.	0.0028	.	.	100 g
VS N3/4	.	.	.	.	.	0.0018	.	.	100 g
VS N4/3	.	.	.	0.0019	.	.	.	.	100 g
NCS HC20502	.	.	.	0.0007	.	0.0024	.	.	100 g

Ag: (0.0004) As: (0.0001) Se: (0.0002)

last of stock

NICKEL BASE CHIPS WITH Cr > 10 % CONTINUED ON THE NEXT PAGE

= class, where 1 = CRM and 2 = RM

C22-215X: typical analysis

#	Number	Cr	Mo	Al	C	Co	Cu	Fe	Mn	Nb	Ni	Si	Ti	W
1	IARM 67C	28.9	4.93	0.14	0.0058	1.75	1.24	13.48	1.01	0.36	45.8	0.14	0.005	1.97
1	VS N11/3	27.04	.	2.83	0.057	.	.	0.47	0.147	.	.	0.263	.	.
1	VS N14/3	24.35	1.32	0.164	0.012	.	0.0082	2.16	0.385	.	57.0	0.67	0.40	13.47
1	SRM 867	23.4	2.73	(0.062)	(0.021)	0.089	1.74	26.6	0.39	(0.45)	43.5	0.32	0.75	(0.006)
2	C23X 80010	22.9	0.52	0.38	0.11	0.98	0.07	.	1.05	.	30.1	0.22	0.44	.
1	IARM 258A	22.8	15.5	0.30	0.005	0.083	1.54	0.85	0.21	0.01	58.6	0.015	0.003	0.14
1	IARM 272A	21.98	9.34	1.16	0.082	12.89	0.015	1.10	0.067	0.015	52.68	0.07	0.50	0.061
1	C28X 62530	21.90	7.86	0.32	0.124	0.39	0.30	5.41	0.54	4.25	56.67	1.26	0.044	.
1	SRM 865	21.9	8.6	0.21	0.037	(0.072)	0.36	4.5	0.18	3.5	59.5	0.41	0.28	(0.007)
1	IARM 59E	21.9	2.72	0.067	0.0073	0.27	1.70	31.6	0.502	0.20	39.7	0.232	0.81	0.17
2	C22X 8010	21.88	0.20	1.03	0.12	0.52	0.22	0.66	0.50	.	.	0.22	2.81	.
1	IARM 69C	21.6	8.32	0.11	0.068	1.11	0.069	18.3	0.47	0.09	48.7	0.35	0.017	0.62
1	IARM 65D	21.5	13.1	0.29	0.0021	1.22	0.050	3.66	0.28	0.033	56.8	0.035	0.005	2.81
1	C28X 71820	21.30	0.88	0.34	0.035	0.64	0.117	17.0	0.184	4.76	52.7	0.47	1.13	.
1	IARM 69D	21.13	8.78	0.21	0.090	1.67	0.075	17.7	0.72	0.204	48.1	0.63	0.004	0.49
1	VS N16/2	21.12	0.49	0.90	0.049	.	0.011	1.11	0.224	0.367	.	0.267	2.71	.
1	C28X 62540	21.1	5.89	0.05	0.037	0.22	0.027	6.46	0.093	3.53	(61.3)	0.58	0.30	.
2	C27X 141840	21.0	10.2	0.05	0.29	10.3	0.09	0.57	0.41	.	.	0.39	0.07	.
1	IARM 274A	21.0	8.06	0.26	0.007	0.143	0.10	7.60	0.08	3.48	57.5	(0.02)	1.55	0.06
2	C22X 9030	20.96	0.06	1.66	0.05	18.04	0.01	0.33	0.20	.	.	1.00	1.85	.
2	C24X 26350	20.9	6.62	0.605	0.11	18.9	0.23	0.17	0.11	.	.	0.55	1.96	.
1	NCS HC41501	20.69	8.37	0.016	0.043	(0.011)	.	3.50	0.124	3.19	63.72	0.071	0.011	.
1	C28X 62510	20.5	9.88	0.16	0.039	0.022	0.051	3.12	0.17	2.70	(62.3)	0.47	(0.01)	.
1	NCS HC23501	20.30	.	1.09	0.042	.	0.059	.	0.345	.	.	0.37	2.89	.
1	NCS HC23504	20.30	2.06	0.635	0.059	.	.	0.442	.	.	.	0.631	0.613	.
1	SRM 866	20.1	0.36	0.29	0.082	0.075	0.49	46.1	0.92	(0.09)	30.8	0.17	0.31	(<0.002)
1	VS N5/3	20.03	.	.	0.076	.	.	0.53	0.274	.	.	0.60	0.28	.
1	VS N6/4	20.0	.	0.8	0.008	.	0.8	0.2	.	.	.	0.1	2.7	.
2	C215X HC50	19.9	15.5	.	0.67	0.13	.	10.96	0.27	.	.	1.04	.	5.5
2	C22X 7530	19.9	0.06	0.07	0.06	0.52	0.05	5.00	0.23	.	.	0.96	0.26	.
1	IARM 58B	19.6	0.01	0.45	0.073	0.02	0.011	47.7	0.51	0.01	30.7	0.282	0.50	0.01
1	IARM 62E	19.56	4.27	1.36	0.035	13.23	0.012	0.90	0.019	0.037	57.3	0.054	3.07	0.036
1	BCS 310/1	19.45	.	1.06	0.068	17.0	.	0.25	0.35	.	58.6	0.46	2.43	.
1	SRM 349a	19.3	4.25	1.23	0.035	12.46	(0.007)	1.15	0.019	(0.05)	58.1	0.018	3.06	(0.06)
1	BCS 351/1	19.14	3.04	0.554	0.0255	0.145	0.0222	17.20	0.0562	5.31	53.35	0.080	0.938	0.0209
#	Number	Cr	Mo	Al	C	Co	Cu	Fe	Mn	Nb	Ni	Si	Ti	W
2	C23X 80030	18.92	0.14	0.06	0.05	0.11	0.53	.	0.42	.	34.7	0.87	0.10	.
1	C28X 71830	18.85	1.31	1.21	0.296	0.94	0.26	(19.6)	0.36	6.25	49.0	0.52	1.21	.
1	C28X 71810	18.71	2.94	(0.007)	0.008	0.01	0.013	(19.5)	0.108	4.97	52.6	0.71	0.025	.
1	NCS HC41502	18.56	3.28	0.635	0.027	0.111	0.023	18.54	0.057	5.15	52.27	0.080	1.03	.
1	IARM 325A	18.52	9.98	1.56	0.067	10.46	(0.003)	0.07	(0.004)	(0.007)	56.1	0.012	3.16	(0.03)
2	C22X 9050	18.10	0.51	1.01	0.20	20.99	0.22	1.09	0.97	.	.	0.21	2.75	.
2	C22X 7550	18.09	0.52	0.58	0.12	0.10	0.23	1.11	0.99	.	.	0.22	0.84	.
1	C28X 71860	18.0	2.95	0.32	0.005	0.41	0.09	.	0.25	5.20	54.9	0.63	0.25	.
1	VS N13/4	17.89	4.39	2.83	0.0097	5.52	.	0.268	0.203	.	.	0.407	1.12	6.50
2	C22X 8030	17.7	0.50	1.84	0.03	1.99	0.08	1.88	0.21	.	Rem	1.09	1.81	.
1	VS N9/4	17.44	2.88	1.33	0.0102	.	0.0122	7.63	0.010	0.83	.	0.096	2.10	3.09
2	C28X 60010	16.75	.	0.02	0.06	0.98	1.08	5.98	0.14	.	.	0.85	0.60	.
1	BAM 326-1	16.37	(0.025)	.	0.092	0.223	(0.027)	.	0.406	.	61.16	1.46	.	.
2	C215X HC10	16.0	19.6	.	0.04	2.28	.	4.50	1.28	.	.	0.38	.	3.58
1	SRM 864 **	15.74	0.204	0.252	(0.063)	0.0602	0.255	9.63	0.288	(0.126)	73.09	(0.114)	(0.251)	(<0.002)
2	C22X 10550	15.52	3.96	4.74	0.30	21.7	<0.01	1.22	<0.01	.	.	0.26	0.44	.
1	VS N12/3	15.49	16.12	.	0.012	.	.	0.085	0.440	.	.	0.107	.	4.08
1	IARM 53E	15.39	0.220	0.25	0.072	0.045	0.168	9.42	0.21	0.024	73.7	0.050	0.254	0.024
1	VS N7/3	14.4	2.9	1.2	0.007	.	0.2	2.0	0.04	1.83	.	0.1	2.0	.
1	IARM 277A	14.35	4.22	4.38	0.080	14.5	0.004	0.16	0.01	0.034	58.9	0.037	3.40	0.047
1	NCS HC23505	14.28	.	1.88	0.038	.	.	.	0.28	.	37.83	0.19	2.89	5.87
1	VS N8/3	14.06	4.30	.	0.0103	.	0.011	0.61	0.010	.	.	0.421	2.18	6.05
2	C28X 60020	13.95	.	0.26	0.16	0.21	0.03	10.07	0.64	.	.	0.20	0.12	.
2	C22X 10530	13.91	6.05	5.24	0.12	17.74	0.21	0.40	0.51	.	.	0.98	1.37	.
2	C22X 90120	13.76	4.49	0.13	0.10	0.38	0.14	.	0.52	.	41.1	0.25	2.01	.
1	BCS 350	13.50	4.30	6.00	0.14	0.30	.	1.5	0.030	2.0	Rem	0.010	0.80	.
2	C211X 71320	12.9	5.50	6.59	0.16	1.04	0.13	0.39	0.27	1.64	.	0.51	1.13	.
1	BCS 387	12.46	5.83	0.24	0.030	0.21	0.032	36.0	0.08	.	41.9	0.28	2.95	.
1	BCS 387/1	11.50	6.00	0.20	0.050	0.020	0.020	38.00	0.020	.	41.0	0.050	3.00	.
2	C22X 90130	11.02	6.38	0.34	0.11	1.02	0.25	.	0.68	.	43.6	0.29	3.88	.
2	C211X 71310	10.92	3.53	5.5	0.04	0.14	0.008	0.57	0.06	2.78	.	0.11	0.45	.
1	VS N15/3	10.0	5.6	4.0	0.05	15.04	0.02	0.5	0.05	.	.	0.2	2.6	5.5
#	Number	Cr	Mo	Al	C	Co	Cu	Fe	Mn	Nb	Ni	Si	Ti	W

* Provisional Analysis

** SRM 864 also contains, in mg/kg, Pb: 2.27 Tl:0.0029

NICKEL BASE CHIPS WITH Cr > 10 % CONTINUED FROM THE PREVIOUS PAGE

Number	Ag	B	Mg	N	O	P	S	Sn	Ta	V	Zr	Units	Other
IARM 67C	.	(0.001)	0.0068	0.035	0.0016	0.011	0.0006	0.0014	(0.006)	0.031	(0.002)	100 g	
VS N11/3	.	.	.	.	.	0.0016	0.003	.	.	.	.	100 g	
VS N14/3	.	.	.	.	.	0.0020	0.0029	.	.	.	.	100 g	
SRM 867	(<0.0001)	(0.002)	.	(0.017)	(0.006)	(0.018)	(0.002)	.	(0.001)	(0.047)	.	100 g	
C23X 80010	.	.	.	.	.	.	.	.	.	.	.	50 g	
IARM 258A	.	0.001	0.009	0.032	0.0009	0.005	0.0007	<0.001	<0.01	0.014	<0.005	100 g	
IARM 272A	(0.0001)	0.003	(0.002)	0.0049	0.0007	(0.003)	0.0002	(0.0003)	(0.01)	(0.005)	(0.002)	100 g	
C28X 62530	.	0.023	.	0.35	.	0.02	0.013	.	.	.	.	50 g	
SRM 865	(0.0002)	(<0.001)	.	(0.066)	(0.004)	(0.012)	(0.001)	.	(<0.01)	(0.019)	.	150 g	
IARM 59E	(0.00004)	0.0027	(0.0001)	0.010	0.0033	0.015	0.0009	0.0031	(0.004)	0.049	(0.002)	100 g	
C22X 8010	<0.00001	(0.0001)	0.008	.	.	.	.	0.0010	.	.	<0.01	50 g	Pb: 0.0001
IARM 69C	(0.00004)	0.0034	0.0030	0.0180	0.0017	0.011	0.0005	(0.002)	.	0.033	0.004	100 g	
IARM 65D	.	(0.001)	0.007	0.019	0.0005	0.008	0.0004	(0.001)	(0.01)	0.012	(0.002)	100 g	
C28X 71820	.	(0.0010)	.	0.033	.	0.004	0.0066	.	.	.	.	50 g	
IARM 69D	0.00012	0.0044	0.0021	0.029	0.0012	0.012	0.0003	0.002	.	0.033	0.0074	100 g	Pb: 1.0 ppm
VS N16/2	.	0.0066	.	.	.	0.0028	0.0019	.	.	0.030	.	100 g	Sb: 0.00014
C28X 62540	.	0.0014	.	0.065	.	.	.	.	.	.	.	50 g	
C27X 141840	.	.	.	.	.	.	.	.	.	.	.	50 g	
IARM 274A	.	0.002	0.0019	0.007	0.0006	0.007	0.0004	0.001	(0.002)	0.019	(0.001)	100 g	
C22X 9030	.	0.023	(<0.005)	.	.	.	.	.	.	.	.	50 g	
C24X 26350	.	<0.001	.	.	.	.	0.005	.	.	.	.	50 g	
NCS HC41501	.	.	.	.	.	0.0023	0.0006	.	(0.001)	.	.	100 g	
C28X 62510	.	0.0047	.	0.211	.	(0.0014)	0.001	.	.	.	.	50 g	
NCS HC23501	.	.	.	.	.	0.011	0.006	.	.	.	.	100 g	
NCS HC23504	.	.	.	.	.	0.0182	0.0107	.	.	.	.	100 g	
SRM 866	(<0.0001)	(<0.001)	.	(0.018)	(0.004)	(0.017)	(0.001)	.	(<0.001)	(0.040)	.	100 g	
VS N5/3	.	.	.	.	.	0.0014	0.0033	.	.	.	.	100 g	
VS N6/4	.	.	.	.	.	0.002	0.003	.	.	.	.	100 g	Pb: 0.004
C215X HC50	.	.	.	.	.	0.085	0.078	.	.	0.60	.	50 g	
C22X 7530	.	.	0.05	.	.	.	.	.	.	.	.	50 g	
IARM 58B	.	(0.0003)	(0.001)	0.010	0.001	0.010	0.001	(0.002)	.	0.035	<0.005	100 g	
IARM 62E	.	0.0068	0.0018	0.0029	(0.001)	0.004	0.0003	0.0011	(0.004)	0.034	0.061	100 g	
BCS 310/1	.	.	.	.	.	.	.	.	.	.	.	100 g	
SRM 349a	.	(0.005)	.	.	.	(0.003)	0.0024	.	.	(0.12)	(0.053)	150 g	
BCS 351/1	.	0.0035	0.0016	0.0077	.	0.0045	0.00037	0.00033	0.0033	0.0181	0.0017	100 g	Sb: 0.00024
Number	Ag	B	Mg	N	O	P	S	Sn	Ta	V	Zr	Units	Other
C23X 80030	.	.	.	.	.	.	.	.	.	.	.	50 g	
C28X 71830	.	0.0016	.	0.037	.	0.003	0.0023	.	.	.	.	50 g	
C28X 71810	.	0.0010	.	0.233	.	(0.003)	0.005	.	.	.	.	50 g	
NCS HC41502	.	0.0025	.	.	.	0.0033	0.0005	.	(0.008)	.	.	100 g	
IARM 325A	(0.00001)	0.0082	0.0044	0.0016	0.0005	(0.003)	0.0003	(0.0002)	(0.003)	0.01	(0.002)	100 g	
C22X 9050	.	(<0.001)	(<0.005)	.	.	.	.	.	.	.	.	50 g	
C22X 7550	.	.	(<0.005)	.	.	.	.	.	.	.	.	50 g	
C28X 71860	.	0.004	.	0.084	.	0.018	0.015	.	.	.	.	50 g	
VS N13/4	.	0.0098	.	.	.	0.0018	0.0020	.	.	.	.	100 g	Ce: 0.0047
C22X 8030	0.018	(<0.001)	0.001	.	.	.	.	0.018	.	.	0.05	50 g	Pb: 0.023
VS N9/4	.	0.0049	.	.	.	.	.	.	.	.	.	100 g	
C28X 60010	.	.	0.003	.	.	.	.	.	.	.	.	50 g	
BAM 326-1	.	.	.	.	.	.	0.0028	.	.	.	0.129	100 g	
C215X HC10	.	.	.	.	.	0.006	0.007	.	.	0.13	.	50 g	
SRM 864 **	(<0.0001)	0.00283	0.01383	(0.01)	(0.004)	(0.011)	(0.0028)	(0.00074)	(<0.001)	0.0327	(0.00037)	100 g	
C22X 10550	.	.	0.014	.	.	.	.	.	.	.	.	50 g	
VS N12/3	.	.	.	.	.	0.0021	0.0027	.	.	.	.	100 g	
IARM 53E	.	0.0026	0.045	0.0055	0.0003	0.007	0.0011	<0.005	(0.01)	0.013	(0.001)	100 g	
VS N7/3	.	.	.	.	.	0.002	0.002	.	.	.	.	100 g	
IARM 277A	.	0.015	0.0021	0.0017	0.0005	0.002	0.0010	<0.003	(0.02)	0.011	0.010	100 g	
NCS HC23505	.	.	.	.	.	0.008	.	.	.	.	.	100 g	
VS N8/3	.	0.020	0.0015	.	.	0.0023	0.0016	.	.	0.58	.	100 g	
C28X 60020	.	.	0.05	.	.	.	.	.	.	.	.	50 g	
C22X 10530	.	.	0.0007	.	.	.	.	.	.	.	.	50 g	
C22X 90120	.	0.008	.	.	.	0.015	0.022	.	.	.	.	50 g	
BCS 350	.	.	.	.	.	.	0.003	.	.	.	.	100 g	
C211X 71320	.	0.016	.	.	.	.	.	.	.	.	0.18	50 g	
BCS 387	.	0.016	.	.	.	0.007	0.003	.	Clearance Sale Item			100 g	
BCS 387/1	.	.	.	.	.	0.005	0.005	.	.	.	.	100 g	
C22X 90130	.	0.036	.	.	.	0.036	0.034	.	.	.	.	50 g	
C211X 71310	.	<0.001	.	.	.	.	.	.	.	.	0.06	50 g	
VS N15/3	.	0.02	.	.	.	0.002	.	.	.	0.3	.	100 g	
Number	Ag	B	Mg	N	O	P	S	Sn	Ta	V	Zr	Units	Other

* Provisional Analysis

** SRM 864 also contains, in mg/kg, Pb: 2.27 Tl:0.0029

IN 100 TYPE NICKEL ALLOY CHIPS

analysis listed in mass %

Number	Al	Co	Cr	Mo	Ti	V	B	C	Cu	Fe	Si	Mn	N	Zr	Units
CRM															
BCS 345	5.58	14.70	9.93	3.01	4.74	1.00	0.019	0.153	.	.	.	.	.	0.044	100 g
BCS 346	(5.5)	(15)	(10)	(3)	(5)	(1)	.	(0.15)	.	.	.	.	.	.	100 g
RM typical analysis															
C210X117750	7.00	14.90	10.45	3.18	5.70	0.46	.	0.023	0.008	1.02	0.37	0.125	0.003	.	50 g
continued analysis listed in mg/kg															
Number	Ag	As	Bi	Ca	Cd	In	Ga	Mg	Pb	Sb	Se	Sn	Te	Tl	Zn
BCS 345	<0.2	(2)	<0.2	(<5)	<0.1	.	8	5	0.2	<2	<0.5	6	<0.2	<0.2	<0.5
BCS 346	35	50	10	(36)	0.4	(19)	(52)	147	21	47	9	91	12	.	29
C210X117750	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.

CRM TRACE ELEMENTS IN SUPERALLOY CHIPS

analysis listed in mg/kg

11520-4: 150 g units

11525-9: 100 g units

Number	Ag	As	B	Bi	Ca	Cd	Ce	Cu	Hf	Ga	Ge	In	P	Mg	Pb	Sb	Sc	Se	Sn	Te	Tl	Zn
NCS HC11529	5.4	25	13	1.8	.	.	0.19	53	12	49	27	10	80	.	11	33	0.6	2.2	43	1.3	1.1	13
NCS HC11522	5.3	15	(90)	0.4	11	1.8	(110)	.	.	108	.	30	(40)	15	11	59	.	11	72	2.1	51	105
NCS HC11521	4.6	11	(100)	0.4	21	4.6	(40)	.	.	32	.	2.6	(40)	16	4.1	95	.	16	53	11	22	32
NCS HC11528	4.4	44	24	2.0	.	.	0.28	94	33	52	75	31	131	.	8.2	49	1.2	2.5	45	2.3	3.9	15
NCS HC11520	3.5	17	(100)	4.2	42	7.3	(30)	.	.	29	.	11	(40)	82	12	204	.	43	103	3.0	8.5	24
NCS HC11527	2.5	96	25	1.2	.	.	0.44	172	3.8	38	38	2.6	55	.	4.7	16	1.2	4.1	18	7.5	4.3	14
NCS HC11526	1.0	14	47	0.19	.	.	1.8	363	7.4	34	24	7.2	36	.	3.7	3.3	2.7	12	8.3	31	0.16	13
NCS HC11525	0.78	6.7	90	0.14	.	0.31	0.37	571	3.5	31	13	0.88	41	.	3.4	1.4	1.3	9.8	3.2	28	0.13	12
NCS HC11524	0.7	72	(100)	3.4	5.3	1.6	(10)	.	.	63	.	9.2	(40)	111	91	6.2	.	53	92	83	8.1	6.0
NCS HC11523	0.3	72	(100)	0.5	32	1.9	(10)	.	.	28	.	0.4	(40)	53	2.2	7.4	.	43	1040	0.5	83	20

CRM TRACE ELEMENTS IN SUPERALLOY CHIPS

analysis listed in mg/kg

analysis listed in mass %

35 g units

Number	Bi	Pb	Se	Te	Tl	Al	B	C	Co	Cr	Hf	Nb	Ni	Ta	Ti	W	Zr
SRM 897	(0.5)	11.7	9.1	1.05	0.51	(2)	(0.01)	(0.12)	(8.5)	(12)	(1.2)	(0.9)	Rem	(1.75)	(2)	(1.75)	(0.1)
SRM 899	(0.3)	3.9	9.5	5.9	0.252	(2)	(0.01)	(0.12)	(8.5)	(12)	(1.2)	(0.9)	Rem	(1.75)	(2)	(1.75)	(0.1)

RM TIN CHIPS

analysis listed in mass %				analysis listed in mg/kg								100 g chips		
Number	C	Sn	Melting Point °C	As	Bi	Cd	Cu	Fe	In	Ni	Pb	S	Sb	Zn
BM Sn	.	99.9999	.	.	<0.5	.	<0.1	<0.1	.	<0.1	<0.3	.	.	<0.4
BCS 192h	0.001	99.998	231.9	<1	<1	<1	<1	<1	<1	<1	6	2	<5	<1

CRM TIN POWDER

analysis listed in mass %												
Number	Ag	As	Cu	Fe	Pb	S	Sb	Zn	SiO ₂	Sn	WO ₃	Units
GBW 07231	0.0025	0.574	.	21.33	2.89	0.183	0.024	0.264	.	45.80	.	100 g
GBW 07232	.	0.306	0.043	9.53	1.62	0.090	0.016	0.120	0.93	.	0.182	100 g

TIN CHIPS AND POWDER

= class, where 1 = CRM and 2 = RM BCS: 100 g powder GBW: 100 g chips SRM: 170 g powder all others: typical analysis 50 g chips

#	Number	Sb	Ag	Cd	Cu	Ni	Pb	Sn	Zn	Al	As	Au	Bi	Co	Fe	In	Te
2	C73XSC70	14.01	0.006	0.0018	6.51	0.008	0.356	.	(0.003)	0.001	0.047	.	0.009	0.0160	0.046	0.014	.
1	GBW 02302	11.81	.	.	6.72	.	1.20	80.27	.	0.020	0.020	.	0.012	.	.	.	.
2	C73XSC110	11.7	0.06	1.63	10.7	0.48	0.04	.	0.066	<0.005	0.30	.	0.53	.	0.07	.	.
1	BCS 178/2	9.45	(0.002)	0.14	4.58	0.17	3.18	82.2	0.040	.	0.15	.	0.11	.	0.024	.	.
2	C73XSC90	8.18	0.004	0.078	8.47	0.008	0.20	.	(0.003)	<0.001	0.53	.	0.066	0.0030	0.037	0.010	.
1	GBW 02301	7.87	.	.	4.06	.	1.32	86.61	.	.	0.018	.	0.014	.	.	.	.
1	SRM 54d	7.04	0.0032	.	3.62	0.0027	0.62	88.57	.	.	0.088	.	0.044	.	0.027	.	.
2	C73XSC40	6.02	0.042	0.052	3.05	0.017	0.514	.	0.008	0.005	0.005	.	0.218	0.0035	0.011	0.011	.
1	C74XHB	5.00	0.070	0.011	4.75	1.12	0.058	.	0.018	.	0.026	.	0.008	.	0.12	.	.
2	C72XSA50R	4.93	.	0.05	0.018	.	0.08	.	0.035	.	0.015	.	0.006	.	(0.004)	.	.
1	C71XSR30	0.14	0.007	0.022	0.10	0.002	0.28	.	0.015	0.003	0.077	0.003	0.10	.	0.001	0.030	0.008
1	C71XSR20	0.063	0.029	0.042	0.055	0.005	0.13	.	0.010	0.003	0.057	0.008	0.057	.	<0.001	0.051	0.023
1	C71XSR10 *	0.0156	0.0121	0.0104	0.0111	0.0041	0.0324	.	0.0146	(0.0016)	0.0102	0.0014	0.0107	.	(0.0021)	0.0120	0.0112

* C71XSR10 also contains Ga: 0.0049 and Hg: 0.0142

CRM TIN-LEAD SOLDER CHIPS AND POWDER

CRM	TIN-LEAD SOLDER CHIPS AND POWDER								BAM, BCS: powder		all others: typical analysis chips				
Number	Sn	Pb	Ag	As	Au	Bi	Cd	Cu	Fe	In	Ni	Sb	Te	Zn	Units
C91XS63 PR40	66.8	Rem	0.030	<0.002	0.05	0.030	0.021	0.021	<0.005	0.014	<0.005	0.093	0.006	<0.001	100 g
BAM BNM 010	63.40	36.47	(0.014)	(0.012)	(<0.001)	0.0245	0.0016	0.0417	(0.0020)	(<0.001)	0.0021	0.0488	.	(<0.0001)	100 g
C91XS63 PR10	63.0	Rem	0.01	0.007	0.046	0.06	0.006	0.009	0.003	.	0.001	0.28	.	<0.001	100 g
BCS 347	62.6	Rem	0.099	(0.02)	0.037	0.080	0.004	0.169	(0.002)	.	0.0072	0.191	.	0.0015	100 g
C91XS63 PR20	62.6	Rem	0.057	0.080	0.090	0.162	0.0168	0.052	0.030	0.019	0.0073	0.614	0.009	0.007	100 g
C91X S63 PR00 *	60.0	Rem	0.01	0.01	0.015	0.007	0.010	0.02	0.002	0.005	0.002	0.02	0.003	<0.001	100 g
C91XS30 PR30	30.88	Rem	0.024	0.0126	0.0063	0.294	0.0115	0.102	0.0016	0.0085	0.0269	0.269	.	(0.003)	100 g

* Provisional Analysis

RM TITANIUM POWDER

typical analysis

powder 50 g

Number	Ti	Al	Co	Cr	Cu	Fe	Mn	Mo	Ni	P	Pb	Si	W	Zn	Zr
DH SL2701	98.52	0.018	0.00123	0.046	0.001	0.174	0.009	.	0.029	.	.	0.021	0.011	0.00027	0.00010
DH SL2703	98.42	0.024	0.00190	0.059	0.002	0.238	0.017	0.016	0.031	<0.006	0.00030	.	0.015	0.00067	0.00020
DH SL2702	97.60	0.036	0.00380	0.066	0.002	0.363	0.035	0.018	0.036	0.005	.	0.042	0.029	0.00100	0.00020

CRM TITANIUM

Number	Al	B	C	Co	Cr	Cu	Fe	H	Mn	Mo	N	Nb	Ni
IARM 311A	0.32	.	0.009	.	0.013	0.0013	0.060	0.0021	0.0013	0.0012	0.012	(0.002)	0.014
BCR 090	(0.074)	0.00282	.	0.0501	0.0533	0.0513	0.0563	.	0.0314	0.0488	.	(0.0492)	0.0667
IARM 312A	0.006	.	0.004	(0.001)	(0.002)	(0.002)	0.028	0.0049	(0.001)	(0.002)	0.0023	.	(0.002)
IARM 174C	(0.003)	.	0.0057	(0.001)	0.009	0.0015	0.28	0.0027	0.0019	0.002	0.004	(0.004)	0.007

BCR produced by HIP; 090A: 40 mm Ø x 20 mm; 090B: 25 g of 0.2 g cubes IARM: 65 g

Number	O	Pd	S	Si	Sn	V	W	Y	Zr
IARM 311A	0.083	.	.	0.005	0.0020	0.004	(0.002)	(0.0002)	0.012
BCR 090	.	.	.	.	(0.071)	(0.057)	(0.050)	.	(0.0436)
IARM 312A	0.066	(0.004)	(0.001)	0.006	0.0012	(0.002)	.	(0.0004)	(0.001)
IARM 174C	0.34	.	(0.0005)	(0.006)	0.023	(0.002)	.	(0.0004)	(0.003) last of stock

TITANIUM ALLOY CHIPS

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	Al	C	Cr	Cu	Fe	Mn	Mo	Nb	Ni	Si	Sn	V	Zr
1	SRM 2433	7.63	.	.	.	0.063	.	0.99	.	.	.	0.98	.	.
1	BCS 356	6.25	(0.0085)	0.0112	0.0055	0.124	.	0.0020	.	0.0070	(0.0200)	.	4.05	.
1	SRM 173c	6.245	0.027	0.0165	0.0040	0.2130	(0.002)	0.0068	.	0.0203	(0.019)	(0.010)	4.154	0.0053
2	C101 P6850	6.11	.	.	.	0.02	.	0.48	.	.	0.21	.	5.05	.
1	IARM 336B	6.04	0.006	(0.001)	(0.002)	0.132	.	6.16	.	(0.002)	0.020	2.04	(0.004)	4.12
1	IARM 300A *	5.97	0.006	0.009	(0.003)	0.19	(0.001)	(0.001)	6.9	0.008	0.019	(0.01)	(0.01)	.
1	IARM 336A	5.9	0.005	(0.002)	(0.002)	0.115	.	6.16	.	(0.002)	0.019	2.03	0.005	3.92
1	SRM 647	5.88	0.006	(0.01)	(0.002)	0.075	(0.01)	1.96	(0.01)	(0.004)	(0.04-0.07)	2.02	(0.02)	3.90
1	SRM 2431	5.73	0.006	(0.01)	(0.01)	0.056	(0.01)	6.01	.	(0.01)	0.088	1.98	(0.01)	4.06
1	IARM 337A	5.60	0.008	2.01	(0.002)	0.114	.	2.05	(0.004)	0.011	0.14	1.96	(0.003)	1.89
1	IARM 314B	5.57	0.010	3.08	0.002	0.39	(0.001)	4.88	0.009	0.0044	0.041	0.022	5.04	(0.002)
1	BCS 357	5.46	(0.0072)	0.0521	0.0537	0.202	.	0.053	.	0.0511	(0.0500)	.	3.53	.
1	SRM 648	5.13	0.011	3.84	(0.01)	0.15	(0.01)	3.75	.	(0.005)	0.027	1.98	(0.02)	1.84
1	IARM 345A *	5.12	0.010	3.89	0.003	0.120	0.0009	4.09	0.002	0.016	0.015	1.99	0.004	1.91
1	IARM 280A	4.11	0.005	0.0055	0.003	0.044	(0.002)	4.01	(0.001)	0.012	0.47	2.07	0.023	(0.002)
1	IARM 344A *	3.16	0.011	3.08	(0.002)	0.20	(0.002)	(0.003)	.	0.011	0.027	3.09	15.0	(0.002)
1	SRM 2432	3.15	0.008	(0.01)	(0.005)	1.77	(0.01)	.	(0.01)	0.029	.	10.00	(0.01)	.
1	SRM 649	3.08	0.011	2.96	(0.001)	0.133	(0.01)	.	(0.01)	(0.01)	.	3.04	15.1	.
1	IARM 261A	3.00	0.007	0.013	.	0.19	0.0011	(0.003)	.	0.006	0.012	0.008	2.48	(0.002)
2	C101 P6790	2.35	.	.	.	0.02	.	1.0	.	.	0.2	10.88	.	4.88
1	SRM 650	<0.01	(0.01)	0.002	0.033	0.024	0.016	0.002	.	0.003	0.004	0.03	0.009	(0.01)

Number	H	N	O	Pd	S	Units	Other
SRM 2433	.	.	.	.	.	50 g	
BCS 356	.	0.0103	.	.	.	50 g	
SRM 173c	(0.006)	(0.028)	0.164	.	.	50 g	Ti: (89.15)
C101 P6850	.	.	.	.	.	50 g	last of stock
IARM 336B	0.0029	0.0016	0.101	.	(0.002)	65 g	
IARM 300A *	0.0019	0.004	0.16	.	.	65 g	
IARM 336A	0.0022	0.0015	0.102	.	(0.002)	65 g	
SRM 647	.	(0.01)	(0.1)	.	.	50 g	
SRM 2431	.	.	.	.	.	50 g	
IARM 337A	0.005	0.0017	0.104	.	(0.001)	65 g	Co: 0.0011
IARM 314B	0.0057	0.0045	0.130	(0.003)	(0.001)	65 g	
BCS 357	.	0.0148	.	.	.	50 g	
SRM 648	.	(0.01)	.	.	.	50 g	
IARM 345A *	0.0040	0.0025	0.12	(0.001)	(0.001)	65 g	
IARM 280A	0.0015	0.0014	0.19	(0.002)	(0.001)	65 g	
IARM 344A *	0.016	0.006	0.11	.	.	65 g	
SRM 2432	.	.	.	.	.	50 g	
SRM 649	.	(0.01)	.	.	.	50 g	Mg: (0.004)
IARM 261A	0.0023	0.007	0.10	.	(0.001)	65 g	last of stock
C101 P6790	.	.	.	.	.	50 g	last of stock
SRM 650	.	(0.01)	.	.	.	30 g	W: 1.55

CRM TUNGSTEN POWDER

analysis listed in mg/kg except % which is mass %

Number	Al	Bi%	Ca	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Si	Sn	W _{0.3} %	Units
BAM S002 VS 1710-79	29.4 .	. 0.146	46 .	45 .	47.0 .	28.4 .	53 .	40.0 .	38.8 .	16.7 .	59 .	41 .	29 .	(7.2) .	106 .	42 .	. 71.96	100 g 100 g

CRM TUNGSTEN ALLOY CHIPS

analysis listed in mass %

Number	Co	Fe	Mn	Ni	Units
NCS HC55905	0.502	3.22	0.060	6.01	50 g
NCS HC55904	0.400	2.43	0.050	4.50	50 g
NCS HC55903	0.302	1.63	0.040	3.00	50 g
NCS HC55902	0.102	0.813	0.030	1.51	50 g

CRM ZINC PELLETS

Number	Cd	Cu	Fe	Pb	Units
GBW 02701	0.0010	0.00010	0.0010	0.0030	50 grams of 3 mm Ø pellets

last of stock

CRM ZINC PELLETS

analysis listed in mg/kg

450g of 3mm Ø pellets

Number	Ag	Al	As	Au	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	In	Ir	K	Mg	Mn
SRM 728	1.08	(0.07)	(<0.005)	(<0.02)	(<0.005)	(0.02)	1.14	(1.0)	(<0.03)	5.68	1.84	(<0.05)	(0.05)	(<0.005)	(<0.005)	(<0.01)	(<0.001)	(0.07)
continued																		
Number	Mo	Na	Nb	Ni	Pb	Pd	Pt	Rh	Ru	Sb	Sc	Si	Sn	Ti	Tl	V	W	Zr
SRM 728	(<0.01)	(0.01)	(<0.01)	(0.45)	11.13	(<0.05)	(<0.01)	(<0.05)	(<0.01)	(0.5)	(<0.001)	(<0.01)	(0.02)	(0.04)	(0.2)	(<0.001)	(0.4)	(<0.01)

CRM ZINC

analysis listed in mass %

Number	Ag	Ca	Cd	Cu	Fe	Hg	Mg	Pb	S	Sn	Zn	Units
SRM 113b IMN 1	0.04607 .	0.8196 .	0.7804 0.00066	0.2953 0.00080	2.077 0.0012	(0.000055) .	0.4460 .	2.731 0.011	30.032 .	. 0.00021	56.49 .	100 g powder 100 g chips

last of stock

RM ZINC

Number	Zn	Al	As	Cd	Cu	Fe	Mg	Pb	Sn	Ti	Units
BM PZn BM Zn ##	[99.995] 99.99	<0.001 <0.0003	. <0.0005	<0.003 <0.004	<0.001 <0.003	<0.002 <0.004	. <0.001	<0.003 <0.003	<0.001 <0.001	. <0.001	100 g chips 100 g chips

SUSPENDED FOR RETESTING 03/16

ZINC SPELTER CHIPS

BS: 50 g units SRM: 100 g units

Number	Al	Cu	Fe	Pb	Sb	Sn
RM BS SP-D	0.25	<0.0005	0.060	0.038	0.006	<0.001
CRM SRM 2139	0.2049	.	.	0.0302	.	.
RM BS SP-B	0.141	<0.002	0.025	0.021	0.061	<0.001
RM BS SP-C	0.185	<0.0005	0.041	0.005	0.031	<0.001
RM BS SP-A	0.051	<0.0005	0.011	0.003	0.099	<0.001

ZINC ALLOY CHIPS, chart 1 of 2

= class, where 1 = CRM and 2 = RM

C41X-43X: typical analysis

FNE: 100 g

NCS, SRM: 150 g

all others: 50 g units

#	Number	Al	Cu	Cd	Fe	Mg	Mn	Ni	Pb	Sb	Sn	Bi	Cr	Si	Ti
2	C43XZ230	29.8	2.73	0.002	0.008	0.01	0.002	0.003	0.002	.	0.003	.	.	.	.
1	CAN NZA-1	28.70	1.51	0.00098	0.046	0.020	.	.	0.0030	.	0.0069	.	.	.	.
1	CAN NZA-4	26.65	2.45	0.0029	0.027	0.0106	.	.	0.0101	.	0.0087	.	.	.	.
1	CAN NZA-3	25.99	2.00	0.0064	0.066	0.049	.	.	0.0045	.	0.0034	.	.	.	.
2	C43XZ210	24.9	2.05	0.01	0.05	0.06	0.009	0.002	0.007	.	0.01	.	.	.	.
1	CAN NZA-2	23.81	3.00	0.0047	0.021	0.029	.	.	0.0076	.	0.0045	.	.	.	.
1	CAN NZA-7	13.17	0.212	0.00020	(0.016)	0.052	.	.	0.0136	.	0.0116	.	.	.	.
2	C43XZ110	11.2	0.47	0.014	0.008	0.05	0.01	0.006	0.015	.	0.02	.	.	.	.
1	CAN NZA-5	10.85	1.04	0.0095	(0.016)	0.021	.	.	0.0012	.	0.0017	.	.	.	.
1	C43XZ120	10.05	0.796	0.0114	0.047	0.027	0.0059	0.004	0.0133	0.0039	0.0089	(0.002)	0.0023	(0.008)	0.0054
1	C43XZ130	9.58	0.977	0.0102	0.06	0.020	0.007	0.011	0.012	0.009	0.011	.	.	.	.
1	C43XZ140	8.24	1.23	0.0067	0.015	0.0026	0.0033	0.0052	0.0082	0.011	0.0053	0.010	0.0046	0.010	0.0012
1	CAN NZA-6	7.54	3.17	0.0147	(0.105)	0.00037	.	.	0.0109	.	0.0051	.	.	.	.
1	C43X Z150	7.36	1.53	0.0030	0.009	0.0024	0.0020	0.0019	0.0054	0.005	0.004	0.005	0.0025	(0.011)	0.0020
1	C42XZ80	7.03	0.0215	0.0003	0.013	0.0033	0.0014	0.0019	0.0025	.	(0.0023)	.	(0.0002)	0.013	.
1	NCSHC28974-Zn	4.85	.	.	.	0.083	.	.	.	.	.	.	.	.	.
1	C43XZ40	4.76	3.21	0.0025	(0.064)	0.0434	0.088	0.0286	(0.002)	0.0043	(0.0024)	0.012	0.0063	(0.0065)	0.0017
1	C42XZ70	4.39	0.0249	0.030	0.027	0.0095	0.0045	0.0067	0.0097	.	0.012	.	(0.001)	0.006	.
2	C42XZ10	4.3	0.003	<0.001	0.002	<0.001	<0.001	0.001	0.002	.	0.002	.	.	.	.
1	C42XZ50	4.22	0.098	0.0021	0.029	0.073	0.0068	0.0185	0.0048	(0.00055)	0.0022	0.006	0.0018	.	.
1	SRM 94c	4.07	1.01	0.002	0.018	0.042	0.014	0.006	0.006	.	0.006	.	.	.	.
1	C43XZ60	4.02	2.72	0.0016	0.019	0.0256	0.0006	0.029	0.0016	0.0045	0.0053	0.049	0.0006	0.012	0.0013
1	C42XZ30	3.72	0.159	0.0048	(0.047)	0.0288	0.0252	0.0102	0.0060	0.003	0.0030	.	0.0020	0.015	.
1	C43XZ30	3.64	1.59	0.0132	0.061	0.0143	0.0125	0.0061	0.0132	0.003	0.0125	0.018	0.004	0.005	.
1	C42XZ40	3.55	0.063	0.008	0.01	0.057	0.008	0.017	0.011	0.002	0.006	.	.	.	.
1	C43XZ50	3.05	6.05	0.0111	0.023	0.041	0.0030	0.0021	0.0045	.	0.0032	.	0.0010	0.003	0.0009
2	C43XZ20	3.2	0.89	0.01	0.02	0.042	0.008	0.003	0.008	0.008	0.01	.	.	.	.
2	C41X0336Z40	1.39	0.874	0.638	(0.018)	0.179	0.038	0.0074	2.87	0.048	2.38	0.027	.	.	.

#	Number	Ag	As	Ce	In	La	Tl
2	C43XZ230	.	.	.	.	.	.
1	CAN NZA-1	.	.	.	.	.	.
1	CAN NZA-4	.	.	.	.	.	.
1	CAN NZA-3	.	.	.	.	.	.
2	C43XZ210	.	.	.	.	.	.
1	CAN NZA-2	.	.	.	.	.	.
1	CAN NZA-7	.	.	.	.	.	.
2	C43XZ110	.	.	.	.	.	.
1	CAN NZA-5	.	.	.	.	.	.
1	C43XZ120	.	.	.	.	.	.
1	C43XZ130	.	.	.	.	.	.
1	C43XZ140	.	.	.	.	.	.
1	CAN NZA-6	.	.	.	.	.	.
1	C43X Z150	.	.	.	.	.	.
1	C42XZ80	.	.	0.0081	.	0.0079	.
1	NCSHC28974-Zn	.	.	.	.	.	.
1	C43XZ40	.	.	.	.	.	.
1	C42XZ70	.	.	0.053	.	0.047	.
2	C42XZ10	.	.	.	.	.	.
1	C42XZ50	.	.	0.011	0.0048	0.009	0.006
1	SRM 94c	.	.	.	.	.	.
1	C43XZ60	.	.	.	.	.	.
1	C42XZ30	.	.	(0.0003)	.	(0.0003)	.
1	C43XZ30	.	.	.	(0.0019)	.	(0.0035)
1	C42XZ40	.	.	0.020	0.001	0.019	0.003
1	C43XZ50	.	.	.	.	.	.
2	C43XZ20	.	.	.	.	.	.
2	C41X0336Z40	0.0023	0.0005	.	.	.	.

= class, where 1 = CRM and 2 = RM

typical analysis

50 a units

#	Number	Al	Cu	Cd	Fe	Mg	Mn	Ni	Pb	Sb	Sn	Bi	Cr
1	C41XGLV40	0.514	0.0321	0.0006	0.0028	0.0034	0.0089	0.0441	0.0062	0.0287	0.0024	0.0061	0.0007
1	C41XGLV60	0.474	0.0394	0.0053	0.0047	.	0.0013	0.0008	0.120	0.0112	0.0152	0.0249	0.0029
1	C41X0336Z30	0.43	0.361	0.341	0.270	0.134	0.0058	.	0.019	.	0.111	.	.
1	C41XGLV70	0.399	0.023	0.00056	0.0031	.	0.0025	0.0060	0.082	0.0031	(0.006)	0.0108	0.0010
1	C41XGLV30	0.334	0.0260	0.0188	0.0031	0.00145	0.0111	0.0300	0.0091	0.058	0.0060	0.0016	0.00084
2	C41X4380Z80	0.225	0.020	0.0079	0.003	0.007	0.0015	0.024	0.73	0.016	0.011	0.011	0.0019
1	C41X4380Z40	0.144	0.0022	0.094	0.056	0.126	0.0007	0.0040	0.325	0.017	0.038	0.011	(0.0003)
1	C41X4380Z70	0.137	0.012	0.015	(0.0044)	0.0028	.	0.012	1.25	0.090	0.0047	.	0.0045
1	C41XZ50	0.13	0.023	0.024	(0.02)	0.012	0.004	0.0116	0.0235	0.006	0.0213	.	.
2	C41XGLV10	0.115	0.0028	0.0093	0.059	.	.	0.0141	0.056	<0.001	0.010	0.0025	.
1	C41X0336Z60	0.105	0.0203	0.014	0.08	0.0008	0.0010	0.0018	1.82	0.234	0.0023	0.123	.
1	C41X2951Z30	0.078	1.89	0.0062	0.029	0.0164	0.0018	0.0010	0.0065	.	(0.006)	.	0.184
2	C41XGLV20	0.070	0.0053	0.0026	0.048	.	.	0.0071	0.214	0.007	0.003	0.017	.
1	C41X4380Z10	0.055	0.175	0.376	0.01	0.0012	0.0015	0.0029	0.068	0.002	0.049	0.0017	0.002
1	C41X0336Z50	0.035	0.023	0.058	0.016	<0.0005	(0.0001)	(0.0005)	0.91	0.008	0.21	(0.001)	.
1	C41X2951Z10	0.029	0.79	0.0005	0.011	0.0029	0.0013	0.0038	0.0042	.	(0.0007)	.	0.083
1	C41X0336Z10	0.014	0.007	0.0056	0.0124	0.0049	0.0035	(0.0006)	0.95	.	0.005	.	.
2	C41XGLV50	0.014	0.0116	0.014	0.077	.	.	0.0029	0.019	0.163	0.020	0.0105	.
1	C41XZ40	0.0096	0.0047	0.0066	0.003	0.0019	0.0012	0.0069	0.0092	0.005	0.0070	.	.
1	C41XZ30	0.0083	0.0019	0.0044	0.002	0.0009	0.0007	0.0031	0.0052	0.0037	0.0039	.	.
1	C41X Z20	0.00082	0.00168	0.00179	0.0077	0.00014	0.00053	0.00131	0.00264	0.00057	0.00159	0.00052	.

#	Number	Ag	As	Co	In	Si	Ti	Tl
1	C41XGLV40	.	(0.0003)	0.0037	.	.	.	.
1	C41XGLV60	.	0.0014	0.0047	.	.	.	.
1	C41X0336Z30	.	.	.	.	.	.	.
1	C41XGLV70	.	0.0016	(0.0001)	.	.	.	.
1	C41XGLV30	.	(0.0007)	0.00150	.	.	.	.
2	C41X4380Z80	.	.	.	.	(0.005)	0.012	.
1	C41X4380Z40	.	.	.	.	(0.002)	0.005	.
1	C41X4380Z70	.	.	.	.	.	0.009	.
1	C41XZ50	.	.	.	0.004	.	.	0.003
2	C41XGLV10	<0.001	.	.	.	.	.	.
1	C41X0336Z60	0.0055	0.0020	.	0.0123	.	0.0132	.
1	C41X2951Z30	.	.	.	.	.	.	0.133
2	C41XGLV20	.	<0.001	.	.	.	.	.
1	C41X4380Z10	.	.	.	.	0.006	.	.
1	C41X0336Z50	.	.	.	.	.	.	.
1	C41X2951Z10	.	.	.	.	.	.	0.278
1	C41X0336Z10	.	.	.	.	.	.	.
2	C41XGLV50	.	0.004	.	.	.	.	.
1	C41XZ40	.	.	.	0.0015	.	<0.005	0.003
1	C41XZ30	.	.	.	0.0007	.	0.0012	0.002
1	C41X Z20	.	.	.	0.00057	.	.	0.00117

certified values listed in mass %

Number	B	Cr	Cu	Fe	Hf	Ni	Sn
SRM 360b	0.191	0.1043	0.00125	0.2138	0.00785	0.00225	1.555
BCR 098	.	0.0906	.	0.2143	.	.	1.4600

informational values listed in mg/kg

[illegible]