

INDEX

ALLOYED CAST IRON [69](#), [70](#)
ALLOY LISTING [73](#)
ALLOY SPECIFICATIONS [75](#)
ALUMINUM IN STEEL [18](#), [24](#)
ANTIMONY IN STEEL [21](#), [22](#)
ARSENIC IN STEEL [21](#), [22](#)

BISMUTH STEEL [23](#), [28](#)
BORON IN STEEL [18](#)

CALCIUM IN STEEL [23](#), [24](#)
CARBON STEEL [2](#), [3](#), [18](#), [19](#), [20](#)
CARBON STEEL SPECIFICATIONS [75](#)
CAST IRON [60](#), [61](#), [62](#), [63](#), [65](#), [66](#), [67](#), [68](#), [69](#), [70](#), [71](#), [72](#)
CAST IRON WITH MAGNESIUM [62](#), [63](#), [64](#)
COBALT IN STAINLESS STEEL [47](#)
Cr-Mo STEEL [24](#), [25](#), [26](#), [27](#)

DUCTILE IRON [61](#)

EPMA SETS [24](#)

GRAY IRON [60](#)

HIGH ALLOY STEEL [17](#), [52](#), [53](#), [54](#), [55](#), [56](#), [57](#), [58](#), [59](#)
HIGH ALLOY STEEL SPECIFICATIONS [78](#)
HIGH CHROMIUM CAST IRON [69](#), [70](#)

IRON [18](#)

LEADED STEEL [4](#), [28](#)
LOW ALLOY STEEL [5](#), [6](#), [7](#), [21](#), [22](#), [23](#), [24](#), [25](#), [26](#), [27](#), [28](#), [29](#), [30](#),
[31](#), [32](#), [33](#), [34](#), [35](#), [36](#), [37](#), [38](#), [39](#), [40](#), [41](#), [42](#)
LOW ALLOY STEEL SPECIFICATIONS [76](#)
LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS [41](#)

MANGANESE STAINLESS STEEL [10](#), [48](#)
MANGANESE STEEL [28](#), [29](#)
MARAGING STEEL [11](#), [47](#)

NICKEL BINARY [49](#)
NITROGEN IN STEEL [24](#)
NODULAR IRON [61](#)

PHOSPHORUS IN STAINLESS STEEL [49](#)

RESULFURIZED STAINLESS STEEL [10](#), [49](#)
RESULFURIZED STEEL [4](#), [30](#), [31](#)
RESULFURIZED STEEL SPECIFICATIONS [75](#)

SET [18](#), [24](#), [28](#), [30](#), [42](#), [59](#), [60](#)
SILICON STEEL [4](#), [33](#)
Si-Mo CAST IRON [60](#)
SOLUBLE ALUMINUM [18](#)
SOLUBLE BORON [18](#)
STAINLESS STEEL [10](#), [11](#), [12](#), [13](#), [14](#), [15](#), [16](#), [47](#), [48](#), [49](#), [50](#), [51](#),
[52](#), [53](#), [54](#), [55](#), [56](#), [57](#), [58](#), [59](#)
STAINLESS STEEL SPECIFICATIONS [78](#)
STAINLESS STEEL WITH LOW NICKEL [50](#), [51](#)
SULFUR IN STAINLESS STEEL [49](#)

TOOL STEEL [8](#), [9](#), [42](#), [43](#), [44](#), [45](#), [46](#), [77](#)

WHITE IRON [64](#)

XRF [18](#), [24](#), [28](#), [30](#), [42](#), [59](#)

LOW ALLOY STEEL ALLOYS, CHART 1 of 3

1 = CRM, 2 = RM, 3 = RM with no uncertainties

Table with 18 columns: Alloy, ISO, #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W. Rows include alloys like 16MnCr5, 20MnCr4, 35MV7, etc.

Table with 18 columns: Alloy, ISO, #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W.

Table with 18 columns: Alloy, ISO, #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W.

Table with 18 columns: Alloy, ISO, #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W. Rows include detailed alloy specifications and units.

Table with 18 columns: Alloy, ISO, #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W.

LOW ALLOY STEEL ALLOYS, CHART 2 of 3

1 = CRM, 2 = RM, 3 = RM with no uncertainties

Alloy	ISO	#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Ti	V	W
5140H		1	IARM Fe5140H-18	0.37	0.93	0.014	0.022	0.187	0.253	0.266	0.67	0.13	0.0081	0.031	0.007	0.0015	(0.0024)	(0.003)
5160		1	IMZ 116	0.64	0.94	0.025	0.035	0.25	0.33	0.022	0.72	0.025	.	0.074	0.0130	(0.0008)	0.076	.
6150		2	BS 4941	0.490	0.79	0.012	0.017	0.27	0.106	0.074	0.96	0.024	0.008	0.039	0.0076	.	0.164	.
8620		1	12X 86200-21	0.211	0.811	0.0128	0.0224	0.237	0.199	0.551	0.507	0.0241	0.0072	0.190	0.0082	.	0.0039	(0.003)
8620	LAST	2	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.021	0.012	0.168	0.0079	.	0.002	.
8620	17034	1	BS 8620G	0.215	0.799	0.0094	0.020	0.264	0.191	0.58	0.568	0.027	0.0077	0.205	0.0080	0.0011	0.0018	(0.0022)
8620		1	IARM Fe8620-18	0.211	0.857	0.012	0.026	0.23	0.197	0.446	0.536	0.0246	0.0085	0.197	0.007	0.0015	0.0061	(0.004)
8620		1	IPT 502	0.210	0.823	0.018	0.026	0.198	0.121	0.408	0.485	0.024	0.0083	0.155	0.0069	0.0016	.	.
8620 + Bi	LAST	2	BS 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.016	0.010	0.16	0.0107	(0.002)	0.004	.
8630	17034	1	BS 8630	0.315	0.752	0.0032	0.0043	0.261	0.046	0.544	0.477	0.023	0.0029	0.194	0.0038	0.0008	0.0006	(0.001)
8740	17034	1	BS 8740	0.39	0.86	0.011	0.023	0.25	0.16	0.55	0.49	0.037	0.0086	0.27	0.0073	0.0012	0.0024	0.0023
8740		1	IARM 252C	0.416	0.92	0.025	0.008	0.248	0.109	0.505	0.501	0.017	0.008	0.205	0.0083	0.001	0.005	<0.005
8740		1	IARM 252D	0.423	0.842	0.0075	0.0128	0.256	0.270	0.424	0.468	0.024	0.0078	0.204	0.0068	0.0012	0.0022	(0.004)
8740		1	IARM 252E	0.413	0.87	(0.009)	(0.012)	0.257	0.164	0.407	0.486	0.028	0.0093	0.204	0.0064	0.0010	(0.0028)	.
8740		1	IARM 252F	0.406	0.88	0.011	0.009	0.247	0.182	0.412	0.463	0.026	0.0086	0.210	0.0059	0.0010	(0.003)	(0.003)
8822	17034	1	BS 8822A	0.212	0.852	0.020	0.031	0.287	0.030	0.569	0.562	(0.010)	0.0042	0.378	0.0086	0.0015	0.0028	<0.005
9310	LAST	2	BS 58C	0.098	0.57	0.011	0.014	0.29	0.14	3.20	1.29	(0.055)	.	0.11
9310	LAST	2	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.042	0.009	0.14	0.0147	.	0.005	.
9310	* Provisional	1	BS 9310 *	0.090	0.64	0.009	0.005	0.22	0.14	3.04	1.16	0.028	0.014	0.095	<0.5	0.001	0.004	0.004
9310		1	IARM FeE9310-18	0.121	0.62	0.009	0.0128	0.256	0.158	3.07	1.09	0.036	0.009	0.086	0.0070	.	0.0030	.
9325	LAST	2	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.030	0.010	0.31	0.0089	.	0.004	.

Number	As	B	Bi	Ca	Fe	Mg	Nb	O	Pb	Sb	Sn	Ta	Zn	Zr	Units
IARM Fe5140H-18 (0.011)	(0.0015)	.	.	.	0.0069	.	.	.	Disc 31 mm Ø x 2 or 18 mm
IMZ 116	Als: 0.012	Disc 40 mm Ø x 40 mm
BS 4941 (0.004)	.	.	.	(0.0002)	.	.	.	0.0017	.	.	0.006	.	.	.	Disc 41 mm Ø x ~7 or 19+ mm
12X 86200-21	0.0045	0.0014	.	.	0.0024	0.0094	.	.	(0.0014)	Disc 38 mm Ø x 19 mm
BS 1931	0.007	.	.	(0.0008)	.	.	.	(0.0052)	.	.	0.007	.	.	.	Disc 41 mm Ø x ~7 mm
BS 8620G	0.0049	0.0002	.	0.0015	97.1	(0.0004)	0.0020	0.0032	<0.005	0.0020	0.0095	<0.0005	<0.005	(0.0007)	Disc 38 mm Ø x ~7-or 19+ mm
IARM Fe8620-18	0.009	(0.0014)	.	.	.	0.0090	.	.	.	Disc 31 mm Ø x 2 or 18 mm
IPT 502	Disc 36 mm Ø x 20 mm
BS 8620A	0.007	.	0.073	0.0003	.	.	(0.004)	(0.001)	.	.	0.009	.	.	.	Disc 38 mm Ø x ~7 mm
BS 8630	0.0038	(0.0002)	.	(0.0007)	97.3	(0.0007)	(0.0006)	0.0008	(0.0007)	0.0012	0.0029	.	.	(0.001)	Disc 44 mm Ø x 19+ mm
BS 8740	0.0051	0.0003	.	(0.0003)	96.91	(0.0002)	(0.0007)	(0.001)	(0.0003)	0.0017	0.008	(0.003)	.	(0.001)	Disc 38 mm Ø x ~7 or 19+ mm
IARM 252C	0.004	(0.0001)	.	(0.0003)	.	.	0.002	(0.002)	0.001	<0.005	0.007	.	.	<0.002	Disc 31 mm Ø x 2 mm
IARM 252D	0.0053	(0.0002)	(0.0005)	(0.001)	.	(0.0002)	0.0013	(0.0013)	(0.0004)	0.0024	0.012	.	(0.0005)	(0.0013)	Disc 31 mm Ø x 2 mm
IARM 252E	0.0046	0.0075	.	.	.	Disc 31 mm Ø x 2 or 18 mm
IARM 252F	(0.006)	0.0016	.	.	.	0.006	.	.	.	Disc 31 mm Ø x 2 or 18 mm
BS 8822A	0.0027	0.0004	.	(0.0002)	96.9	.	0.0024	0.0068	0.0005	(0.0016)	(0.003)	0.007	<0.01	(0.002)	Disc 37 mm Ø x 25 mm
BS 58C	(0.012)	.	.	.	Disc 39 mm Ø x ~17 mm
BS 58D	0.012	.	.	.	Disc 41 mm Ø x ~7 mm
BS 9310 *	0.005	0.0001	.	0.0001	94.5	.	0.002	<0.005	0.0003	0.002	0.008	.	.	0.001	Disc 41 mm Ø x ~7 or 19
IARM FeE9310-18	94.6	.	.	(0.0017)	.	.	0.0072	.	.	.	Disc 31 mm Ø x 2 or 18 mm
BS 9325	0.004	.	.	0.0049	.	.	.	0.0010	.	.	0.009	.	.	.	Disc 38 mm Ø x ~7 mm

Number	As	B	Bi	Ca	Fe	Mg	Nb	O	Pb	Sb	Sn	Ta	Zn	Zr	Unit
--------	----	---	----	----	----	----	----	---	----	----	----	----	----	----	------

MARAGING STEEL ALLOYS

1 = CRM, 2 = RM, 3 = RM with no uncertainties

Alloy	ISO	#	Number	Co	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Ti	V	W
A-538C	25, LAST	1	BS 161A	9.22	0.004	0.031	0.004	0.0007	0.032	0.22	18.40	0.12	0.14	4.82	(0.002)	0.65	0.031	(0.008)
C-350		1	IARM 309A	12.3	0.0059	0.018	0.004	0.0006	0.020	0.023	18.4	0.053	0.11	4.71	0.0010	1.47	0.01	0.01
250	17034	1	BS M250	7.9	0.0021	0.024	0.0031	(0.0005)	(0.003)	(0.003)	18.7	(0.004)	0.098	4.93	<0.005	0.422	<0.05	(0.007)
250		2	CT 250	7.54	0.002	0.006	0.003	0.002	0.008	0.008	18.44	0.008	0.058	4.88	.	0.41	.	.
250		1	ECRM 285-2D	7.76	0.0018	0.0168	0.0053	0.0025	0.0117	0.0094	18.07	0.0236	0.1067	4.99	0.0007	0.520	.	.
250		1	IARM 308A	7.80	0.003	0.019	0.004	0.0005	0.014	0.018	18.53	0.023	0.097	4.78	0.0013	0.46	0.01	0.01
250		1	IARM FeC250-21	7.92	0.0028	0.022	0.0033	0.0006	0.0091	(0.0041)	18.6	(0.0093)	0.101	4.93	0.0004	0.418	(0.0074)	(0.0069)
300	17034	1	BS 161B	9.28	0.0031	0.010	(0.004)	0.0007	0.0107	0.010	18.56	0.034	0.073	4.87	0.0011	0.67	0.0011	0.010
300		2	CT 300	9.07	0.005	0.032	0.005	0.004	0.030	0.047	18.51	0.034	0.12	4.97	.	0.69	.	.
300		1	IARM 99D	9.24	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	4.8	(0.0014)	0.67	(0.037)	(0.010)

Number	As	B	Ca	Fe	H	Mg	Nb	O	Sb	Sn	Ta	Zr	Units
BS 161A	(0.002)	0.0023	(0.0008)	.	.	.	(0.004)	(0.0004)	.	(0.0015)	(0.03)	(0.002)	Disc 38 mm Ø x ~12 or 19 mm
IARM 309A	(0.004)	0.0032	<0.001	.	.	.	0.004	0.0005	.	(0.001)	(0.006)	0.008	Disc 31 mm Ø x 2 mm
BS M250	.	0.0029	(0.003)	67.8	<0.0005	<0.005	<0.005	0.0005	<0.0005	<0.005	<0.005	0.0048	Disc 38 mm Ø x ~7 or 19+ mm
CT 250	.	0.0024	Disc 30-35 mm Ø x ~19 mm
ECRM 285-2D	.	0.0009	0.0050	Disc 38 mm Ø x 25 or 30 mm
IARM 308A	.	0.0029	0.003	0.0005	.	0.001	<0.01	0.01	Disc 31 mm Ø x 2 mm
IARM FeC250-21	(0.0011)	0.0029	0.0019	0.0006	(0.0044)	(0.0015)	(0.0128)	(0.0031)	Disc 38 mm Ø x 3 or 19 mm
BS 161B	.	0.0027	.	66.6	.	.	(0.0034)	0.0005	.	(0.0011)	(0.017)	(0.005)	Disc 41 mm Ø x ~7 or 19+ mm
CT 300	.	0.0020	Disc 30-35 mm Ø x ~16 mm
IARM 99D	.	0.0026	(0.011)	Disc 31 mm Ø x 2 or 18 mm

STAINLESS STEEL ALLOYS

1 = CRM, 2 = RM, 3 = RM with no uncertainties

Alloy	ISO	#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Ti	V	W
A-286	17025, 34	1	BS 188B	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	0.168	0.274	1.30	0.0021	2.20	0.264	0.043
CA6NM		2	HRT FE2009-H	0.035	0.78	0.034	0.003	0.35	0.08	3.89	12.83	.	.	0.42	(0.0339)	.	0.043	0.058
CA6NM		1	IARM 327A	0.018	0.54	0.018	0.0010	0.43	0.082	3.83	12.73	(0.003)	0.019	0.53	0.0157	0.0026	0.036	0.009
CD6MN		1	VS LG58	0.48	0.99	0.0135	0.0280	0.292	0.388	4.26	23.4	.	.	2.41	.	0.039	0.264	0.21
CF-3		1	IRSID 1820	0.021	1.61	(0.021)	0.0079	0.428	0.045	9.07	19.51	.	0.151	0.115	0.064	.	.	.
CF3M		1	ECRM 284-3D	0.0025	0.0615	0.0049	0.0066	0.0442	0.0105	12.09	17.37	.	0.0366	2.236	0.0418	0.0050	.	0.0039
ER321		1	13X 32180A	0.031	2.11	0.007	0.0093	0.485	0.49	10.16	18.92	0.043	0.040	0.245	0.0067	0.81	0.026	0.039
Greek Ascoloy	LAST	2	BS 183A	0.172	0.35	0.016	0.0040	0.37	0.093	1.85	12.14	0.002	0.036	0.12	0.0256	0.002	0.090	2.60
Greek Ascoloy	17034	1	BS 183B	0.181	0.344	0.018	0.0042	0.41	0.074	1.96	12.45	0.0009	0.032	0.33	0.044	(0.0016)	0.165	3.5
Greek Ascoloy	17034	1	BS 183C	0.173	0.368	0.015	0.0040	0.427	0.060	1.87	12.72	0.0020	0.027	0.189	0.039	(0.002)	0.109	2.83
Greek Ascoloy		1	IARM 20C	0.18	0.30	0.018	0.007	0.35	0.060	1.93	12.15	(0.004)	0.031	0.12	0.0222	(0.003)	0.086	2.59
M-152		1	13X 64152A	0.114	0.666	0.0123	0.0020	0.224	0.0622	2.50	11.34	0.0315	0.0185	1.567	0.0067	0.81	0.275	.
M-152		1	IARM 291A	0.11	0.71	0.016	0.009	0.23	0.060	2.62	11.3	(0.004)	0.021	1.61	0.035	0.0011	0.29	(0.01)
RA330		2	BS 86F	0.054	1.30	0.021	0.0011	1.22	0.23	34.99	18.74	(0.007)	0.098	0.24	0.035	(0.006)	0.061	(0.03)
S32750		1	13X NSA13A	0.020	0.761	0.0249	0.0005	0.257	0.156	6.73	25.27	(0.007)	0.032	3.73	0.269	.	0.0712	0.035
S42027		1	13X 42027A	0.294	0.356	0.0139	0.0005	0.544	0.035	0.163	15.25	0.004	0.0191	0.990	0.402	(0.002)	0.048	0.019
Super Duplex		2	TL 2001D	0.0244	0.679	0.0022	0.0006	0.27	0.612	7.5	25.58	.	0.046	3.49	0.279	.	0.079	0.57
Z30C13		1	IRSID 1825	0.305	0.650	0.019	0.022	0.336	0.100	0.308	12.90	.	0.026	0.052	.	.	0.052	.
Zeron 100		1	IARM 319A	0.015	0.53	0.024	0.0006	0.23	0.51	6.92	25.2	(0.010)	0.051	3.56	0.240	(0.003)	0.076	0.52
Zeron 100		1	IARM FeZ100-18	0.017	0.52	0.026	(0.0009)	0.24	0.55	7.1	25.5	(0.017)	0.123	3.61	0.22	.	0.090	0.56
Zeron 100		1	13X NSA8B	0.0206	0.596	0.0248	0.0007	0.285	0.589	7.48	25.49	.	0.0448	3.49	0.232	.	0.0583	0.599

Number	As	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Se	Sn	Ta	Zr	Units
BS 188B	0.0045	0.0047	(0.00003)	55.8	(0.0005)	0.099	0.0006	(0.0001)	(0.0006)	.	0.0051	(0.00003)	(0.002)	Disc 38 mm Ø x ~7 or 19+ mm
HRT FE2009-H	.	.	(0.001)	Disc 40 mm Ø x 40 mm
IARM 327A	(0.004)	(0.001)	.	.	(0.0003)	0.008	0.0047	.	.	.	0.006	(0.004)	(0.002)	Disc 31 mm Ø x 2 or 18 mm
VS LG58	0.214	Disc ~47 mm Ø x ~30 mm
IRSID 1820	.	(0.0013)	Block 47 mm x 47 mm x 30 mm
ECRM 284-3D	0.00131	0.00020	0.00074	.	.	Disc 39 mm Ø x 28 mm
13X 32180A	(0.003)	(0.0011)	.	.	.	(0.0021)	.	.	(0.0011)	.	0.0116	.	.	Disc ~40 mm Ø x ~15 mm
BS 183A	(0.002)	(<0.0005)	0.0020	.	.	0.006	0.0065	.	(0.001)	.	0.003	.	.	Disc 38 mm Ø x ~10 to 19 mm
BS 183B	(0.005)	(0.0007)	(0.0003)	80.4	(0.0002)	(0.0075)	(0.0054)	(0.0003)	0.0009	.	0.0046	(0.004)	(0.0009)	Disc 38 mm Ø x ~7 or 19+ mm
BS 183C	0.0041	(0.0008)	0.0006	81.1	(0.0002)	0.0054	(0.005)	(0.0002)	0.0007	.	0.0039	(0.003)	(0.0005)	Disc 38 mm Ø x ~7 or 19+ mm
IARM 20C	0.010	0.0068	.	.	.	0.004	.	.	Disc 31 mm Ø x 2 mm
13X 64152A	0.0053	.	.	Disc ~38 mm Ø x ~15 mm
IARM 291A	.	0.001	.	.	.	0.022	0.014	.	.	.	0.004	(0.001)	<0.005	Disc 31 mm Ø x 2 or 18 mm
BS 86F	(0.003)	0.0026	(0.001)	.	.	0.19	.	(0.001)	.	.	0.004	.	.	Disc 44 mm Ø x ~7 or 19+ mm
13X NSA13A	.	0.0030	.	.	.	0.028	.	(0.0008)	.	.	0.0046	.	.	Disc ~40 mm Ø x ~15 mm
13X 42027A	0.004	0.0026	.	.	Disc ~40 mm Ø x ~15 mm
TL 2001D	0.024	Disc 40 mm Ø x 20 mm
IRSID 1825	Disc 40 mm Ø x 30 mm
IARM 319A	(0.004)	0.0020	.	.	.	(0.006)	0.0025	.	.	.	0.0055	(0.002)	.	Disc 31 mm Ø x 2 mm
IARM FeZ100-18	.	0.002	.	.	.	(0.005)	(0.003)	.	.	.	(0.006)	.	.	Disc 31 mm Ø x 2 or 18 mm
13X NSA8B	.	0.0017	0.0011	.	.	0.026	Disc ~38 mm Ø x ~15 mm

PURE IRON

= class, where 1 = CRM and 2 = RM

T = total

Table with 15 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, Co, N, O. Rows include SRM 1265a, CZ LA-0A, CZ LA-0B, IARM 27G, BS LC-7B, BS LC-7A, BS 50G, TL 1669, ECRM 098-1D, ECRM 097-2D.

Table with 15 columns: Number, As, B, Mg, Nb, Pb, Sn, Ti, V, W, Units. Rows include SRM 1265a, CZ LA-0A, CZ LA-0B, IARM 27G, BS LC-7B, BS LC-7A, BS 50G, TL 1669, ECRM 098-1D, ECRM 097-2D.

* TL-1669 also contains in ppm Ca: 1.7, Sb: 4.9, Zn: 2.7

RM CARBON STEEL XRF SET

Part Number: BS CS-10 AVAILABLE INDIVIDUALLY 17025, 17034 ~7 mm discs

Table with 17 columns: Grade, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, As, Co, N, Sn, V. Rows include Pure Iron 1018, 1020, 1026, 1035, 1040, 1045, 1095, 1522 (LF2), 1345.

CRM CARBON STEEL SET

AVAILABLE IN SET/6 ONLY

38 mm Ø x 30 mm

Table with 15 columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Al.Sol, Ti, Ti.Sol, V. Rows include NCS HS11719-5, NCS HS11719-1, NCS HS11719-3, NCS HS11719-4, NCS HS11719-2, NCS HS11719-6.

CRM SOLUBLE ALUMINUM AND SOLUBLE BORON STEEL SET

available in set/6 only as grouped .T = total .S = soluble

37 mm Ø x 30 mm

Table with 15 columns: Number, Al.T, Al.S, B.T, B.S, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo. Rows include NCS HS93703-1a, NCS HS93703-2, NCS HS93703-3, NCS HS93703-4, NCS HS93703-5, NCS HS93703-6.

Table with 15 columns: Number, As, Bi, Ca, Nb, Pb, Sb, Sn, Ti, V, W, Zr. Rows include NCS HS93703-1a, NCS HS93703-2, NCS HS93703-3, NCS HS93703-4, NCS HS93703-5, NCS HS93703-6.

CARBON STEEL

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM and 2 = RM

Table listing carbon steel grades (e.g., IRSID 1660, ECRM 090-1D) with chemical composition columns (C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, As, B, Ca, Co, Mo) and their respective values.

Continuation of the carbon steel catalog table, listing grades (e.g., IARM 359A, VS UG94) and their chemical compositions across the same set of element columns.

Final summary row of the carbon steel catalog table with headers for each column.

CRM Al, Ca, AND N IN LOW ALLOY STEEL

Number	Al	Ca	N	Units
IMZ 133	.	.	0.0360	40 mm Ø x 40 mm
IMZ 131	0.0043	.	0.0333	40 mm Ø x 40 mm
IMZ 135	0.0274	0.0008	0.0238	40 mm Ø x 40 mm
IMZ 169	0.075	.	0.0193	40 mm Ø x 40 mm
IMZ 141	0.0071	.	0.0154	40 mm Ø x 40 mm
IMZ 130	0.0046	0.0024	0.0153	40 mm Ø x 40 mm
IMZ 139	(0.029)	0.0031	0.0113	40 mm Ø x 40 mm
IMZ 132	0.0021	0.0002	0.0097	40 mm Ø x 40 mm
IMZ 137	0.0017	0.00025	0.0083	40 mm Ø x 40 mm
IMZ 140	0.0307	0.0015	0.0083	40 mm Ø x 40 mm
IMZ 138	0.0022	.	0.0063	40 mm Ø x 40 mm
IMZ 134	0.0124	0.0005	.	40 mm Ø x 40 mm
IMZ 136	0.0034	0.00031	.	40 mm Ø x 40 mm

C-Mo and Cr-Mo STEEL XRF SET

= class, where 1 = CRM ISO 17025 and 2 = RM, Set Part Number: BS MOLY-5 AVAILABLE INDIVIDUALLY ~7 mm discs

#	Grade	Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V
2	C-.5Mo	4419	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.519	0.048	.	(0.0005)	.	.
1	1.25Cr-.5Mo	F-11	BS 45B	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	1.14	0.60	0.030	0.0090	0.0066	0.0069	0.0083
1	2.25Cr-1Mo	F-22	BS 46B	0.126	0.472	0.0087	0.0187	0.219	0.128	0.081	2.28	1.00	0.020	0.0074	0.0100	0.0073	0.0073
2	5Cr-.5Mo	F-5	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.47	0.015	0.011	0.018	0.008	0.016
1	9Cr-1Mo	F-9	BS 48B	0.110	0.365	0.0228	0.0068	0.75	0.070	0.165	8.78	0.949	0.0157	0.0165	0.0088	0.0049	0.033

CRM EPMA SETS

available in sets only, as grouped 4x10x15mm

Number	Cr	Number	Ni
NMIJ 1001-a	5.00	NMIJ 1006-a	5.04
NMIJ 1002-a	14.96	NMIJ 1007-a	10.05
NMIJ 1003-a	19.87	NMIJ 1008-a	20.02
NMIJ 1004-a	29.84	NMIJ 1009-a	39.92
NMIJ 1005-a	39.69	NMIJ 1010-a	60.07

BRAMMER STANDARD ONLINE CATALOG - IRON SOLIDS

Cr-Mo STEEL (Cr > 0.99, Mo > 0.44) CHART 1 or 3

= Class, where 1 = CRM and 2 = RM

Table with columns: #, Number, Cr, Mo, C, Mn, P, S, Si, Cu, Ni, Al, As, Co, N, Sn, Ti, V, W. Rows include various steel grades such as DSZU C082, HRT FE2019-H, BS 37G, etc., with their respective chemical compositions.

Table with columns: #, Number, B, Ca, Ce, Fe, La, Mg, Nb, O, Pb, Sb, Ta, Zn, Zr, Units, Comment. Rows provide detailed chemical analysis for the same steel grades, including trace elements and units of measurement.

LEADED STEEL		# = Class, where 1 = CRM and 2 = RM										OES regularly requires extension of preburn time					
#	Number	Pb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N	Sn	V
2	BS 74B	0.34	0.08	0.91	0.087	0.316	0.002	0.006	0.012	0.019	(0.002)	.	.	0.008	.	.	.
1	BS 74C	0.328	0.077	0.94	0.082	0.294	(0.002)	0.005	0.011	0.019	(<0.002)	0.004	.	0.008	0.0040	(<0.002)	0.0016
1	14X 12144A	0.328	0.0800	1.227	0.0630	0.325	0.0093	0.0106	0.0162	0.0807	0.0034	0.0022	.	0.0089	0.0066	.	.
2	CZ CM-15C	0.29	0.075	1.13	0.063	0.32	0.006	0.141	0.072	0.052	.	.	(0.01)	0.021	.	.	.
1	BS 74D	0.282	0.072	1.00	0.073	0.28	(0.007)	0.0057	0.0115	0.0185	(0.008)	0.0047	0.0043	0.0063	0.0040	(0.0010)	0.0012
1	BS 75G	0.247	0.161	1.08	0.0085	0.114	0.011	0.0300	0.045	0.079	0.0016	0.0028	0.0031	0.0174	0.0030	0.0014	0.0005
2	BS 75F	0.202	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.002	.	.	0.018	.	.	.
1	BS 73C	0.21	0.206	0.86	0.0111	0.031	0.280	0.025	0.56	0.574	0.028	0.0035	0.0028	0.180	0.0040	(0.002)	0.0031
IARM	Fe86L20-18	0.20	0.175	0.794	0.009	0.015	0.29	0.242	0.458	0.53	0.025	.	0.0085	0.203	0.0052	0.014	0.0016
1	BS 73D	0.18	0.202	0.834	0.018	0.027	0.287	0.240	0.420	0.47	0.015	0.0052	0.0123	0.162	0.0101	0.021	0.0028
2	BS 72B	0.174	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.020	(0.006)	0.012	0.187	0.0081	0.014	0.004
2	BS 73B	0.139	0.200	0.83	0.009	0.030	0.250	0.141	0.416	0.512	0.022	0.004	0.008	0.170	0.0113	0.008	(<0.002)
2	BS 70B	0.135	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.024	.	.	0.205	.	.	.
1	BS 70C	0.133	0.387	0.90	(0.009)	0.020	0.27	0.123	0.247	0.99	0.019	0.007	0.0086	0.202	0.0079	0.008	0.0026

Number	B	Ca	Nb	O	Sb	Ti	W	Zn	Grade	Units
BS 74B	12L14	41 mm Ø x ~7 or 19+ mm
BS 74C	.	.	(<0.005)	12L14	41 mm Ø x ~7 or 19+ mm
14X 12144A	~40 mm Ø x ~15 mm
CZ CM-15C	~39 mm Ø x 25 mm
BS 74D	0.0009	<0.001	(0.0018)	(0.028)	<0.05	(0.0007)	<0.005	Fe:98.2	12L14	41 mm Ø x ~7 or 19+ mm
BS 75G	(0.0002)	(0.0002)	(0.0003)	0.0155	.	(0.0004)	0.0004	.	11L17	41 mm Ø x ~7 or 19+ mm
BS 75F	11L17	40 mm Ø x ~7 or 19+ mm
BS 73C	(0.0002)	(0.0005)	(0.002)	0.0013	(0.002)	0.0024	(0.006)	.	86L20	38 mm Ø x ~7 or 19+ mm
IARM Fe86L20-18	CRM	86L20	38 mm Ø x ~2 or 19 mm
BS 73D	(0.0004)	0.0004	(0.0014)	0.0022	(0.0021)	0.0012	0.0107	<0.05	86L20	38 mm Ø x ~7 or 19+ mm
BS 72B	.	.	(0.001)	.	.	(0.002)	.	.	41L50	37 mm Ø x ~7 or 19+ mm
BS 73B	86L20	41 mm Ø x ~12 or ~17 mm
BS 70B	41L40MOD	41 mm Ø x ~7 or 19+ mm
BS 70C	(0.0003)	.	<0.005	0.0020	(0.003)	0.0020	(0.0006)	.	41L40MOD	41 mm Ø x ~7 or 19+ mm

RM LEADED AND BISMUTH STEEL XRF SET Part Number: BS PB-BI-7 AVAILABLE INDIVIDUALLY ~7 mm discs **17025**

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Bi	Pb	Sn	V	N
11L17	BS 75F	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.018	0.002	.	0.202	.	.	.
12L14	BS 74B	0.08	0.91	0.087	0.316	0.002	0.006	0.012	0.019	0.008	(0.002)	.	0.34	.	.	.
41L40	BS 70B	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.205	0.024	.	0.135	.	.	.
41L50	BS 72B	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.187	0.020	.	0.174	0.014	0.004	0.0081
4140 + Bi & S	BS 4140A	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.16	0.016	0.105	(0.001)	0.011	0.004	0.0098
4150 + Bi & S	BS 4150 MOD	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.21	0.012	0.070	0.0010	0.013	0.008	0.0087
8620 + Bi & S	BS 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.16	0.016	0.073	(0.001)	0.009	0.004	0.0107

CRM MANGANESE STEEL SET AVAILABLE IN SET/6 ONLY 30 mm Ø x 24 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	B	Co	Mo	N	Ti	V
NCS HS11720-6	2.38	5.36	0.029	0.108	1.69	0.474	3.43	0.084	0.017	0.107	1.51	0.016	0.218	0.837
NCS HS11720-1	1.96	22.96	0.188	0.0063	0.348	0.025	0.045	3.01	0.0021	0.0094	(0.0095)	0.091	0.0041	0.034
NCS HS11720-2	1.61	10.66	0.052	0.054	0.652	0.221	0.328	0.467	0.0038	0.010	0.118	0.054	0.047	0.132
NCS HS11720-3	1.16	16.75	0.077	0.055	1.16	0.143	0.152	0.257	0.0013	0.091	0.589	0.033	(0.030)	0.530
NCS HS11720-4	1.06	15.04	0.044	0.059	1.47	0.089	1.66	1.45	0.0023	0.0093	0.881	0.072	0.013	0.567
NCS HS11720-5	0.750	12.20	0.118	0.037	1.01	0.449	0.838	0.680	0.0009	0.0070	0.302	0.026	(0.018)	0.273

RESULFURIZED STEEL

CONTINUED FROM THE PREVIOUS PAGE

Number	B	Bi	Ca	Fe	Nb	O	Pb	Sb	Se	W	Zn	Zr	Units	Comment
14X FeNi40C	Disc ~40 mm Ø x ~15 mm	
IMZ 123	0.030	0.030	Disc 40 mm Ø x 40 mm	
ECRM 085-1D	0.0010	0.0073	.	.	0.0025	.	Disc 38 mm Ø x 25 or 30 mm	
14X 12144A	0.328	Disc ~40 mm Ø x ~15 mm	
IARM Fe1144-22	(0.002)	.	0.0017	.	0.0017	.	.	disc	
BS 66K	Disc 41 mm Ø x ~7 or 19+ mm	
CZ CM-15C	0.29	Disc ~39 mm Ø x 25 mm	
BS 74B	0.34	Disc 41 mm Ø x ~7 or 19+ mm	
BS 66L	(<0.0003)	.	(<0.0010)	.	(0.0012)	.	0.0007	0.0021	.	(<0.0010)	.	.	Disc 44 mm Ø x ~7 or 19+ mm	17025
14X 12130A	Disc ~40 mm Ø x ~15 mm	
BS 74C	(<0.005)	.	0.328	Disc 41 mm Ø x ~7 or 19+ mm	17025
IARM Fe1215-18	0.0012	.	0.0018	Disc ~38 mm Ø x ~3 or ~19 mm	
IARM 199C	0.0012	(0.003)	(0.0011)	.	0.0016	0.0037	(0.001)	(0.003)	.	0.0023	(0.0006)	.	Disc 31 mm Ø x 2(OK) or 18(last) mm	
BS 74D	0.0009	.	<0.001	98.2	(0.0018)	(0.028)	0.282	<0.05	.	<0.005	.	(0.0009)	Disc 41 mm Ø x ~7 or 19+ mm	17034
IMZ 124	(0.002)	0.002	Disc 40 mm Ø x 40 mm	
BS 1144A	(0.0003)	.	(0.0005)	97.3	(0.002)	0.0019	(0.0006)	(0.002)	.	(0.0009)	.	(0.0006)	Disc 38 mm Ø x ~7 or 19+ mm	17025
BS 1144	(0.004)	0.0016	(0.001)	.	.	(0.003)	.	.	Disc 38 mm Ø x ~16 mm	17025
14X MSFM4A	Disc 40 mm Ø x 15 mm	
IMZ 122	(0.020)	0.019	Disc 40 mm Ø x 40 mm	
14X 606M36TA	Disc ~40 mm Ø x ~15 mm	
14X 11390A	Disc ~40 mm Ø x ~15 mm	
ECRM 058-2D	Disc 38 mm Ø x 25 or 30 mm	
14X MSFM3G	0.0043	Disc ~40 mm Ø x ~15 mm	
BS A-11	0.0008	.	(0.0002)	79.5	(0.0070)	0.028	(0.00006)	(0.001)	.	(0.080)	.	(0.001)	Disc 38 mm Ø x ~7 or 19+ mm	17025
IARM 29E	0.0007	.	0.0012	.	0.0024	(0.005)	(0.001)	(0.003)	(0.0006)	.	(0.004)	.	Disc 31 mm Ø x 2 or 18 mm	
14X 11170A	0.0011	Disc ~40 mm Ø x ~15 mm	
BS 75F	0.202	Disc 40 mm Ø x ~7 or 19+ mm	17025
BS 65C	Disc 37 mm Ø x ~7 or 19+ mm	
BS 75G	(0.0002)	.	(0.0002)	[98.2]	(0.0003)	0.0155	0.247	.	.	0.0004	.	.	Disc 41 mm Ø x ~7 or 19+ mm	17025
BS 66B	0.0003	Disc 41 mm Ø x ~7 or 19+ mm	
IARM 348A	(0.0013)	<0.02	0.0010	.	0.027	(0.003)	(0.002)	(0.003)	<0.005	(0.009)	<0.003	(0.003)	Disc 31 mm Ø X 2 or 18 mm	
12X 352E	0.063	0.275	.	.	Disc ~40 mm Ø x ~15 mm	
IMZ 121	0.011	0.017	Disc 40 mm Ø x 40 mm	
IARM 307A	<0.005	<0.02	<0.0005	.	(0.002)	(0.003)	(0.002)	<0.004	<0.006	(0.005)	<0.002	(0.002)	Disc 31 mm Ø X 2 or 18 mm	
IARM 307B	(0.0013)	Disc 31 mm Ø X 2 or 18 mm	

Number	B	Bi	Ca	Fe	Nb	O	Pb	Sb	Se	W	Zn	Zr	Units	Comment
BS 3993	.	.	(0.0002)	.	.	(0.0030)	Disc 38 mm Ø x ~7 or 19+ mm	ISO 25
SRM 1173	Disc 32 mm Ø x 19 mm	
SRM C1173	Disc 32 mm Ø x 19 mm	
12X 15260X	0.183	.	0.0012	0.0054	Disc ~40 mm Ø x ~15 mm	
12X 15253T	0.374	0.276	.	.	Disc ~40 mm Ø x ~15 mm	Ta: 0.007
KUT A12	(0.03)	.	.	0.013	Disc 30-35 mm Ø x 39 mm	
IRSID 1745	(0.003)	.	Disc 48 mm Ø x 30 mm	
BS 4150MOD	.	0.070	0.0010	.	.	(0.003)	0.0010	Disc 38 mm Ø x ~7 mm	last
BS 8620A	.	0.073	0.0003	.	.	(0.004)	(0.001)	Disc 38 mm Ø x ~7 mm	last
BS 10V	0.013	.	.	Disc 41 mm Ø x ~7 or 19+ mm	
IRSID 1750	(0.0002)	(0.00002)	(0.0002)	.	(<0.0010)	.	(<0.001)	0.0031	(0.0002)	(0.004)	(0.0012)	(0.0002)	Disc 38 mm Ø x 25 mm	
BS 42	<0.005	.	<0.005	96.6	(0.0012)	(0.003)	<0.005	.	.	<0.005	.	.	Disc 44 mm Ø X ~7 or 19+ mm	17034
SS 604/2	(<0.005)	Disc 44 mm Ø X 19 mm	
VS UG144	0.0043	.	.	.	0.018	.	0.0017	(0.01)	.	1.32	0.0012	0.068	Disc ~37 mm Ø x ~20 mm	Ce: 0.004
SS 405/1	Disc 38 mm Ø x 19 mm	
12X 15255R	0.203	0.143	.	(0.011)	Disc ~40 mm Ø x ~15 mm	Ta: 0.034
BS TS15	(0.0005)	.	(0.001)	71.4	0.009	(0.018)	.	.	.	11.6	.	(0.003)	Disc 38 mm Ø x ~7 or 19+ mm	17034
12X 12749X	0.016	.	.	0.036	.	.	Disc ~40 mm Ø x ~15 mm	
12X 357D	0.0036	0.0024	.	.	0.011	.	0.040	0.018	0.0057	0.0213	.	0.0049	Disc ~40 mm Ø x ~15 mm	
DSZU C050	(0.002)	Disc 40 mm Ø x 25 mm	
DSZU C043A	(0.001)	.	0.0004	.	0.006	0.092	.	.	Disc 40 mm Ø x 25 mm	
KUT B2/2	Disc 30-35 mm Ø x 39 mm	
12X 12746V	0.105	.	.	Disc ~40 mm Ø x ~15mm	
IARM 168A	0.0004	.	.	.	0.003	0.0008	(<0.01)	.	.	0.52	.	.	Disc 31 mm Ø x 2 mm	
BS 4150MOD-A	(0.0004)	.	(0.0007)	96.7	(0.002)	0.0017	(0.0004)	(0.002)	.	0.0026	.	(0.0005)	Disc 38 mm Ø x ~7 or 19+ mm	17034
IARM FEM4-18	.	.	.	79.0	5.55	.	.	Disc ~38 mm Ø x ~3 or ~19 mm	
12X 1A1B	Disc ~40 mm Ø x ~15 mm	
VS UG145	0.0019	0.0052	0.0006	.	0.102	.	0.021	.	.	0.162	0.0017	0.008	Disc ~37 mm Ø x ~20 mm	
CZ CM-6A	0.015	.	.	.	0.028	.	0.017	0.03	.	0.04	.	0.04	Disc ~39 mm Ø x 25 mm	
IARM 251A	(0.002)	.	(0.0005)	.	0.016	(0.01)	(0.002)	.	.	5.5	.	(0.002)	Disc 31 mm Ø x 2 mm	
SRM 1138a	Disc 32 mm Ø x 13 mm	
SS 603/2	(<0.005)	Disc 44 mm Ø X 19 mm	
DSZU C070	0.29	.	.	Disc ~40 mm Ø x ~15 mm	

Number	B	Bi	Ca	Fe	Nb	O	Pb	Sb	Se	W	Zn	Zr	Units	Comment
--------	---	----	----	----	----	---	----	----	----	---	----	----	-------	---------

SILICON STEEL

CONTINUED FROM THE PREVIOUS PAGE

Number	B	Ca	Ce	Fe	Mg	Nb	O	Pb	Sb	Ta	W	Zn	Zr	Units	Comment
CZ SST-4A	0.0006	0.008	(0.003)	.	0.026	(0.002)	(0.003)	Disc ~37 mm Ø x 25 mm	
CZ CM-12C	0.0033	0.0010	.	.	.	0.0066	(0.004)	.	.	Disc ~37 mm Ø x ~25 mm	
CZ SST-3A	0.0019	0.013	.	.	0.016	0.011	.	Disc ~37 mm Ø x 25 mm	
ECRM 191-3D	0.00024	.	.	.	0.0036	Disc ~30 mm Ø x ~39 mm	
SRM 1135	Disc 31 mm Ø x 19 mm	
CZ SST-2A	0.0089	0.015	0.008	.	0.019	0.011	0.017	Disc ~37 mm Ø x 25 mm	
SRM 1134	Disc 31 mm Ø x 19 mm	
CZ SST-1A	0.0003	(0.002)	(0.002)	Disc ~37 mm Ø x 25 mm	
VS RG28/1	0.041	0.0041	.	.	Disc ~45 mm Ø x ~28 mm	
14X MN5V	0.041	.	.	.	(0.004)	.	.	.	Disc ~40 mm Ø x ~15 mm	
14X MN2S	0.23	.	.	.	(0.006)	.	.	.	Disc ~40 mm Ø x ~15 mm	
BS 38C	(0.002)	.	0.022	.	.	0.004	.	.	Disc 38 mm Ø x ~7 or 19+ mm	
12X 15251U	0.266	0.0393	.	.	Disc ~40 mm Ø x ~15 mm	
VS UG146	0.0019	0.0023	0.009	.	.	0.047	.	0.011	.	0.029	0.028	0.0098	.	Disc ~37 mm Ø x ~20 mm	Bi: 0.0038
VS UG92	0.034	.	0.00017	0.0005	Disc ~47 mm Ø x ~30 mm	Als: 0.08
KUT T4/1	Disc 30-35 mm Ø x 39 mm	last
IARM 47B	(<0.001)	(0.002)	(0.0014)	(0.0003)	.	.	(0.016)	.	.	Disc 31 mm Ø x 2 or 18 mm	
CZ CM-2B	0.0010	(0.58)	.	0.087	0.020	.	0.22	.	0.013	Disc ~37 mm Ø x ~25 mm	
DSZU C047A	0.0006	0.0022	.	.	.	0.020	2.37	.	.	Disc 40 mm Ø x 25 mm	
DSZU C080	3.40	.	.	Disc ~35 mm Ø x 20 or 25 mm	
ECRM 196-2D	0.00014	0.00071	.	.	0.00075	0.00019	.	Disc 38 mm Ø x 25 mm	
VS UG4/5	0.053	0.14	.	.	Disc ~45 mm Ø x ~28 mm	
VS UG1/11	Disc ~45 mm Ø x ~28 mm	
ECRM 186-1D	Disc 38 mm Ø x 25 or 30 mm	
BS 300A	(0.00032)	0.0008	.	93.8	<0.0005	(0.002)	<0.01	<0.0005	0.0011	0.0022	<0.01	.	(0.002)	Disc 38 mm Ø x ~7 or 19+ mm	17034
SS 405/1	Disc 38 mm Ø x 19 mm	
IMZ 56/1	Disc 40 mm Ø x 40 mm	
CZ CM-2A	0.0005	0.48	.	0.06	0.008	0.027	0.23	.	0.03	Disc ~37 mm Ø x 25 mm	last
BS 4340M	(0.001)	Disc 37 mm Ø x ~7 mm	last
IARM Fe300M-22	0.0115	.	.	disc	
VS UG111	0.056	.	.	Disc ~45 mm Ø x ~25 mm	
IARM 340A	0.0004	(0.0004)	.	.	(0.0002)	0.015	(0.001)	(0.001)	0.0021	.	(0.005)	(0.001)	(0.002)	Disc 31 mm Ø x 2 mm	
IARM 342A	0.0004	(0.0001)	.	.	(0.0002)	(0.002)	0.0006	0.0008	0.0021	.	(0.005)	(0.001)	(0.002)	Disc 31 mm Ø x 2 or 18 mm	
VS UG1/9	(0.0003)	0.124	.	(0.002)	.	.	0.063	.	.	Disc ~45 mm Ø x ~28 mm	
VS UG119	Disc ~45 mm Ø x ~25 mm	
VS UG4/10	0.030	0.006	.	.	Disc ~45 mm Ø x ~28 mm	
KUT B1/1	0.001	Disc 30-35 mm Ø x 39 mm	
BS 6418	0.0004	0.0002	.	[94.1]	0.0004	0.0022	0.0011	<0.005	(0.003)	<0.05	<0.05	<0.005	<0.005	Disc 57 mm Ø x ~7 or 19+ mm	17034
14X MN5U	0.102	Disc ~40 mm Ø x ~15 mm	
BS 19A	0.040	Disc 32 mm Ø x 17 mm	
Number	B	Ca	Ce	Fe	Mg	Nb	O	Pb	Sb	Ta	W	Zn	Zr	Units	Comment
SS 409/1	Disc 38 mm Ø x 19 mm	
IMZ 52/1	Disc 40 mm Ø x 40 mm	
SRM C1173	Disc 32 mm Ø x 19 mm	
CZ CM-14C	0.0249	0.248	.	0.0090	0.0170	.	0.0238	.	0.037	Disc 37 mm Ø x 25 mm	
BS Hical-1	(0.0001)	0.0140	.	[91.9]	(0.0003)	(0.002)	.	(0.0005)	.	.	(0.0009)	.	(0.0008)	Disc ~38 mm Ø x ~30 mm	17025
CZ LA-3G	0.0039	0.0016	.	.	.	0.071	.	0.0098	0.024	.	0.105	.	0.068	Disc ~37 mm Ø x ~25 mm	
IARM 172A	0.0003	(0.0001)	.	.	.	0.004	0.0006	<(0.01)	.	.	0.038	.	<(0.005)	Disc 31 mm Ø x 2 mm	
SRM 1173	Disc 32 mm Ø x 19 mm	
BS 69B	Disc 38 mm Ø x ~7 or 19+ mm	
VS UG143	0.0010	0.0015	0.019	.	.	0.014	.	0.0074	0.010	.	0.48	0.013	0.198	Disc ~37 mm Ø x ~20 mm	BI: 0.008
VS UG4/6	(0.03)	.	(0.005)	<(0.0005)	.	0.111	.	.	Disc ~45 mm Ø x ~28 mm	
VS UG1/5	0.078	(0.01)	.	.	Disc ~45 mm Ø x ~28 mm	
DSZU C046	(0.0004)	0.0007	.	.	.	(0.005)	0.47	.	.	Disc 40 mm Ø x 25 mm	
KUT A12	(0.03)	.	.	0.013	Disc 30-35 mm Ø x 39 mm	
VS RG28	0.029	0.006	.	.	Disc ~45 mm Ø x ~28 mm	
BS A-10	<0.005	.	.	Disc 40 mm Ø x ~7 or 19+ mm	
IMZ 173	0.10	.	.	Disc 40 mm Ø x 40 mm	
BS H-13A	(0.0007)	(0.0006)	.	90.2	(0.0002)	0.0052	(0.016)	(0.0004)	(0.002)	.	0.100	.	(0.002)	Disc 38 mm Ø x ~7 or 19+ mm	17034
SS 404/2	Disc 38 mm Ø x 19 mm	
14X MN3U	0.398	.	.	.	0.010	.	.	.	Disc ~40 mm Ø x ~15 mm	
DSZU C081	0.05	.	.	Disc ~35 mm Ø x 25 mm	
BS 34D	0.10	.	.	Disc 41 mm Ø x ~7 mm	last
IMZ 102/3	(0.0007)	(0.007)	Disc 40 mm Ø x 40 mm	
ECRM 274-1D	(0.0005)	(0.0026)	(0.000064)	(0.0002)	.	0.0087	.	.	Disc 38 mm Ø x 25 mm	
CT H13	Disc 30-35 mm Ø x ~16 mm	
ECRM 276-2D	Disc 38 mm Ø x 25 or 30 mm	
BS 41	0.035	.	.	Disc 42 mm Ø x ~7 or 19+ mm	17025
IARM 45A	(0.0001)	0.002	(0.0017)	<(0.005)	Disc 31 mm Ø x 2 mm	
12X 15255R	0.203	.	.	.	0.034	0.143	.	(0.011)	Disc ~40 mm Ø x ~15 mm	
12X 15258P	0.0100	0.133	.	.	.	(0.002)	0.125	.	.	Disc ~40 mm Ø x ~15 mm	
BS A-11	0.0008	(0.0002)	.	79.5	(0.0005)	(0.0070)	0.028	(0.00006)	(0.001)	.	(0.080)	.	(0.001)	Disc 38 mm Ø x ~7 or 19+ mm	17025
BS 41A	.	0.0006	0.002	.	.	.	<(0.003)	.	.	Disc 38 mm Ø x ~7 or 19+ mm	ISO 25
SS 603/2	<(0.005)	Disc 44 mm Ø x 19 mm	
VS UG120	Disc ~45 mm Ø x ~25 mm	
VS UG6/11	Disc ~45 mm Ø x ~28 mm	
14X MN4-21	(0.0029)	.	.	Rem	.	0.182	(0.0026)	.	.	(0.0104)	0.005	.	.	Disc ~40 mm Ø x ~15 mm	
14X MN1AL	0.096	.	.	.	(0.011)	.	.	.	Disc ~40 mm Ø x ~15 mm	
VS UG35/2	Disc ~40 mm Ø x ~28 mm	
CZ CM-23A	0.0129	0.0004	.	.	.	0.628	.	0.0034	0.137	(0.051)	0.104	0.0250	0.137	Disc 37 mm Ø x 25 mm	
SS 113	0.0066	0.0487	0.012	.	0.0029	Disc 44 mm Ø x 19 mm	
IARM 255A	0.0004	(0.0004)	.	.	.	0.004	0.0011	<0.001	.	.	0.007	.	<0.005	Disc 31 mm Ø x 2 mm	
IMZ 174	0.021	.	.	Disc 40 mm Ø x 40 mm	
ECRM 271-1D	.	0.0009	0.0020	.	.	.	0.0054	.	.	Disc 35 mm Ø x 25 mm	
BS 49	0.31	.	.	Disc 49 mm Ø x ~7 or 19+ mm	
BS TH12	1.06	.	.	Disc 38 mm Ø x ~7 or 19+ mm	
IARM 45B	(0.0001)	(0.001)	.	.	.	(0.002)	(0.0005)	(0.001)	(0.001)	(0.0003)	(0.004)	.	(0.001)	Disc 31 mm Ø x 2 or 18 mm	
BS PM15	(0.0002)	(0.0001)	.	[73.0]	(0.0002)	0.014	0.0129	(0.00001)	(0.0010)	(0.0003)	0.109	.	(0.0005)	Disc 38 mm Ø x 19+ mm	17025
13X 14713A	0.0016	Disc ~40 mm Ø x ~15 mm	
IARM 255B	(0.006)	Disc 31 mm Ø x 2 or 18 mm	
Number	B	Ca	Ce	Fe	Mg	Nb	O	Pb	Sb	Ta	W	Zn	Zr	Units	Comment

LOW ALLOY STEEL CHART 1 of 8

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, As, Mo, N, Sn, Ti, V. It lists chemical compositions for various steel grades like VS UG143, IMZ 65/2, DSZU C049, etc.

Table with columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, As, Mo, N, Sn, Ti, V. This is a duplicate of the first table above.

Table with columns: Number, B, Bi, Ca, Ce, Co, Fe, Mg, Nb, O, Pb, Sb, Ta, W, Zn, Zr, Units, Comment. It lists mechanical and processing properties for various steel grades, including units and comments.

LOW ALLOY STEEL CHART 4 of 8

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with 18 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, As, Mo, N, Sn, Ti, V. It lists various steel grades and their chemical compositions.

Table with 18 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, As, Mo, N, Sn, Ti, V. This is a duplicate of the table above.

Table with 20 columns: Number, B, Bi, Ca, Ce, Co, Fe, Mg, Nb, O, Pb, Sb, Ta, W, Zn, Zr, Units, Comment. It lists steel grades, their alloying elements, units, and comments.

LOW ALLOY STEEL CHART 5 of 8

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with 18 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, As, Mo, N, Sn, Ti, V. It lists various steel grades such as BS 1763, IARM 380A, RM Fe 2/4, 12X 12750U, BS 9325B, IARM 380B, HRT FE2018-N, IMZ 113, 12X 722M24A, IARM FeF1-21, IARM 169B, VS UG6/5, DSZU C043A, IARM 229B, ECRM 197-1D, BS 3961, BS 8620G, BS 8822A, DSZU C048, 12X 86200-21, IARM Fe8620-18, TL 1001, IPT 502, VS UG4/11, IARM 33D, BS 3952, BS 4820A, 12X 12747V, VS RG31/1, BS Lf2C *, KUT B3, VS UG5/5, BS 4820B, IARM 155F, SRM 1286, BS 1931, IARM Fe4820-18, VS UG8/10.

Table with 18 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Als, As, Mo, N, Sn, Ti, V. This is a header row for the second table below.

Table with 22 columns: Number, B, Bi, Ca, Ce, Co, Fe, Mg, Nb, O, Pb, Sb, Ta, W, Zn, Zr, Units, Comment. It lists various steel grades and their mechanical properties, such as BS 1763, BS HiCal-1, IARM 380A, RM Fe 2/4, 12X 12750U, BS 9325B, BS 9325, IARM 380B, HRT FE2018-N, IMZ 113, 12X 722M24A, IARM FeF1-21, IARM 169B, VS UG6/5, DSZU C043A, IARM 229B, ECRM 197-1D, BS 3961, BS 8620G, BS 8822A, DSZU C048, 12X 86200-21, IARM Fe8620-18, TL 1001, IPT 502, VS UG4/11, IARM 33D, BS 3952, BS 4820A, 12X 12747V, VS RG31/1, BS Lf2C *, KUT B3, VS UG5/5, BS 4820B, IARM 155F, SRM 1286, BS 1931, IARM Fe4820-18, VS UG8/10.

LOW ALLOY STEEL CHART 8 of 8

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Mo	N	Sn	Ti	V
1	VS UG117	0.064	1.41	0.012	0.021	0.60	0.214	0.072	0.129	0.018	.	.	(0.005)	0.0085	.	0.018	.
1	SRM C1285	0.058	0.332	0.072	0.020	0.36	0.37	1.17	0.80	.	.	.	0.164	.	0.035	.	0.150
2	CZ CM-7A	0.05	1.17	0.011	0.016	0.56	0.09	0.05	0.10	0.13	.	.	0.005	0.015	0.01	0.008	0.14
1	SS 421	(0.049)	(0.11)	(0.012)	(0.027)	(0.07)	(0.028)	.	.	.	(<0.02)
1	12X 12746V	0.048	1.19	0.034	0.064	0.156	0.646	0.226	0.374	0.459	.	0.051	0.658	.	0.264	0.088	0.0208
1	VS UG82	0.046	1.83	(0.003)	(0.004)	0.334	0.056	0.201	0.59	.	.	.	0.93	.	.	.	0.56
1	VS UG102	0.045	1.78	0.0082	.	0.222	0.172	0.277	0.0143	0.036	.	.	0.209
1	VS UG97	0.041	0.59	0.0036	0.0025	0.194	0.0040	0.0048	0.0080	0.51	.	.	0.019	.	.	0.154	(0.001)
1	VS RG26	0.028	0.75	0.0037	.	0.173	0.011	.	0.025	0.30	.	.	0.015	.	.	0.121	.
2	IARM 168A	0.003	0.12	0.030	0.064	0.46	0.009	2.32	0.004	0.19	.	(0.003)	0.69	0.0002	0.003	0.004	0.004

Number	B	Bi	Ca	Ce	Co	Fe	Mg	Nb	O	Pb	Sb	Ta	W	Zn	Zr	Units	Comment
VS UG117	Disc ~45 mm Ø x ~25 mm	
SRM C1285	.	.	.	0.021	0.036	Disc 32 mm Ø x 19 mm	
CZ CM-7A	0.0003	.	.	.	0.007	.	.	0.004	.	(0.0014)	(0.0003)	.	0.01	.	0.042	Disc ~39 mm Ø x 25 mm	
SS 421	0.52	.	.	Disc 38 mm Ø x 19 mm	
12X 12746V	0.142	0.105	.	.	Disc ~40 mm Ø x ~15mm	
VS UG82	Disc ~40 mm Ø x ~28 mm	
VS UG102	.	.	0.0018	0.071	Disc ~45 mm Ø x ~25 mm	
VS UG97	Disc ~40 mm Ø x ~28 mm	
VS RG26	0.0052	.	.	Disc ~45 mm Ø x ~28 mm	
IARM 168A	0.0004	.	.	(0.0002)	0.003	.	.	0.003	0.0008	<0.01	.	.	0.52	.	.	Disc 31 mm Ø x 2 mm	

CRM LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS analysis listed in mass % 31-34 mm Ø x 19 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Nb	Pb	Sn	Ta	Ti	V	W	Zr
SRM 1264a	0.87	0.25	0.010	0.025	0.067	0.25	0.14	0.06	(0.008)	0.010	0.15	0.49	0.15	0.0022	(0.008)	0.11	0.24	0.10	0.10	0.069

continued analysis listed in mass % analysis listed in mg/kg

Number	B	Bi	Fe.diff	Ge	Sb	Te	Zn	Ag	Au	Ca	Ce	H	Hf	La	Mg	N	Nd	O	Pd	Se	Sr
SRM 1264a	(0.011)	(0.0009)	[96.7]	(0.003)	0.034	0.00018	(0.001)	(0.2)	1	0.4	2	<5	(13)	0.7	1.5	(32)	0.7	(10)	(0.3)	(2.1)	(5)

LOW ALLOY STEEL XRF SET

Part Number: BS LAS-24 Set of 24 samples, each 35 - 45 mm Ø x 7 mm discs CRM, 17025, 17034 others are RM

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
300M	BS 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.007	.	0.013	0.0020	0.009	0.056
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	.	0.006	0.0056	(0.0004)	<0.003
3115	BS XCCV	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.004	.	0.017	0.0076	(0.002)	0.031
4130	BS 3932	0.321	0.54	0.016	0.018	0.33	0.200	0.19	1.00	0.229	0.020	0.004	0.0043	0.011	0.0070	0.012	0.005
4140	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.229	0.018	0.007	.	0.008	0.0095	0.010	0.004
4150 + s	BS 42	0.516	1.24	0.021	0.073	0.235	0.252	0.183	0.67	0.190	0.020	(0.004)	.	0.012	0.0080	0.012	0.003
4330	BS 4330MOD	0.316	0.92	0.0052	0.0010	0.269	0.105	1.83	0.848	0.478	0.031	0.0038	(0.001)	0.034	0.0031	0.0062	0.083
4340	BS 4340	0.418	0.695	0.0119	0.0187	0.279	0.149	1.79	0.807	0.231	0.028	0.0043	0.0005	0.0068	0.0080	0.0063	0.0033
4615	BS 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	.	.	0.035	0.0086	0.010	(0.0011)
4620	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.24	0.032	(0.0084)	(0.0001)	0.012	0.0078	0.013	(0.0008)
4820	BS 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.005	0.0046	0.008	0.0079	(0.008)	(0.002)
6150	BS 43A	0.49	0.82	0.0074	0.025	0.252	0.18	0.24	0.92	0.059	(0.003)	(0.005)	(0.0006)	0.008	0.0072	0.011	0.145
8620	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.168	0.021	0.007	(0.0008)	0.012	0.0079	0.007	0.002
8822	BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.34	0.022	0.007	(0.0004)	0.019	0.0085	0.011	0.003
8740	BS 67B	0.40	0.94	0.007	0.020	0.23	0.19	0.53	0.51	0.22	0.024	.	.	0.011	0.0078	0.009	(0.002)
9310	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.14	0.042	.	.	0.009	0.0147	0.012	0.005
9325	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	(0.004)	0.0049	0.010	0.0089	0.009	0.004
P-20	BS 55E	0.307	0.72	0.014	0.024	0.60	0.032	0.053	1.66	0.40	(0.004)	.	.	(0.005)	0.0096	0.002	0.019
AMS 6418	BS 69B	0.2258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	0.024	.	.	0.035	0.0057	0.006	(0.002)
A193	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	0.54	(0.004)	0.005	0.0006	0.010	0.0080	0.014	0.28
A485-1	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.029	0.017	0.006	.	0.010	0.0060	0.011	0.003
E52100	BS 53E	1.08	0.37	0.007	0.012	0.24	0.11	0.26	1.45	0.10	0.003	.	.	0.011	0.0086	0.005	0.004
Nitriding	BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	0.36	1.06	(0.004)	(0.0002)	0.011	0.0045	0.008	0.007
LF 3	BS LF 3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.006	(0.0001)	0.056	0.0054	0.006	(0.002)
Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V

CRM SOLUBLE ELEMENTS IN LOW ALLOY STEEL SET

available in set/7 only

-S = Soluble, -T = Total

38 mm Ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al-S	Al-T	B-S	B-T	Mo
NCS HS11717a-1	0.0023	0.018	0.012	0.0027	0.0054	0.0036	0.011	0.023	0.0069	0.0078	0.0002	0.0004	0.0053
NCS HS11717a-2	0.0028	0.104	0.014	0.011	0.077	0.049	0.045	0.042	0.024	0.026	0.0011	0.0012	0.304
NCS HS11717a-3	0.032	0.303	0.018	0.067	1.55	0.403	0.563	0.236	0.295	0.298	0.0018	0.0020	0.034
NCS HS11717a-4	0.096	0.669	0.012	(0.050)	1.09	0.316	0.400	0.102	0.214	0.216	0.0085	0.0096	0.144
NCS HS11717a-5	0.243	1.04	0.030	0.042	0.769	0.248	0.393	0.106	0.101	0.104	0.0071	0.0074	0.105
NCS HS11717a-6	0.387	1.47	0.038	0.030	0.436	0.167	0.206	0.409	0.050	0.051	0.0047	0.0049	0.071
NCS HS11717a-7	0.498	2.10	0.050	0.022	0.176	0.075	0.107	0.612	0.022	0.024	0.0031	0.0033	0.196
Number	As	Bi	Co	N	Nb	Pb	Sb	Sn	Ti	V			
NCS HS11717a-1	0.0034	(<0.00001)	0.0015	0.0016	(<0.0005)	(<0.0001)	0.00041	0.00020	0.0002	(0.0001)			
NCS HS11717a-2	0.011	(<0.00001)	0.058	0.0017	0.031	(<0.0001)	0.00031	0.0073	0.020	0.011			
NCS HS11717a-3	0.019	(<0.00001)	0.099	0.0032	0.079	(<0.0001)	0.00041	0.016	0.049	0.052			
NCS HS11717a-4	0.073	(0.00001)	0.146	0.0031	0.223	(<0.0001)	0.00044	0.049	0.202	0.098			
NCS HS11717a-5	0.071	(0.00001)	0.296	0.0048	0.318	(<0.0001)	0.00052	0.099	0.178	0.257			
NCS HS11717a-6	0.045	(0.00001)	0.248	0.0049	0.106	(<0.0001)	0.00048	0.151	0.124	0.201			
NCS HS11717a-7	0.034	(0.00001)	0.198	0.0063	0.153	(<0.0001)	0.00050	0.197	0.088	0.147			

RM TOOL STEEL XRF SET

Part Number: BS TS-18

AVAILABLE INDIVIDUALLY

17025

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
A-2	BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	0.99	.	(0.04)	0.11	0.03	.
A-10	BS A-10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	.
D-2	BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	1.09	.	0.16	0.80	0.07	0.016
H-10	BS 49	0.36	0.33	0.014	0.015	0.92	0.072	0.20	3.51	2.41	0.004	0.31	0.62	2.00	0.0186
H-11	BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	1.27	.	(0.01)	0.46	(0.008)	.
H-12	BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	1.41	.	1.06	0.62	0.07	.
H-13	BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	1.24	.	0.10	0.94	0.031	.
L-6	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	0.17	(0.011)	.	(0.01)	(0.02)	.
M-1	BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	8.4	.	1.7	1.05	0.45	.
M-2	BS 32C	0.84	0.29	(0.018)	0.0010	0.29	0.13	0.35	3.98	4.85	(0.02)	6.3	2.03	0.31	.
O-1	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.035	(0.005)	0.46	0.181	0.012	.
O-6	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23	(0.007)	0.035	0.046	.	.
S-1	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	.	2.75	0.19	0.006	.
S-5	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.214	0.036	0.0081
S-7	BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	.	0.19	0.35	0.043	.
T-1	BS 30D	0.745	0.348	0.029	0.0010	0.301	0.116	0.191	3.93	0.342	0.0123	17.73	1.077	0.101	0.0168
	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	0.064
HP9-4-30	BS 9-4-30	0.30	0.22	0.008	<0.001	0.06	0.09	0.07	7.25	1.00	0.004	0.01	0.085	4.40	0.0015
Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N

TOOL STEEL CHART 3 of 4

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with 17 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W. It lists various tool steel grades and their chemical compositions in percentages.

Table with 17 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W. This table continues the list of tool steel grades and their chemical compositions, similar to the first table.

Table with 17 columns: Number, As, B, Ca, Fe, Mg, Nb, O, Pb, Sb, Sn, Ta, Zn, Zr, Units, Comment. This table provides secondary element composition and additional specifications for the tool steel grades.

TOOL STEEL CHART 4 of 4

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Ti	V	W
1	IMZ 178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	0.015	0.20	0.0160	.	0.011	0.017
1	IMZ 171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.036	0.024	1.23	0.057	(0.001)	0.26	.
1	IMZ 196	0.179	0.42	0.018	0.012	0.46	0.080	0.44	11.04	0.029	1.55	0.65	0.058	.	0.34	1.54
1	IMZ 170	0.155	0.50	0.018	0.014	0.32	0.285	0.63	8.82	0.11	(0.022)	0.88	0.065	(0.002)	0.24	(0.19)
1	IMZ 176A	0.15	0.75	0.018	0.003	0.35	0.103	3.62	0.41	(0.058)	(0.010)	0.027	0.0129	.	(0.061)	(0.015)
2	CZ CM-17A	0.142	0.524	0.0310	0.0175	0.612	0.201	0.520	9.58	0.0089	0.0329	1.116	0.0743	0.0236	0.247	0.099
1	VS LG43/1	0.132	0.44	(0.01)	(0.01)	0.57	(0.11)	0.44	7.46	.	.	0.023	.	.	0.49	.
1	IMZ 197	0.130	0.45	0.021	0.007	0.47	0.11	0.053	0.20	8.45	.	(0.011)	.	0.025	0.025	.
1	NCS HS20741	0.125	0.957	0.017	0.0045	0.431	.	.	12.91	.	.	0.41
1	VS LG42/1	0.124	0.41	(0.02)	(0.008)	0.46	(0.16)	0.37	5.08	.	.	0.52	.	.	0.020	.
1	VS LG37/1	0.121	0.444	(0.02)	(0.01)	0.360	(0.13)	0.704	10.10	.	.	0.66	.	.	0.385	.
1	IARM 35L	0.119	0.535	0.007	0.014	0.679	0.123	0.071	1.35	0.017	0.0070	0.607	0.0072	(0.0015)	0.0037	(0.004)
1	IMZ 179	0.114	0.83	0.016	0.003	0.375	0.164	9.98	0.20	0.061	0.016	0.12	0.0108	.	0.023	(0.023)
1	IMZ 175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	(0.013)	0.025	0.0099	.	0.014	(0.019)
1	IMZ 157	0.095	0.63	0.015	0.010	0.59	0.066	0.50	9.51	0.26	.	0.71	0.051	0.044	0.26	.
1	IMZ 177	0.076	0.32	0.013	0.003	0.24	0.110	8.33	0.18	0.043	(0.017)	0.022	0.0089	.	0.010	.
1	13X 14713A	0.0446	0.495	0.0203	0.0080	0.911	0.0368	0.122	7.17	0.551	0.0110	0.0266	0.0065	0.0056	0.0411	.
1	SS 422	(0.036)	(0.09)	(0.015)	(0.025)	(0.06)	(0.033)	.	.	(<0.02)	1.28
1	IMZ 101/2	0.033	1.97	0.010	0.007	(0.092)	0.46	2.06	0.035	0.036	.	0.010	.	.	0.30	.
1	SS 423	(0.030)	(0.07)	(0.017)	(0.027)	(0.05)	(0.027)	.	.	(<0.02)	2.06
1	SS 424	(0.024)	(0.09)	(0.02)	(0.024)	(0.05)	(0.036)	.	.	(<0.02)	3.02
2	IARM 180A	0.007	0.41	0.004	0.046	0.023	0.89	1.29	0.037	0.76	0.004	0.006	0.0096	0.002	0.76	1.48

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Ti	V	W
---	--------	---	----	---	---	----	----	----	----	----	----	----	---	----	---	---

Number	As	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Sn	Ta	Zn	Zr	Units	Comment
IMZ 178	0.105	.	.	.	0.011	.	.	.	Disc 40 mm Ø x 40 mm	
IMZ 171	(0.003)	0.008	.	.	.	Disc 40 mm Ø x 40 mm	
IMZ 196	.	0.065	.	.	.	0.073	Disc 37 mm Ø x 30 mm	
IMZ 170	0.087	.	.	(0.002)	0.007	.	.	.	Disc 40 mm Ø x 40 mm	
IMZ 176A	0.009	.	.	.	Disc 40 mm Ø x 40 mm	
CZ CM-17A	0.0105	0.0060	0.0177	.	0.0109	.	.	.	Disc ~37 mm Ø x ~25 mm	
VS LG43/1	Disc ~45 mm Ø x ~28 mm	
IMZ 197	.	(0.007)	.	.	.	(0.011)	.	.	.	0.015	.	.	.	Disc 37 mm Ø x 30 mm	
NCS HS20741	Disc 35 mm Ø x 40 mm	
VS LG42/1	Disc ~45 mm Ø x ~28 mm	
VS LG37/1	Disc ~45 mm Ø x ~28 mm	
IARM 35L	0.0045	0.00044	.	.	.	(0.0026)	.	.	.	0.0088	.	.	.	Disc 31 mm Ø x 2 mm	
IMZ 179	(0.007)	(0.004)	.	.	.	0.010	.	.	.	Disc 40 mm Ø x 40 mm	
IMZ 175	0.011	.	.	.	Disc 40 mm Ø x 40 mm	
IMZ 157	Disc 40 mm Ø x 40 mm	
IMZ 177	0.008	.	.	.	Disc 40 mm Ø x 40 mm	
13X 14713A	0.0016	0.0034	.	.	.	Disc ~40 mm Ø x ~15 mm	
SS 422	Disc 38 mm Ø x 19 mm	
IMZ 101/2	.	(0.0005)	(0.002)	Disc 40 mm Ø x 40 mm	
SS 423	Disc 38 mm Ø x 19 mm	
SS 424	Disc 38 mm Ø x 19 mm	
IARM 180A	(0.004)	0.0004	.	.	.	(0.005)	0.0006	(0.002)	.	0.002	.	.	.	Disc 31 mm Ø x 2 mm	

Number	As	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Sn	Ta	Zn	Zr	Units	Comment
--------	----	---	----	----	----	----	---	----	----	----	----	----	----	-------	---------

MARAGING STEEL AND COBALT IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM

#	Number	Co	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Ti	V	W
1	IMZ 521	20.25	0.015	0.039	0.0031	0.0058	0.072	0.027	8.63	0.040	.	4.84	0.0113	.	3.97	5.23
1	IMZ 522	18.72	0.0088	0.032	(0.003)	0.0043	0.048	0.019	11.47	0.022	.	6.45	0.0045	0.54	2.21	2.25
1	IMZ 520	17.66	0.011	0.070	0.0043	0.019	0.094	0.080	10.10	0.242	.	4.92	0.0105	(0.007)	4.03	4.90
1	IARM FeKovar-18	17.3	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068	.	0.062	.	.	.	(0.020)
1	BS 160B	17.24	0.022	0.27	0.0033	0.0032	0.112	0.059	29.13	0.06	(0.005)	0.047	0.0006	(0.003)	0.0039	(0.011)
1	BS 160A	17.0	0.0064	0.180	0.0007	(0.0002)	0.158	0.026	29.6	0.0138	0.088	0.0100	0.0026	0.026	0.0008	(0.0001)
1	IARM 98B	17.0	0.007	0.18	0.002	0.0007	0.17	0.028	29.4	0.012	0.07	0.010	0.0024	0.03	(0.003)	(0.02)
1	IMZ 523	14.44	0.0098	0.051	(0.004)	0.0039	0.043	0.059	15.94	0.048	.	6.67	0.0037	0.70	2.01	1.87
1	IARM 242A	13.5	0.24	0.18	0.002	0.0004	0.02	0.007	11.1	3.00	0.004	1.21	0.0003	0.009	0.01	<0.01
1	IARM FeA100-18	13.4	0.222	(0.013)	(0.004)	(0.0010)	(0.039)	(0.010)	11.2	2.98	(0.007)	1.19	(0.0010)	(0.008)	(0.007)	(0.006)
2	CT ISO045A	13.39	0.228	0.002	0.001	0.0004	<0.010	0.006	11.38	3.12	0.004	1.18	.	0.005	.	.
1	IARM 309A	12.3	0.0059	0.018	0.004	0.0006	0.020	0.023	18.4	0.053	0.11	4.71	0.0010	1.47	0.01	0.01
1	IMZ 524	12.25	0.012	0.68	(0.004)	0.004	0.13	0.024	13.75	0.085	.	4.95	0.0038	0.85	3.02	1.84
1	DSZU C093	12.08	0.013	0.32	(0.006)	(0.007)	(0.10)	(0.12)	15.80	0.42	0.17	3.79	.	1.56	.	.
1	BS 161B	9.28	0.0031	0.010	(0.004)	0.0007	0.0107	0.010	18.56	0.034	0.073	4.87	0.0011	0.67	0.0011	0.010
1	IARM 99D	9.24	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	4.8	(0.0014)	0.67	(0.037)	(0.010)
1	BS 161A	9.22	0.004	0.031	0.004	0.0007	0.032	0.22	18.40	0.12	0.14	4.82	(0.002)	0.65	(0.031)	(0.008)
2	CT 300	9.07	0.005	0.032	0.005	0.004	0.030	0.047	18.51	0.034	0.12	4.97	.	0.69	.	.
1	DSZU C091	8.07	0.035	0.092	(0.006)	(0.011)	(0.09)	(0.12)	18.20	0.12	0.05	4.98	.	0.81	.	.
1	IARM FeC250-21	7.92	0.0028	0.022	0.0033	0.0006	0.0091	(0.0041)	18.6	(0.0093)	0.101	4.93	0.0004	0.418	(0.0074)	(0.0069)
1	BS M250	7.9	0.0021	0.024	0.0031	(0.0005)	(0.003)	(0.003)	18.7	(0.004)	0.098	4.93	<0.005	0.422	<0.05	(0.007)
1	IARM 308A	7.80	0.003	0.019	0.004	0.0005	0.014	0.018	18.53	0.023	0.097	4.78	0.0013	0.46	0.01	0.01
1	ECRM 285-2D	7.76	0.0018	0.0168	0.0053	0.0025	0.0117	0.0094	18.07	0.0236	0.1067	4.99	0.0007	0.520	.	.
2	CT 250	7.54	0.002	0.006	0.003	0.002	0.008	0.008	18.44	0.008	0.058	4.88	.	0.41	.	.
2	DSZU C55	5.75	(0.19)	0.73	(0.042)	.	0.68	.	2.24	14.9	.	1.32	(0.11)	.	0.29	(1.17)
1	DSZU C092	5.21	0.015	0.27	(0.006)	(0.009)	(0.10)	(0.16)	20.12	0.23	(0.006)	5.50	.	(0.008)	.	.
2	DSZU C53	5.20	(0.26)	0.82	(0.036)	.	0.29	.	1.47	14.8	.	1.71	.	.	0.33	(0.59)
2	DSZU C54	5.19	(0.06)	0.60	(0.036)	.	0.56	.	1.88	18.5	.	1.47	(0.13)	.	0.47	(0.71)
2	DSZU C51	4.07	(0.16)	0.40	(0.019)	.	0.25	.	1.67	10.8	.	0.68	(0.09)	.	0.15	(0.32)

#	Number	Co	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Ti	V	W
---	--------	----	---	----	---	---	----	----	----	----	----	----	---	----	---	---

Number	As	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Sn	Ta	Zr	Comment
IMZ 521	(0.002)	.	.	Disc 38 mm Ø x 20 mm
IMZ 522	(0.008)	.	.	.	(0.001)	.	.	Disc 38 mm Ø x 20 mm
IMZ 520	.	(0.001)	.	.	.	(0.008)	.	.	.	(0.002)	.	.	Disc 38 mm Ø x 20 mm
IARM FeKovar-18	.	.	.	53.3	0.0021	.	.	Disc 31 mm Ø x 2 or 18 mm
BS 160B	<0.005	0.0003	0.0004	53.0	<0.005	0.0015	0.0010	<0.005	(0.0009)	0.0020	<0.005	(0.0027)	Disc 38 mm Ø x ~7 or 19+ mm 17034
BS 160A	0.0011	0.0010	(0.0004)	52.9	0.0032	0.0014	0.0022	(0.00006)	(0.0004)	0.0024	(0.0001)	0.0048	Disc 38 mm Ø x 19 mm 17025
IARM 98B	<0.002	0.001	<0.0005	52.9	0.0040	0.002	0.0021	<0.0005	.	0.002	<0.05	<0.01	Disc 31 mm Ø x 2 mm
IMZ 523	(0.008)	.	.	.	(0.001)	.	.	Disc 38 mm Ø x 20 mm
IARM 242A	.	(0.0005)	.	.	.	0.004	0.0006	.	.	(0.001)	0.008	.	Disc 31 mm Ø x 2 mm
IARM FeA100-18	(0.003)	(0.0009)	Disc 31 mm Ø x 2 or 18 mm
CT ISO045A	.	.	.	70.70	Disc 30-35 mm Ø x ~19 mm
IARM 309A	(0.004)	0.0032	<0.001	.	.	0.004	0.0005	.	.	(0.001)	(0.006)	0.008	Disc 31 mm Ø x 2 mm
IMZ 524	(0.003)	(0.007)	Disc 38 mm Ø x 20 mm
DSZU C093	Disc ~40 mm Ø x 17 mm
BS 161B	.	0.0027	.	66.6	.	(0.0034)	0.0005	.	.	(0.0011)	(0.017)	(0.005)	Disc 41 mm Ø x ~7 or 19+ m 17034
IARM 99D	.	0.0026	.	.	.	(0.011)	Disc 31 mm Ø x 2 or 18 mm
BS 161A	(0.002)	0.0023	(0.0008)	.	.	(0.004)	(0.0004)	.	.	(0.0015)	(0.03)	(0.002)	Disc 38 mm Ø x ~12 or 19 mm ISO 25, last
CT 300	.	0.0020	Disc 30-35 mm Ø x ~16 mm
DSZU C091	Disc ~40 mm Ø x 17 mm
IARM FeC250-21	(0.0011)	0.0029	.	Rem	.	0.0019	0.0006	.	(0.0044)	(0.0015)	(0.0128)	(0.0031)	Disc 38 mm Ø x 3 or 19 mm
BS M250	.	0.0029	(0.003)	67.8	<0.005	<0.005	0.0005	.	<0.0005	<0.005	<0.005	0.0048	Disc 38 mm Ø x ~7 or 19+ mm 17034
IARM 308A	.	0.0029	.	.	.	0.003	0.0005	.	.	0.001	<0.01	0.01	Disc 31 mm Ø x 2 mm
ECRM 285-2D	.	0.0009	0.0050	Disc 38 mm Ø x 25 or 30 mm
CT 250	.	0.0024	Disc 30-35 mm Ø x ~19 mm
DSZU C55	0.27	Disc 42 mm Ø x 25 mm
DSZU C092	Disc ~40 mm Ø x 17 mm
DSZU C53	0.13	Disc 42 mm Ø x 25 mm
DSZU C54	0.40	Disc 42 mm Ø x 25 mm
DSZU C51	0.10	Disc 42 mm Ø x 25 mm

Number	As	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Sn	Ta	Zr	Comment
--------	----	---	----	----	----	----	---	----	----	----	----	----	---------

MANGANESE STAINLESS STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with 17 columns: #, Number, Mn, C, P, S, Si, Cu, Ni, Cr, Al, Mo, N, Nb, Ti, V, W. It lists various stainless steel grades and their chemical compositions.

Table with 17 columns: #, Number, Mn, C, P, S, Si, Cu, Ni, Cr, Al, Mo, N, Nb, Ti, V, W. This is a continuation of the previous table.

Table with 20 columns: Number, As, B, Ca, Co, Fe, Mg, O, Pb, Sb, Sn, Ta, Zr, Units, Comment. This table provides detailed analysis and units for various stainless steel grades.

Table with 20 columns: Number, As, B, Ca, Co, Fe, Mg, O, Pb, Sb, Sn, Ta, Zr, Units, Comment. This is a continuation of the detailed analysis table.

SULFUR AND PHOSPHORUS IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	S	P	C	Mn	Si	Cu	Ni	Co	Cr	Mo	N	Sn	V
1	IARM Fe416-22	0.37	0.019	0.114	0.83	0.39	0.064	0.230	0.019	12.98	0.027	0.036	0.0041	0.038
2	CT 416	0.36	0.018	0.088	0.52	0.63	0.004	0.24	0.019	13.15	0.065	0.020	0.005	0.025
1	IARM Fe303-18	0.35	0.033	0.046	1.55	0.47	0.61	8.12	0.140	17.2	0.42	0.069	(0.015)	0.072
1	BS 416	0.35	0.0237	0.116	0.64	0.232	0.154	0.371	0.0241	13.41	0.030	0.043	(0.005)	0.100
2	BS 150	0.33	0.020	0.048	1.71	0.43	0.042	0.19	0.024	18.61	1.97	0.029	(0.003)	0.054
1	SRM 1223	0.329	0.018	0.127	1.08	0.327	0.081	0.232	.	12.64	0.053	.	.	0.068
2	BS 90F	0.328	0.023	0.085	0.53	0.58	0.12	0.30	0.021	13.01	0.14	0.037	0.005	0.076
1	BS 303	0.326	0.028	0.044	1.80	0.415	0.627	8.17	0.071	17.23	0.410	0.023	0.0091	0.056
1	13X 30300A	0.312	0.0205	0.041	1.83	0.422	0.025	8.60	0.0255	17.62	0.334	0.034	.	0.091
2	CT 303	0.31	0.029	0.070	1.64	0.58	0.49	9.08	0.16	17.78	0.41	.	0.007	0.044
1	IARM 355A	0.31	0.0186	0.0274	0.47	0.435	0.083	0.427	0.047	17.81	0.337	0.0439	(0.005)	0.038
2	BS 154	0.302	0.027	0.030	0.40	1.26	0.063	0.25	0.019	17.58	0.31	0.039	(0.005)	0.046
1	13X 41600A	0.302	0.0253	0.111	0.627	0.442	0.160	0.331	0.0216	13.23	0.0499	0.0245	0.0066	0.0888
2	CZ SP-1B	0.30	0.039	0.050	1.67	0.505	0.47	8.32	0.161	17.42	0.40	0.063	0.013	0.0660
2	13X 12549K	0.29	0.092	0.16	0.34	0.43	0.10	1.26	0.52	11.70	1.49	.	.	.
2	BS 153	0.280	0.018	0.026	0.41	0.53	0.052	0.140	0.017	17.38	0.30	0.021	0.002	0.045
2	BS 152	0.275	0.022	0.320	0.36	0.44	0.050	0.14	0.015	13.41	0.061	0.020	0.003	0.051
3	CZ SP-1A	0.26	0.024	0.047	1.87	0.33	0.52	8.6	0.095	17.7	0.42	.	0.01	0.058
1	IARM 352A	0.21	0.0182	0.341	1.13	0.357	0.148	0.269	(0.016)	13.11	0.38	0.029	0.0046	0.028
1	13X 43020A	0.189	0.0246	0.147	1.439	0.415	0.0687	0.517	0.0191	16.07	0.226	0.0212	.	0.0542
1	13X 12548N	0.189	0.023	0.175	0.510	0.193	0.264	1.10	0.388	12.70	1.42	0.102	0.0064	0.025
1	NCS HS41751A	0.16	0.035	0.075	1.70	0.71	0.26	8.07	0.13	17.41	0.33	0.077	.	0.068
2	13X 14775S	0.154	0.047	0.006	1.405	0.552	0.167	1.949	0.153	17.78	0.529	.	0.0007	0.0287
2	BS 155	0.145	0.014	1.00	0.35	0.40	0.035	0.13	0.019	16.64	0.46	0.032	(0.003)	0.10
1	13X 12536T	0.090	0.0449	0.146	0.374	0.546	0.0793	12.12	0.280	16.09	2.48	0.0084	0.0068	0.0513
1	IARM 253A	0.0089	0.140	0.041	1.50	0.50	0.223	9.17	0.088	17.90	0.348	0.0373	0.01	0.106
1	IARM 253B	0.011	0.13	0.051	1.61	0.46	0.44	9.11	0.145	17.64	0.59	0.031	(0.012)	0.092
1	13X 19004C	0.0135	0.074	0.075	2.01	0.35	0.0112	17.90	0.0501	22.77	3.43	.	(0.001)	0.041
1	13X 18003C	0.0245	0.0545	0.113	1.000	0.805	0.0433	10.08	0.100	19.56	0.401	0.090	.	0.0750
1	13X 17001C	0.0134	0.055	0.0769	1.543	0.215	0.0161	6.31	0.0979	14.83	0.0967	.	.	.

#	Number	S	P	C	Mn	Si	Cu	Ni	Co	Cr	Mo	N	Sn	V
---	--------	---	---	---	----	----	----	----	----	----	----	---	----	---

Number	Al	As	B	Nb	O	Pb	Sb	Se	Ta	Ti	W	Units	Comment
IARM Fe416-22	(0.0016)	(0.003)	.	(0.004)	(0.008)	0.0015	(0.004)	disc	
CT 416	<0.001	Disc 30-35 mm Ø x ~16 mm	Ag: 0.0002
IARM Fe303-18	.	0.007	(0.0012)	0.015	(0.006)	0.029	Disc 31 mm Ø x 2 or 18 mm	
BS 416	(0.002)	0.0039	(0.001)	(0.006)	0.0081	(0.0006)	(0.002)	.	(0.004)	0.0012	0.0034	Disc 38 mm Ø x ~7 or 19+ mm	17025
BS 150	0.002	.	.	0.003	0.012	0.01	Disc 35 mm Ø x ~7 or 19+ mm	
SRM 1223	Disc 32 mm Ø x 19 mm	
BS 90F	(0.006)	.	.	0.011	0.011	0.032	Disc 38 mm Ø x ~7 to 19 mm last	
BS 303	0.0019	.	0.0013	0.008	0.0058	.	(0.002)	.	.	0.017	0.023	Disc 44 mm Ø x ~7 or 19+ mm	17025
13X 30300A	.	.	0.0035	Disc ~40 mm Ø x ~15 mm	
CT 303	0.001	Disc 30-35 mm Ø x ~16 mm	Ag: 0.0003
IARM 355A	0.0016	(0.004)	(0.0011)	0.0095	(0.010)	(0.0002)	.	(0.0001)	(0.001)	0.0020	(0.018)	Disc 31 mm Ø x 2 or 18 mm	
BS 154	(0.002)	.	.	0.005	0.008	(0.01)	Disc 38 mm Ø x ~7 or 19+ mm	
13X 41600A	(0.004)	.	.	0.0053	(0.003)	Disc ~41 mm Ø x ~15 mm	
CZ SP-1B	(0.003)	(0.003)	0.0007	(0.012)	(0.002)	0.032	Disc ~37 mm Ø x ~25 mm	
13X 12549K	.	.	.	0.23	Disc 40 mm Ø x 15 mm	
BS 153	0.002	(0.004)	.	0.002	.	(0.001)	.	.	.	(0.004)	(0.002)	Disc 35 mm Ø x ~7 or 19+ mm	
BS 152	(0.002)	.	.	0.006	<0.01	Disc 41 mm Ø x ~7 or 19+ mm	
CZ SP-1A	0.004	0.006	0.0007	0.012	0.02	0.03	Disc ~39 mm Ø x 25 mm	
IARM 352A	(0.0025)	(0.005)	(0.0007)	(0.012)	(0.005)	.	.	(0.006)	(0.0007)	0.0015	(0.005)	Disc 31 mm Ø x 2 or 18 mm	
13X 43020A	0.0047	.	(0.0032)	0.0102	0.0108	Disc ~40 mm Ø x ~15 mm	
13X 12548N	(0.02)	(0.003)	.	0.49	.	(0.002)	0.019	.	.	0.0015	0.038	Disc ~40 mm Ø x ~15 mm	Batch N
NCS HS41751A	Disc 38 mm Ø x 38 mm	
13X 14775S	0.0301	(0.002)	.	0.691	Disc ~40 mm Ø x ~15 mm	
BS 155	(0.001)	.	.	0.002	0.0048	Disc 36 mm Ø x ~7 or 19+ mm	
13X 12536T	0.108	.	0.0214	0.060	0.104	0.444	.	Disc ~40 mm Ø x ~15 mm	
IARM 253A	0.003	.	0.0003	0.016	0.009	.	.	0.21	.	0.002	0.10	Disc 31 mm Ø x 2 mm	
IARM 253B	(0.004)	0.0052	0.0007	0.021	0.007	(0.0002)	(0.0018)	0.13	(0.003)	0.0027	(0.05)	Disc 31 mm Ø x 2 or 18 mm	
13X 19004C	0.030	.	(0.001)	0.152	0.011	.	.	Disc ~40 mm Ø x ~15 mm	
13X 18003C	0.0292	.	.	1.042	Disc ~40 mm Ø x ~15 mm	
13X 17001C	0.0312	.	0.0085	0.546	0.0124	.	.	Disc ~40 mm Ø x ~15 mm	

Number	Al	As	B	Nb	O	Pb	Sb	Se	Ta	Ti	W	Units	Comment
--------	----	----	---	----	---	----	----	----	----	----	---	-------	---------

CRM NICKEL BINARIES analysis listed in mass % ~40 mm Ø x ~15 mm

Number	Ni	C	Mn	P	S	Si	Cu	Cr	Al	Co	N	Mg	Mo	Nb	Ti	W
14X FeNi50C	51.5	0.0245	0.057	0.0168	0.16	0.151	0.089	0.066	0.319	0.416
14X FeNi45C	45.88	0.0082	0.0222	0.026	0.0015	0.77	0.089	0.076	0.98	0.572
14X FeNi40C	40.1	0.012	0.031	0.0148	1.03	0.050	0.081	0.64	2.00	1.057
14X 94100A	41.00	0.0055	0.443	0.0051	0.0027	0.103	0.0628	0.0265	.	0.0208	0.0016	0.0021	0.0053	(0.01)	0.0011	0.0017
14X FeNi10A	10.12	0.095	0.272	0.015	0.027	0.061	0.029	0.070	0.025	.	0.0055
14X FeNi8A	8.10	0.097	0.330	0.015	0.029	0.097	0.030	0.250	0.029	.	0.0061
14X FeNi6A	6.08	0.100	0.330	0.0155	0.028	0.075	0.028	0.073	0.025	.	0.0055

STAINLESS AND HIGH ALLOY STEEL, CHART 3 of 7

= Class, 1=CRM, 2=RM, and 3=RM with no uncertainties

Table with columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo, N, Nb, Sn, Ti, V, W. Rows list various stainless steel grades like NM 302, IARM 152C, VS LG72, etc., with their respective chemical composition values.

Table with columns: #, Number, Al, As, B, Ca, Fe, Mg, O, Pb, Sb, Ta, Zr, Units, Comment. This table provides mechanical and physical properties for the same stainless steel grades listed in the first table, including yield strength, tensile strength, and elongation.

CRM	CAST IRON SETS																		AVAILABLE IN SETS ONLY, as grouped																	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Sn	Ti	V	Ce	La	Mg	N																			
30 mm Ø x 28 mm																																				
NCS HS11712a-6	4.02	1.41	0.021	0.026	0.163	1.83	1.89	0.112	0.019	0.726	0.057	0.238	0.509	<0.0001	<0.0001	0.104	0.013																			
NCS HS11712a-7	3.94	1.38	0.085	0.0048	0.918	1.10	1.37	1.05	0.214	0.168	0.134	0.114	0.390	<0.0001	<0.0001	0.056	0.0063																			
NCS HS11712a-5	3.52	0.311	0.420	0.019	1.17	0.389	1.03	0.766	.	0.629	0.013	0.161	0.324	<0.0001	<0.0001	0.021	0.0047																			
NCS HS11712a-4	3.16	0.462	0.396	0.017	1.96	0.921	0.778	1.40	0.0073	0.428	0.024	0.065	0.166	<0.0001	<0.0001	0.025	0.0073																			
NCS HS11712a-2	2.22	0.301	0.043	0.058	2.44	0.458	0.341	2.13	0.060	0.087	0.044	0.065	0.055	0.0010	0.010	0.0085	0.024																			
NCS HS11712a-3	2.55	0.878	0.071	0.045	1.50	0.641	0.519	0.417	0.034	0.354	0.021	0.027	0.085	0.027	0.0061	0.024	0.024																			
NCS HS11712a-1	1.75	0.080	0.580	0.119	3.40	0.025	0.030	2.48	0.248	0.031	0.0031	0.038	0.021	<0.0001	<0.0001	0.0006	0.015																			
30 mm Ø x 30 mm																																				
NCS HS19701-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	0.043	0.399	0.821																			
NCS HS19701-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	(0.112)	0.0018	0.105	0.506																			
NCS HS19701-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	(0.68)	0.0022	0.066	0.335																			
NCS HS19701-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	(0.031)	0.0017	0.030	0.158																			
NCS HS19701-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	0.009	0.043	0.071																			
NCS HS19701-2	2.99	0.329	0.033	0.038	0.937	.	0.194	0.080	.	.	0.024	0.216	0.044																			
NCS HS19701-1	2.46	0.072	0.011	0.019	0.099	.	0.183	0.511	.	.	0.005	0.0059	0.0090																			

RM GRAY IRON

as cast (not chill cast) CONTAINS FREE GRAPHITE OES regularly requires extension of preburn time to analyze correctly

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Sb	Sn	Ti	V	mm Ø x mm H
BS 20G	3.33	0.58	0.028	0.029	3.02	0.54	0.38	0.086	0.008	0.004	0.022	0.19	(<0.001)	0.12	0.012	0.018	47 x 19+
BS 20W	3.27	0.62	0.045	0.036	2.64	0.29	0.082	0.092	0.004	0.004	0.005	0.054	(<0.001)	0.086	0.015	0.007	47 x 13
BS 20R	3.25	0.62	0.047	0.034	2.72	0.35	0.096	0.094	0.005	0.004	0.006	0.053	(<0.001)	0.104	0.015	0.007	47 x 19+
BS 20E	3.24	0.80	0.042	0.044	2.29	0.23	0.156	0.088	0.006	(0.003)	0.006	0.042	(<0.002)	0.093	0.017	0.007	47 x 19+
BS 20P	3.22	0.63	0.032	0.044	2.62	0.067	0.143	0.079	0.008	(0.004)	0.018	0.033	(<0.001)	0.099	0.018	0.017	44 x 19+

RM Si-Mo CAST IRON

BAS SIMO: 48 mm x 42 mm x 12 mm block

CTIF: each unit = one pair 43 mm Ø x 5 mm discs

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Ti	V	Co	As	Sn	Ce	Mg
CTIF SiMo-3	3.18	0.61	0.053	(0.0006)	4.02	0.0325	0.066	0.110	0.604	1.15	0.0176	0.0171	0.0296	.	.	.	0.013
CTIF SiMo-1	2.98	0.365	0.013	(0.0015)	4.03	0.035	0.065	0.036	0.752	.	(0.018)	(0.018)	(0.03)	.	.	.	0.019
CTIF SiMo-5	2.94	0.439	0.0282	.	4.31	0.0121	0.194	0.032	0.841	.	0.010	(0.0095)	(0.013)
CTIF SiMo-2	(2.85)	0.335	0.0260	(0.001)	3.85	0.036	(0.061)	0.038	1.04	1.51	(0.016)	(0.017)	(0.030)	.	.	.	0.072
BAS SIMO 1/3	2.70	0.333	0.040	0.007	4.07	0.028	0.030	0.899	0.776	0.026	0.007	0.007	0.013	0.047	0.048	.	0.036
CTIF SiMo-4	2.70	0.280	0.0211	(0.0015)	4.35	0.0657	(0.029)	0.0845	0.400	(0.038)	0.0171	0.0133	(0.015)	.	.	.	0.100
BAS SIMO 1/6	2.50	0.372	0.036	0.005	4.04	0.016	0.060	0.750	0.727	0.025	0.010	0.020	0.025	(0.001)	0.053	.	(0.002)
BAS SIMO 2/4	2.26	0.440	0.026	0.009	4.49	0.009	0.015	0.896	0.443	0.013	0.006	0.008	0.005	(0.002)	0.056	0.006	(0.002)
BAS SIMO 2/2	2.14	0.434	0.025	0.007	4.75	0.010	0.0189	0.856	0.484	0.013	0.005	0.009	0.0029	0.039	0.038	0.006	0.026
BAS SIMO 2/3	2.20	0.463	0.035	0.010	4.78	0.007	0.011	0.903	0.486	0.026	0.010	0.005	0.005	(0.001)	0.052	(0.001)	0.024

last

CAST IRON WITH MAGNESIUM - continued on the next page

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 20034 17b	4.38	0.501	0.089	0.0040	0.178	0.111	2.34	0.200	0.009	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17a	4.30	0.494	0.115	0.0034	0.170	0.082	2.38	0.200	0.007	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17c	4.08	0.503	0.104	0.0033	0.150	0.037	2.32	0.178	0.007	.	(0.002)	(0.003)	0.043	0.030	0.015	0.076
1	Y 2863-11A	4.03	0.61	0.613	0.026	0.79	0.96	0.46	1.65	0.008	0.94	0.30	0.079
2	CZ SPL17 43A	3.98	1.322	0.190	0.008	1.63	0.385	0.411	0.032	(0.04)	.	0.024	0.017	0.045	0.152	0.065	0.152
2	CZ SPL17 42A	3.94	0.764	0.294	0.0040	1.94	0.199	0.492	0.145	(0.06)	.	0.087	0.039	0.010	0.021	0.126	0.093
1	Y 451045	3.90	0.12	0.023	0.0027	2.29	0.022	0.45	0.028	0.033	0.0030	0.016	0.014
1	SCRM 668/14	3.77	0.702	0.045	0.0220	1.72	0.65	0.096	0.99	0.009	.	.	0.023	.	0.0179	0.086	0.195
1	Y 2863-12	3.77	0.158	0.053	0.057	0.150	0.55	0.192	2.31	0.0024	0.44	0.030	0.229
1	CZ 02033 2f	3.77	0.091	0.159	0.009	1.23	0.89	0.658	0.022	0.953	.	0.024	0.018	(0.003)	(0.002)	0.021	0.010
1	VS ChG 25/1	3.75	0.67	0.013	0.0048	1.46	0.81	0.406	0.214	0.0096	0.271	0.0087	0.0070
1	CZ 02033 3c	3.68	0.333	0.026	0.007	2.15	0.421	0.040	0.100	0.006	(0.005)	0.024	0.013	0.026	0.490	0.021	0.016
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	0.0838	0.0979	0.1069	0.0486
1	VS ChG 27/1	3.59	1.20	0.039	0.019	1.97	0.351	0.030	0.139	.	.	0.011	.	.	0.131	0.060	0.070
2	Y 4510058B-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.042	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058C-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.039	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058D-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.036	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058E-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.032	.	.	0.022	.	0.180	0.044	0.174
2	CZ SPL17 31A	3.54	0.041	0.025	0.006	2.10	0.005	0.538	0.019	0.070	.	0.005	(0.004)	0.022	0.004	0.007	0.008
2	CZ SPL17 34A	3.48	0.980	0.105	0.008	2.29	0.230	0.493	0.102	0.026	.	0.010	0.008	0.025	0.072	0.044	0.073
1	CZ 20034 15c	3.47	0.060	0.054	0.0028	1.68	1.123	0.728	0.078	0.040	.	0.010	0.030	0.026	(0.002)	0.036	0.019
2	CZ SPL17 32A	3.39	0.288	0.037	0.007	2.74	0.306	0.015	0.060	0.024	.	0.029	(0.004)	(0.002)	0.116	0.044	0.005
2	CZ SPL17 40A	3.38	0.042	0.021	0.0035	1.98	0.010	0.045	0.031	0.007	.	0.096	0.012	0.027	0.005	0.015	0.014
1	VS ChG 28	3.29	0.414	0.025	0.015	2.22	1.29	0.166	0.127	0.010	.	0.015	.	.	0.0024	0.0041	0.0020
1	VS ChG 28/1	3.28	0.420	0.039	0.008	2.14	1.30	0.177	0.177	0.014	.	0.0097	.	.	.	0.019	0.013
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 02033 1f	3.23	0.693	0.043	0.005	2.68	0.018	0.373	0.035	0.070	(0.007)	0.073	0.036	0.024	0.182	0.041	0.014
1	CZ 20034 13c	3.15	0.704	0.0261	0.0044	2.23	0.089	1.299	0.124	0.064	.	0.022	0.011	0.024	0.360	0.015	0.043
1	CZ 20034 14c	3.14	0.275	0.0162	0.0081	2.49	0.585	0.030	0.045	0.017	.	0.007	0.019	0.009	0.646	0.018	0.013
1	CZ 20034 13a	3.13	0.691	0.0244	0.0046	2.19	0.021	1.266	0.122	0.053	.	0.017	0.011	0.024	0.364	0.014	0.048
1	CZ 20034 13b	3.12	0.692	0.0243	0.0041	2.12	0.021	1.313	0.125	0.054	.	0.019	0.011	0.024	0.364	0.012	0.048
1	BS CC-11A	3.07	1.23	0.020	0.011	1.90	0.007	0.046	0.048	0.014	0.026	0.0055	0.018	(0.007)	0.0063	0.0091	0.0066
1	VS ChM5/1	3.04	0.311	0.056	0.016	1.37	.	.	.	0.045	.	0.013
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	0.070	.	.	0.110	.	.	.	0.103
1	VS ChG 24/1	3.04	0.280	0.237	0.007	2.40	0.104	0.85	0.030	0.021	.	0.027	0.021	.	0.028	0.089	0.026
1	VS ChM6/1	3.03	0.54	0.055	0.0074	2.75	.	.	.	0.072	.	0.022
2	CZ SPL17 36A	3.02	0.057	0.026	0.010	2.13	0.007	0.011	0.014	0.012	.	(0.003)	0.0007	(0.004)	0.004	0.021	0.021
1	BS CC-11B	2.97	1.17	0.020	0.008	1.94	0.0210	0.173	0.189	0.025	0.019	0.028	0.045	(0.022)	0.018	0.031	0.0179
1	VS ChM13	2.96	1.05	0.043	0.009	2.98	0.062	1.65	0.273	0.09	.	0.065	.	.	.	0.018	0.0096
1	VS ChG 26/1	2.96	0.132	0.104	0.0058	2.89	0.022	1.41	0.050	0.052	.	0.041	0.017	.	0.070	0.016	0.159
1	SCRM 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	0.0224	.	.	0.0415	.	0.0550	0.0499	0.532
1	VS ChG 26	(2.9)	0.126	0.123	0.0041	2.98	0.014	1.52	0.050	0.044	.	0.038	.	.	0.075	0.0026	0.040
1	VS ChM10	2.89	0.43	0.067	0.017	1.13	0.082	0.85	0.067	0.024	.	0.005	.	.	.	0.028	0.079
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	0.032	.	(0.007)	0.016	.	0.86	(0.04)	0.019
2	CZ SPL17 33A	2.75	0.710	0.060	0.007	3.10	0.730	0.389	0.239	0.021	.	0.054	0.026	0.015	0.220	0.130	0.356
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	0.006	.	<0.01	0.0046	(0.05)	0.019	0.050	0.083
1	VS ChM9	2.61	1.28	0.075	0.021	1.59	0.095	0.38	0.083	0.011	.	0.016	.	.	.	0.027	0.068
1	VS ChM11	2.26	0.77	0.032	0.011	2.32	0.067	1.75	0.122	0.066	.	0.035	.	.	.	0.014	0.0044
1	Y 2863-7	1.98	3.42	0.067	0.0061	3.10	0.089	4.47	0.150	0.050	.	.	0.019	.	0.052	0.060	0.87
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V

BS: 28-34 mm Ø x 17-35 mm

CKD 24x: 37 mm x 37 mm x ~15-20 mm
CZ: 40 mm Ø x 18 mmSCRM: 48 mm x 42 mm x 12 mm
SRM: 32 mm Ø x 19 mmVS: ~40 mm Ø x ~40 mm
Y: 30 mm Ø x 30 mm

CAST IRON WITH MAGNESIUM - continued from the previous page

sizes shown below

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ 20034 17b	0.008	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17a	0.007	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17c	0.0005	(0.0006)	(0.002)	(0.002)	.	.	(0.002)	0.004	.	.
Y 2863-11A	(0.022)	0.053	0.34	(0.0057)	(0.174)	.	(0.108)	0.010	.	30mm Ø x 28mm
CZ SPL17 43A	.	0.0014	(0.002)	.	.	.	0.008	0.014	(0.004)	.	0.067	0.038	Zn:0.013	.
CZ SPL17 42A	.	0.0036	(0.002)	.	.	.	0.045	0.020	0.015	.	0.027	0.020	Zn:0.013	.
Y 451045	last
SCRM 668/14
Y 2863-12	(0.0097)	0.0078	0.21	(0.056)	(0.471)	.	(0.307)	0.13	.	.
CZ 02033 2f	.	0.0020	(0.002)	0.005	0.028	.	0.014	(0.003)	(0.005)	Zn: 0.018
VS ChG 25/1	0.067	.	0.011	.	.	.
CZ 02033 3c	(0.007)	0.0044	(0.002)	0.005	.	.	0.009	(0.003)	.	.
SCRM 666/12
VS ChG 27/1	0.036	.	0.125	.	.	.
Y 4510058B-18	0.0021	0.024
Y 4510058C-18	0.0021	0.024
Y 4510058D-18	0.0021	0.024
Y 4510058E-18	0.0021	0.024	last
CZ SPL17 31A	.	(0.0004)	(0.003)	(0.005)	.	.
CZ SPL17 34A	.	0.0076	(0.005)	.	.	.	0.014	(0.006)	0.007	.	0.051	0.016	Zn:0.007	.
CZ 20034 15c	(0.003)	0.0057	0.008	0.056	.	0.006	0.004	.	.
CZ SPL17 32A	.	(0.0005)	(0.007)	0.022	0.023	.	(0.012)	(0.008)	Zn:0.011	.
CZ SPL17 40A	.	0.0008	(0.004)	.	Zn:(0.002)	.
VS ChG 28	0.015	.	0.0017	.	.	.
VS ChG 28/1	0.0017	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ 02033 1f	.	0.0043	(0.001)	0.009	.	.	0.030	0.022	(0.008)	last
CZ 20034 13c	(0.002)	(0.002)	.	0.014	(0.003)	(0.02)	.
CZ 20034 14c	0.035	0.0123	0.020	.	0.025	(0.003)	0.013	Zn: 0.010
CZ 20034 13a	(0.002)	(0.002)	.	0.014	(0.003)	0.029	.
CZ 20034 13b	(0.002)	(0.002)	.	0.014	(0.003)	0.023	.
BS CC-11A	0.0018	0.0008	(0.005)	(0.0009)	93.6	(0.004)	(0.007)	(0.002)	(0.01)	Zn:0.0032	(0.004)	(0.017)	(0.0025)	17034
VS ChM5/1
SCRM 667/13
VS ChG 24/1	0.011	.	0.081	.	.	.
VS ChM6/1
CZ SPL17 36A	.	0.022	(0.007)	0.016	.	.	(0.002)	.	Zn:(0.002)	.
BS CC-11B	0.0074	0.0033	(0.016)	(0.002)	93.2	(0.008)	0.043	0.014	0.026	Zn:0.008	0.021	0.028	0.0165	17034
VS ChM13
VS ChG 26/1	0.0055	.	0.034	.	.	.
SCRM 669/14
VS ChG 26	0.031	.	.	.
VS ChM10
SRM C1137a
CZ SPL17 33A	.	0.0064	(0.002)	.	.	.	0.032	0.010	0.019	.	0.039	0.079	Zn:0.009	.
SRM C2424	.	(0.002)	.	.	.	0.0011
VS ChM9
VS ChM11
Y 2863-7	(0.021)	0.100	0.041	(0.0025)	(0.010)	.	(0.0073)	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
--------	----	---	----	----	----	----	----	----	----	----	----	---	----	-------

BS: 28-35 mm Ø x 17-35 mm

CZ: 40 mm Ø x 18 mm
SCRM: 48 mm x 42 mm x 12 mm

SRM: 32 mm Ø x 19 mm
Y: 30-35 mm Ø x 18-30 mm

VS ChM: ~39 mm Ø x ~39 mm
VS ChG: ~34 mm x ~35 mm X ~22 mm

RM CAST IRON WITH YOUR CHOICE OF MAGNESIUM LEVELS each unit: 2 pcs mushroom 43 mm Ø x 5 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Al	Ce	Co	Sn	Ti	V	Zn	Other
CTIF 6134	3.70	0.25	0.030	<0.01	1.60	0.020	2.00	0.040	*	.	<0.03
CTIF 8532	3.7	0.288	0.05	.	2.6	0.0443	0.888	0.04	*	.	<0.025	.	0.0303	0.02	0.07	.	.
CTIF 6135	3.6	0.38	0.0130	(0.003)	0.9	0.0219	1.98	0.04	*	(0.006)	.	0.037	.	0.007	0.0155	.	.
CTIF 4500	3.38	0.60	0.059	(0.002)	1.97	.	1.45	0.014	*	0.033	0.023	0.065
CTIF 5781	3.35	0.26	0.030	(0.0025)	2.50	0.0061	0.83	0.040	*	.	.	(0.004)	.	0.0208	0.0150	.	.
CTIF 4497	3.12	0.605	0.043	(<0.002)	2.66	0.048	1.90	0.040	*	.	.	.	0.094	0.031	0.44	.	.
CTIF 7160	3.1	0.57	0.05	(0.001)	2.4	0.08	1.0	(0.1)	*	(0.02)	0.02	0.09	.	0.013	0.018	.	As: 0.009
CTIF 5037	3.04	0.76	0.043	(0.0025)	3.40	.	0.64	0.014	*	0.029	.	.	.
CTIF 3601B	3.0	0.35	0.037	(0.005)	2.1	0.019	1.08	0.029	*	.	<0.01	.	.	0.016	(0.005)	<0.05	Pb: (<0.002)
CTIF 8018	3.0	0.7	0.07	(0.0015)	3.0	0.08	0.127	0.09	*	0.02	(<0.02)	.	0.07	0.06	0.39	.	Sb: (0.01)
CTIF 6736	2.8	0.65	0.012	(0.002)	1.6	0.0258	1.7	0.03	*	0.008	(0.03)	.	.
CTIF 5783	2.55	0.2	0.0266	(0.003)	2.3	0.110	1.23	0.05	*	.	.	0.0074	.	0.015	0.0127	.	As: 0.0016

Magnesium level available in the below samples. X = available

For Mg Range	Order Suffix	3601B	4497	4500	5037	5781	5783	6134	6135	6736	7160	8018	8532
<0.005	<0.005	X	.	.	.	X	X	X	X
0.005 - 0.009	0.005	X	.	.	X	X	X	.	.	X	.	X	X
0.010 - 0.014	0.01	.	.	.	X	X	X	.	.	X	X	X	.
0.015 - 0.024	0.02	X	.	.	X	X	X	.	X	X	X	X	.
0.025 - 0.034	0.03	.	.	.	X	.	X	.	X	X	X	X	.
0.035 - 0.044	0.04	.	.	.	X	.	X	.	X	X	X	X	.
0.045 - 0.054	0.05	.	.	.	X	.	X	.	X	X	X	X	.
0.055 - 0.064	0.06	.	X	.	.	.	X	.	X	X	X	X	.
0.065 - 0.074	0.07	.	X	X	.	.	X	.	X	X	X	X	.
0.075 - 0.084	0.08	.	.	X	.	.	X	.	X	X	X	X	.
0.085 - 0.094	0.09	.	X	X	.	.	X	.	X	X	X	X	.
0.095 - 0.104	0.10	X	.	X	X	X	X	.
0.105 - 0.114	0.11	X	X	X	X	X	.
0.115 - 0.124	0.12	X	X	X	X	X	.
0.125 - 0.134	0.13	X	X	X	X	X	.
0.135 - 0.144	0.14	X	.	.	X	.	.
0.145 - 0.154	0.15	X	.	.
0.155 - 0.164	0.16	X	.	.
0.165 - 0.174	0.17	X	.	.
0.175 - 0.184	0.18

The above cast iron samples can be ordered with your choice of Magnesium. Examples:
to order CTIF 6736 with Mg 0.035 - 0.044 then order as part number CTIF 6736 0.04
to order CTIF 8018 with 0.08 % Mg, order as part number CTIF 8018 0.08

CRM WHITE IRON analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	Nb	Ti	V	
BS WI-2	3.61	0.80	0.22	0.056	0.52	0.0124	0.254	0.229	0.0118	0.219	0.128	0.089	0.215	17025
SRM CII45	2.92	0.187	0.215	0.191	0.271	0.46	0.62	0.63	0.058	0.48	.	0.012	0.112	
VS ChG 10/6	(2.7)	0.86	0.103	0.0072	2.86	.	.	(0.2)	(0.3)	
VS ChG 11/6	(2.7)	0.312	0.23	0.039	1.79	.	.	(0.2)	(0.3)	
VS ChG 9/6	(2.7)	0.155	0.38	0.071	0.80	.	.	(0.2)	(0.3)	
BS WI-1	1.75	0.24	0.051	0.114	1.90	0.027	0.053	0.048	0.0074	0.0103	0.027	0.020	0.008	17025

Number	Al	As	B	Bi	Ca	Fe	Mg	Pb	Sb	Sn	W	Zr	Units
BS WI-2	0.0192	0.0016	0.0008	.	(0.00013)	[93.6]	(0.0002)	0.013	0.023	0.0042	0.023	0.0045	~35 mm Ø x ~30 mm
SRM CII45	(0.04)	(0.03)	(0.02)	(<0.01)	.	.	.	0.0012	(0.04)	(0.10)	.	(0.002)	32 mm Ø x 19 mm
VS ChG 10/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 11/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 9/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
BS WI-1	0.075	0.0067	0.0032	.	0.0005	[95.5]	0.0009	0.115	.	0.0081	0.185	0.0034	~35 mm Ø x ~30 mm

CAST IRON

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Ce	La	Mg	Se	Te
1	MBH-FEPIGH-21	4.42	0.127	0.050	0.141	1.60	0.0113	0.040	0.088	0.20	0.018
1	NCS AH11112	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	.	.	0.032	.	.
1	NCS HS11799	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	0.012	0.0064	0.032	.	.
2	CZ SPL22 47A	3.82	0.084	0.137	0.011	1.07	0.82	0.606	0.016	0.024	(0.002)	0.010	.	0.035	.	.
1	VS ChG 56	(3.8)	(0.2)	(0.8)	(0.01)	(0.5)	(0.4)	(0.1)	(0.1)	(0.01)	(0.005)
1	VS ChG 57	(3.8)	(0.2)	1.17	(0.03)	(0.6)	(0.3)	(0.3)	(0.4)	(0.06)	(0.01)
1	NCS HS11798	3.78	0.606	0.053	0.020	2.73	0.526	0.856	0.700	0.042	.	0.0097	0.0042	(0.034)	.	.
1	SCRM 660/11	3.62	0.444	0.137	0.115	1.74
2	CZ SPL22 46A	3.66	0.098	0.109	0.010	1.42	0.86	0.628	0.014	0.026	.	0.005	.	0.047	.	.
2	CZ SPL22 48A	3.63	0.338	0.025	0.006	2.15	0.407	0.043	0.128	0.021	0.025	0.009	.	0.019	.	.
1	NCS HS92744c	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	.	.	0.022	.	0.042	.	.
1	NCS HS92746a	3.59	0.226	0.046	0.012	2.25	0.263	0.501	0.097	0.014	.	.	.	0.029	.	.
2	CZ SPL22 53A	3.56	0.052	0.053	0.0097	1.60	1.357	0.687	0.071	0.047	0.032	0.023	.	0.032	.	.
2	CZ SPL22 51A	3.46	0.405	0.147	0.004	1.63	0.152	0.111	0.075	0.006	0.035
2	CZ SPL22 50A	3.39	0.529	0.179	0.055	2.14	0.151	0.113	0.137	0.004	0.029
2	CZ SPL22 45A	3.33	0.778	0.031	0.010	2.83	0.008	0.405	0.058	0.078	0.031	0.032	.	0.066	.	.
1	MBH FEPIGM-21	3.22	0.077	0.051	0.053	0.71	0.0117	0.028	0.057	0.060	0.015
2	CZ SPL22 44A	3.20	0.711	0.033	0.005	2.51	0.018	0.521	0.063	0.046	0.024	0.005	.	0.015	.	.
1	NCS AH11353	3.15	0.47	0.020	0.0006	2.30	0.029	0.59	0.025	0.023	0.015	.	.	0.029	.	.
2	CZ SPL22 49A	3.12	0.328	0.038	0.009	2.06	0.384	0.132	0.300	0.064	0.094	(0.005)	.	0.007	.	.
1	SCRM 658/13	3.106	0.563	0.259	0.0547	1.973
1	Y 2863-9A	3.04	1.43	0.049	0.015	1.53	0.269	1.59	0.72	.	0.042
2	CZ SPL22 52A	3.03	0.301	0.021	0.0094	2.38	0.607	0.021	0.025	0.011	0.010	0.012	.	0.008	.	.
1	BS CC-23	2.96	0.73	0.53	0.082	0.43	0.307	0.56	0.467	0.060	0.090	(0.0006)	(0.0008)	(0.0006)	.	(0.03)
1	TIIX C1-22	2.78	1.28	0.098	0.048	1.41	0.179	0.588	0.293	0.0131	0.086	.	.	.	(0.003)	.
1	MBH FePIGL-21	1.69	0.218	0.052	0.004	0.335	0.0041	0.014	0.0209	0.0154	0.0114
2	MBH FePIGL-RM	1.6	0.17	0.051	0.004	0.12	0.003	0.013	0.017	0.004	0.011	no uncertainties				.

Number	As	B	Bi	Fe	Mo	Nb	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units in mm
MBH-FEPIGH-21	0.0015	.	.	.	0.027	0.019	.	.	0.0075	0.42	0.108	(0.004)	.	0.0039	~40 Ø x ~15
NCS AH11112	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
NCS HS11799	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
CZ SPL22 47A	.	(0.0005)	.	.	(0.002)	.	0.012	0.026	0.016	0.027	0.007	0.004	0.027	(0.010)	40 Ø x 18
VS ChG 56	0.18	(0.001)	.	.	(0.01)	(0.002)	.	0.014	.	(0.06)	(0.02)	(0.004)	.	.	~37 Ø x ~17
VS ChG 57	0.095	(0.002)	.	.	(0.01)	(0.004)	.	(0.001)	(0.01)	(0.08)	(0.04)	(0.01)	.	.	~37 Ø x ~17
NCS HS11798	0.359	.	.	0.025	0.032	0.117	0.018	.	.	.	31 Ø x 30
SCRM 660/11	48 x 42 x 12
CZ SPL22 46A	(0.003)	0.0021	0.005	.	0.011	(0.012)	0.021	0.024	0.014	0.046	0.008	0.008	0.018	(0.004)	40 Ø x 18
CZ SPL22 48A	(0.021)	0.0045	.	.	0.482	.	0.015	.	0.010	0.030	0.016	.	.	.	40 Ø x 18
NCS HS92744c	0.0021	0.024	.	.	0.180	0.044	0.174	.	.	.	35 Ø x 30
NCS HS92746a	(0.003)	0.0086	.	.	0.214	.	.	.	0.040	0.033	35 Ø x 30
CZ SPL22 53A	(0.004)	0.0046	(0.007)	.	0.002	.	.	0.066	0.007	0.035	0.013	0.010	(0.004)	.	40 Ø x 18
CZ SPL22 51A	(0.007)	.	(0.008)	.	0.037	.	0.006	0.012	0.072	0.033	0.017	(0.005)	(0.002)	.	40 Ø x 18
CZ SPL22 50A	.	(0.0008)	0.011	.	0.045	.	0.004	0.011	0.068	0.030	0.015	(0.006)	.	.	40 Ø x 18
CZ SPL22 45A	.	0.022	.	.	0.182	.	0.005	.	0.034	0.079	0.022	0.015	.	(0.015)	40 Ø x 18
MBH FEPIGM-21	(0.0018)	.	.	.	0.0157	0.014	.	.	0.0061	0.258	0.071	(0.003)	.	0.0022	~40 Ø x ~15
CZ SPL22 44A	.	0.0037	0.009	.	0.174	(0.014)	0.017	0.018	0.026	0.084	0.014	0.018	0.009	(0.007)	40 Ø x 18
NCS AH11353	0.008	0.004	.	.	0.002	N:0.003	.	0.0005	0.003	0.027	0.032	0.003	.	.	30 Ø x 25
CZ SPL22 49A	0.020	0.0075	.	.	0.475	(0.005)	0.008	(0.007)	0.011	0.024	0.081	0.013	(0.003)	.	40 Ø x 18
SCRM 658/13	48 x 42 x 12
Y 2863-9A	(0.041)	0.153	.	.	1.38	0.11	(0.093)	(0.116)	(0.124)	0.212	0.41	.	.	.	30 Ø x 18-30
CZ SPL22 52A	0.041	0.0082	0.011	.	0.621	(0.003)	(0.003)	0.014	0.032	0.029	0.023	(0.004)	0.004	0.015	40 Ø x 18
BS CC-23	0.016	0.067	.	(92.8)	0.267	(0.002)	0.008	0.17	0.052	0.091	0.195	(0.002)	17025	0.057	~32 Ø x ~17
TIIX C1-22	0.0145	0.031	0.0048	N:0.013	0.034	0.080	(0.003)	0.048	0.049	0.103	0.142	0.104	.	0.0028	disc 17034
MBH FePIGL-21	0.0023	0.007	.	.	0.0028	0.0048	0.0184	0.0015	.	.	disc
MBH FePIGL-RM	0.003	0.002	0.015	.	.	.	disc

CAST IRON WITH C < 2.75%

= Class, 1 = CRM and 2 = RM

analysis in mass % except * = mg/kg

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	VS ChL4/1	2.69	1.37	0.054	0.027	1.99	0.161	0.725	0.92	.	0.017	0.116	.	.	0.11	0.258	.
1	SRM C1291	2.67	1.14	0.028	0.032	1.34	0.26	4.34	2.78	.	.	0.32	.	.	.	0.031	.
1	VS ChG 6/9	2.65	0.83	0.54	0.027	0.53	0.34	.	0.241	0.028	0.130	.
1	DSZU CH01	2.61	0.258	0.012	0.0045	1.95	0.097	0.072	0.88	0.079	(0.06)	0.070	(0.010)	(0.05)	0.132	0.134	.
1	VS ChG 40	2.59	1.56	0.059	0.019	1.60	0.98	1.61	1.47	.	.	0.229	.	.	0.18	0.325	.
1	11X C8V	2.60	0.394	1.00	0.204	1.643	0.310	0.275	0.148	0.086	0.126	0.148	0.0217	0.1063	0.235	0.064	0.0068
1	SCRM 661/4	2.56	0.30	0.84	0.068	2.96	.	.	(1)
1	SCRM 656/9	2.537	0.820	0.060	0.108	2.504
1	Y 2863-2	2.50	1.83	0.069	0.026	3.14	0.020	3.73	0.136	.	.	0.096	.	.	0.066	0.61	.
1	VS ChG 37	2.49	0.92	0.038	0.046	2.03	0.512	0.90	0.82	.	.	0.55	.	.	0.092	0.227	.
1	SCRM 673/1	2.455	0.123	0.317	0.0112	1.702	.	0.103	0.0423	0.0287	0.053	0.0092	.	0.0206	0.0718	0.052	.
1	CZ 20034 11b	2.44	0.382	0.271	0.140	3.67	0.130	0.082	1.178	0.067	0.005	1.144	.	0.074	0.041	0.182	.
1	VS ChG 38	2.43	0.302	0.386	0.084	2.30	1.20	0.162	1.98	.	.	0.046	.	.	0.105	0.119	.
1	CZ 02033 5b	2.42	0.812	0.033	0.073	1.32	0.031	0.188	0.061	0.062	.	0.089	.	.	0.007	0.005	.
1	VS ChL2/1	2.38	1.03	0.054	0.023	0.55	0.97	0.114	0.077	.	0.013	0.012	.	.	0.009	0.050	.
1	CZ 20034 11a	2.37	0.343	0.271	0.163	3.31	0.086	0.084	1.219	0.046	0.005	1.130	.	0.070	0.028	0.184	.
1	DSZU CH07	2.33	1.36	0.090	0.064	3.01	0.35	0.403	0.34	0.036	.	0.66	(0.08)	(0.07)	0.150	0.52	.
1	CZ 02033 5c	2.30	0.704	0.027	0.091	1.40	0.013	0.188	0.085	0.103	0.013	0.104	.	(0.002)	0.008	0.054	.
1	11X C4S	1.954	0.565	0.1014	0.096	2.98	0.095	3.21	1.382	0.006	0.0210	0.177	0.0233	(0.0140)	0.080	0.0165	0.0037
1	SCRM 675	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	0.007	0.178	0.0006
1	SCRM 655/4	1.90	0.44	0.180	0.076	2.110	.	.	(1)
1	Y 2863-1	1.78	2.41	0.021	0.009	3.62	0.022	4.77	0.031	.	.	0.038	0.0052	.	0.068	1.13	.

Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
VS ChL4/1	~38 mm Ø x ~38 mm
SRM C1291	32 mm Ø x 19 mm
VS ChG 6/9	(0.003)	~38 mm Ø x ~40 mm
DSZU CH01	.	(0.03)	.	(10)	.	(0.0005)	(0.02)	.	~30 mm x ~35 mm
VS ChG 40	~34 mm Ø x ~37 mm
11X C8V	0.0812	0.0366	0.014	.	.	.	0.0065	0.0052	0.069	0.0210	0.0049	0.0258	0.0064	~40 mm Ø x ~15 mm
SCRM 661/4	48 mm x 42 mm x 12 mm
SCRM 656/9	48 mm x 42 mm x 12 mm
Y 2863-2	.	0.0025	30 mm Ø x 18-30 mm
VS ChG 37	~34 mm Ø x ~37 mm
SCRM 673/1	40 mm x 37 mm x 10 mm
CZ 20034 11b	0.005	0.0032	0.007	0.007	0.011	.	.	(0.005)	0.007	40 mm Ø x 18 mm
VS ChG 38	~34 mm Ø x ~37 mm
CZ 02033 5b	.	0.014	0.020	40 mm Ø x 18 mm
VS ChL2/1	~38 mm Ø x ~38 mm
CZ 20034 11a	0.005	0.0018	0.011	0.017	0.013	.	.	(0.005)	0.007	40 mm Ø x 18 mm
DSZU CH07	.	(0.13)	.	(10)	.	(0.01)	~35 mm x ~35 mm x ~19mm
CZ 02033 5c	.	0.0078	0.007	(0.002)	(0.010)	.	(0.009)	40 mm Ø x 18 mm
11X C4S	0.0235	0.0351	0.0070	.	.	.	0.0126	0.034	0.0055	0.009	.	0.099	.	~40 mm Ø x ~15 mm
SCRM 675	0.035	40 mm x 37 mm x 10 mm
SCRM 655/4	48 mm x 42 mm x 12 mm
Y 2863-1	.	0.0024	30 mm Ø x 18-30 mm

ALLOYED CAST IRON, CHART 1 of 2

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
2	DSZU CH021	3.93	3.66	0.064	0.009	0.52	0.369	5.86	9.07	0.168	4.42	.	.	0.093	0.61	.	.
1	VS CHG 41/1	3.88	1.23	0.037	0.090	1.77	0.56	5.84	8.7	.	0.50	.	.	0.21	0.25	.	.
2	BAS NCRM5	3.70	0.27	0.025	0.015	1.15	0.204	6.74	10.44	.	0.10	.	.	.	0.06	.	.
1	SRM C1292	3.47	0.55	0.049	0.016	0.59	0.36	5.04	11.4	.	0.25	.	.	.	0.041	.	.
2	BAS CRRM5/2	3.43	0.30	0.029	0.018	0.20	0.22	0.36	30.35	0.15	0.63	.	.	0.009	0.11	.	.
1	Y 451052-1	3.31	1.54	0.369	0.0047	0.098	0.449	2.57	1.17	.	1.47	.	.	.	0.952	.	.
1	BS PM15	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0025	1.22	(0.00001)	0.0034	0.0029	14.79	(0.0002)	0.111
1	VS CHG 48	3.44	0.100	0.0070	0.0039	0.923	0.90	0.280	22.79	0.049	0.591	.	0.0018	0.0022	0.0016	0.072	.
1	VS CHG 44/1	3.25	1.91	0.018	0.029	1.28	2.46	0.210	25.4	.	0.028	.	.	0.43	0.106	.	.
1	11X 15309T	3.18	1.53	0.034	0.021	1.22	0.056	0.152	24.9	0.097	0.066	.	0.0047	0.013	0.098	.	.
1	Y 451052-7	3.13	0.201	0.024	0.116	2.48	0.154	0.129	31.26	.	0.086	.	.	0.033	0.087	.	.
2	58A SC01141	3.08	0.62	0.045	0.036	0.56	0.77	1.21	15.32	.	2.70	.	.	0.020	0.28	.	.
1	SRM C1290	3.04	0.66	0.030	0.013	0.971	0.065	0.917	30.5	.	(0.041)	.	.	.	0.442	.	.
1	Y TSK205	3.03	0.16	0.041	0.088	1.65	0.35	0.37	30.35	.	0.22	.	.	.	0.077	.	0.108
1	Y 451054-2	3.00	1.42	0.133	0.016	0.56	0.324	1.43	7.23	.	2.48	.	.	0.015	0.88	.	.
1	NCS HS11788	2.97	1.62	0.191	0.010	3.29	0.51	17.77	2.56	(0.0023)	0.0013	.	0.0003	0.043	0.017	.	.
1	Y 451052-2	2.96	1.24	0.211	0.0077	0.491	1.57	1.99	9.75	.	2.17	.	.	0.300	0.669	.	.
2	BAS NIRM5/1	2.95	1.01	0.103	0.005	1.50	0.21	21.7	0.51	0.055	.	.
2	58A ZS01036	2.95	0.719	0.077	0.024	0.970	0.448	0.806	13.89	.	0.683	.	0.048	0.035	0.135	.	.
2	BAS NIRM2/2	2.94	2.01	0.096	0.007	1.43	5.93	13.69	1.48	0.044	.	.
2	BAS CRRM4/2	2.93	0.58	0.049	0.042	0.45	0.53	0.58	21.93	<0.005	1.15	.	.	0.008	0.11	.	.
2	11X 20003K	2.91	1.53	0.174	0.007	3.03	0.52	17.8	2.53
1	11X S/1 Cr3J	2.91	0.861	0.072	0.023	1.07	9.01	14.53	1.61
2	DSZU CH022	2.90	1.76	0.033	0.018	0.43	2.53	2.19	14.85	0.053	2.65	.	.	0.078	0.45	.	.
2	11X 20001J	2.90	0.58	0.005	0.143	1.01	0.01	21.4	1.50
1	11X 15294W	2.76	0.451	0.082	0.029	0.36	0.103	0.309	29.3	(0.147)	0.091	0.012	0.036	.	0.132	.	.
1	Y 451054-3	2.73	1.09	0.105	0.036	0.99	0.451	1.20	12.97	.	2.08	.	.	0.045	0.66	.	.
1	VS CHG 45	(2.7)	1.01	0.096	0.047	2.96	0.040	0.60	32.65	.	0.198	.	.	0.011	0.111	.	.
1	VS CgG 42/1	2.69	2.78	0.068	0.034	0.411	1.37	0.26	14.8	.	1.87	.	.	0.131	0.48	.	.
2	BAS NCRM4	2.66	0.40	0.203	0.012	2.13	0.68	5.34	7.94	.	0.57	.	.	.	0.11	.	.
1	NCS HS11787	2.65	1.08	0.067	0.037	2.07	0.306	19.84	1.98	(0.085)	0.0014	.	0.0054	0.022	0.0096	.	.
1	11X 15310B	2.63	0.97	0.070	0.029	0.99	2.37	4.59	20.7	0.018	0.92	.	.	0.034	0.096	.	.
1	11X 0331-2M	2.62	1.85	0.050	(0.09)	3.14	6.68	15.1	1.54	0.137	0.067	0.019	0.0271	0.198	0.051	.	.
1	11X 15295S	2.58	1.02	0.059	0.048	0.783	0.213	0.326	28.5	0.122	0.363	0.008	0.026	0.008	0.270	.	.
1	Y TSK201	2.56	1.07	0.253	0.023	0.66	1.53	2.44	10.14	.	2.56	.	.	.	0.42	.	0.029
2	BAS NIRM6/1	2.53	4.07	0.225	0.049	2.68	0.11	26.9	1.02	.	0.51
2	BAS NIRM3	2.51	0.51	0.208	0.096	2.21	1.00	17.8	2.43	0.29	.	.
1	VS CHG 47	2.43	0.949	0.099	0.083	2.73	0.0104	0.149	14.45	0.0056	0.0019	.	0.093	0.041	0.129	.	.
1	VS CHG 45/1	1.96	0.59	0.021	0.0091	3.08	0.056	0.95	33.8	.	0.209	.	.	.	0.21	.	.
1	VS CHG 43/1	0.87	1.02	0.063	0.076	4.44	0.171	0.439	23.7	.	0.107	.	.	0.033	0.040	.	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
---	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	---	----	---

Number	B	Ce	Co	Nb	W	Zr	Units	Other
--------	---	----	----	----	---	----	-------	-------

DSZU CH021	35 mm x 35 mm x 16 mm	
VS CHG41/1	~37 mm Ø x ~22 mm	
BAS NCRM5	40 mm x 37 mm x 10 mm	
SRM C1292	32 mm Ø x 19 mm	
BAS CRRM5/2	48 mm x 42 mm x 12 mm	

Y 451052-1	0.177	.	.	0.018	0.015	.	30 mm Ø x 18-30 mm	
BS PM15	.	.	0.0330	0.014	0.109	(0.0005)	38 mm Ø x 19+ mm	17025 Fe:[73.0] As:0.0040 N:0.111 O:0.0129
VS CHG 48	As:0.0021	.	0.044	.	.	Sb:0.0017	~35 mm Ø x ~17 mm	
VS CHG44/1	~37 mm Ø x ~22 mm	
11X 15309T	.	.	0.76	0.056	0.022	.	~40 mm Ø x ~15 mm	

Y 451052-7	0.015	.	.	0.010	0.175	.	30 mm Ø x 18-30 mm	
58A SC01141	~35 mm Ø x ~30 mm	
SRM C1290	32 mm Ø x 19 mm	
Y TSK205	35 mm Ø x 18-30 mm	
Y 451054-2	30 mm Ø x 18-30 mm	

NCS HS11788	0.0008	.	(0.0063)	.	(0.0002)	.	31 mm Ø x 28 mm	As: 0.014
Y 451052-2	0.142	.	.	0.182	1.99	.	30 mm Ø x 18-30 mm	
BAS NIRM5/1	.	0.016	.	0.15	.	.	48 mm x 42 mm x 12 mm	
58A ZS01036	.	.	0.024	0.025	0.172	.	~32 mm Ø x ~30 mm	As: (0.003)
BAS NIRM2/2	.	0.018	48 mm x 42 mm x 12 mm	

BAS CRRM4/2	48 mm x 42 mm x 12 mm	
11X 20003K	40 mm Ø x 15 mm	
11X S/1 Cr3J	~40 mm Ø x ~15 mm	
DSZU CH022	35 mm x 35 mm x 16 mm	
11X 20001J	40 mm Ø x 15 mm	

11X 15294W	.	.	0.128	.	0.265	.	~40 mm Ø x ~15 mm	
Y 451054-3	30 mm Ø x 18-30 mm	
VS CHG45	~36 mm x ~36 mm Ø x ~18 mm	last
VS CHG42/1	~37 mm Ø x ~22 mm	
BAS NCRM4	40 mm x 37 mm x 10 mm	

NCS HS11787	0.0007	.	(0.0054)	.	(0.0002)	.	31 mm Ø x 28 mm	As: 0.0075
11X 15310B	.	.	0.157	.	0.188	.	~40 mm Ø x ~15 mm	
11X 0331-2M	.	.	0.179	0.134	0.004	0.0022	~40 mm Ø x ~15 mm	
11X 15295S	.	.	1.55	0.091	0.202	(0.0012)	~40 mm Ø x ~15 mm	
Y TSK201	35 mm Ø x 18-30 mm	

BAS NIRM6/1	.	0.006	48 mm x 42 mm x 12 mm	
BAS NIRM3	.	0.007	.	0.09	.	.	40 mm x 37 mm x 10 mm	
VS CHG 47	As:0.014	.	0.0042	.	.	Sb:0.040	~35 mm Ø x ~17 mm	
VS CHG45/1	~37 mm Ø x ~22 mm	
VS CHG43/1	~37 mm Ø x ~22 mm	

Number	B	Ce	Co	Nb	W	Zr	Units	Other
--------	---	----	----	----	---	----	-------	-------

ALLOYED CAST IRON, CHART 2 of 2

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
1	Y 451052-3	2.40	1.06	0.115	0.015	0.821	0.953	1.55	13.30	.	0.869	.	.	0.171	0.482	.	.
2	BAS CRRM3/2	2.37	0.92	0.073	0.087	1.21	1.09	1.35	18.78	0.102	1.58	.	.	0.015	0.042	.	.
2	DSZU CH023	2.33	0.43	0.023	0.073	0.98	0.054	0.715	23.45	0.255	1.46	.	.	0.38	0.288	.	.
1	Y 451054-4	2.31	0.725	0.071	0.046	1.40	0.739	0.914	17.60	.	1.44	.	.	0.084	0.46	.	.
1	Y TSK200	2.11	0.82	0.319	0.022	0.17	1.86	3.22	4.97	.	3.50	.	.	.	0.60	.	0.021
2	DSZU CH024	2.01	1.22	0.102	0.037	2.18	0.88	0.222	27.84	0.096	3.86	.	.	0.099	0.164	.	.
1	Y 451052-4	2.00	0.803	0.090	0.025	1.16	0.738	1.07	18.28	.	0.598	.	.	0.087	0.380	.	.
2	BAS NIRM4	1.97	2.37	0.051	0.008	3.03	0.52	20.2	3.56	0.014	.
1	NCS HS11789	1.97	1.08	0.048	0.076	2.58	6.39	17.80	2.51	0.061	0.062	0.015	0.014	0.011	0.0093	.	.
2	BAS CRRM2/1	1.92	1.11	0.097	0.079	1.18	1.59	1.61	14.13	0.054	2.44	.	.	0.070	0.063	.	.
1	VS ChG 46	1.87	0.067	0.0106	0.108	3.24	0.0109	5.44	8.58	.	0.63	.	.	.	0.109	.	.
1	BAS NIRM1/1	1.83	6.74	0.058	0.015	3.26	0.20	11.8	0.300	0.021	.
2	BAS CRRM1/1	1.83	1.45	0.132	0.099	1.53	2.01	2.03	11.18	0.117	3.05	.	.	0.096	0.040	.	.
1	Y 451054-5	1.83	0.466	0.043	0.091	1.80	0.904	0.517	23.40	.	0.739	.	.	0.068	0.26	.	.
1	Y TSK202	1.81	1.16	0.201	0.057	2.00	1.10	1.91	15.42	.	2.20	.	.	.	0.33	.	0.075
2	DSZU CH025	1.80	0.387	0.030	0.026	2.70	1.23	1.77	35.14	0.351	0.302	.	.	0.117	0.044	.	.
2	BAS CRRM1/2	1.70	1.43	0.16	0.099	1.84	1.97	2.03	11.28	0.140	3.06	.	.	0.054	0.063	.	.
2	DSZU CH026	1.62	0.305	0.050	0.032	1.14	0.288	3.63	35.87	0.059	0.96	.	.	0.013	0.067	.	.
1	Y 451052-5	1.48	0.579	0.041	0.058	1.37	0.583	0.708	22.55	.	0.359	.	.	0.056	0.314	.	.
2	BAS NIRM8/2	1.45	1.58	0.105	0.014	5.61	0.23	35.3	2.47	.	0.77	0.033	.
1	Y 451054-6	1.45	0.254	0.024	0.123	2.38	1.15	0.216	28.96	.	0.213	.	.	0.084	0.13	.	.
1	Y TSK203	1.23	0.68	0.117	0.044	0.46	0.75	1.55	19.93	.	1.58	.	.	.	0.22	.	0.094
1	Y 451052-6	1.16	0.302	0.033	0.086	1.44	0.845	0.289	25.76	.	0.150	.	.	0.019	0.146	.	.
1	Y TSK204	0.91	0.34	0.078	0.063	1.00	0.53	0.97	25.37	.	0.95	.	.	.	0.14	.	0.114

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	B	Ce	Co	Nb	W	Units	Other									
	Y 451052-3	0.102	.	.	0.149	1.57	30 mm Ø x 18-30 mm										
	BAS CRRM3/2	40 mm x 37 mm x 10 mm										
	DSZU CH023	35 mm x 35 mm x 16 mm										
	Y 451054-4	30 mm Ø x 18-30 mm										
	Y TSK200	35 mm Ø x 18-30 mm										
	DSZU CH024	35 mm x 35 mm x 16 mm										
	Y 451052-4	0.086	.	.	0.071	1.05	30 mm Ø x 18-30 mm										
	BAS NIRM4	.	0.011	.	0.37	.	40 mm x 37 mm x 10 mm										
	NCS HS11789	0.0008	.	(0.0075)	.	(0.0002)	31 mm Ø x 28 mm	As: 0.0076	Bi: 0.067								
	BAS CRRM2/1	40 mm x 37 mm x 10 mm										
	VS ChG 46	Sb:0.140	~35 mm Ø x ~17 mm										
	BAS NIRM1/1	.	0.022	.	.	.	40 mm x 37 mm x 10 mm										
	BAS CRRM1/1	40 mm x 37 mm x 10 mm	last									
	Y 451054-5	30 mm Ø x 18-30 mm										
	Y TSK202	35 mm Ø x 18-30 mm										
	DSZU CH025	35 mm x 35 mm x 16 mm										
	BAS CRRM1/2	40 mm x 37 mm x 10 mm										
	DSZU CH026	35 mm x 35 mm x 16 mm										
	Y 451052-5	0.076	.	.	0.022	0.694	30 mm Ø x 18-30 mm										
	BAS NIRM8/2	.	0.013	.	.	.	48 mm x 42 mm x 12 mm										
	Y 451054-6	30 mm Ø x 18-30 mm										
	Y TSK203	35 mm Ø x 18-30 mm										
	Y 451052-6	0.055	.	.	0.014	0.370	30 mm Ø x 18-30 mm										
	Y TSK204	35 mm Ø x 18-30 mm										
	Number	B	Ce	Co	Nb	W	Units	Other									

RM CAST IRON MUSHROOMS CONTINUED ON THE NEXT PAGE

typical analysis

each unit is one pair of 43 mm Ø x 5 mm mushroom discs

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF FO19	4.04	1.05	1.05	0.032	0.057
CTIF FO12	3.71	1.86	0.44	0.038	0.004	0.77	.	.	0.008	.	.	0.011	.	.	.
CTIF FO8	3.6	1.04	0.37	0.107	0.021	0.215	0.30	0.30	.	.	0.005	0.05	0.055	0.014	.
CTIF FCR7	3.59	1.07	0.365	0.099	0.0427	0.704	0.947	33.65	.	.	2.62
CTIF FO6	3.49	0.55	0.715	0.87	0.106	0.120	0.128	0.45	.	.	0.202	0.039	0.080	0.110	.
CTIF FO10	3.5	0.67	1.05	0.20	0.101	0.114	0.118	0.38	.	.	0.20	.	0.1	0.08	.
CTIF NH3	3.47	0.85	0.175	0.36	0.024	0.031	2.53	1.76	.	.	0.73	.	.	1.76	.
CTIF FO11	3.45	1.57	0.685	0.052	0.103	0.211	0.235	0.34	.	(0.013)	0.225	0.066	0.078	0.113	.
CTIF FO18-2	3.4	1.2	0.60	1.34	0.136	0.049	0.140	0.170	.	.	0.179	0.046	0.055	0.102	.
CTIF NH7-1	3.43	0.95	0.63	0.035	0.022	0.105	5.53	9.02
CTIF FCR5	3.43	0.35	0.62	0.052	0.0175	1.02	2.69	28.5	.	.	3.27
CTIF FT2-1	3.39	1.415	0.78	0.045	0.095	0.01	0.070	0.030	0.100	0.405	.
CTIF FO18-1	3.25	1.33	0.52	1.11	0.132	0.09	0.18	0.087	.	.	0.16	0.15	0.17	0.17	.
CTIF NiMo1	3.22	2.585	0.200	0.0590	(0.0030)	0.376	2.165	0.0353	.	0.0205	0.457	0.0020	0.0190	0.0169	.
CTIF FL7	3.22	2.550	0.100	1.34	0.048	0.351	0.232	0.043	.	.	0.335	0.0291	0.0525	0.0796	.
CTIF FT3	3.2	1.55	0.345	0.063	0.051	0.015	0.092	0.685	0.2	0.016	.
CTIF NH7-2	3.2	1.20	0.91	0.034	0.0120	0.108	5.53	8.87
CTIF FO5	3.2	0.7	0.2	1.30	0.027	0.12	0.172	0.3	.	.	0.41	0.109	0.04	0.14	.
CTIF NH9	3.13	1.24	0.65	0.087	0.029	0.203	4.11	11.70	.	.	0.059
CTIF NR Cu1	3.12	1.465	0.172	0.090	0.99	4.95	18.02	0.994	(0.095)
CTIF FL6	3.1	1.4	0.6	0.012	0.18	0.079	1.03	0.167	.	0.028	0.50	0.005	0.15	0.033	.
CTIF FL10	3.1	1.3	0.85	0.323	0.066	0.104	0.10	(0.07)	(0.03)	.	0.0335	0.028	0.045	0.048	(0.02)
CTIF FPA 1	3.090	0.0300	0.100	0.0022	0.0009	0.0622	0.0450	0.0710	.	0.0097	0.0109	.	0.0010	0.0010	.
CTIF NR 8S	3.05	1.41	4.39	0.124	.	0.071	14.20	0.191
CTIF FO17	3.01	2.48	0.475	0.470	0.168	(0.006)	0.021	(0.016)	.	0.032	.	0.024	0.032	0.018	.
CTIF FAL 1	3.0	1.0	0.2	0.04	<0.001	0.2	0.06	0.04	2.1	.	0.015	.	0.01	.	.
CTIF NR 3L	2.99	3.05	0.72	0.088	0.052	0.26	21.58	2.97
CTIF NH1	2.98	1.35	0.90	0.060	0.105	1.99	1.38	0.83	.	.	1.45
CTIF NH8	2.98	0.80	0.57	0.052	0.076	0.065	8.16	5.03	.	.	0.125
CTIF NR 3S	2.92	2.91	0.77	0.024	.	0.33	24.63	3.05
Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF FT1	2.9	2.12	0.71	0.12	0.025	0.012	0.11	0.057	.	.	.	0.067	0.19	0.525	.
CTIF NR 8L	2.89	1.70	5.19	0.054	0.030	0.075	13.33	0.165
CTIF NH4	2.84	0.49	0.28	0.12	0.022	0.09	3.60	2.46	.	.	0.30
CTIF FO4	2.81	1.51	0.64	0.58	0.009	0.31	0.32	0.17	.	.	0.095	0.013	0.075	0.049	.
CTIF FCR2	2.86	1.07	0.740	0.137	0.055	0.135	1.87	11.8	.	.	3.88
CTIF FL5	2.8	2.3	0.4	0.02	(0.005)	0.5	0.05	0.35	.	0.010	0.01	0.07	0.01	0.01	.
CTIF FCR Ni3	2.74	0.69	0.47	0.036	0.011	.	11.05	31.65	0.47
CTIF NH6	2.70	2.28	0.355	0.066	0.036	0.115	7.06	6.60	.	.	0.11
CTIF FO9	2.7	1.5	0.7	0.02	0.015	0.31	0.355	0.18	.	0.02	0.13	0.144	0.017	0.022	.
CTIF FL4	2.6	2.91	0.5	0.288	0.137	0.0168	0.061	0.45	.	.	0.090	0.011	0.0296	0.116	.
CTIF NR 1S	2.58	3.02	1.54	0.19	0.0015	0.11	20.60	2.00
CTIF NR 1L	2.50	3.00	1.34	0.125	0.10	0.49	25.87	1.74
CTIF NH2	2.50	1.81	1.04	0.047	0.058	1.02	1.78	1.26	.	.	1.01
CTIF NR Cu2	2.48	2.07	1.078	0.113	0.049	6.50	15.85	2.05
CTIF NR 4S	2.47	4.87	1.71	0.145	.	0.63	18.30	1.50
CTIF FCR4	2.47	1.40	2.05	0.097	0.066	1.32	0.571	24.2	.	.	2.16
CTIF FCR1	2.46	0.48	0.63	0.019	0.007	0.031	1.30	18.71	.	.	1.41
CTIF FO7-2	2.45	0.675	0.70	0.84	0.085	0.125	0.15	0.455	.	.	0.26	.	0.065	0.13	.
CTIF NR 4L	2.41	5.89	1.495	0.155	0.010	0.758	15.90	1.403
CTIF FO7-3	2.40	0.65	0.74	0.82	0.097	0.075	0.125	0.52	.	.	0.26	0.0015	0.045	0.12	.
CTIF NR 2S	2.32	1.43	0.530	0.062	.	0.210	36.3	0.51
CTIF NH5	2.31	0.31	0.24	0.115	0.04	0.035	4.90	2.85	.	.	0.017
CTIF FL3	2.3	2.1	0.27	0.729	(0.013)	0.102	0.553	0.107	.	.	0.106	0.111	0.05	0.049	.
CTIF NR 4G	2.24	5.60	1.72	0.11	(0.002)	0.64	21.30	1.40
CTIF NR 2G	2.25	1.47	0.380	0.0476	(0.003)	0.232	36.34	0.395
CTIF FL2	2.18	3.61	0.0400	0.049	0.082	0.0497	0.0238	0.440	(0.006)	0.0263	(0.004)	0.140	0.0750	0.201	.
CTIF FL1	2.1	3.2	0.80	0.118	0.0765	0.0195	0.245	0.06	.	(0.022)	0.038	0.305	0.020	0.015	.
CTIF FCR Ni2	2.02	1.50	0.61	0.185	0.024	.	13.05	29.00
CTIF NR Cu3	1.94	3.12	0.60	0.046	0.016	8.05	13.3	3.50
CTIF NR 6S	1.82	2.44	0.99	0.019	.	0.03	30.75	1.06
CTIF NR 5L	1.77	2.99	1.207	0.037	0.083	0.48	33.89	0.27
CTIF NR 6L	1.76	2.07	0.70	0.031	0.063	0.020	30.37	3.49
CTIF NR 5S	1.67	1.97	1.23	0.035	.	0.50	27.05	0.24
CTIF FCR6	1.44	0.76	1.47	0.201	0.086	0.480	0.188	30.84	.	.	0.455
CTIF FCR Ni1	1.27	1.63	0.71	0.41	0.06	0.02	16.50	26.20
Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W

CAST IRON MUSHROOMS

CONTINUED FROM THE PREVIOUS PAGE

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF FO19	0.0005	.
CTIF FO12
CTIF FO8
CTIF FCR7
CTIF FO6
CTIF FO10
CTIF NH3
CTIF FO11
CTIF FO18-2	0.004
CTIF NH7-1
CTIF FCR5
CTIF FT2-1
CTIF FO18-1
CTIF NiMo1
CTIF FL7	(0.0266)	(0.010)	.	(0.010)	.	0.0035
CTIF FT3
CTIF NH7-2
CTIF FO5
CTIF NH9
CTIF NR Cu1
CTIF FL6	.	0.008
CTIF FL10	(0.022)	.	(0.012)	(0.004)	.	.	(0.018)	(0.002)	(0.032)	(0.001)	(0.029)
CTIF FPA 1	0.0109	0.0125
CTIF NR 8S
CTIF FO17
CTIF FAL 1
CTIF NR 3L
CTIF NH1
CTIF NH8
CTIF NR 3S
Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF FT1
CTIF NR 8L
CTIF NH4
CTIF FO4
CTIF FCR2
CTIF FL5	.	(0.002)	.	(0.0005)
CTIF FCR Ni3
CTIF NH6
CTIF FO9
CTIF FL4	(0.05)	.	.	(0.003)	.	0.007
CTIF NR 1S
CTIF NR 1L
CTIF NH2
CTIF NR Cu2	(0.0079)
CTIF NR 4S
CTIF FCR4
CTIF FCR1
CTIF FO7-2	0.0113
CTIF NR 4L
CTIF FO7-3
CTIF NR 2S - producer low stock, only undersized pieces remaining
CTIF NH5
CTIF FL3	0.008
CTIF NR 4G
CTIF NR 2G	0.27
CTIF FL2	.	.	.	(0.0135)
CTIF FL1
CTIF FCR Ni2
CTIF NR Cu3
CTIF NR 6S
CTIF NR 5L
CTIF NR 6L
CTIF NR 5S
CTIF FCR6
CTIF FCR Ni1
Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
1.0812		ECRM 191-2D	15-5PH		IARM Fe155PH-18	314		IMZ 165
1.2344		ECRM 271-1D	15-5PH		ECRM 273-1D	314		IMZ 166A
1.4410		ECRM 298-2D	16MnCr5		PV 102/1	316 H		CT 316
1.4435, 1.4436		JK 27B	17-4PH		13X PH2	316 H		IARM 339A
1.5415		HRT FE2012-N	17-4PH		BS 17-4PHA	316 H		NILAB 500HAD
1.6587		HRT FE2013-N	17-4PH	17034	BS 17-4PHB	316 L	17034	BS 316F
1.7149	20MnCrS5	ECRM 187-2D	17-4PH	17034	BS 17-4PHC	316 L		CZ SL-2A
1.7160		ECRM 194-1D	17-4PH		IARM Fe174PH-18	316 L		IARM 163E
1.8550		ECRM 129-3D	17-4PH		SRM C2400	316L		IARM Fe316L-23
1.8519		HRT FE2010-N	17-7PH		13X PH17700	316 L		SRM 1155A
1005	17034	BS 1005	17-7PH 25(preceded 17025)		BS 192	316 L		SS 466/2
1005		DSZU C040a	17-7PH 25(preceded 17025)		BS 192A	316 MOD		TL 2002
1005		ECRM 064-2D	17-7PH		IARM 152C	316 Ti		IRSID 1821
1005		SRM 1765	17-7PH		IARM Fe177PH-18	316 Ti		PV 112/1
1005		SRM 1766	182FM		BS 150	316 Ti		VS LG72
1005		SS 111/1	18Cr2Ni12Mn		CT ISO035A	317 L	17034	BS 317L
1006		IRSID 1670	201		BS 191	317 L	25(pre-17025)	BS 9941
1008	17034	BS XCAS	201		SRM 1297	317 L	25(pre-17025)	BS 9942
1008		ECRM 057-2D	20Cb3		BS 187A	317 L		IARM 153C
1009	17034	BS 1009	20Cb3		CT 20 Cb-3	318	17034	BS 2205A
1009 + Al	17034	BS XCOS-2	20MoCr4		ECRM 197-1D	321		13X 32100
100C6		IRSID 1747	2101		IARM 292A	321	17034	BS 85D
1010		IMZ 111	21Cr6Ni9Mn		CT ISO129A	321	17034	BS 321D
1011		IMZ 73	2205		13x NSA9	321		IARM 61
1012, 1013	17034	IMZ 71A	2205	17034	BS 2205A	321		IARM 6J
1016		BS 1016	2205		IARM 212D	321		SRM 1171
1017		IMZ 112B	2205		HRT FE2000-H	321		SS 465/1
1017		IRSID 1664	2205		IARM Fe2205-18	321 - Ti		IMZ 152
1018		12X 10180C	2304		IARM 317A	32750		13X NSA13
1018		12X 10180D	2507	17034	BS 2507	3310	17034	BS 3310
1018	17034	BS 1018	2507		IARM 301B	347		13X 34700
1018		ECRM 087-1D	2507		IARM Fe2507-21	347		BS 347A
1018		IARM 28K	253 MA	25(pre-17025)	BS 253	347		BS 347B
1020	17025	BS 1020	253 MA		IARM 316A	347	17034	BS 347C
1020		BS 57F	254 SMO	17034	BS 254	347		IARM 8G
1020		IARM Fe1020-18	254 SMO		IARM Fe254SMO-21	347		IARM 8H
1023		IMZ 112A	254 SMO		NILAB 501HAD	347		IARM 8i
1026	17034	BS 1026A	255, Duplex		IARM 239B	347 H		BS 87F
1026		IARM 359A	255, Duplex		IARM 239C	348		SRM 1172
1030	17025	BS 1030	300M	17034	BS 300A	355	17025	BS 355
1030	17034	BS 1030A	300M		IARM 340A	355		IARM 335A
1030		IARM 209D	300M		IARM Fe300M-22	35MV7		IRSID 1750
1033		IRSID 1663	301		IARM 289A	405		SRM 1295
1035	17034	BS 1035	301		IARM 289B	408		13X 40800A
1035		IARM 360A	301		IRSID 1819	409		13X 40900
1039		IRSID 1637	302		IARM 241D	409		13X 40930
1040	17034	BS 1040	302 HQ		IARM 234C	409		IARM Fe409-20
1040		IARM 210D	303		13X 30300	409 + Cr		NCS HS20743
1040		IRSID 1657	303	17025	BS 303	410		13X 41008
1042		IRSID 1656	303		CT 303	410	25(pre-17025)	BS 0021
1042		NM EN-8	303		CZ SP-1A	410, F6NM	25(pre-17025)	BS 0022
1043		IRSID 1652	303		IARM Fe303-18	410	17034	BS 410C
1045	17034	BS 1045	303 Se		IARM 253A	410		CT 410
1045		BS 56E	303 Se		IARM 253B	410		IARM Fe410-18
1045		IARM 200D	304 H		13X NSB1	410 + Mo		ECRM 296-1D
1045		IPT 503	304 H + Ca	17034	BS CA304-4	410 + Mo		IMZ 161
1050		IARM Fe1050-18	304 H		CT 304	410 H		13X 41001
1060		IARM 373A	304 H		IARM Fe304H-18	4130	17025	BS 4130
1060 + P		NM 309	304 H		SS 468/1	4130	17034	BS 4130A
1069	17034	ECRM 059-2D	304 L		13X 30403	4130		IARM 143F
1070		BS 54H	304 L		BS 304C	4130		SRM 1225
1078		ECRM 056-2D	304 L		IARM 162D	4130 H		IPT 501
1078		SRM 1224	304 L		IARM Fe304L-22	4140		12X 41400
1080		BS 54J	304 L		ECRM 287-1D	4140	25(pre-17025)	BS 1962
1090		SS 602/2	304 L		ECRM 292-1D	4140	17034	BS 4140C
1095		BS 64C	304 L		IARM 162D	4140		IARM 30H
1095		SRM 1227	304 L		PV 111/1	4140		IARM 30J
1117	25(preceded 17025)	BS 3993	304 L		TL 2003D	4140		IARM Fe4140-19
1117		BS 65C	304 L		SS 463/1	4140 Bi		BS 4140A
1117		IARM 29E	305		ECRM 297-1D	4140 Bi		BS 4140B
11L17	17025	BS 75F	306		13X 30600A	41L40MOD	17025	BS 70B
11L17	17025	BS 75G	308		DSZU C017	41L40MOD	17034	BS 70C
1118		IARM 307A	309		BS 82E	4150 Bi & S		BS 4150MOD
1118		IARM 307B	309	17034	BS 309	4150 S	17034	BS 4150MOD-A
1141		BS 66B	309		IARM Fe309-18	4150 S	17034	BS 42
1141		IARM 348A	310		13X 31008	415		13X 41500A
1144	17025	BS 1144	310		BS 83G	415		IARM Fe415-21
1144	17025	BS 1144A	310	25(pre-17025)	BS 9841	416		BS 90F
1144		IARM 199C	310	25(pre-17025)	BS 9842	416	17025	BS 416
1144		IARM Fe1144-22	310		CZ SL-3A	416		CT 416
1215		BS 66K	310		IARM 4E	416		IARM Fe416-22
1215	17025	BS 66L	310		IARM 4F	416		SRM 1223
1215		IARM Fe1215-18	310		IARM 4G	416 H		13X 41600
12L14		BS 74B	310		SS 464/1	416 Se		BS 151
12L14	17025	BS 74C	3115		BS XCCT	418		IARM Fe418-18
12L14	17034	BS 74D			IRSID 1749	41CAD7		IRSID 1749
12Mn18Cr		BS 193			41L40	17025		BS 70B
1345		BS XCCV			41L50	17025		BS 72B
13-8PH		13X PH13800			42			CT ISO138A
13-8PH		BS 184A			42			CT ISO139A
13-8PH		CT X92834			42CrMo4			PV 101/1
13-8PH		IARM 21D			420			BS 98
1429		ECRM 058-2D			420			BS SS4951
1513		IMZ 76			420			BS SS4952
1526 MOD		SRM 1269			420			ECRM 272-1D
1541		IARM 349A			420			IARM 154C
1541		IPT 504			420			SS 469
1541		IRSID 1648			420 F			BS 152
1544		IRSID 1644			420 F S			IARM 352A
15-5PH		BS 185A			422			13X 42200
15-5PH		BS 9621			422			BS 97
15-5PH		BS 9622			422	17025		BS 422
					422			IARM 205D
					422			IARM Fe422-22
					430			BS 91E
					430	17034		BS 430

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within the catalog.

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
430		IARM 11D	A-36		BS 1018	HY 80		SRM 1286
430		NCS HS20742	A-36		BS 1020	Hy-Tuff		IARM 342A
430 F		BS 153	A-36		BS LF2B	Invar		14X 93603
430 F		BS 154	A-36		IARM 213C	Invar-36	17034	BS 186B
430 F S		IARM 355A	A-36		IARM 213D	Invar-36 + Se		BS 186A
431	17025	BS 431	A-485-1		BS A485-1	Invar-36 + Se		IARM 24B
431	17034	BS 431A	A-6		BS 40B	Invar 36 + Se		IARM FeINVR36-22
4130	17025	BS 4130	A-6		IARM 40B	Invar 42		14X 94100
4130	17034	BS 4130A	A-6		IARM 40C	ISO 898-1		SS 457/2
431		BS 92B	A615-75		IARM 378A	Kovar	17025	BS 160A
431		IARM 12C	A706-60		IARM 380A	Kovar	17034	BS 160B
431		HRT FE2010-H	A706-60		IARM 380B	Kovar		IARM 98B
431		SRM 1219	A706-80		IARM 381A	Kovar		IARM FeKovar-18
4320		BS 3961	Aermet 100		CT ISO045A	L-6	17025	BS 39B
4320		BS 4320	Aermet 100		IARM 242A	L-6		IARM FeL6-18
4330 MOD	17034	BS 4330MOD	Aermet 100		IARM FeA100-18	LDX2101		13X 32101
4330 MOD		IARM 330B	AL6XN	17025	BS 189A	LF-2		BS 2971
4340	17025	BS 4340	AL6XN		IARM 157D	LF-2	17025	BS LF2B
4340	17025	BS 4340A	C- 5Mo	17034	BS 3952	LF-2		BS LF2C
4340	17034	BS 4340B	C- 5Mo		IARM 229B	LF-2		SS 601/2
4340		IARM 31G	C-250		IARM 308A	LF-3		BS LF3
4340		IARM Fe4340-22	C-350		IARM 309A	M-1		BS TML
440 C		13X 44004	CA6NM		HRT FE2009-H	M-1		CT M1
440 C		BS 93E	CA6NM		IARM 327A	M-1		IARM 304A
440 C	17025	BS 93F	CD3MN		ECRM 298-2D	M-1		IARM FeM1-18
440 C		IARM 13D	CD4MCU	17034	BS CD4MCU	M-10		CT M10
440 F		BS 155	CD4MCU	17034	BS CD4MCU-A	M-10		IARM 324A
440 F Se		BS 156	CD6MN		VS LG58	M-152		13X 64152
440 F Se		IARM 353A	CF-3		IRSTD 1820	M-152		IARM 291A
446		BS 94C	CF3M		ECRM 284-3D	M-2		BS 32D
450		BS 95A	CLA6		IARM 169B	M-2		CT M2
450	17034	BS 450	CLA7		IARM 170B	M-2		IARM 44C
450	25 (pre-17025)	BS 9811	CLA11		IARM 180A	M-2		IARM FeM2-18
450	25 (pre-17025)	BS 9812	CLA5		IARM 168A	M-2		SRM 1157
450		IARM 15C	CLA9		IARM 172A	M-35		IARM 320A
450		CT 450	CPM15V	17025	BS PM15	M-4		IARM 251A
455		13X 45500	CPM15V		IARM Fe15V-18	M-4		IARM FeM4-18
455		BS 96A	D-2		BS 37E	M-42		SS 487/1
455		BS SS1962	D-2		BS 37G	M-47	17025	BS M-47
455		CT 455	D-2		BS 37H	M-50	17025	BS M-50
455		IARM 16C	D-2		CT D2	M-50		IARM 306B
455		IARM Fe455-22	D-2		IARM 41D	M-65		IARM FeM62-18
4615	17034	BS 3962	D-6	17025	BS D-6	M-7		CT M7
4620		BS 4620	D-6	17034	BS D-6A	Maraging 250	17034	BS M250
4620	17034	BS 51F	D6-AC		IARM 299A	Maraging 250		CT 250
4620		IARM 33D	DP1080		IARM 299A	Maraging 250		ECRM 285-2
465		13X 46500	Duplex		13X NSA9	Maraging 250		IARM FeC250-21
465		IARM 354A	Duplex	17034	BS 2205A	Maraging 300	25 (pre17025)	BS 161A
465		CT ISO123A	Duplex		IMZ 163A	Maraging 300	17034	BS 161B
4820	17025	BS 4820A	Duplex		IMZ 164	Maraging 300		CT 300
4820	17034	BS 4820B	Duplex		TL 2001	Maraging 300		IARM 99D
4820		IARM 155F	E52100	17034	BS E52100	Mold Steel	17025	BS PP20
4820		IARM Fe4820-18	E52100		IARM 49E	NIT 135M		IARM 305B
5140H		IARM Fe5140H-18	E52100 Bi		BS 53MOD	Nitriding 135G		BS 68B
5160		IMZ 116	Elect./ Magnetic		SRM 1159	Nitriding 135G	17025	BS 68E
6150	17034	BS 43A	Electrolytic		SRM 1265a	Nitronic 40		13X NSC6
6150		BS 4941	ER321		13X 32180A	Nitronic 40		BS 190
6150		IARM 34C	F-1		IARM FeF1-21	Nitronic 40		IARM FeN40-18
630		CT 630	F-1		RM Fe 2	Nitronic 50		BS 180A
6418	17034	BS 6418	F-11		BS 45A	Nitronic 50	17034	BS 180B
6418		BS 69B	F-11	17034	BS 45B	Nitronic 50		IARM 17D
6526		BS 9-4-30	F-11		BS 45C	Nitronic 50		IARM FeN50-18
709		CT X67975	F-11		IARM 35L	Nitronic 60		BS 181A
8620		12X 86200-21	F-11		IARM FeF11-21	Nitronic 60	17025	BS 181B
8620		BS 1931	F-2		CT X27081	Nitronic 60		IARM 18D
8620 + Bi		BS 8620A	F-22	17034	BS 46B	NMS 100		IARM 214A
8620	17034	BS 8620G	F-22	25 (preceeded 17025)	BS 1982	NMS 140		IARM 295A
8620		IARM Fe8620-18	F-22		IARM 36C	O-1	17025	BS 35D
8620		IPT 502	F-22		SRM 1270	O-1		CT O1
86L20	25 (preceeded 17025)	BS 73B	F-22 + Cr		HRT FE2009-N	O-2		CZ LA-4C
86L20	17034	BS 73C	F-5		BS 47A	O-6	17025	BS 41
86L20	17034	BS 73D	F-5		BS 47B	O-6	25 (preceeded 17025)	BS 41A
8630	17034	BS 8630	F-5		IARM 37C	O-6		IARM 45A
8740		BS 67B	F-51	17034	BS 2205A	O-6		IARM 45B
8740	17034	BS 8740	F-9	17034	BS 48B	P-20	17034	BS 55G
8740		IARM 252C	F-9		IARM FeF9-18	P-20 MOD	17034	BS 55H
8740		IARM 252D	F-91		13X 90901	P-20 + Al		BS 68C
8740		IARM 252E	F-91	17025	BS 9905A	PP-20	17025	BS PP20
8740		IARM 252F	F-91		HRT FE2003-H	RA330		BS 86F
8822		BS 8822	F-91		IARM Fe91-18	Railroad Steel	17034	BS 54H
8822	17034	BS 8822A	Ferrallium 255		BS 179A	Railroad Steel	17034	BS 54J
904L		13X NSA12	Ferrallium 255	17025	BS 179B	s-1		BS 33D
904L		ECRM 295-1D	Ferrallium 255	17025	BS 179C	s-1		BS 33E
904L		IARM Fe904L-22	F6NM 25 (preceeded 17025)		BS 0022	s-1		IARM 46B
9310		BS 58C	Greek Ascoloy		BS 183A	s-1 MOD	17034	BS 33F
9310		BS 58D	Greek Ascoloy	17034	BS 183B	s-5		BS 38C
9310		BS 58E	Greek Ascoloy	17034	BS 183C	s-5		IARM 47B
9310		BS 9310	Greek Ascoloy		IARM 20C	s-7		BS TS7
9310		IARM Fe9310-18	H-10		BS 49	s-7	17034	BS TS-7A
9325	17034	BS 9325A	H-11		BS TH11	s-7		IARM 259A
9325	17034	BS 9325B	H-11		ECRM 276-2D	s-7		IARM FeS7-18
9-4-30		IARM 341A	H-11		IARM 255A	s-7		SRM 1772
A-10		BS A-10	H-11		IARM 255B	S42027		13X 42027A
A-11		BS 10V	H-11		IMZ 173	SA213-T22		IMZ 159
A-11	17025	BS A-11	H-12		BS TH12	SA213-T22		IMZ 160
A-106 Gr B		SRM 1228	H-13		BS 34D	SA213-T22		IMZ 169
A-193 B16		BS 4942	H-13	17034	BS H-13A	SAE G2500		BS 20E
A-193 B16	17025	BS 4942A	H-13		CT H13	STA 361		IARM 268B
A-2		BS 36C	H-13		IARM 42C	T-1	17025	BS 30D
A-2		BS 36D	H-13		IMZ 174	T-1		IARM FeT1-18
A-2		BS 36E	H-19	17025	BS H-19	T-4		IARM 281A
A-2		CT A2	HC 250+V		SRM CL290	T-15	17034	BS TS15
A-2		IARM 39B	High Perm		CT ISO124A	T23		IARM FeT23-18
A-2		IARM 39C	High Perm		CT ISO136A	VM12		IMZ 196
A-242		IPT 500	High Perm 49		CT ISO141A	W-5		14X 72305
A-242 Mod		SRM C1285	HSLA 100		SRM 1271	Z30C13		IRSTD 1825
A-286	17025	BS 188B	HY 130		SRM 1226	Zeron 100, Duplex		13X NSA8
A-286		IARM 26D				Zeron 100, Duplex		IARM 319A
A-286		SRM 1230				Zeron 100, Duplex		IARM FeZ100-18
A-36		BS 1016						
A-36		BS 1016						

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S
1005	<0.06	<0.35	<0.03	<0.05
1006	<0.08	0.25-0.40	<0.03	<0.05
1008	<0.10	0.30-0.50	<0.03	<0.05
1009	<0.15	<0.60	<0.03	<0.05
1010	0.08-0.13	0.30-0.60	<0.03	<0.05
1011	0.09-0.14	0.60-0.90	<0.03	<0.05
1012	0.10-0.15	0.30-0.60	<0.03	<0.05
1013	0.11-0.16	0.50-0.80	<0.03	<0.05
1015	0.13-0.18	0.30-0.60	<0.03	<0.05
1016	0.13-0.18	0.60-0.90	<0.03	<0.05
1017	0.15-0.20	0.30-0.60	<0.03	<0.05
1018	0.15-0.20	0.60-0.90	<0.03	<0.05
1019	0.15-0.20	0.70-1.00	<0.03	<0.05
1020	0.18-0.23	0.30-0.60	<0.03	<0.05
1021	0.18-0.23	0.60-0.90	<0.03	<0.05
1022	0.18-0.23	0.70-1.00	<0.03	<0.05
1023	0.20-0.25	0.30-0.60	<0.03	<0.05
1025	0.22-0.28	0.30-0.60	<0.03	<0.05
1026	0.22-0.28	0.60-0.90	<0.03	<0.05
1029	0.25-0.31	0.60-0.90	<0.03	<0.05
1030	0.28-0.34	0.60-0.90	<0.03	<0.05
1033	0.29-0.36	0.70-1.00	<0.03	<0.05
1034	0.32-0.38	0.50-0.80	<0.03	<0.05
1035	0.32-0.38	0.60-0.90	<0.03	<0.05
1037	0.32-0.38	0.70-1.00	<0.03	<0.05
1038	0.35-0.42	0.60-0.90	<0.03	<0.05
1039	0.37-0.44	0.70-1.00	<0.03	<0.05
1040	0.37-0.44	0.60-0.90	<0.03	<0.05
1042	0.40-0.47	0.60-0.90	<0.03	<0.05
1043	0.40-0.47	0.70-1.00	<0.03	<0.05
1044	0.43-0.50	0.30-0.60	<0.03	<0.05
1045	0.43-0.50	0.60-0.90	<0.03	<0.05
1046	0.43-0.50	0.70-1.00	<0.03	<0.05
1049	0.46-0.53	0.60-0.90	<0.03	<0.05
1050	0.48-0.55	0.60-0.90	<0.03	<0.05
1053	0.48-0.55	0.70-1.00	<0.03	<0.05
1055	0.50-0.60	0.60-0.90	<0.03	<0.05
1059	0.55-0.65	0.50-0.80	<0.03	<0.05
1060	0.55-0.65	0.60-0.90	<0.03	<0.05
1064	0.60-0.70	0.50-0.80	<0.03	<0.05
1065	0.60-0.70	0.60-0.90	<0.03	<0.05
1069	0.65-0.75	0.40-0.70	<0.03	<0.05
1070	0.65-0.75	0.60-0.90	<0.03	<0.05
1074	0.70-0.80	0.50-0.80	<0.03	<0.05
1078	0.72-0.85	0.30-0.60	<0.03	<0.05
1080	0.75-0.88	0.60-0.90	<0.03	<0.05
1084	0.83-0.93	0.60-0.90	<0.03	<0.05
1085	0.80-0.94	0.70-1.00	<0.03	<0.05
1086	0.80-0.93	0.30-0.50	<0.03	<0.05
1090	0.85-0.98	0.60-0.90	<0.03	<0.05
1095	0.90-1.03	0.30-0.50	<0.03	<0.05
Number	C	Mn	P	S

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si
1513	0.10-0.16	1.10-1.40	<0.03	<0.05	.
1522	0.18-0.24	1.10-1.40	<0.04	<0.05	.
1524	0.19-0.25	1.35-1.65	<0.04	<0.05	.
1526	0.22-0.29	1.10-1.40	<0.04	<0.05	.
1527	0.22-0.29	1.20-1.50	<0.04	<0.05	.
1533	0.30-0.37	1.10-1.40	<0.04	<0.05	.
1534	0.30-0.37	1.20-1.50	<0.04	<0.05	.
1541	0.36-0.44	1.35-1.65	<0.04	<0.05	.
1544	0.40-0.47	0.80-1.10	<0.04	<0.05	.
1545	0.43-0.50	0.80-1.10	<0.04	<0.05	.
1546	0.44-0.52	1.00-1.30	<0.04	<0.05	.
1548	0.44-0.52	1.10-1.40	<0.04	<0.05	.
1552	0.47-0.55	1.20-1.50	<0.04	<0.05	.
1553	0.48-0.55	0.80-1.10	<0.04	<0.05	.
1566	0.60-0.70	0.85-1.15	<0.04	<0.05	.
1570	0.65-0.75	0.80-1.10	<0.04	<0.05	.
1580	0.75-0.88	0.80-1.10	<0.04	<0.05	.
1590	0.85-0.98	0.80-1.10	<0.04	<0.05	.
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30

Number	C	Mn	P	S	Si
--------	---	----	---	---	----

RESULFURIZED STEEL SPECIFICATIONS

Number	C	Mn	P	S
1108	0.08-0.13	0.50-0.80	<0.04	0.08-0.13
1109	0.08-0.13	0.60-0.90	<0.04	0.08-0.13
1110	0.08-0.13	0.30-0.60	<0.04	0.08-0.13
1116	0.14-0.20	1.10-1.40	<0.04	0.16-0.23
1117	0.14-0.20	1.00-1.30	<0.04	0.08-0.13
1118	0.14-0.20	1.30-1.60	<0.04	0.08-0.13
1119	0.14-0.20	1.00-1.30	<0.04	0.24-0.33
1123	0.20-0.27	1.20-1.50	<0.04	0.06-0.09
1132	0.27-0.34	1.35-1.65	<0.04	0.09-0.13
1137	0.32-0.39	1.35-1.65	<0.03	0.08-0.13
1139	0.35-0.43	1.35-1.65	<0.04	0.13-0.20
1140	0.37-0.44	0.70-1.00	<0.03	0.08-0.13
1141	0.37-0.45	1.35-1.65	<0.03	0.08-0.13
1144	0.40-0.48	1.35-1.65	<0.03	0.24-0.33
1145	0.41-0.49	0.70-1.00	<0.04	0.08-0.13
1146	0.42-0.49	0.70-1.00	<0.04	0.08-0.13
1151	0.48-0.55	0.70-1.00	<0.04	0.08-0.13
1152	0.48-0.55	0.70-1.00	<0.04	0.06-0.09
1211	<0.13	0.60-0.90	0.07-0.12	0.10-0.15
1212	<0.13	0.70-1.00	0.07-0.12	0.16-0.23
1213	<0.13	0.70-1.00	0.07-0.12	0.24-0.33
1215	<0.09	0.75-1.05	0.04-0.09	0.26-0.35

Number	C	Mn	P	S
--------	---	----	---	---

These are specifications, not samples for sale.

LOW ALLOY STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
1330	0.28-0.33	1.60-1.90	<0.035	<0.04	0.15-0.35	
1335	0.33-0.38	1.60-1.90	<0.035	<0.04	0.15-0.35	
1340	0.38-0.43	1.60-1.90	<0.035	<0.04	0.15-0.35	
1345	0.43-0.48	1.60-1.90	<0.035	<0.04	0.15-0.35	
3140	0.38-0.43	0.70-0.90	<0.04	<0.04	0.15-0.35	1.10-1.40	0.55-0.75	.	.	
4023	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	
4027	0.25-0.30	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	
4028	0.25-0.30	0.70-0.90	<0.035	0.035-0.050	0.15-0.35	.	.	0.20-0.30	.	
4037	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	
4047	0.45-0.50	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	
4118	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.08-0.15	.	
4120	0.18-0.23	0.80-1.20	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.15-0.25	.	
4121	0.18-0.23	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.45-0.65	0.15-0.25	.	
4130	0.28-0.33	0.40-0.60	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
4135	0.33-0.38	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
4137	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
4140	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
41L40	0.38-0.43	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	
4142	0.40-0.45	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
4145	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
4147	0.45-0.50	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
4150	0.48-0.53	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	
41L50	0.48-0.53	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	
4320	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30	.	
4340	0.38-0.43	0.60-0.80	<0.035	<0.04	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	
4615	0.13-0.18	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	
4617	0.15-0.20	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	
4620	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	
4715	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.65	.	
4720	0.17-0.22	0.50-0.70	<0.035	<0.04	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25	.	
4815	0.13-0.18	0.40-0.60	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	
4820	0.18-0.23	0.50-0.70	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	
50B46	0.44-0.49	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.20-0.35	.	.	B: 0.0005-0.003
5120	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	
51L20	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	0.15-0.35	
5130	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	
5132	0.30-0.35	0.60-0.80	<0.035	<0.04	0.15-0.35	.	0.75-1.00	.	.	
5140	0.38-0.43	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	
5150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	
5160	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	
51B60	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	B: >0.0005
6150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	V: >0.15
8615	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
8617	0.15-0.20	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
8620	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
86L20	0.18-0.21	0.70-0.90	<0.035	0.02-0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	0.15-0.35	
8622	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
8630	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
8637	0.35-0.40	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
8640	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
8645	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	
8720	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	
8740	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	
8822	0.20-0.25	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.30-0.40	.	
9259	0.56-0.64	0.75-1.00	<0.035	<0.04	0.70-1.10	.	0.45-0.65	.	.	
9260	0.56-0.64	0.75-1.00	<0.035	<0.04	1.80-2.20	
E4340	0.38-0.43	0.65-0.85	<0.025	<0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	
E51100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	0.90-1.15	.	.	
E52100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	1.30-1.60	.	.	
E9310	0.08-0.13	0.45-0.65	<0.025	<0.025	0.15-0.35	3.00-3.50	1.00-1.40	0.08-0.15	.	
F-11	0.10-0.20	0.30-0.60	<0.04	<0.04	0.50-1.00	.	1.00-1.50	0.44-0.65	.	
F-22	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	2.00-2.50	0.90-1.10	.	
F-5	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	4.00-6.00	0.45-0.65	.	
F-9	<0.15	0.30-0.60	<0.03	<0.03	0.50-1.0	.	8.00-10.00	0.90-1.10	.	
F-91	0.08-0.12	0.30-0.60	<0.02	<0.01	0.20-0.50	<0.40	8.00-9.50	0.85-1.05	.	Al: <0.04 N: 0.03-0.07
F-91	continued									Nb: 0.06-0.10 V: 0.18-0.25
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30	
LF3	<0.20	<0.90	<0.035	<0.04	0.20-0.35	3.25-3.75	.	.	.	
Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other

These are specifications, not samples for sale.

TOOL STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
A-2	0.95-1.05	<1.00	<0.03	<0.03	<0.50	.	4.75-5.50	.	0.90-1.40	0.15-0.50	.	
A-4	0.95-1.05	1.80-2.20	<0.03	<0.03	<0.50	.	0.90-2.20	.	0.90-1.40	.	.	
A-6	0.65-0.75	1.80-2.50	<0.03	<0.03	<0.50	.	0.90-1.20	.	0.90-1.40	.	.	
A-7	2.00-2.85	<0.80	<0.03	<0.03	<0.50	.	5.00-5.75	.	0.90-1.40	3.90-5.15	0.50-1.50	
A-8	0.50-0.60	<0.50	<0.03	<0.03	0.75-1.10	.	4.75-5.50	.	1.15-1.65	.	1.00-1.50	
A-9	0.45-0.55	<0.50	<0.03	<0.03	0.95-1.15	1.25-1.75	4.75-5.50	.	1.30-1.80	0.80-1.40	.	
A-10	1.25-1.50	1.60-2.10	<0.03	<0.03	1.00-1.50	1.55-2.05	.	.	1.25-1.75	.	.	
A-11	2.45	0.50	.	.	0.90	.	5.25	.	1.30	9.75	.	
D-2	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	<1.00	0.70-1.20	<1.10	.	
D-3	2.00-2.35	<0.60	<0.03	<0.03	<0.60	.	11.00-13.50	.	.	<1.00	<1.00	
D-4	2.05-2.40	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	.	0.70-1.20	<1.00	.	
D-5	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	2.50-3.50	0.70-1.20	<1.00	.	
D-7	2.15-2.50	<0.60	<0.03	<0.03	<0.60	.	11.50-13.50	.	0.70-1.20	3.80-4.40	.	
H-10	0.35-0.45	0.25-0.70	<0.03	<0.03	0.80-1.20	.	3.00-3.75	.	2.00-3.00	0.50-0.75	.	
H-11	0.33-0.43	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.60	0.30-0.60	.	
H-12	0.30-0.40	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.25-1.75	<0.50	1.00-1.70	
H-13	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.75	0.80-1.20	.	
H-14	0.35-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	.	.	4.00-5.25	
H-19	0.32-0.45	0.20-0.50	<0.03	<0.03	0.20-0.50	.	4.00-4.75	4.00-4.50	0.30-0.55	1.75-2.20	3.75-4.50	
H-21	0.26-0.36	0.15-0.40	<0.03	<0.03	0.15-0.50	.	3.00-3.75	.	.	0.30-0.60	8.50-10.00	
H-22	0.30-0.40	0.15-0.40	<0.03	<0.03	0.15-0.40	.	1.75-3.75	.	.	0.25-0.50	10.00-11.75	
H-23	0.25-0.35	0.15-0.40	<0.03	<0.03	0.15-0.60	.	11.00-12.75	.	.	0.75-1.25	11.00-12.75	
H-24	0.42-0.53	0.15-0.40	<0.03	<0.03	0.15-0.40	.	2.50-3.50	.	.	0.40-0.60	14.00-16.00	
H-26	0.45-0.55	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-4.50	.	.	0.75-1.25	17.25-19.00	
H-42	0.55-0.70	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	
L-2	0.45-1.00	0.10-0.90	<0.03	<0.03	<0.50	.	0.70-1.20	.	<0.25	0.10-0.30	.	
L-6	0.65-0.75	0.25-0.80	<0.03	<0.03	<0.50	1.25-2.00	0.60-1.20	.	<0.50	.	.	
M-1	0.78-0.88	0.15-0.40	<0.03	<0.03	0.20-0.50	.	3.50-4.00	.	8.20-9.20	1.00-1.35	1.40-2.10	
M-2	0.78-1.05	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	
M-3.1	1.00-1.10	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.25-2.75	5.00-6.75	
M-3.2	1.15-1.25	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.75-3.25	5.00-6.75	
M-4	1.25-1.40	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.75	.	4.25-5.50	3.75-4.50	5.25-6.50	
M-6	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	11.00-13.00	4.50-5.50	1.30-1.70	3.75-4.75	
M-7	0.97-1.05	0.15-0.40	<0.03	<0.03	0.20-0.55	.	3.50-4.00	.	8.20-9.20	1.75-2.25	1.40-2.10	
M-10	0.84-1.05	0.10-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	7.75-8.50	1.80-2.20	.	
M-30	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.25	4.50-5.50	7.75-9.00	1.00-1.40	1.30-2.30	
M-33	0.85-0.92	0.15-0.40	<0.03	<0.03	0.25-0.55	.	3.50-4.00	7.75-8.75	9.00-10.00	1.00-1.35	1.30-2.10	
M-34	0.85-0.92	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.00	7.75-8.75	7.75-9.20	1.90-2.30	1.40-2.10	
M-36	0.80-0.90	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	7.75-8.75	4.50-5.50	1.75-2.25	5.50-6.50	
M-41	1.05-1.15	0.20-0.60	<0.03	<0.03	0.15-0.50	.	3.75-4.50	4.75-5.75	3.25-4.25	1.75-2.25	6.25-7.00	
M-42	1.05-1.15	0.15-0.40	<0.03	<0.03	0.15-0.65	.	3.50-4.25	7.75-8.75	9.00-10.00	0.95-1.35	1.15-1.85	
M-46	1.22-1.30	0.20-0.40	<0.03	<0.03	0.40-0.65	.	3.70-4.20	7.80-8.80	8.00-8.50	3.00-3.30	1.90-2.20	
M-48	1.50	3.75	9.00	5.25	3.10	10.0	
M-52	0.90	4.00	.	4.00	2.00	1.25	
M-61	1.60	4.00	.	6.50	5.00	12.0	
M-62	1.30	3.75	.	10.5	2.00	6.25	
O-1	0.85-1.00	1.00-1.40	<0.03	<0.03	<0.50	.	0.40-0.60	.	.	<0.30	0.40-0.60	
O-2	0.85-0.95	1.40-1.80	<0.03	<0.03	<0.50	.	<0.35	.	<0.30	<0.30	.	
O-6	1.25-1.55	0.30-1.10	<0.03	<0.03	0.55-1.50	.	<0.30	.	0.20-0.30	.	.	
O-7	1.10-1.30	<1.00	<0.03	<0.03	<0.60	.	0.35-0.85	.	<0.30	<0.40	1.00-2.00	
P-20	0.28-0.40	0.60-1.00	<0.03	<0.03	0.20-0.80	.	1.40-2.00	.	0.30-0.55	.	.	
P-21	0.18-0.22	0.20-0.40	<0.03	<0.03	0.20-0.40	4.00-4.25	0.20-0.30	.	.	0.15-0.25	.	Al: 1.05-1.25
P-6	0.05-0.15	0.35-0.70	<0.03	<0.03	0.10-0.40	3.25-3.75	1.25-1.75	
S-1	0.40-0.55	0.10-0.40	<0.03	<0.03	0.15-1.20	.	1.00-1.80	.	<0.50	0.15-0.30	1.50-3.00	
S-2	0.40-0.55	0.30-0.50	<0.03	<0.03	0.90-1.20	.	.	.	0.30-0.60	<0.50	.	
S-4	0.50-0.65	0.60-0.95	<0.03	<0.03	1.75-2.25	.	<0.35	.	.	<0.35	.	
S-5	0.50-0.65	0.60-1.00	<0.03	<0.03	1.75-2.25	.	<0.35	.	0.20-1.35	<0.35	.	
S-6	0.40-0.50	1.20-1.50	<0.03	<0.03	2.00-2.50	.	1.20-1.50	.	0.30-0.50	0.20-0.40	.	
S-7	0.45-0.55	0.20-0.80	<0.03	<0.03	0.20-1.00	.	3.00-3.50	.	1.30-1.80	0.20-0.30*	.	
T-1	0.65-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	.	.	0.90-1.30	17.25-18.25	
T-15	1.50-1.60	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-5.00	4.75-5.25	<1.00	4.50-5.25	11.75-13.00	
T-4	0.70-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	0.80-1.20	17.50-19.00	
T-5	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-5.00	7.00-9.50	0.50-1.25	1.80-2.40	17.50-19.00	
T-6	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	4.00-4.75	11.00-13.00	0.40-1.00	1.50-2.10	18.50-21.00	
T-8	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	1.80-2.40	13.25-14.75	
W-1	0.70-1.50	0.10-0.40	<0.025	<0.025	0.10-0.40	<0.20	<0.15	.	<0.10	<0.10	<0.15	Cu: <0.20
W-2	0.85-1.50	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	<0.15	.	<0.10	0.15-0.35	<0.15	Cu: <0.20
W-5	1.05-1.15	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	0.40-0.60	.	<0.10	<0.10	<0.15	Cu: <0.20
Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other

These are specifications, not samples for sale.

STAINLESS AND HIGH ALLOY STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	N	Nb	Other
13-8PH	<0.05	<0.20	<0.01	<0.008	<0.10	.	7.50-8.50	12.25-13.25	2.00-2.50	<0.01	.	Al: 0.90-1.35
15-5PH	<0.07	<1.00	<0.04	<0.03	<1.00	2.50-4.50	3.50-5.50	14.00-15.50	.	.	0.15-0.45	
17-4PH	<0.07	<1.00	<0.04	<0.03	<1.00	3.00-5.00	3.00-5.00	15.00-17.50	.	.	0.15-0.45	
201	<0.15	5.5-7.5	<0.060	<0.03	<1.00	.	3.50-5.50	16.00-18.00	.	<0.25	.	
202	<0.15	7.5-10.0	<0.060	<0.03	<1.00	.	4.00-6.00	17.00-19.00	.	<0.25	.	
301	<0.15	<2.00	<0.045	<0.03	<1.00	.	6.00-8.00	16.00-18.00	.	.	.	
302	<0.15	<2.00	<0.045	<0.03	<1.00	.	8.00-10.00	17.00-19.00	.	.	.	
302B	<0.15	<2.00	<0.045	<0.03	2.00-3.00	.	8.00-10.00	17.00-19.00	.	.	.	
303	<0.15	<2.00	<0.20	>0.15	<1.00	.	8.00-10.00	17.00-19.00	<0.60*	.	.	Zr: <0.60*
304	<0.08	<2.00	<0.045	<0.03	<1.00	.	8.00-10.50	18.00-20.00	.	.	.	
304L	<0.03	<2.00	<0.045	<0.03	<1.00	.	8.00-12.00	18.00-20.00	.	.	.	
305	<0.12	<2.00	<0.045	<0.03	<1.00	.	10.00-13.00	17.00-19.00	.	.	.	
308	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-12.00	19.00-21.00	.	.	.	
309	<0.20	<2.00	<0.045	<0.03	<1.00	.	12.00-15.00	22.00-24.00	.	.	.	
310	<0.25	<2.00	<0.045	<0.03	<1.50	.	19.00-22.00	24.00-26.00	.	.	.	
314	<0.25	<2.00	<0.045	<0.03	1.50-3.00	.	19.00-22.00	23.00-26.00	.	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316L	<0.03	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
321	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-12.00	17.00-19.00	.	.	.	Ti: >5xC
347	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
348	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	Ta: <0.10
384	<0.08	<2.00	<0.045	<0.03	<1.00	.	17.00-19.00	15.00-17.00	.	.	.	
385	<0.08	<2.00	<0.045	<0.03	<1.00	.	14.00-16.00	11.50-13.50	.	.	.	
403	<0.15	<1.00	<0.04	<0.03	<0.50	.	.	11.50-13.00	.	.	.	
405	<0.08	<1.00	<0.04	<0.03	<1.00	.	.	11.50-14.50	.	.	.	Al: 0.10-0.30
409	<0.08	<1.00	<0.04	<0.01	<1.00	.	<0.50	10.50-11.75	.	.	.	Ti: 6\mtC-0.75
410	<0.15	<1.00	<0.04	<0.03	<1.00	.	.	11.50-13.50	.	.	.	
414	<0.15	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	11.50-13.50	.	.	.	
416	<0.15	<1.25	<0.06	>0.15	<1.00	.	.	12.00-14.00	<0.60*	.	.	Zr: <0.60*
420	>0.15	<1.00	<0.04	<0.03	<1.00	.	.	12.00-14.00	.	.	.	
422	0.20-0.25	<1.00	<0.04	<0.03	<0.75	<0.50	0.50-1.00	11.00-12.50	0.75-1.25	.	.	V: 0.15-0.30
422	continued											W: 0.75-1.25
430	<0.12	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	.	.	.	
430F	<0.12	<1.25	<0.06	>0.15	<1.00	.	.	16.00-18.00	<0.60*	.	.	Zr: <0.60*
431	<0.20	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	15.00-17.00	.	.	.	
440A	0.60-0.75	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440B	0.75-0.95	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440C	0.95-1.20	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
450	<0.05	<1.00	<0.03	<0.03	<1.00	1.25-1.75	5.00-7.00	14.00-16.00	0.50-1.00	.	8\mtC	
455	<0.05	<0.50	<0.04	<0.03	<0.50	1.50-2.50	7.50-9.50	11.00-12.50	<0.50	.	0.10-0.50	Ti: 0.80-1.40
501	>0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
502	<0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
Duplex	<0.05	<3.00	<0.035	<0.03	<1.50	<2.50*	4.00-7.00	18.00-25.00	0.20-5.50	<0.40	.	

These are specifications, not
samples for sale.