

INDEX

- ALUMINUM [2, 4](#)
ALUMINUM IN XRF DISCS [15](#)
AUSMON [24, 25](#)
- BARIUM IN XRF DISCS [15](#)
BAUXITE [24](#)
BORON IN XRF DISCS [15](#)
BRASS [5](#)
BRONZE [5](#)
- CALCIUM IN XRF DISCS [16](#)
CARBONATE IN XRF DISC [16](#)
CARBON STEEL [11, 12](#)
CAST IRON [9, 10](#)
CEMENT [24](#)
CERAMIC [5](#)
COBALT [5](#)
COPPER [5](#)
- ELEMENTS IN XRF DISCS [17](#)
- FLUORITE IN XRF DISCS [16](#)
- GLASS XRF DISCS AND PLATES [17](#)
- HIGH ALLOY STEEL [14](#)
- ILMENITE [24](#)
IRON [9, 10](#)
IRON ORE [24](#)
- LAYER [7](#)
LEAD [6](#)
LEAD IN XRF DISCS [17](#)
LOW ALLOY STEEL [11, 12, 13](#)
- MAGNESIUM [6](#)
MANGANESE ORE [24](#)
MINERAL SANDS [24](#)
MONAZITE [24](#)
MULTI-ELEMENT XRF DISCS [19](#)
- NEODYMIUM IN XRF DISCS [17](#)
NICKEL [7](#)
NICKEL ORE [24](#)
- PHOSPHORUS IN XRF DISCS [17](#)
- RARE EARTHS [24](#)
RoHS [7](#)
RUTILE [24](#)
- SETS [10, 13](#)
SILICA IN XRF DISCS [18, 24](#)
STAINLESS STEEL [13, 14](#)
SULFIDES [24](#)
- TIN [7](#)
- URANIUM IN XRF DISCS [18](#)
- WEEE [7](#)
- XENOTIME [24](#)
XRF DISCS [7, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25](#)
- ZINC [8](#)
ZINC IN XRF DISCS [18](#)
ZIRCONIUM IN XRF DISCS [18](#)

PURITY ALUMINUM SETTING-UP SAMPLES

typical analysis listed in mass % except * which is mg/kg

Number	Si	Ag	As	B*	Ba*	Be	Bi	Ca	Cd	Ce	Co	Cr	Cu	Fe
AL RC11/08	0.028	0.010	0.0036	.	74	0.0015	0.010	0.0016	0.0049	0.0020	0.013	0.013	0.015	0.045
R A 10	<0.0050	<0.0005	.	<5	.	<0.0001	<0.0020	<0.0005	<0.0010	.	<0.0010	<0.0010	<0.0010	<0.0010
AL RC10/02	<0.002	<0.0002	.	<2	<1	<0.0001	<0.0002	<0.0001	<0.0002	.	<0.0002	<0.0002	<0.0002	<0.001
ARM 220H	0.002	<0.0005	.	<2	<1	<0.0001	<0.0010	<0.0005	<0.0005	<0.0015	<0.001	<0.0003	0.001	<0.0005
KUT Al 4N	0.0013	.	.	0.6	.	0.00001	0.00001	0.00002	0.0001	.	.	0.00006	0.0025	0.0018
V E10	<0.0010	<0.00005	.	<2	<3	<0.00002	<0.0003	<0.0001	<0.0001	.	<0.0001	<0.0001	<0.0004	<0.0005
V E1/0	<0.0005	<0.00001	.	<2	<1	<0.00001	<0.00005	<0.0001	<0.00002	.	<0.00001	<0.00005	<0.0004	<0.0003
V E0	<0.00008	<0.00001	.	<0.4	<0.1	<0.00001	<0.00002	<0.00004	<0.00002	.	<0.00001	<0.00003	<0.00004	<0.00005
AA SQ-10
C Fe 0

Number	Ga	Hg	In	La	Li	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sc
AL RC11/08	0.021	0.0045	0.010	0.012	0.0004	0.017	0.016	0.033	0.0017	0.010	0.0020	0.014	0.013	0.0093
R A 10	<0.0010	.	.	.	<0.0010	<0.0010	<0.0010	.	<0.0001	<0.0020	.	<0.0010	<0.0020	.
AL RC10/02	<0.0002	.	<0.0002	.	<0.0001	<0.0003	<0.0002	.	<0.0001	0.0002	<0.0005	<0.0003	<0.0003	.
ARM 220H	<0.0005	<0.0010	<0.0003	<0.0003	<0.0001	<0.0005	<0.0003	<0.0005	<0.0001	<0.0010	<0.0005	<0.0003	<0.0003	<0.0005
KUT Al 4N	<0.0001	.	.	.	0.00002	0.0015	0.0002	.	0.0001	0.00004	.	0.0001	0.0002	.
V E10	<0.00002	.	<0.0002	.	<0.00002	<0.0003	<0.0001	.	<0.0001	<0.0001	.	<0.0002	<0.0003	.
V E1	<0.00001	.	<0.00001	.	<0.00001	<0.0003	<0.00005	.	<0.0001	<0.00005	.	<0.00005	<0.0001	.
V E0	.	.	<0.00001	.	<0.00001	<0.00006	<0.00002	.	<0.00002	<0.00001	.	<0.00001	<0.00002	.
AA SQ-10
C Al 0

Number	Sn	Sr	Ti	V	W	Zn	Zr	Units
AL RC11/08	0.016	0.0050	0.016	0.016	0.0044	0.018	0.015	60 mm Ø x 25 mm
R A 10	<0.0010	<0.0010	<0.0010	<0.0010	.	<0.0010	<0.0010	50 mm Ø x 50 mm
AL RC10/02	<0.0002	<0.0001	0.0004	<0.0002	.	<0.0005	<0.0002	60 mm Ø x 25 mm
ARM 220H	<0.0005	<0.0001	<0.0002	<0.0010	.	<0.0010	<0.0005	57 mm Ø x 30 mm HE: <0.001, V: <0.0030
KUT Al 4N	0.00005	0.0001	0.00006	0.0001	.	0.0003	0.00005	50 mm Ø x 35 mm
V E10	<0.0003	<0.00005	<0.0001	<0.0002	.	<0.0003	<0.0001	60 mm Ø x 40 mm
V E1	<0.00002	<0.00005	<0.0001	<0.00003	.	<0.0002	<0.00005	60 mm Ø x 40 mm
V E0	<0.00002	<0.00002	<0.00005	<0.00003	.	<0.00005	<0.00003	60 mm Ø x 40 mm
AA SQ-10	64 mm Ø x 37 mm
C Al 0	50 mm Ø x 30-50 mm

POT METAL SETTING-UP SAMPLE typical analysis

Number	Base Metal	B	Li	Na	Units
AA SQ-18	P0506	0.02	0.02	0.02	64 mm Ø x 25 mm

SPECIALTY ALUMINUM SETTING-UP SAMPLES

typical analysis

Number	As	Bi	Cu	Fe	Mg	P	Pb	Sb	Sc	Si	Ti	Units
PY 10914	.	0.7	0.3	0.2	1.2	.	0.8	.	.	0.9	0.05	60 mm Ø x 41 mm
AA SQ-19	0.03	0.014	.	0.02	0.20	.	.	64 mm Ø x 37 mm

ALUMINUM SETTING-UP SAMPLES, chart 1 of 2

typical analysis

Number	Si	Cu	Fe	Mg	Mn	Ni	Zn	Be	Ca	Cr	Na	Pb	Sb	Sn	Sr	Ti
C Al 4	18	0.01	5	<0.001	0.03	1.9	<0.01	.	0.009	.	.	<0.01
PY 9601	17.3	1.21	0.43	1.09	0.12	1.1	0.07	.	0.0026	.	0.0003	0.006	0.02	0.004	0.0058	0.08
KUT ASC-1	14.0	6.0	1.6	1.2	0.4	0.6	0.5	0.003	0.02	0.2	.	0.1	0.02	0.1	0.03	0.5
AL RC40/02	13.2	1.03	1.19	1.09	.	.	6.03	.	0.0131	.	.	0.10	.	0.21	0.14	0.20
PY 9327	12.8	0.01	0.15	0.003	0.005	0.003	0.01	.	<0.0007	.	<0.0004	0.001	<0.0003	0.0003	.	0.006
PY 9326	12.8	0.01	0.15	0.003	0.005	0.003	0.01	.	<0.0007	.	<0.0004	0.001	<0.0003	0.0003	.	0.006
R A 18	12.7	8.4	0.2	0.2	0.3	2.9	0.35	.	<0.005	<0.01	<0.005	0.4	0.1	0.3	<0.01	<0.003
AL RC40/03	12.5	1.03	1.23	1.05	.	.	6.14	.	0.0195	.	.	0.11	.	0.21	0.14	0.20
AA SQ-15	12.0	0.5	0.7	1.2	0.05	2.5	.	.	.	0.05	0.02	0.1
PY 9415	11.7	1.24	0.53	1	0.12	0.86	0.07	.	0.0006	.	0.00004	0.01	0.01	0.01	.	0.02
PY 2150	10.6	0.6	.	0.9	0.4	0.5	1.2	.	.	0.06	.	0.8	.	0.3	0.1	0.3
V E3	10.0	4.0	.	.	.	0.9	.	.	0.009	.	.	0.25	0.3	.	.	.
C Al 5	8.8	1.4	0.7	1.9	0.08	1.3	0.24	.	.	0.08	.	0.07	.	0.07	.	0.09
PY 9313	8.8	0.003	0.1	0.32	0.005	<0.002	0.01	.	0.0009	.	<0.0004	<0.0004	<0.003	0.0004	.	0.12
PY 2001	8.5	2.9	0.7	0.22	0.23	0.05	0.13	.	0.002	.	.	0.07	.	0.012	.	0.08
PY 9520	6.6	0.012	0.1	0.34	0.005	0.003	0.017	.	0.0044	.	0.0005	<0.0001	<0.008	0.0004	0.052	0.12
PY 9517	6.4	2.8	0.48	0.3	0.25	0.02	0.2	.	0.009	.	0.001	0.02	0.01	0.01	0.014	0.13
AL RC41/01	5.9	5.1	0.4	0.09	0.5	0.02	1.3	.	0.004	0.03	.	0.02	.	0.02	0.02	0.03
PY 9809	5.5	.	0.5	.	.	1.9
PY 20001	5.4	3.1	0.48	0.23	0.22	0.03	0.14	.	0.0033	.	0.00004	0.01	.	0.01	.	0.07
58A AC19215b	5.05	0.049	1.0	0.08
AA SQ-16	4.0	10.0	1.0	0.3	0.2	0.2	0.2
58A AC19214b	3.96	0.096	2.07	0.041
58A AC19213b	2.88	0.21	3.15	0.017
AL RC60/02	1.34	0.29	0.49	0.92	1.1	0.10	0.10	.	.	0.20	0.21
R A 19	1.25	0.51	0.90	8.0	1.1	0.51	7.73	0.006	0.001	0.15	0.001	<0.01	.	.	.	0.23
C Al 2	1.205	0.0614	0.439	0.809	0.662	0.0036	0.052
KUT AMS-1	1.2	0.6	0.8	1.3	0.5	0.02	0.4	0.002	0.01	0.2	0.005	0.05	0.02	0.03	.	0.2
PY 2006	1.2	0.07	0.11	6.2	0.07	0.06	7.8	0.01	0.03	.	0.02	0.04	.	0.06	.	0.06
3.2315	1.12	0.08	0.22	0.65	0.66	0.003	0.006	.	.	0.005	.	0.008	0.001	0.005	.	0.04
AA SQ-12	1.1	4.8	0.6	0.15	1.1	0.25	0.20	0.005	.	.	.	0.06	.	0.06	.	.
PY 2004	1.1	0.08	0.11	6.1	0.07	0.07	7.7	0.01	0.03	.	0.03	0.04	.	0.06	.	0.06
164X ALSUS 7	0.9	4	0.55	0.15	0.06	1.1	0.12	0.1	<0.001	0.01	.	0.11	0.12	0.01	0.003	0.3
V E2	0.9	0.20	0.9	0.20	0.20	0.20	0.10	0.004	0.008	0.05	0.008	0.10	.	0.20	0.11	0.20

Number	Si	Cu	Fe	Mg	Mn	Ni	Zn	Be	Ca	Cr	Na	Pb	Sb	Sn	Sr	Ti
Number	Ag	As	B	Bi	Cd	Co	Ga	In	Li	Mo	P	V	Zr	Al	Ø X H mm	
C Al 4	.	.	0.0008	75	50x30-50	
PY 9601	0.0086	.	.	.	50 x 50	
KUT ASC-1	.	.	.	0.1	0.05	.	0.04	0.02	0.01	.	45 x 35	
AL RC40/02	60 x 25	Sc: 0.20
PY 9327	0.0017	.	.	.	50 x 50	
PY 9326	0.0017	.	.	.	50 x 50	
R A 18	.	<0.01	<0.01	<0.01	.	<0.01	<0.01	.	.	<0.1	<0.01	<0.01	<0.01	Rem	50 x 50	Sc: 0.20
AL RC40/03	60 x 25	
AA SQ-15	64 x 37	
PY 9415	0.0058	.	.	.	50 x 50	
PY 2150	0.9	.	.	0.02	.	0.04	.	0.06	.	0.04	.	0.02	.	.	60 x 40	
V E3	.	.	0.01	0.007	60 x 40	
C Al 5	.	.	0.0010	0.0050	.	.	85.3	50x30-50	
PY 9313	0.0011	.	.	.	50 x 50	
PY 2001	50 x 50	
PY 9520	0.0009	.	.	.	50 x 50	
PY 9517	0.002	.	.	.	50 x 50	
AL RC41/01	0.001	.	0.01	0.008	0.005	.	60 x 25	
PY 9809	0.01	0.12	0.14	.	60 x 40	
PY 20001	0.001	.	.	.	50 x 50	
58A AC19215b	0.083	45 x 35	
AA SQ-16	64 x 37	
58A AC19214b	0.044	45 x 35	
58A AC19213b	0.024	45 x 35	
AL RC60/02	.	.	.	0.10	.	.	0.011	.	.	0.0045	0.11	.	.	.	60 x 25	
R A 19	0.19	.	0.002	0.10	0.03	0.38	0.06	0.06	<0.01	.	.	0.14	0.18	Rem	50 x 50	
C Al 2	0.010	50x30-50	
KUT AMS-1	.	.	0.004	0.01	0.03	.	0.01	.	0.01	.	.	0.03	.	.	45 x 35	
PY 2006	0.01	.	0.03	.	0.01	.	.	.	0.02	.	50 x 50	
3.2315	Rem	40 x 25	
AA SQ-12	0.05	.	.	0.06	0.20	0.01	0.03	0.10	0.15	.	64 x 37	Hg: 0.01
PY 2004	0.02	.	0.03	.	0.01	.	.	.	0.02	.	60 x 40	
164X ALSUS 7	0.2	0.18	.	40 x 15	
V E2	0.22	0.04	0.06	0.11	.	.	60 x 40	

ALUMINUM SETTING-UP SAMPLES, chart 2 of 2

typical analysis

Number	Si	Cu	Fe	Mg	Mn	Ni	Zn	Be	Ca	Cr	Na	Pb	Sb	Sn	Sr	Ti
PY 9632	0.8	4.1	0.32	0.48	0.71	.	0.033	.	.	0.0181	.	0.0096	.	.	.	0.022
AA SQ-17	0.7	0.35	0.4	1.6	0.12	0.12	0.12	0.005	.	0.25	.	0.1	.	0.1	.	0.08
BS 6061	0.55	0.29	0.19	0.81	0.010	0.004	0.04	.	.	0.050	.	0.010	.	<0.001	.	0.024
3.1645	0.5	3.3	0.4	0.7	0.6	0.03	0.2	.	.	0.02	.	0.8	<0.01	.	.	0.07
AA SQ-13	0.5	0.04	0.6	0.04	0.04	0.04	0.04	0.005	.	0.04	.	0.04	.	0.04	.	0.04
AL RC50/02	0.5	0.003	0.85	4.5	0.005	0.5	0.02	0.005	0.02	0.5	0.004	.	0.05	0.3	0.02	.
PY 906	0.40	0.005	0.19	0.43	0.03	0.005	0.019	.	.	<0.004	<0.0001	0.011
BS 2017	0.30	4.05	0.25	0.51	0.51	0.006	0.065	.	.	0.015	.	0.010	.	0.002	.	0.020
IARM 221C	0.2	0.6	0.2	4.8	0.4	.	6.8	0.005	0.03	0.2	.	.	0.01	.	.	0.1
IARM 221D	0.2	0.6	0.2	4.7	0.4	.	6.7	0.005	0.03	0.2	.	.	0.02	.	.	0.1
IARM 221B	0.2	0.6	0.2	4.8	0.4	.	6.8	0.005	0.03	0.2	.	.	0.01	.	.	0.1
AA SQ-11	0.2	0.5	0.2	3.0	0.4	.	6.6	0.005	0.02	0.25	0.10
PY 9627	0.2	0.13	0.57	0.0004	1.06	0.01	0.057	.	.	0.0223	<0.00002	0.0065	.	.	.	0.022
PY 310	0.16	0.0037	0.58	0.0003	0.0078	0.004	0.017	.	.	0.0028	<0.00002	0.0019	.	.	.	0.004
3.4345	0.15	1.48	0.29	2.55	0.09	0.005	5.59	.	.	0.2	.	0.01	.	0.02	.	0.03
C Al 3	0.11	0.02	0.27	2.61	0.44	0.005	0.08	.	.	0.13	.	0.006	.	<0.0003	.	<0.001
PY 9325	0.11	0.0069	0.24	4.33	0.4	.	0.014	0.0001	0.0003	0.0007	<0.00002	0.007	.	.	.	0.005
PY 9324	0.11	0.0055	0.24	4.28	0.4	.	0.014	0.0001	0.0003	0.0007	<0.00002	0.007	.	.	.	0.005
BS 7075	0.10	1.40	0.13	2.26	0.03	0.005	5.6	.	.	0.19	.	0.003	.	0.001	.	0.028
3.4365	0.1	1.7	0.3	2.5	0.1	0.01	5.6	.	.	0.2	.	0.03	.	0.03	.	0.08
AA SQ-14	0.1	0.5	0.1	0.9	0.4	0.4	1.2	0.002	.	.	.	0.5	.	0.1	.	0.1
PY 9630	0.1	0.062	0.46	0.0006	0.0123	0.008	0.054	.	.	0.0216	0.00003	0.0035	.	.	.	0.018
PY 325	0.1	0.003	0.27	0.74	0.005	<0.001	0.021	.	0.0011	0.011	0.0001	0.001	.	.	.	0.01
PY 9806-1	0.08	6.9	1.3	0.08	1.9	0.05	0.05	.	.	0.3	.	.	0.4	.	.	.
BS 2024	0.08	4.7	0.20	1.30	0.57	0.006	0.07	.	.	0.03	.	0.006	.	0.001	.	0.030
3.3525	0.08	0.004	0.17	2.8	0.22	0.002	0.007	.	.	0.001	.	0.002	.	0.002	.	0.009
PY 9614	0.08	0.043	0.18	2.28	0.055	0.01	0.051	.	0.0009	0.21	0.00006	0.0057	.	.	.	0.019
PY 9321	0.07	4.2	0.013	0.27	0.02	0.01	0.04	.	.	<0.00002	0.001	0.21
BS 2011	0.052	5.2	0.32	0.016	0.010	0.004	0.024	.	.	0.001	.	0.56	.	0.001	.	0.006
PY 9401	0.04	1.58	0.12	2.29	0.01	0.007	5.84	.	.	0.006	<0.00002	0.032
AL RC20/02	0.029	6.0	0.061	0.29	0.24	1.45	0.24	0.41	0.20	0.051	.	.
V E8	0.012	0.020	0.013	0.005	0.006	0.004	0.005	0.001	0.004	0.005	.	0.003	0.010	0.004	0.002	0.004
R Al Mn 12	12
R Al Ce	Ce: 1	.	.	5	La: 0.4	.	Nd: 0.1	.	Pr: 0.05	.	Sm: 0.01	.	Y: 0.2	.	.	.
V E5	.	.	.	4.8	1.3
V E4	.	.	.	1.1	0.7	.	5.2	.	.	0.2
V E13	.	.	4.8

Number	Si	Cu	Fe	Mg	Mn	Ni	Zn	Be	Ca	Cr	Na	Pb	Sb	Sn	Sr	Ti
PY 9632	0.033	.	50 x 50	.	.	.
AA SQ-17	.	.	.	0.08	.	.	0.03	.	.	.	0.03	.	64 x 37	.	.	.
BS 6061	.	.	.	0.006	0.01	<0.002	.	62 x 50	.	.	.
3.1645	.	.	.	0.01	.	.	0.01	Rem	40 x 25	.	.	.
AA SQ-13	.	.	.	0.04	0.04	0.01	0.03	.	.	0.04	0.4	.	64 x 37	.	.	.
AL RC50/02	Ce:0.1	0.005	0.02	La:0.1	0.2	Mo:0.03	0.03	P:0.005	0.05	0.003	0.01	0.01	W:0.04	60 x 25	.	.
PY 906	.	.	.	0.002	0.007	0.002	.	50 x 50	.	.	.
BS 2017	62 x 50	.	.	.
IARM 221C	0.2	.	0.03	63 x 39	.	.	.
IARM 221D	0.2	.	0.03	63 x 39	.	.	.
IARM 221B	0.2	.	0.03	63 x 39	.	.	.
AA SQ-11	0.01	.	0.03	64 x 37	.	.	.
PY 9627	<0.0001	.	0.0001	.	0.00002	.	0.01	.	50 x 50	.	.	.
PY 310	<0.0002	.	<0.00002	.	0.00004	.	.	.	50 x 50	.	.	.
3.4345	Rem	40 x 25	.	.	.
C Al 3	0.008	96.1	~40-50 x 30-50	.	.
PY 9325	<0.0001	50 x 50	.	.	.
PY 9324	<0.0001	50 x 50	.	.	.
BS 7075	.	.	.	<0.001	0.006	0.006	.	62 x 50	.	.	.
3.4365	Rem	40 x 25	.	.	.
AA SQ-14	.	.	.	0.5	64 x 37	.	.	.
PY 9630	0.0002	.	.	0.0001	.	0.00007	.	.	50 x 50	.	.	.
PY 325	.	0.0007	0.006	0.0005	.	50 x 50	.	.	.
PY 9806-1	.	.	.	0.7	.	0.9	60 x 40	.	.	.
BS 2024	.	.	.	0.002	0.01	0.01	.	62 x 50	.	.	.
3.3525	Rem	40 x 25	.	.	.
PY 9614	0.0001	.	.	0.0004	.	.	.	0.02	50 x 50	.	.	.
PY 9321	50 x 50	.	.	.
BS 2011	.	.	.	0.44	0.007	<0.002	.	62 x 50	.	.	.
PY 9401	0.13	.	50 x 50	.	.	.
AL RC20/02	0.73	.	.	0.38	0.036	0.44	0.17	60 x 25	.	.	.
V E8	0.005	.	0.005	0.006	0.003	0.003	0.006	.	0.005	.	0.003	0.003	60 x 40	.	.	.
R Al Mn 12	50 x 50	.	.	.
R Al Ce	0.02	.	40 x 25	.	.	.
V E5	.	.	.	0.2	0.01	.	.	.	60 x 40	.	.	.
V E4	0.20	.	.	.	0.06	0.4	0.2	.	60 x 40	.	.	.
V E13	60 x 40	.	.	.

Number	Ag	B	Ba	Bi	Cd	Co	Ga	Hg	In	Li	V	Zr	Al	Ø X H mm
--------	----	---	----	----	----	----	----	----	----	----	---	----	----	----------

CERAMIC SETTING-UP SAMPLE

Number	Al	C	Fe	O	Ti	W	Units
JK CE 650A	34	6	2.1	30	21	0.8	~25 mm Ø x 8 mm

COBALT BASE SETTING-UP SAMPLES

typical analysis T = trace, such as "<0.005" or "<0.01" ~35 mm Ø x ~25-35 mm

Number	Al	B	C	Cr	Cu	Fe	Mn	Mo	Nb	Ni	P	S	Si	Sn	Ta	Ti	V	W	Zr
R Co 16	0.13	0.03	0.31	0.03	0.92	21.3	0.02	2.76	1.82	<0.001	<0.001	<0.01	0.33	0.21	0.04	0.42	0.70	.	.
R Co 15	0.05	.	0.8	0.3	2	22	.	8	2	0.1	0.03	0.06	0.9	.	0.08	.	0.1	0.1	.
R Co 14	0.05	0.05	0.5	29	Co:51	0.9	0.3	.	.	10	<0.001	<0.01	0.7	.	.	.	<0.01	7	.
R Co 11	T	.	T	T	T	T	T	T	T	T	T	T	T	.	.	T	T	T	T

COPPER BASE SETTING-UP SAMPLES

typical analysis listed in mass %

Number	Cu	Sn	Zn	Al	Bi	Cr	Fe	Mn	Ni	Pb	Si	Ag	As	Au	Be
COPPER															
R C 11	Rem	<0.0010	<0.0005	.	<0.0030	<0.0005	<0.0005	<0.0010	<0.0005	<0.0030	<0.0005	<0.0010	<0.0010	.	.
2.0070	Rem	<0.001	<0.001	<0.001	.	<0.001	<0.001	<0.001	<0.001	<0.001	<0.001
R C 20	99.9
R C 110	Rem	0.006	0.006	0.002	0.004	0.004	0.005	0.004	0.002	0.003	0.003	0.005	0.001	0.002	0.0002
R C 14	Rem	<0.0005	<0.001	<0.002	<0.002	0.7	<0.01	<0.005	<0.005	<0.005	0.03
C Cu 3	0.0875	.
R C 38	67	0.01	0.01	<0.01	<0.01	<0.001	0.7	0.8	31	<0.01	0.02	<0.001	0.02	.	.
BRASS															
BS SU 464	[60.3]	0.73	38.8	.	.	.	0.05	.	0.007	0.04	0.004	.	0.001	.	.
R C 32	rem	0.03	35.7	1.7	0.02	<0.005	0.2	1.5	0.2	0.5	0.02	<0.001	<0.005	.	.
2.0401	Rem	0.2	39.9	.	.	.	0.2	<0.01	0.09	2.4	.	<0.01	<0.01	.	.
BRONZE															
R C 12	Rem	0.2	0.3	0.08	0.009	0.03	0.1	0.03	0.07	0.09	0.05	0.05	0.03	0.004	<0.001
165X PB10SUS	Rem	11	0.05	0.001	0.02	0.001	0.002	<0.001	0.06	0.04	0.001	.	0.02	.	.
BS SU 932A	83.5	6.88	2.29	.	0.003	.	0.008	0.002	0.19	6.9	0.011	0.0198	0.047	.	.
BS SU 932B	83.1	6.15	2.77	.	.	.	0.05	0.0005	0.52	7.1	0.004	0.0006	0.016	.	.
BS SU 936	82.5	7.0	0.25	0.001	.	.	0.003	0.001	0.36	9.6	0.004	.	0.002	.	.
BS SU 936A	82.5	7.0	0.24	0.0003	.	.	0.0007	0.0006	0.35	9.7	0.004	.	0.004	.	.
BS SU 932	82.1	7.28	2.80	.	0.002	.	0.03	0.002	0.19	7.4	0.015	0.0107	0.049	.	.
BS SU 936B	81.0	7.5	0.54	<0.005	.	<0.005	0.006	<0.001	0.51	10.2	0.003	.	0.01	.	.
R C 40	Rem	<0.01	<0.01	8	<0.01	.	1.5	5.5	2	0.02	0.02	.	<0.01	.	.
165X ALB1 SUS	82	0.03	0.06	9.0	0.015	0.01	2.8	0.08	5.3	0.20	0.10	.	0.005	.	.
R C 33	80	0.03	0.08	11	<0.006	0.03	3.8	0.2	4.6	<0.01	0.05	<0.001	0.02	.	.
R C 36	76	7.4	1.0	<0.005	0.01	<0.001	0.03	<0.005	1.6	14	<0.005	0.015	0.009	.	<0.001
BS SU 863	62.7	0.031	27.1	4.87	.	0.0005	2.3	2.85	0.06	0.040	0.025	.	<0.005	.	.
2.1052	Rem	11.3	0.10	0.002	<0.001	.	0.3	<0.001	0.40	0.4	<0.001	0.01	.	.	.
2.1090	Rem	6.86	3.81	.	0.005	.	0.09	<0.001	1.12	5.56	.	0.02	0.01	.	.

Number	Cu	Sn	Zn	Al	Bi	Cr	Fe	Mn	Ni	Pb	Si	Ag	As	Au	Be
--------	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----

Number	C	Ca	Cd	Co	Mg	O	P	S	Sb	Se	Te	Ti	Zr	Units
--------	---	----	----	----	----	---	---	---	----	----	----	----	----	-------

COPPER														
R C 11	.	.	<0.0001	<0.0010	<0.0001	(0.0010)	<0.0010	<0.0010	<0.0030	<0.0001	<0.0010	.	.	40 mm Ø x 40 mm
2.0070	<0.001	.	<0.001	40 mm Ø x 25 mm
R C 20	0.038	40 mm Ø x 40 mm
R C 110	.	.	0.003	0.003	0.003	.	0.003	0.004	0.006	0.005	0.007	0.001	<0.002	40 mm Ø x 40 mm
R C 14	<0.005	<0.001	0.1	40 mm Ø x 40 mm
C Cu 3	.	.	0.0096	0.0496	.	.	.	0.0229	.	0.0475	0.0194	.	last	40 mm Ø x 30 mm
R C 38	.	.	<0.01	<0.001	<0.001	.	<0.01	<0.01	0.01	.	.	.	<0.001	40 mm Ø x 40 mm
BRASS														
BS SU 464	0.0006	0.0009	0.005	0.001	0.006	38 mm Ø x 40 mm
R C 32	.	.	<0.001	.	.	.	<0.01	.	0.02	40 mm Ø x 40 mm
2.0401	<0.01	<0.001	40 mm Ø x 25 mm
BRONZE														
R C 12	.	.	0.05	0.04	0.003	.	0.1	0.05	0.04	0.01	0.01	0.003	<0.001	40 mm Ø x 40 mm
165X PB10SUS	.	.	.	0.01	.	.	0.002	0.03	0.15	0.01	.	.	.	~42 mm Ø x ~18 mm
BS SU 932A	0.001	0.007	0.053	0.15	38 mm Ø x 40+ mm
BS SU 932B	0.002	0.008	0.046	0.19	38 mm Ø x 40+ mm
BS SU 936	0.0008	.	.	0.009	.	0.003	0.07	0.007	0.10	50 mm Ø x 19 mm
BS SU 936A	0.009	.	.	0.008	.	0.0037	0.031	0.007	0.13	50 mm Ø x 19 mm
BS SU 932	0.002	0.008	0.051	0.13	38 mm Ø x 40+ mm
BS SU 936B	<0.05	.	0.01	.	.	0.01	0.03	0.03	0.14	38 mm Ø x 40+ mm
R C 40	<0.01	.	<0.01	40 mm Ø x 40 mm
165X ALB1 SUS	0.04	.	0.015	40 mm Ø x 18 mm
R C 33	.	.	<0.005	<0.01	<0.001	.	<0.01	<0.005	<0.001	40 mm Ø x 40 mm
R C 36	.	.	<0.001	<0.001	<0.001	.	<0.01	0.04	0.23	.	.	<0.001	<0.001	40 mm Ø x 40 mm
BS SU 863	0.002	.	.	<0.005	<0.005	.	0.0081	0.0003	0.009	.	.	.	<0.005	38 mm Ø x 40+ mm
2.1052	0.02	0.01	<0.001	40 mm Ø x 25 mm
2.1090	0.02	0.04	0.09	40 mm Ø x 25 mm

Number	C	Ca	Cd	Co	Mg	O	P	S	Sb	Se	Te	Ti	Zr	Units
--------	---	----	----	----	----	---	---	---	----	----	----	----	----	-------

LEAD BASE SETTING-UP SAMPLES

chill cast typical analysis listed in mass % except * which is mg/kg

Number	Sn	Sb	Ag	As	Bi	Cd	Cu	Fe	In	Ni	S	Te	Tl	Zn
R Pb 15	30	2.2	2.6	0.07	0.10	0.02	1.5	<0.001	<0.01	0.002	.	.	.	0.08
R Pb 17	3.8	10.2	1.6	0.09	0.1	0.001	1.8	0.002	<0.001	0.002	<0.001	0.003	.	<0.005
R Pb 13	0.14	0.15	0.05	0.05	0.29	0.06	0.14	0.03	(0.03)	0.06
R Pb 16	0.12	<0.001	0.002	<0.001	<0.01	<0.001	<0.001	<0.001	<0.0005	<0.001	0.002	.	<0.001	<0.001
R Pb 18	0.07	1.28	0.11	3.32	>3.34	0.02	0.05	<0.0001	0.02	<0.001	0.003	0.02	0.019	0.0001
R Pb 14	<0.005	12.6	0.008	1.4	0.02	<0.005	0.06	<0.001	<0.002	<0.001	0.01	<0.005	.	<0.001
R Pb 11	<0.0005	<0.0005	<0.0010	<0.0010	<0.0030	<0.0005	<0.0005	<0.0005	.	<0.0005	.	<0.0005	.	<0.0005
R Pb PM	.	.	0.0100

continued R Pb: 40 mm Ø x 30 mm 168X: ~45-50 mm Ø x ~20-40 mm

Number	Al	Au	Ba	Ca	Co*	Cr*	Ge	Hg	Ir*	Mg*	Mn*	Na	Pd	Pt	Rh*	Ru*	Se
R Pb 15
R Pb 17	0.002	0.003	(0.001)	0.001	(0.001)	.	.	.
R Pb 13	0.003
R Pb 16	0.03	.	(0.01)	0.2	(10)	.	<0.001
R Pb 18	<0.0001	.	.	<0.0001	<1	1	<10	(0.01)
R Pb 14
R Pb 11
R Pb PM	.	0.0100	3	.	.	.	0.0050	0.0050	50	50	.

MAGNESIUM BASE SETTING-UP SAMPLES

cast typical analysis listed in mass %

Number	Al	Cd	Cu	Fe	Mg	Mn	Ni	Pb	Si	Sn	Zn	Zr
R Mg 17	7.5	<0.01	<0.01	0.009	Rem	0.2	0.001	.	0.04	0.03	0.4	<0.001
R Mg 13 *	5.7	0.0001	0.006	0.001	Rem	0.2	0.001	0.001	0.01	0.001	0.8	0.004
C Mg 2 *	5.7	0.0001	0.006	0.001	Rem	0.2	0.001	0.001	0.01	0.001	0.8	0.004
R Mg 11	0.022	.	<0.003	<0.004	99.9	0.022	<0.005	.	0.037	.	<0.005	.
58A ST7310	0.004	.	1.64	0.0098	Rem	0.967	0.002	.	0.025	.	7.2	.
R Mg 18	.	.	.	<0.001	Rem	0.4

continued * currently R Mg 13 and C Mg 2 have the same chemistry

Number	Ce	La	Na	Nd	Pr	Sm	Y	Units
R Mg 17	.	.	<0.001	50 mm Ø x 50 mm
R Mg 13 *	.	.	0.001	50 mm Ø x 50 mm
C Mg 2 *	.	.	0.001	50 mm Ø x 40-50 mm
R Mg 11	50 mm Ø x 50 mm
58A ST7310	45 mm Ø x 25 mm
R Mg 18	0.05	0.08	.	2.3	0.09	0.1	5.3	50 mm Ø x 50 mm

NICKEL BASE SETTING-UP SAMPLES

typical analysis

Number	Ni	Al	C	Co	Cr	Cu	Fe	Mn	Mo	Nb	P	S	Si	Ti	W
R Ni 10	>99.9	<0.001	<0.005	<0.001	.	<0.001	0.02	<0.001	<0.002	.	.
2.4068	Rem	0.03	<0.01	0.03	0.04	<0.01	0.17	0.11	.	.	<0.01	<0.01	0.1	0.04	.
R Ni 11	99.4	<0.01	0.02	0.05	<0.01	.	0.06	0.27	.	.	<0.01	<0.01	0.18	<0.01	.
BS SU 750	71.0	0.92	0.05	0.11	15.3	0.027	8.22	0.155	0.147	1.05	0.006	0.002	0.148	2.56	<0.5
R Ni 17	Rem	0.01	0.20	0.2	0.8	0.3	18	0.25	0.2	0.2	<0.01	<0.01	0.32	0.3	10
R Ni 12	65	3	0.1	<0.01	0.01	29	1.2	0.6	.	.	<0.01	<0.01	0.09	0.6	.
2.4360	.	0.05	0.12	<0.001	<0.005	30	1.9	1.25	0.23	0.04	.
BS SU 625	[60.8]	0.16	0.022	0.040	21.8	0.15	3.83	0.096	9.11	3.52	0.008	<0.005	0.11	0.23	0.036
BS SU C-22	[57.8]	0.19	0.002	0.11	21.3	0.057	3.45	0.32	13.6	0.016	0.008	<0.005	<0.05	0.004	3.09
R Ni 13	57	0.3	0.01	0.06	17	0.01	4.6	0.04	17	0.05	<0.01	<0.01	(0.01)	0.02	3.3
BS SU 617	[53.5]	1.04	0.07	12.3	21.4	0.007	1.6	0.15	9.2	0.03	0.004	<0.005	0.2	0.4	0.02
2.4663	Rem	1.0	0.06	11.2	22	<0.001	0.3	0.03	8.9	<0.001	<0.01	.	0.03	0.4	0.06
R Ni 15	Rem	0.6	0.01	0.2	18	0.06	18	0.10	3	5	<0.01	<0.01	0.09	1	0.09
R Ni 14	50.5	0.5	0.05	19.4	20.9	0.01	0.3	0.2	5.2	.	0.01	<0.01	0.05	2.2	0.1
2.4665	Rem	0.12	0.08	1.0	22	0.08	19	0.40	8.6	0.18	0.02	.	0.32	0.01	0.8
2.4858	Rem	0.1	0.02	0.06	23.8	1.6	27.6	0.5	3.1	<0.003	0.02	.	0.3	1.1	.

Number	As	B	Ca	Mg	N	O	Pb	Sn	Ta	V	Zr	Units
R Ni 10	40 mm Ø x 40 mm
2.4068	40 mm Ø x 25 mm
R Ni 11	.	.	.	0.02	40 mm Ø x 40 mm
BS SU 750	<0.005	0.005	.	0.003	0.005	<0.05	.	.	<0.05	0.04	0.035	38 mm Ø x 40+ mm
R Ni 17	.	0.02	0.02	0.06	.	40 mm Ø x 30 mm
R Ni 12	<0.01	.	.	40 mm Ø x 40 mm
2.4360	40 mm Ø x 25 mm
BS SU 625	<0.005	0.0025	.	0.005	0.028	0.001	.	0.001	<0.05	0.015	0.001	38 mm Ø x 40+ mm
BS SU C-22	<0.005	0.001	.	0.004	<0.05	<0.005	.	0.002	0.004	0.009	.	38 mm Ø x 40 mm
R Ni 13	.	<0.01	<0.01	0.2	.	40 mm Ø x 40 mm
BS SU 617	0.002	0.005	<0.005	<0.005	0.004	<0.005	<0.005	<0.005	0.004	0.005	0.02	38 mm Ø x 40+ mm
2.4663	0.04	.	40 mm Ø x 25 mm
R Ni 15	.	<0.01	<0.01	0.09	0.02	40 mm Ø x 40 mm
R Ni 14	0.5	0.003	<0.01	0.01	40 mm Ø x 40 mm
2.4665	.	<0.01	0.03	.	40 mm Ø x 25 mm
2.4858	0.1	.	40 mm Ø x 25 mm

NICKEL-PHOSPHORUS LAYER ON STEEL

Number	Ni	P%	Pb%	Layer	Intended For	Unit
JK SUS NiP-1	Rem	5.8	0.26	8.7µm	GD-OES	plate 102mm x 68mm x 0.5mm

RoHS/WEEE DIRECTIVE XRF DISCS

available individually or in SET/3 typical analysis 40 mm Ø x 5 mm

Number	Al ₂ O ₃	B ₂ O ₃	Br	CaO	CdO	Cl	Cr ₂ O ₃	MgO	Na ₂ O	PbO	Sb ₂ O ₃	SiO ₂
BR ROHS 1/3	7.0	5.5	0	10.0	0	0	0	6.5	17.0	0	1.0	53.0
BR ROHS 2/3	7.0	4.536	0.100	10.0	0.011	0.5	0.146	6.5	17.0	0.107	1.1	53.0
BR ROHS 3/3	7.0	2.118	0.5	10.0	0.114	1.0	0.73	6.5	17.0	0.538	1.5	53.0

TIN BASE SETTING-UP SAMPLES

typical analysis

Number	Sn	As	Bi	Cu	Fe	Pb	Sb	Ag	Al	Au	Cd	Co	Ge
R Sn 10	>99.99	<0.0010	<0.0005	<0.0005	<0.0005	<0.0010	<0.0020	<0.0001	<0.0005	.	<0.0001	.	.
R Sn 11	99.9	<0.002	0.002	0.002	0.001	0.02	0.005
1611X SAC305	.	.	.	0.47	.	0.11	.	2.9	.	.	0.35	.	.
R Sn 21	Rem	0.006	0.1	0.4	0.1	0.09	0.06	10	0.02	.	<0.001	0.1	0.1
R Sn 13	84.7	<0.01	0.05	0.2	0.13	1.3	13.4	<0.01	0.04	.	0.02	0.05	.
R Sn 15	Rem	.	0.3	7.0	0.04	.	8	2.5	0.04	0.01	.	.	0.8
R Sn 20	Rem	<0.001	10	<0.01	<0.01	0.07	0.02	<0.001	<0.001	.	<0.001	<0.001	.
R Sn 12	Rem	0.3	0.1	1	<0.01	34	2	0.2	<0.001	.	0.1	<0.001	.
R Sn 14	45	.	40	12	.	.

Number	In	Ni	P	Pt	S	Se	Te	Tl	Zn	Units
R Sn 10	<0.0005	<0.0005	<0.0003	.	<0.0003	.	.	<0.0005	<0.0001	40 mm Ø x 40 mm
R Sn 11	<0.001	40 mm Ø x 40 mm
1611X SAC305	40 mm Ø x 6-10 mm last
R Sn 21	0.08	0.4	<0.001	<0.001	0.3	40 mm Ø x 40 mm
R Sn 13	<0.01	0.23	<0.001	0.02	40 mm Ø x 40 mm
R Sn 15	.	0.03	0.06	40 mm Ø x 40 mm
R Sn 20	7.7	<0.01	<0.01	<0.001	25	40 mm Ø x 40 mm
R Sn 12	0.1	<0.001	(0.03)	0.03	40 mm Ø x 40 mm
R Sn 14	.	.	0.05	40 mm Ø x 40 mm last

TITANIUM BASE SETTING-UP SAMPLES

typical analysis

40 mm Ø x 40 mm

Number	Ti	Al	C	Fe	Mo	Pd	Sn	V	Zr
R Ti 11	99.9	.	0.01	0.05
R Ti 12	Rem.	.	0.02	0.2	.	0.2	.	.	.
R Ti 13	Rem.	6	<0.01	0.2	.	.	.	4	.
R Ti 14	Rem.	6	<0.01	0.02	2	.	2	.	4

ZINC BASE SETTING-UP SAMPLES

typical analysis

169X, 1690X: 50 mm Ø x 20 mm

C: 40 mm Ø x 30-40 mm

JK, R: 40 mm Ø x 30 mm

Number	Al	Cd	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Sn	Tl	Ag	Bi	Cr	Ga	In	Ti	Zn
R Zn 14	8	0.02	2	0.06	0.09	0.03	<0.001	0.09	<0.001	0.04	<0.001	<0.001	.	.	.	<0.001	0.009	90
C Zn 3/4	3.93	0.001	0.071	0.016	0.055	.	.	0.0056	.	0.001
C Zn 4/8	0.93	0.10	0.51	1.26	.	0.99
R Zn 13	0.4	0.3	0.3	0.01	<0.01	<0.01	0.04	0.6	0.2	0.3	0.05	0.05	.	.	.	0.2	<0.01	97
R Zn 15	0.2	0.4	0.2	0.2	.	0.005	.	0.1	0.04	0.05	Rem
R Zn 16	0.23	0.049	0.011	0.092	.	.	.	0.23	.	0.009
JK SUS Zn-1	0.2024	0.0014	0.0014	0.0273	.	0.0006	0.0043	0.0021	0.00001	0.00003	0.0008	0.0002	0.00002	0.0055	0.00004	.	.	.
JK SUS Zn-5	0.1992	0.0063	0.0015	0.0318	.	0.0009	0.0047	0.0108	0.0024	0.0099	0.0003	0.0002	0.0136	0.0081	0.0019	0.0029	.	.
JK SUS Zn-2	0.1394	0.0075	0.0019	0.0314	.	0.0007	0.0043	0.0077	0.0034	0.0061	0.0005	0.0002	0.0056	0.0063	0.00004	.	.	.
R Zn 12	0.006	0.008	0.009	0.024	0.005	0.002	0.008	0.009	(0.01)	0.007	0.007	0.004	0.006	.	.	0.009	0.006	99.9
R Zn 11	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	.	<0.0005	<0.0010	99.99

CAST IRON SETTING-UP SAMPLES

chill cast		typical analysis															
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Nb	Sn	Ti	V	W	Mg	Ce
C Fe 5	4.12	0.2	0.09	0.03	0.36	0.08	0.08	0.11	0.11	0.05	<0.0015	0.003	0.02	0.13	.	.	.
NCS AH11355a	4.07	0.220	0.054	0.041	1.45	0.266	1.46	2.12	0.724	0.073	0.022	0.146	0.042	0.090	0.039	0.024	(0.0006)
SUS 5/58	3.8	0.60	.	0.006	2.1	0.006	1.02	0.02	0.073	0.04	.	0.07	0.004	0.49	.	0.09	0.03
SUS 2/50	3.6	0.71	0.28	0.10	1.8	0.41	0.48	0.04	0.09	0.01	.	0.13	0.05	0.54	.	.	.
SUS 5/59	3.5	0.66	.	0.008	1.9	0.006	1.06	0.01	.	0.04	.	0.07	0.004	0.46	.	0.10	0.03
SUS GGG	3.5	0.3	0.03	0.008	2.1	0.6	0.02	0.04	0.008	0.03	.	0.08	0.01	0.004	.	0.03	.
R G 13+Se	3.4	1.0	0.6	0.06	2.1	0.7	0.5	1.0	0.3	0.05	<0.01	0.3	0.03	0.3	0.01	.	.
SUS 3/21	3.4	0.90	1.0	0.10	2.2	0.01	0.01	0.25	<0.005	<0.005	.	<0.005	0.11	0.27	.	.	.
BS SU CCD	3.28	0.59	0.020	0.008	2.53	0.050	0.020	0.030	0.002	0.015	.	0.002	0.006	0.014	.	0.032	.
SUS 1/20	3.2	0.45	0.06	0.06	2.7	0.53	0.21	0.48	0.34	0.02	.	0.05	0.013	0.04	.	.	.
C Fe 8	3.2	0.42	0.025	0.02	1.3	0.062	0.11	0.05	<0.01	0.05	<0.001	0.01	0.05	0.04	<0.01	.	.
R G 16	3.2	0.2	0.2	<0.005	1.8	0.09	1.2	1.0	.	0.06	.	0.2	0.04	0.2	.	0.05	0.03
SUS 4/29	3.2	0.15	.	0.01	2.7	0.78	0.10	0.10	.	0.01	.	<0.005	0.06	0.51	.	0.02	.
R G 14	3.18	0.18	0.05	.	1.89	0.07	1.16	0.97	.	0.04	.	0.16	<0.01	0.15	.	0.06	0.04
R G 13	3.1	1.0	0.5	0.1	2.0	0.5	0.5	1.1	0.3	0.05	.	0.3	0.06	0.4	.	.	.
R N 15	2.9	1.6	0.008	0.07	<0.1	.	2.3	0.05	.	0.14	.	0.05	0.06	0.01	.	.	.
SUS 7/8	2.8	0.29	0.09	0.18	0.94	0.21	.	0.07	.	0.02	.	<0.01	0.06	0.06	.	.	.
BS DNR-2	2.72	0.85	0.031	0.006	2.52	0.02	18.9	1.62	0.007	<0.1	<0.05	<0.1	<0.05	<0.1	.	0.05	.
BS DNR-1	2.52	0.88	0.031	0.005	2.79	0.016	18.6	1.56	0.006	<0.1	<0.1	<0.1	<0.1	<0.1	.	0.04	.
NCS AH11354a	2.25	1.17	0.375	0.095	2.66	1.65	0.623	0.493	0.253	0.072	0.117	0.046	0.184	0.518	0.434	0.0056	(0.0033)
R G 15	2.1	0.8	0.3	0.1	4.4	<0.01	0.5	0.6	0.9	0.06	.	0.1
C Fe 4	1.53	0.40	0.012	0.012	0.31	0.06	0.27	11.4	0.75	<0.005	<0.02	<0.02	<0.02	0.90	<0.02	.	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Nb	Sn	Ti	V	W	Mg	Ce
C Fe 5
NCS AH11355a	.	0.013	.	.	.	0.027	(0.0003)
SUS 5/58	0.003	0.03
SUS 2/50
SUS 5/59	0.002	0.05
SUS GGG	0.003
R G 13+Se	<0.01	.	.	<0.001	.	~0.02
SUS 3/21
BS SU CCD	0.001	.	.	0.0027	0.009
SUS 1/20
C Fe 8	.	0.03	.	.	0.005	0.003
R G 16	.	0.01	.	.	.	0.01
SUS 4/29	<0.005	<0.005
R G 14	.	0.01	.	.	.	0.01
R G 13	.	0.006	.	.	0.01
R N 15	.	0.01	0.03
SUS 7/8	.	0.004	<0.001
BS DNR-2	<0.1	Fe: [73.3]	.	<0.1
BS DNR-1	<0.1	Fe: [73.5]	.	<0.1
NCS AH11354a	.	0.055	.	.	0.094	(0.0013)
R G 15
C Fe 4	0.02	.	0.047	<0.02

Number	As	B	Bi	Ca	Co	La	N	Pb	Sb	Se	Te	Zn	Zr	Units
--------	----	---	----	----	----	----	---	----	----	----	----	----	----	-------

CAST IRON SETTING-UP SET

Number	typical analysis			available in SET/6 only			34 mm Ø x 5 mm		
	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
KTC-9 B1	2.40	0.04	0.005	0.11	3.03	0.04	1.03	0.99	0.049
KTC-9 B2	2.61	0.23	0.024	0.082	2.69	0.20	0.81	0.81	0.20
KTC-9 B3	3.05	0.37	0.049	0.059	2.28	0.40	0.60	0.62	0.43
KTC-9 B4	3.36	0.55	0.069	0.039	1.91	0.61	0.41	0.42	0.62
KTC-9 B5	3.70	0.83	0.094	0.021	1.49	0.82	0.21	0.21	0.83
KTC-9 B6	4.08	0.99	0.12	0.003	0.94	1.01	0.05	0.06	1.06

DUCTILE IRON SETTING-UP SET

Number	typical analysis			sold in set/5 only			45 mm Ø x 5 mm		
	Mg	C	Mn	P	S	Si	Mg	C	Mn
KTC-10 M-1	0.05	3.4	0.1	0.015	0.002	2.5	0.05	3.4	0.1
KTC-10 M-2	0.04	3.4	0.1	0.015	0.002	2.5	0.04	3.4	0.1
KTC-10 M-3	0.03	3.4	0.1	0.015	0.002	2.5	0.03	3.4	0.1
KTC-10 M-4	0.02	3.4	0.1	0.015	0.002	2.5	0.02	3.4	0.1
KTC-10 M-5	0.01	3.4	0.1	0.015	0.002	2.5	0.01	3.4	0.1

CARBON AND LOW ALLOY STEEL SETTING-UP SAMPLES - CONTINUED FROM PREVIOUS

typical analysis

Number	As	B	Bi	Ca	Nb	O	Pb	Sb	Ta	Te	Zn	Zr	Units
1.2080	0.004	40 mm Ø x 25 mm
BS SU D2	0.003	0.0002	.	.	0.004	.	0.0006	0.003	38 mm Ø x 40 mm
1.2379	<0.01	40 mm Ø x 25 mm
R H 18	40 mm Ø x 40 mm
BR ST2	0.027	0.0018	.	.	0.086	.	(0.001)	(0.002)	.	.	.	0.005	45 mm Ø x 30 mm last
KUT K3	30-35 mm Ø x 39 mm
1.2067	0.005	40 mm Ø x 25 mm
BS SU E52100A	0.003	.	.	<0.005	0.001	<0.005	<0.005	<0.05	.	.	.	0.002	38 mm Ø x 40 mm Fe: [96.6]
BS SU E52100	0.004	0.0001	.	<0.0005	0.0008	0.001	<0.0005	0.0004	38 mm Ø x 40 mm Fe: [96.7]
R N 13	<0.001	<0.001	<0.001	<0.001	<0.005	.	<0.001	0.04	<0.001	<0.005	.	0.1	40 mm Ø x 40 mm
R H 13	0.02	40 mm Ø x 40 mm
R N 16	<0.01	<0.001	<0.001	<0.001	<0.01	.	<0.01	0.04	<0.01	<0.01	.	0.18	40 mm Ø x 40 mm
1.2842	<0.01	40 mm Ø x 25 mm
BAM SUS-1 R	0.6	50 mm Ø x 42 mm
1.3243	<0.01	40 mm Ø x 25 mm
R Fe D	<0.01	<0.01	<0.005	0.001	0.3	.	<0.005	0.07	0.03	0.001	.	0.03	40 mm Ø x 40 mm
R-N 19	0.06	0.006	0.008	.	0.42	.	0.01	0.02	0.28	0.01	0.01	0.05	40 mm Ø x 40 mm
NCS AH21311	40 mm Ø x 40 mm
SUS D	.	<0.001	.	.	0.05	44 mm Ø x 25, 75, or 150 mm
BS SU LAS 14-2	0.011	0.004	<0.05	0.002	0.016	0.004	0.014	0.021	0.007	.	0.003	0.008	37 mm Ø x 40 mm Fe: [95.1]
NCS AH21313	0.027	40 mm Ø x 40 mm
KUT K4	30-35 mm Ø x 39 mm
KUT K6	30-35 mm Ø x 39 mm
IMZ S-04	43 mm Ø x ~35 mm
BS 02H	0.006	0.0004	.	0.0012	<0.001	.	<0.001	<0.001	<0.001	.	.	<0.001	38 mm Ø x 150 mm
BS SU 4340	0.005	0.0002	.	0.0002	0.004	0.0007	0.0001	0.002	38 mm Ø x 40 mm Fe: 95.5
BS SU 8740	0.0016	38 mm Ø x 40 mm
1.7225	<0.002	40 mm Ø x 25 mm
BS SU41L40	<0.05	<0.005	.	<0.005	<0.05	<0.05	0.14	<0.05	41 mm Ø x 40+ mm Fe: 96.6
BS SU 4942	0.0009	<0.0005	.	<0.005	0.001	0.001	<0.005	<0.005	38 mm Ø x 40 mm Fe: [96.7]
C Fe 2 50mm	0.053	0.0032	.	0.0006	0.015	.	(0.0006)	0.02	0.02	.	.	.	40 mm Ø x 50 mm
BS SU 4130A	0.005	0.001	.	<0.001	0.002	.	<0.0005	<0.01	0.009	.	.	0.001	38 mm Ø x 40 mm Fe: [97.4]
C Fe 2	0.045	0.0015	.	<0.001	0.018	.	(0.0009)	0.005	0.03	.	.	.	40 mm Ø x 40 mm
BS 210	0.016	32 mm Ø x 17 mm last
BS SU LF-1a	<0.005	<0.005	.	0.002	<0.005	0.012	0.001	<0.005	~36 mm Ø x ~40 mm Fe: [98.69]
Number	As	B	Bi	Ca	Nb	O	Pb	Sb	Ta	Te	Zn	Zr	Units
BS SU8620MOD	0.005	0.0002	.	0.0007	0.001	0.0009	Fe: [97.6]	Mg: 0.0002	.	.	.	<0.001	38 mm Ø x 40 or 150 mm
BS SU LF-1	<0.005	<0.005	.	0.002	<0.005	0.010	0.001	<0.005	~36 mm Ø x ~40 mm Fe: 98.71
BS SU 8620A	0.005	0.0003	.	0.0006	0.003	0.0019	0.0005	.	.	Mg: 0.0002	0.0007	0.0001	38 mm Ø x 40 mm Fe: 97.1
BS SU LF-2B	0.003	0.0002	<0.05	0.0080	<0.005	0.002	<0.005	0.001	0.004	.	.	0.001	38 mm Ø x 40 or 150 mm Fe: 97.98
BS SU 4620	0.002	44 mm Ø x 40 mm
1.0580	0.03	40 mm Ø x 25 mm
1.7131	<0.002	40 mm Ø x 25 mm
BS SU 4820	0.006	<0.0005	.	0.0003	0.003	0.0016	<0.0005	0.003	0.006	Mg: 0.0004	.	<0.0005	38 mm Ø x 40 mm Fe: [95.2]
BS 03D	41 mm Ø x 150 mm
BS SU 1018D	0.005	0.0005	.	0.001	0.003	.	<0.002	<0.001	<0.001	.	.	<0.001	41 mm Ø x ~110 mm last
BS SU 1018F	0.004	0.0003	.	<0.005	0.001	<0.05	.	0.002	.	.	.	0.001	38 mm Ø x 150 mm Fe: [98.92]
1.5415	<0.01	40 mm Ø x 25 mm
IMZ S-07	40 mm Ø x ~30 mm
BS SU 1018C	0.006	0.0006	.	0.0012	0.002	.	<0.002	<0.001	<0.001	.	.	0.001	38 mm Ø x ~40 mm last
BS SU LF-3	0.002	44 mm Ø x 40 mm
BS SU 11L17	.	<0.0005	.	<0.0005	0.002	0.016	0.27	41 mm Ø x 40 mm Fe: [98.1]
BS 213	0.013	32 mm Ø x 17 mm Tl: (0.002)
CZ CM-22A (RM)	0.057	.	.	.	0.019	~39 mm Ø x ~25 mm
BS 207	0.024	32 mm Ø x 17 mm
IMZ 501	48 mm Ø x 25 mm
IMZ 503	48 mm Ø x 25 mm
BS SU 9310	0.006	0.002	38 mm Ø x 40 mm
R Fe C	0.05	<0.005	0.003	<0.001	0.01	.	0.001	0.01	0.19	0.002	0.001	<0.001	40 mm Ø x 40 mm
BS SU 9310A	0.004	<0.005	.	<0.005	0.008	0.0016	<0.005	<0.005	38 mm Ø x 40+ mm Fe: [94.1]
BS 214	(0.007)	32 mm Ø x 17 mm Tl: (0.002)
KUT K9	(0.04)	30-35 mm Ø x 18 mm
IMZ S-11	40 mm Ø x ~25 mm
BS SU LAS 13/3	0.045	0.003	0.020	0.0006	0.14	0.005	0.004	0.009	0.052	Ce: 0.009	0.010	0.021	37 mm Ø x 40 mm Mg: 0.0002
1.0737	0.3	40 mm Ø x 25 mm
C Fe 9	0.003	0.0001	0.3	0.0005	40 mm Ø x 30, 40, or 50 mm
R N 14	0.06	<0.01	<0.01	.	0.5	.	0.01	<0.01	0.1	<0.01	.	.	40 mm Ø x 40 mm
SUS A/8	<0.005	44 mm Ø x 75 mm
SAG 0203	0.002	<0.0005	.	<0.001	<0.001	.	<0.001	<0.001	<0.001	<0.001	.	.	32 mm Ø x 40 mm
SAG 0204	0.002	<0.0005	.	<0.001	<0.001	.	<0.001	<0.001	<0.001	<0.001	.	.	40 mm Ø x 40 mm
SAG 0202	0.001	40 mm Ø x 40 mm
Number	As	B	Bi	Ca	Nb	O	Pb	Sb	Ta	Te	Zn	Zr	Units

* NCS 28301 also contains Al(ins): 0.0049 and Al(sol): 0.0056.

LOW ALLOY STEEL SETTING-UP SETS WITH SOLUBLE/INSOLUBLE VALUES

available in SETS only, as grouped																Sol. = soluble		Ins. = insoluble		typical analysis				35 mm Ø x 20 mm	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Sol.Al	Ins.Al	B	Ca	Sol.N	Ins.N									
KTC-1/5 01	0.0008	0.01	0.001	<0.001	<0.01	0.01	0.01	0.01	<0.001	.	<0.001	<0.001	0.0002	0.0001	.	.									
KTC-1/5 02	0.10	0.21	0.003	0.005	0.61	0.07	0.05	3.99	0.50	.	0.003	0.001									
KTC-1/5 03	0.16	0.76	0.002	0.009	0.40	0.70	0.10	3.24	0.40	.	0.012	<0.001									
KTC-1/5 04	0.20	2.01	0.010	0.016	0.05	0.10	0.52	2.51	0.32	.	0.083	<0.001									
KTC-1/5 05	0.24	1.63	0.013	<0.001	0.26	0.40	1.02	2.04	0.10	.	0.036	0.002	.	0.0002	.	.									
KTC-1/5 06	0.36	1.33	0.049	0.001	0.36	0.50	1.53	1.54	0.20	.	0.020	0.001	0.0005	0.0006	.	.									
KTC-1/5 07	0.51	1.02	0.040	0.029	0.30	0.20	2.05	1.02	0.62	.	0.029	0.001	0.0009	0.0018	.	.									
KTC-1/5 08	0.66	0.50	0.031	0.023	0.16	0.31	2.54	0.51	1.01	.	0.056	<0.001	0.0020	0.0030	.	.									
KTC-1/5 09	0.80	0.31	0.019	<0.001	0.20	0.15	3.26	0.10	0.84	.	0.064	<0.001	0.0038	0.0031	.	.									
KTC-1/5 10	1.05	0.10	0.006	0.022	0.10	0.07	4.06	0.07	0.050	.	0.090	0.001	0.0088	.	.	.									
KTC-15 N-1	0.015	0.10	0.002	0.003	0.10	.	.	0.21	.	0.050	0.0012	0.0001									
KTC-15 N-2	0.014	0.10	0.002	0.003	0.10	.	.	0.29	.	0.048	0.0048	0.0002									
KTC-15 N-3	0.012	0.10	0.002	0.003	0.10	.	.	0.19	.	0.048	0.0076	0.0003									
KTC-15 N-4	0.012	0.10	0.003	0.004	0.10	.	.	0.20	.	0.048	0.0110	0.0002									
KTC-15 N-5	0.012	0.11	0.003	0.004	0.10	.	.	0.41	.	0.050	0.0194	0.0008									

Number	As	Co	Nb	Sn	Ti	V	W
KTC-1/5 01	<0.001	<0.001	0.001	0.001	0.001	0.001	<0.01
KTC-1/5 02	0.010	0.010	0.10	0.062	0.021	0.40	.
KTC-1/5 03	0.010	0.15	0.069	0.042	0.10	0.022	.
KTC-1/5 04	0.021	0.050	0.019	0.021	0.31	.	.
KTC-1/5 05	0.044	0.10	0.040	0.010	0.011	0.31	.
KTC-1/5 06	0.062	0.20	0.010	.	0.054	0.052	.
KTC-1/5 07	0.20	0.11	0.05
KTC-1/5 08	0.16	0.15	0.12
KTC-1/5 09	0.21	0.22
KTC-1/5 10	0.50	0.15
KTC-15 N-1
KTC-15 N-2
KTC-15 N-3
KTC-15 N-4
KTC-15 N-5

LOW ALLOY STEEL SETTING-UP SET

SOLD AS SET/3 ONLY																typical analysis				formerly known as set ST A-C				35 mm Ø x 20 mm	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	Sol.Al	Ins.Al	Nb	Ti	V	W	As	B	Ca	Co					
KTC-2 A	1.00	0.01	0.002	0.001	0.05	0.11	4.09	.	.	.	0.086	<0.001	0.10	0.36	0.03	0.19					
KTC-2 B	0.01	0.52	0.045	.	0.57	0.69	0.50	3.98	0.20	0.093	.	.	0.03	.	.	.	0.050	0.0085	0.0035	0.01					
KTC-2 C	0.11	1.96	.	0.028	.	.	.	0.50	1.00	.	0.019	0.001	.	0.50	0.20					

STAINLESS STEEL SETTING-UP SAMPLE SETS

available in SETS only, as grouped																Sol. = soluble		Ins. = insoluble		typical analysis				35 mm Ø x 20 mm	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sol.Al	Ins.Al	As	Co	Nb	Ti	Pb	Ta								
KTC-3/1 21	0.13	0.40	0.003	0.024	0.18	.	4.03	27.02	0.003	.	0.003	.	.								
KTC-3/1 22	0.058	0.62	0.029	0.005	0.43	.	19.73	24.90	.	0.073	0.003	0.001								
KTC-3/1 23	0.11	1.60	0.005	0.021	0.82	0.048	9.99	22.17	1.01	0.045	0.003	0.104	.	<0.01	.	0.005	.								
KTC-3/1 24	0.084	0.80	0.009	0.014	0.60	0.031	14.12	20.18	1.46	0.006	0.004	0.050	.	.	.	0.018	.								
KTC-3/1 25	0.027	1.42	0.010	0.021	1.43	0.011	8.05	18.32	2.49	0.001	0.001	0.012	0.050	.	.	0.044	.								
KTC-3/1 26	0.044	1.19	0.021	0.008	1.01	.	17.62	16.18	0.49	0.004	0.002	.	0.21	0.29	0.075	.	0.40								
KTC-3/1 27	0.057	1.00	0.019	0.011	1.19	.	15.74	13.39	0.008	0.016	0.002	.	0.014	1.53	0.24	.	0.24								
KTC-3/1 28	0.011	0.22	0.036	0.003	0.10	.	29.79	10.06	.	0.019	<0.001	.	.	0.072	0.45	.	0.054								
ST I	0.26	0.21	0.008	0.024	0.19	0.01	0.01	26.78	0.046	0.002	0.004	<0.001	0.003	0.013	0.010	CLEARANCE SALE	.								
ST H	0.088	0.47	0.009	0.010	0.50	0.04	0.57	17.95	0.49	0.031	0.005	0.011	0.054	0.094	0.094	CLEARANCE SALE	.								
ST G	0.031	1.37	0.029	0.005	1.26	0.19	3.87	11.85	1.14	0.086	0.005	0.075	0.19	0.98	0.30	CLEARANCE SALE	.								
KTC-5 31	0.068	0.51	0.023	0.005	1.24	0.19	3.91	11.23	0.71	0.10	0.003	0.10	0.19	0.90	0.31	.	.								
KTC-5 32	0.040	1.16	0.030	0.007	0.52	0.01	2.56	12.71	1.01	0.013	0.004	0.008	0.014	0.082	0.051	.	.								
KTC-5 33	0.044	0.30	0.008	0.022	0.32	0.10	1.03	15.12	1.19	0.031	0.004	0.001	0.10	0.30	0.007	.	.								
KTC-5 34	0.084	0.99	0.025	0.004	0.78	0.04	0.48	16.99	0.48	0.045	0.006	0.009	0.051	0.083	0.098	.	.								
KTC-5 35	0.22	1.35	0.002	0.029	0.58	<0.01	0.05	24.14	0.029	0.057	0.007	<0.001	0.005	0.007	0.005	.	.								
KTC-5 36	0.15	0.43	0.014	0.009	0.14	<0.01	0.11	22.31	0.043	0.001	0.008	<0.001	0.003	0.001	0.005	.	.								
KTC-5 37	0.11	0.74	0.007	0.019	0.99	<0.01	0.20	19.51	0.20	0.001	0.002	<0.001	0.002	<0.001	0.003	.	.								
KTC-5 38	0.30	0.19	0.010	0.013	0.40	<0.01	0.01	25.52	0.004	0.001	0.002	<0.001	0.002	<0.001	0.003	.	.								
JSM M205 1	0.054	0.43	0.031	0.011	0.27	0.09	0.26	15.9	0.13	.	.	.	0.022	.	N:0.0409	.	V:0.052								
JSM M205 2	0.049	1.64	0.042	0.26	0.36	0.35	8.46	17.0	0.29	Al: <0.005	.	.	0.17	.	N:0.077	.	V:0.049								
JSM M205 3	0.059	1.48	0.034	0.025	0.49	0.38	8.16	18.2	0.22	Al: <0.005	.	.	0.21	.	N:0.079	.	V:0.099								
JSM M205 4	0.028	1.85	0.035	0.010	0.27	0.52	9.09	19.4	0.31	Al: <0.005	.	.	1.9	.	N:0.076	.	V:0.10								
JSM M205 5	0.068	1.58	0.033	0.001	0.32	0.26	13.1	22.1	0.19	Al: <0.005	.	.	0.27	.	N:0.067	.	V:0.080								
JSM M205 6	0.020	1.08	0.029	<0.001	0.39	0.32	19.1	24.2	0.17	Al: 0.010	.	.	0.35	.	N:0.0281	.	V:0.074								
JSM M205 7	0.057	1.31	0.034	0.026	0.47	0.30	10.2	16.6	2.04	Al: <0.005	.	.	0.24	.	N:0.0472	.	V:0.079								
JSM M205 8	0.022	1.28	0.036	0.017	0.51	0.27	12.1	17.2	2.02	Al: <0.005	.	.	0.17	.	N:0.0432	.	V:0.046								

STAINLESS AND HIGH ALLOY STEEL SETTING-UP SAMPLES

typical analysis

Table with 18 columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Sn, Al, Co, Nb, Ti, V, W, N. Rows include various stainless steel samples like IMZ S-22, BS SU 420, and BS SU 304.

Table with 18 columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Sn, Al, Co, Nb, Ti, V, W, N. This section includes detailed analysis for elements like As, B, Bi, Ca, Fe, O, Pb, Sb, Ta, Te, Zn, Zr, and Units.

HIGH SILICA IN XRF DISCS

typical analysis		40 mm Ø x 5-6 mm								
Number	SiO ₂	Al ₂ O ₃	CaO	Cl	Fe ₂ O ₃	K ₂ O	Na ₂ O	SO ₃	TiO ₂	
ASO TU1	99.99	0.005	0.005	.	<0.01	.	0.005	.	.	last
FLX Q0	99.99
BR K 1/3	99.5	0.17	0.02	0.05	0.02	0.07	0.10	0.04	0.02	.

CRM URANIUM IN XRF DISCS

typical analysis listed in mg/kg		12 mm Ø x 5 mm	
Number	U		
IRMM 540R	15.0	last	

URANIUM IN XRF DISCS

typical analysis		30-40 mm Ø x 5 mm																					
Number	UO ₃	U ₃ O ₈	Al ₂ O ₃	As ₂ O ₃	B ₂ O ₃	BaO	CaO	CdO	CoO	Cr ₂ O ₃	CuO	F	Fe ₂ O ₃	K ₂ O	MgO	MnO	Na ₂ O	NiO	P ₂ O ₅	SiO ₂	Sb ₂ O ₃	TiO ₂	ZnO
SV F	1.0	.	2.0	.	3.0	0.3	3.0	.	0.5	.	.	4.0	.	29.3	1.0	.	1.0	.	.	58.23	1.0	1.0	0.2
SV E	0.5	.	1.5	0.5	6.0	3.0	5.0	.	1.0	4.0	1.0	0.8	.	2.5	.	5.0	15.0	0.5	.	50.9	.	.	2.0
BR AS1	0.01	.	15.8	0.44	3.22	.	0.83	0.39	.	0.15	.	0.17	1.16	2.16	3.20	20.3	0.13	.	0.58	38.9	.	3.9	7.4
BR U 26	.	1.0	1.5	.	.	0.1	6.5	1.0	0.07	3.0	.	.	13.3	.	.	69.98	0.25	.	1.0
BR U 21	.	0.40	2.0	.	10	.	6.5	1.5	0.25	0.6	1	.	0.05	5.8	0.05	0.15	10.0	0.15	.	60.0	0.25	.	.
BR EK01	.	0.10	.	0.13	0.74	2.24	4.96	0.02	0.38	1.17	0.63	.	.	6.82	.	.	8.54	0.64	.	67.05	0.44	.	3.73
BR U 25	.	0.10	3.0	.	.	.	6.9	.	.	0.27	0.10	.	0.34	2.9	0.15	6.0	0.3	.	.	69.3	0.20	.	0.0
BR CH1	.	0.1	28.0	0.8	20.0	1.0	.	0.15	7.0	8.0	.	0.5	6.5	0.3	14.0	9.11	.	0.1	.

Number	Bi ₂ O ₃	CeO ₂	Cs ₂ O	Ga ₂ O ₃	GeO ₂	In ₂ O ₃	La ₂ O ₃	MoO ₃	Nb ₂ O ₅	Nd ₂ O ₃	PbO	Pr ₂ O ₃	Rb ₂ O	SO ₃	SeO ₂	SnO	SrO	Ta ₂ O ₅	TeO ₂	ThO ₂	V ₂ O ₅	WO ₃	ZrO ₂	
SV F	.	0.5	.	0.1	.	.	0.5	.	0.5	0.6	.	0.15	1.0	0.12	1.0	last
SV E	0.5	0.3	last
BR AS1	.	.	0.04	.	0.08	0.04	0.5	.	0.04	.	.	.	0.71	.	0.04	0.04	0.01	.	0.15	.
BR U 26	.	2.0	0.2	0.14
BR U 21	.	0.15	0.15	0.02
BR EK01	0.30	.	.	0.65	0.57	0.89	.	.
BR U 25	0.12
BR CH1	1.0	.	.	.	0.3	.	.	.	0.7	0.5	.	0.4	0.04	0.3	1.2	.

ZINC AND ZIRCONIUM IN XRF DISCS

typical analysis		40 mm Ø x 5-6 mm																	
Number	ZnO	ZrO ₂	SiO ₂	Al ₂ O ₃	B ₂ O ₃	BaO	Bi ₂ O ₃	CaO	Cr ₂ O ₃	CdO	Co ₂ O ₃	F	Fe ₂ O ₃	K ₂ O	Li ₂ O	MgO	MnO ₂	Na ₂ O	
BR TL2	.	30	10	0.5	9.3	0.1	15	5	.	.	.	15
BR N 1	80.2	.	0.2	.	.	.	4.5	.	1.6	.	1.9	0.7	.
FLX F1	12.92	.	65.81	2.14	.	.	.	1.62	.	0.181	.	2.57	0.116	0.781	13.53
FLX SP2	2.50	2.17	44.75	.	20.0	5.35	.	.	.	3.71	18.42	.	.	.

Number	NiO	P ₂ O ₅	PbO	Sb ₂ O ₃	SO ₃	TiO ₂
BR TL2	.	0.1	10	.	.	5
BR N 1	0.7	.	.	9.3	.	0.9
FLX F1	0.264	.
FLX SP2	.	.	4.65	.	.	.

last of stock

AUSMON XRF DRIFT MONITORS (wavelength dispersive XRF)

The monitors listed below have been formulated so that they have appropriate count rates for different ores and products. The monitors contain little flux and most have been in use for many years and have given excellent stability.

The monitor discs are 32 or 40mm diameter and about 4mm high. The monitors are polished flat so that they can be mounted precisely and are easily cleaned. The following types for wavelength dispersive XRF are available:

AUSMON Bauxite

Suitable with bauxites and other materials with high Aluminum and contain **Fe, Si, Al, Ca, F, Na, Mg, P, S, Cl, K, Ti, V, Cr, Mn, Co, Ni, Cu, Zn, As, Br, Sn, and Ga.** (24 elements)

AUSMON Cement A

Suitable when making detailed analyses of cements or other materials with high Calcium and contain **Ca, Si, Al, Mg, Fe, Na, Cl, S, F, P, K, Ti, Cr, Mn, Zn, Sr, Br, Ba, and Pb.** (19 elements)

AUSMON Iron Ore

Suitable with iron ores and related materials, containing **Fe, Si, Al, Ca, F, Na, Mg, P, S, Cl, K, Ti, V, Cr, Mn, Co, Ni, Cu, Zn, As, Br, Sn, Cd, Sb, Bi, Mo, Ba, and Pb.** (28 elements)

AUSMON Manganese Ore

Suitable with manganese ores and contain: **Mn, Fe, Si, Na, Mg, Al, P, K, Ca, Ti, V, Sr, Br, Ba, and Pb.** (15 elements)

AUSMON Mineral Sands

Suitable with mineral sand products, including but not limited to ilmenite, rutile, zircon, monazite and xenotime. The following elements are present: **Ti, Fe, Zr, Si, Y, La, Ce, Nd, Pr, Yb, P, F, Na, Mg, Al, S, Cl, K, Ca, Sc, V, Mn, Cr, Co, Ni, Cu, Zn, Br, As, Sr, Nb, Mo, Cd, Sn, Ba, Hf, Pb, Th, and U.** (39 elements)

AUSMON Nickel Ore

Suitable with nickel ores and related materials, containing **Ni, Fe, S, Si, F, Na, Mg, Al, P, Cl, K, Ca, Ti, Mn, Cr, Co, Cu, Zn, As, Se, Br, Mo, Ag, Pb, and Bi.** (25 elements)

AUSMON Rare Earths

Suitable with monazite, xenotime and other rare earth minerals for the rare earth oxides. The following elements are present: **La, Ce, Pr, Nd, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu, Y, P, F, Na, Mg, Al, Si, S, Cl, K, Ca, Sc, Ti, Mn, Fe, Ni, Br, Sr, Zr, Nb, Ba, Hf, Pb, Th, and U.** (39 elements)

AUSMON Silicates

These monitors were designed for the analysis of rocks, soils and related materials. They can also be used as general purpose monitors for a wide range of materials, eg. vegetables, etc. They contain the following elements as majors: **Fe, Mn, Ti, Ca, K, Cl, S, P, Si, Al, Mg, Na and F.** In addition about 2000ppm of each of the following are present: **Sc** (1000ppm), **V, Cr, Co, Cu, Ni, Zn, Ga, Ge, Se, As, Rb, Sr, Br, Y, Zr, Nb, Mo, Ag, Cd, Sn, Sb, Te, Cs, Ba, La, Ce, Nd, Pr, Gd, Sm, Yb, Hf, Ta, W, Bi, Tl, Pb, Th, and U.** (53 elements)

AUSMON Sulfides

These monitors are for use with lead, zinc, iron and copper sulphides, as ores, concentrates and related products. They contain: **Pb, Zn, Fe, Cu, S, F, Na, Mg, Al, Si, P, K, Ca, Cl, Ti, Co, Ni, Cr, Mn, As, Sr, Se, Ag, Cd, Sn, Sb, Ba, Te, Tl, Mo, U, and Bi.** (32 elements)

AUSMON XRF DRIFT MONITORS (energy dispersive XRF)

The monitors listed below have been formulated so that they have appropriate count rates for different ores and products. The monitors contain little flux and most have been in use for many years and have given excellent stability.

The monitor discs (except AUSMON Cement B) are 32mm diameter and about 4mm high. The monitors are polished flat so that they can be mounted precisely and are easily cleaned. The following types for energy dispersive XRF are available:

AUSMON MCACAL

Intended for the energy dispersive XRF system, this monitor contains the following elements: **F, Na, Mg, Si, Cl, Ca, V, Zn, As, Fe, Y, Mo, Cd, Ba.** (14 elements)

AUSMON Mon A

This is intended as a drift monitor with the following elements: **Mg, Si, P, W, Pb, Sn.** (6 elements)

AUSMON Mon B

This is a drift monitor with the following elements: **Na, Al, Si, Ca, Ti, Cr, and Ni.** (7 elements)

AUSMON SPECIALS

Monitor discs can be made to suite needs not covered by the above. Very often this is for laboratories performing analysis on materials that do not have long term stability and so they cannot use a similar product as a monitor, eg aqueous liquids or liquids from the petroleum industry. Cl in brine, Ca in milk, Cl, Br, and trace elements in synthetic rubbers are some common examples for which custom monitors have been made.