

Issue February 2017

Valid to December 2017

MBH

Reference Materials

MBH

VISIT OUR WEBSITE
<http://www.mbh.co.uk>



Index	Page
	Inside front cover
Introduction & Abbreviations.	1
Information - Definitions etc.	43
Conditions of Sale - Ordering procedure.	44
Conditions of Sale - Prices & payment terms including bank details.	45 & 46

Certified Reference Materials

		Pages
Section 1	Iron Base	3 - 10
Section 2	Nickel Base	11 - 13
Section 3	Copper Base	14 - 20
Section 4	Zinc Base	21 - 23
Section 5	Aluminium Base	24 - 28
Section 6	Magnesium Base	29 & 30
Section 7	Tin Base	31 & 32
Section 8	Lead Base	33 - 35
Section 9	Lead/Tin Solders	36 & 37
Section 10	Titanium Base	38

		Pages
Section 11	Cobalt Base	38
Section 13	Noble Metals	39
Section 16	Setting Up & Control Samples	40 & 41
Section 18	Gases in Metals	41
<u>Chippings</u>		42

Please note. Most of the MBH range of discs are also available in chippings form. Please see the following data for general composition information.

Please enquire for availability, bottle size and price.

Note: Chippings are made to order, and are non-returnable. Please ensure you have correctly identified your requirement before ordering.

<u>Listing of new materials added in this catalogue.</u>	2
---	----------

This catalogue is not the full listing of the materials supplied by MBH but only those materials exclusively produced by MBH. Please also see our full product catalogue.

On the following pages you will find the current range of reference materials, principally for optical emission spectroscopy (OES), produced by MBH. The range includes Reference Materials, Certified Reference Materials and Setting Up Samples for both ferrous and non-ferrous alloys.

Whilst every effort has been made to detail the latest information, it is possible that products will be remade or replaced and values and dimensions changed. This catalogue can therefore only be a snapshot of the information available at the time of publication. Please check on our website at www.mbh.co.uk for more up to date information on availability and new materials.

Listed you will find details of the latest additions and imminent new materials produced by MBH. Materials noted as "provisional values" are currently being certified and can be supplied with a Provisional certificate of analysis prior to the completion of the full certificate. The final certificate is mailed to all purchasers when completed.

The catalogue lists currently available or forthcoming materials produced by MBH only. If you cannot find the catalogue reference number you want listed it may have been changed, deleted or excluded because of its age or availability. It may not be produced by MBH but from another producer. Please enquire.

We trust you will find this 'MBH only' catalogue useful. Should you have any questions or require further information please do not hesitate to contact us.

Information

Abbreviations

CRM	This material is classified by MBH as a Certified Reference Material. Where the catalogue entry is not preceded with CRM the material is considered to be only of Reference Material (RM) status.
()	The concentration value stated within the brackets is not certified and is provided for information purposes only
R.E.	Rare Earth
ppm	Parts per Million (w/w)
Form	
C	Material is a Cast product
CC or (2xCC)	Material is Chill Cast product or (Double Chill Cast)
HIP	Material is Hot Isostatically Pressed powder
SC	Material is a Spray Cast product
W	Material is a Wrought product
R	Material has been cut from Rolled strip
** provisional values	This material is in production and is currently available for purchase and will be supplied with a provisional certificate. However the values presented are the result of an incomplete analysis programme. The final certified values are expected to be available within ~8 months, but may differ slightly. Please enquire .
Sold Out	Materials where data is struck through (for example 14X-MN2-Q etc.) and indicated as 'sold out' will be remade later; please enquire.
	Material listed in previous editions but now no longer listed herein should be considered no longer available and may or may not be remade.

Listing of New Materials Added to this Catalogue.

January 2017

Blocks / Discs

1.2.3 Low Alloy Steel (continued)		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	V	Co	As	Ca	N			Size (mm) Ø x H	Form		
	12X 14072 A **	0.44	0.32	0.006	0.015	0.68	0.14	1.07	0.57	0.200	0.005	0.003	0.31	0.01			0.010	** provisional values		38 x 15	W		
CRM	12X 605M36 A	0.373	0.283	0.0317	(0.009)	1.504	0.146	0.243	0.292	0.199	0.0101	0.0105		0.0151	0.0102	0.0033	0.0095			38 x 15	W		
1.3.4 Ferritic & Martensitic Stainless Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	Ti	V	Co	Nb	W	B	Ca	N	Size (mm) Ø x H	Form	
CRM	13X 1.4122 A **	0.35	0.46	0.002	0.017	0.47	0.62	15.9	0.85	0.065	0.003	0.002		0.10	0.022	0.006	0.003			0.030	** provisional values	40 x 15	W
CRM	13X 1.4418 A **	0.042	0.29	0.015	0.025	0.81	4.65	15.4	0.85	0.17	0.005	0.002		0.055	0.10	0.01	0.01			0.042	** provisional values	40 x 15	W
CRM	13X 1.4923 A **	0.20	0.33	0.003	0.021	0.50	0.46	11.2	0.82	0.055	0.003	0.003		0.30	0.02	0.005			0.005	0.033	** provisional values	40 x 15	W
CRM	13X 1.4713 A **	0.045	0.92	0.008	0.018	0.49	0.12	7.1	0.025	0.038	0.003	0.55	0.005	0.045	0.01					0.006	** provisional values	40 x 15	W
CRM	13X 1.4742 A **	0.085	0.90	0.002	0.022	0.72	0.45	17.6	0.10	0.13	0.005	0.82	0.005	0.045	0.015	0.02				0.02	** provisional values	40 x 15	W
CRM	13X 1.4762 A **	0.082	1.05	0.001	0.028	0.66	0.35	24.3	0.055	0.08	0.005	1.3	0.007	0.10	0.03	0.03			0.0025	0.027	** provisional values	40 x 15	W
CRM	13X 43020 A **	0.15	0.45	0.19	0.025	1.45	0.52	16.0	0.23	0.07		0.005		0.055	0.02	0.01	0.01	0.005		0.022	** provisional values	40 x 15	W
1.3.5 Special Stainless Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Al	V	W	Co	Nb	N			Size (mm) Ø x H	Form			
CRM	13X 42200 A **	0.22	0.32	0.001	0.018	0.65	0.73	11.5	1.06	0.14	0.003	0.25	1.15	0.01	0.02	0.02	** provisional values		UNS S42200	38 x 15	W		
1.3.6 Precipitation Hardening Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Ti	Al	V	Co	N			Size (mm) Ø x H	Form				
CRM	13X 45500 A **	0.003	0.055	0.002	0.005	0.027	8.3	11.4	0.015	2.2	1.2	0.07	0.065	0.015	0.002	** provisional values		UNS S45500	38 x 15	W			
8.5 Various Lead Alloys		Sn	Sb	Bi	Cu	As	Ag	Te	Se	S							Size (mm) Ø x H	Form					
CRM	85X S744 A **	0.25	1.55	0.02	0.035	0.12	0.005	0.002	0.025	0.003							** provisional values		40 x 15	C			

In addition to the above new materials we have also re-made many of our existing range and the new batches are detailed in the following pages.

1. Iron Base

Irons

Updated: 15th December 2016

Blocks / Discs

1.1.3 High Phosphorus		C	Si	S	P	Mn	Cr	Mo	Cu	Nb	Ni	Ti	V									Size (mm) Ø x H	Form	
CRM	11X HPC1 H	3.29	3.27	0.0035	0.808	0.620	1.056	0.060														40 x 15	CC	
CRM	11X HPC2 L	3.18	2.20	0.0418	1.51	1.005	1.509	0.0354	0.0460	0.0354	0.388	0.0502	0.0350									40 x 15	CC	
CRM	11X HPC3 J	3.38	1.63	0.0473	2.01	1.287	1.48	0.120			2.18											40 x 15	CC	
CRM	11X HPC5 A	3.68	1.175	0.223	0.246	1.028	1.42															40 x 15	CC	
1.1.4 Spheroidal Graphite		C	Si	S	P	Mn	Ni	Cr	Cu	Al	Ti	Mg	As	Zn									Size (mm) Ø x H	Form
CRM	11X SG1 A	3.53	2.96	0.0095	0.0363	0.278	0.042	0.0299	0.0194	0.0187	0.0150	0.040	0.0021	0.041	Note: Both these products contain free carbon;								40 x 15	concast
CRM	11X SG2 A	3.48	3.03	0.0075	0.0353	0.297	0.0263	0.0304	0.0245	0.0238	0.0146	0.055	0.0022	0.040	use for the measurement of grey irons only								40 x 15	concast
1.1.7 Low Alloy		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	Ti	V	Nb	Co	W	As	Sb	Bi	Se	Zn	continued	
CRM	11X C1 Q	2.82	1.40	0.0349	0.092	1.341	0.556	0.335	0.062	0.154	0.0248	0.069	0.196	0.1036	0.091	0.0407		0.0105	0.055	0.0093	0.005	0.0051		
CRM	11X C2 U	3.414	1.081	0.093	0.268	1.203	1.702	0.882	0.111	0.1085	0.046	0.053	0.094	0.314	(0.030)	0.226	0.062	0.0288	0.104	0.0055	0.0199			
CRM	11X C3 AB	3.408	0.849	0.201	0.451	0.447	3.20	2.02	0.216	0.295	0.209	0.0090	0.040	0.692	(0.19)	0.241	0.0520	0.098	0.245	0.0144	0.0193	0.0386		
CRM	11X C4 R	1.86	2.92	0.098	0.108	0.493	2.02	1.531	0.101	0.345	0.0102	0.040	0.080	0.0208	0.0373	0.0316	0.120	0.0050	0.015	0.0144	0.021	0.0083		
CRM	11X C5 X	2.52	2.09	0.096	0.080	0.846	1.595	1.111	0.471	1.80	0.0371	0.05	0.056	0.089	0.0403	0.0558	0.031	0.0199	0.0265	0.0108	0.005	0.019		
CRM	11X C7 P	3.24	0.604	0.0081	0.0587	2.214	0.0273	0.61	0.0401	0.072	0.0110	0.029	0.064	0.0081	0.0195	0.0068	0.053	0.0110	0.009			0.0152		
CRM	11X C8 U	2.50	1.38	0.154	0.831	0.424	0.175	0.360	0.128	0.259	0.080	(0.10)	0.071	0.0452	0.031	0.081	0.013	0.077	0.0631	0.0164	0.0280	0.0051		
CRM	11X C9 D	3.24	1.462	0.0260	0.069	1.886	2.79	1.206	0.155	0.581	0.040	0.051	(0.062)	0.359	0.0766	0.1301	0.304	0.068	0.149			0.009		
CRM	11X C10 C	3.48	2.10	0.050	0.103	0.696	2.673	0.302	0.335	1.54	0.0458	0.104	0.0709	0.0589			0.327	0.0200	0.0095					
Continuation from above		Pb	B	Zr	Te	Ag	N																Size (mm) Ø x H	Form
	11X C1 Q	0.0107	0.054	0.0072			0.0095																40 x 15	CC
	11X C2 U	0.023	0.0213				0.0110																40 x 15	CC
	11X C3 AB	0.022	0.0054				0.0095																40 x 15	CC
	11X C4 R	0.019	0.0086	0.0031		0.008	0.0078																40 x 15	CC
	11X C5 X	0.0295	0.011	0.0050	0.0010		0.0171																40 x 15	CC
	11X C7 P	0.0106	0.0099			(0.026)	0.0153																40 x 15	CC
	11X C8 U	0.0057	0.0330	0.0040	0.0043	0.008	0.0032																40 x 15	CC
	11X C9 D	0.0052	0.0049		0.011																		40 x 15	CC
	11X C10 C	0.0050					0.0096																40 x 15	CC
1.1.8 Abrasion Resistant		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Al	Ti	V	Co	W	Nb	Pb					Size (mm) Ø x H	Form	
CRM	11X AR5 K	3.20	1.695	0.0215	0.0405	0.535	5.15	8.83	0.149	0.0517	0.120	0.062	0.0533	0.34	0.073	0.027	0.0035					40 x 15	CC	

1. Iron Base

Irons

Updated: 15th December 2016

Blocks / Discs

1.1.9 Corrosion Resistant		C	Si	S	P	Mn	Ni	Cr	Cu									Size (mm) Ø x H	Form	
CRM	11X S/1 Cr3 J	2.91	1.07	0.023	0.072	0.861	14.53	1.61	9.01									40 x 13	CC	
	11X S/2Cr1 E	2.83	2.85	0.011	0.31	1.68	16.5	2.48	0.02									40 x 15	CC	
	11X S/2Cr4 D	2.82	2.59	0.010	0.049	0.97	20.7	1.10	0.24									40 x 15	CC	
	11X S/3Cr1 D	2.61	2.52	0.011	0.046	0.70	31.7	0.15	0.19									40 x 15	CC	
	11X S/3Cr2 C	2.30	2.59	0.010	0.045	0.85	31.0	2.62	0.21									40 x 15	CC	
	11X S/3Cr3 B	2.49	2.44	0.050	0.053	0.66	29.4	4.06	0.23									40 x 15	CC	
			C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Co	Ti	V	Nb	Al	Sn	Pb	Size (mm) Ø x H	Form
	11X 20001 J	2.90	1.01	0.143	0.005	0.58	21.4	1.50		0.01								40 x 15	C	
	11X 20002 J	2.67	2.04	0.045	0.060	1.06	20.0	2.03		0.30								40 x 15	C	
	11X 20003 K	2.91	3.03	0.007	0.174	1.53	17.8	2.53		0.52								40 x 15	C	
Note: items that are cast (form C) may contain some primary carbon.																				
CRM	11X 0331.1 J	2.82	2.50	0.13	0.069	1.646	12.43	0.607	0.120	7.59	0.1117	0.1099		0.149	0.122	0.0439	0.0327	40 x 13	CC	
CRM	11X 0331.2 K	2.64	2.32	0.119	0.049	1.272	14.26	1.025	0.0644	6.47	0.161	0.14	0.0158	0.104	0.191	0.0205	0.0205	40 X 13	CC	
CRM	11X 0331.3 G	2.27	1.79	0.049	0.0339	0.613	17.23	2.014	0.0518	6.02	0.108	0.085	0.029		(0.116)	0.0127	0.0247	Sold out	40 X 13	CC
CRM	11X 0331.5 C	2.73	2.93	0.217	0.164	0.893	14.52	0.582	0.117	7.74					0.018	0.121	0.0056	40 X 13	CC	
1.1.11 With Chromium		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	V	W	Co	Nb	Ti	Sn	Pb	Size (mm) Ø x H	Form	
CRM	11X 15294 V **	2.3	0.4	0.03	0.10	0.50	0.65	31	0.32	0.13	0.12	0.30	0.1			0.06	0.01	** provisional values	40 x 15	CC
CRM	11X 15295 R **	2.5	0.6	0.04	0.05	0.50	0.32	27.5	0.40	0.19	0.20	0.19	1.5	0.04		0.04	0.01	** provisional values	40 x 15	CC
CRM	11X 15309 S	3.05	1.398	0.086	0.040	1.506	0.919	23.26	0.249	0.505	0.056	0.015	0.032	0.0192	0.0156			40 x 15	CC	
CRM	11X 15310 A	2.71	0.892	0.0278	0.051	1.45	5.66	21.22	0.980	2.64	0.071	0.137	0.0709					40 x 15	CC	

1.2.2 Residuals in Mild Steel																						Size (mm)	Form			
		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	Ti	V	W	As	Co	Zn	Nb	N	Bi	Se		Sb	Ø x H	
CRM	12X 10180 A	0.170	0.221	0.0336	0.0104	0.806	0.102	0.095	0.0220	0.176	0.0143	0.0243				0.0058		0.0031		0.0106					40 x 20	W
CRM	12X 10180 B	0.169	0.114	0.0056	0.0101	0.722	0.0333	0.0451	0.0062	0.0544	0.0065	0.043				0.0059		0.0079		0.0071					40 x 20	W
CRM	12X 10180 C	0.171	0.147	0.0200	0.0150	0.803	0.0284	0.0793	0.0047	0.0500	0.0024	0.0198				0.0029		0.0005		0.0051					40 x 20	W
CRM	12X 10400 A	0.420	0.220	0.0305	0.0137	0.754	0.0631	0.139	0.0169	0.140	0.0127	0.0323				0.0068		0.0033		0.0133					40 x 15	W
CRM	12X 10550 A	0.549	0.281	0.0055	0.0184	0.685	0.0247	0.338	0.0086	0.0290	0.0018	0.0325				0.0059		(0.002)		0.0051					40 x 20	W
CRM	12X 15180 A	0.170	0.212	0.0022	0.0110	1.196	0.1030	0.118	0.0231	0.141	0.0115	0.018				0.0117		0.0016		0.0051					40 x 20	W
CRM	12X 15240 A	0.201	0.198	0.0201	0.0152	1.496	0.0761	0.1032	0.0166	0.200	0.0153	0.0188		0.0020		0.0106		0.0020		0.0070					40 x 20	W
CRM	12X 12700 A	0.365	0.238	0.0116	0.0205	0.636	0.0197	0.070	0.0345	0.0342		0.055		0.0033		0.0060	0.0047	0.0120		0.0073					50 x 20	C
CRM	12X 12701 A	0.330	0.308	0.0124	0.0218	0.636	0.0557	0.235	0.0163	0.0346		0.0426		0.0040		0.0060	0.0058	0.0014		0.0072					50 x 20	C
CRM	12X 12746 U	0.0132	0.183	0.064	0.0247	1.70	0.161	0.182	0.654	0.368	0.202	0.021	0.0283	0.0160	0.101	0.049	0.115								40 x 15	W
CRM	12X 12747 U	0.149	0.337	0.041	0.029	2.02	0.391	0.443	0.500	0.437	0.167	0.015	0.072	0.0375	0.030	0.0114	0.200								40 x 15	W
CRM	12X 12748 U	0.106	0.221	0.050	0.0309	0.902	0.376	0.401	0.329	0.347	0.080	0.111	0.105	0.0499	0.0464	0.129	0.323								40 x 15	W
CRM	12X 12749 W	0.132	0.298	0.101	0.0257	1.250	0.485	0.554	0.224	0.311	0.040	0.004	0.031	0.069	0.034	0.071	0.436								40 x 15	W
CRM	12X 12750 U	0.258	0.599	0.0053	0.0078	0.510	0.786	0.792	0.088	0.106	0.110	0.253	0.159	0.102	0.100		0.581		0.111						40 x 15	W
CRM	12X 349 D	0.194	0.201	0.0232	0.0162	0.498	0.289	0.268	0.123	0.106	0.153	0.149	0.101	0.0172	0.049	0.0096	0.021								40 x 15	W
CRM	12X 350 B	0.138	0.672	0.0363	0.029	0.706	0.162	0.392	0.149	0.150	0.0298	0.341	0.099	0.0286	0.275	0.053	0.0206								40 x 15	W
CRM	12X 352 D	0.298	0.338	0.125	0.066	0.627	0.334	0.423	0.257	0.144	0.105	0.146	0.285	0.0584	0.223	0.0095	0.0504								40 x 15	W
CRM	12X 353 F	0.122	0.154	0.0200	0.0098	0.644	0.218	0.704	0.107	0.271	0.1178	0.093	0.069	0.0108	0.134	0.0489	0.0261		0.060	0.0112	Sold out			40 x 15	W	
CRM	12X 354 B **	0.25	0.20	0.01	0.05	5.0	0.08	0.05	0.03	0.07	0.015	0.02	0.025	0.02	0.025	0.03	0.025		0.08	0.002	** provisional values			40 x 15	W	
CRM	12X 355 C	0.159	0.494	0.0241	0.0214	0.508	0.0710	0.113	0.1010	0.657	0.0564	0.1104	0.153	0.1265	0.037	0.0331	0.0495		0.023	0.0023		0.0395	0.0796		40 x 15	W
CRM	12X 356 C	0.211	0.0662	0.0341	0.0526	0.199	0.0349	0.253	0.0294	0.449	0.0365	0.0338	0.0252	0.0588	0.107	0.0253	0.1499	0.0099	0.0030	0.0061	0.0072	0.0059	0.0291		40 x 15	W
CRM	12X 357 C	0.270	0.153	0.0590	0.0101	0.220	0.0954	0.094	0.0105	0.265	0.0188	0.208	0.0569	0.166	0.0194	0.0147	0.199	0.0094	0.0051	0.0079	0.0058	(0.004)	0.0140		40 x 15	W
1.2.3 Low Alloy Steel																						Size (mm)	Form			
		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	V	W	As	Co	Nb	Ti	Ta	Zn	Zr	N		Ø x H		
CRM	12X LA1 B	0.104	0.777	0.060	0.0090	1.262	0.210	1.026	0.068	0.0572		0.0104	0.448		0.0213	0.0144						0.0144			40 x 15	W
CRM	12X LA2 E	0.195	0.678	0.0263	0.0241	0.57	0.783	0.813	0.136	0.786	0.0066	1.381	0.0990		0.282	0.0306						0.0173			40 x 15	W
CRM	12X LA3 C **	0.50	0.15	0.045	0.025	1.6	0.30	0.35	0.30	0.20		0.04	0.15		0.03	0.05	** provis values			0.003	0.02	0.003			40 x 15	W
CRM	12X LA4 B	0.537	0.335	0.039	0.0363	0.303	0.521	0.499	0.489	0.334		0.057	0.328	0.091		0.105						0.0222			42 x 15	W
CRM	12X LA5 C	0.783	0.493	0.0261	0.0577	0.726	0.484	0.678	0.305	0.158	0.0100	0.10	0.579		0.0085	0.166				0.0091					40 x 15	W
CRM	12X LA6 C	0.018	0.088	0.0103	0.0051	0.0957	0.0549	0.1592	0.0151	0.0240		0.152	0.0061			0.0045				0.0083		0.0059			40 x 15	W
CRM	12X 15217 Q	0.176	1.390	0.073	0.058	0.652	0.864	1.24	0.358	0.231	0.0737	(0.021)	0.662	0.121		0.248	0.131					0.0253			40 x 15	W
CRM	12X 15251 T	1.17	2.27	0.0258	0.0284	1.003	1.035	0.792	0.205	0.110	0.0047	0.050	0.405	0.053		0.259	0.29					0.0232			40 x 15	W
CRM	12X 15252 Q	0.0478	0.265	0.0580	0.0213	0.818	2.03	0.887	0.248	0.154	0.0448	0.074	0.330			0.154	0.10		(0.054)			0.0218			40 x 15	W
CRM	12X 15253 S	0.173	0.299	0.053	0.0552	0.992	0.506	1.505	0.513	0.326	0.129	0.024	0.242	0.265	0.0259	0.0898	0.383		0.011			0.0235			40 x 15	W
CRM	12X 15255 Q	0.351	1.02	0.070	0.104	1.191	0.296	1.509	0.1193	0.279	0.101	0.073	0.475	0.150	0.0193	0.0502	0.152	0.0377				0.027			40 x 15	W
CRM	12X 15256 Q	0.123	0.190	0.0163	0.0125	0.492	5.33	0.362	0.0740	0.0550	0.107	0.1300	0.619	0.101		0.493	0.0509					0.0056			40 x 15	W
CRM	12X 15259 Q	0.603	1.81	0.0704	0.0401	0.401	4.02	0.512	0.407	0.200	0.053	0.1488	0.139	0.49		0.141	0.249					0.0151			40 x 15	W
CRM	12X 15260 W	0.352	0.485	0.074	0.0275	2.08	0.453	2.98	0.098	0.152	0.0094	0.191	0.442		0.055	0.0884	0.254		(0.016)						40 x 15	W
CRM	12X 15266 U	0.425	0.589	0.0156	0.0468	1.203	1.581	3.12	0.318	0.229	0.020	0.466	0.102		0.068	0.379	1.467		0.110		Sold out			40 x 15	EE	
CRM	12X 15254 Z	0.285	0.916	0.047	0.043	1.117	0.394	2.12	0.758	0.123	0.0651	0.599	0.290	0.349		0.550	0.347	0.303							40 x 15	W
CRM	12X 15258 N	0.548	1.020	0.070	0.0439	1.434	0.327	0.465	0.215	0.0934	0.0453	0.032	0.218	0.102		0.272	0.103	0.120							40 x 15	W
CRM	12X 15261 X	0.546	1.513	0.0518	0.090	0.483	0.0985	0.496	1.594	0.308	0.0172	1.648	0.122	0.269	0.0051	0.333	0.601	0.385			0.0297				40 x 15	W

1. Iron Base

Low Alloy Steels

Updated: 12th December 2016

Blocks / Discs

1.2.3 Low Alloy Steel (continued)		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	V	Co	Ti	As	Zn	Pb	Ca	N	Size (mm) Ø x H	Form	
CRM	12X 11572 A	0.111	0.649	0.0025	0.0069	0.498	0.0977	1.107	0.499	0.0576	0.0049	0.0290				0.0030	0.0009			0.0058	38 x 15	W	
CRM	12X 14072 A **	0.44	0.32	0.006	0.015	0.68	0.14	1.07	0.57	0.200	0.005	0.003	0.31	0.01						0.010	** provisional values	38 x 15	W
CRM	12X 19965 A	0.936	0.247	0.0081	0.0196	0.600	0.141	1.713	0.210	0.148	0.0070	0.0256	0.0087				0.0008			0.0087	38 x 15	W	
CRM	12X 21590 A	0.139	0.211	0.0059	0.0128	0.457	0.144	2.10	0.935	0.283	0.0190	0.0202	0.0032		0.0011	0.0091	0.0045			0.0134	ASTM A182 F22	40 x 15	W
CRM	12X 32550 A	0.257	1.59	0.0054	0.0061	1.350	1.750	0.377	0.417	0.108	0.0206	0.0178	0.0222			0.0054				0.0101	38 x 15	W	
CRM	12X 41300 A	0.319	0.183	0.0156	0.0082	0.551	0.084	0.996	0.217	0.131	0.0060	0.027				0.0043	0.0012			0.0095	38 x 15	W	
CRM	12X 41400 A	0.418	0.221	0.0210	0.0138	0.795	0.127	1.003	0.211	0.238	0.0181	0.0195				0.0088				0.0101	38 x 20	W	
CRM	12X 41450 A	0.446	0.261	0.0032	0.0093	1.011	0.187	1.194	0.340	0.1318	0.0090	0.0220	0.0385			0.0053				0.0080	38 x 15	W	
CRM	12X 43400 A	0.422	0.259	0.0284	0.0164	0.592	1.378	1.181	0.223	0.177	0.007	0.013				0.0084	0.0027			0.0089	40 x 15	W	
CRM	12X 44220 A	0.417	1.662	0.0009	0.0050	0.874	1.89	0.846	0.401	0.031	0.0019	0.029	0.0764			0.0026				0.0030	38 x 15	W	
CRM	12X 46150 A	0.160	0.24	0.0074	0.0162	0.471	1.590	0.0348	0.243	0.0158	0.0012	0.0116	0.0019			0.0016	0.0067	0.0012		0.0082	45 x 15	W	
CRM	12X 52986 A	1.023	0.246	0.0011	0.0049	0.372	0.0411	1.418	0.0169	0.077	0.0063	0.0258	0.0615			(0.002)				(0.002)	38 x 15	W	
CRM	12X 61500 A	0.530	0.240	0.0102	0.0104	0.912	0.0976	1.023	0.0195	0.157	0.0114	(0.007)	0.110			0.0067	0.0055				38 x 15	W	
CRM	12X 86200 A	0.198	0.299	0.0104	0.0110	0.849	0.598	0.602	0.224	0.213	0.0100	0.0305	0.0045			0.0051				0.0091	38 x 15	W	
CRM	12X 93106 A	0.122	0.206	0.0103	0.0071	0.605	3.255	1.107	0.0879	0.199	0.0094	0.0246	0.0030			0.0050				0.0098	38 x 15	W	
CRM	12X 24065 A	0.370	0.218	0.0044	0.0129	0.502	0.271	1.412	0.1716	0.216	0.0120	1.035	0.0040		0.0028	0.0074	0.0033			0.0076	40 x 15	W	
CRM	12X 4330V A	0.327	0.303	0.0030	0.0062	0.857	1.99	0.922	0.470	0.0954	0.0071	0.0311	0.0507			0.0059				0.0078	45 x 15	W	
CRM	12X 15CDV6 A	0.171	0.152	0.0086	0.0056	0.839	0.044	1.397	0.875	0.0231	0.0011	0.019	0.242			0.0041				0.0069	40 x 15	W	
CRM	12X 40CDV12 A	0.401	0.250	0.0013	0.0060	0.604	0.1062	3.29	0.946	0.0978	0.0049	0.0208	0.198	0.0197		0.0040				0.0155	38 x 15	W	
CRM	12X 605M36 A	0.373	0.283	0.0317	(0.009)	1.504	0.146	0.243	0.292	0.199	0.0101	0.0105		0.0151		0.0102			0.0033	0.0095	38 x 15	W	
CRM	12X 722M24 A	0.236	0.262	0.0199	0.0135	0.510	0.208	3.094	0.497	0.200	0.0116	0.0187	0.0080			0.0075	0.0028				38 x 15	W	
CRM	12X 826M40 A	0.395	0.248	0.0025	0.0094	0.529	2.408	0.649	0.510	0.1294	0.0085	0.0404				0.0056				0.0089	38 x 15	W	
CRM	12X 835M30 A	0.275	0.198	0.0157	0.0071	0.457	4.01	1.119	0.213	0.195	0.0101	0.004	0.0029		0.0012	0.0068				0.0087	45 x 15	W	
CRM	12X 19MNV56 A	0.174	0.357	0.0245	0.0114	1.563	0.110	0.1087	0.0270	0.203	0.0214	0.0101	0.0939							0.0210	38 x 15	W	

1. Iron Base

Stainless Steels

Updated: 15th December 2016

Blocks / Discs

1.3.2 Austenitic Stainless Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	Co	Nb	N	B	Ta	V	Sb	Ti	W	Zr	Ca	Size (mm) Ø x H	Form	
CRM	13X 17001 B	0.114	0.34	0.016	0.080	1.73	6.05	14.89	0.12	0.037	0.030	0.01	0.15	0.76	0.040	0.008	----	----	----	----	Sold out			----	40 x 15	G
	13X 17002 E	0.112	0.486	0.0250	0.0409	0.801	7.87	17.45	0.204	0.1012	----	(0.030)	0.0702	0.487	0.061	0.0012	(0.012)	0.0587	----	----	----	----	----	40 x 15	W	
	13X 17003 A	0.10	0.78	0.035	0.037	0.85	11.90	11.89	0.27	0.08	----	----	0.07	0.34	----	----	----	----	----	----	----	----	----	40 x 15	C	
CRM	13X 17004 A	0.06	1.32	0.048	0.024	0.62	16.06	21.78	0.31	0.11	----	----	0.05	0.23	----	----	----	----	----	----	sold out			----	40 x 15	G
	13X 17005 D	0.107	1.500	0.057	0.0209	0.349	20.84	24.72	0.699	0.1076	----	----	0.0510	0.191	0.064	0.0028	0.049	----	----	----	----	----	----	40 x 15	CC	
CRM	13X 30300 A	0.041	0.424	0.312	0.0199	1.84	8.55	17.59	0.333	0.0252	----	----	0.0259	----	0.0350	0.0035	----	0.092	----	----	----	----	----	40 x 15	W	
CRM	13X 30403 A	0.0201	0.284	0.0248	0.0297	1.488	7.92	18.25	0.192	0.217	----	----	0.101	(0.019)	0.081	----	----	0.113	----	----	0.018	----	----	40 x 15	W	
CRM	13X 30908 A	0.0560	0.320	0.0011	0.0267	1.638	12.05	22.51	0.221	0.269	----	0.0035	0.120	0.0142	0.0652	0.0027	----	0.128	----	----	----	----	----	38 x 15	W	
CRM	13X 32100 A	0.0463	0.498	0.0011	0.0298	1.52	9.32	17.39	0.282	0.415	0.0115	0.0247	0.105	0.0191	0.0115	0.0025	----	0.106	----	0.376	0.021	----	----	38 x 15	W	
CRM	13X 34700 A	0.016	0.480	(0.0005)	0.0276	1.283	9.32	17.22	0.392	0.165	0.0053	0.025	0.132	0.329	0.0163	0.0007	----	0.123	----	----	0.144	----	----	38 x 15	W	
CRM	13X 18001 B	0.207	0.203	0.0786	0.0090	0.463	6.13	15.92	0.816	0.149	----	0.0157	0.0231	0.612	0.0347	----	----	0.0996	----	----	----	----	----	40 x 15	W	
CRM	13X 18002 D	0.159	0.352	0.0487	0.0245	0.722	7.92	17.77	0.209	0.116	----	0.0617	0.0514	1.531	0.072	----	----	0.0542	----	----	----	----	----	40 x 15	W	
CRM	13X 18003 C	0.113	0.805	0.0245	0.0545	1.000	10.08	19.56	0.401	0.0433	----	0.0292	0.100	1.042	0.090	----	----	0.0750	----	----	----	----	----	40 x 15	W	
CRM	13X 18004 B	0.099	1.21	0.0191	0.068	1.400	12.67	21.57	0.601	0.050	----	0.0111	0.211	0.749	0.061	----	----	0.161	----	----	----	----	----	40 x 15	W	
CRM	13X 19001 B	0.055	1.20	0.0174	0.0151	0.460	5.10	15.07	1.51	0.202	----	----	0.025	0.032	0.070	----	(0.019)	0.083	----	----	----	----	----	40 x 15	W	
CRM	13X 19003 C	0.047	0.497	0.046	0.0382	1.138	12.46	18.99	2.50	0.171	----	----	0.105	0.120	0.077	----	----	0.0486	----	----	----	----	----	40 x 15	W	
	13X 19004 B	0.066	0.36	0.014	0.069	1.96	17.9	22.8	3.62	0.022	----	----	----	0.18	----	----	----	----	----	sold out			----	40 x 15	G	
CRM	13X 12533 Z	0.110	0.440	0.0156	0.0149	0.812	5.06	18.80	1.05	0.131	0.0097	0.059	0.0299	----	0.073	0.0100	----	0.181	----	0.147	----	----	----	40 x 15	CC	
CRM	13X 12534 X	0.0716	0.811	0.0086	0.0192	0.589	8.50	17.71	2.04	0.0586	----	0.0485	0.0602	0.201	----	----	0.031	0.110	----	0.348	0.010	----	----	40 x 15	W	
CRM	13X 12535 BE	0.229	1.407	0.0591	0.0400	0.342	14.79	16.95	4.09	0.130	0.0194	0.194	0.146	----	0.029	0.0051	(0.020)	0.252	----	0.625	----	----	----	40 x 15	CC	
CRM	13X 12536 S	0.149	0.865	0.136	0.052	0.406	12.07	15.30	2.54	0.065	0.018	0.049	0.298	----	0.062	0.0274	0.091	----	----	0.105	----	----	----	40 x 15	CC	
CRM	13X 12537 T	0.0889	1.151	0.0206	0.0382	1.116	10.71	20.43	3.05	0.248	0.0401	(0.062)	0.1520	0.102	0.048	0.0029	0.0194	0.0908	----	0.273	----	----	----	40 x 15	CC	
CRM	13X 31603 A	0.0242	0.332	0.0246	0.0284	1.78	10.17	16.83	1.98	0.322	0.0045	0.0098	0.0571	0.0078	0.080	0.0011	----	0.093	----	----	0.0444	----	----	40 x 15	W	
CRM	13X 31603 B	0.0167	0.325	0.0210	0.0262	1.898	10.07	16.89	2.04	0.350	0.0057	0.009	0.133	0.0099	0.082	----	----	0.101	----	(0.001)	0.063	----	0.0022	30 x 20	W	
CRM	13X 31603 C	0.023	0.350	0.0245	0.0263	1.879	10.03	16.83	2.02	0.306	0.0053	(0.005)	0.148	0.0197	0.080	----	----	0.0895	----	----	0.0427	----	0.0029	30 x 20	W	
CRM	13X 31635 A	0.0254	0.487	0.0301	0.0352	1.807	10.80	16.98	2.089	0.404	----	0.0054	0.174	0.010	0.020	----	----	0.0584	----	0.149	0.031	----	----	40 x 15	W	
CRM	13X 12853 K	0.109	1.057	0.025	0.0216	0.838	12.09	17.15	2.73	0.587	----	----	0.285	----	----	0.0051	0.013	----	0.0203	0.0028	0.095	0.015	----	40 x 15	CC	
CRM	13X 12854 L	0.053	1.308	0.0278	0.024	1.300	11.60	15.77	2.50	0.306	----	----	0.33	0.689	0.0550	0.0076	(0.06)	----	----	0.065	0.16	----	----	40 x 15	CC	
CRM	13X 12855 M	0.182	1.10	0.0233	0.0240	1.162	10.80	17.13	2.86	0.446	----	----	0.226	----	----	0.0099	0.050	----	0.210	0.061	0.201	----	----	40 x 15	CC	
1.3.3 Maraging Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Al	Ti	Co	N											Size (mm) Ø x H	Form	
CRM	13X 14934 Q	0.0254	0.502	0.0288	0.024	0.254	17.60	0.388	4.22	0.15	0.694	9.03	0.006											40 x 15	CC	
CRM	13X 14935 T	0.0105	0.441	0.055	0.036	0.494	18.96	0.745	5.61	(0.007)	0.106	7.17	0.0102											40 x 15	CC	

1. Iron Base

Stainless Steels

Updated: 15th December 2016

Blocks / Discs

1.3.4 Ferritic & Martensitic Stainless Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	Ti	V	As	Co	Nb	W	B	Sb	Pb	Ca	N	Size (mm)	Form
		Ø x H																							
CRM	13X 12547 M	0.238	0.344	0.0746	0.0441	1.191	1.492	17.49	1.006	0.531	0.030			0.1021		0.302	0.347						0.099	40 x 15	CC
CRM	13X 12548 M	0.189	0.421	0.218	0.0260	0.576	1.08	12.98	1.33	0.228						0.352	0.585	0.033		0.022			0.0508	40 x 15	CC
CRM	13X 12549 L	0.1025	0.344	0.124	0.0052	0.354	1.203	12.01	1.311	0.492				0.0144		0.492	0.19						0.0393	40 x 15	concast
CRM	13X 14775 R	0.05	0.63	0.054	0.053	1.37	1.75	17.7	0.47	0.21						0.15	0.75							40 x 15	C
	13X 15023 V	0.118	0.311	0.008	0.014	1.352	0.850	10.96	1.052	(0.052)		0.14		0.0252		0.0555	1.53	0.018		sold out			0.0409	40 x 15	CC
CRM	13X 15024 X	0.166	0.749	0.0294	0.0284	0.610	2.99	14.65	0.299	0.332		0.0049		0.150		0.1059	0.099	0.039					0.0156	40 x 15	W
CRM	13X 15035 U	0.115	0.636	0.0456	0.0415	0.674	2.38	14.00	0.399	0.204		(0.093)		0.160		0.199	0.500	0.048					0.0584	40 x 15	CC
CRM	13X 15059 P	0.084	0.495	0.0133	0.0130	0.995	1.584	15.85	0.600	0.105	(0.02)		0.038	0.070		0.266	0.430	0.081					0.113	40 x 15	CC
CRM	13X 1.4122 A **	0.35	0.46	0.002	0.017	0.47	0.62	15.9	0.85	0.065	0.003	0.002		0.10		0.022	0.006	0.003	** provis values				0.030	40 x 15	W
CRM	13X 1.4418 A **	0.042	0.29	0.015	0.025	0.81	4.65	15.4	0.85	0.17	0.005	0.002		0.055		0.10	0.01	0.01	** provis values				0.042	40 x 15	W
CRM	13X 1.4923 A **	0.20	0.33	0.003	0.021	0.50	0.46	11.2	0.82	0.055	0.003	0.003		0.30		0.02	0.005		** provis values			0.005	0.033	40 x 15	W
CRM	13X 1.4713 A **	0.045	0.92	0.008	0.018	0.49	0.12	7.1	0.025	0.038	0.003	0.55	0.005	0.045		0.01			** provis values				0.006	40 x 15	W
CRM	13X 1.4742 A **	0.085	0.90	0.002	0.022	0.72	0.45	17.6	0.10	0.13	0.005	0.82	0.005	0.045		0.015	0.02		** provis values				0.02	40 x 15	W
CRM	13X 1.4762 A **	0.082	1.05	0.001	0.028	0.66	0.35	24.3	0.055	0.08	0.005	1.3	0.007	0.10		0.03	0.03		** provis values			0.0025	0.027	40 x 15	W
CRM	13X 41001 A	0.136	0.298	0.0037	0.0142	0.464	0.0939	12.06	0.0102	0.056	0.0051	(0.004)		0.079		0.0143						0.0010	0.0316	41 x 15	W
CRM	13X 41500 A	0.0385	0.402	0.0101	0.021	0.596	3.52	13.00	0.504	0.1296			0.0012	0.091		0.0999	0.0405						0.0504	40 x 15	W
CRM	13X 42000 A	0.208	0.496	0.0253	0.0241	0.679	0.295	12.56	0.0398	0.202	0.0073			0.046		0.0161		0.0013					0.0273	38 x 15	W
CRM	13X 43100 A	0.166	0.535	0.0050	0.0199	0.378	2.10	16.39	0.0768	0.134	0.004			0.0577		0.0239	0.006	0.004					0.075	38 x 15	W
CRM	13X 44004 A	1.052	0.363	0.0178	0.0214	0.346	0.207	16.74	0.462	0.0548		0.0305		0.076		0.0188		0.030					0.0247	40 x 15	W
CRM	13X 41600 A	0.111	0.442	0.302	0.0253	0.627	0.331	13.23	0.0499	0.160	0.0066	(0.004)		0.0888		0.0216	0.0053	(0.003)					0.0245	41 x 15	W
CRM	13X 43020 A **	0.15	0.45	0.19	0.025	1.45	0.52	16.0	0.23	0.07		0.005		0.055		0.02	0.01	0.01	0.005	** provis values			0.022	40 x 15	W
CRM	13X 8110L D	0.750	0.812	0.068	0.052	0.446	4.62	12.30	2.81	0.344		(0.071)	0.0108	0.211	0.074	0.31			0.989				0.0286	40 x 15	CC
1.3.5 Special Stainless Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Al	Ti	V	W	Co	Nb	Ta	N	B	Size (mm)		Form			
		Ø x H																							
CRM	13X 12538 J	0.04	0.64			0.78	6.07	23.72	1.53											40 x 15			C		
	13X 12540 M	0.131	0.805	0.0512	0.051	0.800	4.975	27.44	0.993	0.181			0.210	0.097	0.109	0.107		0.054		40 x 15			CC		
CRM	13X 14207 K	0.147	1.52	0.052	0.0213	0.901	12.60	19.83	0.299	0.248				3.18	0.033	0.245	(0.064)	0.097		low stock		40 x 15	CC		
CRM	13X 14211 Q	0.064	1.64	0.0146	0.0157	0.766	12.55	25.70	0.325	0.161	(0.11)	0.220		3.24	0.071	0.161				40 x 15			CC		
CRM	13X 14212 R	0.104	2.02	0.025	0.0290	1.29	8.79	20.86	0.670	1.184	0.12	0.15	0.134	2.01	0.252	0.980		0.156		sold out		40 x 15	CC		
CRM	13X 14215 L	0.136	0.596	0.0068	0.0050	1.110	15.86	22.89	0.0048	0.0110			0.0480	3.02	0.0057	0.0196				40 x 15			concast		
CRM	13X 14216 P	0.0424	1.566	0.0070	0.0048	0.663	12.06	23.44	0.209	0.231			0.0722	2.25	0.248	0.248		0.0152		40 x 15			concast		
CRM	13X 14219 K	0.0997	1.504	0.0456	0.0401	0.482	12.66	21.46	0.169	0.138			0.0188	4.17	0.0475	0.140				40 x 15			concast		
CRM	13X 31008 A	0.063	0.503	0.0040	0.0302	1.234	19.34	24.48	0.338	0.159			0.078	0.165	0.078	0.013		0.063		UNS S31008		38 x 15	W		
CRM	13X 42200 A **	0.22	0.32	0.001	0.018	0.65	0.73	11.5	1.06	0.14	0.003		0.25	1.15	0.01	0.02		0.060	** provis values		UNS S42200	38 x 15	W		
CRM	13X 64152 A	0.114	0.224	0.0020	0.0123	0.666	2.50	11.34	1.567	0.0622	0.0315		0.275		0.0185			0.0339		UNS S64152		38 x 15	W		
CRM	13X 66286 A	0.035	0.216	(0.0006)	0.0172	1.173	25.21	14.99	1.185	0.195	0.193	1.92	0.262	0.098	0.083			0.0040	0.0044	UNS S66286		38 x 15	W		

1. Iron Base

Stainless Steels

Updated: 15th December 2016

Blocks / Discs

1.3.6		Precipitation Hardening Steels																	Size (mm)		Form	
		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Ti	Al	V	Co	Nb	W	B	N	Ø x H			
CRM	13X PH2 M	0.0598	0.502	0.0419	0.0201	1.184	3.56	16.80	1.009	4.03	0.049	0.0419	0.1028	0.0927	0.143		0.0047	0.052	40 x 15	W		
CRM	13X PH3 M	0.184	1.60	0.0208	0.0188	0.395	3.08	15.86	0.751	5.99			0.176	0.420	0.394		0.0049	0.070	40 x 15	CC		
CRM	13X PH4 N	0.0400	0.747	0.0166	0.0285	0.793	4.00	14.87	0.247	5.24	0.100	0.094	0.500	0.600	0.303		0.0033	0.078	40 x 15	W		
CRM	13X PH7 F	0.118	1.402	0.0057	0.0283	1.487	5.41	13.16	2.52	0.777	0.0196	0.012	0.043	0.0493	0.241			0.044	40 x 15	W		
CRM	13X PH13800 A	0.0386	0.081	0.0030	0.0064	0.0332	8.04	12.52	2.10	0.0449	0.0122	1.075	0.0188	0.0220				0.0041	UNS S13800	38 x 15	W	
CRM	13X PH17400 A	0.0200	0.349	0.0215	0.0202	0.829	4.52	15.74	0.061	3.09			0.112	0.0411	0.184			0.0342	UNS S17400	41 x 15	W	
CRM	13X PH17700 A	0.0732	0.551	0.0008	0.0181	0.496	6.98	16.88	0.340	0.146	0.051	1.172	0.0390	0.0464	0.0201	0.009	0.0033	0.0192	UNS S17700	38 x 15	W	
CRM	13X PH2S143 A	0.044	0.479	0.0021	0.0212	0.546	5.20	13.46	1.326	1.61			0.087	0.0483	0.225	0.018		0.0246		32 x 15	W	
CRM	13X FV520B A	0.0181	0.342	0.0016	0.0221	0.655	5.29	13.73	1.334	1.462			0.080	0.030	0.301	0.020		0.0197		40 x 15	W	
CRM	13X 45500 A **	0.003	0.055	0.002	0.005	0.027	8.3	11.4	0.015	2.2	1.2	0.07	0.065	0.015				0.002	** provis values	UNS S45500	38 x 15	W
1.3.7		High Nitrogen Stainless Steels																	Size (mm)		Form	
		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Al	V	W	Co	Nb	B	N	Ø x H				
CRM	13X NSA2 H	0.132	0.739	0.0278	0.0252	1.014	10.08	17.82	2.013	0.259		0.139			0.155		0.131	40 x 15	CC			
	13X NSA3 J	0.16	0.57			1.07	12.0	16.1	2.8								0.20	40 x 15	W			
CRM	13X NSA4 B	0.115	0.519	0.0095	0.0302	5.55	17.62	23.85	4.32	0.595	0.0048				0.154		0.446	40 x 15	CC			
CRM	13X NSA5 A	0.063	0.281	0.0212	(0.010)	4.27	9.52	20.73	2.32	0.098	(0.012)				0.574		0.340	40 x 15	CC			
CRM	13X NSA6 B	0.0467	0.64	0.0113	0.060	1.607	31.13	26.14	7.03	1.52	(0.08)				0.149		0.245	40 x 15	CC			
CRM	13X NSA7 A	0.0209	0.359	0.0009	0.022	0.951	5.67	25.91	3.25	1.42	(0.009)				0.015		0.247	UNS S32550	42 x 15	W		
CRM	13X NSA8 A	0.0240	(0.40)	0.0008	0.0216	0.656	6.29	25.93	3.60	0.903		0.060	0.586	0.0374	(0.004)		0.239	UNS S32760	44 x 15	W		
CRM	13X NSA9 A	0.019	0.469	(0.0007)	0.0248	1.592	5.44	22.57	3.11	0.240		0.068	0.024	0.072	0.012		0.156	UNS S31803	40 x 15	W		
CRM	13X NSA10 A	0.016	0.375	0.0006	0.0207	5.23	12.96	20.69	2.636	0.175		0.151	0.061	0.061	0.142	(0.0029)	0.343	UNS S20910	38 x 15	W		
CRM	13X NSA11 A	0.0159	0.275	<0.001	0.0186	0.640	23.89	20.19	6.16	0.187	(0.02)	0.0513	0.038	0.0981	0.150		0.203	UNS N08367	38 x 15	W		
CRM	13X NSA12 A	0.0192	0.492	0.0007	0.0267	1.272	24.84	19.63	4.20	1.485	0.0169	0.0660	0.047	0.090	0.0088	0.0020	0.0662	UNS N08904	40 x 15	W		
CRM	13X 21800 A	0.0765	4.03	0.0011	0.032	8.00	8.32	16.81	0.325	0.431	0.012	0.0619		0.0943	0.007	(0.001)	0.125	Nitronic 60/UNS S21800	38 x 15	W		
CRM	13X 31254 A	0.0185	0.400	0.0011	0.0191	0.590	18.34	20.11	6.13	0.575	0.0134	0.0595	0.017	0.125		0.0025	0.205	254SMO/UNS S31254	40 x 15	W		
CRM	13X 31726 A	0.0124	0.415	0.0012	0.0218	1.849	13.56	17.62	4.56	0.206	0.0208	0.0426	0.0384	0.0502	0.009		0.135	317LMN/UNS S31726	40 x 15	W		
CRM	13X 32101 A	0.0325	0.777	(0.0004)	0.0194	4.913	1.476	21.12	0.0970	0.295	0.0122	0.0830		0.0347	0.0070	0.0014	0.241	UNS S32101	38 x 15	W		
CRM	13X 32900 A	0.0251	0.556	0.0269	0.0276	1.478	5.57	24.91	1.310	0.354	0.007	0.0938	0.017	0.0724		0.0028	0.097	UNS S32900	40 x 15	W		
	13X NSB1 D	0.17	0.58			0.44	10.0	19.1	0.11								0.04	40 x 15	W			
	13X NSB2 D	0.06	0.66			0.62	11.1	18.2	0.21								0.095	40 x 15	W			
CRM	13X NSB3 G	0.121	0.471			0.632	9.26	15.22	0.630								0.198	42 x 15	W			
CRM	13X NSC1 P	0.316	0.788	0.0097		6.53	5.06	18.76	0.196	0.391		0.501	0.100		1.499		0.0877	40 x 15	CC			
CRM	13X NSC2 P	0.560	0.997	0.0117		8.70	4.20	21.98	0.850	1.026		0.321	0.062		2.21		0.341	40 x 15	CC			
CRM	13X NSC3 Z	0.895	1.28	0.0110		10.15	2.96	23.02	0.060	0.100	0.105	0.110			2.81		0.498	40 x 15	CC			
CRM	13X NSC4 F	0.513	1.52	0.0071		7.97	7.03	32.58	1.390	0.162	0.119	0.219	0.204	0.218	2.41		0.942	40 x 15	CC			
CRM	13X NSC5 B	0.558	1.19	0.0155		2.22	4.34	22.10	(0.01)	0.787	0.21	0.0461			2.38		0.296	40 x 15	CC			
CRM	13X NSC6 A	0.0266	0.523	0.0055	0.0049	8.85	6.52	20.47	(0.002)	0.0064	(0.009)	0.0052					0.235	40 x 13	HIP			
CRM	13X NSC7 A	0.410	0.803	0.0091	0.0155	3.80	7.41	23.63	0.448	0.144	(0.1)	0.123	0.052	0.308	0.509		0.337	40 x 15	CC			

1. Iron Base		Special Steels																		Updated: 15th December 2016		Blocks / Discs	
1.4.2 Tool Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	V	W	As	Co	Nb	N	Pb	Alloy Type	Size (mm) Ø x H	Form	
CRM	14X HS1 C	0.718	0.22	0.020	0.018	0.29	0.27	4.00	0.37	0.069	(0.035)		1.05	17.0		0.25		0.023		T-1	40 x 15	W	
CRM	14X HS10 A	1.710	0.660	0.0099	0.0135	0.134	0.146	14.83	1.679	0.0605			1.142	1.75		0.0866		(0.001)			48 x 13	HIP	
CRM	14X HS11 A	1.739	0.794	0.0107	0.0133	0.237	0.188	19.34	1.52	0.0562			1.032	2.24		0.074		(0.002)			48 x 13	HIP	
CRM	14X 72305 A	1.085	0.206	0.0028	0.0128	0.349	0.089	0.425	0.0231	0.149	0.0101	0.0049	0.0045					0.0068		W-5	40 x 15	W	
	14X 14946 D	0.85	0.46	0.048	0.051	0.53	1.06	5.06	0.21	0.25			1.03	16.9(7)		0.44				T-1	40 x 15	C	
1.4.5 High Manganese Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	V	Nb	Ti	Ta	N			Size (mm) Ø x H	Form		
CRM	14X MN1 AL **	0.57	0.9	0.005	0.05	22	0.7	1.3	0.5	0.2	0.04	0.2	0.025	0.1	0.035	0.007	0.06	** provisional values		40 x 15	CC		
CRM	14X MN2 R	0.701	1.48	0.0098	0.0198	9.65	0.530	0.355	1.546	0.081	0.061	0.120	0.121	0.294	0.179		0.0125			40 x 15	CC		
CRM	14X MN3 T	0.994	1.00	0.0091	0.039	11.03	0.497	0.749	0.259	0.153	0.0195	0.041	0.0198	0.407			0.034			40 x 15	CC		
CRM	14X MN4 AC **	0.9	0.9	0.02	0.07	13.7	1.05	2.0	0.8	0.27	0.07	0.2	0.035	0.15	0.075	0.001	0.045	** provisional values		40 x 15	CC		
CRM	14X MN5 T	1.377	1.59	0.0110	0.0270	8.55	1.372	3.31	1.91	0.421	0.0129	(0.26)	0.0397	0.021	(1.00)	0.005	0.0155			40 x 15	CC		
1.4.8 Free Machining & Resulfurised Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	V	Co	As	Pb	B	N			Size (mm) Ø x H	Form	
CRM	14X MSFM1 L	0.143	0.404	0.414	0.0689	1.155	0.147	0.89	0.264	0.1073	0.0289	(0.08)	0.0154	0.0509				0.026			40 x 15	CC	
CRM	14X MSFM2 K	0.272	0.353	0.248	0.0491	1.568	0.235	0.996	0.355	0.162	0.0218	0.123	0.0324	0.104				0.028			40 x 15	CC	
CRM	14X MSFM3 G	0.438	0.292	0.147	0.0297	1.809	0.161	0.454	0.390	0.205	0.0378	(0.18)	0.0199	0.0494			0.0043	0.0206			40 x 15	CC	
CRM	14X MSFM4 A	0.226	0.469	0.224	0.0386	1.141	6.22	1.69	0.974	0.429	0.0141	(0.007)	0.0151	0.0253				0.0220			40 x 15	CC	
CRM	14X 11170 A	0.154	0.151	0.120	0.0133	1.129	0.0877	0.1126	0.0317	0.1101	0.0110	0.0023			0.0044	0.0011		0.0112			38 x 15	W	
CRM	14X 11390 A	0.419	0.198	0.191	0.0342	1.040	0.0239	0.0609	0.0067	0.0395	0.0022	0.0026			0.0028			0.0042			38 x 15	W	
CRM	14X 12144 A	0.0800	0.0093	0.325	0.0630	1.227	0.0162	0.0807	0.0089	0.0106		0.0034			0.0022	0.328		0.0066			38 x 15	W	
CRM	14X 12130 A	0.0871	0.022	0.305	0.061	1.219	0.0345	0.0505	0.0102	0.0201	0.0054	0.0024			0.0016			0.0097			38 x 15	W	
CRM	14X 606M36T A	0.378	0.167	0.196	0.0159	1.574	0.0931	0.163	0.272	0.179	0.0103	0.0071			0.0085			0.0096			38 x 15	W	
1.4.11 High-Ni Steels		C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Al	Co	Ti	Mg	N			Size (mm) Ø x H	Form				
CRM	14X FeNi6 A	0.100	0.0750	0.0275	0.0150	0.331	6.09	0.0732		0.0287	0.0247				0.0056			40 x 15	W				
CRM	14X FeNi 8 A	0.0974	0.099	0.0284	0.0151	0.333	8.11	0.251		0.0304	0.030				0.0062			40 x 15	W				
CRM	14X FeNi10 A	0.094	0.061	0.0275	0.0151	0.274	10.10	0.070		0.0281	0.0251				0.0052			40 x 15	W				
CRM	14X FeNi20 B	0.0137	1.12	0.0089	0.010	0.0284	20.06	0.102		0.074	0.018	0.994						40 x 15	CC				
CRM	14X FeNi25 B	0.0084	0.019	0.58	0.011	0.0121	25.10	0.0334		0.035	0.103	0.746						40 x 15	CC				
CRM	14X FeNi35 C	0.082	0.309	0.140	0.030	0.174	34.52	0.1006		0.355	0.004	0.343				sold out		40 x 15	CC				
CRM	14X FeNi40 B	0.0450	0.030	(1.09)	0.0185	0.081	40.57	0.0446		0.0517	1.18	0.858				low stock		40 x 15	CC				
CRM	14X FeNi45 B	0.0045	0.567	0.038	0.0416	0.0149	45.20	0.048		0.078	0.552	0.654				low stock		40 x 15	CC				
CRM	14X FeNi50 B	0.0488	0.203	0.243	0.0259	0.115	50.09	0.093		0.105	0.052	0.499				sold out		40 x 15	CC				
CRM	14X 93603 A	0.0101	0.153	0.0045	0.0050	0.339	35.79	0.024	0.0145	0.0460	0.0404	0.0974	0.0011	0.0019	0.0057	Invar/UNS K93603		40 x 15	W				
CRM	14X 94100 A	0.0055	0.103	0.0027	0.0051	0.443	41.00	0.0265	0.0053	0.0628		0.0208	0.0011	0.0021	0.0016	UNS K94100		40 x 15	W				

2. Nickel Base

Updated: 12th December 2016

Blocks / Discs

2.1.2 Residuals in Nickel																	Size (mm)	Form			
		Si	Mn	Cu	Fe	Cr	Co	Ti	Al	Mg							Ø x H				
	21X 17520 H	0.20	0.18	0.09	0.25	0.10	0.48	0.08	0.04	0.06							40 x 15	C			
	21X 17521 J	0.28	0.11	0.16	0.24	0.16	0.26	0.12	0.03	0.03							40 x 15	C			
2.2	Ni/Cr (Nimonic Type)															Size (mm)	Form				
		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	Mg	Zr	Pb	W	B	Ø x H				
	22X 801 D	0.14	0.51	0.56	0.22	0.57	20.75	0.25	0.25	2.19	1.33	0.03					40 x 15	C			
	22X 803 E	0.06	1.05	0.22	0.007	0.33	19.85	0.50	0.50	1.93	1.60	0.0002					40 x 15	C			
	22X 804 D	0.07	0.56	0.54	0.21	0.66	19.72	0.09	0.20	2.34	1.33	0.004					40 x 15	C			
	22X 806 D	0.007	0.10	0.09	0.004	0.18	19.66	0.01	0.03	2.48	1.35		0.004	0.007	0.02	0.004	40 x 15	C			
																	Size (mm)	Form			
			C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	Mg	S	P	B	Ø x H				
	22X 903 C	0.08	1.09	0.25	0.01	0.83	19.84	0.07	17.60	1.86	1.67	0.002					40 x 15	C			
	22X 904 C	0.08	0.52	0.50	0.10	0.25	19.9	0.21	16.9	2.26	1.29	0.005					40 x 15	C			
22X 1052 C	0.19	0.51	0.26	0.13	0.65	15.7	4.48	18.6	1.09	4.08	0.002					40 x 15	C				
2.3	Fe/Ni/Cr (Incoloy Type)															Size (mm)	Form				
		C	Si	Mn	Cu	Cr	Mo	Co	Ti	Al	Ni						Ø x H				
	23X 8004 E	0.06	0.53	0.70	0.30	19.72	0.33	0.53	0.34	0.31	31.8						40 x 15	C			
	23X DS2 E	0.06	2.07	1.00	0.30	17.81	0.30	0.48	0.17	0.04	37.4						40 x 15	C			
	23X DS4 E	0.06	2.01	1.02	0.30	16.83	0.29	0.48	0.20	0.037	37.15						40 x 15	C			
	23X DS5 E	0.080	1.98	1.04	0.30	18.64	0.30	0.50	0.17	0.083	36.57						40 x 15	C			
2.4.1 Waspalloy, 720-types																	Size (mm)	Form			
		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	S	P	Ni	B	W	Zr	Nb	N	Ø x H	
CRM	24X 07001 B	0.0357	0.064	0.0311	0.0115	0.997	19.52	4.29	13.31	3.01	1.384	(0.0007)	0.0033	57.2	0.0060		0.0563	0.0314		32 x 20	W
CRM	24X 7201 A	0.0326	0.039	0.0022		0.09	15.99	3.01	14.79	5.11	2.47	0.0027	0.0030	57.09	0.0246	1.29	0.0432		0.0043	40 x 13	HIP
2.5	Ni/Cr/Nb/Mo															Size (mm)	Form				
		Si	Mn	Cu	Fe	Cr	Mo	Co	W	Nb							Ø x H				
	25X 10221 F	0.45	0.28	0.11	0.62	20.0	6.57	0.26	2.23	7.43							40 x 15	C			
	25X 10235 E	0.56	0.53	0.26	1.26	19.87	5.85	0.53	3.14	7.25							40 x 15	C			
2.6	Ni/Cr/Mo															Size (mm)	Form				
		Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al							Ø x H				
	26X 11384 E	0.15	0.13	0.12	0.98	20.5	10.2	0.30	2.6	0.50							40 x 15	C			

2. Nickel Base

Updated: 15th December 2016

Blocks / Discs

2.7 Ni/Cr/Mo/Co		Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al											Size (mm) Ø x H	Form			
	27X 14184 F	0.41	0.40	0.09	0.40	21.8	10.7	10.5	0.02	0.02											40 x 15	C			
	27X 14188 D	0.33	0.30	(0.003)	0.44	21.17	10.3	10.4	0.03	<0.01											40 x 15	C			
	27X 14387 E	0.28	0.27	<0.005	1.11	20.2	10.8	10.0	<0.005	<0.005											40 x 15	C			
2.8 Ni/Cr/Fe (Inconel Type)		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	Mg	S	P	Nb	Ta	B	Ni	N	Size (mm) Ø x H	Form				
	28X 6001 G		0.95	0.12	0.83	6.33	16.38		1.02	0.58	0.02	0.01								40 x 15	C				
	28X 6002 F		0.25	0.65	0.02	8.24	16.23		0.22	0.12	0.18	0.004								40 x 15	C				
	28X 6003 E		0.74	0.47	0.42	7.1	15.56		0.62	0.22	0.025	0.01								40 x 15	C				
	28X 6004 E		0.65	0.38	0.42	7.17	16.21		0.77	0.27	0.05	0.008								40 x 15	C				
	28X 6005 E		0.60	0.39	0.39	6.98	16.93		0.62	0.28	0.06	0.002								40 x 15	C				
	28X X7504 D	0.03	0.39	1.09	0.22	6.42	14.22	0.46		2.59	0.70				0.95					40 x 15	C				
CRM	28X 6251 M	0.002	0.252	0.069	0.057	4.21	20.24	9.58	0.0078	0.0097	0.006		0.0013	0.0023	2.64	0.0111	0.0040	62.95		40 x 15	concast				
CRM	28X 6252 P	0.093	0.605	0.323	0.161	4.55	21.48	9.04	0.215	0.072			0.0145	0.0106	3.60	0.017		60.00	0.0796	sold out ** provisional values	40 x 15	CC			
CRM	28X 6253 T **	0.12	1.3	0.52	0.31	5.6	22	7.8	0.40	0.25	0.2		0.01	0.02	4.5	0.04		[bal]	0.09		40 x 15	CC			
CRM	28X 6254 M	0.047	(0.79)	0.457	0.044	3.33	22.71	8.92	0.195	(0.15)	(0.01)		0.0160	0.0097	3.60		0.005	59.55	0.0364		40 x 15	CC			
CRM	28X 6255 M	0.0343	0.447	0.203	0.0646	2.03	19.63	8.31	0.164	0.348	0.337		0.0081	0.0104	4.09	0.093	0.0101	64.2		40 x 15	concast				
CRM	28X 6256 A	0.0173	0.041	0.0004	0.018	(0.034)	21.29	8.81		0.266	0.301		(0.002)	0.0033	3.75			65.4	0.007	40 x 13	HIP				
CRM	28X 06625 A	0.020	0.273	0.090	0.0288	0.917	21.94	9.15	0.031	0.238	0.184		0.0037	(0.002)	3.52		0.0009	63.49	0.0219	40 x 15	W				
CRM	28X 7181 J	0.0198	0.811	0.150	0.042	18.98	18.42	3.25	(0.014)	0.125	0.070		0.0089	0.0146	4.88		0.0021	53.10	0.038	40 x 15	CC				
CRM	28X 7182 N	0.0840	0.706	0.417	0.125	18.04	19.22	2.59	0.515	0.691	(0.31)		0.0125	0.0110	4.54	0.025	0.0042	52.6	0.064	40 x 15	CC				
CRM	28X 7183 U	0.104	0.903	0.534	0.321	15.48	18.38	3.66	0.986	0.959	0.499		0.0217	0.0213	5.66		0.0114	(52.3)	0.0420	sold out low stock	40 x 15	CC			
CRM	28X 7184 K	0.085	0.403	0.215	0.123	18.22	16.91	3.07	0.44	0.633	0.620		0.0158	0.0103	5.07	0.077	0.0052	54.16	0.084		40 x 15	CC			
CRM	28X 7185 K	0.060	0.882	0.286	0.203	18.44	20.77	2.71	0.220	0.281	0.359		0.0089	0.0189	4.61	0.115	0.0107	50.67	0.172		40 x 15	CC			
CRM	28X 7186 K **	0.03	0.55	0.22	0.10	16.1	17.5	3.1	0.32	0.89	0.67		0.008	0.02	5.1		0.005	[bal]	0.035	** provisional values	40 x 15	CC			
CRM	28X 07718 A	0.026	0.076	0.055	0.038	19.55	18.62	3.01	0.172	0.945	0.544		0.0015	0.0063	5.05		0.0034	51.99	0.0056	38 x 15	W				
2.10 Ni/Co/Cr/Al/Ti		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	Zr	V											Size (mm) Ø x H	Form
	210X 11979 G	0.025	0.30	0.13	0.07	0.56	8.07	3.28	14.32	5.22	3.76	0.04	0.82											40 x 15	C

2. Nickel Base

Updated: 15th December 2016

Blocks / Discs

2.12 Ni/Cu (Monel Type)																						Size (mm)	Form			
		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	Mg	S	P	Nb	Pb	Sn	Zn	Cd	Be	Bi	Se		Ni	Ø x H	
CRM	212X 4001 P	0.0130	1.48	2.95	28.92	0.503	0.0795		0.111	(0.094)	0.0396	0.0016	0.0206	0.0198	0.100	0.0703	0.053						65.49	40 x 15	CC	
CRM	212X 4002 L	0.0369	0.090	1.68	32.41	1.022	0.084		0.064	0.0421	0.081	0.0222	0.0019		0.0318	0.0373							64.33	40 x 15	CC	
CRM	212X 4003 K	0.036	0.245	1.105	30.13	2.63	0.097	0.0317	0.0286	0.0201	0.010	0.050	0.0257	0.0059	0.150	0.053							(65.3)	40 x 15	CC	
CRM	212X 4004 M	0.081	0.557	0.953	29.0	3.68	0.822	0.197	0.0758	0.652	0.71		0.0110	0.0400	0.949	0.0206	0.0596		0.0010				62.1	40 x 15	CC	
CRM	212X 4005 F	0.0529	2.55	1.784	21.53	1.503	0.152	0.094	0.170	0.792	1.29	0.0168	0.0193	0.016	0.30	0.0212							(69.6)	40 x 15	CC	
CRM	212X 4005 G **	0.05	2.5	1.45	21.5	1.0	0.15	0.1	0.15	0.9	1.4	0.002	0.003	0.01	0.3	0.01			** provisional values				[bal]	40 x 15	CC	
CRM	212X 4006 H	0.065	3.94	0.907	24.56	2.29	0.123		0.0327	1.507	3.99	0.041	0.0256		0.497	0.0310	0.0290	0.0708					61.96	40 x 15	CC	
CRM	212X 4007 B **	0.05	2.1	1.0	29.2	2.0		0.04	0.02	0.10	0.03	0.05	0.003	0.02	2.3	0.02	0.01	0.05	0.003		0.04	0.02	[bal]	40 x 15	CC	
		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	Mg	S	P	Nb	Zr	Pb	B	N	Ni			Size (mm)	Form		
		Ø x H																								
CRM	212X NA2 G	0.07	2.50	1.06	29.8	1.53						0.008	0.023	0.019			0.02						40 x 15	C		
	212X NA4 A	0.098	3.83	1.082	29.34	2.26	0.120	0.026	0.046	0.037	0.012	0.0014	0.004	0.0053	(0.51)		0.018			62.8	low stock		40 x 10	CC		
CRM	212X 04400 A	0.157	0.253	1.027	32.47	2.065	0.166	0.0307	0.0432	0.0193	0.030	0.053	(0.002)	0.0033				0.0019	0.0005	63.69			40 x 15	W		
CRM	212X 05500 A	0.135	0.167	0.634	29.91	1.162	0.073		(0.009)	0.632	3.00	0.0098	0.0010	0.0031		0.0343		0.0015	0.0010	64.3			38 x 15	W		
2.15 Ni/Co/Cr/Fe/Mo (Hastelloy Type)																						Size (mm)	Form			
		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	S	P	B	Nb	V	W	Mg	Zr	N	Ni	Ø x H				
CRM	215X HB1 P	0.0422	0.150	0.697	0.0718	5.78	1.090	33.04	0.252			0.0506	0.0056		0.203	0.504				0.0156	58.00			40 x 15	CC	
CRM	215X HB2 G	0.049	0.390	0.800	0.0526	4.20	0.689	31.84	0.584	0.13	0.19	0.0196	0.0084		0.248	0.480				0.0108	60.2			40 x 15	CC	
CRM	215X HB3 H	0.069	0.799	0.61	0.134	6.32	2.35	27.17	1.03	0.21	0.23	0.0156	0.0197		0.699	0.287				0.0271	(60.1)			40 x 15	CC	
CRM	215X HB4 G **	0.085	1.02	0.593	0.018	5.88	0.374	28.0	1.71	0.034		0.031	0.05		0.056	0.215	0.10			0.001	[bal]	** provisional	40 x 15	concast		
CRM	215X HB5 L	0.154	1.05	0.335	0.268	3.45	0.423	26.1	2.49	0.192	0.49	0.0113	0.038	0.003		0.136				0.006	65.3	Sold out		40 x 15	CC	
CRM	215X HC1 M **	0.026	0.50	1.26	0.020	4.02	15.6	19.7	2.48	0.268	0.008	0.002				0.153	3.59			0.005	[bal]	** provisional	40 x 15	concast		
CRM	215X HC2 K **	0.046	1.23	0.91		2.96	16.5	18.4	1.71	0.170	0.005	0.016				0.295	4.05			0.009	[bal]	** provisional	40 x 15	concast		
CRM	215X HC3 M **	0.089	0.95	0.67	0.10	4.84	17.92	17.3	0.98	0.148	0.110	0.013	0.021			0.40	4.62			0.006	[bal]	** provisional	40 x 15	concast		
CRM	215X HC4 M **	0.13	1.15	0.45	0.32	6.0	18.5	17	0.72	0.09	0.05	0.02	0.04			0.50	5.0			0.075	[bal]	** provisional	40 x 15	CC		
CRM	215X HC5 V **	0.20	1.38	0.10	0.47	8.22	20.1	16.0	0.048	0.195	0.72	0.039	0.056			0.608	6.15			0.008	[bal]	** provisional	40 x 15	concast		
CRM	215X HC6 A	0.005	(0.048)	0.099		5.00	15.67	16.14	1.16	0.003	0.066	0.0021				0.012	3.22			0.0034	58.45			40 x 13	HIP	
CRM	215X 10276 A	0.008	0.029	0.498	0.0423	5.79	15.56	15.96	0.182	0.0186	0.203	(0.001)	0.0027		0.031	0.196	3.59	0.0090	0.009	0.0099	57.81			38 x 15	W	
2.19 Various Nickel Alloys																						Size (mm)	Form			
		C	Si	Mn	Cu	Fe	Cr	Mo	Co	Ti	Al	S	P	Ta	V	W	Nb	Zr	B	Mg	Ni	N		Ø x H		
CRM	219X 20500 C	0.0212	1.29	0.300	0.0101	1.515	51.1	0.0103	0.0110			0.0137	0.0048			0.0086	0.0117				45.45	0.199			40 x 15	CC
CRM	219X 1867 D	0.092	0.187	0.134	0.308	0.244	7.78	6.00	9.80	1.355	6.05	0.0055	0.0054	4.05		0.066	0.052	0.273	0.0152		63.81	Sold out		40 x 15	CC	
CRM	219X 08825 A	0.015	0.232	0.499	1.87	31.82	21.94	3.01	0.0646	1.192	0.149	(0.001)	0.0189		0.038		(0.007)	0.0021	0.0028	(0.003)	39.12				40 x 15	W
CRM	219X 20004 A	0.224	0.916	14.07	0.319	9.48	13.63	0.104	(0.104)	0.52		0.0028	0.0147	0.077			1.53				59.1				40 x 15	CC
CRM	219X 86182 A	0.148	0.807	7.68	0.150	7.88	15.88	0.078	0.047	0.421		0.0034	0.0098	0.031			2.17				64.7				40 x 13	CC

3. Copper Base

Updated: 15th December 2016

Blocks / Discs

3.1 Brass - Cu/Zn Binaries		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	Cr	Co	P	Ag	S	B	Cd	Te	Cu	Size (mm) Ø x H	Form
CRM	31X B1 Q **	0.03	0.015	45	0.02	0.02	0.002	0.01	0.007	0.01	0.02	0.007	0.01	0.002	0.04			0.001	0.002		[bal]	40 x 15	CC
CRM	31X B2 M	0.0113	0.0103	39.50	0.0146	0.0121	(0.001)	0.0047	0.0049	0.0147	0.0105	0.0111		0.0032	0.0121			0.0008	0.0029		60.42	40 x 15	CC
CRM	31X B3 L	0.0149	0.0194	34.95	0.0541	0.0431	0.287	0.0126	0.0144	0.0072	0.0098	0.0159	0.0022	0.0212				0.0021	0.0108		64.57	40 x 15	CC
CRM	31X B4 M	0.053	0.045	28.97	0.111	0.0649	0.0011	(0.002)	0.0516	0.0011	0.0103	0.0118	0.0038	0.0263	0.0302		0.0114		0.0236		70.60	40 x 15	CC
CRM	31X B5 K	0.045	0.021	23.60	0.056	0.0085	(0.001)	(0.001)	0.0054	0.0006	0.0061	0.0057	0.0002	0.0062				0.0002	0.00050		76.22	40 x 15	CC
CRM	31X B6 K	0.0029	0.0122	19.93	0.0097	0.0066	0.0010	0.015	0.0009	0.0039	0.0010	0.0011	<0.0005	0.0063				0.0023	0.0037		79.90	40 x 15	CC
CRM	31X B7 L	0.089	0.0416	15.34	0.099	0.0351	0.0435	0.018	0.0054	0.0088	0.0607	0.0196		0.0044				0.0013	0.0064	(0.002)	84.22	40 x 15	CC
CRM	31X B8 J	0.0311	0.082	10.23	0.132	0.0421	(0.001)	(0.002)	0.0074	0.0006	0.030	0.0254	(0.001)	0.0072	0.0026		0.045		0.0155		89.37	40 x 15	CC
CRM	31X B9 M **	0.01	0.10	5.0	0.04	0.04	0.01		0.01	0.001	0.005	0.01			0.005	0.01		0.0005		0.02	[bal]	40 x 15	CC
** provisional values																							
3.1.1 Alloyed Brass		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	B	Co	Cr	Cd	Ag	Te	Cu	Size (mm) Ø x H	Form
CRM	31X B10 M	0.0310	0.0274	36.05	(1.39)	1.475	0.358	0.0389	0.0087	0.205	0.0215	0.0124				0.0390	0.0192				60.18	40 x 15	CC
CRM	31X B11 H	0.0117	0.0134	36.65	0.802	1.033	0.0262	0.0063	0.0061	0.653	0.0054	0.0057									60.72	40 x 15	CC
CRM	31X B12 G	0.0229	0.0244	36.67	0.430	0.491	0.081	0.0207	0.0181	1.720	0.0198	0.0194									60.51	40 x 15	CC
CRM	31X B13 G	0.0127	0.0188	36.67	0.182	0.212	0.0148	0.032	0.0120	2.84	0.0116	0.0056									60.03	40 x 15	CC
CRM	31X B14 G	0.486	0.0104	36.52	0.0183	0.0190	4.02	0.051	0.0091	0.0117	0.0103	0.0139				0.0109			0.0130		58.85	40 x 15	CC
CRM	31X B15 H	0.944	0.0073	36.80	0.0176	0.0102	2.98	0.109	0.0048	0.0122	0.0074	0.0111				0.0046			0.0071		59.07	40 x 15	CC
CRM	31X B16 H	2.13	0.0295	37.18	0.0162	0.0076	1.98	0.197	0.0056	0.0029	0.0042	0.0126				0.0023			0.0052		58.37	40 x 15	CC
CRM	31X B17 F	0.010	(0.05)	(33.9)	(0.02)	(0.01)	6.05	(0.007)	(0.015)	<0.001	<0.001	<0.001									60.0	40 x 15	CC
CRM	31X B18 K	0.0117	1.018	39.41	0.0237	0.0233	0.0193	0.019	0.0215	0.0207	0.0196	0.0205	0.0195			0.0015	(0.013)	0.0254	0.0143	0.017	59.37	40 x 15	CC
CRM	31X B19 R	0.0324	2.49	37.78	0.0295	0.0218	0.087	0.0392	0.0129	0.0109	0.0208	0.0105	0.0630	0.0019				0.0048		(0.002)	59.33	40 x 15	CC
CRM	31X B20 N	0.0244	4.43	37.03	0.024	0.021	0.0025	(0.005)	0.0028	0.0005	0.0025	0.0039	0.0230	(0.004)							58.53	40 x 15	CC
CRM	31X B21 E	0.101	0.113	29.55	0.126	0.117	0.0244	0.059	0.0908	0.0603	0.104	0.105	0.1269	(0.002)							69.32	40 x 15	CC
CRM	31X B22 F	0.160	0.152	15.92	0.158	0.154	0.0402	0.047	0.165		0.17	0.161	0.207	0.030	0.0043	0.139		0.0117			82.47	40 x 15	CC
CRM	31X B23 D	0.060	0.046	9.97	0.060	0.047	0.0048	0.0046	0.0482	0.0053	0.0463	0.0448	0.030	0.053		0.0472		0.0010			89.57	40 x 15	CC
CRM	31X B24 D	1.93	0.050	1.99	0.0342	0.134	(0.002)		0.0116	0.0030	0.0126	0.118	0.0065	0.050				0.0008			95.65	40 x 15	CC
CRM	31X B25 B	0.613	0.298	40.83	0.056	0.236	0.470	0.254	0.0284	0.127	0.0594	0.0843	0.093		(0.0045)						56.95	40 x 15	CC
CRM	31X B26 F	1.476	0.930	30.30	0.650	1.397	1.005	0.252	0.126	0.408	0.106	0.098	0.0593			0.1197		0.0147	0.053		62.93	40 x 15	CC
CRM	31X B27 B	0.985	0.492	17.65	0.111	0.0315	0.0015	0.0044	0.048	0.0059	0.0320	0.0243	0.0150	0.0080	(0.0005)						80.65	40 x 15	CC
CRM	31X B29 A	0.0328	0.146	24.75	0.144	4.11	0.219			0.0625			3.33				0.062	0.0144			67.08	40 x 15	CC
3.1.2 Brass - Trace Elements		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	Cr	Co	Cd	B	Te	Ag	Cu	Size (mm) Ø x H	Form		
CRM	31X TB1 K	0.134	0.207	35.17	0.171	0.0619	0.493	0.080	0.111	0.280	0.0414	0.105		0.0500	0.0118	0.0010		0.0455	63.08		40 x 15	CC	
CRM	31X TB2 H	0.106	0.0982	36.47	0.087	0.111	0.0876	0.034	0.111	0.204	0.0404	0.0533	0.0112	0.0864	0.0014	0.0014			62.54	sold out	40 x 15	CC	
CRM	31X TB3 K	0.089	0.169	37.92	0.0282	0.0637	0.0045	0.016	0.0454	0.0244	0.0030	0.0222			0.0043	(0.0005)			61.58		40 x 15	CC	
CRM	31X TB4 G	0.0197	0.0246	33.64	0.0340	0.0133	0.0041	0.0203	0.0106	0.0013	0.0058	0.0095		0.0067	0.0032	(0.0004)	0.0035		66.07		40 x 15	CC	
CRM	31X TB5 A	0.107	0.576	40.63	0.178	0.079	0.0458	0.122	0.349	0.445	0.314	0.174	(0.20)	0.0229	0.501			0.213	55.84		40 x 15	CC	

3. Copper Base

Updated: 15th December 2016

Blocks / Discs

3.1.3 Naval Brass		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	Co	B	C	Ag	Cu	Size (mm) Ø x H	Form	
CRM	31X NB1 H	0.535	0.504	29.73	0.037	0.520	(0.0004)	0.004	0.161	0.051	0.0065	0.0057	0.0223	0.0024	(0.0006)				68.35	40 x 15	CC	
CRM	31X NB2 H	1.009	0.239	35.47	0.112	0.0578	0.168	0.107	0.0970	0.151	0.100	0.099	0.0139	0.0019					62.21	40 x 15	CC	
CRM	31X NB3 H	1.67	0.197	24.64	0.113	0.0299	0.094	0.145	0.074	0.0166	0.093	0.265	0.150	(0.006)		0.0026	(0.0020)		72.45	40 x 15	CC	
CRM	31X NB4 J	2.01	0.067	32.57	0.235	0.230	0.178	0.203	0.0062	0.0053	0.104	0.450	0.230	(0.0032)		0.0009			63.71	40 x 15	CC	
CRM	31X CZ112 A	1.130	0.458	37.07	0.0488	0.0150	(0.001)	(0.003)	0.0052	0.0010		0.0043	0.0136					0.0043	61.24	41 x 15	W	
3.1.5 High Tensile Brass		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Sb	P	S	C	Cu	Size (mm) Ø x H		Form				
CRM	31X HT31 A	0.0149	0.020	18.19	2.90	0.196	6.70	0.041	0.0006	5.27	(0.0011)	0.00032	(0.0003)	0.006	66.67	50 x 18		W				
CRM	31X HT37 A	0.0116	0.623	34.69	0.0344	0.0105	0.0004	1.38	0.0011	2.88	0.0007	0.003	<0.0005	0.003	60.33	40 x 18		W				
CRM	31X HT38 A	0.039	0.051	36.66	0.0530	0.0242	0.960	0.869	0.0008	2.60	(0.0006)	0.0024	(0.001)	0.003	58.77	50 x 18		W				
3.1.6 Bismuth Brass		Bi	Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Co	Sb	P	S	Se	Cd	B	Cu	Size (mm) Ø x H	Form	
CRM	31X BIB1 D	1.87	0.463	0.157	37.20	0.053	0.255	0.124	0.169	0.0303	0.0273		0.0106	0.0451	(0.001)	0.0031	0.0100		59.57	40 x 15	CC	
CRM	31X BIB2 D	0.998	1.177	0.151	33.43	0.228	0.467	0.403	0.148	0.0202		0.055	0.0780	0.0304	0.0011	0.0052	0.0093		62.84	40 x 15	CC	
CRM	31X BIB3 C	4.04	0.198	0.181	31.83	0.0510	0.127	0.154	0.0516	0.0476		0.0032	0.0321	0.0626	0.0018	0.0047	0.0014		63.18	40 x 15	CC	
CRM	31X BIB4 C **	0.85	0.85	0.09	34.5	0.12	0.21	0.40	0.2			0.03	0.05	0.037	0.005	0.015	0.003	0.0015	[bal]	** provisional values	40 x 15	CC
3.1.7 Lead Brass		Pb	Sn	Zn	Fe	Ni	Mn	Al	Si	As	Bi	Sb	P	S	Co	Ag	Se	Cd	B	Cu	Size (mm) Ø x H	Form
CRM	31X 7835.1 T	2.72	0.349	33.49	0.157	0.1224		0.0083	(0.008)	0.0059	0.0075	(0.008)	0.0112		0.0021	0.0056		0.0020		63.09	40 x 15	CC
CRM	31X 7835.2 K	2.07	0.152	32.94	0.0309	0.0462		0.060	0.0193	0.0280	0.0099	0.0358	0.0226		0.0290	0.0102		0.0020	0.0023	64.49	40 x 15	CC
CRM	31X 7835.3 J	1.501	0.1032	35.57	0.246	0.294		0.142	(0.009)	0.1023	0.0282	0.0916	0.0307		0.0046	0.0159		0.0031		61.81	40 x 15	CC
CRM	31X 7835.4 J	1.049	0.070	30.36	0.0350	0.477		0.525		0.142	0.0169	0.068	0.121		0.0027			0.0088	0.0021	67.13	40 x 15	CC
CRM	31X 7835.5 A	1.64	0.116	6.23	0.126	0.249		0.078		0.104		0.114	0.018							91.25	40 x 15	CC
CRM	31X 7835.6 C	1.422	0.548	36.60	0.0211	0.021		0.573	0.0214	0.0152	0.0043		0.0253	(0.0016)	0.0048	0.0044	0.0010	0.0017	0.0045	60.70	40 x 15	CC
CRM	31X 7835.7 A	2.29	0.137	7.50	0.030	0.943		0.0084	0.039		0.048	0.0327	0.080	0.0075	0.0120			0.0047		88.87	40 x 15	CC
CRM	31X 7835.8 B	3.22	0.451	21.55	0.0446	0.157	0.0102	0.219		0.151	0.101	0.110	0.154		0.313	0.549		0.0944		72.7	40 x 15	CC
CRM	31X 7835.9 A	1.024	1.48	14.34	0.408	0.100	0.0009	0.092		0.107	0.81	0.445	0.0390	0.0161	0.0813	2.12	0.34	0.0673		78.48	40 x 15	CC
CRM	31X 7835.10 A	1.419	0.234	34.36	0.408	0.159	0.0318	0.648	0.010	0.0635	0.0202	0.0216	0.0417		0.0203					62.55	40 x 15	CC
CRM	31X 7835.11 A	1.695	0.1522	30.98	0.192	0.1007	0.0101	0.908	0.010	0.143	0.011	0.0122	0.024		0.0065					65.75	40 x 15	CC
CRM	31X CZ114 A	1.219	0.511	38.25	0.740	0.0183	1.475	0.714	(0.006)		0.0107	(0.003)	0.0018							57.10	38 x 15	W
CRM	31X CZ115 A	1.169	0.729	39.20	0.601	0.0143	1.095	0.0007	(<0.005)	0.0008		0.0020	0.0091			0.0041				57.19	41 x 15	W
CRM	31X CZ121 A	3.01	0.1940	38.57	0.167	0.1028	0.0052	0.0034	(0.003)	0.0299	0.0046	0.0050	0.0028			0.0060				57.84	41 x 15	W
See also Section 3.1.1 products 31X B18 - B20																						

See also Section 3.1.1 products 31X B18 - B20

3. Copper Base

Updated: 12th December 2016

Blocks / Discs

3.1.8 Manganese Brass		Mn	Sn	Pb	Zn	Fe	Ni	Al	Si	As	Bi	Sb	P	S	Co	Ag	Cr	C	Cu	Size (mm) Form Ø x H		
CRM	31X MNB1 C	0.188	0.105	1.44	29.37	0.268	0.053	0.599	0.128	----	----	----	----	----	----	----	----	----	67.77	sold out	40 x 15	GG
CRM	31X MNB2 D	2.05	0.289	0.983	31.30	0.548	0.118	0.272	0.579	0.0201	----	0.0177	0.0246	----	0.0086	0.041	----	----	63.75		40 x 15	CC
CRM	31X MNB3 E	3.08	0.459	0.504	25.97	1.15	0.348	0.584	1.53	0.0179	----	0.0056	0.0259	----	0.0556	0.0162	----	----	66.18		40 x 15	CC
CRM	31X MNB4 F	2.97	0.547	0.221	25.59	1.728	0.347	3.91	0.103	0.0125	----	0.0189	0.0274	----	0.0312	0.0131	----	----	64.62		40 x 15	CC
CRM	31X MNB5 Q	0.137	1.60	0.243	37.12	0.013	0.996	2.96	0.44	0.0100	----	0.0118	(0.008)	----	0.0155	0.0063	0.19	----	56.18		40 x 15	CC
CRM	31X MNB5 R	0.175	1.228	0.157	37.11	0.898	1.32	3.24	0.528	0.0021	----	(0.006)	0.0399	----	0.066	0.0195	0.0116	----	55.14		40 x 15	CC
CRM	31X MNB6 C	0.871	0.0310	0.016	28.53	0.0697	0.261	0.0148	0.0196	0.0107	----	0.0128	0.0226	----	0.0107	0.0509	----	----	70.01		40 x 15	CC
CRM	31X MNB11 A	11.99	0.161	1.610	22.85	0.337	4.46	1.19	0.071	0.0010	0.0021	0.0051	0.0186	(0.0007)	0.0046	----	0.0046	(0.009)	57.36		40 x 15	CC
CRM	31X MNB12 B	18.37	0.194	1.96	21.76	0.313	0.497	0.70	0.0487	0.0077	0.0204	0.0072	0.0521	(0.0006)	0.0040	----	0.0013	0.0125	56.03	40 x 15	CC	
3.1.9 Silicon Brass		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Sb	P	Co	Cd	Ag	B	Cu	Size (mm) Form Ø x H				
CRM	31X WSB6 E	0.071	0.225	0.450	0.088	0.1114	0.0311	3.60	0.0048	0.900	0.0022	0.0206	0.0079	0.0004	----	----	94.47		40 x 15	CC		
CRM	31X WSB6 F	0.015	0.03	0.05	0.15	0.05	0.002	3.1	0.01	0.90	0.04	0.02	0.01	0.004	0.015	0.005	[bal]		40 x 15	CC		
3.2.1 Phosphor-Bronze		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	Co	Mg	C	Ag	Cu	Size (mm) Form Ø x H		
CRM	32X PB10 P	12.37	0.0182	0.256	0.0043	0.0130	(0.002)	(0.001)	0.0126	<0.001	0.034	0.0134	0.0030	0.0144	0.0062	----	----	----	87.14	** provis values	40 x 15	CC
CRM	32X PB11 G	3.306	0.995	1.71	0.399	0.898	0.081	0.123	0.198	0.132	0.0310	0.584	0.946	0.0148	0.090	0.0091	----	----	90.44		40 x 15	CC
CRM	32X PB12 F	5.03	0.0436	0.130	0.053	0.205	(0.001)	(0.002)	0.0512	0.0014	0.0647	0.1822	0.076	0.0108	0.0150	----	0.0155	94.16	40 x 15		CC	
CRM	32X PB13 E	6.55	0.109	0.301	0.0549	0.0953	0.0251	0.053	0.0391	0.0440	0.0224	0.092	0.089	----	0.0088	----	0.0205	92.48	40 x 15		CC	
CRM	32X PB14 E **	9.6	0.035	0.10	0.02	0.12	0.02	0.002	0.025	0.015	0.15	0.04	0.13	0.07	0.005	----	0.015	[bal]	40 x 15		CC	
CRM	32X PB15 A	2.21	0.174	0.76	0.116	0.212	0.045	0.043	0.123	0.0125	----	0.026	0.0873	----	0.0509	0.0275	----	96.07	40 x 15		CC	
CRM	32X PB20 A	4.55	0.0045	0.007	0.0013	0.0090	<0.001	0.0046	0.0011	(0.007)	----	0.0012	0.196	0.0030	----	----	(0.0014)	95.22	38 x 17		W	
CRM	32X PB23 A	7.56	0.0042	0.0020	(0.0005)	0.0033	(0.0004)	0.0016	0.0011	(0.0006)	----	0.0025	0.319	0.0015	----	----	0.004	92.04	49 x 17		W	
CRM	32X 51000 A	4.86	0.0031	0.0112	0.0025	0.0083	(0.001)	----	----	----	----	----	0.300	0.0021	----	----	0.0024	94.84	38 x 15	W		
CRM	32X 52100 A	7.72	0.0031	0.0028	(0.001)	0.0110	0.0008	----	0.0009	----	0.0019	----	0.147	0.0007	----	----	0.0011	92.08	38 x 15	W		
3.2.2 Lead Bronze		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	Co	Cd	Ag	Cu	Size (mm) Form Ø x H			
CRM	32X LB10 F	8.26	12.46	0.426	0.0045	0.695	0.0188	0.008	0.146	----	0.0563	0.557	0.0063	0.010	0.0395	----	0.0459	77.23		40 x 15	CC	
CRM	32X LB11 D	10.87	10.17	0.124	0.0025	0.565	0.0022	(0.002)	0.0315	(0.0003)	0.0338	0.111	0.007	0.053	0.0202	----	0.118	77.97		40 x 15	CC	
CRM	32X LB12 D	9.52	9.06	0.584	0.0223	0.433	(0.001)	<0.001	0.0897	----	0.0231	0.442	0.383	0.094	0.0751	----	----	79.27		40 x 15	CC	
CRM	32X LB13 C	5.80	7.59	0.520	0.0160	0.828	0.0011	(0.0035)	0.131	0.0005	0.0721	0.0186	0.0161	0.115	0.0293	----	0.0063	84.87		40 x 15	CC	
CRM	32X LB14 G	5.63	15.42	0.586	0.0094	0.254	0.0006	(0.001)	0.0500	0.0005	0.720	0.0750	0.0589	0.0176	0.089	----	0.120	77.02		40 x 15	CC	

3. Copper Base

Updated: 15th December 2016

Blocks / Discs

3.2.2		Lead Bronze continued																		Size (mm)		Form	
		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	Co	Cd	Ag	Cu	Ø x H				
CRM	32X LB15 E	4.51	21.42	0.064	0.0012	0.123	(0.001)	0.0008	0.0273		(0.13)	0.127	0.0035	0.032	0.0051		0.0217	73.60	40 x 15	CC			
CRM	32X LB16 A	5.55	18.78	0.458	0.0040	0.793	(0.001)				0.0119	(0.001)	(0.002)	0.0012			0.0016	74.42	32 x 17	W			
CRM	32X LB17 A	5.97	9.83	0.634	0.488	0.465	0.388		1.51	0.296	0.220	4.10	0.051		0.0083	0.151	0.911	74.83	40 x 15	CC			
CRM	32X 93700 A	9.95	8.38	0.78	0.0011	0.307						0.0051	(0.0015)	0.0017	0.0004			80.43	42 x 15	concast			
3.2.3		Aluminium Bronze																		Size (mm)		Form	
		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	P	Cr	Co	Mg	Nb	Sb	Ag	Bi	Se	Be	Cu		Ø x H
CRM	32X ALB1 P	0.0314	0.207	0.0228	3.11	5.74	8.83	0.106	0.0083	0.057	0.0145	0.0052		0.0092				sold out			81.85	40 x 15	CC
CRM	32X ALB2 L	0.0806	0.0685	0.671	4.628	4.515	10.48	0.198	0.0062	0.401	0.031	0.052	0.198	0.0088	0.070		0.018				78.50	40 x 15	CC
CRM	32X ALB3 S	0.1209	0.118	1.314	3.718	3.51	10.43	0.155	0.0213	0.243	0.0345	0.0392	0.0760	0.0659	0.018		0.0272				80.01	40 x 15	CC
CRM	32X ALB4 H	0.085	0.120	0.264	3.55	7.03	7.87	0.252	0.0130	1.028	0.036	0.022		0.153							79.61	40 x 15	CC
CRM	32X ALB5 K	0.0293	0.0512	0.80	2.04	3.92	7.21	0.107		1.417	(0.05)	0.192	0.0606	0.179	0.181		0.0061				83.71	40 x 15	CC
CRM	32X ALB6 K	0.120	0.0749	0.126	2.71	5.42	9.69	0.073	0.0116	0.787	(0.006)		0.139	0.0104			0.0082				80.77	40 x 15	CC
CRM	32X ALB7 C	0.30	0.029	0.527	4.82	4.96	4.01	0.399	0.056	0.383	0.057	0.061		0.0039							84.40	40 x 15	CC
CRM	32X ALB8 E	0.312	0.071	0.352	5.54	6.68	6.38	0.603	0.145	1.562	0.171	0.36	0.554	0.015		0.024	0.0099	low stock			77.17	40 x 15	CC
CRM	32X ALB9 C	0.0601	0.267	0.142	3.12	0.628	13.52	0.235	0.0163	0.159	0.096	0.0206	0.0027	0.090			0.0417				81.64	40 x 15	CC
CRM	32X ALB10 B	0.201	0.152	0.961	3.63	7.21	12.11	0.158	0.0194	1.626	0.069	0.0152	0.0984	0.0122			0.0144				73.64	40 x 15	CC
CRM	32X ALB11 A	0.0289	0.118	0.576	3.81	4.33	8.80	0.069		1.13	0.045		0.089	0.075		0.093		0.120	0.006	0.0194	80.58	40 x 15	CC
CRM	32X ALB11 B	0.0062	0.0316	0.508	3.99	4.44	8.85	0.015		1.290	0.0249		0.0180	0.072		0.203		0.082	0.007	0.064	80.38	40 x 15	CC
		Sn	Pb	Zn	Fe	Ni	Al	Si	Mn	P	Cr	Co	Mg	Ag	C	Cu	Size (mm)		Form				
		Ø x H																					
CRM	32X ALB12 A	0.310	0.0018	0.0625	1.094	6.33	8.29	0.0202	0.958	0.0101		0.0056	0.0013	0.044		82.90	41 x 15		W				
CRM	32X ALB13 A	0.0072	(0.001)	0.0194	1.171	1.381	7.09	0.086	5.39	0.009		0.0011				84.96	35 x 15		W				
CRM	32X 61400 A	0.301	(0.001)	0.060	2.74	0.0242	6.81	0.0124	0.082	0.0008			0.0050	0.0010		89.99	42 x 15		W				
CRM	32X CA1 A	0.0180	0.007	0.162	4.63	4.94	9.79	0.090	0.296	0.003	0.0049		0.0003	0.0012	(0.007)	80.03	42 x 18		W				
CRM	32X CA7 A	0.0172	(0.004)	0.006	2.09	0.234	9.37	0.017	0.151		0.0028		0.0004	0.0009	0.0028	88.06	42 x 18		W				
CRM	32X CA12 A	0.0157	(0.0017)	0.0405	0.657	0.088	6.14	2.57	0.0290				0.0005	0.0010	(0.002)	90.48	42 x 18		W				
CRM	32X CA23 A	0.0164	(0.0026)	0.031	3.63	4.71	9.19	0.026	1.298	0.0011	0.0018		0.0003	0.0008	(0.0050)	81.05	50 x 18		W				
CRM	32X CA31 A	0.0037	(0.0024)	0.041	4.06	4.28	8.95	0.036	0.336	(0.003)	0.0026		0.0008	0.0008	0.006	82.24	42 x 18		W				
3.2.4		Bismuth Bronze (Sebiloy Type)																		Size (mm)		Form	
		Sn	Pb	Zn	Fe	Ni	As	Bi	Sb	P	S	Co	Al	Se	In	Ag	Cd	Cu	Ø x H				
CRM	32X SEB1 D	4.26	0.197	7.81	0.071	0.102	0.0402	4.25	0.305	0.0021	0.0052	0.0478		0.812			0.0033	81.88	40 x 15	CC			
CRM	32X SEB2 D	6.96	0.104	1.40	0.074	0.0449	0.0160	4.57	0.0222	0.036	0.030	0.0133		0.044	0.074	0.0443	0.0255	86.56	40 x 15	CC			
CRM	32X SEB3 E	2.96	0.296	0.887	0.0113	1.214	0.0325	6.47	0.108	0.0139	0.0180	0.0491		1.30			0.0095	86.47	40 x 15	CC			
CRM	32X SEB4 E	10.05	0.0357	7.02	0.093	0.0199	0.0065	2.48	0.0343	0.0043		0.308	0.0007	0.119			0.0017	79.82	40 x 15	CC			
CRM	32X SEB5 C	5.18	0.268	5.30	0.0430	0.317		1.056	0.0334	0.072	0.050	0.0156	(0.001)	0.471			0.0051	87.21	40 x 15	CC			
CRM	32X SEB6 C	7.14	0.0463	4.55	0.151	0.860	0.083	0.615	0.235	0.0118		0.231		0.322			0.0036	85.66	40 x 15	CC			
CRM	32X SEB7 A	3.20	0.343	4.42	0.074	1.165	0.038	3.58	0.262	0.0206	0.067	0.119		1.19			0.0074	85.46	40 x 15	CC			

3. Copper Base

Updated: 12th December 2016

Blocks / Discs

3.2.9 Bronze		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Cr	Co	Bi	Sb	Cd	Au	Ag	P	S	Cu	Size (mm) Ø x H	Form	
CRM	32X SN1 F	11.65	5.66	0.259	0.0014	1.931	(0.001)	(0.001)	0.0111	<0.001		0.0136		0.0274				0.0022	0.0126	80.34	40 x 15	CC	
CRM	32X SN2 J	14.22	2.06	0.940	0.041	1.025	(0.002)	0.009	0.0119	0.0246		0.0343	0.119	0.106			0.0107	0.220	0.0106	81.17	40 x 15	CC	
CRM	32X SN3 G	16.14	0.159	0.150	0.14	0.464	(0.14)	0.0247	0.0323	0.067		0.0460		0.362				0.646	0.035	81.7	40 x 15	CC	
CRM	32X SN4 B **	19.0	0.85	0.50	0.08	0.60	0.05	0.02	0.06	0.015		0.10	0.015	0.15			0.50	1.2	0.015	[bal]	** provis values	40 x 15	CC
CRM	32X SN5 B	15.90	0.860	0.604	1.009	0.667	0.215		0.0557	0.528	0.0238	0.129	0.124	0.702	0.130	0.0102	0.095			78.97	40 x 15	CC	
CRM	32X SN6 A	7.34	1.559	1.17	0.099	0.203	0.0343		0.764	0.0024	0.0074	0.655	0.158	0.323	0.0903	0.0073	1.159		0.018	86.39	sold out	40 x 15	CC
CRM	32X SN7 A	12.60	2.60	1.96	(0.06)	0.175	0.052		1.071	0.0010		0.443	0.052	0.263	0.0385	0.0005	0.305	0.056		80.30	40 x 15	CC	
CRM	32X CSN1 A	0.306		0.0039	0.0020													0.0007			20 x 22	W	
3.3 Gun Metal		Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	Se	Cr	Co	Ag	Cd	Cu	Size (mm) Ø x H	Form	
CRM	33X GM4 AC	2.57	5.21	5.78	0.024	1.510	(0.001)	0.0011	0.0205	0.0007	0.0132	0.0101	0.0022	0.107			0.0195	0.0108		84.79	40 x 15	CC	
CRM	33X GM5 N	5.18	4.80	4.16	0.194	0.802	0.070	0.070	0.0408		0.0510	0.0654	0.0098	0.063			0.0207	0.049	0.0111	84.56	40 x 15	CC	
CRM	33X GM6 K	6.58	3.94	1.409	0.0256	0.890	0.0012	(0.001)	0.158	0.0022	0.0359	0.259	0.0041	0.090			0.0100	0.0148		86.51	40 x 15	CC	
CRM	33X GM7 J	9.61	1.119	2.72	0.050	0.511	0.0110	(0.003)	0.103	0.0088	0.119	0.1092	0.082	0.064			0.095	0.050		85.40	40 x 15	CC	
CRM	33X GM8 G	4.03	6.21	5.71	0.033	0.1491			0.0114		0.062	0.0237	0.0062	0.0083			0.0222	0.1018		83.64	40 x 15	CC	
CRM	33X GM20 A	4.07	0.106	3.87	0.570	0.999	(0.001)		0.196	0.219	0.031	2.004	0.063			0.015	0.0382	0.141	0.0229	87.58	40 x 15	CC	
CRM	33X GM21 A	4.55	6.99	5.05	0.751	0.129	0.255	0.0156	0.464		0.452	1.049	0.050	0.080	0.194			0.694	0.255	78.90	40 x 15	CC	
CRM	33X GM24 A	3.85	3.35	3.67	0.0083	0.0087		0.0028	0.0010	<0.0005	0.0009	0.0012	0.190	0.003		(0.0013)		0.0046		88.88	44 x 17	W	
CRM	33X GM29 A	6.12	0.050	4.23	0.0102	0.0289		0.0027	0.0017	(0.0005)	0.0019	0.0015	0.138	0.0024		(0.0004)		0.0026		89.36	33 x 19	W	
CRM	33X RB1 A	2.137	5.02	7.95	0.928	0.0539	0.0048	0.063	0.0030	0.0167	0.0029	0.432	0.020	0.0044		0.0013		0.0174		83.24	40 x 15	CC	
CRM	33X RB2 B **	4.6	3.0	9.0	0.50	0.33	0.01		0.04	0.005	0.09	0.05	0.045	0.07			0.035	0.09		[bal]	** provis values	40 x 15	CC
CRM	33X 54400 A	3.97	4.69	3.87	0.072	0.244	0.0009		0.0156			0.0362	0.243	0.0251			0.0013	0.0124		86.79	38 x 15	W	
3.4 Nickel Silver		Sn	Pb	Zn	Fe	Ni	Al	Si	Mn	P	S	Co	Cr	Ag	Mg	C	Cu			Size (mm) Ø x H	Form		
CRM	34X NS1 F	0.0110	0.0141	33.41	0.064	7.81	(0.003)	(0.002)	0.0009	0.0140	(0.0004)	0.052	0.0003	0.069	0.0020	(0.0018)	58.63	sold out		40 x 15	CC		
CRM	34X NS2 F	0.019	0.063	25.34	0.085	13.39		(0.003)	0.0013	0.0091	(0.020)	0.0118	(0.001)	0.0026	<0.0005		61.09	sold out		40 x 15	CC		
CRM	34X NS3 F	0.056	0.178	19.96	0.285	14.96	<0.001	(0.002)	0.0377	0.0295	0.0028	0.0922		0.100	<0.001		64.16			40 x 15	CC		
CRM	34X NS4 F	0.0301	0.071	17.09	0.449	16.61	0.0454	0.102	0.304	0.0570	0.0110	0.152		0.0324	0.0009		64.97			40 x 15	CC		
CRM	34X NS5 G	0.142	0.896	23.87	0.247	16.55	0.085	0.122	0.1103	0.104		0.211		0.0096			57.53			40 x 15	CC		
CRM	34X 79830 A	0.1158	2.033	41.80	0.079	9.76	0.0012		0.311	0.0047	(0.001)	(0.001)		0.0028		(0.005)	45.88			38 x 15	W		

3. Copper Base

Updated: 15th December 2016

Blocks / Discs

3.6.1 Cupro Nickel		Sn	Pb	Zn	Fe	Ni	Al	Si	Mn	Bi	P	S	Co	Cr	Mg	B	C	Ti	Nb	Zr	Be	Cu	Size (mm)	Form	
		Ø x H																							
CRM	36X CN1 P	0.227	0.035	0.351	1.856	9.27	0.055	0.104	1.77		0.0574	0.0071	0.114	0.156	0.0321		0.0106		0.0236			(85.9)	40 x 15	CC	
CRM	36X CN2 J	0.061	0.048	0.0358	1.70	15.47	0.005	0.044	1.26	0.0045	0.015	0.035	0.264	0.240	0.0006		0.004	0.0102	(0.032)			80.78	40 x 15	CC	
CRM	36X CN3 M	0.190	0.223	1.014	0.996	19.55		0.349	0.726		0.049	0.0153	0.0701	0.0259	0.075	(0.002)	0.020		0.030		0.0042	76.60	40 x 15	CC	
CRM	36X CN4 L	0.0093	0.0193	0.164	0.548	25.58	0.040	0.448	0.529	0.0096	0.0140	0.0075	0.0305	0.0273	0.008		(0.005)		0.461			72.09	40 x 15	CC	
CRM	36X CN5 P	0.0090	0.0120	0.209	0.347	31.03		0.689	0.217		0.034	0.088	0.0238	0.141	0.0106	0.0053	(0.008)	0.0203	0.430		0.0035	66.67	40 x 15	CC	
CRM	36X CN6 J		0.0165	0.147	0.481	32.51	0.079	0.150	0.567	0.0260	0.0187	0.0097	0.0433	2.17			0.0198	0.0510	0.271	0.0228		63.41	40 x 15	CC	
CRM	36X CN7 F	0.039	0.028	0.203	1.021	29.95		0.304	0.659	(0.014)	(0.021)	0.0151	0.108	1.51	0.0041	(0.004)	0.0106	(0.037)	0.58	(0.003)		65.58	40 x 15	CC	
CRM	36X CN8 J	0.0502	0.037	0.107	1.65	28.94	(0.030)	0.309	0.951	0.0518	0.019	0.0119	0.121	1.38		0.005	0.013	(0.038)	0.585			65.78	40 x 15	CC	
CRM	36X CN9 K	0.0351	0.070		1.262	26.40	0.051	0.406	1.005	0.0197	(0.021)	0.0105	0.0785	2.02			0.005	0.111	1.37	0.102		66.94	40 x 15	CC	
CRM	36X CN10 B	0.0164	0.013	0.058	4.76	28.35	1.346	0.906	0.552		(0.009)	0.030	0.122	1.498		(0.012)	0.0107	0.227	0.450	0.080		61.63	40 x 15	CC	
CRM	36X CN11 A	(0.002)	(0.003)	(0.006)	0.992	14.96	1.457	0.083	4.34		(0.002)	0.0012	0.0049	0.380	0.0241		(0.001)		0.124			77.56	40 x 15	W	
CRM	36X CN12 A	(0.001)	0.0037	0.157	0.105	13.05	2.41	0.040	0.402		0.0011		0.0056		0.072	0.0055	0.0101		0.0010			83.79	40 x 15	W	
CRM	36X CN13 A	(0.001)	(0.001)	0.0017	0.870	14.52	2.65	0.012	0.442		0.0011	(0.002)	(0.001)		0.0039	(0.002)	(0.003)					81.46	38 x 15	W	
CRM	36X 70600 A	0.0090	0.0086	0.115	1.619	10.65	(0.001)		0.759		0.0062	0.0136	0.0087				(0.002)					86.70	40 x 15	W	
CRM	36X 71500 A	0.0113	0.0114	0.150	0.888	31.24	(0.001)		0.850		0.0074	0.0454	0.0163			0.0049	0.0240					66.74	40 x 15	W	
																							Size (mm)	Form	
		Sn	Pb	Zn	Fe	Ni	Al	Mn	P	Co	Cr	As	Ag	Cd	C	Cu							Ø x H		
CRM	36X CN21 A	0.038	0.051	0.0203	0.0316	5.50	1.95	0.0391	0.053	0.0079	0.0050	0.0067	0.0064	0.0021		92.17							40 x 15	CC	
CRM	36X CN22 A	0.0371	0.0260	0.0175	0.088	1.806	6.09	(0.016)	0.0178	0.0231	0.0144	0.0208	0.0196	0.0083		91.80							40 x 15	CC	
CRM	36X CN23 A	0.102	0.115	14.88	0.140	14.38	0.007	0.0095	0.0299	0.0509	0.0021	0.047	0.042	0.0021		70.22							40 x 15	CC	
																							Size (mm)	Form	
																							W x D x H		
CRM	36X CN24 A	(0.002)	0.0056	8.00	0.127	15.41	(0.001)	23.60	0.0037	0.0096	0.0065	(0.001)	0.0466		0.0436	52.56							Block	38 x 13 x 13	concast
3.6.1a Cu/Ni/Sn (Spinodal Alloy)																							Size (mm)	Form	
		Sn	Ni	Cu	Zn	Fe	Al	Si	Mn	Bi	Sb	P	S	Ag	Pb	Mg	Co	B	Ti	Nb			Ø x H		
CRM	36X SP1 A	5.75	8.33	84.90	0.344	0.45	0.0020	0.004	0.084	0.0039	0.0177	(0.003)	0.005	0.005	0.0115		0.057	0.0007	(0.0004)	(0.031)			40 x 15	CC	
CRM	36X SP2 A	8.92	15.72	74.91	0.029	(0.09)	0.0003	(0.0023)	0.0019	(0.0027)	0.006	(0.0006)	0.0030	0.0181	0.026	0.0002	0.119	0.0005	(0.0008)				40 x 15	CC	

3. Copper Base

Updated: 15th December 2016

Blocks / Discs

3.6.4 Cu/Be/Co		Sn	Pb	Zn	Fe	Ni	Al	Si	Co	P	Ag	Mg	Be	Cu	Size (mm) Ø x H		Form									
CRM	36X CBC3 D	0.0021	0.0025	0.004	0.046	0.007	0.019	0.039	0.209			0.0040	1.840	97.77	40 x 15		W									
CRM	36X CBC4 E	0.002	0.329	0.003	0.0274	0.0080	0.0258	0.048	0.215	0.0027		0.0035	1.869	97.47	40 x 15		W									
CRM	36X CBC5 B	0.0013	0.0015	0.0010	0.0108	1.905	0.0104	0.004	0.0084		0.0011	0.0009	0.404	97.61	41 x 15		W									
3.6.5 Cu/Cr		Sn	Pb	Zn	Fe	Ni	Al	Si	Mn	S	P	Co	Cr	Ag	As	Mg	Zr	Cu	Size (mm) Ø x H		Form					
CRM	36X CCR1 E	0.0018	0.0008	(0.001)	0.0170	0.0111	0.0013			0.0016	0.0223		0.652	0.0042	0.0007	(0.0003)	0.079	99.24	50 x 17		W					
CRM	36X 274 B **	0.001	0.001	0.001	0.02	2.6	0.001	0.65	0.001		0.001	0.005	0.35	0.002				[bal]	** provisional values	40 x 15		W				
3.7.1 Various Copper Alloys		Sn	Pb	Zn	Fe	Ni	Al	Si	Mn	P	S	Cr	Co	C	Cu	Size (mm) Ø x H		Form								
CRM	37X 218 A	0.015	0.0025	0.027	0.074	2.52	0.0022	0.58	0.083	0.0014	0.007	0.032	0.0013	0.0022	96.57	38 x 17		W								
CRM	37X 218 B	0.0032	0.0014	0.0054	0.0209	1.892	0.0018	0.564	0.0022			0.176			97.29	38 x 15		W								
CRM	37X 65500 A	0.0426	0.0034	0.0353	0.035	0.0059	0.0028	3.13	0.960	0.0046	0.0010	0.0029		(0.004)	95.75	38 x 15		W								
3.8 Residuals in Pure Copper - Wire		Sn	Pb	Zn	Fe	Ni	Ag	As	Mn	Bi	Sb	Cr	Si	P	Cd	Te	Se	S	O	Size (mm) Ø x H		Form				
CRM	38X C1 C	(0.01)	(0.05)	<0.1	1.7	0.27	11	0.19	(0.005)	0.10	0.10	<0.005	<0.1	<0.05	<0.01	(0.21)	(0.25)	2.0	266	(5 x 80mm pcs.)		Wire				
3.9 Residuals in Pure Copper		Sn	Pb	Zn	Fe	Ni	Al	As	Mn	Bi	Sb	P	S	Co	Cr	Cd	Ag	Au	Se	Te	In	Mg	Ge	Size (mm) Ø x H		Form
CRM	39X 17866 AG	1710	280	470	(20)	608	(10)	547	17	128	65	16	520	325		52	77	24	72	224	364			40 x 15		CC
CRM	39X 17867 AD	1150	196	325		410		387		153	143	15	410	194		110	79	75	67	78	130	41	62	40 x 15		CC
CRM	39X 17868 AG	1030	1040	1970	1100	222	72	226	123	308	300	510	220	248		130	249	101	133	206	76	85		40 x 15		CC
CRM	39X 17869 AF	440	880	820	79	102	136	99	23	450	400	163	90	36		201	376	53	243	319	37	10		40 x 15		CC
CRM	39X 17870 AH	54	328	285	740	555	1440	23	596	494	415	535	18	21	12	22	556	17	118	500	102	330		40 x 15		CC
CRM	39X 17871 C	48	65	27	(6)	344	11	207		530	124		54	9		58	219	37	287	82	47		<10	40 x 15		CC
CRM	39X 27866 A	448	54	287	30	487		383		47	52	147	469	308	12	139	57	16	28	32	437		29	38 x 20		W
CRM	39X 27869 A	106	225	65	30	190		98		376	362	119	112	36	(2)	28	349	80	127	153	90		123	38 x 20		W
		All Elements %																			Size (mm) Ø x H		Form			
		Sn	Pb	Zn	Fe	Ni	Al	As	Mn	Bi	Sb	P	S	Co	Cr	Cd	Ag	Au	Se	Te	In					
CRM	39X 17872 A	0.180	0.293	0.107	(0.045)	0.0537	0.0118	0.0203	0.0055	0.0240	0.0217	0.0045	0.0242	0.0102		0.0013	0.0214	(0.002)	0.0103	0.0208	0.0241	42 x 15		C		
CRM	39X 17873 B	0.0247	0.059	0.0160	0.0052	0.0280		0.0197	0.0005	0.0254	0.0202	0.0009	0.0095	0.0004	(0.0003)	0.0023	0.0291		0.0143	0.0144	0.0040	40 x 15		CC		

4. Zinc Base

Updated: 12th December 2016

Blocks / Discs

4.1		Residuals in Pure Zinc						All elements ppm										Size (mm)		Form	
		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Bi	Sb	Tl	In	Hg			Ø x H			
CRM	41X Z1 Q	27.6	(1)	(1.1)	12.0	28.2	5.1	11.6	1.4	4.7	3.0	(2.4)	2.8	2.6	3.4			50 x 20	C		
CRM	41X Z2 P	40.0	(3.3)	1.5	21.4	33.1	19.7	20.1	11.1	34.1	11.6	2.0	11.2	11.1	15.0			50 x 20	C		
CRM	41X Z3 M	50.2	(3.4)	15.8	32.7	60.5	29.7	34.5	20.9	52.4	31.5	16.7	21.0	23.3	28.9			50 x 20	C		
CRM	41X Z4 L	58.4	33.1	65	43.7	148	22.1	32.6	32.0	28.6	31.9	34.0	27.7	30.4	25			50 x 20	C		
CRM	41X Z5 N	286	107	243	165	262	63.2	109	51.4	49.4	56	54	68	57.3	50			50 x 20	C		
CRM	41X Z6 A	310	<5	96	93	(20)	38	88	2	2	122		4	228				50 x 20	C		
CRM	41X Z11 A	77		261	155	19	72	116			189	26	(10)	345	(9)			50 x 20	C		
4.1.1		Zinc with Impurities																	Size (mm)		Form
		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Bi	Sb	Tl	Ag	As	Cr	Co	Ag	Ti	Ø x H	
CRM	41X 0336Zn1 L	1.007	0.0062	0.0177	0.0067	0.0106	0.0051	0.0088	0.0009	0.0102					0.0008					50 x 20	C
CRM	41X 0336Zn2 M	0.486	0.099	1.55	0.145	(0.01)	0.038	0.354	0.0137	0.0212	0.0099	0.0007	0.0012	0.0102	0.0009					50 x 20	C
CRM	41X 0336Zn3 K	0.0282	0.147	0.336	0.341	0.0456	0.127	0.353	0.0022	0.0106					0.0003					50 x 20	C
CRM	41X 0336Zn5 A	0.91	<0.0005	0.035	0.056	0.016	0.21	0.023	(0.0005)	(0.0001)	(0.001)	0.008								50 x 20	C
CRM	41X 4380Zn1 D	0.0618	0.0032	0.039	0.394	0.0276	0.0510	0.178	0.0058	0.0006	0.0021	0.0019				0.0007		0.0012	0.0004	50 x 20	C
CRM	41X 4380Zn2 C	0.268	0.0243	0.0153	0.284	0.048	0.0021	0.0288	0.0023	0.0087	0.0076	0.0093				0.0027			0.0251	50 x 20	C
CRM	41X 4380Zn3 C	0.180	0.0220	0.0203	0.0950	0.017	0.080	0.073	0.0120	0.0180	0.0103	0.0046				0.0029			0.125	50 x 20	C
CRM	41X 4380Zn4 D	0.310	0.118	0.446	0.086	0.017	0.0416	0.0284	0.0172	0.0092	0.0101	0.0156				0.0029	0.0018		(0.0003)	50 x 20	C
CRM	41X 4380Zn5 C	0.140	0.00165	0.0215	0.0571	0.0120	0.0101	0.071	0.00147	0.035	0.0308	0.0061				0.0075			0.339	50 x 20	C
CRM	41X 4380Zn6 D	0.427	0.0044	0.0260	0.0466	0.0307	0.101	0.0327	0.0073	0.200	0.0047	(0.002)				0.0064	0.0091	0.0030	0.0029	50 x 20	C
CRM	41X 4380Zn7 D	1.18	0.0029	0.277	0.0156	0.0018	0.0036	0.0133	0.0120	0.0036		0.086							0.0065	50 x 20	C
CRM	41X 4380Zn8 D	0.700	0.0054	0.232	0.0097	0.0074	0.0177	0.0208	0.0445	0.0081	0.0156	0.0151				(0.0001)		0.0140	0.0020	50 x 20	C
CRM	41X 4380Zn9 A	0.0139	0.0153	0.295	0.0032	0.0113	0.0008	0.0416	0.0009	0.0018	0.00046	0.0060				0.0015				50 x 20	C
CRM	41X 4380Zn10 A	0.0043	0.184	0.0004	0.0007	0.49	0.0014	0.0022	0.063			0.0005				0.117				50 x 18	C
4.1.2		Galvanising Alloys																	Size (mm)		Form
		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Bi	Sb	As	Cr	Co	V	Sr		Ø x H		
CRM	41X GLV1 D	0.0224	0.0008	0.202	0.0100	0.021	0.0134	0.0169	0.0019		0.0040	0.0010	0.0002		0.0003				50 x 20	C	
CRM	41X GLV2 B	0.259	0.0006	0.111	0.0037	0.143	0.0148	0.0050	0.0145	(0.033)	0.0172	0.0071	0.0035	0.014	0.0024				50 x 20	C	
CRM	41X GLV3 B	0.0091	0.00145	0.334	0.0188	0.0031	0.0060	0.0260	0.0300	0.0111	0.0016	0.058	(0.0007)	0.00084	0.00150				50 x 20	C	
CRM	41X GLV4 D	0.0058	0.0025	0.503	0.0013	0.008	0.0035	0.0246	0.0078	0.164	0.0047	0.0235	0.0002	0.0010	0.0061				50 x 20	C	
CRM	41X GLV5 B	0.0166	0.0014	0.0139	0.0136	0.0443	0.0172	0.0103	0.0025		0.0098	0.148	0.00044		0.0011				50 x 20	C	
CRM	41X GLV6 A	0.120		0.474	0.0053	0.0047	0.0152	0.039	0.0008	0.0013	0.0248	0.0112	0.0014	0.0029	0.0047	<0.0005		sold out	50 x 20	C	
CRM	41X GLV7 A	0.082		0.399	0.00056	0.0031	(0.0006)	0.023	0.0060	0.0025	0.0108	0.0031	0.0016	0.0010	(0.0001)	<0.0001			50 x 20	C	
CRM	41X GLV8 B	0.0039	0.0009	0.258	0.0004	0.0080	0.0005	0.0111	0.0023	0.0035	0.0006	0.0062		(0.0001)					50 x 20	C	
CRM	41X GLV9 A	0.0043	0.0014	0.547	0.0028	0.0039	0.0028	0.0037	0.0009	0.0027	0.0019	0.0048			0.0005				50 x 20	C	
CRM	41X GLV10 A	0.0066	0.0040	0.969	0.0030	0.0051	0.0062	0.0073	0.0022	0.0062	0.0031	0.0009			0.0002				50 x 20	C	
CRM	41X GLV11 A	0.0057	0.0009	0.463	0.0010	0.0027	0.0009	0.0017	0.0008	0.0008	0.0009	0.168			(0.0001)		(0.0004)		50 x 20	C	

4. Zinc Base

Updated: 12th December 2016

Blocks / Discs

4.1.3		Zn/Mn, Zn/Mg, Zn/Ni & Zn/Sb Binaries											Size (mm)		Form					
		Pb	Al	Cd	Fe	Cu	Ni	Mn	Mg	Sb	Sn	Bi		Ø x H						
	41X ZMn1 A	(0.0026)	(0.0001)	(0.0002)	(0.0025)	(0.0005)	(0.0009)	1.07						50 x 20	C					
	41X ZMg1 A								1.13					40 x 15	C					
CRM	41X ZNiBi A	0.0187	0.050	0.0020	0.0133	0.0132	2.02				0.154	0.502		50 x 20	C					
CRM	41X ZNi2 A	0.0172	0.0135	0.0010	0.0061	0.0056	1.97				0.141	0.0050		50 x 20	C					
	41X ZSb1 A									1.03				40 x 15	C					
	41X ZSb4 A									3.78				40 x 15	C					
	41X ZSb8 A									7.68				40 x 15	C					
4.1.4		Special Alloys											Size (mm)		Form					
		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Ti	Cr		Ø x H						
CRM	41X 2951Zn1 A	0.0042	0.0029	0.029	0.0005	0.011	(0.0007)	0.79	0.0038	0.0013	0.278	0.083		50 x 20	C					
CRM	41X 2951Zn2 A	0.0040	0.0123	0.032	0.0037	0.019	(0.0015)	1.37	0.0027	0.0011	0.209	0.142		50 x 20	C					
CRM	41X 2951Zn3 A	0.0065	0.0164	0.078	0.0062	0.029	(0.006)	1.89	0.0010	0.0018	0.133	0.184		50 x 20	C					
4.1.5		RoHS Monitors											Size (mm)		Form					
		Pb	Cd	Hg	Cr								Ø x H							
CRM	41X ZSC1 A	0.0621	0.0288	0.026	0.0039								50 x 20	C						
CRM	41X ZSC2 A	0.111	0.0016	0.0053	0.0036								50 x 20	C						
CRM	41X ZSC3 A	0.0273	0.119	0.0021	0.0148								50 x 20	C						
CRM	41X ZSC4 A	0.156	0.0131	0.050	0.0299								50 x 20	C						
CRM	41X ZSC6 A	0.0077	0.215	0.029	<0.0002								50 x 20	C						
4.2		Zn/Al											Size (mm)		Form					
		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Sb	Cr	Si	Ti	In	Ce	La	Zr	Ø x H	
CRM	42X Z1 J	0.0017	0.0009	4.66	0.0014	0.013	0.0007	0.0050	0.0014	0.0038	0.0011	0.0004	(0.002)			0.0011	(0.0008)		50 x 20	C
CRM	42X Z2 K	0.0029	0.0146	3.79	0.0017	0.0055	0.0011	0.0300	0.0155	0.0274	0.0010	(0.0001)	0.0011			0.0055	0.0026		50 x 20	C
CRM	42X Z3 J	0.0068	0.0503	3.84	0.0065	0.0145	0.0048	0.135	0.0071	0.0090	0.0006		(0.002)			0.0032	0.0013		50 x 20	C
CRM	42X Z4 J	0.0133	0.0663	3.52	0.0065	0.019	0.0052	0.0752	0.0170	0.0083		(0.0002)	0.006		0.0025	0.0361	0.0183		50 x 20	C
CRM	42X Z5 M	0.0030	0.0508	4.33	0.0013	(0.05)	0.0012	0.111	0.041	0.0049		(0.0002)		0.0017	0.0047	0.0328	0.0150		50 x 20	C
CRM	42X Z6 B	0.0093	0.177	3.67	0.0039	0.008	0.0057	0.238	0.00030	0.0157	0.0169	0.0034	(0.010)	0.0021	0.0019	(0.012)	(0.011)		50 x 20	C
CRM	42X Z7 B	0.0097	0.0095	4.39	0.030	0.027	0.012	0.0249	0.0067	0.0045		(0.0001)	0.006			0.072	0.061		50 x 20	C
CRM	42X Z8 A	0.0025	0.0033	7.03	0.0003	0.013	(0.002)	0.0215	0.0019	0.0014		(0.0002)	0.013			0.0081	0.0079		50 x 20	C
CRM	42X Z9 A	0.0021	0.0464	5.58	0.0054	0.032	(0.0004)	0.0070	(0.0003)	0.0006			(0.004)			0.0047	0.0044	0.011	50 x 20	C
CRM	42X Z11 A	0.0058	0.0329	3.19	0.0020	(0.036)	0.0017	0.093	0.0241	0.0196	0.0047	0.0016		0.0047	0.0037	0.0014	(0.0009)		50 x 20	C
CRM	42X Z12 A	0.0079	0.0488	4.72	0.00277	0.046	0.0022	0.156	0.0413	0.0483	0.0070	0.00063		0.0076	0.0068	0.0116	0.0084		50 x 20	C
CRM	42X Z15 A	0.0074	0.0026	9.99	0.0023	0.026	0.0006	0.0028	0.0017	0.0037	0.0006	0.0003			0.0024				50 x 20	C
CRM	42X Z16 A	0.0090	0.105	12.28	0.0045	0.033	0.0034	0.235	0.0039	0.0028		0.0007	0.011	(0.003)	0.0051				50 x 20	C

4. Zinc Base

Updated: 12th December 2016

Blocks / Discs

4.3	Zn/Al/Cu	Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Bi	Sb	Ti	Cr	Si	Be	Ag	Sr	Size (mm) Ø x H	Form
CRM	43X Z1 K	0.0038	0.0256	4.50	0.0014	0.0070	0.0019	0.717	0.0010	0.0014	0.0015	0.0007		0.0007					50 x 20	C
CRM	43X Z2 M	0.0106	0.0828	3.89	0.0053	0.0081	0.0099	1.004	0.0024	0.0086	0.0022	0.0068	0.0008	0.0063	0.011				50 x 20	C
CRM	43X Z2 N	0.0125	0.0885	4.02	0.0080	0.0023	0.0052	1.049	0.0022	0.099	0.0027	0.0062	0.0008	0.0011	(0.001)				50 x 20	C
CRM	43X Z3 M	0.0077	0.114	3.40	0.0109	(0.042)	0.0058	1.499	0.0062	0.0013	0.0092	0.0029		0.0046					50 x 20	C
CRM	43X Z4 C	0.0062	0.0480	4.79	0.0033	0.0017	0.0030	2.69	0.0258	0.0153	0.0113	(0.002)			(0.001)				50 x 20	C
CRM	43X Z5 B	0.0029	0.0144	3.164	0.0030	0.10	(0.0004)	5.92	0.0056	0.0061	0.0148	0.065					0.0254	(0.0013)	50 x 20	C
CRM	43X Z6 B	0.005	0.0238	4.51	0.0031	0.024	0.0052	2.85	0.0027	0.0022	0.0054	0.0044		0.0005					50 x 20	C
CRM	43X Z7 A	0.0058	0.062	3.68	0.00092	0.029	0.0031	3.14	0.0005	0.0025	(0.001)	0.0016	0.067	0.0003		0.0194			50 x 20	C
CRM	43X Z8 A	0.0027	0.00155	2.51	0.00090	(0.002)	(0.0005)	0.481	0.00033	0.00021				0.00024					50 x 20	C
CRM	43X Z9 A	0.0078	0.0472	3.17	0.0034	0.073	0.0020	4.82	0.0027	0.0108	0.0033	0.0033	0.0012	0.0034		0.0010			50 x 20	C
CRM	43X Z10 A	0.0046	0.0403	3.99	0.0014	0.007	0.0012	2.97	0.0036	0.0050				0.0003	0.009				50 x 20	C
CRM	43X Z11 F	0.0202	0.0357	11.12	0.0175	0.015	0.0145	0.335	0.0014	0.0032	0.0046	0.0009		(0.0003)	0.0013				50 x 20	C
CRM	43X Z12 E	0.0041	0.0287	10.38	0.0045	0.037	0.0017	0.791	0.0033	0.0026	0.0021	0.0032	0.0050	0.0008	(0.002)				50 x 20	C
CRM	43X Z13 E	0.0086	0.0198	9.01	0.0072	0.0045	0.0056	1.113	0.0036	0.0025	0.0014	0.0020		0.0004	(0.001)				50 x 20	C
CRM	43X Z14 E	0.015	0.0133	8.05	0.0083	0.031	0.0054	1.13	0.0066	0.0050	0.0096	0.0089	0.0014	0.0047	0.016				50 x 20	C
CRM	43X Z15 C	0.0054	0.0024	7.36	0.0030	0.009	0.004	1.53	0.0019	0.0020	0.005	0.005	0.0020	0.0025	(0.011)				50 x 20	C
CRM	43X Z21 D	0.0087	0.0142	23.9	0.0010	0.0067	0.0007	2.68	0.0021	0.0022					0.0191			(0.0005)	50 x 20	C
CRM	43X Z22 D	0.0053	0.0099	27.4	0.0043	0.068	0.0020	2.11	0.0101	0.0057			0.0073	0.0010	0.019				50 x 20	C
CRM	43X Z23 E	0.0112	0.0242	30.7	0.0042	0.055	0.0115	3.22	0.0236	0.0090			0.0045	0.0147	0.077				50 x 20	C
		Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Cr	Si	Ce	La					Size (mm) Ø x H	Form
CRM	43X SC1 A	0.0150	0.740	3.75	0.0011	0.073	0.0082	1.903	0.0161	0.0201	0.0082	0.022							50 x 20	C
CRM	43X SC2 A	0.0097	0.498	3.41	0.0018	0.046	0.0031	4.80	0.0096	0.0183	0.023	0.0133							50 x 20	C
CRM	43X SC3 A	0.0066	0.257	3.14	0.0028	0.018	0.0078	3.03	0.0261	0.0337	0.0108	0.022							50 x 20	C
CRM	43X SC4 A	0.0064	0.093	4.35	0.0058	0.022	0.0056	1.122	0.0249	0.044	0.009	0.022							50 x 20	C
CRM	43X GALF1 A	0.0505	0.0999	4.68	0.0499	0.061	0.0514	4.39					0.0569	0.0284					50 x 20	C
CRM	43X GALF2 A	0.0050	0.0504	5.40	0.0043	0.032	0.0040	0.0585					0.0318	0.0158					50 x 20	C
CRM	43X GALF3 A	0.0032	0.0099	8.37	0.0018	0.018	0.0025	0.507					0.0152	0.0076					50 x 20	C
CRM	43X GALF4 A	0.0122	0.0062	10.71	0.0108	0.074	0.0110	2.470					0.079	0.041					50 x 20	C
CRM	43X GALF5 A	0.0084	0.0016	15.03	0.0080	(0.072)	0.0081	0.0114					0.0041	0.0019					50 x 20	C
4.5	Zn/Al 'Galvalume'	Zn	Si	Fe	Cu	Ni	Sn	Pb	Mg	Ca	Ti	Li	Sr	Al					Size (mm) Ø x H	Form
	45X ZnAl1 B	24.6	3.07	0.22	0.057		0.017	0.021	0.044	0.0021	0.016	0.0015		(bal)					55 x 6	CC
	45X ZnAl3 B	45.2	0.606	0.047	0.0088		0.0034	0.0062	(0.0002)	0.0004	0.020	(0.0004)		(bal)					55 x 6	CC
	45X ZnAl7 C	47.5	1.59	0.077	0.0050	0.0049	0.0096	0.010	0.0070		0.0049		(0.0004)	(bal)					55 x 6	CC
	45X ZnAl7 D	43.6	1.56	0.170	0.0100	0.0032	(0.0005)	0.0042	0.0005		0.028		(0.007)	(bal)					55 x 6	CC

Note these are not CRMs

5. Aluminium Base

Updated: 12th December 2016

Blocks / Discs

5.1.1 Residuals in Aluminium																						Size (mm)		Form
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Zr	Co	V	Ag	Bi	Sb	Cd	Ga	As	Hg	Ø x H	
CRM	51X G00H1 D	0.0131	0.054	0.142	0.831	0.0074	0.231	0.243	0.0021	0.096	0.0135	0.0061	(0.001)		0.0081		0.023	(0.003)					40 x 15	C
CRM	51X G00H2 E	0.111	0.093	0.350	0.356	0.154	0.119	0.113	0.114	0.0065	0.128	0.0174	0.0150		0.0148		0.011	0.0265	0.0031	0.011	(0.005)		40x15 or 50x20	C
CRM	51X G00H3 D	0.399	0.0077	0.895	0.313	0.210	0.0115	0.097	0.055	0.083	0.0043	0.095	0.0095	0.0042	0.0142	0.0079	0.076	0.0025	0.0186	0.010	(0.0003)	<0.001	50 x 20	C
CRM	51X G00H4 B	0.051	0.024	0.028	0.072	0.0309	0.036	0.151	0.021	0.031	0.029	0.040	0.0261	0.030	0.0108	0.0227	0.0202		0.0208	0.022	0.0014	0.012	50 x 20	C
CRM	51X G00H5 B	0.227	0.110	0.739	0.490	0.196	0.161	0.479	0.130	0.201	0.100	0.0249	0.0005	0.045	0.0295	0.11	0.130	0.056	0.0103	0.0122	(0.0005)	<0.001	50 x 20	C
CRM	51X A1350 A	0.0016	0.0032	0.0232	0.0968	0.0019	0.0071	0.0148	(0.001)	0.0005	0.0029	0.0024	0.0007	0.0005	0.0042					0.0137			50 x 20	W
5.4 Al/Si																						Size (mm)		Form
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Be	Bi	Cd	Sr	Ga	Zr	Li	Ca	Ø x H	
CRM	54X G231H1 D	1.141	0.342	10.52	0.945	0.0568	0.349	0.726	0.096	0.156	0.0233	0.107			0.0018			0.010					50 x 15	C
CRM	54X G231H2 C	0.868	0.159	11.6	0.131	0.191	0.171	0.397	0.082	0.127	0.085	0.0469			0.0146			(0.0006)					50 x 15	C
CRM	54X G231H3 C	0.420	0.039	13.17	0.393	0.477	0.0932	0.130	0.0080	0.0139	0.128	0.0630			0.0003								50 x 15	C
CRM	54X GS20J1 E	0.308	0.186	18.8	0.79	0.097	0.159	0.43	0.120	0.130	0.129	0.115			(0.0001)			<0.0001					40x13 or 50x17	C
CRM	54X GS20J2 E	0.168	0.178	18.7	0.56	0.059	0.091	0.305	0.066	0.075	0.082	0.066			<0.0001			<0.0001					40x13 or 50x17	C
CRM	54X GS20J3 D	0.079	0.118	23.9	0.328	0.302	(0.003)	0.030	0.077	(0.012)	0.0055	0.0017			<0.0001			<0.0001					40x13 or 50x17	C
CRM	54X GS20J4 D	(0.0037)	0.0050	25.5	0.227	0.146	0.265	0.224	0.0014	(0.0021)	0.107	0.194			0.0017			(0.002)					40x13 or 50x17	C
CRM	54X G06H1 R	0.630	0.489	8.43	1.08	0.022	0.611	0.60	0.082	0.133	0.248	0.084	0.015	0.010		0.006	0.0074				<0.001		40 x 13	C
CRM	54X G06H2 S	0.54	0.40	10.19	0.640	0.234	0.55	0.47	0.213	0.116	0.179	0.130	0.0086	0.018		0.027	(0.0004)				(0.0044)		40 x 13	C
CRM	54X G06H3 P	0.322	0.202	9.94	0.510	0.345	0.214	0.0270	0.0203	0.0488	0.079	0.0530	0.0208	0.0278		0.0067	0.0048						50 x 15	C
CRM	54X G06H4 R **	0.13	0.12	12.1	0.25	0.52	0.12	0.12	0.04	0.005	0.12	0.01	0.12	0.06	** provisional	0.003	0.003	0.005		0.002	0.002		65 x 20	HIP
CRM	54X G06H5 L	0.0229	(0.0022)	13.76	0.210	0.85	0.0067	0.225	(0.0020)	0.022	0.0106	0.026		0.008			(0.0002)				(0.0001)		40x13 or 50x 17	C
CRM	54X G13H1 N	1.87	2.89	8.91	0.801	0.0137	1.83	0.37	0.240	0.260	0.112	0.062	0.0051		0.0078	<0.001		<0.001		<0.005			40x13 or 50x17	C
CRM	54X G13H2 M	1.29	1.37	10.42	0.767	0.248	1.15	0.530	0.083	0.145	0.166	0.103	0.004										40x13 or 50x17	C
CRM	54X G13H3 M	0.82	0.89	10.2	0.79	0.43	0.95	0.42	0.050	0.092	0.152	0.060	0.009		0.0075					(0.004)			40 x 13	C
CRM	54X G13H4 P	0.688	0.644	12.41	0.534	0.227	0.789	0.443	0.062	0.060	0.109	0.0283	0.0048		0.0018			0.045		0.0165			50 x 15	C
CRM	54X G13H5 L	0.216	0.092	13.26	0.715	0.119	0.115	0.070	0.013	0.009	0.032	0.044	0.0016		0.0049			(0.033)					50 x 15	C
CRM	54X G25D1 L	0.010	0.67	3.37	0.721	0.815	0.262	0.359	(0.0033)	<0.005	0.099	0.140		0.016	0.0011	0.112				(0.004)			40x15 or 50x20	C
CRM	54X G25D2 K	0.130	0.59	3.93	0.576	0.479	0.139	0.169	0.073	0.042	0.152	0.150	0.105	(0.006)	0.049	0.22	0.011						40x15 or 50x20	C
CRM	54X G25D3 S	0.119	0.386	6.29	0.379	0.253	0.0353	0.102	0.050	0.046	0.067	0.0413	0.0086	0.0047	0.0022			(0.045)					50 x 15	C
CRM	54X G25D4 P	0.148	0.151	7.22	0.14	0.195	0.0665	0.207	0.142	0.076	0.0978	0.043	0.0204	0.0542	0.0067	0.0705	0.0070						50 x 15	C
CRM	54X G25D5 L	0.273	(0.0011)	8.14	0.191	(0.0046)	0.0082	0.020	0.273	0.130	0.0068	0.0097	0.0024	(0.0025)	0.022								40x15 or 50x20	C
CRM	54X G25D6 A	0.0021	0.715	5.97	0.080	0.0096	0.0044	0.0050	(0.003)	(0.002)	0.0071	0.0009		0.0133	0.0220				0.0027				50 x 15	C
CRM	54X G25DX A	0.0200	0.402	7.20	0.0792	0.0302	0.0084	0.0354	0.0018	0.0011	0.1519	0.0053		0.0080					0.0209	0.0065		0.0048	65 x 30	HIP
5.5 Al/Si/Cu																						Size (mm)		Form
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Bi	Sb	Zr	Be	Li	Ø x H				
CRM	55X G900J1 F	0.91	0.966	0.127	0.549	0.0133	0.0048	0.152	0.202	0.348	0.0056	0.0012		0.0108	0.071		0.0236	0.0011					50 x 15	C
CRM	55X G900J2 G	0.726	0.594	0.227	0.504	0.192	0.083	0.295	0.217	0.240	0.079	0.080			0.366	0.0374	0.0637	0.0035	(0.007)				50 x 15	C
	55X G900J3 F	0.41	0.38	0.82	0.29	0.56	0.21	0.39	0.14	0.15	0.16	0.25	0.070			(0.029)							40 x 15	C
CRM	55X G900J4 F	0.249	0.459	1.39	0.306	0.75	0.351	0.149	0.088	0.153	0.171	0.343		(0.010)	0.285								40x15 or 50x20	C
	55X G900J5 E	0.024	0.009	1.65	0.18	1.16	0.41	0.023	0.014	0.006	0.33	0.46											40x15 or 50x20	C

5. Aluminium Base

Updated: 13th December 2016

Blocks / Discs

5.5 Al/Si/Cu (continued)																						Size (mm)	Form	
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Be	Bi	Sb	Ag	Ca	P	Cd	Zr		Ø x H
CRM	55X G02D5 A	0.406	0.331	10.03	0.557	0.391	0.0652	0.131	0.067	0.051	0.0180	0.760	0.0752	0.0129	0.0037		0.031				0.0182		50 x 15	C
CRM	55X G02D6 K	0.510	0.376	11.55	0.528	0.300	0.0511	0.577	0.0580	0.0355	0.055	0.366	0.0195	0.0182	0.0026		0.0150				0.0115		50 x 15	C
CRM	55X G02D7 N	1.35	0.332	9.79	0.950	0.502	0.192	0.786	0.311	0.158	0.195	0.0481	0.0419	0.0208	0.0012		0.0039				0.0022		50 x 13	C
CRM	55X G02D8 L	2.36	0.119	9.38	0.779	0.443	0.364	1.38	0.248	0.239	0.182	0.0704	0.0303	0.0438	0.0008		0.0245				0.0049		50 x 13	C
CRM	55X G02D8 M	2.481	0.1517	9.24	0.776	0.256	0.406	1.415	0.201	0.201	0.1535	0.0756	0.0107	0.0536	0.0008		0.0112				0.0029		65 x 30	HIP
CRM	55X G02D9 K	3.51	0.093	8.49	0.423	0.269	0.494	2.48	0.10	0.187	0.096	0.185	0.0074	0.0223	0.0035	0.033	0.049				0.0012		50 x 15	C
CRM	55X G02D10 L	4.59	0.0206	7.33	0.975	0.0524	0.645	2.77	0.022	0.138	0.0302	0.128	0.0544	0.0341	0.0389		0.0086				0.0012		50 x 15	C
CRM	55X G02DX A	2.33	0.118	9.58	0.773	0.247	0.206	1.030	0.029	0.0288	0.0410	0.0321	0.0108	0.0129	0.0020	0.020		0.0052	(0.001)	0.0053	0.0011	0.0103	65 x 30	HIP
CRM	55X G02DY A	3.67	0.309	11.31	0.591	0.107	0.109	0.153	0.0620	0.0747	0.0687	0.063	0.0195	0.0250	0.0012	0.0100		0.0102	(0.001)	0.0100	0.0032	0.0218	65 x 30	HIP
CRM	55X G04HX A	3.40	0.063	5.78	0.280	0.193	0.302	0.492	0.0125	0.0112	0.176	0.0165	0.0060	0.0183	0.0006	0.0058	0.0053	0.0030	0.0011	(0.002)	0.0048	0.0278	65 x 30	HIP
																						Size (mm)	Form	
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Bi	Ca	Cd	Sr	Ga	Na	Li	P		Ø x H
CRM	55X G04H2 D	3.21	0.360	5.22	0.349	0.203	0.0104	0.185	0.0159	0.0049	0.0553	0.0108				0.0010		0.0025		(0.0009)		(0.0020)	45 x 20	C
CRM	55X G04H3 N	3.67	0.173	5.56	0.643	0.362	0.0100	0.507	0.025	0.0047	0.109	0.0136				0.0010		0.0022		(0.0009)		0.0021	45 x 20	C
CRM	55X G04H6 E	5.56	0.151	3.30	0.83	0.028	0.77	0.199	0.221	0.181	0.126	0.126	0.0024	0.014	0.029		0.0039				0.019		40x15 or 50x20	C
CRM	55X G04H7 E	4.65	0.263	4.43	0.633	0.212	0.500	0.537	0.227	0.174	0.0476	0.035	0.030	0.0057	0.022		0.0073				0.0066		40x15 or 50x20	C
CRM	55X G04H8 J	2.86	0.126	4.96	0.529	0.255	0.197	0.998	0.128	0.0809	0.179	0.0301	0.0160	0.0214	0.007		0.0055				0.0033		50 x 15	C
CRM	55X G04H9 E	2.70	0.043	6.60	0.393	0.436	0.160	1.70	0.101	0.0563	0.117	0.0172	0.0114	0.0188	(0.0037)		0.0018				(0.0028)		50 x 15	C
CRM	55X G04H10 D	1.36	0.004	7.21	0.512	0.532	0.0232	2.26	(0.0074)	<0.01	0.0097	0.090	0.043	0.008	0.029				0.011		(0.001)		40x15 or 50x20	C
CRM	55X G26H1 F	4.34	0.29	7.69	1.78	0.015	0.012	1.14	0.24	(0.008)	0.21	0.20	0.022	0.012	0.07								40x15 or 50x20	C
	55X G26H2 F	4.14	1.49	9.36	0.71	0.52	0.41	0.64	0.111	0.110	0.120	0.083	0.052	0.011	0.035		(0.0024)						40x15 or 50x20	C
	55X G26H3 F	2.19	1.01	9.6	1.07	0.45	0.51	0.79	0.23	0.16	0.147	0.130	0.076	0.020									40x15 or 50x20	C
CRM	55X G26H4 D	3.72	1.64	10.37	0.511	0.165	0.909	0.286	0.120	0.234	0.304	0.0623		0.0189	(0.025)								40x15 or 50x20	C
CRM	55X G26H5 E	1.40	1.41	11.38	0.199	0.495	1.13	0.008	0.0108	0.035	0.018	0.0394	0.015	0.0169	0.0201								50 x 20	C
																						Size (mm)	Form	
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Be	Sb	Cd	P	Bi	Ca		Ø x H		
CRM	55X G28J1 Z	1.82	1.26	14.33	0.678	0.024	2.47	0.258	0.0036	0.182	0.104	0.319	0.119	0.0095				(0.0048)				40x13 or 50x17	C	
CRM	55X G28J2 T	1.44	0.0902	15.04	0.516	0.231	1.63	0.292	0.058	0.136	0.065	0.088	0.0029	0.0221	(0.0002)	0.030	0.0023					50 x 20	C	
	55X G28J3 U	1.45	1.30	21.6	0.43	0.33	1.47	0.30	0.07	0.11	0.07	0.09										40x13 or 50x17	C	
CRM	55X G28J4 T	0.82	0.60	20.4	0.52	0.45	0.84	0.32	0.094	0.041	0.28	0.040	0.079	0.010				(0.002)				40x13 or 50x17	C	
	55X G28J5 Y	0.69	0.73	27.6	0.26	0.67	0.43	0.015	0.18	0.03	0.24	0.009						<0.005				40 x 13	C	
CRM	55X G28J6 A	(0.035)	(0.032)	27.15	(0.26)	(0.12)	<0.01	(0.052)	(0.008)	<0.002	(0.024)	(0.006)				(0.007)	(0.038)					65 x 30	SC	
CRM	55X A30J1 H	5.75	1.03	14.6	1.07	0.132	0.014	0.233	0.135	0.006	0.194	0.031	0.091	0.0114	0.0043			(0.004)	0.015			40x13 or 50x17	C	
CRM	55X A30J4 G	3.21	0.508	16.4	0.511	0.350	0.164	0.067	0.0257	0.0190	0.0231	0.0752		0.020				(0.003)				40x13 or 50x17	C	
CRM	55X A30J5 A	4.51	0.722	17.08	0.727	0.213	0.209	0.693	0.084	0.0776	0.070	0.069	0.0396		0.0029			0.016	0.0100	0.0053		65 x 30	HIP	

5. Aluminium Base

Updated: 13th December 2016

Blocks / Discs

5.6		Al/Cu																				Size (mm)		Form
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Be	Bi	Sb	Zr	Ag	Li	Ca	Ø x H		
CRM	56X G14H4 C	3.82	1.72	0.504	0.251	0.122	2.37	0.091	0.050	0.037	0.069	0.0309	0.0288	0.0252									50 x 20	C
CRM	56X G250J1 C	3.82	0.075	0.26	0.41	0.040	1.33	0.28	0.101	0.125	0.008	0.0067	0.008	0.102	<0.0005		(0.003)	(0.003)					40x15 or 50x20	C
CRM	56X G250J2 D	4.81	0.060	0.211	0.346	0.225	1.10	0.155	(0.0016)	(0.004)	0.210	0.063	0.195	0.018			0.324	0.247					40x15 or 50x20	C
CRM	56X G250J3 C	4.90	(0.001)	0.11	0.079	0.278	0.92	0.103	0.024	0.031	0.162	0.024	0.264	0.036	0.0014		0.35	0.275					40x13 or 50x18	C
CRM	56X G250J5 D	4.36	0.022	0.205	0.535	0.150	1.77	0.086	0.076	0.097	0.051	0.047	0.34	0.021	0.0022		0.076	0.22					40x15 or 50x20	C
CRM	56 X G2000J1 C	3.29	1.70	0.099	0.086	1.27	0.0046	0.864	0.022	0.099	0.0053	0.0007	0.00044	0.0097		0.008		0.293	0.0048	(0.0001)			40x15 or 50x20	C
CRM	56 X G2000J2 C	3.73	1.292	0.517	1.38	0.937	0.149	0.711	1.114	0.092	0.096	0.0200	0.056	0.170	0.0054	0.078		0.188	0.0446	0.0112			50 x 20	C
CRM	56 X G2000J3 C	4.78	1.018	0.773	0.382	0.589	0.091	0.114	0.375	0.0157	0.196	0.0573	0.108	0.0099	0.0039	0.152		0.0268	0.0105	0.0019			40x15 or 50x20	C
CRM	56 X G2000J4 C	5.02	0.505	1.33	0.705	0.271	0.089	0.0131	0.879	0.0092	0.135	0.053	0.0247	0.0132		0.0049		0.105	0.0122	0.0025			40x15 or 50x20	C
CRM	56 X G2000J5 C	5.52	0.39	0.321	0.98	0.007	0.204	0.368	0.69	<0.005	0.063	0.0078	0.077	0.027	0.0050	0.136		0.064	0.234	0.009			40x15 or 50x20	C
CRM	56X G2007 A	3.699	0.663	0.328	0.252	0.605	0.0087	0.386	0.889	0.0676	0.0236	0.0354				0.147		0.0020			0.0051		50 x 20	W
CRM	56X G2011 A	5.70	0.0102	0.089	0.632	0.0183	0.0044	0.0188	0.332	0.0037	0.0121	0.0031				0.527							50 x 20	W
CRM	56X G2014 A	4.41	0.453	0.611	0.243	0.572	0.0070	0.195	0.0110	(0.0047)	0.0244	0.0766				0.0013		0.135					50 x 20	W
CRM	56X G2024 A	4.34	1.509	0.122	0.178	0.658	0.0055	0.0446	0.0010	0.0010	0.0099	0.0389		0.0070				0.0053					50 x 20	W
CRM	56X G2618 A	2.45	1.625	0.175	1.057	0.0394	0.953	0.0139	0.0020	0.0007	0.069	0.0165		0.0162				0.0011			0.0020		50 x 20	W
5.6.1		Al/Cu/Ag																				Size (mm)		Form
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Ag	Ø x H										
CRM	56X A201.1 A	4.49	0.198	0.193	0.089	0.310	0.0066	0.0113	0.0020	(0.0025)	0.132	0.0029	0.494	50 x 20		C								
5.7		Al/Cu/Si																				Size (mm)		Form
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Be	Sb	Cd	Ga	Zr	B	Li	Ø x H		
CRM	57X G12H1 C	5.54	0.40	2.52	0.88	0.032	0.31	1.03	0.016	0.095	0.114	0.069	0.113	0.15	0.0019		0.012		0.07		0.008		40x15 or 50x20	C
CRM	57X G12H2 C	7.96	0.336	2.79	1.021	0.0900	0.309	0.999	0.12	0.202	0.0081	0.0148	0.0391	0.0027			0.0025		0.0111	(0.003)			50 x 15	C
CRM	57X G12H3 C	8.69	0.296	1.48	0.350	0.117	0.479	0.554	0.092	0.132	0.196	0.086	0.039	0.0126	0.0016		0.0055		(0.001)				50 x 20	C
	57X G12H5 G	12.2	0.028	0.55	0.19	0.073	0.11	0.072	0.068	0.067	0.036	0.016	0.054	0.033	0.003	0.066	0.023	0.017	0.045				40x15 or 50x20	C
CRM	57X G12H6 A	8.28	0.292	1.63	0.85	0.223	0.387	6.74	0.110	0.108	0.108	0.054	0.0247	0.0143	(0.0003)		0.0028		0.0262				50 x 20	C
CRM	57X G12H7 A	4.75	0.020	1.21	0.369	0.0327	0.0380	0.384	0.030	0.0307	0.0565	0.0221	0.0483	0.0111			0.0002		0.0328	0.0093			50 x 20	C
	57X AlCu25 A	25.08	0.0012	5.78	0.42	0.0035	0.0017	5.89		0.0024													50 x 20	C
	57X AlCu28 A	27.78	0.0020	5.44	0.22	0.0032	0.0030	5.42		0.0023													50 x 20	C

5. Aluminium Base

Updated: 15th December 2016

Blocks / Discs

5.8		Al/Zn																		Size (mm)	Form			
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	Be	Zr	Cd	Sb	Li						
																				Ø x H				
CRM	58X G40H6 B	0.111	(0.003)	0.09	0.08	0.004	0.008	7.55	<0.002	<0.005	0.064	0.005	0.006	(0.002)	(0.004)	0.032	<0.0005	(0.004)	40x15 or 50x20		C			
CRM	58X G40H7 B	0.050	0.304	0.161	0.101	0.078	0.142	7.16	0.054	0.067	0.0045	0.0018	0.026	0.0012	0.0030	0.027	0.007	(0.0003)	40x15 or 50x20		C			
	58X G40H8 B	0.14	0.69	0.1	0.30	0.20	0.22	6.5	0.090	0.010	0.063	0.22			(0.004)				40x15 or 50x20		C			
CRM	58X G40H9 C	0.172	0.960	0.347	0.320	0.0372	0.062	4.83	0.190	0.068	0.279	0.241	0.0150	(0.0001)	0.157				50 x 20		C			
CRM	58X G40H10 C	0.188	1.25	0.224	0.361	0.269	0.097	4.66	0.044	0.042	0.187	0.468	0.050	(0.0003)	0.215				50 x 20		C			
5.9		Al/Zn/Mg/Cu																		Size (mm)	Form			
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Bi	Cd	Ga	Zr	Be	B				
																				Ø x H				
CRM	59X G77J1 G	2.810	4.52	0.1015	0.209	0.810	0.205	2.289	0.158	0.148	0.251	0.297	0.0104	0.0064	0.0578	0.0351	0.010	0.0484			65 x 30		HIP	
CRM	59X G77J2 E	2.37	3.04	0.206	0.293	0.239	0.527	3.25	0.127	0.0054	0.0156	0.0966		0.0153		0.0023		0.152			40x15 or 50x20		C	
CRM	59X G77J3 F	1.30	2.53	0.647	0.70	0.246	0.402	4.72	0.108	0.122	0.148	0.150	0.032	0.0181	0.0297	0.0095		0.0144			50 x 20		C	
CRM	59X G77J4 E	0.81	1.47	0.59	1.04	0.224	0.0037	5.30	0.073	0.219	0.119	0.071		0.0067		0.00054		0.080			40x15 or 50x20		C	
CRM	59X G77J5 E	0.0203	0.851	0.562	1.37	0.0398	1.002	7.82	0.0194	0.0140	0.0255	0.0301	0.0373	0.052		0.0142		0.0194	0.0036		50 x 15		C	
CRM	59X G77J6 B	1.08	2.60	0.094	0.293	0.0318	0.0248	12.02	0.0123	0.0267	0.020	0.0127	0.0087	0.0107		0.0015		0.261	0.0079		50 x 20		C	
CRM	59X G7020 A	0.0320	1.313	0.049	0.178	0.200	0.0051	4.82	0.0018	0.0022	0.0261	0.192		0.0107				0.146		0.0025	50 x 20		W	
CRM	59X G7022 A	0.631	2.69	0.126	0.120	0.127	0.0030	5.17	0.0019	0.0006	0.0160	0.140						0.0016			50 x 20		W	
CRM	59X G7050 A	2.119	2.030	0.045	0.0745	0.0047	0.0041	6.18	0.0010	0.0010	0.0242	0.0097		0.0092				0.100		0.0011	50 x 20		W	
CRM	59X G7068 A	1.676	2.70	0.051	0.117	0.0156	0.0056	7.96	0.0020	(0.001)	0.0419	0.0324						0.088			50 x 20		W	
CRM	59X G7075 A	1.68	2.324	0.147	0.239	0.0757	0.0045	5.69	0.0177	0.0008	0.0615	0.196					0.0088	0.0008			50 x 20		W	
5.11		Al/Mg																		Size (mm)	Form			
		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Be	Cd	Ga	Zr	B	Li	Mo			
																				Ø x H				
CRM	511X G05H1 H	0.32	2.02	0.42	0.79	0.012	0.125	0.47	0.023	0.178	0.204	0.242		0.053	(0.0002)	0.013		(0.002)				40 x 15		C
CRM	511X G05H2 H	0.188	3.58	0.299	0.641	0.124	0.157	0.372	0.049	0.0495	0.068	0.172		0.0248	0.0018	0.0023		0.0105	0.0083			50 x 15		C
	511X G05H3 H	0.093	3.97	0.21	0.41	0.40	0.090	0.092	0.107	0.096	0.25	0.095			0.0074							40x15 or 50x20		C
	511X G05H4 F	0.056	5.1	0.11	0.14	0.55	0.040	0.062	0.15	0.14	0.048	0.029			0.014							40 x 15		C
CRM	511X G05H5 F	0.071	9.22	0.141	0.129	1.110	0.0129	0.019	0.185	0.0089	0.0157	0.0113		0.041	0.0062			0.107				50 x 20		C
CRM	511X G10H4 C	0.163	10.24	0.244	0.193	0.228	0.117	0.117	0.080	0.075	0.155	0.083			0.0061							50 x 20		C
CRM	511X G10H5 B	0.0227	13.97	0.050	0.057	0.098	0.036	0.029	0.165	0.013	0.0052	0.0017			0.0274					0.0032		50 x 20		C
CRM	511X G3000B1 C	0.287	0.253	0.788	0.669	0.752	0.142	0.0347	0.145	0.163	0.0327	0.0972		0.054			0.051					40x15 or 50x20		C
CRM	511X G3000B2 B	0.20	0.68	0.23	0.335	0.81	0.063	0.098	0.137	0.105	0.111	0.200	0.007	<0.005	0.0017	(0.0007)	0.012			0.017	(0.059)	40x15 or 50x20		C
CRM	511X G3000B3 B	0.120	0.80	0.35	0.376	1.06	0.116	0.140	0.062	0.028	0.22	0.056	0.008	<0.005	0.005	(0.001)	0.014				(0.093)	40 x 15		C
CRM	511X G3000B4 C	0.086	1.267	0.130	0.440	0.916	0.0347	0.058	0.0285	0.0456	0.052	0.0121		0.0199	0.0140		0.0284					50 x 20		C

5. Aluminium Base

Updated: 13th December 2016

Blocks / Discs

5.11 Al/Mg continued		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	V	Zr	Bi	Ga			Size (mm) Ø x H	Form		
CRM	511X G5083 A	0.042	3.98	0.22	0.363	0.592	0.0094	0.0488	0.0069	0.0015	0.0294	0.237	0.0092	0.0011	0.0016				50 x 20	W		
CRM	511X G6061 A	0.260	0.896	0.696	0.304	0.0721	0.0044	0.0105	0.0014	0.0012	0.0204	0.200	0.0138			0.0160			50 x 20	W		
CRM	511X G6063 A	0.0014	0.437	0.412	0.185	0.0239	0.0021	0.0062	0.0011	(0.001)	0.011	0.0021	0.0087						50 x 20	W		
CRM	511X G6082 A	0.0184	0.759	0.753	0.081	0.534	0.0035	0.054	0.0012	0.0011	0.0278	0.0606							50 x 20	W		
CRM	511X G6082 B	0.0141	0.660	0.910	0.180	0.566	0.0044	0.0016	(0.001)	(0.001)	0.0158	0.0055			(0.0007)				50 x 20	W		
5.11 Al/Mg with Bi, Sn and Pb		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Bi	Zr	Be	V	B	Ga	Size (mm) Ø x H	Form		
CRM	511X G6012	0.114	1.10	1.35	0.285	0.910	0.0154	0.255	1.10	0.040	0.016	0.269	0.552	0.032	0.0072				50 x 17	C		
CRM	511X G6012A	0.351	0.712	0.768	0.71	0.424	0.048	0.060	0.211	1.88	0.197	0.0223	0.701	0.0480	0.0110				50 x 17	C		
CRM	511X G6023 A	0.451	0.512	1.21	0.51	0.556	0.036	0.0260	0.0110	1.037	0.0117	0.0054	0.353	0.0110	0.0020				50 x 17	C		
CRM	511X G6026 A **	0.42	0.70	0.90	0.47	0.72	0.005	0.08	0.28	0.005	0.025	0.07	0.49	0.003		0.005	0.002	0.008	** provisional values	50 x 20	W	
CRM	511X G6065 A	0.214	1.180	0.495	0.74	0.131	0.0144	0.164	0.0310	0.0251	0.112	0.0759	1.27	0.144	0.0011				50 x 17	C		
CRM	511X G6262 A	0.267	0.881	0.649	0.58	0.163	0.028	0.198	0.0081	0.539	0.045	0.121	0.444	0.0051	0.0011				50 x 17	C		
CRM	511X G6262 B	0.243	0.829	0.557	0.329	0.0737	0.0034	0.0209	0.499	(0.001)	0.0194	0.0666	0.424						50 x 20	W		
5.14 Al/Mn		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Zr							Size (mm) Ø x H	Form	
CRM	514X 9091.1 C	0.046	(0.001)	0.035	0.081	6.93	(0.0026)	0.029	0.016	0.013	0.0017	<0.005	0.184							40 x 13	C	
5.17 Sacrificial Anode		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	In	Ga	Cd					Size (mm) Ø x H	Form	
CRM	517X LF1 A	0.0020	0.0097	0.248	0.101	0.0013	0.0010	3.71	(0.002)	(0.005)	0.0396	(0.001)	0.0187	0.0164	<0.0005					45 x 20	C	
5.18 Pressed Powder Alloys		Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	V	Ca	Mo	Zr	Sr	B	P	Size (mm) Ø x H	Form
CRM	518X 429 A	1.023	1.25	28.9	0.201	0.0165	0.014	0.0042	0.0020		0.0163	0.0034	2.22	0.0090	0.020			0.0006	(0.002)	(0.004)	65 x 25	HIP
CRM	518X 905 A	2.51	0.645	0.10	2.54	0.994	4.98	0.0052	(0.001)	(0.0024)	0.587	0.0090	0.0033	0.0186	(0.0007)	0.807	0.77				45 x 40	HIP

6. Magnesium Base

Updated: 15th December 2016

Blocks / Discs

6.1		Residuals in Pure Magnesium																		Size (mm)		Form
		Al	Zn	Mn	Zr	Cu	Si	Fe	Ni	Ca	Sn	Pb	Ag	Be	Cd	Ce	La	Nd	Y	Ø x H		
CRM	61X MGP2 A **	0.065	0.0122	0.0118	(0.0007)	0.0109	0.031	0.0061	0.0029	0.0138	0.0073	0.0061	0.003	<0.0001	0.0063	0.0019	0.0014			** unsuitable for use with glow discharge systems	45 x 20	C
CRM	61X MGP3 A **	0.096	0.0196	0.0137	(0.0014)	0.0292	0.044	0.014	0.0048	0.054	0.0155	0.0148	0.0125	<0.0001	0.0154	0.0055	0.0038				45 x 20	C
CRM	61X MGP4 A **	0.0247	0.0158	0.0100	0.030	0.0108	0.037	(0.0044)	0.0028	0.028	0.0067	0.0066	0.0203	<0.0001	0.0071	0.0041	0.0030				45 x 20	C
CRM	61X MGP5 A	0.119	0.099	0.201		0.092	0.094	0.0048	0.0176		0.0352	0.0357	0.0342	0.0018	0.0292	0.049	0.0382	0.0446	0.0132		40x15 or 50x20	C
CRM	61X MGP6 A	0.0449	0.010	0.0125		0.0067	0.044	0.0041	0.0025	(0.001)	0.0091	0.0120	0.0043		0.0025	0.0209	0.0137	0.0238	0.0375		40x15 or 50x20	C
6.3		Mg/Mn																		Size (mm)		Form
		Al	Zn	Mn	Cu	Si	Fe	Ni	Ca	Sn	Pb	Ag	Be	Cd						Ø x H		
CRM	63X MGE1 E	(0.088)	0.083	0.860	0.0503	0.052	0.0014	0.0162		0.0053	0.011	0.0195	(0.0002)	0.0017						40x15 or 50x20	C	
CRM	63X MGE2 B	0.0432	0.0245	1.75	0.0203	0.019	0.0020	0.0035	0.0015	0.0024	0.0020	0.0090		0.0009						40x15 or 50x20	C	
CRM	63X MGE3 C	(0.056)	0.0101	1.62	0.0072	0.014	0.0005	0.0028		0.006	0.0046	0.0041	<0.0001	0.0046						40x15 or 45x20	C	
6.4		Mg/Al														Typical alloy type				Form		
		Al	Zn	Mn	Cu	Si	Fe	Ni	Sn	Pb	Be	Ce	La	Nd								
CRM	64X MGQ1 A	1.083	0.235	0.377	0.0840	0.062	0.0034	0.0041	0.0195	0.0199	0.00036				AZ10A				40x15 or 50x20	C		
CRM	64X MGQ2 A	4.53	0.107	0.378	0.0151	0.051	0.0041	0.0061	0.0107	0.0107	0.0013				AM50A				40x15 or 50x20	C		
CRM	64X MGQ3 A	8.66	0.0039	0.206	0.0349	0.083	0.0090	0.0032	0.0019	0.0022	0.0041				AM90A				40x15 or 50x20	C		
CRM	64X MGQ4 A	6.50	0.188	0.183	0.310	0.067	0.0040	0.0068	0.0282	0.0322	0.00029				AM60A				40x15 or 50x20	C		
CRM	64X MGQ5 A	5.76	0.0465	0.276	0.0072	0.052	0.0043	0.0010	0.0050	0.0056	0.0013				AM60B				40x15 or 50x20	C		
CRM	64X MGQ6 A	2.31	0.072	(0.26)	0.0045	(0.97)	(0.004)	0.0026	0.0055	0.0060	0.0007				AS21A				Mn and Si segregation	40x15 or 50x20	C	
CRM	64X MGQ7 A	4.02	0.061	(0.43)	0.0167	(1.05)	0.0028	0.0053	0.0096	0.0126	0.00042				AS41A				Mn and Si segregation	40x15 or 50x20	C	
CRM	64X MGQ8 A	1.030	0.0442	0.700	0.0019	0.045	0.0018	0.0004	0.0022	0.0008	0.00015				AZ10-mod					40x15 or 50x20	C	
CRM	64X MGQ9 A	2.14	0.243	0.0684	0.0104	(0.37)	0.0069	0.0020	0.0076	0.0096	0.0015	0.111	0.083	0.114	AS21B				Si segregation	40x15 or 50x20	C	
6.5		Mg/Al/Zn																		Size (mm)		Form
		Al	Zn	Mn	Cu	Si	Fe	Ni	Sn	Pb	Be	Ca	Ag	Ce	La	Cd	Sr	Hg	Typical alloy type	Ø x H		
CRM	65X MGA1 J **	5.45	1.26	0.060	0.221	0.20	0.021	0.021	0.072	0.012	0.006	0.029	0.012	0.009	0.007	0.013	** unsuitable for use with glow-discharge systems				45 x 20	C
CRM	65X MGA5 A	8.00	0.411	0.401	0.0195	0.110	0.006	0.0201	0.0124	0.042	0.0013	(0.014)	0.0050			0.0035	0.0004			50 x 20	C	
CRM	65X MGA11 A	3.63	1.59	0.044	0.0496	0.022	0.0048	0.0134	0.093	0.0190	0.0021	0.102	(0.0002)	(0.0005)	(0.0005)	0.0014		0.006		40x15 or 50x20	C	
CRM	65X MGA12 A	5.68	3.18	0.198	0.266	0.0142	0.0053	0.0148	0.0021	0.010	(0.0036)	0.037	0.0128	0.0009	0.0007	0.0121		(0.016)		40x15 or 50x20	C	
CRM	65X MGA13 A	7.45	0.925	0.092	0.125	0.022	(0.008)	0.0039	0.043	0.0085	(0.010)	0.0064	0.0074	0.0024	0.0021	0.0055		(0.033)		40x15 or 50x20	C	
CRM	65X MGA14 B	9.09	0.685	0.282	0.0102	0.080	0.0084	0.0082	0.0085	0.0061	0.0029		0.0016	0.0120	0.0111	0.0014		(0.08)		50 x 15	C	
CRM	65X MGA15 A	10.67	0.348	0.067	0.0273	0.034	0.010	0.0026	0.0021	0.0051	0.0062	(0.0014)	0.030	0.0069	0.0048	0.0034		0.011		40x15 or 50x20	C	
CRM	65X MGA16 A	6.78	4.03	0.271	0.099	0.023	0.0073	0.0057	0.028	0.050	0.0011	0.0024	0.0035	0.0017	0.0012	0.0066		0.005		40x15 or 50x20	C	
CRM	65X MGA17 A	4.20	0.128	0.203	0.0215	0.33	0.0069	0.0141	0.0050	0.0009		0.021	0.0064			0.0049				40x15 or 50x20	C	

6. Magnesium Base

Updated: 13th December 2016

Blocks / Discs

6.5		Mg/Al/Zn - continued.										Typical alloy type								Size (mm) Ø x H		Form
		Al	Zn	Mn	Cu	Si	Fe	Ni	Sn	Pb	Be											
CRM	65X MGA18 A	6.75	0.502	0.192	0.052	0.043	0.0081	0.0074	0.0114	0.0244	0.00051									AZ61A	40x15 or 50x20	C
CRM	65X MGA19 A	8.97	2.17	0.322	0.0426	0.196	0.0085	0.0065	0.0489	0.0489	0.00025									AZ92A	40x15 or 50x20	C
CRM	65X MGA20 A	5.87	1.32	0.067	0.0131	0.052	0.0078	0.0025	0.0320	0.0075	0.0018									AZ61A	40x15 or 50x20	C
CRM	65X MGA21 A	12.37	5.11	0.0777	0.0020	0.028	0.0140	0.0010	0.0063	0.0048	0.0006									AZ125A	40x15 or 50x20	C
CRM	65X MGA22 A	8.62	0.89	0.40	0.078	0.085	0.0060	0.0058	0.0033	0.0038	0.0006									AZ91A	40x15 or 50x20	C
CRM	65X MGA23 A	9.75	0.555	0.130	0.0155	0.027	0.0085	0.0011	0.0024	0.0019	0.0024									AZ91D	40x15 or 50x20	C
		Al	Zn	Mn	Cu	Si	Fe	Ni	Ca	Sn	Pb	Ag	Ce	La	Be	Cd	Ti	Size (mm) Ø x H		Form		
CRM	65X MGB1 E	1.90	1.60	0.770	0.051	0.069	0.0027	0.0020	(0.067)	0.0098	0.0095	0.0300			0.0008	0.076		40x15 or 50x20		C		
CRM	65X MGB2 C	2.67	0.95	0.333	0.113	0.069	0.010	0.0028	0.011	0.0047	0.0036	0.0099	0.0009	0.0007	0.0008	0.0115	0.0003	40 x 18		C		
CRM	65X MGB2 D	2.81	1.047	0.526	0.065	(0.088)	0.0032	0.0043	(0.010)	0.0052	0.0053	0.0099			0.0014	0.0103		40x15 or 50x20		C		
CRM	65X MGB3 B **	3.19	0.608	0.0122	0.0214	0.012	(0.005)	0.0020	0.030	0.0050	0.0037	(0.002)			0.0029	0.012	(0.003)	** unsuitable for use with glow-discharge		C		
CRM	65X MGB3 C	3.38	0.711	0.277	0.0222	0.042	0.0028	0.0027	(0.003)	0.0017	0.0023	0.0028			0.0019	0.0025		40x15 or 50x20		C		
CRM	65X MGB4 C	3.86	0.333	0.031	0.0183	0.037	(0.009)	0.0003	0.0010	0.0050	0.0037	0.0046	0.0003	(0.0001)	0.0033	0.00016	(0.0008)	40 x 18		C		
6.6		Mg/Zn																Size (mm) Ø x H		Form		
		Al	Zn	Mn	Zr	Cu	Si	Fe	Ni	Ca	Sn	Pb	Ag	Ce	La	Nd	Be	Sr				
CRM	66X MGC4 C	0.039	6.81	0.166	<0.001	0.0024	0.06	0.006	0.0009		0.021	0.0030	0.0074				(0.0001)(0.00014)		40x15 or 50x20	C		
CRM	66X MGC5 A	0.072	6.61	1.17		0.0286	0.026	0.0008	0.0111		0.0051	0.0281							40x15 or 50x20	C		
CRM	66X MGD1 B	0.147	1.19	0.125		0.066	(0.073)	0.0029	0.0162		0.026	0.026		0.065	0.031	0.064			40x15 or 50x20	C		
CRM	66X MGD5 A	0.040	6.25	0.307		2.88	0.134	0.008	0.0120	(0.030)	0.104	0.097	0.044				<0.0005		40x15 or 50x20	C		
6.7		Mg/Al/Rare Earth																Size (mm) Ø x H		Form		
		Al	Zn	Mn	Cu	Si	Fe	Ni	Be	Ce	La	Nd	Pr	Gd								
CRM	67X MGK2 A	3.84	0.132	0.534	0.0041	0.057	0.0016	0.0033	0.0025	0.70	0.34	0.125	0.053	0.053					40x15 or 50x20	C		
CRM	67X MGK3 A	4.56	0.050	0.516	0.0017	0.068	0.0024	0.0016	0.0007	0.83	0.374	0.175	0.069	0.038					40x15 or 50x20	C		

7. Tin Base

Updated: 15th December 2016

Blocks / Discs

7.1 Tin with Impurities																						Size (mm)	Form		
		As	Bi	Sb	Pb	Cu	Fe	Cd	Zn	Ni	Al	Ag	Cr	Co	In	Au	Te	Se	P	Ga	Ge	Hg		Ø x H	
CRM	71X PB3 A	0.0022	0.0103	0.0024	2.77	0.0074		0.0008	0.0016			0.0011												40 x 15	C
CRM	71X PB4 A	0.0045	(0.002)	0.0059	4.00	0.0014		0.0027	0.0063			0.0047												40 x 15	C
CRM	71X SR0 C	0.0005	0.0029	0.0055	0.0457	0.0073	0.0040	0.0024	0.0053	0.0025	0.0414	0.0024		0.0004	0.0088	0.0012	0.0021	0.0006	0.0004	0.0054	0.0021	0.0099	40 x 15	C	
CRM	71X SR1 E	0.0102	0.0107	0.0156	0.0324	0.0111	(0.0021)	0.0104	0.0146	0.0041	(0.0016)	0.0212			0.0120	0.0014	0.0112	(0.0015)		0.0049		0.0142	40 x 15	C	
CRM	71X SR2 F	0.0070	0.0403	0.074	0.151	0.116	0.0133	0.0351	0.0058	0.0183	0.0022	0.0305	0.0031		0.0597	0.0077	0.0246				0.009	0.140	40 x 15	C	
CRM	71X SR3 F	0.097	0.123	0.128	0.306	0.121	0.0203	0.100	0.054	0.0371	(0.0014)	0.050			0.104	0.0145	0.070	0.0031		0.0339		0.115	40 x 15	C	
7.3 Tin White Metals (Pewter, Babbitt)																						Size (mm)	Form		
		As	Bi	Sb	Pb	Cu	Fe	Cd	Zn	Ni	Al	Ag	Co	In	S	P						Ø x H			
CRM	73X SC1 A	0.008	0.084	1.48	0.067	2.02	0.0025	0.006	0.003	0.0041	0.0025	0.010	<0.001	0.008	<0.002							40 x 15	C		
CRM	73X SC2 B	0.0355	0.602	3.05	0.0457	1.028	0.0037	0.0282	(0.0007)	0.0156		0.0318	0.0217	0.0099								40 x 15	C		
CRM	73X SC3 A	0.029	0.020	4.60	0.040	0.222	0.017	0.024	0.0014	0.0136	0.001	0.013	0.006	0.031	(0.002)							40 x 15	C		
CRM	73X SC4 B	0.0268	0.153	5.94	0.429	2.63	0.0014	0.0085	(0.001)	0.0130	(0.002)	0.0525	0.0020	0.0143		0.005						40 x 15	C		
CRM	73X SC5 A	0.013	0.43	7.03	0.136	0.57	0.004	0.008	0.001	0.0058	0.003	0.063	0.011	0.036	(0.001)							40 x 15	C		
CRM	73X SC6 A	0.204	0.115	0.092	0.100	5.17	0.007	0.0125	0.01	0.013	(0.003)	0.08	0.0050	0.058	(0.004)							40 x 15	C		
CRM	73X SC7 B	0.059	0.013	13.86	0.32	5.71	(0.043)	0.0019	0.0033	0.0160	(0.001)	0.0059	0.0143	0.0194	(0.001)							40 x 15	C		
CRM	73X SC8 B	0.11	0.0531	5.52	0.110	3.78	0.055	0.098	0.004	0.0351	(0.001)	0.0253	0.0267	0.0325	0.004							40 x 15	C		
CRM	73X SC9 B	0.117	0.0825	8.31	0.305	8.03	0.053	0.0506		0.0084	(0.001)	0.0055	0.0051	0.0059								40 x 12	C		
CRM	73X SC11 C	0.248	0.554	12.98	0.0630	11.51	0.0052	1.72	0.005	0.110		(0.056)				0.025						40 x 12	C		
CRM	73X SC12 B	(0.034)	0.0301	7.50	0.091	6.03	0.024	0.758	0.0210	0.115	0.0015	0.842	0.0210									40 x 15	C		
CRM	73X SC13 A	0.054	0.0188	4.21	0.259	4.19	0.053	0.0021	0.0126		(0.01)					(0.02)						40 x 15	C		
7.4 Tin Lead-Free Solders																						Size (mm)	Form		
		As	Bi	Sb	Pb	Cu	Fe	Cd	Zn	Ni	Al	Ag	P	Se	Au	Co	Ge	In				Ø x H			
CRM	74X AM F	0.0038	0.190	1.064	0.126	3.07	(0.001)	0.0061	(0.006)	0.0260	(0.001)	0.496	(0.002)	(0.001)				0.0082				40 x 15	C		
CRM	74X E F	0.0092	0.0099	0.0168	0.0248	2.94	0.0008	0.0003	(0.005)	0.0069	(0.001)	0.667	(0.001)	0.0008				0.0074				40 x 15	C		
CRM	74X HA G	0.0032	0.0639	2.10	0.077	0.629	0.0029	0.0018	2.73	0.0133	(0.002)	2.80	(0.001)	(0.001)				0.0090				40 x 15	C		
CRM	74X HB G	0.045	0.038	4.81	0.056	4.49	0.0138	0.0103	(0.02)	1.22	(0.003)	0.086	(0.002)	0.0038				0.0179				40 x 15	C		
CRM	74X HN E	0.010	0.122	0.037	0.0404	3.82	0.010	0.0057	(0.0009)	0.185	0.005	0.143	(0.002)	0.0016								40 x 15	C		
CRM	74X TC F	0.024	0.106	0.124	0.183	4.99	0.0031	0.0150	0.004	0.0167	(0.001)	0.039	(0.002)	0.0473				0.0215				40 x 15	C		
CRM	74X BZ1 A	0.0119	3.03	0.031	0.0238	0.026	0.011	0.0012	8.27	0.0097	0.0021	0.004										40 x 15	C		
CRM	74X AB1 A	0.0280	0.997	0.0111	0.0353	0.0285	0.0435	0.0199		0.0036		3.58			0.0010	0.0032		0.0262				40 x 15	C		
CRM	74X GE1 A				0.0339	0.662		0.0059		0.0289	0.065	0.052					0.046					38 x 13	C		
CRM	74X GE2 A				0.0467	0.713		0.0086		0.031	0.068	0.079					0.479					38 x 13	C		

7. Tin Base

Updated: 13th December 2016

Blocks / Discs

7.4 Tin Lead-Free Solders		As	Bi	Sb	Pb	Cu	Fe	Cd	Zn	Ni	Al	Ag	P	In	Au	Se	Co	Hg	Ge	Cr	Size (mm) Ø x H	Form
CRM	74X OA A	0.080	1.065	0.0098	0.128	3.41	0.007	0.00063	(0.002)	0.0025	(0.001)	0.100	0.0072	0.0034	(0.0001)						40 x 15	C
CRM	74X WS A	0.0105	0.0063	1.49	0.037	4.58	(0.004)	0.00140	0.0009	0.0048	(0.001)	0.298	0.0122	0.0032	(0.0002)						40 x 15	C
CRM	74X CA1 B		0.0131	0.0169	0.077	0.682		0.0071			0.0262	0.440			0.0053						40 x 15	C
CRM	74X CA2 B	0.018	0.0365	0.079	0.0496	0.795	0.0023	0.0017	0.0005	0.0361	<0.001	3.50	0.010	0.0053	0.0009	0.0022	0.0019	0.0017	0.023		40 x 13	C
CRM	74X CA3 B	0.0039	0.0156	0.0266	0.0491	0.0869	0.006	0.00045	0.0009	0.0077	0.0010	2.98	0.031	0.0042	0.007				0.0093		40 x 15	C
CRM	74X CA4 C	0.0076	0.0608	0.0709	0.0800	0.545	0.0052	0.0018	(0.006)	0.0872	0.0005	3.01		0.0057		(0.001)	0.0052	0.0054		0.0094	40 x 15	C
CRM	74X CA5 B	0.0125	0.0050	0.124	0.044	1.189	0.0021	0.0023	(0.002)	0.0149	(0.001)	4.09	(0.011)	0.0129	0.0091	0.0004		0.0030			40 x 15	C
CRM	74X CA6 B	0.0133	0.0098	(0.010)	0.0287	0.602	0.0120	0.0005	(0.0005)	0.0246	(0.0003)	0.305	(0.001)	0.0243	0.0048	(0.0005)		0.0039			40 x 15	C
CRM	74X CA7 B	0.0085	0.0102	0.0194	0.107	0.347	0.007	0.0059	0.0501	0.0315		4.02		0.0053			(0.002)	0.049		0.0045	40 x 15	C
CRM	74X CA8 B	0.0144	0.0172	0.0180	0.084	0.950	0.0043	0.0101		0.0020		2.47	0.010	0.0062			0.0202	0.101	0.0020		40 x 15	C
CRM	74X CA9 A	0.0173	0.0364	0.076	0.038	0.097	0.0085	0.0015	0.0010	0.0039	0.0007	1.002	0.011	0.0165	0.0025				0.0049		40 x 15	C

8. Lead Base

Updated: 13th December 2016

Blocks / Discs

8.1	Binaries: Pb/Sb, Pb/As & Pb/Mg												Size (mm)		Form								
		Sb	As	Mg									Ø x H										
CRM	81X PA0.5 C	0.481											40 x 15		C								
CRM	81X PA1.0 C	0.989											40 x 15		C								
CRM	81X PA2.0 D	1.996											40 x 15		C								
CRM	81X PA3.5 E	3.49											40 x 15		C								
CRM	81X PA7.0 D	7.02											40 x 15		C								
CRM	81X PA10.0 C	9.60											40 x 15		C								
CRM	81X PA12.5 D	12.72											40 x 15		C								
	81X PAs1 A		1.25										40 x 15		C								
	81X PMg1 A			1.15									40 x 15		C								
	81X PMg2 A			0.173									40 x 15		C								
	81X PMg3 A			0.023									40 x 15		C								
8.2	Pb/Ag												Size (mm)		Form								
		Sn	Sb	Bi	Cu	As	Ag	Zn	Cd	Fe	In	Al	Ø x H										
CRM	82X PAg 1.5R E	0.036	0.386	0.065	0.27	0.005	1.55	(0.004)					These products are affected by localized Ag segregation			40 x 15		C					
CRM	82X PAg 2.5R D	0.082	0.246	0.13	0.26	0.009	2.21	(0.0024)								40 x 15		C					
CRM	82X PAg 3.5R D	0.25	0.106	0.290	0.073	0.020	3.54	(0.0004)	0.0027	<0.001	0.037	0.0015				40 x 15		C					
CRM	82X PAg 6.0R A	0.50	0.48	0.52	0.18	0.021	5.93	0.007	0.010	<0.001	0.008	<0.001				40 x 15		C					
	82X PAG0.7 A						0.733									40 x 15		C					
	82X PAG0.9 A						0.903									40 x 15		C					
8.3	Lead with Impurities																			Size (mm)		Form	
		Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Ni	Te	Se	Au	Tl	Na	Hg	Pt	S	Ø x H		
CRM	83X PR1 K	0.016	0.0100	0.0508	0.0465	0.0338	0.1029		(0.002)	0.074	0.0080	(0.0004)	0.0058	0.0008	0.0019						40 x 15		C
CRM	83X PR2 G	0.0948	0.0499	0.0404	0.0309	0.0233	0.055		0.0005	0.0020	0.0010	0.0006	0.0100	0.0005	0.0005	(0.0017)	0.0013	0.003			40 x 15		C
CRM	83X PR3 G **	0.043	0.093	0.14	0.074	0.0013	0.003		(0.0005)	0.043	0.005	0.010	0.004	0.017				** provisional values			40 x 15		C
CRM	83X PR4 H		0.0050	0.0150	0.0454	0.0003	0.0114			0.0081		0.0029	0.0229	(0.004)	0.0021	0.0021		0.019			40 x 15		C
CRM	83X PR5 G	0.0010	0.0006	0.0086	0.0006	0.0004	0.0011		(0.0002)	0.0003	0.0002	(0.0002)	0.0003	0.0004		(0.0001)		(0.0001)			40 x 15		C
CRM	83X PR7 B	0.189	0.795	0.479	0.176	0.051	0.290	(0.0008)	(0.0006)	0.455	0.653	(0.0015)	0.0097	0.0052					0.0047		40 x 15		C
CRM	83X PR8 D	0.604	0.257	1.18	0.0448	0.134	0.497		0.0004	0.199	0.293	0.0008	0.0014	(0.0003)	0.0106			0.086			40 x 15		C
CRM	83X PR11 A	0.119	0.497	0.0117	0.0551	0.0095	0.0030	(0.0003)		0.0008		0.0011		(0.0001)		0.0042				0.009	40 x 15		C
CRM	83X PR12 A	0.0005	0.0011	0.0119	0.0353	(0.0003)	0.0030	(0.0003)		0.0011		0.0009		(0.0002)		0.0051				(0.0002)	40 x 15		C
CRM	83X CU06 A	(0.0004)	(0.0008)	0.0134	0.0554	(0.0001)	0.0019		(0.0003)	(0.0001)		0.0003	(0.0002)	(0.0005)						0.0011	40 x 15		C

8. Lead Base

Updated: 12th December 2016

Blocks / Discs

8.3		Lead with Impurities - continued											Size (mm)		Form	
		Sn	Ag	Zn	Cd	Al	Li	Na	Mg	Ca	Ba			Ø x H		
CRM	83X PR9 A	0.153	0.0049	0.0045	0.0007	0.0138	0.066	0.077	0.054	0.556	0.200			40 x 13	C	
	83X PR9-1 A	0.054	0.003	0.0007	0.0004	0.0001	0.004	0.015	0.006	0.096	0.033	these are not CRMs		40 x 13	C	
	83X PR9-2 A	0.015	0.003	0.0002	0.0004	0.0001	0.002	0.007	0.002	0.046	0.015			40 x 13	C	
8.4		Battery Alloys (Pb/Sn/Ca)											Size (mm)		Form	
		Sn	Sb	Bi	Cu	As	Ag	Zn	Cd	Al	Ca	Ni	Te	Ø x H		
CRM	84X BA1 K	0.888	0.0009	0.0146	(0.0013)	0.0005	0.0098	0.0068	0.0014	0.0336	0.120	(0.0001)	(0.0003)	40 x 15	C	
CRM	84X BA2 D	0.544	(0.003)	0.0230	(0.002)	0.0004	0.0044	0.0273	0.0040	0.0183	0.0756	(0.0004)	(0.0003)	40 x 15	C	
CRM	84X BA3 D **	0.32	0.005	0.035	0.006		0.006	0.003	0.005	0.004	0.022			40 x 15	C	
CRM	84X BA4 C	0.0480	0.0078	0.0260	0.0064	(0.003)	0.0020	0.0065	0.0092	0.0015	0.0014	(0.0004)	0.0205	40 x 15	C	
CRM	84X BA7 B	0.594	0.0022	0.0140	0.0020	(0.0004)	0.0015	0.0024	0.0004	0.0085	0.0391	(0.0003)	(0.0002)	40 x 15	C	
CRM	84X BA8 D	0.325	0.0043	0.0147	0.0008	0.0005	0.0035	0.0018	0.0004	0.0359	0.136	0.0002	(0.0002)	40 x 15	C	
CRM	84X BA9 C	2.94	(0.005)	0.0145	0.0021	(0.0005)	0.0023	0.0017	0.0011	0.0207	0.118	(0.0001)	(0.0003)	40 x 15	C	
CRM	84X BA11 B	1.289	(0.005)	0.0159	0.0017	0.0006	0.0025	0.0006	0.0006	0.0207	0.0546			40 x 15	C	
CRM	84X BA12 B	1.483	0.0007	0.0181	(0.001)	0.0005	0.0051	0.0025	0.0009	0.0148	0.0665			40 x 15	C	
CRM	84X BA13 B	1.685	0.0018	0.0282	0.0010	0.0004	0.0076	0.0079	0.0014	0.0363	0.0725			40 x 15	C	
CRM	84X BA14 A	0.959	(0.002)	0.0162	0.0016	(0.0004)	0.0103	0.0057	0.0015	0.0188	0.076	(0.0002)	(0.0002)	40 x 15	C	
CRM	84X BA15 A	0.941	0.0047	0.0140	0.0011	0.0005	0.0095	0.0062	0.0013	0.0161	0.0865			38 x 15	C	
CRM	84X BA20 B	0.370	0.0038	0.0144			0.0295	0.0435	0.0051	0.065	0.368			38 x 15	C	
CRM	84X BA21 B	0.162	0.0028	0.0173			0.0102	0.0155	0.0007	0.0125	0.553			40 x 15	C	
CRM	84X BA22 B	0.128	0.0022	0.0138			0.0044	0.0053	0.0018	0.074	0.799			38 x 15	C	
CRM	84X BA23 B	0.237	0.0061	0.0134			0.0024	0.0026	0.00012	0.0569	1.052			38 x 15	C	
8.5		Various Lead Alloys											Size (mm)		Form	
		Sn	Sb	Bi	Cu	As	Ag	Zn	Cd	Ni	Te	Se	S	Co	Ø x H	
CRM	85X PSn2 C	2.06	0.0239	0.0154	0.0128	0.0048	0.0048	(0.0004)	0.0007	0.0003	0.0045	0.0042	(0.0009)	0.0004	40 x 15	C
CRM	85X PSb3 J	0.161	2.26	0.0214	0.0308	0.293	0.0042	(0.0008)	0.0028	0.0016	0.0055	0.0317	(0.0008)		40 x 15	C
CRM	85X PSb5 E	0.285	4.51	0.0134	0.0593	0.149	0.0018	0.00057	0.0016	0.0015	0.0029	0.014	0.018		38 x 15	C
CRM	85X PSb5 F **	0.22	4.80	0.025	0.035	0.22	0.004	(0.0002)	0.0010	0.0015	0.0015	0.008	0.007		40 x 15	C
CRM	85X PSb8 B	0.041	8.04	0.0178	0.0169	0.0352	0.0049	<0.001	0.0010	0.0016	0.0043	0.0022	0.005		40 x 15	C
CRM	85X PSb10 B	0.090	10.00	0.0410	0.169	0.127	0.0020	0.015	0.0018	0.0027	0.0037	0.0020	<0.001		40 x 15	C
CRM	85X PSb12 B	0.270	11.50	0.0310	0.330	0.071	0.0019	0.071	0.00053	0.0033	0.0056	0.0004	<0.001		40 x 15	C
** provisional values																

8. Lead Base

Updated: 13th December 2016

Blocks / Discs

8.5 Various Lead Alloys		Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Ni	Te	Se	Au	Tl	S	Hg	Co	Mn	Size (mm) Ø x H	Form
CRM	85X ANTH F	1.25	6.25	0.0196	0.0072	0.183	0.0070	(0.0004)	0.0005	0.0039		0.0045	0.0067	0.014			0.0026		0.0006		40 x 15	C
CRM	85X CADH B	0.096	1.85	0.0292	0.0260	0.201	0.0076	0.0005	0.044	2.09		0.0045	0.0121	0.0010			<0.0005			<0.0005	40 x 15	C
CRM	85X CADL A	0.010	1.54	0.0169	0.0093	0.0065	0.0076	(0.0006)	(0.0018)	1.69		(0.0005)	0.0030	(0.0011)							40 x 15	C
CRM	85X HRH H	0.851	1.107	0.0996	0.072	0.721	0.236			0.0066		0.0012	0.0024	0.0375			(0.0022)				40 x 15	C
CRM	85X SASH A	0.0130	1.54	0.0602	0.0245	0.683	0.0016			0.00024		0.0005	0.0006				(0.0005)				40 x 15	C
CRM	85X S744 A **	0.25	1.55	0.02	0.035	0.12	0.005						0.002	0.025			0.003	** provisional values			40 x 15	C
CRM	85X A16 A	0.0356	1.57	0.0165	0.0006	0.0503	0.0297	(0.0001)	0.0001	0.0001		0.0006		0.0218			(0.0003)				38 x 15	C
CRM	85X M2 A	0.071	1.847	0.0141	0.0281	0.259	0.0016	(0.0002)	(0.0001)	0.0003		0.0005		0.0247			(0.0008)				38 x 15	C
CRM	85X MS2X A	0.392	1.367	0.0188	0.0277	0.176	0.0043	(0.0001)	0.0003	0.0002		0.0004		0.0334			(0.0002)				38 x 15	C
CRM	85X N35 A	0.044	3.42	0.0130	0.0246	0.201	0.0011	(0.0001)	0.0001	0.00013		0.0006		0.0004			0.007				38 x 15	C
CRM	85X SB28 A	0.051	2.87	0.0140	0.0035	0.162	0.0025	(0.0002)	(0.0001)	(0.0001)		0.0012		0.0223			0.0010				38 x 15	C
CRM	85X SM31 A	0.0274	2.98	0.0114	0.0084	0.0581	0.0009	(0.0001)	0.0002	(0.0001)		0.0006		0.0183			0.0003				38 x 15	C
CRM	85X YUM A	0.0046	2.47	0.0137	0.0234	0.306	0.0018		(0.0002)	0.0002		0.0007	0.0005	0.0008			0.0062				40 x 15	C
CRM	85X 2.5LA A	0.068	2.48	0.0142	0.0372	0.334	0.0017		0.0002	(0.0002)		0.0005	0.0004	0.0006			(0.0006)				40 x 15	C
CRM	85X SSBC A	9.70	2.14	0.413		0.075	0.456			0.455	0.209		0.0037	0.0029	0.0079	0.0196	(0.0008)				40 x 15	C
CRM	85X SSCH A	2.64	5.52	0.0441	0.177	0.208	0.0134	(0.002)	0.0007	0.0040		0.010	0.0070	(0.015)			0.0035				40 x 15	C
CRM	85X 0494Pb1 A	0.051	0.95	0.0017	0.012	0.049								0.004							40 x 15	C
CRM	85X 9494Pb2 C **	0.13	1.95	0.04	0.028	0.10	0.032						0.004	0.027			0.005	** provisional values			40 x 15	C
CRM	85X 0494Pb3 D **	0.23	3.10	0.13	0.092	0.25	0.02						0.017	0.046			0.018	** provisional values			40 x 15	C
CRM	85X 0616Pb1 C	0.0045	1.59	0.0333	0.0143	0.060	0.0071		0.0004	0.0016		0.0011	0.0065	0.0087				0.0010			40 x 15	C
8.6 Lead Babbitts		Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Ni	Pd	Te	Size (mm) Ø x H		Form					
CRM	86X PSS1 B	4.29	11.54	0.195	0.0249	0.554	0.0049	0.0018	0.0030	0.0057	0.0074	0.0100	0.0023		40 x 15		C					
CRM	86X PSS2 B	7.00	8.04	0.0646	0.127	1.43	0.0179	(0.001)	0.031	0.066	0.0059	0.0165	0.0049		40 x 15		C					
CRM	86X PSS3 B	9.39	14.13	0.0273	0.489	0.409	0.0140	0.0025	0.0030	0.0170	0.0111	0.0009		0.0050	40 x 15		C					
CRM	86X PSS4 B	10.64	15.93	0.102	0.355	0.241	0.0264	0.0035	0.012	0.0539	0.0174	0.0010		0.0146	40 x 15		C					

9. Lead/Tin Solders

Updated: 15th December 2016

Blocks / Discs

9.1		Tin / Lead Solders																Size (mm)	Form
		Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Ni	Al	Te	Au	Se	Hg	Ø x H	
CRM	91X S10PR1 C	9.10	0.0278	0.0277	0.0097	0.0045	0.0078	(0.0016)	<0.001	0.0029		0.0006						40 x 15	C
CRM	91X S10P D	10.07	(0.002)	(0.006)	(0.001)	(0.001)	(0.001)	<0.001	<0.0001	<0.0001	<0.001	<0.001	<0.001					40 x 15	C
CRM	91X S30PR2 C	30.17	0.619	0.158	0.095	0.028	0.060	0.009	0.016	0.0060		0.0077	<0.0005		0.0017			40 x 15	C
CRM	91X S30PR3 C	30.88	0.269	0.294	0.102	0.0126	0.024	0.0016	(0.003)	0.0115	0.0085	0.0269			0.0063			40 x 15	C
CRM	91X S40PR2 D	40.68	0.596	0.154	0.085	0.010	0.086	0.0096	0.0275	0.0046		0.0050						40 x 15	C
CRM	91X S40P D	40.00	(0.002)	(0.005)	(0.001)	(0.007)	(0.001)	(0.001)	<0.0001	<0.0001	(0.002)	<0.001	<0.0005					40 x 15	C
CRM	91X S50PR4 B	53.06	0.132	0.114	1.184	0.0364	0.0704	0.0025	0.032	0.0123	0.0502	0.0171	(0.0006)	...	0.0355	0.003		40 x 15	C
CRM	91X S50P E	50.05	(0.002)	(0.005)	(0.002)	(0.006)	(0.001)	(0.001)	<0.0001	<0.0001	(0.003)	(0.001)	<0.0005					40 x 15	C
CRM	91X S62AG2 A	61.68	0.347	0.168	0.069	0.022	2.03	0.0065	0.0011	0.0016		(0.0016)	(0.0011)		0.0020			40 x 15	C
CRM	91X S63PR0 B	60.03	0.0182	0.0084	0.0202	0.0094	0.0097	(0.002)	<0.0005	0.0097	0.0048	0.0018		0.0034	0.0148		0.004	40 x 15	C
CRM	91X S63PR1 G	61.45	0.052	0.0588	0.214	0.0064	0.0061	(0.002)	(0.002)	0.0045	0.0308	0.0060		0.0047	0.0348		(0.015)	40 x 15	C
CRM	91X S63PR2 K	61.84	0.531	0.175	0.0841	0.0094	0.0528	0.0053	0.0032	0.0089	0.0157	0.0027	0.0005	0.0036	0.082			40 x 15	C
CRM	91X S63PR3 G	64.01	0.243	0.254	0.101	0.0264	0.0193	0.0078	0.0061	0.0009	0.0097	0.0085		0.0068	0.169		(0.038)	40 x 15	C
CRM	91X S63Bi1 A	61.9	0.470	0.597	0.105	<0.002	0.0592	0.0204	(0.002)	0.0095	0.0067	0.0131	(0.0015)	0.0012	0.074			40 x 15	C
CRM	91X S63P J	62.96	0.011	0.0056	0.0156	(0.001)	0.0170	0.0015	(0.0003)	(0.0001)	0.0064	0.0003	(0.0003)	(0.0002)	(0.0005)			40 x 15	C
9.3		Tin / Lead / Antimony Solders																Size (mm)	Form
		Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Ni	Te					Ø x H	
CRM	93X S30APR1 C	28.58	2.54	0.059	0.192	0.010	0.0144	(0.012)	(0.0004)	0.0014	0.0094	0.0010	0.0024					40 x 15	C
CRM	93X S30APR2 C	30.68	1.80	0.168	0.062	0.0178	0.049	0.0026	0.028	0.0061	0.0199	0.042	0.0102					40 x 15	C
CRM	93X S30APR3 C	33.0	0.96	0.28	0.008	0.018	0.021	0.0026	0.005	0.009		0.010						40 x 15	C

9. Other Solders

Note: All these listed below are RMs not CRMs

Updated: 15th December 2016

Blocks / Discs

9.5 Fusible Alloys	Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Al	Pb	Co	Ni	Au	Nominal Melting Temperature °C	Size (mm) Ø x H	Form
95X 117 A	7.99	0.012	45.3	0.011		0.0047		0.0053	4.99	18.6		23.1				47	40 x 15	C
95X 136 A	12.05	0.023	48.7	0.0029		0.0057		0.030	0.0091	21.5		17.8				58	40 x 15	C
95X 158 A	13.5	0.057	50.2	0.048		0.002		0.044	9.6	0.006		27.0				70	40 x 15	C
95X 174 A	16.79	0.082	57.12	0.0029		0.0076		0.036	0.0089	26.2		0.081				79	40 x 15	C
95X 255 A	0.24	0.32	55.7	0.045		0.0019		0.035	0.0065	0.010		43.7				124	40 x 15	C
95X BIS40P1 B	42.3	0.092	57.4	0.0670	0.0101	0.035	(0.001)		0.0050	0.0164		0.043				138	40 x 15	C
95X BIS40P2 A	44.7	0.005	55.3	0.003	0.002	0.005	0.001	0.002	0.0008	0.005	0.002	0.020	0.001	0.002	0.0006		40 x 15	C
95X BIS50P1 A	50.0		49.8				0.051	0.006	0.022					0.025			40 x 15	C
95X BIS50P2 A	50.3		49.6		0.002	0.090	0.007				0.005				0.015		40 x 15	C
95X BIS50P3 A	48.6		49.8		0.073	1.50	0.003	0.002	0.015						0.0025		40 x 15	C
95X BIS70P1 A	69.1		29.6		0.025	1.10	0.010			0.040	<0.001			0.029	0.0004		40 x 15	C
95X BIS70P2 A	65.0		32.8			2.01		0.001		0.049	<0.001						40 x 15	C
95X CDS50P1 A	50.1	0.113	0.13	0.26	0.027	0.030	(0.0022)	0.007	18.1	0.092	<0.002	31.0				145	40 x 15	C
95X PBS40P1 A	42.6	0.016	13.8	0.025	0.005	0.011	(0.0006)	0.0010	0.0043	0.005	(0.0006)	(43.6)					40 x 15	C
95X SC34 A	34.05								(65.99)								40 x 15	C
95X SC36 A	36.09								(63.98)								40 x 15	C

10. Titanium Base

Updated: 15th December 2016

Blocks / Discs

10.1	Various Ti Alloys	Al	Sn	V	Mo	Nb	Zr	Cr	Fe	Ni	Cu	Si	Y	C	S	N	O	H	Size (mm) Ø x H	Form
CRM	101X Ti2 A	6.02	2.05		2.08		3.97	0.0054	0.053	0.0073	(0.003)	0.110	0.0002	0.016		0.0053	0.143	0.0076	please ask	HIP
Note: This product is nearly sold out; only a few pieces remaining																				

11. Cobalt Base

Updated: 15th December 2016

Blocks / Discs

11.1	Co/Cr/W (Alloy WI 52 Type)	C	Si	S	P	Mn	Ni	Cr	W	Fe	Mo	Nb	Ta	Al	Cu	N	Pb	Sn	Size (mm) Ø x H	Form
	111X 12671 J		0.51			0.61	0.88	20.5	11.8	1.45		1.95							40 x 15	C
11.2	Co/Cr/Mo (Stellite 8 / BS 3531 Type)	C	Si	S	P	Mn	Ni	Cr	W	Fe	Mo	Al	Nb	Cu	Ta	B	N		Size (mm) Ø x H	Form
CRM	112X 14943 H**	0.20	0.20	0.02	0.005	1.0	0.15	31	0.05	0.75	8.0	0.1	0.09	0.21	0.01	0.005	0.03	** provisional values	40 x 15	CC
11.9	Various Cobalt Alloys	C	Si	S	P	Mn	Ni	Cr	W	Fe	Mo	Cu	Nb	Al	B	N			Size (mm) Ø x H	Form
CRM	119 X COB1 H	0.0518	0.492	0.0099	0.0195	0.513	22.11	24.62	11.99	15.14	0.416	0.0607	0.398	0.056		0.094			40 x 15	CC
CRM	119X ST3 L	2.36	0.807	0.0260		0.887	2.15	29.9	12.6	3.42	0.163	0.032			0.127	0.053			40 x 15	CC

13. Noble Metals

Note: All these listed below are RMs not CRMs

Updated: 13th December 2016

Discs

13.1	Silver with Impurities	All Elements ppm																			Size (mm)	Form		
		Cu	Pb	Bi	Zn	As	Sb	Se	Au	Sn	Pt	Pd	Fe	Te	Mn	Cd	Ni	Si	Ga	Al	Ø x H			
	131X AGP1 B	815	420	523	502	145	485	299	521	505	505	332	57	435	404	377	276				25 x 3	R		
	131X AGP2 B	193	75	96	109	29	107	65	114	95	112	105	(20)	90	49	56	57				25 x 3	R		
	131X AGP3 B	66	12	12	34	6	21	16	26	22	23	16	(11)	18	3	6	12				25 x 3	R		
	131X AGP4 B	41	5	7	20	3	12	6	9	6	7	7	(23)	5	3	2	6				25 x 3	R		
		R = Samples prepared from rolled strip																						
	131X PAg1 A	75	40	40	50	12	50	35	120	40	35	180	5	120	35	35	25	30	60	8	34 x 12	concast		
	131X PAg2 A	400	12	12	40	8	12	10	20	10	10	180	7	15	10	5	9	4	15	2	34 x 12	concast		
		All Elements ppm																			Size (mm)	Form		
		Bi	Se	Fe	Cu	Cr	Si	Al															Ø x H	
	131X AgSe1 A	304	162	23																		40 x 10	C	
	131X AgSe2 A	790	465	22	1333	37	39	43														40 x 10	C	
		C = Samples cast																						
13.2	Silver Copper Alloys	All Elements %																				Size (mm)	Form	
		Ag	Cu	Zn																		Ø x H		
	132X AGB75 C	75.11	24.53																			40 x 10	C	
	132X AGB85 C	84.87	15.09																			40 x 10	C	
	132X AGB87 B	87.13	12.67																			40 x 10	C	
	132X AGB90 B	89.73	10.24																			40 x 10	C	
	132X AGB93 B	92.70	7.27																			40 x 10	C	
	132X AGB100 C	99.94	0.0090																			40 x 10	C	
		C = Samples cast																						
	132X 925Zn1 B	92.70	6.09	1.39																		Unmounted	25 x 3**	R
	132X 925Zn3 B	92.64	4.53	2.88																		Unmounted	25 x 3**	R
		**Also available mounted in 30mm dia. Bakelite holder																			R = Samples prepared from rolled strip			
13.3	Silver Alloys	These Elements in %								These Elements in ppm												Size (mm)	Form	
		Au	Cu	Pb	Zn	Sn	Bi	Sb	Fe	Al	As	Cd	Co	Mn	Ni	Pd	Pt	Se	Te	Ge	In	Ø x H		
	133X AGA1 A	1.48	19.95	0.207	0.211	0.291	0.194	0.050	0.039	96	255	165	406	61	118	54	67	169	271	107	37	Unmounted	25 x 3	R
	133X AGA2 A	0.507	10.00	1.02	0.502	0.520	0.113	0.192	0.027	19	144	113	163	115	264	76	114	78	98	47	65	Unmounted	25 x 3	R
	133X AGA3 A	0.258	4.91	1.89	0.816	0.921	0.048	0.459	(0.015)	(20)	80	42	50	98	450	156	256	44	54	45	134	Unmounted	25 x 3	R
	133X AGQ1 C	0.251	2.532	0.245																		Unmounted	25 x 3	R
	133X AGQ2 C	0.978	5.808	0.469																		Unmounted	25 x 3	R
	133X AGQ3 C	1.975	9.612	0.921																		Unmounted	25 x 3	R
		R = Samples prepared from rolled strip																						

16. Setting Up Samples

Updated: 13th December 2016

Blocks / Discs

All of these samples have been prepared to meet the daily setting up requirements of laboratories using Direct Reading Spectrometers.

Analytical Data are supplied with each sample but are not certified as accurate as these are not intended to be used as Primary Reference Materials, and should not be used for calibration..

16.4.2 Aluminium																				Size (mm)	Form
	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr	Co	Be	Sb	Ca	Sr	Zr	Ag			
164X ALSUS7	4	0.15	0.9	0.55	0.06	1.1	0.12	0.11	0.01	0.3	0.01	0.2	0.1	0.12	<0.001	0.003	0.18		50 x 25	C	
164X ALSUS8	0.75	0.9	9.5	0.25	0.45	0.12	0.25	0.001	0.13	0.02	0.06	0.025	0.015	0.03	<0.001	0.07	0.025	0.09	50 x 25	C	
16.5.1 Pure Copper																				Size (mm)	Form
	Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	Cr	Co	Ag	Mg	C	Se	O	N
165X CUSUS1	0.7	11	0.4	8	1	0.05	0.05	0.05	0.01	0.05	0.1	1	11	0.01	0.1	0.05	0.01	(0.5)	0.05	(370)	(6)
16.5.2 Copper																				Size (mm)	Form
	Sn	Pb	Zn	Fe	Ni	Al	Si	As	Mn	Bi	Sb	P	S	Cr	Co	Mg	Se	Cu			
165X MNB5 SUS	1.6	0.20	38	0.55	1.1	3.2	0.40		0.20									55	40 x 17	CC	
165X PB10 SUS	11.0	0.04	0.05	0.002	0.06	0.001	0.001	0.02	<0.001	0.02	0.15	0.002	0.03	0.001	0.01		0.01	89	42 x 18	CC	
165X ALB1 SUS	0.03	0.20	0.06	2.8	5.3	9.0	0.10	0.005	0.08	0.015		0.015		0.01		0.04		82	40 x 18	CC	
16.6 Magnesium																				Size (mm)	Form
	Al	Zn	Mn	Cu	Si	Fe	Ni	Ti	Sn	Pb	Ag	Be	Cd								
166X MGSUS3	0.4	0.09	0.8	0.07	0.01	<0.005	0.02		0.005	0.04	0.02	0.0005	0.005					50 x 15	C		
166X MGSUS4	9	5	0.12	0.2	0.015	0.02	0.003	0.005	0.05	0.02	1.6	0.003	0.04					50 x 15	C		

16. Setting Up Samples

Updated: 13th December 2016

Blocks / Discs

All of these samples have been prepared to meet the daily setting up requirements of laboratories using Direct Reading Spectrometers.

Analytical Data are supplied with each sample but are not certified as accurate as these are not intended to be used as Primary Reference Materials, and should not be used for calibration.

16.8	Lead	Sn	Sb	Bi	Cu	As	Ag	Fe	Zn	Cd	In	Ni	Te	Se	Tl	Au	S	Hg	Size (mm) Ø x H	Form			
	168X PBSUS1	1.3	6.2	0.04	0.03	0.37	0.01	0.002	0.001	0.015	0.01	0.003	0.01	0.01	0.001	0.001	0.002		45 x 30	C			
	168X PBSUS5	0.9	0.35	0.35	0.06	0.35	0.2	<0.001		0.09	0.08	0.001	0.003		0.002	0.0005	0.0005	0.02	50 x 25	C			
	168X PBSUS6	0.15	0.12	0.22	0.10	0.025	0.04	<0.001	0.002	0.015	0.01	0.003	0.0005	0.003	0.03	0.001	0.0005		45 x 35	C			
16.8.1	Lead for fire assay	ppm Pt	ppm Pd	ppm Au	ppm Rh	ppm Ru	ppm Ir	ppm Ag	ppm Fe	ppm Bi	ppm Cu	ppm Ni	ppm Te	ppm As	ppm Sb	ppm Tl	ppm S	Size (mm) Ø x H	Form				
	168X PBSUS PM1	55	20	35	12	0.1	2	40	1	100	5	3	1	2	1	10	2	48 x 28	C				
16.9	Zinc	Pb	Mg	Al	Cd	Fe	Sn	Cu	Ni	Mn	Bi	Sb	Ti	Tl	In	Ag	Cr	Si	Size (mm) Ø x H	Form			
	169X ZN SUS1	0.6	0.002	0.35	0.3	0.05	0.3	0.35	0.06	0.001	0.005	0.2	0.001	0.06	0.25	0.04	0.001	0.003	50 x 20	C			
16.11	Tin	As	Bi	Sb	Pb	Cu	Fe	Cd	Zn	Ni	Al	Ag	Co	In	Au	Se	Te	Tl	Size (mm) Ø x H	Form			
	1611X SNSUS6	0.3	0.08	0.15	1.0	0.4	0.03	0.01	0.005	0.03		0.1	0.02	0.005	0.001	0.003	0.001	0.005	50 x 20	C			
	1611X SNSUS7	2.1	2.3	9	0.35	11	(0.05)	0.03	0.005	0.05	<0.001	0.3	0.005	0.03	0.005	0.005	0.003	0.03	50 x 20	C			
16.12	Cobalt	C	Si	S	P	Mn	Ni	Cr	W	Fe	Mo	Al	Nb	Cu	B	Sn	Pb	Ta	Ti	V	Co	Size (mm) Ø x H	Form
	1612X COSUS1	1.0	1.6	0.07	0.05	1.7	17	26	8.0	3.5	6.5	1.5	2.2	0.15	0.01	0.08	0.01	0.02	0.20	0.25	~30	43 x 20	C

18. Gases in Metals

Updated: 13th December 2016

Powders

18.1 Gases in Tool Steels		C	S	N	O	Approximate Matrix Composition	Size grams
CRM	18X D7 A	2.32	0.0111	0.0124	0.072	12% Cr, 4% V, 1% Mo	100
This material is supplied in powder form - particle size approximately <200u							

Most of the MBH range of discs can also be supplied in chippings form. See the sections earlier for general composition information.
Chippings are made to order from the currently available disc material as detailed in this catalogue.

Please note that the certification for chippings may differ slightly from the disc certification. This is caused by a review of the relevant analytical techniques used in certifying the material applicable to the chippings form of the material

Note: chippings are made to order and are non-returnable

Please enquire to confirm availability, bottle quantity and price.

As material is made to order it is not possible for us to give a general listing of available material. Please contact us for all chippings enquiries to confirm our ability to supply and to confirm the quantity of material per bottle and unit price.

Definitions

The materials in this catalogue have been categorised as Certified Reference Materials, Reference Materials or Setting Up / Control Samples. The following definitions used in ISO Guide 30: 1992 apply to the first two categories;

Certified Reference Material (CRM)	"A Reference Material, accompanied by a certificate, one or more of whose property values are certified by a procedure which establishes its traceability to an accurate realisation of the unit in which the property values are expressed and for which each certified values ia accompanied by an uncertainty at a stated level of confidence." Such materials are indicated with CRM in the left hand margin against the catalogue number.
Reference Material (RM)	"A material or substance one or more of whose property values are sufficiently homogeneous and well established to be used for the calibration of an apparatus, the assessment of a measured method, or for assigning values to materials."
Setting Up Samples (SUS)	Samples which have been prepared to meet the routine setting up requirements of laboratories using direct reading spectrometers. Whilst analytical data are supplied with each sample they are not certified and are only intended to be used as Setting Up Samples.

Note: Products that are not marked in this catalogue as 'CRM' may be presumed to be Reference Materials as defined above.

Use of Reference Materials

Whilst modern instrumental methods of analysis are capable of high accuracy and precision, they are comparative techniques. Reference materials must be selected and used correctly for optimum performance to be achieved, and the following points should be considered.

The instrument manufacturer's recommendations and advice should be followed.

Users should be aware of the possible effects of structure, sample preparation and physico-chemical interferences when using reference materials.

Validity of Information

IMPORTANT - Please Note

The majority of the analytical data in this catalogue indicates actual values for the batch currently available. However some materials may be remade during the lifetime of this catalogue and the values achieved for the replacements may differ from those stated.

We recommend that customers verify the availability of any material where it is important that the material supplied has the element concentration values listed.

All concentration values in this catalogue are given in % (w/w) unless otherwise stated.

All stated dimensions and weights are approximate. Finished sizes/weights may differ from those stated.

Whilst every effort is taken to present accurate data, errors and omissions excepted, it remains the responsibility of the purchaser to verify data prior to purchase.

For materials not classified as 'CRM' it is the responsibility of the purchaser to ensure the end-user is willing to use a material of lower status.

General Conditions

All materials are subject to our general Conditions of Sale . The text is reproduced here for your convenience

- 1 All items listed in this catalogue or otherwise offered for sale are subject to availability and any delivery dates that may be quoted are conditional on supplies. We are unable to accept liability for delay and if any item becomes unavailable during the life of a catalogue we will advise on suitable alternatives where appropriate.
- 2 Unless credit facilities have been agreed with us (in which case payment is due on a net monthly basis), payment for items is due either against a Pro Forma invoice at the time of ordering or by Confirmed Irrevocable Letter of Credit through a British Clearing Bank payable on presentation of invoice and despatch documents.
- 3 We draw the attention of all customers to the notes in our catalogue relating to definitions, analyses and calibration procedures.
- 4 To the extent that the law may permit, the following condition stands in substitution for all conditions and warranties as to merchantability and fitness for purpose as implied by statute, common law or otherwise.
 - a. It is the responsibility of the customer to decide on the suitability and fitness for purpose of all items purchased
 - b. Any items claimed to be defective must be returned to us (within 3 months of delivery) for examination and analysis. No claims can be entertained if this is not done.
 - c. We may, at our discretion, replace any item shown to be defective or refund the price paid. Our liability in respect of any such item will not in any circumstances exceed the amount paid for the item in question and no liability is accepted for consequential losses however arising.
- 5 These conditions shall apply to all contracts entered into by us to the exclusion of all other conditions and notwithstanding any items that may appear on any printed stationery of any customer. No variation of these conditions shall be effective unless confirmed by us in writing on or prior to formal acceptance by us of any order.
- 6 Until such a time as we have received full payment, items supplied to customers shall remain our property notwithstanding delivery to the customer and we shall be entitled to enter upon the customer's premises to recover the property if the customer shall go into liquidation, or if a receiver is appointed .
- 7 This contract shall be governed by English Law and any disputes shall be referred to the exclusive jurisdiction of the English Courts.

Ordering Procedure

Purchase Orders are accepted by e-mail, fax or post. Please ensure any subsequent confirmation of an order is appropriately marked so as to avoid duplication.

Send your order to:	MBH Analytical Ltd	Tel: ++44 (0)208 441 2024
	Holland House	
	Queens Road	Fax: ++44 (0)208 449 0810
	Barnet, Herts., EN5 4DJ	
	United Kingdom	Email: sales@mbh.co.uk

Orders placed shall include; Catalogue number, quantity required, description, price, agreed discount and confirmation of invoicing and delivery address.
Unless specifically instructed all orders will be despatched by our chosen carrier, with due regard to speed, security and cost.

All orders will be acknowledged by either e-mail or post. Please check the acknowledgement upon receipt to ensure we have correctly understood your requirement.

Prices

All prices are stated Packed Ex Works (Barnet) and include usual commercial packing, but exclude any shipping costs, special packing requirements requested by the customer (and subject to prior agreement) or extra documentation (please enquire)

Prices are subject to change without notice. We recommend that customers verify the price of items prior to placing their order.

Although we endeavour to give advance notice of any price changes, the prices ruling at the time of placing your order will apply unless otherwise agreed in writing. Should prices be requested in US\$ or Euro €, we will be pleased to submit our quotation in either of these currencies. Payment should be made to the corresponding currency account at our bank as detailed below.

We are pleased to provide written quotations upon request indicating current availability and estimated despatch costs.

Value Added Tax (VAT)

All orders delivered to a UK address are subject to VAT at the rate applicable at the time of despatch. European Community countries are also subject to UK VAT unless we are advised of your VAT number at the time of placing your purchase order. Orders originating from outside the EU but for delivery to an address in the EU (such as a freight agent) for onward despatch will also be liable for VAT until we receive proof of export from the EU within 90 days of our initial despatch from MBH. The VAT charged will then be refunded upon receipt of the proof of export (bank fees will apply) but this must be presented to MBH within the 90 day period. After 90 days you will need to apply direct to the tax authorities for any refund of VAT.

Insurance & Freight

Insurance and freight costs are charged extra at cost. We will be pleased to provide our quotation detailing these costs upon request. All materials are packed in strong cardboard outer cartons suitable for despatch by air parcel post, courier or air freight as necessary. Special packing instructions and freight requirements should be discussed and agreed with us prior to placing your order.

Payment Terms

Payment should be in the currency stated on the invoice and made to the corresponding currency account, free of all local/senders bank charges.

MBH will only accept our own bank's charges.

Payments must be sent for the full amount **after** deduction of all transmission fees (including senders fee & intermediary bank fees).

Payment may be made by any of the following methods.

- Visa Purchasing Card or major debit/credit/charge card (Visa, Mastercard or American Express). Payments over £500.00 are subject to a 2.5% surcharge. Please note we can only invoice/collect payment in Sterling for card transactions. The currency amount billed to your card will reflect your card company's currency conversion rate from Sterling and fee.

The card payment will be taken (in Sterling) at the time of confirming your order and a receipt forwarded with the invoice.

continues.....

Conditions of Sale - Prices, VAT and payment terms (2).

December 2016

Payment Terms

.... continued.

- Sterling (or stated currency) prepayment with your purchase order against our Proforma invoice by bankers draft or automated bank transfer.
- Irrevocable Letter of Credit through a London bank, payable at sight upon presentation of documents (minimum order value stg£4,000.00 applies).
- Established customers may apply to receive strictly Net Monthly Account terms, subject to satisfactory bank and trade references.

Our bank details for payments are:

Name of Banker: **National Westminster Bank plc. (Natwest Bank)**
Branch Address: **181 Darkes Lane
POTTERS BAR
Herts EN6 1XT
United Kingdom**

Account Name: **MBH Analytical Ltd**
Account No: **(£ Sterling) 13140922** (IBAN) GB10NWBK60174913140922
Please see the currency a/c details and IBAN references below for remittances in US Dollar or EURO.
Branch Sort Code: **60-17-49** BIC (Swift code): **NWBKGB2L**

For payments of invoices stated in **Euros** please remit to our Euro currency account stated below, and for invoices stated in **US Dollars** please use our US Dollar currency account stated below. Both accounts are held at the NATWEST bank detailed above.

Currency Account Numbers: **Euro 06848966** (IBAN) GB18NWBK60720506848966
(All other bank details remain as stated above.) **US Dollar 16500466** (IBAN) GB71NWBK60730116500466

Please ensure you send your payment to the correct currency account as currency losses may be incurred on your account when moving payment to the correct MBH a/c.

All payments should exclude any charges/fees from the payees bank or intermediary (or correspondent) bank.
Our bank must receive the full invoiced amount after deducting senders fees and before our own bank fees are applied.

Conditions of Sale

All materials sold are subject to our standard Conditions of Sale. These are printed on pages 44 & 45.

MBH Analytical Ltd.

Registered in England. Reg. No. 1875653. Registered Office; Holland House, Queens Road, Barnet, Herts., EN5 4DJ, United Kingdom.
VAT registration No. GB873 1047 32

MBH

Periodic Table of the Elements

Periodic Table of the Elements																		18
1 H Hydrogen 1.008																	2 He Helium 4.003	
3 Li Lithium 6.941	4 Be Beryllium 9.012											13 B Boron 10.811	14 C Carbon 12.011	15 N Nitrogen 14.007	16 O Oxygen 15.999	17 F Fluorine 18.998	18 Ne Neon 20.180	
11 Na Sodium 22.990	12 Mg Magnesium 24.305											13 Al Aluminum 26.982	14 Si Silicon 28.086	15 P Phosphorus 30.974	16 S Sulfur 32.066	17 Cl Chlorine 35.453	18 Ar Argon 39.948	
19 K Potassium 39.098	20 Ca Calcium 40.078	21 Sc Scandium 44.956	22 Ti Titanium 47.867	23 V Vanadium 50.942	24 Cr Chromium 51.996	25 Mn Manganese 54.938	26 Fe Iron 55.845	27 Co Cobalt 58.933	28 Ni Nickel 58.693	29 Cu Copper 63.546	30 Zn Zinc 65.38	31 Ga Gallium 69.723	32 Ge Germanium 72.631	33 As Arsenic 74.922	34 Se Selenium 78.971	35 Br Bromine 79.904	36 Kr Krypton 84.798	
37 Rb Rubidium 84.468	38 Sr Strontium 87.62	39 Y Yttrium 88.906	40 Zr Zirconium 91.224	41 Nb Niobium 92.906	42 Mo Molibdenum 95.95	43 Tc Technetium 98.907	44 Ru Ruthenium 101.07	45 Rh Rhodium 102.906	46 Pd Palladium 106.42	47 Ag Silver 107.868	48 Cd Cadmium 112.414	49 In Indium 114.818	50 Sn Tin 118.711	51 Sb Antimony 121.760	52 Te Tellurium 127.6	53 I Iodine 126.904	54 Xe Xenon 131.249	
55 Cs Cesium 132.905	56 Ba Barium 137.328	57-71 Lanthanides	72 Hf Hafnium 178.49	73 Ta Tantalum 180.948	74 W Tungsten 183.84	75 Re Rhenium 186.207	76 Os Osmium 190.23	77 Ir Iridium 192.217	78 Pt Platinum 195.085	79 Au Gold 196.967	80 Hg Mercury 200.592	81 Tl Thallium 204.383	82 Pb Lead 207.2	83 Bi Bismuth 208.980	84 Po Polonium [208.982]	85 At Astatine 209.987	86 Rn Radon 222.018	
87 Fr Francium 223.020	88 Ra Radium 226.025	89-103 Actinides	104 Rf Rutherfordium [261]	105 Db Dubnium [262]	106 Sg Seaborgium [266]	107 Bh Bohrium [264]	108 Hs Hassium [269]	109 Mt Meitnerium [268]	110 Ds Darmstadtium [269]	111 Rg Roentgenium [272]	112 Cn Copernicium [277]	113 Uut Ununtrium unknown	114 Fl Flerovium [289]	115 Uup Ununpentium unknown	116 Lv Livermorium [298]	117 Uus Ununseptium unknown	118 Uuo Ununoctium unknown	

57 La Lanthanum 138.905	58 Ce Cerium 140.116	59 Pr Praseodymium 140.908	60 Nd Neodymium 144.243	61 Pm Promethium 144.913	62 Sm Samarium 150.36	63 Eu Europium 151.964	64 Gd Gadolinium 157.25	65 Tb Terbium 158.925	66 Dy Dysprosium 162.500	67 Ho Holmium 164.930	68 Er Erbium 167.259	69 Tm Thulium 168.934	70 Yb Ytterbium 173.055	71 Lu Lutetium 174.967
89 Ac Actinium 227.028	90 Th Thorium 232.038	91 Pa Protactinium 231.036	92 U Uranium 238.029	93 Np Neptunium 237.048	94 Pu Plutonium 244.064	95 Am Americium 243.061	96 Cm Curium 247.070	97 Bk Berkelium 247.070	98 Cf Californium 251.080	99 Es Einsteinium [254]	100 Fm Fermium 257.095	101 Md Mendelevium 258.1	102 No Nobelium 259.101	103 Lr Lawrencium [262]

For Your Notes



The full range of
Reference Materials
and Standards for
Spectroscopic
Analysis Techniques
can be found within our two
main catalogues for
Solids / Powders
and
Liquids / Glassware



Please ask for copies or visit our website:
www.mbh.co.uk
where copies can be downloaded.

The MBH catalogues are periodically re-issued to include the latest information.
Please ensure you have the latest version to hand.

MBH[®]
ANALYTICAL LTD

HOLLAND HOUSE • QUEENS ROAD • BARNET • EN5 4DJ • ENGLAND • TEL: +44 (0)20 8441 2024 • FAX: +44 (0)20 8449 0810
E-mail: info@mbh.co.uk Website <http://www.mbh.co.uk>